

HANDBOOK OF OPTICAL MATERIALS

The CRC Press
Laser and Optical Science and Technology Series
Editor-in-Chief: Marvin J. Weber

A.V. Dotsenko, L.B. Glebov, and V.A. Tsekhomsky
Physics and Chemistry of Photochromic Glasses

Andrei M. Efimov
Optical Constants of Inorganic Glasses

Alexander A. Kaminskii
**Crystalline Lasers:
Physical Processes and Operating Schemes**

Valentina F. Kokorina
Glasses for Infrared Optics

Sergei V. Nemilov
**Thermodynamic and Kinetic Aspects
of the Vitreous State**

Piotr A. Rodnyi
Physical Processes in Inorganic Scintillators

Michael C. Roggemann and Byron M. Welsh
Imaging Through Turbulence

Shigeo Shionoya and William M. Yen
Phosphor Handbook

Hiroyuki Yokoyama and Kikuo Ujihara
**Spontaneous Emission and Laser Oscillation
in Microcavities**

Marvin J. Weber, Editor
Handbook of Laser Science and Technology
Volume I: Lasers and Masers
Volume II: Gas Lasers
Volume III: Optical Materials, Part 1
Volume IV: Optical Materials, Part 2
Volume V: Optical Materials, Part 3
Supplement I: Lasers
Supplement II: Optical Materials

Marvin J. Weber
Handbook of Laser Wavelengths
Handbook of Lasers

HANDBOOK OF OPTICAL MATERIALS

Marvin J. Weber, Ph.D.

Lawrence Berkeley National Laboratory

University of California

Berkeley, California



CRC PRESS

Boca Raton London New York Washington, D.C.

Library of Congress Cataloging-in-Publication Data

Weber, Marvin J., 1932-

Handbook of optical materials / Marvin J. Weber.

p. cm.

Includes bibliographical references and index.

ISBN 0-8493-3512-4 (alk. paper)

1. Optical materials—Handbooks, manuals, etc. 2. Lasers—Handbooks, manuals, etc. 3.

Electrooptics—Handbooks, manuals, etc. I. Title.

QC374 .W43 2002

621.36—dc21

2002073628

This book contains information obtained from authentic and highly regarded sources. Reprinted material is quoted with permission, and sources are indicated. A wide variety of references are listed. Reasonable efforts have been made to publish reliable data and information, but the author and the publisher cannot assume responsibility for the validity of all materials or for the consequences of their use.

Neither this book nor any part may be reproduced or transmitted in any form or by any means, electronic or mechanical, including photocopying, microfilming, and recording, or by any information storage or retrieval system, without prior permission in writing from the publisher.

The consent of CRC Press LLC does not extend to copying for general distribution, for promotion, for creating new works, or for resale. Specific permission must be obtained in writing from CRC Press LLC for such copying.

Direct all inquiries to CRC Press LLC, 2000 N.W. Corporate Blvd., Boca Raton, Florida 33431.

Trademark Notice: Product or corporate names may be trademarks or registered trademarks, and are used only for identification and explanation, without intent to infringe.

Visit the CRC Press Web site at www.crcpress.com

© 2003 by CRC Press LLC

No claim to original U.S. Government works

International Standard Book Number 0-8493-3512-4

Library of Congress Card Number 2002073628

Printed in the United States of America 1 2 3 4 5 6 7 8 9 0

Printed on acid-free paper

Preface

The *Handbook of Optical Materials* is a compilation of the physical properties of optical materials used in optical systems and lasers. It contains extensive data tabulations but with a minimum of narration, in a style similar to that of the *CRC Handbook of Chemistry and Physics*. References to original or secondary sources of the data are included throughout. The objective of the handbook is to provide a convenient, reliable source of information on the properties of optical materials.

Data in a handbook of optical materials can be presented by material (e.g., SiO₂, CaF₂, Ge), by property (e.g., refractive index, thermal expansion, hardness), by wavelength region (e.g., infrared, visible, ultraviolet), or by application (e.g., transmitting optics, laser hosts, polarizers). In this handbook data are grouped by material properties. Thereby one can compare different materials with respect to their properties and suitability for a particular application.

The volume is divided into sections devoted to various forms of condensed matter (crystals, glasses, polymers, metals), liquids, and gases. Within each section physical properties, linear and nonlinear optical properties, and many special properties such as electrooptic, magnetooptic, and elastooptic properties of the materials are tabulated. The optical solids included are mainly inorganic materials; optical liquids are mainly organic substances.

If by an optical material one means a material that exhibits some optical property such as transmission, absorption, reflection, refraction, scattering, etc., the number of materials to be considered becomes unmanageable. Thus the inclusion of materials in this volume is selective rather than exhaustive. In the case of commercial optical glasses, for example, properties of representative types of glasses are given but not properties for all compositional variations. Glasses with special properties or for special applications are included, however.

Bulk materials rather than thin films and multilayer structures are considered. Although optical glasses epitomizes an engineered material, other engineered optical materials such as nanomaterials, quantum wells, or photonic crystals are also not included (although one of the last is listed in Appendix II).

Although today optics can encompass x-ray and millimeterwave optics, coverage is limited to materials for the spectral range from the vacuum ultraviolet (~100 nm) to the infrared (up to 100 μm) portion of the electromagnetic spectrum.

Among optical materials and properties not treated explicitly are photorefractive materials, liquid crystals, optical fibers, phase-change optical recording materials, luminescent materials (phosphors, scintillators), optical damage, and materials preparation and fabrication.

Much of the numerical data in this handbook is from Volumes III, IV, V, and Supplement 2 of the *CRC Handbook of Laser Science and Technology*. These volumes should be consulted for more detailed descriptions of properties and their measurement (the contents of the volumes and the contributors are given in the following pages). In many instances the data in these volumes have been reformatted and combined with additions and recent developments. Several new sections have been added. For example, gases can play various roles as

an optical material—as transmitting media, active media for Faraday rotation, frequency conversion, filter, and phase conjugation. Physical and optical properties of a selected number of gases are therefore included in a final section.

The discovery of new optical materials has been accompanied by a somewhat bewildering and befuddling proliferation of abbreviations and acronyms. An appendix has been added to decode several hundred of these terms. Common or mineralogical names for optical materials are also included. Methods of preparing optical materials and thin films have developed their own terminology; many of these abbreviations are given in another appendix.

This volume has benefited from the efforts of many contributors to the *CRC Handbook of Laser Science and Technology* series. I am indebted to them for what in many cases have been very extensive compilations. In the course of preparing this volume I have also benefited from other input provided by Mark Davis, Alexander Marker, Lisa Moore, John Myers, and Charlene Smith; these are gratefully acknowledged. Finally, I appreciate the excellent help provided by Project Editors Samar Haddad and Joette Lynch, Production Supervisor Helena Redshaw, and the staff of the CRC Press in the process of preparing this handbook.

Marvin J. Weber
Danville, California

The Author

Marvin John Weber received his education at the University of California, Berkeley, and was awarded the A.B., M.A., and Ph.D. degrees in physics. After graduation, Dr. Weber continued as a postdoctoral Research Associate and then joined the Research Division of the Raytheon Company where he was a Principal Scientist working in the areas of spectroscopy and quantum electronics. As Manager of Solid State Lasers, his group developed many new laser materials including rare-earth-doped yttrium orthoaluminate. While at Raytheon, he also discovered luminescence in bismuth germanate, a scintillator crystal widely used for the detection of high energy particles and radiation.

During 1966 to 1967, Dr. Weber was a Visiting Research Associate with Professor Arthur Schawlow's group in the Department of Physics, Stanford University.

In 1973, Dr. Weber joined the Laser Program at the Lawrence Livermore National Laboratory. As Head of Basic Materials Research and Assistant Program Leader, he was responsible for the physics and characterization of optical materials for high-power laser systems used in inertial confinement fusion research. From 1983 to 1985, he accepted a transfer assignment with the Office of Basic Energy Sciences of the U.S. Department of Energy in Washington, DC, where he was involved with planning for advanced synchrotron radiation facilities and for atomistic computer simulations of materials. Dr. Weber returned to the Chemistry and Materials Science Department at LLNL in 1986 and served as Associate Division Leader for condensed matter research and as spokesperson for the University of California/National Laboratories research facilities at the Stanford Synchrotron Radiation Laboratory. He retired from LLNL in 1993 and is at present a staff scientist in the Department of Nuclear Medicine and Functional Imaging of the Life Sciences Division at the Lawrence Berkeley National Laboratory.

Dr. Weber is Editor-in-Chief of the multi-volume *CRC Handbook Series of Laser Science and Technology*. He has also served as Regional Editor for the *Journal of Non-Crystalline Solids*, as Associate Editor for the *Journal of Luminescence* and the *Journal of Optical Materials*, and as a member of the International Editorial Advisory Boards of the Russian journals *Fizika i Khimiya Stekla* (Glass Physics and Chemistry) and *Kvantovaya Elektronika* (Quantum Electronics).

Among several honors he has received are an Industrial Research IR-100 Award for research and development of fluorophosphate laser glass, the George W. Morey Award of the American Ceramics Society for his basic studies of fluorescence, stimulated emission, and the atomic structure of glass, and the International Conference on Luminescence Prize for his research on the dynamic processes affecting luminescence efficiency and the application of this knowledge to laser and scintillator materials.

Dr. Weber is a Fellow of the American Physical Society, the Optical Society of America, and the American Ceramics Society and a member of the Materials Research Society.

Contributors

Stanley S. Ballard, Ph.D.
University of Florida
Gainesville, Florida

Lee L. Blyler, Ph.D.
AT&T Bell Laboratories
Murray Hill, New Jersey

James S. Browder, Ph.D.
Jacksonville University
Jacksonville, Florida

Allan J. Bruce, Ph.D.
AT&T Bell Laboratories
Murray Hill, New Jersey

Hans Brusselbach, Ph.D.
Hughes Research Laboratory
Malibu, California

Bruce H. T. Chai, Ph.D.
Center for Research in
Electro-Optics and Lasers
University of Central Florida
Orlando, Florida

Lloyd Chase, Ph.D.
Lawrence Livermore National Laboratory
Livermore, California

Di Chen, Ph.D.
Honeywell Corporate Research Center
Hopkins, Minnesota

Lee M. Cook, Ph.D.
Galileo Electro-Optic Corp.
Sturbridge, Massachusetts

Gordon W. Day, Ph.D.
National Institute of Standards
and Technology
Boulder, Colorado

Merritt N. Deeter, Ph.D.
National Institute of Standards
and Technology
Boulder, Colorado

Larry G. DeShazer, Ph.D.
Spectra Technology, Inc.
Bellevue, Washington

Marilyn J. Dodge, Ph.D.
National Bureau of Standards
Washington, DC

Albert Feldman, Ph.D.
National Institute of Standards
and Technology
Washington, DC

James W. Fleming, Ph.D.
AT&T Bell Laboratories
Murray Hill, New Jersey

Anthony F. Garito, Ph.D.
Department of Physics
University of Pennsylvania
Philadelphia, Pennsylvania

Milton Gottlieb, Ph.D.
Westinghouse Science and
Technology Center
Pittsburgh, Pennsylvania

William R. Holland, Ph.D.
AT&T Bell Laboratories
Princeton, New Jersey

Ivan P. Kaminow, Ph.D.
AT&T Bell Laboratories
Holmdel, New Jersey

Donald Keyes
U.S. Precision Lens, Inc.
Cincinnati, Ohio

Marvin Klein, Ph.D.
Hughes Research Laboratory
Malibu, California

Mark Kuzyk, Ph.D.
Department of Physics
Washington State University
Pullman, Washington

David W. Lynch, Ph.D.
Iowa State University
Ames, Iowa

Fred Milanovich, Ph.D.
Lawrence Livermore National Laboratory
Livermore, California

Monica Minden, Ph.D.
Hughes Research Laboratory
Malibu, California

Duncan T. Moore, Ph.D.
University of Rochester
Rochester, New York

Lisa A. Moore, Ph.D.
Corning, Inc.
Corning, New York

Egberto Munin, Ph.D.
Universidade de Campinas
Campinas, Brazil

David M. Pepper, Ph.D.
Hughes Research Laboratory
Malibu, California

Stephen C. Rand, Ph.D.
Hughes Research Laboratory
Malibu, California

Charles F. Rapp, Ph.D.
Owens Corning Fiberglass
Granville, Ohio

John F. Reintjes, Ph.D.
Naval Research Laboratory
Washington, DC

Allen H. Rose, Ph.D.
National Institute of Standards and Technology
Boulder, Colorado

Robert Sacher
R. P. Cargille Laboratories, Inc.
Cedar Grove, New Jersey

William Sacher
R. P. Cargille Laboratories, Inc.
Cedar Grove, New Jersey

N. B. Singh, Ph.D.
Westinghouse Science and
Technology Center
Pittsburgh, Pennsylvania

Shobha Singh, Ph.D.
AT&T Bell Laboratories
Murray Hill, New Jersey, and
Polaroid Corporation
Cambridge, Massachusetts

Charlene M. Smith, Ph.D.
Corning, Inc.
Corning, New York

Stanley Stokowski, Ph.D.
Lawrence Livermore National Laboratory
Livermore, California

David S. Sumida, Ph.D.
Hughes Research Laboratory
Malibu, California

Eric W. Van Stryland, Ph.D.
Center for Research in
Electro-Optics and Lasers
University of Central Florida
Orlando, Florida

Barry A. Wechsler, Ph.D.
Hughes Research Laboratory
Malibu, California

Contents of previous volumes on optical materials from the
CRC HANDBOOK OF LASER SCIENCE AND TECHNOLOGY

VOLUME III: OPTICAL MATERIALS
PART 1: NONLINEAR OPTICAL PROPERTIES/RADIATION DAMAGE

SECTION 1: NONLINEAR OPTICAL PROPERTIES

- 1.1 Nonlinear and Harmonic Generation Materials — Shobha Singh
- 1.2 Two-Photon Absorption — Walter L. Smith
- 1.3 Nonlinear Refractive Index — Walter L. Smith
- 1.4 Stimulated Raman Scattering — Fred Milanovich

SECTION 2: RADIATION DAMAGE

- 2.1 Introduction — Richard T. Williams and E. Joseph Friebel
- 2.2 Crystals — Richard T. Williams
- 2.3 Glasses — E. Joseph Friebel

VOLUME IV: OPTICAL MATERIALS
PART 2: PROPERTIES

SECTION 1: FUNDAMENTAL PROPERTIES

- 1.1 Transmitting Materials
 - 1.1. 1 Crystals — Perry A. Miles, Marilyn J. Dodge, Stanley S. Ballard, James S. Browder, Albert Feldman, and Marvin J. Weber
 - 1.1. 2 Glasses — James W. Fleming
 - 1.1. 3 Plastics — Monis Manning
- 1.2 Filter Materials — Lee M. Cook and Stanley E. Stokowski
- 1.3 Mirror and Reflector Materials — David W. Lynch
- 1.4 Polarizer Materials — Jean M. Bennett and Ann T. Glassman

SECTION 2: SPECIAL PROPERTIES

- 2.1 Linear Electro-Optic Materials — Ivan P. Kaminow
- 2.2 Magneto-Optic Materials — Di Chen
- 2.3 Elasto-Optic Materials — Milton Gottlieb
- 2.4 Photorefractive Materials — Peter Günter
- 2.5 Liquid Crystals — Stephen D. Jacobs

VOLUME V: OPTICAL MATERIALS
PART 3: APPLICATIONS, COATINGS, AND FABRICATION

SECTION 1: APPLICATIONS

- 1.1 Optical Waveguide Materials — Peter L. Bocko and John R. Gannon
- 1.2 Materials for High Density Optical Data Storage — Alan E. Bell
- 1.3 Holographic Parameters and Recording Materials — K. S. Pennington
- 1.4 Phase Conjugation Materials — Robert A. Fisher
- 1.5 Laser Crystals — Charles F. Rapp
- 1.7 Infrared Quantum Counter Materials — Leon Esterowitz

SECTION 2: THIN FILMS AND COATINGS

- 2.1 Multilayer Dielectric Coatings — Verne R. Costich
- 2.2 Graded-Index Surfaces and Films — W. Howard Lowdermilk

SECTION 3: OPTICAL MATERIALS FABRICATION

- 3.1 Fabrications Techniques — G. M. Sanger and S. D. Fantone
- 3.2 Fabrication Procedures for Specific Materials — G. M. Sanger and S. D. Fantone

SUPPLEMENT 2: OPTICAL MATERIALS

SECTION 1. OPTICAL CRYSTALS — Bruce H. T. Chai

SECTION 2. OPTICAL GLASSES — James W Fleming

SECTION 3. OPTICAL PLASTICS — Donald Keyes

SECTION 4. OPTICAL LIQUIDS — Robert Sacher and William Sacher

SECTION 5. FILTER MATERIALS — Lee M. Cook

SECTION 6. LINEAR ELECTROOPTIC MATERIALS — William R. Holland and Ivan P. Kaminow

SECTION 7. NONLINEAR OPTICAL MATERIALS

7.1 Crystals — Shobha Singh

7.2 Cluster-Insulator Composite Materials — Joseph H. Simmons, Barrett G. Potter, Jr., and O. Romulo Ochoa

SECTION 8. NONLINEAR OPTICAL PROPERTIES

8.1 Nonlinear Refractive Index :

Inorganic Materials — Lloyd Chase and Eric W. Van Stryland
Organic Materials — Anthony F. Garito and Mark Kuzyk

8.2 Two-Photon Absorption:

Inorganic Materials — Lloyd Chase and Eric W. Van Stryland
Organic Materials — Anthony F. Garito and Mark Kuzyk

8.3 Stimulated Raman and Brillouin Scattering — John F. Reintjes

SECTION 9. MAGNETOOPTIC MATERIALS

9.1 Crystals and Glasses — Merritt N. Deeter, Gordon W. Day, and Allen H. Rose

9.2 Organic and Inorganic Liquids — Egberto Munin

SECTION 10. ELASTOOPTIC MATERIALS — M. Gottlieb and N. B. Singh

SECTION 11. PHOTOREFRACTIVE MATERIALS — Carolina Medrano and Peter Günter

SECTION 12. OPTICAL PHASE CONJUGATION MATERIALS — David M. Pepper, Marvin Klein, Monica Minden, Hans Brusselbach

SECTION 13. GRADIENT INDEX MATERIALS — Duncan T. Moore

SECTION 14. LIQUID CRYSTALS — Stephen D. Jacobs, Kenneth L. Marshall, and Ansgar Schmid

SECTION 15. DIAMOND OPTICS — Albert Feldman

SECTION 16. LASER CRYSTALS — David S. Sumida and Barry A. Wechsler

SECTION 17. LASER GLASSES

17.1 Bulk Glasses — Charles F. Rapp

17.2 Waveguide Glasses — Steven T. Davey, B. James Ainslie, and Richard Wyatt

SECTION 18. OPTICAL WAVEGUIDE MATERIALS

- 18.1 Crystals — Patricia A. Morris Hotsenpiller
- 18.2 Glasses — Allen J. Bruce
- 18.3 Plastic Optical Fibers — Lee L. Blyler, Jr.

SECTION 19. OPTICAL COATINGS FOR HIGH POWER LASERS — Mark R. Kozlowski, Robert Chow, and Ian M. Thomas

APPENDIX 1. ABBREVIATIONS, ACRONYMS, INITIALISMS, AND MINERALOGICAL OR COMMON NAMES FOR OPTICAL MATERIALS

APPENDIX 2. ABBREVIATIONS FOR METHODS OF PREPARING OPTICAL MATERIALS

APPENDIX 3. DESIGNATIONS OF RUSSIAN OPTICAL GLASSES
Leonid B. Glebov and Mikhail N. Tolstoi

Table of Contents

SECTION 1: CRYSTALLINE MATERIALS

- 1.1 Introduction
- 1.2 Physical Properties
 - 1.2.1 Isotropic Crystals
 - 1.2.2 Uniaxial Crystals
 - 1.2.3 Biaxial Crystals
- 1.3 Optical Properties
 - 1.3.1 Isotropic Crystals
 - 1.3.2 Uniaxial Crystals
 - 1.3.3 Biaxial Crystals
 - 1.3.4 Dispersion Formulas for Refractive Index
 - 1.3.5 Thermooptic Coefficients
- 1.4 Mechanical Properties
 - 1.4.1 Elastic Constants
 - 1.4.2 Elastic Moduli
 - 1.4.3 Engineering Data
- 1.5 Thermal Properties
 - 1.5.1 Melting Point, Heat Capacity, Thermal Expansion, Conductivity
 - 1.5.2 Temperature Dependence of Heat Capacity for Selected Solids
 - 1.5.3 Debye Temperature
- 1.6 Magnetooptic Properties
 - 1.6.1 Diamagnetic Crystals
 - 1.6.2 Paramagnetic Crystals
 - 1.6.3 Ferromagnetic, Antiferromagnetic, and Ferrimagnetic Crystals
- 1.7 Electrooptic Properties
 - 1.7.1 Linear Electrooptic Coefficients
 - 1.7.2 Quadratic Electrooptic Materials
- 1.8 Elastooptic Properties
 - 1.8.1 Elastooptic Coefficients
 - 1.8.2 Acoustooptic Materials
- 1.9 Nonlinear Optical Properties
 - 1.9.1 Nonlinear Refractive Index
 - 1.9.2 Two-Photon Absorption
 - 1.9.3 Second Harmonic Generation Coefficients
 - 1.9.4 Third-Order Nonlinear Optical Coefficients
 - 1.9.5 Optical Phase Conjugation Materials

SECTION 2: GLASSES

- 2.1 Introduction
- 2.2 Commercial Optical Glasses
 - 2.2.1 Optical Properties
 - 2.2.2 Internal Transmittance
 - 2.2.3 Mechanical Properties
 - 2.2.4 Thermal Properties
- 2.3 Specialty Optical Glasses

- 2.3.1 Optical Properties
- 2.3.2 Mechanical Properties
- 2.3.3 Thermal Properties
- 2.4 Fused Silica
- 2.5 Fluoride Glasses
 - 2.5.1 Fluorozirconate Glasses
 - 2.5.2 Fluorohafnate Glasses
 - 2.5.3 Other Fluoride Glasses
- 2.6 Chalcogenide Glasses
- 2.7 Magnetooptic Properties
 - 2.7.1 Diamagnetic Glasses
 - 2.7.2 Paramagnetic Glasses
- 2.8 Electrooptic Properties
- 2.9 Elastooptic Properties
- 2.10 Nonlinear Optical Properties
 - 2.10.1 Nonlinear Refractive Index
 - 2.10.2 Two-Photon Absorption
 - 2.10.3 Third-Order Nonlinear Optical Coefficients
 - 2.10.4 Brillouin Phase Conjugation
- 2.11 Special Glasses
 - 2.11.1 Filter Glasses
 - 2.11.2 Laser Glasses
 - 2.11.3 Faraday Rotator Glasses
 - 2.11.4 Gradient-Index Glasses
 - 2.11.5 Mirror Substrate Glasses
 - 2.11.6 Athermal Glasses
 - 2.11.7 Acoustooptic Glasses
 - 2.11.8 Abnormal Dispersion Glasses

SECTION 3: POLYMERIC MATERIALS

- 3.1 Optical Plastics
- 3.2 Index of Refraction
- 3.3 Nonlinear Optical Properties
- 3.4 Thermal Properties
- 3.5 Engineering Data

SECTION 4: METALS

- 4.1 Physical Properties of Selected Metals
- 4.2 Optical Properties
- 4.3 Mechanical Properties
- 4.4 Thermal Properties
- 4.5 Mirror Substrate Materials

SECTION 5: LIQUIDS

- 5.1 Introduction
- 5.2 Water
 - 5.2.1 Physical Properties
 - 5.2.2 Absorption

- 5.2.3 Index of Refraction
- 5.3 Physical Properties of Selected Liquids
 - 5.3.1 Thermal Conductivity
 - 5.3.2 Viscosity
 - 5.3.3 Surface Tension
 - 5.3.4 Absorption
- 5.4 Index of Refraction
 - 5.4.1 Organic Liquids
 - 5.4.2 Inorganic Liquids
 - 5.4.3 Calibration Liquids
 - 5.4.4 Abnormal Dispersion Liquids
- 5.5 Nonlinear Optical Properties
 - 5.5.1 Two-Photon Absorption Cross Sections
 - 5.5.2 Nonlinear Refraction
 - 5.5.3 Kerr Constants
 - 5.5.4 Third-Order Nonlinear Optical Coefficients
 - 5.5.5 Stimulated Raman Scattering
 - 5.5.6 Stimulated Brillouin Scattering
- 5.6 Magnetooptic Properties
 - 5.6.1 Verdet Constants of Inorganic Liquids
 - 5.6.2 Verdet Constants of Organic Liquids
 - 5.6.3 Dispersion of Verdet Constants
- 5.7 Commercial Optical Liquids

SECTION 6: GASES

- 6.1 Introduction
- 6.2 Physical Properties of Selected Gases
- 6.3 Index of Refraction
- 6.4 Nonlinear Optical Properties
 - 6.4.1 Nonlinear Refractive Index
 - 6.4.2 Two-Photon Absorption
 - 6.4.3 Third-Order Nonlinear Optical Coefficients
 - 6.4.4 Stimulated Raman Scattering
 - 6.4.5 Brillouin Phase Conjugation
- 6.5 Magnetooptic Properties
- 6.6 Atomic Resonance Filters

APPENDICES

- Appendix I Safe Handling of Optical Materials
- Appendix II Abbreviations, Acronyms, Initialisms, and Mineralogical or Common Names of Optical Materials
- Appendix III Abbreviations for Methods of Preparing Optical Materials and Thin Films
- Appendix IV Fundamental Physical Constants
- Appendix V Units and Conversion Factors

Section 1: Crystalline Materials

- 1.1 Introduction
- 1.2 Physical Properties
- 1.3 Optical Properties
- 1.4 Mechanical Properties
- 1.5 Thermal Properties
- 1.6 Magnetooptic Properties
- 1.7 Electrooptic Properties
- 1.8 Elastooptic Properties
- 1.9 Nonlinear Optical Properties

Section 1

CRYSTALLINE MATERIALS

1.1 Introduction*

Crystalline materials included in this section are insulators and semiconductors that have a transparent region within the range from the vacuum ultraviolet (from ~100 nm) to the infrared (up to 100 μm) portion of the electromagnetic spectrum. Crystals with wide band gaps are transparent from the ultraviolet through the visible region; crystals with a narrower band gap may appear opaque but are transparent in the infrared region. Using this broad transparency definition of optical crystals, virtually all known crystals can be included. Coverage, however, is limited to those crystals which either occur in nature or are produced in the laboratory for optical use or with potential for such use. For this reason hydrate or hydroxide crystals are generally excluded because they are thermally less stable and have limited transmission range due to OH absorption. Highly hygroscopic materials are also excluded because of the obvious difficulty of handling, unless they have already been used, such as urea, KDP, CD*A, etc. Only pure compounds are considered. Compounds containing elements having intrinsic absorptions due to incompletely filled d or f shell electrons are also avoided.

Other critical issues for the use of optical crystals are solid-state phase transitions that occur as a function of both temperature and pressure and polymorphism. Compounds that have a very small stability field or serious phase transition problems have limited use as optical materials. Phase change and decomposition temperatures of crystals are noted in Section 1.5 on thermal properties. Generally only the thermodynamically stable structure at room temperature and pressure are listed in this section. Compounds that have naturally occurring polymorphic forms are included, however, e.g., CaCO_3 , TiO_2 , and aluminum silicate Al_2SiO_5 . In other cases, only the stable phase is listed, e.g., quartz ($\alpha\text{-SiO}_2$).

Many compounds were considered appropriate as entries of optical crystals in Sections 1.1–1.3 regardless of the amount of information available. As Chai* has noted, merely showing the existence of a compound with its chemical constituents can help to estimate the stability of its isomorphs and the structural tolerance of doping or other modifications. Most of the basic material properties such as optical transparency and refractive indices of an unstudied compound can be estimated with reasonable accuracy based on its better studied isomorphs that have measured properties listed in the tables.

Optical crystals in Sections 1.1–1.3 are classified into three categories:

Isotropic crystals include materials through which monochromatic light travels with the same speed, regardless of the direction of vibration, and the vibration direction of a light ray is always perpendicular to the ray path. Whereas amorphous materials such as glasses and plastics are isotropic, only those crystals with cubic symmetry are isotropic.

* This section was adapted from “Optical crystals” by B. H. T. Chai, *Handbook of Laser Science and Technology, Suppl. 2, Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 3 ff (with additions).

Anisotropic crystals include materials through which a light ray may travel with different speeds for different directions of vibration and in which the angle between the vibration directions and ray path may not always be 90°. The index of refraction of such crystals varies according to the vibration direction of the light; the optical indicatrix is no longer a sphere but an ellipsoid. Depending on the geometry of the ellipsoid, it is necessary to divide the class of the anisotropic materials further into two subgroups. Crystals with tetragonal, hexagonal, and trigonal (or rhombohedral) symmetry exhibit a unique index of refraction (symbolized as e or ϵ) when light vibrates parallel to the c -axis (the extraordinary ray). For light vibrating at 90° to the c -axis (the ordinary ray), the refractive indices are the same (symbolized as o or ω) in all 360° directions. Crystals with these types of optical properties are called *uniaxial crystals*. Crystals with orthorhombic, monoclinic, and triclinic symmetry possess three significant indices of refraction, commonly symbolized as x , y , and z or α , β , and γ in the order from smallest to largest. The shape of the indicatrix is a three-dimensional ellipsoid with all central sections being ellipses, except for two. These two are circular sections with a radius of β . The normal of the two circular sections are called the optical axes. Crystals with these types of optical properties are called *biaxial crystals*. In Sections 1.2 and 1.3 crystals are grouped as isotropic, uniaxial, and biaxial.

Crystal symmetry plays a critical role in the selection of material for optical applications. Optically isotropic crystals are used most frequently for windows and lenses although a uniaxial single crystal (such as sapphire) precisely oriented along the optical axis can be used as a window material. Faraday rotator crystals for optical isolators based must be cubic or uniaxial, not biaxial. Anisotropic single crystals are widely used for other specific optical applications such as the polarizers, optical wave plates, and wedges. In nonlinear frequency conversion, all the optical materials used at present must not only be crystalline but also highly anisotropic and noncentrosymmetric.

For simplicity of crystal orientation and fabrication, materials with highest symmetry are preferred. It is easy to orient crystals with cubic (isometric), tetragonal, and hexagonal (uniaxial) symmetries. For the biaxial crystals, orthorhombic symmetry is still relatively easy to orient because all the crystallographic axes are still orthogonal and in alignment with the optical indicatrix axes. In monoclinic crystals, the crystallographic a - and c -axes are no longer orthogonal. With the exception of the b -axis, two of the optical indicatrix axes are no longer aligned with the crystallographic ones. With a few exceptions, crystals with triclinic symmetry are not listed because they are difficult to orient and have too many parameters to define (no degeneracy at all).

The preceding symmetry properties of a crystal structure refer to space group operations. For measured macroscopic properties the point group (the group of operations under which the property remains unchanged) is of interest. Eleven of the 32 point groups are centrosymmetric. Except for cubic 432, the remaining groups exhibit polarization when the crystal is subject to an applied stress (piezoelectric). Ten of these latter groups possess a unique polar axis and are pyroelectric, i.e., spontaneous polarize in the absence of stress. Crystallographic point groups and related properties are listed in the following table.

Crystallographic Point Groups and Properties

Crystal system	International symbol	Schoenflies symbol	Centro-symmetric	Piezo-electric	Pyro-electric
Cubic	m3m	O _h			
	-43m	T _d			
	432	O			
	m3	T _h			
	23	T			
Hexagonal	6/mmm	D _{6h}			
	-6m2	D _{3h}			
	6mm	C _{6v}			
	622	D ₆			
	6/m	C _{6h}			
	-6	C _{3h}			
	6	C ₆			
Tetragonal	4/mmm	D _{4h}			
	-42m	D _{2d}			
	4mm	C _{4v}			
	422	D ₄			
	4/m	C _{4h}			
	-4	S ₄			
	4	C ₄			
Trigonal	-3m	D _{3d}			
	3m	C _{3v}			
	32	D ₃			
	-3	S ₆			
	3	C ₃			
Orthorhombic	mmm	D _{2h}			
	mm2	C _{2v}			
	222	D ₂			
Monoclinic	2/m	C _{2h}			
	m	C _s			
	2	C ₂			
Triclinic	-1	C _i			
	1	C ₁			

Crystals in the following table are listed alphabetically by chemical name (with mineral name* and acronym in parentheses) and include the chemical formula, crystal system, and space group. In the space group notation, a negative number indicates inversion symmetry.

* A mineralogy database containing names, physical properties, and an audio pronunciation guide for a very large number of materials is available at www.webmineral.com.

Name, Formula, Crystal System, and Space Group for Optical Crystals

Name	Formula	Crystal system (Space group)
Aluminum antimonide	AlSb	Cubic (F-43m)
Aluminum arsenate	AlAsO ₄	Trigonal (P3 ₁ 2)
Aluminum arsenide	AlAs	Cubic (F-43m)
Aluminum borate	AlBO ₃	Trigonal (R-3c)
Aluminum borate	Al ₄ B ₂ O ₉	Orthorhombic (Pbam)
Aluminum fluoride	AlF ₃	Rhombohedral (R32)
Aluminum fluorosilicate (topaz)	Al ₂ SiO ₄ F ₂	Orthorhombic (Pbnm)
Aluminum gallate	AlGaO ₃	Hexagonal (P6 ₃ mmc)
Aluminum germanate	Al ₂ Ge ₂ O ₇	Monoclinic (C2/c)
Aluminum germanate	Al ₆ Ge ₂ O ₁₃	Orthorhombic (Pbnm)
Aluminum germanate	Al ₆ Ge ₂ O ₁₃	Orthorhombic (Pbnm)
Aluminum hafnium tantalate	AlHfTaO ₆	Orthorhombic (Pbcn)
Aluminum molybdate	Al ₂ (MoO ₄) ₃	Monoclinic (P2 ₁ /a)
Aluminum niobate	AlNbO ₄	Monoclinic (C2/m)
Aluminum nitride	AlN	Hexagonal (6 ₃ mc)
Aluminum oxide (corundum, sapphire, alumina)	Al ₂ O ₃	Trigonal (R-3c)
Aluminum oxynitrate (ALON)	Al ₂₃ O ₂₇ N ₅	Cubic (Fd3m)
Aluminum phosphate (berlinitite)	AlPO ₄	Trigonal (P3 ₁ 2)
Aluminum phosphide	AlP	Hexagonal (6 ₃ mc)
Aluminum silicate (andalusite)	Al ₂ SiO ₅	Orthorhombic (Pmam)
Aluminum silicate (kyanite)	Al ₂ SiO ₅	Triclinic (P-1)
Aluminum silicate (mullite)	Al ₆ Si ₂ O ₁₃	Orthorhombic (Pbnm)
Aluminum silicate (sillimanite)	Al ₂ SiO ₅	Orthorhombic (Pbnm)
Aluminum tantalate (alumotantite)	AlTaO ₄	Orthorhombic (Pc2 ₁ n)
Aluminum titanium tantalate	AlTiTaO ₆	Tetragonal (P4 ₂ /mm)
Aluminum tungstate	Al ₂ (WO ₄) ₃	Orthorhombic (Pcna)
Amino carbonyl (urea)	(NH ₂) ₂ CO	Tetragonal (I-42m)
Ammonium aluminum selenate	NH ₄ Al(SeO ₄) ₂	Trigonal (P321)
Ammonium aluminum sulfate	NH ₄ Al(SO ₄) ₂	Trigonal (P321)
Ammonium dihydrogen phosphate (ADP)	NH ₄ H ₂ PO ₄	Tetragonal (I-42m)
Ammonium gallium selenate	NH ₄ Ga(SeO ₄) ₂	Trigonal (P321)
Ammonium gallium sulfate	NH ₄ Ga(SO ₄) ₂	Trigonal (P321)
Ammonium pentaborate	NH ₄ B ₅ O ₈ •4H ₂ O	Orthorhombic (Aba2)
Antimony niobate (stibiocolumbite)	SbNbO ₄	Orthorhombic (Pna2 ₁)
Antimony oxide (senarmontite)	Sb ₂ O ₃	Cubic (Fd3m)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Antimony oxide (valentinite)	Sb ₂ O ₃	Orthorhombic (Pccn)
Antimony tantalate (stibiotantalite)	SbTaO ₄	Orthorhombic (Pc2 ₁ n)
Arsenic antimony sulfide (getchellite)	AsSbS ₃	Monoclinic (P21/a)
Arsenic oxide (arsenolite)	As ₂ O ₃	Cubic (Fd3m)
Arsenic sulfide (orpiment)	As ₂ S ₃	Monoclinic (P21n)
Arsenic sulfide (realgar)	AsS	Monoclinic (P21n)
Barium aluminate	BaAl ₂ O ₄	Hexagonal (P6 ₃ 22)
Barium aluminate	Ba ₃ Al ₂ O ₆	Cubic (Pa3)
Barium aluminum borate	BaAl ₂ B ₂ O ₇	Monoclinic (P2/c)
Barium aluminum fluoride	Ba ₃ Al ₂ F ₁₂	Orthorhombic (Pnnm)
Barium aluminum germanate	BaAl ₂ Ge ₂ O ₈	Monoclinic (P2 ₁ /a)
Barium aluminum silicate (celsian)	BaAl ₂ Si ₂ O ₈	Monoclinic (I2/a)
Barium antimonate	BaSb ₂ O ₆	Triclinic (P-31m)
Barium beryllium fluorophosphate (babefphite)	BaBe(PO ₄)F	Hexagonal(P-6c2)
Barium beryllium silicate (barylite)	BaBe ₂ Si ₂ O ₇	Orthorhombic (Pnma)
Barium tetraborate	BaB ₄ O ₇	Monoclinic (P21/c)
Barium borate	β-BaB ₂ O ₄	Trigonal (R3c)
Barium cadmium aluminum fluoride	BaCdAlF ₇	Monoclinic (C2/c)
Barium cadmium gallium fluoride	BaCdGaF ₇	Monoclinic (C2/c)
Barium cadmium magnesium aluminum fluoride	Ba ₂ CdMgAl ₂ F ₁₄	Monoclinic (C2/c)
Barium calcium magnesium aluminum fluoride	Ba ₂ CaMgAl ₂ F ₁₄	Monoclinic (C2/c)
Barium calcium magnesium silicate	BaCa ₂ Mg(SiO ₄) ₂	Orthorhombic
Barium calcium silicate (walstromite)	BaCa ₂ Si ₃ O ₉	Triclinic(P-1)
Barium carbonate (witherite)	BaCO ₃	Orthorhombic (Pnam)
Barium chloroarsenate (movelandite)	Ba ₅ (AsO ₄) ₃ Cl	Hexagonal(P6 ₃ /m)
Barium chloroborate	Ba ₂ B ₅ O ₉ Cl	Tetragonal (P4 ₂ 2 ₁ -2)
Barium chlorophosphate (alforsite)	Ba ₅ (PO ₄) ₃ Cl	Hexagonal(P6 ₃ /m)
Barium chlorovanadate	Ba ₅ (VO ₄) ₃ Cl	Hexagonal(P6 ₃ /m)
Barium fluoride-calcium fluoride (T-12)	BaF ₂ -CaF ₂	Cubic (Fm3m)
Barium fluoride (frankdicksonite)	BaF ₂	Cubic (Fm3m)
Barium fluoroarsenate	Ba ₅ (AsO ₄) ₃ F	Hexagonal(P6 ₃ /m)
Barium fluorophosphate	Ba ₅ (PO ₄) ₃ F	Hexagonal(P6 ₃ /m)
Barium fluorovanadate	Ba ₅ (VO ₄) ₃ F	Hexagonal(P6 ₃ /m)
Barium gallium fluoride	BaGaF ₅	Orthorhombic (P2 ₁ 2 ₁ 2 ₁)
Barium germanate	BaGeO ₃	Orthorhombic
Barium germanate	BaGe ₂ O ₅	Monoclinic (P2 ₁ /a)
Barium germanate	BaGe ₄ O ₉	Hexagonal(P-6c2)
Barium germanium aluminate	BaGeAl ₆ O ₁₂	Orthorhombic (Pnnm)
Barium germanium gallate	BaGeGa ₆ O ₁₂	Orthorhombic (Pnnm)
Barium hexa-aluminate	BaAl ₁₂ O ₁₉	Hexagonal (P6 ₃ /mmc)
Barium lithium niobate	Ba ₂ LiNb ₅ O ₁₅	Orthorhombic (Im2a)
Barium lutetium borate	Ba ₃ Lu(BO ₃) ₃	Hexagonal(P6 ₃ cm)
Barium magnesium aluminum fluoride	Ba ₂ MgAlF ₉	Tetragonal (P4)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Barium magnesium fluoride	BaMgF ₄	Orthorhombic (A2 ₁ am)
Barium magnesium fluoride	Ba ₂ MgF ₆	Tetragonal (I422)
Barium magnesium germanate	Ba ₂ MgGe ₂ O ₇	Tetragonal (P42 ₁ m)
Barium magnesium silicate	Ba ₂ MgSi ₂ O ₇	Tetragonal (P42 ₁ m)
Barium magnesium tantalate	Ba ₃ MgTa ₂ O ₉	Cubic (Fm3m)
Barium magnesium vanadate	BaMg ₂ (VO ₄) ₂	Tetragonal (I4 ₁ /acd)
Barium molybdate	BaMoO ₄	Tetragonal (I4 ₁ /a)
Barium niobate	BaNb ₂ O ₆	Orthorhombic (Pcan)
Barium nitrate (nitrobarite)	Ba(NO ₃) ₂	Cubic (P2 ₁ 3)
Barium scandate	Ba ₂ Sc ₄ O ₉	Trigonal(R-3)
Barium scandate	BaSc ₂ O ₄	Monoclinic (C2/c)
Barium scandate	Ba ₆ Sc ₆ O ₁₅	Tetragonal
Barium silicate (sabbornite)	β-BaSi ₂ O ₅	Orthorhombic (Pmn _b)
Barium sodium niobate	Ba ₂ NaNb ₅ O ₁₅	Orthorhombic (Im2a)
Barium sodium phosphate	Ba ₂ Na(PO ₅) ₅	Orthorhombic (P212121))
Barium strontium niobate	Ba ₃ SrNb ₂ O ₉	Hexagonal (P63/mmc)
Barium strontium tantalate	Ba ₃ SrTa ₂ O ₉	Hexagonal (P63/mmc)
Barium sulfate (barite)	BaSO ₄	Orthorhombic (Pbnm)
Barium tantalate	BaTa ₂ O ₆	Orthorhombic (Pcan)
Barium tantalate	BaTa ₂ O ₆	Orthorhombic (Pcan)
Barium tin borate	BaSnB ₂ O ₆	Trigonal(R-3)
Barium tin silicate (pabstite)	BaSnSi ₃ O ₉	Hexagonal (P-6c2)
Barium titanate	BaTiO ₃	Cubic (Fm3m)
Barium titanate	BaTiO ₃	Tetragonal (Pm3m)
Barium titanium aluminate	BaTiAl ₆ O ₁₂	Orthorhombic (Pnnm)
Barium titanium aluminate	Ba ₃ TiAl ₁₀ O ₂₀	Monoclinic (C2/m)
Barium titanium borate	BaTiB ₂ O ₆	Trigonal(R-3)
Barium titanium gallate	BaTiGa ₆ O ₁₂	Orthorhombic (Pnnm)
Barium titanium oxide	BaTi ₄ O ₉	Orthorhombic (Pnmm)
Barium titanium silicate (benitoite)	BaTiSi ₃ O ₉	Hexagonal (P-6c2)
Barium titanium silicate (fresnoite)	Ba ₂ TiSi ₂ O ₈	Tetragonal (P4bm)
Barium tungstate	BaWO ₄	Tetragonal (I4 ₁ /a)
Barium vanadate	Ba ₃ (VO ₄) ₂	Rhombohedral (R-3m)
Barium yttrium borate	Ba ₃ Lu(BO ₃) ₃	Hexagonal(P6 ₃ cm)
Barium yttrium fluoride	BaY ₂ F ₈	Monoclinic (C2/m)
Barium yttrium oxide	BaY ₂ O ₄	Orthorhombic (Pnab)
Barium zinc aluminum fluoride	Ba ₂ ZnAlF ₉	Orthorhombic (Pnma)
Barium zinc fluoride	BaZnF ₄	Orthorhombic (C222)
Barium zinc fluoride	Ba ₂ Zn ₃ F ₁₀	Monoclinic (C2/m)
Barium zinc fluoride	Ba ₂ ZnF ₆	Tetragonal (I422)
Barium zinc gallium fluoride	Ba ₂ ZnGaF ₉	Monoclinic (P2 ₁ /n)
Barium zinc germanate	BaZnGeO ₄	Hexagonal (P6 ₃)
Barium zinc germanate	Ba ₂ ZnGe ₂ O ₇	Tetragonal (P42 ₁ m)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Barium zinc silicate	Ba ₂ ZnSi ₂ O ₇	Tetragonal (P42 ₁ m)
Barium zinc silicate	BaZnSiO ₄	Hexagonal (P6 ₃)
Barium zirconium silicate	Ba ₂ ZrSi ₂ O ₈	Tetragonal (P4bm)
Barium zirconium silicate	Ba ₂ Zr ₂ Si ₃ O ₁₂	Cubic (P2 ₁ 3)
Barium zirconium silicate (bazirite)	BaZrSi ₃ O ₉	Hexagonal (P6 ₃ 22)
Beryllium aluminate	BeAl ₆ O ₁₀	Orthorhombic (Pca2)
Beryllium aluminate (chrysoberyl)	BeAl ₂ O ₄	Orthorhombic (Pnma)
Beryllium aluminum silicate (beryl)	Be ₃ Al ₂ Si ₆ O ₁₈	Hexagonal (P6/mcc)
Beryllium fluoroborate (hambergite)	Be ₂ BO ₃ F	Monoclinic (C21)
Beryllium germanate	Be ₂ GeO ₄	Trigonal(R-3)
Beryllium magnesium aluminate (taaffeite)	BeMg ₃ Al ₈ O ₁₆	Hexagonal
Beryllium oxide (bormellite)	BeO	Hexagonal (P6 ₃ /mc)
Beryllium scandium silicate (bazzite)	Be ₃ Sc ₂ Si ₆ O ₁₈	Hexagonal (P6/mcc)
Beryllium silicate (phenakite)	Be ₂ SiO ₄	Trigonal(R-3)
Bismuth aluminate	Bi ₂ Al ₄ O ₉	Orthorhombic (Pbam)
Bismuth antimonate	BiSbO ₄	Monoclinic (P2 ₁ /c)
Bismuth borate	Bi ₄ B ₂ O ₉	Monoclinic (P2 ₁ /c)
Bismuth germanate	Bi ₂ Ge ₃ O ₉	Hexagonal (P6 ₃ /m)
Bismuth germanate	Bi ₂ GeO ₅	Orthorhombic (Cmc2 ₁)
Bismuth germanate	Bi ₁₂ GeO ₂₀	Cubic (I23)
Bismuth germanate (BGO)	Bi ₄ Ge ₃ O ₁₂	Cubic (I43d)
Bismuth metaborate	BiB ₃ O ₆	Monoclinic (2/m)
Bismuth molybdate	Bi ₂ Mo ₂ O ₉	Monoclinic (P2 ₁ /m)
Bismuth molybdate	Bi ₂ Mo ₃ O ₁₂	Monoclinic (P2 ₁ /m)
Bismuth niobate	BiNbO ₄	Orthorhombic (Pann)
Bismuth oxide (bismite)	Bi ₂ O ₃	Monoclinic (P2 ₁ /c)
Bismuth oxymolybdate (koechlinite)	γ-Bi ₂ MoO ₆	Orthorhombic (Pba2)
Bismuth oxytungstate (rusellite)	Bi ₂ WO ₆	Orthorhombic (Pba2)
Bismuth silicate	Bi ₂ SiO ₅	Orthorhombic (Cmc2 ₁)
Bismuth silicate (eulytite)	Bi ₄ Si ₃ O ₁₂	Cubic (I43d)
Bismuth silicate (sillenite, BSO)	Bi ₁₂ SiO ₂₀	Cubic (I23)
Bismuth tantalate	BiTaO ₄	Orthorhombic (Pnna)
Bismuth tin oxide	Bi ₂ Sn ₂ O ₇	Hexagonal (P6 ₃ /m)
Bismuth titanate	Bi ₄ Ti ₃ O ₁₂	Orthorhombic (B2cb)
Bismuth titanium niobate	Bi ₃ TiNbO ₉	Orthorhombic (A2 ₁ am)
Bismuth titanium oxide	Bi ₁₂ TiO ₂₀	Cubic (I23)
Bismuth vanadate (clinobisvanite)	BiVO ₄	Monoclinic (I2/a)
Bismuth vanadate (dreyerite)	BiVO ₄	Tetragonal (I4 ₁ /amd)
Bismuth vanadate (pucherite)	BiVO ₄	Orthorhombic (Pnca)
Boron nitride	BN	Cubic (F-43m)
Boron phosphide	BP	Cubic (F-43m)
Cadmium antimonide	Cd ₂ Sb ₂ O ₇	Cubic (Fd3m)
Cadmium borate	CdB ₄ O ₇	Orthorhombic (Pbca)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Cadmium borate	$\text{Cd}_2\text{B}_2\text{O}_5$	Triclinic (P1)
Cadmium borate	$\text{Cd}_2\text{B}_6\text{O}_{11}$	Monoclinic (P2 ₁ /b)
Cadmium borate	$\text{Cd}\text{B}_2\text{O}_4$	Cubic (P-43m)
Cadmium carbonate (otavite)	CdCO_3	Rhombohedral (R-3c)
Cadmium chloride	CdCl_2	Rhombohedral (R-3m)
Cadmium chloroarsenate	$\text{Cd}_5(\text{AsO}_4)_3\text{Cl}$	Hexagonal (P6 ₃ /m)
Cadmium chlorophosphate	$\text{Cd}_5(\text{PO}_4)_3\text{Cl}$	Hexagonal(P6 ₃ /m)
Cadmium chlorovanadate	$\text{Cd}_5(\text{VO}_4)_3\text{Cl}$	Hexagonal (P6 ₃ /m)
Cadmium fluoride	CdF_2	Cubic (Fm3m)
Cadmium fluorophosphate	$\text{Cd}_5(\text{PO}_4)_3\text{F}$	Hexagonal (P6 ₃ /m)
Cadmium gallate	CdGa_2O_4	Cubic (Fd3m)
Cadmium germanate	Cd_2GeO_4	Orthorhombic (Pbnm)
Cadmium germanium arsenide	CdGeAs_2	Tetragonal (I-42d)
Cadmium germanium phosphide	CdGeP_2	Tetragonal (I-42d)
Cadmium indium oxide spinel	CdIn_2O_4	Cubic (Fd3m)
Cadmium iodide	CdI_2	Hexagonal (P6 ₃ mc)
Cadmium niobate	$\text{Cd}_2\text{Nb}_2\text{O}_7$	Cubic (Fd3m)
Cadmium oxide (monteponite)	CdO	Cubic (Fm3m)
Cadmium scandium germanate	$\text{Cd}_3\text{Sc}_2\text{Ge}_3\text{O}_{12}$	Cubic (Ia3d)
Cadmium selenide (cadmoselite)	CdSe	Hexagonal (P6mm)
Cadmium silicon arsenide	CdSiAs_2	Tetragonal (I-42d)
Cadmium silicon phosphide	CdSiP_2	Tetragonal (I-42d)
Cadmium sulfide (greenockite)	CdS	Hexagonal (6mm)
Cadmium tellurite (Irtran 6)	CdTe	Cubic (Fm3m)
Cadmium tin arsenide	CdSnAs_2	Tetragonal (I-42d)
Cadmium tin borate	CdSnB_2O_6	Rhombohedral (R-3c)
Cadmium tin phosphide	CdSnP_2	Tetragonal (I-42d)
Cadmium titanate	CdTiO_3	Rhombohedral(R-3)
Cadmium tungstate	CdWO_4	Monoclinic (P2/c)
Cadmium vanadate	CdV_2O_6	Monoclinic (C2/m)
Cadmium vanadate	$\text{Cd}_2\text{V}_2\text{O}_7$	Monoclinic (C2/m)
Calcium aluminate	CaAl_2O_4	Monoclinic (P2 ₁ /n)
Calcium aluminate	$\text{Ca}_3\text{Al}_2\text{O}_6$	Cubic (Pa-3)
Calcium aluminate	CaAl_4O_7	Monoclinic (C2/c)
Calcium aluminate	$\text{Ca}_5\text{Al}_6\text{O}_{14}$	Orthorhombic (C222)
Calcium aluminate (brownmillerite)	$\text{Ca}_2\text{Al}_2\text{O}_5$	Orthorhombic
Calcium aluminate (mayenite)	$\text{Ca}_{12}\text{Al}_{14}\text{O}_{33}$	Cubic (I43d)
Calcium aluminum borate	CaAlBO_4	Otthorhombic (Pnam)
Calcium aluminum borate	$\text{CaAl}_2\text{B}_2\text{O}_7$	Hexagonal (P6 ₃ 22)
Calcium aluminum borate (johachidolite)	CaAlB_3O_7	Orthorhombic (Cmma)
Calcium aluminum fluoride	CaAlF_5	Monoclinic (C2/c)
Calcium aluminum fluoride	Ca_2AlF_7	Orthorhombic (Pnma)
Calcium aluminum fluoride (prosopite)	CaAl_2F_8	Monoclinic

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Calcium aluminum germanate	$\text{Ca}_2\text{Al}_2\text{GeO}_7$	Tetragonal ($\text{P}42_1\text{m}$)
Calcium aluminum germanate	$\text{Ca}_3\text{Al}_2\text{Ge}_3\text{O}_{12}$	Cubic ($\text{Ia}3\text{d}$)
Calcium aluminum oxyfluoride	$\text{Ca}_2\text{Al}_3\text{O}_6\text{F}$	Hexagonal
Calcium aluminum silicate (anorthite)	$\text{CaAl}_2\text{Si}_2\text{O}_8$	Triclinic($\text{P}-1$)
Calcium aluminum silicate (gehlenite, CAS)	$\text{Ca}_2\text{Al}_2\text{SiO}_7$	Tetragonal ($\text{P}42_1\text{m}$)
Calcium aluminum silicate (grossularite)	$\text{Ca}_3\text{Al}_2\text{Si}_3\text{O}_{12}$	Cubic ($\text{Ia}3\text{d}$)
Calcium antimonate	$\text{Ca}_2\text{Sb}_2\text{O}_7$	Orthorhombic ($\text{Imm}2$)
Calcium antimonate	$\text{Ca}_2\text{Sb}_2\text{O}_7$	Cubic ($\text{Fd}3\text{m}$)
Calcium barium carbonate (alstonite)	$\text{CaBa}(\text{CO}_3)_2$	Orthorhombic (Pnam)
Calcium beryllium fluorophosphate (herderite)	$\text{CaBe}(\text{PO}_4)\text{F}$	Monoclinic
Calcium beryllium phosphate (hurlbutite)	$\text{CaBe}_2(\text{PO}_4)_2$	Monoclinic ($\text{P}2_1/\text{a}$)
Calcium beryllium silicate (gugiaite)	$\text{Ca}_2\text{BeSi}_2\text{O}_7$	Tetragonal ($\text{P}42_1\text{m}$)
Calcium borate	$\text{Ca}_2\text{B}_2\text{O}_5$	Monoclinic ($\text{P}2_1/\text{a}$)
Calcium borate	$\text{Ca}_2\text{B}_6\text{O}_{11}$	Monoclinic ($\text{P}2_1/\text{b}$)
Calcium borate	CaB_4O_7	Monoclinic ($\text{P}2_1/\text{c}$)
Calcium borate	$\text{Ca}_3\text{B}_2\text{O}_6$	Rhombohedral ($\text{R}-3\text{c}$)
Calcium borate (calciborite)	CaB_2O_4	Orthorhombic (Pnca)
Calcium boron silicate (danburite)	$\text{CaB}_2\text{Si}_2\text{O}_8$	Orthorhombic (Pmam)
Calcium carbonate (aragonite)	CaCO_3	Orthorhombic (Pnam)
Calcium carbonate (calcite)	CaCO_3	Rhombohedral ($\text{R}-3\text{c}$)
Calcium carbonate (vaterite)	CaCO_3	Hexagonal ($\text{P}6_3/\text{mmc}$)
Calcium chloroarsenate	$\text{Ca}_2\text{AsO}_4\text{Cl}$	Orthorhombic (Pbcm)
Calcium chloroarsenate	$\text{Ca}_5(\text{AsO}_4)_3\text{Cl}$	Hexagonal($\text{P}6_3/\text{m}$)
Calcium chloroborate	$\text{Ca}_2\text{BO}_3\text{Cl}$	Monoclinic ($\text{P}2_1/\text{c}$)
Calcium chloroborate	$\text{Ca}_2\text{B}_5\text{O}_9\text{Cl}$	Tetragonal ($\text{P}4_2\text{2}_1\text{2}$)
Calcium chlorophosphate	$\text{Ca}_2\text{PO}_4\text{Cl}$	Orthorhombic (Pbcm)
Calcium chlorophosphate (chlorapatite)	$\text{Ca}_5(\text{PO}_4)_3\text{Cl}$	Hexagonal($\text{P}6_3/\text{m}$)
Calcium chlorovanadate	$\text{Ca}_2\text{VO}_4\text{Cl}$	Orthorhombic (Pbcm)
Calcium chlorovanadate	$\text{Ca}_5(\text{VO}_4)_3\text{Cl}$	Hexagonal($\text{P}6_3/\text{m}$)
Calcium fluoride (fluorite, fluorspar, Irtran 3)	CaF_2	Cubic ($\text{Fm}3\text{m}$)
Calcium fluoroarsenate (svabite, CAAP)	$\text{Ca}_5(\text{AsO}_4)_3\text{F}$	Hexagonal($\text{P}6_3/\text{m}$)
Calcium fluoroborate (fabianite)	$\text{CaB}_3\text{O}_5\text{F}$	Orthorhombic ($\text{Pbn}2_1$)
Calcium fluorophosphate (apatite, FAP)	$\text{Ca}_5(\text{PO}_4)_3\text{F}$	Hexagonal($\text{P}6_3/\text{m}$)
Calcium fluorophosphate (spodiosite)	$\text{Ca}_2(\text{PO}_4)\text{F}$	Orthorhombic (Pbcm)
Calcium fluorovanadate (VAP)	$\text{Ca}_5(\text{VO}_4)_3\text{F}$	Hexagonal($\text{P}6_3/\text{m}$)
Calcium gadolinium aluminate	CaGaAlO_4	Hexagonal ($\text{P}6_3/\text{m}$)
Calcium gadolinium double borate	$\text{Ca}_3\text{Gd}_2(\text{BO}_3)_4$	Orthorhombic ($\text{Pc}2_1\text{n}$)
Calcium gadolinium oxysilicate	$\text{CaGd}_4(\text{SiO}_4)_3\text{O}$	Tetragonal ($\text{I}4/\text{mmm}$)
Calcium gadolinium phosphate	$\text{Ca}_3\text{Gd}(\text{PO}_4)_3$	Cubic ($\text{I}-43\text{d}$)
Calcium gallate	CaGa_2O_4	Monoclinic ($\text{P}2_1/\text{c}$)
Calcium gallate	$\text{Ca}_3\text{Ga}_4\text{O}_9$	Orthorhombic ($\text{Cmm}2$)
Calcium gallate	$\text{Ca}_5\text{Ga}_6\text{O}_{14}$	Orthorhombic ($\text{Cmc}2_1$)
Calcium gallium germanate	$\text{Ca}_2\text{Ga}_2\text{GeO}_7$	Tetragonal ($\text{P}42_1\text{m}$)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Calcium gallium germanate	$\text{Ca}_3\text{Ga}_2\text{Ge}_4\text{O}_{14}$	Trigonal ($\text{P}32_1$)
Calcium gallium germanium garnet	$\text{Ca}_3\text{Ga}_2\text{Ge}_3\text{O}_{12}$	Cubic ($\text{I}a3d$)
Calcium gallium silicate (CGS)	$\text{Ca}_2\text{Ga}_2\text{SiO}_7$	Tetragonal ($\text{P}42_1m$)
Calcium germanate	CaGe_2O_5	Monoclinic ($\text{P}2_1/a$)
Calcium germanate	CaGe_4O_9	Hexagonal ($P-6c2$)
Calcium hexa-aluminate	$\text{CaAl}_{12}\text{O}_{19}$	Hexagonal ($\text{P}63/\text{mmc}$)
Calcium indate	CaIn_2O_4	Orthorhombic (Pbcm)
Calcium indium germanate	$\text{Ca}_3\text{In}_2\text{Ge}_3\text{O}_{12}$	Cubic ($\text{I}a3d$)
Calcium indium oxide	$\text{Ca}_3\text{In}_2\text{O}_6$	Orthorhombic (Pbam)
Calcium iodate (lautarite)	$\text{Ca}(\text{IO}_3)_2$	Monoclinic
Calcium lanthanum aluminate	CaLaAlO_4	Tetragonal ($I4/\text{mmm}$)
Calcium lanthanum borate	CaLaBO_4	Hexagonal ($\text{P}6_322$)
Calcium lanthanum oxyphosphate	$\text{Ca}_4\text{La}(\text{PO}_4)_3\text{O}$	Hexagonal ($\text{P}6_3/m$)
Calcium lanthanum oxysilicate	$\text{CaLa}_4(\text{SiO}_4)_3\text{O}$	Hexagonal ($\text{P}6_3/m$)
Calcium lanthanum phosphate	$\text{Ca}_3\text{La}(\text{PO}_4)_3$	Cubic ($I-43d$)
Calcium lanthanum sulfide	CaLa_2S_4	Cubic ($I-43d$)
Calcium lithium magnesium vanadate	$\text{Ca}_2\text{LiMg}_2\text{V}_3\text{O}_{12}$	Cubic ($\text{I}a3d$)
Calcium lithium magnesium vanadate	$\text{Ca}_3\text{LiMgV}_3\text{O}_{12}$	Cubic ($\text{I}a3d$)
Calcium lithium zinc vanadate	$\text{Ca}_2\text{LiZn}_2\text{V}_3\text{O}_{12}$	Cubic ($\text{I}a3d$)
Calcium lithium zinc vanadate	$\text{Ca}_3\text{LiZnV}_3\text{O}_{12}$	Cubic ($\text{I}a3d$)
Calcium lutetium germanate	$\text{Ca}_3\text{Lu}_2\text{Ge}_3\text{O}_{12}$	Cubic ($\text{I}a3d$)
Calcium magnesium borate (kurchatovite)	CaMgB_2O_5	Orthorhombic
Calcium magnesium carbonate (dolomite)	$\text{CaMg}(\text{CO}_3)_2$	Rhombohedral ($\text{R}-3c$)
Calcium magnesium carbonate (huntite)	$\text{CaMg}_3(\text{CO}_3)_4$	Rhombohedral ($\text{R}32$)
Calcium magnesium fluoroarsenate (tilasite)	$\text{CaMgAsO}_4\text{F}$	Orthorhombic
Calcium magnesium fluorophosphate (isokite)	CaMgPO_4F	Monoclinic ($\text{C}2/c$)
Calcium magnesium germanate	$\text{CaMgGe}_2\text{O}_6$	Monoclinic ($\text{C}2/c$)
Calcium magnesium silicate (akermanite)	$\text{Ca}_2\text{MgSi}_2\text{O}_7$	Tetragonal ($\text{P}42_1m$)
Calcium magnesium silicate (diopside)	$\text{CaMgSi}_2\text{O}_6$	Monoclinic ($\text{C}2/c$)
Calcium magnesium silicate (merwinite)	$\text{Ca}_3\text{MgSi}_2\text{O}_8$	Monoclinic ($\text{P}2_1/a$)
Calcium magnesium silicate (monticellite)	CaMgSiO_4	Orthorhombic ($\text{Pmn}b$)
Calcium magnesium vanadate	$\text{CaMg}_2(\text{VO}_4)_2$	Tetragonal ($\text{I}4_1/\text{acd}$)
Calcium molybdate	CaMoO_4	Tetragonal ($\text{I}4_1/a$)
Calcium niobate	$\text{Ca}_2\text{Nb}_2\text{O}_7$	Orthorhombic ($\text{Pn}2_1a$)
Calcium niobate (rynersonite)	CaNb_2O_6	Orthorhombic (Pcan)
Calcium niobium gallium garnet	$\text{Ca}_3(\text{Nb},\text{Ga})_2\text{Ga}_3\text{O}_{12}$	Cubic ($\text{I}a3d$)
Calcium oxide (lime)	CaO	Cubic ($\text{Fm}3m$)
Calcium phosphate	$\beta\text{-CaP}_2\text{O}_7$	Hexagonal ($P-6c2$)
Calcium phosphate	$\beta\text{-CaP}_2\text{O}_7$	Tetragonal ($\text{P}4_1$)
Calcium scandate	CaSc_2O_4	Orthorhombic (Pnam)
Calcium scandium germanate	$\text{Ca}_3\text{Sc}_2\text{Ge}_3\text{O}_{12}$	Cubic ($\text{I}a3d$)
Calcium scandium silicate	$\text{Ca}_3\text{Sc}_2\text{Si}_3\text{O}_{12}$	Cubic ($\text{I}a3d$)
Calcium silicate (larnite)	$b\text{-Ca}_2\text{SiO}_4$	Monoclinic ($\text{P}2_1/n$)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Calcium silicate (rankinite)	$\text{Ca}_3\text{Si}_2\text{O}_7$	Monoclinic
Calcium silicate (wollastonite)	CaSiO_3	Triclinic(P-1)
Calcium sodium magnesium vanadate	$\text{Ca}_2\text{NaMg}_2\text{V}_3\text{O}_{12}$	Cubic (Ia3d)
Calcium sodium zinc vanadate	$\text{Ca}_2\text{NaZn}_2\text{V}_3\text{O}_{12}$	Cubic (Ia3d)
Calcium sulfate (anhydrite)	CaSO_4	Orthorhombic (Bbmm)
Calcium tantalate	CaTa_2O_6	Orthorhombic (Pcan)
Calcium tellurate (denningite)	$\text{Ca}_2\text{Te}_2\text{O}_5$	Tetragonal
Calcium tin borate (nordenskiöldine)	CaSnB_2O_6	Trigonal (R-3m)
Calcium tin oxide	CaSnO_3	Orthorhombic (P2 ₁ 2 ₁ 2 ₁)
Calcium tin silicate (malayaite)	CaSnSiO_5	Monoclinic (P2 ₁ /a)
Calcium titanate (perovskite)	CaTiO_3	Cubic (Pm3m)
Calcium titanium germanate	CaTiGeO_4	Monoclinic (P2 ₁ /a)
Calcium titanium silicate (sphene)	CaTiSiO_5	Monoclinic (P2 ₁ /a)
Calcium tungstate (scheelite)	CaWO_4	Tetragonal (I4 ₁ /a)
Calcium vanadate	CaV_2O_6	Monoclinic (C2/m)
Calcium vanadate	$\text{Ca}_2\text{V}_2\text{O}_7$	Monoclinic (C2/m)
Calcium vanadate	$\text{Ca}_3(\text{VO}_4)_2$	Trigonal (R3c)
Calcium yttrium aluminate	CaYAlO_4	Tetragonal (I4/mmm)
Calcium yttrium borate	CaYBO_4	Orthorhombic (Pnam)
Calcium gadolinium double borate	$\text{Ca}_3\text{Y}_2(\text{BO}_3)_4$	Orthorhombic (Pc2 ₁ n)
Calcium yttrium magnesium germanium garnet	$\text{CaY}_2\text{Mg}_2\text{Ge}_3\text{O}_{12}$	Cubic (Ia3d)
Calcium yttrium oxysilicate	$\text{Ca}_4\text{Y}_6(\text{SiO}_4)_6$	Hexagonal (P6 ₃ /m)
Calcium yttrium oxysilicate (SOAP)	$\text{CaY}_4(\text{SiO}_4)_3\text{O}$	Hexagonal (P6 ₃ /m)
Calcium zinc fluoride	CaZnF_4	Tetragonal (I4 ₁ /a)
Calcium zinc germanate	$\text{CaZnGe}_2\text{O}_6$	Monoclinic (C2/c)
Calcium zinc silicate (esperite)	CaZnSiO_4	Tetragonal (P-42 ₁ m)
Calcium zinc silicate (hardystonite)	$\text{Ca}_2\text{ZnSi}_2\text{O}_7$	Tetragonal (P-42 ₁ m)
Calcium zirconium boron aluminate (painite)	$\text{CaZrBAI}_9\text{O}_{18}$	Hexagonal (P6 ₃)
Calcium zirconium silicate (gittinsite)	$\text{CaZrSi}_2\text{O}_7$	Monoclinic (C2/m)
Calcium zirconium titanate (zirkelite)	$\text{CaZrTi}_2\text{O}_7$	Monoclinic (C2/m)
Calcium zirconium titanium silicate	$\text{Ca}_3(\text{Zr,Ti})\text{Si}_2\text{O}_9$	Monoclinic
Carbon (diamond)	C	Cubic (F-43m)
Cesium aluminum sulfate	$\text{CsAl}(\text{SO}_4)_2$	Trigonal (P321)
Cesium beryllium fluoride	Cs_2BeF_4	Orthorhombic (Pna2 ₁)
Cesium borate (CBO)	CsB_3O_5	Orthorhombic (P2 ₁ 2 ₁ 2 ₁)
Cesium bromide	CsBr	Cubic (Fm3m)
Cesium cadmium bromide	Cs_2CdBr_4	Orthorhombic (Pnma)
Cesium cadmium bromide	CsCdBr_3	Cubic (Pm3m)
Cesium cadmium chloride	Cs_2CdCl_4	Tetragonal (I4/mmm)
Cesium cadmium fluoride	CsCdF_3	Cubic (Pm3m)
Cesium cadmium zinc fluoride	$\text{Cs}_2\text{CdZnF}_6$	Rhombohedral (R-3m)
Cesium calcium fluoride	CsCaF_3	Cubic (Pm3m)
Cesium chloride	CsCl	Cubic (Fm3m)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Cesium dideuterium arsenate	CsD_2AsO_4	Tetragonal (I-42m)
Cesium dideuterium phosphate	CsD_2PO_4	Tetragonal (I-42m)
Cesium dihydrogen arsenate	CsH_2AsO_4	Tetragonal (I-42m)
Cesium dihydrogen phosphate	CsH_2PO_4	Tetragonal (I-42m)
Cesium fluoride	CsF	Cubic (Fm3m)
Cesium gadolinium molybdate	$\text{CsGd}(\text{MoO}_4)_2$	Orthorhombic (Pnma)
Cesium gallium sulfate	$\text{CsGa}(\text{SO}_4)_2$	Trigonal (P321)
Cesium germanate	Ga_2GeO_5	Orthorhombic (Pnnm)
Cesium iodide	CsI	Cubic (Fm3m)
Cesium lanthanum tungstate	$\text{CsLa}(\text{WO}_4)_2$	Tetragonal (P4 ₂ /nmc)
Cesium lithium aluminum fluoride	$\text{Cs}_2\text{LiAl}_3\text{F}_{12}$	Rhombohedral (R-3m)
Cesium lithium aluminum fluoride	$\text{Cs}_2\text{LiAlF}_6$	Hexagonal (P6 ₃ /mmc)
Cesium lithium beryllium fluoride	CsLiBeF_4	Monoclinic (P2 ₁ /n)
Cesium lithium borate (CLBO)	$\text{CsLiB}_6\text{O}_{10}$	Tetragonal (I-42d)
Cesium lithium gallium fluoride	$\text{Cs}_2\text{LiGa}_3\text{F}_{12}$	Rhombohedral (R-3m)
Cesium lithium gallium fluoride	$\text{Cs}_2\text{LiGaF}_6$	Hexagonal (P6 ₃ /mmc)
Cesium lithium sulfate	CsLiSO_4	Orthorhombic (Pc2)
Cesium magnesium chloride	Cs_2MgCl_4	Orthorhombic (Pnma)
Cesium mercury iodide	Cs_2HgI_4	Monoclinic (P2 ₁)
Cesium niobium borate (CNB)	CsNbB_2O_6	Orthorhombic (Pn2 ₁ m)
Cesium niobium sulfate	$\text{CsNbO}(\text{SO}_4)_2$	Orthorhombic
Cesium potassium aluminum fluoride	$\text{Cs}_2\text{KAl}_3\text{F}_{12}$	Rhombohedral (R-3m)
Cesium potassium lanthanum fluoride	Cs_2KLaF_6	Cubic (Fm3m)
Cesium scandium molybdate	$\text{CsSc}(\text{MoO}_4)_2$	Trigonal (P-3m1)
Cesium scandium tungstate	$\text{CsSc}(\text{WO}_4)_2$	Trigonal (P-3m1)
Cesium silver fluoride	Cs_2AgF_4	Tetragonal (I4/mmm)
Cesium sodium aluminum fluoride	$\text{Cs}_2\text{NaAl}_3\text{F}_{12}$	Rhombohedral (R-3m)
Cesium sodium aluminum fluoride	$\text{Cs}_2\text{NaAlF}_6$	Rhombohedral (R-3m)
Cesium sodium gallium fluoride	$\text{Cs}_2\text{NaGaF}_6$	Rhombohedral (R-3m)
Cesium sodium yttrium fluoride	Cs_2NaYF_6	Cubic (Fm3m)
Cesium strontium fluoride	CsSrF_3	Cubic (Pm3m)
Cesium tin germanate	$\text{Cs}_2\text{SnGe}_3\text{O}_9$	Hexagonal (P6 ₃ /m)
Cesium titanium germanate	$\text{Cs}_2\text{TiGe}_3\text{O}_9$	Hexagonal (P6 ₃ /m)
Cesium titano arsenate (CTA)	CsTiOAsO_4	Orthorhombic (P2 ₁ nb)
Cesium zinc aluminum fluoride	CsZnAlF_6	Orthorhombic
Cesium zinc bromide	Cs_2ZnBr_4	Orthorhombic (Pnma)
Cesium zinc chloride	Cs_2ZnCl_4	Orthorhombic (Pnma)
Copper bromide (cuprous)	CuBr	Cubic (Fm3m)
Copper chloride (cuprous, nantokite)	CuCl	Cubic (Fm3m)
Copper iodide (cuprous, marshite)	CuI	Cubic (Fm3m)
Cuprous oxide (cuprite)	Cu_2O	Cubic (Pm3m)
Gadolinium aluminate	$\text{Gd}_4\text{Al}_2\text{O}_9$	Monoclinic (P2 ₁ /a)
Gadolinium aluminate	GdAlO_3	Orthorhombic (Pbnm)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Gadolinium aluminum borate	GdAl ₃ (BO ₃) ₄	Trigonal (R32)
Gadolinium aluminum germanate	GdAlGe ₂ O ₇	Monoclinic (P2 ₁ /c)
Gadolinium borate	Gd(BO ₂) ₃	Monoclinic (I2/a)
Gadolinium borate	GdBO ₃	Hexagonal (P6 ₃ /mmc)
Gadolinium calcium oxyborate	GdCa ₄ O(BO ₃) ₃	Monoclinic (Cm)
Gadolinium gallium borate	GdGa ₃ (BO ₃) ₄	Trigonal (R32)
Gadolinium gallium garnet (GGG)	Gd ₃ Ga ₅ O ₁₂	Cubic (Ia3d)
Gadolinium gallium germanate	GdGaGe ₂ O ₇	Monoclinic (P2 ₁ /c)
Gadolinium germanate	Gd ₂ GeO ₅	Monoclinic (P2 ₁ /c)
Gadolinium germanium beryllate	Gd ₂ GeBe ₂ O ₇	Tetragonal (P42 ₁ m)
Gadolinium indate	GdInO ₃	Hexagonal (P6 ₃ cm)
Gadolinium magnesium borate	GdMgB ₅ O ₁₀	Monoclinic (P2 ₁ /c)
Gadolinium molybdate	Gd ₂ (MoO ₄) ₃	Orthorhombic (Pba2)
Gadolinium niobate	GdNbO ₄	Monoclinic (I2/a)
Gadolinium niobate	Gd ₃ NbO ₇	Orthorhombic (C222 ₁)
Gadolinium orthosilicate	Gd ₂ SiO ₅	Monoclinic (P2 ₁ /c)
Gadolinium oxide	Gd ₂ O ₃	Monoclinic (C2/m)
Gadolinium oxymolybdate	Gd ₂ MoO ₆	Monoclinic (I2/c)
Gadolinium oxysulfate	Gd ₂ O ₂ SO ₄	Orthorhombic
Gadolinium oxytungstate	Gd ₂ WO ₆	Monoclinic (I2/c)
Gadolinium pentaphosphate	GdP ₅ O ₁₄	Monoclinic (P2 ₁ /c)
Gadolinium phosphate	GdPO ₄	Monoclinic (P2 ₁ /n)
Gadolinium scandate	GdScO ₃	Orthorhombic (Pbnm)
Gadolinium scandium aluminum garnet (GSAG)	Gd ₃ Sc ₂ Al ₃ O ₁₂	Cubic (Ia3d)
Gadolinium scandium gallium garnet (GSGG)	Gd ₃ Sc ₂ Ga ₃ O ₁₂	Cubic (Ia3d)
Gadolinium strontium borate	Gd ₂ Sr ₃ (BO ₃) ₄	Orthorhombic (P2 ₁ cn)
Gadolinium tantalate	Gd ₃ TaO ₇	Orthorhombic (C222 ₁)
Gadolinium titanate	Gd ₂ Ti ₂ O ₇	Cubic (Fd3m)
Gadolinium tungstate	Gd ₂ (WO ₄) ₃	Monoclinic (C2/c)
Gadolinium vanadate	GdVO ₄	Tetragonal (I4 ₁ /amd)
Gallium antimonide	GaSb	Cubic (F-43m)
Gallium arsenide	GaAs	Cubic (F-43m)
Gallium germanate	α -Ga ₄ GeO ₈	Monoclinic (C2/m)
Gallium molybdate	Ga ₂ (MoO ₄) ₃	Monoclinic (P2 ₁ /a)
Gallium niobate	GaNbO ₄	Monoclinic (C2)
Gallium nitride - wurtzite	α -GaN	Hexagonal(P6 ₃ mc)
Gallium nitride - zincblende	β -GaN	Cubic (F-43m)
Gallium oxide	β -Ga ₂ O ₃	Monoclinic (A2/m)
Gallium phosphate	GaPO ₄	Trigonal (P3 ₁ 2)
Gallium phosphide	GaP	Cubic (F-43m)
Gallium selenide	GaSe	Hexagonal(P-62m)
Gallium sulfide	GaS	Hexagonal(P-62m)
Gallium tungstate	Ga ₂ (WO ₄) ₃	Orthorhombic (Pcna)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Germanium	Ge	Cubic (F-43m)
Germanium oxide (argutite)	GeO ₂	Tetragonal (P4 ₂ /mm)
Hafnium oxide	HfO ₂	Monoclinic (P2 ₁ /c)
Hafnium silicate (hafnon)	HfSiO ₄	Tetragonal (I4 ₁ /amd)
Indium antimonide	InSb	Cubic (F-43m)
Indium arsenide	InAs	Cubic (F-43m)
Indium borate	InBO ₃	Rhombohedral (R-3c)
Indium cadmium borate	InCdBO ₄	Orthorhombic (Pnam)
Indium calcium borate	InCaBO ₄	Orthorhombic (Pnam)
Indium gallate	InGaO ₃	Monoclinic (C2/m)
Indium molybdate	In ₂ (MoO ₄) ₃	Monoclinic (P2 ₁ /a)
Indium niobate	InNbO ₄	Monoclinic (P2/c)
Indium nitride	InN	Hexagonal(P6 ₃ mc)
Indium oxide	In ₂ O ₃	Rhombohedral (R3c)
Indium phosphate	InPO ₄	Orthorhombic (Cmcm)
Indium phosphide	InP	Cubic (F-43m)
Indium tantalate	InTaO ₄	Monoclinic (P2/c)
Indium tungstate	In ₂ (WO ₄) ₃	Orthorhombic (Pcna)
Indium vanadate	InVO ₄	Monoclinic (C2/m)
Iodic acid	HIO ₃	Orthorhombic (P2 ₁ 2 ₁ 2 ₁)
Lanthanum aluminate	LaAlO ₃	Trigonal (R-3m)
Lanthanum aluminum germanate	LaAlGe ₂ O ₇	Monoclinic (P2 ₁ /c)
Lanthanum aluminum germanate	LaAlGe ₂ O ₇	Monoclinic (P2 ₁ /c)
Lanthanum antimonade	LaSbO ₄	Monoclinic (P2 ₁ /c)
Lanthanum antimonade	La ₃ SbO ₇	Orthorhombic (Cmcm)
Lanthanum barium borate	La ₂ Ba ₃ (BO ₃) ₄	Orthorhombic (P2 ₁ cn)
Lanthanum barium gallate	BaLaGa ₃ O ₇	Tetragonal (P42 ₁ m)
Lanthanum barium germanate	LaBaGa ₃ O ₇	Tetragonal (P42 ₁ m)
Lanthanum beryllate (BEL)	La ₂ Be ₂ O ₅	Monoclinic (C2/c)
Lanthanum borate	LaBO ₃	Orthorhombic (Pnam)
Lanthanum boron germanate	LaBGeO ₅	Trigonal (C3m)
Lanthanum boron molybdate	LaBMoO ₆	Monoclinic (P2 ₁)
Lanthanum boron silicate (stillwellite)	LaBSiO ₅	Trigonal (C3m)
Lanthanum boron tungstate	LaBWO ₆	Monoclinic (P2 ₁)
Lanthanum calcium aluminate	LaCaAl ₃ O ₇	Tetragonal (P42 ₁ m)
Lanthanum calcium borate	La ₂ Ca ₃ (BO ₃) ₄	Orthorhombic (P2 ₁ cn)
Lanthanum calcium gallate	LaCaGa ₃ O ₇	Tetragonal (P42 ₁ m)
Lanthanum chloride	LaCl ₃	Hexagonal (P6 ₃ /m)
Lanthanum fluoride (tysonite)	LaF ₃	Trigonal (P-3c1)
Lanthanum gallate	LaGaO ₃	Orthorhombic (Pbnm)
Lanthanum gallium germanate	LaGaGe ₂ O ₇	Monoclinic (P2 ₁ /c)
Lanthanum gallium germanate	La ₃ Ga ₅ GeO ₁₄	Trigonal (P32 ₁)
Lanthanum gallium silicate	La ₃ Ga ₅ SiO ₁₄	Trigonal (P32 ₁)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Lanthanum germanium beryllate	La ₂ GeBe ₂ O ₇	Tetragonal (P42 ₁ m)
Lanthanum indate	LaInO ₃	Orthorhombic (Pbnm)
Lanthanum lutetium gallium garnet (LLGG)	La ₃ Lu ₂ Ga ₃ O ₁₂	Cubic (Ia3d)
Lanthanum magnesium borate	LaMgB ₅ O ₁₀	Monoclinic (P2 ₁ /c)
Lanthanum magnesium hexa-aluminate (LMA)	LaMgAl ₁₁ O ₁₉	Hexagonal (P6 ₃ /mmc)
Lanthanum metaborate	LaB ₃ O ₆	Monoclinic (I2/a)
Lanthanum molbydate	La ₂ (MoO ₄) ₃	Monoclinic (C2/c)
Lanthanum molybdate	La ₂ (MoO ₄) ₃	Tetragonal (I-42m)
Lanthanum niobate	LaNbO ₄	Monoclinic (I2/a)
Lanthanum niobate	LaNb ₅ O ₁₄	Orthorhombic (Pnam)
Lanthanum niobate	La ₃ NbO ₇	Orthorhombic (Cmcm)
Lanthanum niobogallate	La ₃ Nb _{0.5} Ga _{5.5} O ₁₄	Trigonal (P32 ₁)
Lanthanum oxide	La ₂ O ₃	Trigonal (P-3m1)
Lanthanum oxybromide	LaOBr	Tetragonal (P4/nmm)
Lanthanum oxymolybdate	La ₂ MoO ₆	Tetragonal (I-42m)
Lanthanum oxysulfate	La ₂ O ₂ SO ₄	Orthorhombic
Lanthanum oxysulfide	La ₂ O ₂ S	Trigonal (P-3m)
Lanthanum oxytungstate	La ₂ WO ₆	Hexagonal (P6 ₃ /mmc)
Lanthanum pentaphosphate	LaP ₅ O ₁₄	Orthorhombic (Pcmn)
Lanthanum phosphate (monazite)	LaPO ₄	Monoclinic (P2 ₁ /n)
Lanthanum scandate	LaScO ₃	Orthorhombic (Pbnm)
Lanthanum scandium borate	LaSc ₃ (BO ₃) ₄	Monoclinic
Lanthanum silicate	La ₂ SiO ₅	Monoclinic
Lanthanum strontium borate	La ₂ Sr ₃ (BO ₃) ₄	Orthorhombic (P2 ₁ cn)
Lanthanum strontium gallate	LaSrGa ₃ O ₇	Tetragonal (P42 ₁ m)
Lanthanum tantalate	La ₃ TaO ₇	Orthorhombic (Cmcm)
Lanthanum tantalogallate	La ₃ Ta _{0.5} Ga _{5.5} O ₁₄	Trigonal (P32 ₁)
Lanthanum titanate	La ₂ TiO ₅	Orthorhombic (Pnam)
Lanthanum titanate	La ₂ Ti ₂ O ₇	Monoclinic (P2 ₁ /c)
Lanthanum tungstate	La ₂ (WO ₄) ₃	Monoclinic (C2/c)
Lanthanum yttrium tungstate	LaY(WO ₄) ₃	Monoclinic (C2/c)
Lathanium vanadate	LaVO ₄	Monoclinic (P2 ₁ /c)
Lead antimonade	Pb ₂ Sb ₂ O ₇	Cubic (Fd3m)
Lead bismuth niobate	PbBi ₂ Nb ₂ O ₉	Orthorhombic (Fmm2)
Lead bromide	PbBr ₂	Orthorhombic (Pnma)
Lead cadmium niobate	Pb ₃ CdNb ₂ O ₉	Orthorhombic
Lead calcium chloroarsenate (hedyphane)	Pb ₃ Ca ₂ (AsO ₄) ₃ Cl	Hexagonal (P6 ₃ /m)
Lead carbonate (cerussite)	PbCO ₃	Orthorhombic (Pnam)
Lead chloride (cotunnite)	PbCl ₂	Orthorhombic (Pnam)
Lead chloroarsenate (mimetite)	Pb ₅ (AsO ₄) ₃ Cl	Hexagonal (P6 ₃ /m)
Lead chlorophosphate (pyromorphite)	Pb ₅ (PO ₄) ₃ Cl	Hexagonal (P6 ₃ /m)
Lead chlorovanadate (vanadinite)	Pb ₅ (VO ₄) ₃ Cl	Hexagonal (P6 ₃ /m)
Lead fluoride	PbF ₂	Cubic (Fm3m)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Lead fluoroarsenate	Pb ₅ (AsO ₄) ₃ F	Hexagonal (P6 ₃ /m)
Lead fluorophosphate	Pb ₅ (PO ₄) ₃ F	Hexagonal (P6 ₃ /m)
Lead fluorovanadate	Pb ₅ (VO ₄) ₃ F	Hexagonal (P6 ₃ /m)
Lead germanate	PbGeO ₃	Monoclinic (P2 ₁ /a)
Lead germanate	Pb ₃ GeO ₅	Monoclinic (P12)
Lead germanate	Pb ₃ Ge ₃ O ₁₁	Trigonal (P3)
Lead germanate	Pb ₅ Ge ₂ O ₇	Hexagonal
Lead hafnate	PbHfO ₃	Orthorhombic (Pbam)
Lead hexa-aluminate (magnetoplumbite)	PbAl ₁₂ O ₁₉	Hexagonal (P6 ₃ /mmc)
Lead indium niobate	Pb ₂ InNbO ₆	Rhombohedral
Lead iodide	2H-PbI ₂	Trigonal (P3m1)
Lead magnesium niobate	Pb ₃ MgNb ₂ O ₉	Orthorhombic
Lead molybdate (wulfenite)	PbMoO ₄	Tetragonal (I4 ₁ /a)
Lead niobate (changbaiite)	PbNb ₂ O ₆	Orthorhombic (Cm2m)
Lead nitrate	Pb(NO ₃) ₂	Cubic (Pa3)
Lead oxide (litharge)	PbO	Tetragonal (P4/nmm)
Lead oxide (massicot)	PbO	Orthorhombic (Pbcm)
Lead phosphate	Pb ₃ (PO ₄) ₂	Monoclinic (PC2/c)
Lead potassium niobate	Pb ₂ KNb ₅ O ₁₅	Orthorhombic (Im2m)
Lead scandium niobate	Pb ₂ ScNbO ₆	Rhombohedral
Lead selenate (kerstenite)	PbSeO ₄	Orthorhombic (Pnma)
Lead selenide (clausthalite)	PbSe	Cubic (Fm3m)
Lead selenite (molybdomenite)	PbSeO ₃	Monoclinic
Lead silicate (alamosite)	PbSiO ₃	Monoclinic (Pn)
Lead sodium niobate	PbNaNb ₅ O ₁₅	Orthorhombic (Im2a)
Lead sulfate (anglesite)	PbSO ₄	Orthorhombic (Pnma)
Lead sulfide (galena)	PbS	Cubic (Fm3m)
Lead tantalate	PbTa ₂ O ₆	Orthorhombic (Cm2m)
Lead telluride (altaite)	PbTe	Cubic (Fm3m)
Lead titanate (macedonite)	PbTiO ₃	Tetragonal (P4mm)
Lead titanium phosphate	PbTiP ₂ O ₈	Orthorhombic
Lead tungstate (stolzite)	PbWO ₄	Tetragonal (I4 ₁ /a)
Lead vanadate	Pb ₃ (VO ₄) ₂	Monoclinic (P2/c)
Lead vanadate (chervetite)	Pb ₂ V ₂ O ₇	Monoclinic (P21/a)
Lead zinc niobate	Pb ₃ ZnNb ₂ O ₉	Orthorhombic
Lead zinc silicate	Pb ₂ ZnSi ₂ O ₇	Tetragonal (P421m)
Lead zinc silicate (larsenite)	PbZnSiO ₄	Orthorhombic (Pnam)
Lithium aluminate	Li ₅ AlO ₄	Orthorhombic (Pbca)
Lithium aluminate	γ-LiAlO ₂	Tetragonal (P4 ₁ 2 ₁ 2)
Lithium aluminate spinel	LiAl ₅ O ₈	Cubic (P4 ₁ 32)
Lithium aluminum borate	Li ₆ Al ₂ (BO ₃) ₄	Triclinic(P-1)
Lithium aluminum fluorophosphate (amblygonite)	LiAl(PO ₄)F	Triclinic(P-1)
Lithium aluminum germanate	LiAlGe ₂ O ₆	Monoclinic (P21/n)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Lithium aluminum germanate	LiAlGeO ₄	Trigonal(R-3)
Lithium aluminum molybdate	LiAl(MoO ₄) ₂	Triclinic(P-1)
Lithium aluminum silicate	LiAlSi ₂ O ₆	Monoclinic (C2/c)
Lithium aluminum silicate	LiAlSi ₄ O ₁₀	Monoclinic (P2 ₁ /n)
Lithium aluminum silicate (eucryptite)	LiAlSiO ₄	Rhombohedral(R-3)
Lithium aluminum silicate (petalite)	LiAlSi ₄ O ₁₀	Monoclinic (P2 ₁ /n)
Lithium aluminum silicate (spodumene)	LiAlSi ₂ O ₆	Rhombohedral(R-3)
Lithium barium aluminum fluoride (LiBAF)	LiBaAlF ₆	Monoclinic (P2 ₁ /a)
Lithium barium fluoride	LiBaF ₃	Cubic (Pm3m)
Lithium barium gallium fluoride	LiBaGaF ₆	Monoclinic (P2 ₁ /a)
Lithium beryllium fluoride	Li ₂ BeF ₄	Cubic (Fd3m)
Lithium beryllium silicate (liberite)	Li ₂ BeSiO ₄	Monoclinic (Pn)
Lithium borate	LiBO ₂	Monoclinic (P2 ₁ /c)
Lithium borate	LiB ₃ O ₅	Orthorhombic (Pna ₂ ₁)
Lithium bromide	LiBr	Cubic (Fm3m)
Lithium cadmium borate	LiCdBO ₃	Hexagonal (P-6)
Lithium cadmium chloride	Li ₂ CdCl ₄	Cubic (Fd3m)
Lithium cadmium indium fluoride	LiCdInF ₆	Trigonal (P321)
Lithium calcium aluminum fluoride (LiCAF)	LiCaAlF ₆	Trigonal(P-31c)
Lithium calcium gallium fluoride (LiCGaF)	LiCaGaF ₆	Trigonal(P-31c)
Lithium calcium germanate	Li ₂ CaGeO ₄	Tetragonal (I-42m)
Lithium calcium indium fluoride	LiCaInF ₆	Trigonal (P321)
Lithium calcium silicate	Li ₂ CaSiO ₄	Tetragonal (I-42m)
Lithium carbonate (zabuyelite)	Li ₂ CO ₃	Monoclinic (C2/c)
Lithium chloride	LiCl	Cubic (Fm3m)
Lithium fluoride (griceite)	LiF	Cubic (Fm3m)
Lithium gadolinium borate	Li ₃ Gd ₂ (BO ₃) ₃	Monoclinic (P2 ₁ /n)
Lithium gadolinium borate	Li ₆ Gd(BO ₃) ₃	Monoclinic (P2 ₁ /b)
Lithium gadolinium molybdate	LiGd(MoO ₄) ₂	Tetragonal (I4 ₁ /a)
Lithium gadolinium molybdate	LiGd(MoO ₄) ₂	Tetragonal (I4 ₁ /a)
Lithium gadolinium oxide	LiGdO ₂	Orthorhombic (Pnma)
Lithium gadolinium tetrafluoride (GLF)	LiGdF ₄	Tetragonal (I4 ₁ /a)
Lithium gadolinium tetraphosphate	LiGdP ₄ O ₁₂	Monoclinic (I2/c)
Lithium gadolinium tungstate	LiGd(WO ₄) ₂	Tetragonal (I4 ₁ /a)
Lithium gallate	LiGaO ₂	Orthorhombic (Pna ₂ ₁)
Lithium gallate	Li ₅ GaO ₄	Orthorhombic (Pnam)
Lithium gallate spinel	LiGa ₅ O ₈	Cubic (P4 ₁ 32)
Lithium gallium germanate	LiGaGe ₂ O ₆	Monoclinic (P2 ₁ /c)
Lithium gallium germanate	LiGaGe ₂ O ₆	Monoclinic (P2 ₁ /c)
Lithium gallium germanate	LiGaGeO ₄	Trigonal(R-3)
Lithium gallium silicate	LiGaSi ₂ O ₆	Monoclinic (C2/c)
Lithium gallium silicate	LiGaSiO ₄	Rhombohedral(R-3)
Lithium gallium tungstate	LiGa(WO ₄) ₂	Monoclinic (P2/c)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Lithium germanate	Li ₂ GeO ₃	Orthorhombic (Cmc2 ₁)
Lithium indium germanate	LiInGe ₂ O ₆	Orhtorhimbic (Pbca)
Lithium indium molybdate	LiIn(MoO ₄) ₂	Monoclinic (P2 ₁ /c)
Lithium indium oxide	Li ₃ InO ₃	Trigonal (P-3c1)
Lithium indium oxide	LiInO ₂	Tetragonal(I4 ₁ /amd)
Lithium indium silicate	LiInSiO ₄	Orthorhombic (Pnma)
Lithium indium silicate	LiInSi ₂ O ₆	Monoclinic (C2/c)
Lithium indium tungstate	LiIn(WO ₄) ₂	Monoclinic (P2/c)
Lithium iodate	α-LiIO ₃	Hexagonal (P6 ₃)
Lithium iodide	LiI	Cubic (Fm3m)
Lithium lanthanum borate	Li ₃ La ₂ (BO ₃) ₃	Monoclinic (P2 ₁ /n)
Lithium lanthanum molybdate	LiLa(MoO ₄) ₂	Orthorhombic (Pbca)
Lithium lanthanum oxide	LiLaO ₂	Orthorhombic (Pbmm)
Lithium lanthanum tetraphosphate	LiLaP ₄ O ₁₂	Monoclinic (I2/c)
Lithium lanthanum tungstate	LiLa(WO ₄) ₂	Tetragonal (I4 ₁ /a)
Lithium lutetium borate	Li ₆ Lu(BO ₃) ₃	Monoclinic (P2 ₁ /b)
Lithium lutetium fluoride	LiLuF ₄	Tetragonal (I4 ₁ /a)
Lithium lutetium germanate	LiLuGeO ₄	Orthorhombic (Pbcn)
Lithium lutetium oxide	LiLuO ₂	Tetragonal (I4 ₁ /amd)
Lithium lutetium silicate	LiLuSiO ₄	Orthorhombic (Pbcn)
Lithium lutetium tetraphosphate	LiLuP ₄ O ₁₂	Monoclinic (I2/c)
Lithium lutetium tungstate	LiLu(WO ₄) ₂	Monoclinic (P2/c)
Lithium magnesium aluminum fluoride	LiMgAlF ₆	Trigonal (P321)
Lithium magnesium borate	LiMgBO ₃	Monoclinic (C2/c)
Lithium magnesium borate	Li ₂ MgB ₂ O ₅	Monoclinic
Lithium magnesium chloride	Li ₂ MgCl ₄	Cubic (Fd3m)
Lithium magnesium gallium fluoride	LiMgGaF ₆	Tetragonal (P4 ₂ /mmm)
Lithium magnesium germanate	Li ₂ MgGeO ₄	Orthorhombic (Pmn2 ₁)
Lithium magnesium indium fluoride	LiMgInF ₆	Trigonal (P321)
Lithium niobate	LiNbO ₃	Trigonal (R3c)
Lithium phosphate (lithiophosphate)	Li ₃ PO ₄	Orthorhombic
Lithium scandate	LiScO ₂	Tetragonal(I4 ₁ /amd)
Lithium scandium germanate	LiScGeO ₄	Orthorhombic (Pbnm)
Lithium scandium germanate	LiScGe ₂ O ₆	Orthorhombic (Pbca)
Lithium scandium silicate	LiScSiO ₄	Orthorhombic (Pbnm)
Lithium scandium silicate	LiScSi ₂ O ₆	Monoclinic (C2/c)
Lithium scandium tungstate	LiSc(WO ₄) ₂	Monoclinic (P2/c)
Lithium silicate	Li ₂ SiO ₃	Orthorhombic (Cc _m 2 ₁)
Lithium strontium aluminum fluoride (LiSAF)	LiSrAlF ₆	Trigonal(P-31c)
Lithium strontium gallium fluoride (LiSGF)	LiSrGaF ₆	Trigonal(P-31c)
Lithium tantalate (LT)	LiTaO ₃	Trigonal (R3c)
Lithium tetraborate (diomignite)	Li ₂ B ₄ O ₇	Tetragonal (I4 ₁ cd)
Lithium triborate (LBO)	LiB ₃ O ₅	Orthorhombic (Pn2 ₁ a)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Lithium vanadate	LiVO_3	Monoclinic (C2/c)
Lithium vanadate	Li_3VO_4	Orthorhombic ($\text{Pmn}2_1$)
Lithium yttrium borate	$\text{Li}_3\text{Y}_2(\text{BO}_3)_3$	Monoclinic (P2 ₁ /n)
Lithium yttrium borate	$\text{Li}_6\text{Y}(\text{BO}_3)_3$	Monoclinic (P2 ₁ /b)
Lithium yttrium fluoride (YLF)	LiYF_4	Tetragonal (I4 ₁ /a)
Lithium yttrium germanate	LiYGeO_4	Orthorhombic (Pbcn)
Lithium yttrium oxide	LiYO_2	Monoclinic (P2 ₁ /c)
Lithium yttrium silicate	LiYSiO_4	Orthorhombic (Pbcn)
Lithium yttrium tungstate	$\text{LiY(WO}_4)_2$	Monoclinic (P2/c)
Lithium zinc borate	LiZnBO_3	Monoclinic (C2/c)
Lithium zinc indium fluoride	LiZnInF_6	Trigonal (P321)
Lithium zinc niobate	LiZnNbO_4	Tetragonal (P4 ₁ 22)
Lutetium aluminum borate	$\text{LuAl}_3(\text{BO}_3)_3$	Trigonal (R32)
Lutetium aluminum garnet	$\text{Lu}_3\text{Al}_5\text{O}_{12}$	Cubic (Ia3d)
Lutetium borate	LuBO_3	Rhombohedral (R-3c)
Lutetium calcium borate	LuCaBO_4	Orthorhombic (Pnam)
Lutetium gallium garnet	$\text{Lu}_3\text{Ga}_5\text{O}_{12}$	Cubic (Ia3d)
Lutetium molybdate	$\text{Lu}_2(\text{MoO}_4)_3$	Orthorhombic (Pbcn)
Lutetium orthosilicate	Lu_2SiO_5	Monoclinic (C2/c)
Lutetium oxide	Lu_2O_3	Cubic (Ia3)
Lutetium oxymolybdate	Lu_2MO_6	Monoclinic (I2/c)
Lutetium oxysulfate	$\text{Lu}_2\text{O}_2\text{SO}_4$	Orthorhombic
Lutetium oxytungstate	Lu_2WO_6	Monoclinic (P2/c)
Lutetium pentaphosphate	$\text{LuP}_5\text{O}_{14}$	Monoclinic (C2/c)
Lutetium phosphate	LuPO_4	Tetragonal (I4 ₁ /amd)
Lutetium scandate	LuScO_3	Cubic (Ia3)
Lutetium scandium aluminum garnet (LSAG)	$\text{Lu}_3\text{Sc}_2\text{Al}_3\text{O}_{12}$	Cubic (Ia3d)
Lutetium tantalate	LuTaO_4	Monoclinic (P2/a)
Lutetium titanate	$\text{Lu}_2\text{Ti}_2\text{O}_3$	Cubic (Fd3m)
Lutetium tungstate	$\text{Lu}_2(\text{WO}_4)_3$	Orthorhombic (Pcna)
Lutetium vanadate	LuVO_4	Tetragonal (I4 ₁ /amd)
Magnesium aluminate (spinel)	MgAl_2O_4	Cubic (Fd3m)
Magnesium aluminum borate (sinhalite)	MgAlBO_4	Orthorhombic (Pnma)
Magnesium aluminum borosilicate (grandidierite)	$\text{MgAl}_3\text{BSiO}_9$	Orthorhombic
Magnesium aluminum silicate (cordierite)	$\text{Mg}_2\text{Al}_3(\text{Si}_5\text{Al})\text{O}_{18}$	Hexagonal (P6/mcc)
Magnesium aluminum silicate (sapphirine)	$\text{Mg}_4\text{Al}_8\text{Si}_2\text{O}_{20}$	Monoclinic (P2 ₁ /a)
Magnesium aluminum silicate garnet (pyrope)	$\text{Mg}_3\text{Al}_2\text{Si}_3\text{O}_{12}$	Cubic (Ia3d)
Magnesium borate (kotoite)	$\text{Mg}_3\text{B}_2\text{O}_6$	Orthorhombic (Pnma)
Magnesium borate (suanite)	$\text{Mg}_2\text{B}_2\text{O}_5$	Monoclinic
Magnesium carbonate (magnesite)	MgCO_3	Rhombohedral (R-3c)
Magnesium chloroborate (boracite)	$\text{Mg}_3\text{B}_7\text{O}_{13}\text{Cl}$	Orthorhombic
Magnesium fluoride (sellaite, Irtran 1)	MgF_2	Tetragonal (P4 ₂ /mm)
Magnesium fluoroborate	$\text{Mg}_2\text{BO}_3\text{F}$	Orthorhombic

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Magnesium fluoroborate	Mg ₅ (BO ₃) ₃ F	Orthorhombic (P*nb)
Magnesium fluorophosphate (wagnerite)	Mg ₂ PO ₄ F	Monoclinic (P21/a)
Magnesium gallate spinel	MgGa ₂ O ₄	Cubic (Fd3m)
Magnesium gallium borate	MgGaBO ₄	Orthorhombic (Pnam)
Magnesium gallium germanate	Mg ₄ Ga ₈ Ge ₂ O ₂₀	Monoclinic (P2 ₁ /a)
Magnesium germanate	MgGeO ₃	Orthorhombic (Pbca)
Magnesium germanate	Mg ₂ GeO ₄	Orthorhombic (Pnma)
Magnesium molybdate	MgMoO ₄	Monoclinic (C2/m)
Magnesium oxide (periclase, Irtran 5)	MgO	Cubic (Fm3m)
Magnesium phosphate (farringtonite)	Mg ₃ (PO ₄) ₂	Monoclinic
Magnesium pyroarsenate	Mg ₂ As ₂ O ₇	Monoclinic (C2/m)
Magnesium silicate (enstatite)	MgSiO ₃	Monoclinic (P2 ₁ /c)
Magnesium silicate (forsterite)	Mg ₂ SiO ₄	Orthorhombic (Pbcn)
Magnesium titanate	MgTi ₂ O ₅	Orthorhombic (Bbmm)
Magnesium titanate	Mg ₂ TiO ₄	Cubic (Fd3m)
Magnesium titanate (geikielite)	MgTiO ₃	Trigonal(R-3)
Magnesium titanium sulfate	MgTi(SO ₄) ₂	Monoclinic (P2 ₁ /n)
Magnesium titanium borate (warwickite)	Mg ₃ TiB ₂ O ₈	Orthorhombic
Magnesium tungstate	MgWO ₄	Monoclinic (P2/c)
Magnesium vanadate	MgV ₂ O ₆	Orthorhombic (Pbcn)
Magnesium vanadate	MgVO ₃	Monoclinic (Cmc2 ₁)
Magnesium vanadate	Mg ₂ V ₂ O ₇	Monoclinic (C2/m)
Magnesium vanadate	Mg ₃ (VO ₄) ₂	Orthorhombic (Cmca)
Manganese fluoride	MnF ₂	Tetragonal (P4 ₂ /mm)
Manganese oxide (manganosite)	MnO	Cubic (Fm3m)
Mercurous bromide (kuzminite)	Hg ₂ Br ₂	Tetragonal (I4/mmm)
Mercurous chloride (calomel)	Hg ₂ Cl ₂	Tetragonal (I4/mmm)
Mercurous iodide (moschelite)	Hg ₂ I ₂	Tetragonal (I4/mmm)
Mercury antimonade	Hg ₂ Sb ₂ O ₇	Cubic (Fd3m)
Mercury chloride	HgCl ₂	Orthorhombic (Pmnb)
Mercury iodide	HgI ₂	Tetragonal (P4 ₂ /mmc)
Mercury oxide	HgO	Orthorhombic (Pmna)
Mercury peroxide	Hg ₂ O ₂	Monoclinic (C2/m)
Mercury selenide (tiemannite)	HgSe	Cubic (F43m)
Mercury sulfide (cinnabar)	HgS	Trigonal (R32)
Mercury tellurite (coloradoite)	HgTe	Cubic (F43m)
Neodymium calcium aluminum oxide	NdCaAlO ₄	Tetragonal (I4/mmm)
Neodymium gallate	NbGaO ₃	Orthorhombic (Pbnm)
Neodymium yttrium aluminum borate	Nd _x Y _{1-x} Al ₃ (BO ₃) ₄	Trigonal (R32)
Niobium phosphate	NbOPO ₄	Tetragonal (P4/n)
Potassium aluminum borate	K ₂ A ₂ IB ₂ O ₇	Trigonal (P321)
Potassium aluminum fluoride	K ₃ AlF ₆	Cubic (Pm3m)
Potassium aluminum germanate	KAlGeO ₄	Hexagonal (P6 ₃)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Potassium aluminum molybdate	KAl(MoO ₄) ₂	Trigonal (P-3m1)
Potassium aluminum silicate (kaliophilite)	KAlSiO ₄	Hexagonal (P6 ₃)
Potassium aluminum silicate (leucite)	KAlSi ₂ O ₆	Tetragonal (I4 ₁ /a)
Potassium aluminum silicate (orthoclase)	KAlSi ₃ O ₈	Monoclinic (C2/m)
Potassium aluminum silicate hydroxide (mica)	KAl ₃ Si ₃ O ₁₀ •(OH) ₂	Monoclinic
Potassium aluminum sulfate	KAl(SO ₄) ₂	Trigonal (P321)
Potassium aluminum tetrafluoride	KAlF ₄	Tetragonal (P4/mbm)
Potassium beryllium fluoride	K ₂ BeF ₄	Orthorhombic (Pna2 ₁)
Potassium beryllium fluoroborate (KBBF)	KBe ₂ BO ₃ F ₂	Trigonal (R32)
Potassium bismuth niobate	KBiNb ₅ O ₁₅	Tetragonal
Potassium boron fluoride (avogadrite)	KBF ₄	Orthorhombic (Cmcm)
Potassium bromide	KBr	Cubic (Fm3m)
Potassium cadmium fluoride	KCdF ₃	Cubic (Pm3m)
Potassium calcium fluoride	KCaF ₃	Cubic (Pm3M)
Potassium calcium silicate	K ₂ CaSiO ₄	Orthorhombic (Pnmm)
Potassium calcium zirconium silicate (wadeite)	K ₂ CaZr(SiO ₃) ₄	Hexagonal (P6 ₃ m)
Potassium chloride (sylvite)	KCl	Cubic (Fm3m)
Potassium dideuterium phosphate (KDP)	KD ₂ PO ₄	Hexagonal (P6 ₃)
Potassium dihydrogen phosphate (KDP)	KH ₂ PO ₄	Tetragonal (I-42m)
Potassium fluoride (carrobbiite)	KF	Cubic (Fm3m)
Potassium gadolinium niobate	K ₂ GdNb ₅ O ₁₅	Tetragonal
Potassium gadolinium tungstate	KGd(WO ₄) ₂	Monoclinic (C2/c)
Potassium gadolinium vanadate	K ₃ Gd(VO ₄) ₂	Monoclinic (P2 ₁ /m)
Potassium gallium germanate	KGaGeO ₄	Hexagonal (P6 ₃)
Potassium gallium silicate	KGaSi ₃ O ₈	Monoclinic (C2/m)
Potassium gallium silicate	KGaSiO ₄	Hexagonal (P6 ₃)
Potassium indium molybdate	KIn(MoO ₄) ₂	Orthorhombic (Pnam)
Potassium indium tungstate	KIn(WO ₄) ₂	Trigonal (P-3m1)
Potassium iodide	KI	Cubic (Fm3m)
Potassium iodide	KIO ₃	Monoclinic (P1)
Potassium lanthanum molybdate	KLa(MoO ₄) ₄	Tetragonal (I4 ₁ /a)
Potassium lanthanum niobate	K ₂ LaNb ₅ O ₁₅	Tetragonal
Potassium lanthanum phosphate	K ₃ La(PO ₄) ₂	Monoclinic (P2 ₁ /m)
Potassium lanthanum tetraphosphate	KLaP ₄ O ₁₂	Monoclinic (P2 ₁)
Potassium lanthanum tungstate	KLa(WO ₄) ₂	Monoclinic (C2/m)
Potassium lead chloride	KPb ₂ Cl ₅	Monoclinic (P2 ₁ /c)
Potassium lithium beryllium fluoride	KLiBeF ₄	Hexagonal (P-3m1)
Potassium lithium gadolinium fluoride (KLGF)	KLiGdF ₅	Monoclinic (P2 ₁ /c)
Potassium lithium niobate (KLN)	K ₃ Li ₂ Nb ₅ O ₁₅	Tetragonal (P4bm)
Potassium lithium yttrium fluoride (KLYF)	KLiYF ₅	Monoclinic (P21/c)
Potassium lutetium tungstate	KLu(WO ₄) ₄	Monoclinic (C2/c)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Potassium lutetium vanadate	K ₃ Lu(VO ₄) ₄	Monoclinic (P21/m)
Potassium magnesium chloride	K ₂ MgCl ₄	Tetragonal (I4/mmm)
Potassium magnesium fluoride	K ₂ MgF ₄	Tetragonal (I4/mmm)
Potassium magnesium fluoride	KMgF ₃	Cubic (Pm3m)
Potassium magnesium sulfate (langbeinite)	K ₂ Mg ₂ (SO ₄) ₃	Cubic (P2 ₁ 3)
Potassium niobate (KN)	KNbO ₃	Orthorhombic (Amm2)
Potassium niobium borate	KNbB ₂ O ₆	Orthorhombic (Pn2 ₁ m)
Potassium nitrate (nitre)	KNO ₃	Orthorhombic (Pmcn)
Potassium pentaborate	KB ₅ O ₈ *4H ₂ O	Orthorhombic (Aba2)
Potassium scandium molybdate	KSc(MoO ₄) ₂	Tetragonal (P-3m1)
Potassium scandium tungstate	KSc(WO ₄) ₂	Trigonal (P-3m1)
Potassium scandium vanadate	KSc(VO ₄) ₂	Trigonal
Potassium sodium aluminum fluoride (elpasolite)	K ₂ NaAlF ₆	Cubic (Fm3m)
Potassium sodium gallium fluoride	K ₂ NaGaF ₆	Cubic (Fm3m)
Potassium sodium lithium niobate	KNaLi ₂ Nb ₅ O ₁₅	Trigonal
Potassium sodium lithium niobate	K ₂ NaLi ₂ Nb ₅ O ₁₅	Tetragonal (P4bm)
Potassium strontium sulfate (kalistrontite)	K ₂ Sr(SO ₄) ₂	Trigonal
Potassium tantalate	KTaO ₃	Cubic (Pm-3m)
Potassium tantalum borate	KTaB ₂ O ₆	Orthorhombic (Pmm)
Potassium tin germanate	K ₂ SnGe ₃ O ₉	Trigonal (P-3c1)
Potassium tin silicate	K ₂ SnSi ₃ O ₉	Hexagonal (P6 ₃ /m)
Potassium titanium germanate	K ₂ TiGe ₃ O ₉	Trigonal (P-3c1)
Potassium titanium niobate	KTiNbO ₅	Orthorhombic (Pnma)
Potassium titanium niobate	KTi ₃ NbO ₉	Orthorhombic (Pnmm)
Potassium titanoarsenate (KTA)	KTiOAsO ₄	Orthorhombic (P2 ₁ nb)
Potassium titanophosphate (KTP)	KTiOPO ₄	Orthorhombic (P2 ₁ nb)
Potassium titanium silicate	K ₂ TiSi ₃ O ₉	Hexagonal (P6 ₃ /m)
Potassium vanadate	KVO ₃	Orthorhombic (Pmab)
Potassium yttrium fluoride	KY ₃ F ₁₀	Cubic (Fm3m)
Potassium yttrium molybdate	KY(MoO ₄) ₂	Orthorhombic (Pbna)
Potassium yttrium niobate	K ₂ YNb ₅ O ₁₅	Tetragonal
Potassium yttrium tetrafluoride (KYF)	KYF ₄	Trigonal (P3 ₁)
Potassium yttrium tungstate	KY(WO ₄) ₂	Monoclinic (C2/c)
Potassium yttrium vanadate	K ₃ Y(VO ₄) ₂	Monoclinic
Potassium zinc fluoride	K ₂ ZnF ₄	Tetragonal (I4/mmm)
Potassium zinc fluoride	KZnF ₃	Tetragonal
Rubidium aluminum selenate	RbAl(SeO ₄) ₂	Trigonal (P321)
Rubidium aluminum silicate	RbAlSiO ₄	Orthorhombic (Pcmn)
Rubidium aluminum silicate	RbAlSi ₂ O ₆	Tetragonal (I4 ₁ /a)
Rubidium aluminum sulfate	RbAl(SO ₄) ₂	Trigonal (P321)
Rubidium aluminum tetrafluoride	RbAlF ₄	Tetragonal (P4/mmm)
Rubidium beryllium fluoride	Rb ₂ BeF ₄	Orthorhombic (Pna ₂ ₁)
Rubidium bismuth molybdate	RbBi(MoO ₄) ₂	Monoclinic (P2 ₁ /c)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Rubidium bromide	RbBr	Cubic (Fm3m)
Rubidium cadmium fluoride	RbCdF ₃	Cubic (Pm3m)
Rubidium calcium fluoride	RbCaF ₃	Cubic (Pm3m)
Rubidium chloride	RbCl	Cubic (Fm3m)
Rubidium dihydrogen arsenate (RDA)	RbH ₂ AsO ₄	Tetragonal (I4 ₁ /a)
Rubidium dihydrogen phosphate (RDP)	RbH ₂ PO ₄	Tetragonal ((I-42m)
Rubidium fluoride	RbF	Cubic (Fm3m)
Rubidium gadolinium bromide	RbGd ₂ Br ₇	Orthorhombic (Pnma)
Rubidium gadolinium vanadate	Rb ₃ Gd(VO ₄) ₂	Trigonal
Rubidium gadolinium vanadate	RbGd(VO ₄) ₂	Tetragonal (P4/mmm)
Rubidium gallium selenate	RbGa(SeO ₄) ₂	Trigonal (P321)
Rubidium gallium sulfate	RbGa(SO ₄) ₂	Trigonal (P321)
Rubidium indium molybdate	RbIn(MoO ₄) ₂	Trigonal (P321)
Rubidium indium tungstate	RbIn(WO ₄) ₂	Trigonal (P321)
Rubidium iodide	RbI	Cubic (Fm3m)
Rubidium lanthanum niobate	Rb ₂ LaNb ₅ O ₁₅	Tetragonal
Rubidium lanthanum tungstate	RbLa(WO ₄) ₂	Monoclinic (C2/c)
Rubidium lithium aluminum fluoride	Rb ₂ LiAlF ₆	Rhombohedral (R-3m)
Rubidium lithium gallium fluoride	Rb ₂ LiGaF ₆	Rhombohedral (R-3m)
Rubidium lutetium vanadate	Rb ₃ Lu(VO ₄) ₂	Trigonal
Rubidium lutetium vanadate	RbLu(VO ₄) ₂	Trigonal
Rubidium magnesium chloride	Rb ₂ MgCl ₄	Tetragonal (I4/mmm)
Rubidium magnesium fluoride	Rb ₂ MgF ₄	Tetragonal (I4/mmm)
Rubidium niobium borate	RbNbB ₂ O ₆	Orthorhombic (Pn2 ₁ m)
Rubidium pentaborate	RbB ₅ O ₈ •4H ₂ O	Orthorhombic (Aba2)
Rubidium potassium gallium fluoride	Rb ₂ KGaF ₆	Cubic (Fm3m)
Rubidium scandium molybdate	RbSc(MoO ₄) ₂	Trigonal (P-3m1)
Rubidium scandium tungstate	RbSc(WO ₄) ₂	Trigonal (P-3m1)
Rubidium scandium vanadate	Rb ₃ Sc(VO ₄) ₂	Trigonal
Rubidium scandium vanadate	RbSc(VO ₄) ₂	Trigonal
Rubidium sodium beryllium fluoride	Rb ₃ NaBeF ₈	Hexagonal (P6 ₃)
Rubidium sodium indium fluoride	Rb ₂ NaInF ₆	Cubic (Fm3m)
Rubidium tantalum borate	RbTaB ₂ O ₆	Orthorhombic (Pn2 ₁ m)
Rubidium tin germanate	Rb ₂ SnGe ₃ O ₉	Trigonal (P-3c1)
Rubidium tin silicate	Rb ₂ SnSi ₃ O ₉	Hexagonal (P6 ₃ /m)
Rubidium titanium germanate	Rb ₂ TiGe ₃ O ₉	Trigonal (P-3c1)
Rubidium titanium silicate	Rb ₂ TiSi ₃ O ₉	Hexagonal (P6 ₃ /m)
Rubidium titano arsenate (RTA)	RbTiOAsO ₄	Orthorhombic (P2 ₁ nb)
Rubidium titano phosphate (RTP)	RbTiOPO ₄	Orthorhombic (P2 ₁ nb)
Rubidium yttrium vanadate	Rb ₃ Y(VO ₄) ₂	Trigonal
Rubidium yttrium vanadate	RbY(VO ₄) ₂	Trigonal
Rubidium zinc bromide	Rb ₂ ZnBr ₄	Orthorhombic (Pnma)
Rubidium zinc chloride	Rb ₂ ZnCl ₄	Orthorhombic (Pnma)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Rubidium zinc fluoride	Rb ₂ ZnF ₄	Tetragonal (I4/mmm)
Rubidium zinc fluoride	RbZnF ₃	Cubic (Pm3m)
Scandium aluminum beryllate (SCAB)	ScAlBeO ₄	Orthorhombic (Pmcn)
Scandium borate	ScBO ₃	Rhombohedral (R-31)
Scandium calcium borate	ScCaBO ₄	Orthorhombic (Pnam)
Scandium gallate	ScGaO ₃	Monoclinic (A2/m)
Scandium germanate	Sc ₂ GeO ₅	Monoclinic (B2/b)
Scandium magnesium borate	ScMgBO ₄	Orthorhombic (Pnam)
Scandium metaphosphate	Sc(PO ₃) ₃	Monoclinic (Cc)
Scandium molybdate	Sc ₂ (MoO ₄) ₃	Orthorhombic (Pbcn)
Scandium niobate	ScNbO ₄	Monoclinic (P2/c)
Scandium orthosilicate	Sc ₂ SiO ₅	Monoclinic (I2/a)
Scandium oxide	Sc ₂ O ₃	Cubic (I213)
Scandium phosphate	ScPO ₄	Tetragonal (I4 ₁ /amd)
Scandium silicate	Sc ₂ Si ₂ O ₇	Monoclinic (C2/m)
Scandium tantalate	ScTaO ₄	Monoclinic (P2/c)
Scandium titanate	Sc ₂ TiO ₅	Orthorhombic (Bbmm)
Scandium tungstate	Sc ₂ (WO ₄) ₃	Orthorhombic (Pcna)
Scandium vanadate	ScVO ₄	Tetragonal (I4 ₁ /amd)
Scandium yttrium silicate (thortveitite)	(Sc,Y) ₂ Si ₂ O ₇	Monoclinic (C2/m)
Selenium	Se	Trigonal (32)
Selenium dioxide (downeyite)	SeO ₂	Tetragonal (P4 ₂ /nbc)
Silicon	Si	Cubic (F-43m)
Silicon carbide (carborundum, moissanite)	α-SiC (2H)	Hexagonal (P6 ₃ /m)
Silicon carbide	β-SiC (3C)	Cubic (Fd3m)
Silicon dioxide (α-quartz)	SiO ₂	Trigonal (P3 ₁ 2)
Silicon nitride	Si ₃ N ₄	Hexagonal (P6 ₃ /m)
Silver antimony sulfide (pyrargyrite)	Ag ₃ SbS ₃	Trigonal (R3c)
Silver arsenic selenide	Ag ₃ AsSe ₃	Trigonal (R3c)
Silver arsenic sulfide (proustite)	Ag ₃ AsS ₃	Trigonal (R3c)
Silver arsenic sulfide (trechmannite)	AgAsS ₂	Tetragonal (I-42d)
Silver bromide (bromyrite)	AgBr	Cubic (Fm3m)
Silver chloride (cerargyrite)	AgCl	Cubic (Fm3m)
Silver gallium selenide	AgGaSe ₂	Tetragonal (I-42d)
Silver gallium sulfide	AgGaS ₂	Tetragonal (I-42d)
Silver iodide (iodargyrite)	AgI	Hexagonal (P6 ₃ mc)
Silver mercury iodide	Ag ₂ HgI ₄	Tetragonal (I-4)
Sodium aluminum borate	Na ₂ Al ₂ B ₂ O ₇	Tetragonal (I-42d)
Sodium aluminum chlorosilicate (sodalite)	Na ₈ Al ₆ Si ₆ O ₂₄ Cl ₂	Cubic
Sodium aluminum fluoride (chiolite)	Na ₅ Al ₃ F ₁₄	Tetragonal (P4/mnc)
Sodium aluminum fluoride (cryolite)	Na ₃ AlF ₆	Monoclinic (P2 ₁ /n)
Sodium aluminum fluoroarsenate (durangite)	NaAl(AsO ₄)F	Monoclinic (C2/c)
Sodium aluminum fluorophosphate (lacroixite)	NaAl(PO ₄)F	Monoclinic

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Sodium aluminum germanate	NaAlGeO ₄	Monoclinic (P2 ₁ /n)
Sodium aluminum silicate (albite)	NaAlSi ₃ O ₈	Triclinic (P-1)
Sodium aluminum silicate (nepheline)	NaAlSiO ₄	Hexagonal (P6 ₃)
Sodium antimony beryllate (swedenburgite)	NaSbBe ₄ O ₇	Hexagonal (P6 ₃ mc)
Sodium barium phosphate	NaBaPO ₄	Hexagonal (P-3m1)
Sodium barium titanium silicate (batisite)	Na ₂ BaTi ₂ Si ₄ O ₁₄	Orthorhombic
Sodium beryllium fluoride	Na ₂ BeF ₄	Monoclinic (P2 ₁ /n)
Sodium beryllium fluoroborate	NaBe ₂ BO ₃ F ₂	Trigonal (R32)
Sodium beryllium phosphate (beryllonite)	NaBePO ₄	Monoclinic (P2 ₁ /n)
Sodium beryllium silicate (chkalovite)	Na ₂ BeSi ₂ O ₆	Orthorhombic (Fd _{ddd})
Sodium beryllium silicate	Na ₂ BeSiO ₄	Orthorhombic (Pca2 ₁)
Sodium bismuth magnesium vanadate	Na ₂ BiMg ₂ V ₃ O ₁₂	Cubic (Ia3d)
Sodium bismuth zinc vanadate	Na ₂ BiZn ₂ V ₃ O ₁₂	Cubic (Ia3d)
Sodium boron fluoride (ferruccite)	NaBF ₄	Orthorhombic (Cmcm)
Sodium bromide	NaBr	Cubic (Fm3m)
Sodium cadmium magnesium fluoride	NaCdMg ₂ F ₇	Cubic (Fd3m)
Sodium cadmium phosphate	NaCdPO ₄	Orthorhombic (Pnma)
Sodium cadmium zinc fluoride	NaCdZn ₂ F ₇	Cubic (Fd3m)
Sodium calcium fluorophosphate (arctite)	Na ₂ Ca ₄ (PO ₄) ₃ F	Trigonal
Sodium calcium fluorophosphate (nacaphte)	Na ₂ CaPO ₄ F	Orthorhombic
Sodium calcium magnesium phosphate (brianite)	Na ₂ CaMg(PO ₄) ₂	Orthorhombic
Sodium calcium phosphate (bushwaldite)	NaCaPO ₄	Orthorhombic (Pnam)
Sodium calcium silicate	Na ₂ CaSiO ₄	Cubic (Fm3m)
Sodium calcium silicate (combeite)	Na ₂ Ca ₂ Si ₃ O ₉	Trigonal (P3 ₁ 22 ₁)
Sodium calcium yttrium fluoride (α -gagarinite)	α -NaCaYF ₆	Hexagonal
Sodium carbonate (natrite)	Na ₂ CO ₃	Hexagonal (P6 ₃ mc)
Sodium chloride (halite)	NaCl	Cubic (Fm3m)
Sodium fluoride (villiaumite)	NaF	Cubic (Fm3m)
Sodium gadolinium arsenate	Na ₃ Gd(AsO ₄) ₂	Monoclinic (Cc)
Sodium gadolinium germanate	NaGdGeO ₄	Orthorhombic (Pbn2 ₁)
Sodium gadolinium germanate	Na ₅ GdGe ₄ O ₁₂	Trigonal (R32)
Sodium gadolinium magnesium vanadate	Na ₂ GdMg ₂ V ₃ O ₁₂	Cubic (Ia3d)
Sodium gadolinium molybdate	NaGd(MoO ₄) ₂	Tetragonal (I4 ₁ /a)
Sodium gadolinium oxide	NaGdO ₂	Tetragonal (I4 ₁ /amd)
Sodium gadolinium phosphate	Na ₃ Gd(PO ₄) ₂	Monoclinic
Sodium gadolinium pyrophosphate	NaGdP ₂ O ₇	Monoclinic
Sodium gadolinium silicate	NaGdSiO ₄	Orthorhombic (Pbn2 ₁)
Sodium gadolinium silicate	Na ₃ GdSi ₃ O ₉	Orthorhombic (P2 ₁ 2 ₁ 2 ₁)
Sodium gadolinium silicate	Na ₅ GdSi ₄ O ₁₂	Trigonal (R32)
Sodium gadolinium tetraphosphate	NaGdP ₄ O ₁₂	Monoclinic (P2 ₁ /n)
Sodium gadolinium tungstate	NaGd(WO ₄) ₂	Tetragonal (I4 ₁ /a)
Sodium gadolinium vanadate	Na ₃ Gd(VO ₄) ₂	Monoclinic (Cc)
Sodium gallium borate	Na ₂ Ga ₂ B ₂ O ₇	Tetragonal

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Sodium gallium germanate	NaGaGeO ₄	Monoclinic (P2 ₁ /n)
Sodium gallium germanate	NaGaGe ₂ O ₆	Monoclinic (C2/c)
Sodium gallium silicate	NaGaSiO ₄	Monoclinic (P2 ₁ /n)
Sodium germanate	Na ₂ GeO ₃	Orthorhombic (Cmc2 ₁)
Sodium indate	NaInO ₂	Rhombohedral (R3/m)
Sodium indium germanate	Na ₃ InGe ₄ O ₁₂	Trigonal (R32)
Sodium indium molybdate	NaIn(MoO ₄) ₂	Triclinic (P-1)
Sodium indium silicate	Na ₅ InSi ₄ O ₁₂	Trigonal (R32)
Sodium iodide	NaI	Cubic (Fm3m)
Sodium lanthanum arsenate	Na ₃ La(AsO ₄) ₂	Orthorhombic (Pbc2 ₁)
Sodium lanthanum borate	Na ₃ La(BO ₃) ₂	Monoclinic (P2 ₁ /c)
Sodium lanthanum borate	Na ₃ La ₂ (BO ₃) ₃	Orthorhombic (Amm2)
Sodium lanthanum borate	Na ₁₈ La(BO ₃) ₇	Monoclinic
Sodium lanthanum molybdate	NaLa(MoO ₄) ₂	Tetragonal (I4 ₁ /a)
Sodium lanthanum oxide	NaLaO ₂	Tetragonal (I4 ₁ /amd)
Sodium lanthanum phosphate	Na ₃ La(PO ₄) ₂	Orthorhombic (Pbc2 ₁)
Sodium lanthanum pyrophosphate	NaLaP ₂ O ₇	Orthorhombic
Sodium lanthanum tetraphosphate	NaLaP ₄ O ₁₂	Monoclinic (P2 ₁ /n)
Sodium lanthanum tungstate	NaLa(WO ₄) ₂	Tetragonal (I4 ₁ /a)
Sodium lanthanum vanadate	Na ₃ La(VO ₄) ₂	Orthorhombic (Pbc2 ₁)
Sodium lithium aluminum borosilicate (elbaite)	Na(Li,Al) ₃ Al ₆ (BO ₃) ₃ -Si ₆ O ₁₈ (OH)	Trigonal (R3m)
Sodium lithium aluminum fluoride	Na ₂ LiAlF ₆	Monoclinic (P2 ₁ /n)
Sodium lithium aluminum fluorogarnet	Na ₃ Li ₃ Al ₂ F ₁₂	Cubic (Ia3d)
Sodium lithium gallium fluorogarnet (GFG)	Na ₃ Li ₃ Ga ₂ F ₁₂	Cubic (Ia3d)
Sodium lithium indium fluorogarnet	Na ₃ Li ₃ In ₂ F ₁₂	Cubic (Ia3d)
Sodium lithium niobate	Na ₃ Li ₂ Nb ₅ O ₁₅	Tetragonal (P4bm)
Sodium lithium scandium fluorogarnet	Na ₃ Li ₃ Sc ₂ F ₁₂	Cubic (Ia3d)
Sodium lithium vanadate	NaLiV ₂ O ₆	Monoclinic (C2/c)
Sodium lithium yttrium silicate	Na ₂ LiYSi ₆ O ₁₅	Orthorhombic (Cmca)
Sodium lithium zirconium silicate (Zektzerite)	Na ₂ LiZrSi ₆ O ₁₅	Orthorhombic (Cmca)
Sodium lutetium arsenate	Na ₃ Lu(AsO ₄) ₂	Monoclinic (Cc)
Sodium lutetium germanate	NaLuGeO ₄	Orthorhombic (Pbn2 ₁)
Sodium lutetium germanate	Na ₅ LuGe ₄ O ₁₂	Trigonal (R32)
Sodium lutetium magnesium vanadate	Na ₂ LuMg ₂ V ₃ O ₁₂	Cubic (Ia3d)
Sodium lutetium oxide	NaLuO ₂	Tetragonal(I4 ₁ /amd)
Sodium lutetium phosphate	Na ₃ Lu(PO ₄) ₂	Monoclinic
Sodium lutetium pyrophosphate	NaLuP ₂ O ₇	Monoclinic
Sodium lutetium silicate	NaLuSiO ₄	Orthorhombic (Pbcn)
Sodium lutetium silicate	Na ₅ LuSi ₄ O ₁₂	Trigonal (R32)
Sodium lutetium vanadate	Na ₃ Lu(VO ₄) ₂	Monoclinic (P2 ₁ /n)
Sodium magnesium aluminum fluoride (weberite)	NaMgAlF ₇	Orthorhombic (Imm2)
Sodium magnesium carbonate (eitelite)	Na ₂ Mg(CO ₃) ₂	Trigonal (R-3)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Sodium magnesium fluoride (neighborite)	NaMgF ₃	Orthorhombic (Pcmm)
Sodium magnesium gallium fluoride	NaMgGaF ₇	Orthorhombic (Imm2)
Sodium magnesium indium fluoride	NaMgInF ₇	Orthorhombic (Imm2)
Sodium magnesium scandium fluoride	NaMgScF ₇	Orthorhombic (Imm2)
Sodium magnesium silicate	Na ₂ MgSiO ₄	Monoclinic
Sodium niobate (natroniobite)	NaNbO ₃	Orthorhombic (Pbma)
Sodium nitrate (soda-nitre)	NaNO ₃	Trigonal (R-3c)
Sodium potassium titanoniobosilicate	Na ₂ KTiNbSi ₄ O ₁₄	Orthorhombic
Sodium scandium germanate	NaScGeO ₄	Orthorhombic (Pbnm)
Sodium scandium germanate	NaScGe ₂ O ₆	Monoclinic (C2/m)
Sodium scandium germanate	Na ₅ ScGe ₄ O ₁₂	Trigonal (R32)
Sodium scandium indium vanadate	Na ₃ Sc _{1.5} In _{0.5} V ₃ O ₁₂	Cubic (Ia3d)
Sodium scandium oxide	NaScO ₂	Rhombohedral (R3/m)
Sodium scandium silicate	Na ₃ ScSi ₂ O ₇	Orthorhombic (Pbcn)
Sodium scandium silicate	Na ₅ ScSi ₄ O ₁₂	Trigonal (R32)
Sodium scandium silicate (jervisite)	NaScSi ₂ O ₆	Monoclinic (C2/c)
Sodium scandium vanadate	Na ₃ Sc ₂ V ₃ O ₁₂	Cubic (Ia3d)
Sodium silicate	Na ₂ SiO ₃	Orthorhombic (Cmc2 ₁)
Sodium silicate (natrosilite)	Na ₂ Si ₂ O ₅	Monoclinic(P21/a)
Sodium strontium aluminum fluoride	NaSrAlF ₆	Orthorhombic (Pna ₂ 1)
Sodium strontium aluminum fluoride (jarllite)	NaSr ₃ Al ₃ F ₁₆	Monoclinic
Sodium strontium phosphate	Na ₂ Sr(PO ₄) ₂	Tetragonal (P4/nbm)
Sodium tantalate	NaTaO ₃	Orthorhombic (Pbma)
Sodium titanium silicate (lorenzenite)	Na ₂ Ti ₂ Si ₂ O ₉	Orthorhombic (Pnca)
Sodium titanium silicate (natisite)	Na ₂ TiOSiO ₄	Tetragonal (P4/nmm)
Sodium vanadate	NaVO ₃	Monoclinic (C2/c)
Sodium yttrium fluoride	5NaF–9YF ₃	Cubic (Ia3d)
Sodium yttrium fluorosilicate	Na ₅ Y ₄ (SiO ₄) ₄ F	Rhombohedral (R-3)
Sodium yttrium germanate	NaYGeO ₄	Orthorhombic (Pbn ₂ 1)
Sodium yttrium germanate	Na ₅ YG ₄ O ₁₂	Trigonal (R32)
Sodium yttrium magnesium vanadate	Na ₂ YMg ₂ V ₃ O ₁₂	Cubic (Ia3d)
Sodium yttrium molybdate	NaY(MoO ₄) ₂	Tetragonal (I4 ₁ /a)
Sodium yttrium oxide	NaYO ₂	Monoclinic (P2 ₁ /c)
Sodium yttrium silicate	NaYSiO ₄	Orthorhombic (Pbcn)
Sodium yttrium silicate	Na ₃ YSi ₃ O ₉	Orthorhombic (P2 ₁ 2 ₁ 2 ₁)
Sodium yttrium silicate	Na ₃ YSi ₂ O ₇	Hexagonal (P6 ₃ /m)
Sodium yttrium silicate	Na ₅ YSi ₄ O ₁₂	Trigonal (R32)
Sodium yttrium tetrafluoride	NaYF ₄	Trigonal (P3 ₁)
Sodium zinc chloride	NaZnF ₃	Orthorhombic (Pnmc)
Sodium zinc fluoride	Na ₂ ZnCl ₄	Orthorhombic (Pnma)
Strontium aluminate	SrAl ₂ O ₄	Monoclinic (P2 ₁ /n)
Strontium aluminate	SrAl ₄ O ₇	Monoclinic (C2/c)
Strontium aluminate	Sr ₃ Al ₂ O ₆	Cubic (Pa3)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Strontium aluminum fluoride	SrAlF ₅	Tetragonal (P4)
Strontium aluminum germanate	SrAl ₂ Ge ₂ O ₈	Monoclinic (P2 ₁ /a)
Strontium aluminum silicate	SrAl ₂ Si ₂ O ₈	Monoclinic (P2 ₁ /a)
Strontium aluminum silicate	Sr ₂ Al ₂ SiO ₇	Tetragonal (P42 ₁ m)
Strontium barium niobate (SBN)	Sr _{0.6} Ba _{0.4} Nb ₂ O ₆	Tetragonal
Strontium borate	SrB ₂ O ₄	Orthorhombic (Pnca)
Strontium borate	SrB ₄ O ₇	Orthorhombic (Pbca)
Strontium borate	Sr ₃ B ₂ O ₆	Rhombohedral (R-3c)
Strontium bromovanadate	Sr ₂ VO ₄ Br	Orthorhombic (Pbcm)
Strontium carbonate (strontianite)	SrCO ₃	Orthorhombic (Pnam)
Strontium chloroarsenate	Sr ₂ AsO ₄ Cl	Orthorhombic (Pbcm)
Strontium chloroarsenate	Sr ₅ (AsO ₄) ₃ Cl	Hexagonal(P6 ₃ /m)
Strontium chloraborate	Sr ₂ B ₅ O ₉ Cl	Tetragonal (P4 ₂ 2 ₁ 2)
Strontium chlorophosphate	Sr ₅ (PO ₄) ₃ Cl	Hexagonal(P6 ₃ /m)
Strontium chlorovanadate	Sr ₂ VO ₄ Cl	Orthorhombic (Pbcm)
Strontium chlorovanadate	Sr ₅ (VO ₄) ₃ Cl	Hexagonal(P6 ₃ /m)
Strontium fluoride	SrF ₂	Cubic (Fm3m)
Strontium fluoroarsenate	Sr ₅ (AsO ₄) ₃ F	Hexagonal(P6 ₃ /m)
Strontium fluorophosphate (SFAP)	Sr ₅ (PO ₄) ₃ F	Hexagonal(P6 ₃ /m)
Strontium fluorovanadate (SVAP)	Sr ₅ (VO ₄) ₃ F	Hexagonal(P6 ₃ /m)
Strontium gadolinium aluminate	SrGdAlO ₄	Tetragonal (I4/mmm)
Strontium gadolinium gallate (SGGM)	SrGdGa ₃ O ₇	Tetragonal (P42 ₁ m)
Strontium gadolinium phosphate	Sr ₃ Gd(PO ₄) ₃	Cubic (I-43d)
Strontium gadolinium oxide	SrGd ₂ O ₄	Orthorhombic (Pnma)
Strontium gallate	SrGa ₂ O ₄	Monoclinic (P2 ₁ /n)
Strontium gallium fluoride	SrGaF ₅	Tetragonal (P4)
Strontium gallium germanate	Sr ₃ Ga ₂ Ge ₄ O ₁₄	Trigonal (P32 ₁)
Strontium gallium silicate	SrGa ₂ Si ₂ O ₈	Monoclinic (P2 ₁ /a)
Strontium gallium silicate	Sr ₂ Ga ₂ SiO ₇	Tetragonal (P42 ₁ m)
Strontium hexa-aluminate	SrAl ₁₂ O ₁₉	Hexagonal (P6 ₃ /mmc)
Strontium indium germanium garnet	Sr ₃ In ₂ Ge ₃ O ₁₂	Cubic (Ia3d)
Strontium indium oxide	SrIn ₂ O ₄	Orthorhombic (Pnma)
Strontium lanthanum aluminate	SrLaAlO ₄	Tetragonal (I4/mmm)
Strontium lanthanum borate	SrLaBO ₄	Hexagonal (P6 ₃ 22)
Strontium lanthanum gallate	SrLaGaO ₄	Tetragonal (I4/mmm)
Strontium lanthanum oxysilicate	SrLa ₄ (SiO ₄) ₃ O	Hexagonal (P6 ₃ /m)
Strontium lanthanum phosphate	Sr ₃ La(PO ₄) ₃	Cubic (I-43d)
Strontium lutetium oxide	SrLu ₂ O ₄	Orthorhombic (Pnma)
Strontium magnesium germanate	Sr ₂ MgGe ₂ O ₇	Tetragonal (P42 ₁ m)
Strontium magnesium silicate	Sr ₂ MgSi ₂ O ₇	Tetragonal (P42 ₁ m)
Strontium magnesium vanadate	SrMg ₂ (VO ₄) ₂	Tetragonal (I4 ₁ /acd)
Strontium molybdate	SrMoO ₄	Tetragonal (I4 ₁ /a)
Strontium niobate	SrNb ₂ O ₆	Orthorhombic (Pcan)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Strontium niobate	Sr ₂ Nb ₂ O ₇	Orthorhombic (Cmc2 ₁)
Strontium niobate	Sr ₅ Nb ₄ O ₁₅	Monoclinic (P2 ₁ /m)
Strontium niobate	SrNb ₂ O ₆	Monoclinic (P2 ₁ /c)
Strontium potassium niobate	Sr ₂ KNb ₅ O ₁₅	Orthorhombic (Im2a)
Strontium potassium tantalate	Sr ₂ KTa ₅ O ₁₅	Orthorhombic (Im2a)
Strontium scandate	SrSc ₂ O ₄	Orthorhombic (Pnam)
Strontium scandium germanium garnet	Sr ₃ Sc ₂ Ge ₃ O ₁₂	Cubic (Ia3d)
Strontium silicate	SrSiO ₃	Monoclinic (C2)
Strontium sodium niobate	Sr ₂ NaNb ₅ O ₁₅	Orthorhombic (Im2a)
Strontium sulfate (celestite)	SrSO ₄	Orthorhombic (Pmma)
Strontium tantalate	Sr ₂ Ta ₂ O ₇	Orthorhombic (Pnma)
Strontium tin borate	SrSnB ₂ O ₆	Trigonal (R-3)
Strontium tin oxide	SrSnO ₃	Cubic (P2 ₁ 3)
Strontium titanate	Sr ₃ Ti ₂ O ₇	Tetragonal (I4/mmm)
Strontium titanate (tausonite)	SrTiO ₃	Cubic (Pm3m)
Strontium titanium borate	SrTiB ₂ O ₆	Trigonal (R-3)
Strontium tungstate	SrWO ₄	Tetragonal (I4 ₁ /a)
Strontium vanadate	SrV ₂ O ₆	Monoclinic (C2/m)
Strontium vanadate	β-Sr ₂ V ₂ O ₇	Tetragonal (I4 ₁ /amd)
Strontium vanadate	Sr ₃ (VO ₄) ₂	Rhombohedral (R-3m)
Strontium vanadate	β-Sr ₂ V ₂ O ₇	Tetragonal (P4 ₁)
Strontium vanadate	SrVO ₃	Cubic (Pm3m)
Strontium yttrium borate	Sr ₃ Y(BO ₃) ₃	Trigonal (R-3)
Strontium yttrium oxide	SrY ₂ O ₄	Orthorhombic (Pnma)
Strontium yttrium oxysilicate	SrY ₄ (SiO ₄) ₃ O	Hexagonal (P6 ₃ /m)
Strontium zinc fluoride	SrZnF ₄	Tetragonal (I4 ₁ /a)
Strontium zinc germanate	SrZnGe ₂ O ₆	Monoclinic (C2/c)
Strontium zinc germanate	Sr ₂ ZnGe ₂ O ₇	Tetragonal (P42 ₁ m)
Strontium zinc silicate	Sr ₂ ZnSi ₂ O ₇	Tetragonal (P42 ₁ m)
Strontium zirconate	SrZrO ₃	Orthorhombic (Pnma)
Strontium zirconium borate	SrZrB ₂ O ₆	Trigonal (R-3)
Strontium tantalate	SrTa ₂ O ₆	Orthorhombic (Pcan)
Strontium tantalate	Sr ₂ Ta ₂ O ₇	Orthorhombic (Cmcm)
Strontium tantalate	Sr ₅ Ta ₄ O ₁₅	Hexagonal
Strontium tantalate	Sr ₆ Ta ₂ O ₁₁	Cubic
Tantalum borate (behierite)	TaBO ₄	Tetragonal (I4 ₁ /amd)
Tantalum oxide (tantite)	Ta ₂ O ₅	Orthorhombic (P2mm)
Tantalum oxyphosphate	TaOPO ₄	Tetragonal (P4/n)
Tellurium	Te	Trigonal (32)
Tellurium oxide (tellurite)	TeO ₂	Orthorhombic (Pbca)
Thallium aluminum selenate	TlAl(SeO ₄) ₂	Trigonal (P321)
Thallium aluminum sulfate	TlAl(SO ₄) ₂	Trigonal (P321)
Thallium aluminum tetrafluoride	TlAlF ₄	Tetragonal (P4/mmm)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Thallium arsenic selenide	Tl ₃ AsSe ₃	Trigonal (R3c)
Thallium arsenic sulfide (ellisite)	Tl ₃ AsS ₃	Trigonal (R3c)
Thallium bromide	TlBr	Cubic (Fm3m)
Thallium bromoiodide (KRS-5)	Tl(Br,I)	Cubic (Fm3m)
Thallium chloride	TlCl	Cubic (Fm3m)
Thallium chlorobromide (KRS-6)	Tl(Cl,Br)	Cubic (Fm3m)
Thallium gallium selenate	TlGa(SeO ₄) ₂	Trigonal (P321)
Thallium gallium sulfate	TlGa(SO ₄) ₂	Trigonal (P321)
Thallium niobium borate	TlNbB ₂ O ₆	Orthorhombic (Pn2 ₁ m)
Thallium oxide (avicennite)	Tl ₂ O ₃	Cubic (Ia3d)
Thallium tantalum borate	TlTaB ₂ O ₆	Orthorhombic (Pn2 ₁ m)
Thallium tin germanate	Tl ₂ SnGe ₃ O ₉	Trigonal (P-3c1)
Thallium titanium germanate	Tl ₂ TiGe ₃ O ₉	Hexagonal (P6 ₃ /m)
Thorium oxide (thorianite)	ThO ₂	Cubic (Fm3m)
Thorium silicate (thorite)	ThSiO ₄	Tetragonal (I4 ₁ /amd)
Tin dioxide (cassiterite)	SnO ₂	Tetragonal (P4 ₂ /mm)
Titanium dioxide (rutile)	TiO ₂	Tetragonal (P4 ₂ /mm)
Tourmaline (elbaite)	Na(Li,Al) ₃ Al ₆ (BO ₃) ₃ -Si ₆ O ₁₈ (OH)	Trigonal (R3m)
Urea	(NH ₂) ₂ CO	Tetragonal (I-42m)
Vanadium oxide (shcherbinaite)	V ₂ O ₅	Orthorhombic (Pmmm)
Yttrium aluminate	Y ₄ Al ₂ O ₉	Monoclinic (P2 ₁ /a)
Yttrium aluminate (YAP, YALO)	YAlO ₃	Orthorhombic (Pnma)
Yttrium aluminum borate (YAB)	YAl ₃ (BO ₃) ₄	Trigonal (R32)
Yttrium aluminum garnet (YAG)	Y ₃ Al ₅ O ₁₂	Cubic (Ia3d)
Yttrium antimonade	Y ₃ SbO ₇	Orthorhombic (C222 ₁)
Yttrium arsenate (chernovite)	YAsO ₄	Tetragonal (I4 ₁ /amd)
Yttrium beryllate	YBeBO ₄	Monoclinic (C2/c)
Yttrium beryllium aluminate	Y ₂ BeAl ₂ O ₇	Tetragonal (P42 ₁ m)
Yttrium borate	YBO ₃	Hexagonal (P6 ₃ /mmc)
Yttrium calcium aluminate	YCaAl ₃ O ₇	Tetragonal (P42 ₁ m)
Yttrium calcium gallium beryllium silicate	YCaGaBe ₂ Si ₂ O ₁₀	Monoclinic (P2 ₁ /c)
Yttrium calcium oxyborate	YCa ₄ O(BO ₃) ₃	Monoclinic (Cm)
Yttrium chlorosilicate	Y ₃ (SiO ₄) ₂ Cl	Orthorhombic (Pnma)
Yttrium fluoride	YF ₃	Orthorhombic (Pnma)
Yttrium gadolinium antimonade	Y ₂ GdSbO ₇	Orthorhombic (C222 ₁)
Yttrium gadolinium niobate	YGd ₂ NbO ₇	Orthorhombic (C222 ₁)
Yttrium gadolinium tantalate	Y ₂ GdTaO ₇	Orthorhombic (C222 ₁)
Yttrium gallium borate	YGa ₃ (BO ₃) ₄	Trigonal (R32)
Yttrium gallium garnet (YGG)	Y ₃ Ga ₅ O ₁₂	Cubic (Ia3d)
Yttrium germanate	Y ₂ GeO ₅	Monoclinic (P2 ₁ /c)
Yttrium germanium beryllate	Y ₂ GeBe ₂ O ₇	Tetragonal (P42 ₁ m)
Yttrium hafnium tantalate	YHfTaO ₆	Orthorhombic

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Yttrium indate	YInO ₃	Hexagonal (P6 ₃ cm)
Yttrium indium gallium garnet	Y ₃ In ₂ Ga ₃ O ₁₂	Cubic (Ia3d)
Yttrium iron garnet (YAG)	Y ₃ Fe ₅ O ₁₂	Cubic (Ia3d)
yttrium lithium fluoride (YLF)	LiYF ₄	Tetragonal (I4 ₁ /a)
Yttrium magnesium beryllium silicate (gadolinite)	Y ₂ MgBe ₂ Si ₂ O ₁₀	Monoclinic (P2 ₁ /c)
Yttrium molybdate	Y ₂ (MoO ₄) ₃	Orthorhombic (Pbcn)
Yttrium niobate (fergusonite)	YNbO ₄	Monoclinic (C2/c)
Yttrium orthosilicate (YOS, YSO)	Y ₂ SiO ₅	Monoclinic (C2/c)
Yttrium oxide (yttria)	Y ₂ O ₃	Cubic (Ia3)
Yttrium oxychloride	YOCl	Rhombohedral (R-3m)
Yttrium molybdate	Y ₂ Mo ₂ O ₇	Cubic (Fd3m)
Yttrium oxymolybdate	Y ₂ MoO ₆	Monoclinic (I2/c)
Yttrium oxysulfate	Y ₂ OS ₂	Monoclinic (P2 ₁ /c)
Yttrium oxytungstate	Y ₂ WO ₆	Monoclinic (P2/c)
Yttrium pentaphosphate	YP ₅ O ₁₄	Orthorhombic (Pcmn)
Yttrium phosphate (xenotime)	YPO ₄	Tetragonal (I4 ₁ /amd)
Yttrium scandate	YScO ₃	Orthorhombic (Pbnm)
Yttrium scandium aluminum garnet (YSAG)	Y ₃ Sc ₂ Al ₃ O ₁₂	Cubic (Ia3d)
Yttrium scandium gallium garnet (YSGG)	Y ₃ Sc ₂ Ga ₃ O ₁₂	Cubic (Ia3d)
Yttrium silicate (keiviite)	Y ₂ Si ₂ O ₇	Monoclinic (C2/m)
Yttrium silicon beryllate	Y ₂ SiBe ₂ O ₇	Tetragonal (P4 ₂ 1m)
Yttrium tantalate	Y ₃ TaO ₇	Orthorhombic (C222 ₁)
Yttrium tantalate (formanite)	YTaO ₄	Monoclinic (P2/a)
Yttrium titanate	Y ₂ Ti ₂ O ₇	Cubic (Fd3m)
Yttrium titanium silicate (trimounsite)	Y ₂ Ti ₂ SiO ₉	Monoclinic
Yttrium titanium tantalate	YTiTaO ₆	Orthorhombic (Pbcn)
Yttrium tungstate	Y ₂ (WO ₄) ₃	Orthorhombic (Pcna)
Yttrium vanadate (wakefieldite)	YVO ₄	Tetragonal (I4 ₁ /amd)
Yttrium zinc beryllium silicate	Y ₂ ZnBe ₂ Si ₂ O ₁₀	Monoclinic (P2 ₁ /c)
Zinc aluminate (gahnite)	ZnAl ₂ O ₄	Cubic (Fd3m)
Zinc antimonate (ordonezite)	ZnSb ₂ O ₆	Tetragonal (P4 ₂ /mm)
Zinc arsenate	ZnAsO ₄	Monoclinic (P2 ₁ /c)
Zinc arsenide (reinerite)	Zn ₃ (AsO ₃) ₂	Orthorhombic (Pbam)
Zinc borate	Zn ₃ (BO ₃) ₂	Monoclinic (P2/c)
Zinc borate	ZnB ₄ O ₇	Orthorhombic (Pbca)
Zinc borate	Zn ₄ B ₆ O ₁₃	Cubic (I-43m)
Zinc carbonate (smithsonite)	ZnCO ₃	Rhombohedral (R-3c)
Zinc chloride	ZnCl ₂	Tetragonal (P4 ₂ /mnmm)
Zinc fluoride	ZnF ₂	Tetragonal (P4 ₂ /mnmm)
Zinc gallate	ZnGa ₂ O ₄	Cubic (Fd3m)
Zinc germanate	Zn ₂ GeO ₄	Tetragonal (I4 ₁ 22)
Zinc germanium arsenide	ZnGeAs ₂	Tetragonal (I-42d)
Zinc germanium phosphide	ZnGeP ₂	Tetragonal (I-42d)

Name, Formula, Crystal System, and Space Group for Optical Crystals—continued

Name	Formula	Crystal system (Space group)
Zinc oxide (zincite)	ZnO	Hexagonal (6mm)
Zinc pyroarsenide	Zn ₂ As ₂ O ₇	Monoclinic (C2/m)
Zinc selenide (stilleite, Irtran 4)	ZnSe	Cubic (Fm3m)
Zinc silicate (willemite)	Zn ₂ SiO ₄	Trigonal (R-3)
Zinc silicon arsenide	ZnSiAs ₂	Tetragonal (I-42d)
Zinc silicon phosphide	ZnSiP ₂	Tetragonal (I-42d)
Zinc sulfide (sphalerite, Irtran 2, zincblende)	β-ZnS	Cubic (Fm3m)
Zinc sulfide (wurtzite)	α-ZnS	Hexagonal (P6mm)
Zinc telluride	ZnTe	Cubic (Fm3m)
Zinc tin antimonide	ZnSnSb ₂	Tetragonal (I-42d)
Zinc tin arsenide	ZnSnAs ₂	Tetragonal (I-42d)
Zinc tin phosphide	ZnSnP ₂	Tetragonal (I-42d)
Zinc tungstate	ZnWO ₄	Monoclinic (P2/c)
Zinc vanadate	ZnV ₂ O ₆	Monoclinic (C2)
Zirc silicon arsenate	ZnSiAs ₂	Cubic (F-43m)
Zirconium oxide	ZrO ₂	Tetragonal (P4 ₂ /nmc)
Zirconium oxide (cubic zirconia, CZ)	ZrO ₂ :0.12Y ₂ O ₃	Cubic (Fm3m)
Zirconium silicate (zircon)	ZrSiO ₄	Tetragonal (I4 ₁ /amd)

1.2 Physical Properties*

Physical properties of optical crystals in this section are grouped into three tables: isotropic crystals, uniaxial crystals, and biaxial crystals. Materials are listed alphabetically in order of the chemical formulas. The following properties are included:

Density: Data are for room temperature.

Hardness: This is an empirical and relative measure of a material's resistance to wear. Average Knoop (indentation test) hardness numbers or range of values at room temperature are given when available. In many cases only Vicker (V) or Mohs hardness are known. This is indicated parentheses after the value. The hardness of a crystal varies with orientation even for cubic symmetry crystals.

Cleavage: The ease of cleavage varies greatly depending on the crystal quality and the nature and direction of stress applied. In many crystals there can be more than one set of cleavage planes. Miller indices are used to denote the cleavage planes. The actual number of cleavage planes depends on the plane orientation relative to the symmetry of the crystal. Only the easiest cleavage plane for each crystal is listed. They are ranked qualitatively as perfect (p) or imperfect (i). A crystal listed with a perfect cleavage plane can crack along that direction with a smooth surface if a stress is applied. The imperfect cleavage plane means that the crack does not easily move along the plane, although a small area of oriented flat surfaces may form along the cracking surface when the crystal is fractured.

Solubility: Solubility is defined as the weight loss in grams per 100 grams of water. The dissolution temperature in °C is included in parentheses, if given. If the solubility is less than 10^{-3} g/100 g, the material is generally considered to be insoluble. If a crystal is listed as insoluble, it means that, when submerged in water with a reasonable amount of time (a day or so), no noticeable loss of weight nor visible surface erosion of the crystal is observed.

* This section was adapted from "Optical Crystals" by B. H. T. Chai, *Handbook of Laser Science and Technology, Suppl. 2, Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 30 ff (with additions).

1.2.1 Isotropic Crystals

Physical Properties of Isotropic Crystalline Materials

Cubic material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
AgBr	6.473	7	None	1.2×10^{-5} (20)
AgCl	5.56	9.5	None	1.5×10^{-4} (20)
AlAs	3.729	—	(111)-p	Insoluble
Al ₂₃ O ₂₇ N ₅ (ALON)	3.713	1850	—	Insoluble
AlP	2.40	—	—	Slightly soluble
AlSb	4.26	—	—	
As ₂ O ₃	3.87	1.5 (Mohs)	(111)	Soluble
Ba(NO ₃) ₂	3.24	—	None	Soluble
Ba ₂ Zr ₂ Si ₃ O ₁₂	—	—	—	Insoluble
Ba ₃ Al ₂ O ₆	5.008	—	—	—

Physical Properties of Isotropic Crystalline Materials—*continued*

Cubic material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
Ba ₃ MgTa ₂ O ₉	6.435	—	—	Insoluble
BaF ₂	4.83	82(500)	(111)-p	0.12
BaF ₂ -CaF ₂	4.89	—	(111)-p	0.16
Bi ₁₂ GeO ₂₀	9.22	4.5(Mohs)	None	Insoluble
Bi ₁₂ SiO ₂₀	9.20	—	None	Insoluble
Bi ₁₂ TiO ₂₀	9.069	—	None	Insoluble
Bi ₄ Ge ₃ O ₁₂	7.13	5.0 (Mohs)	None	Insoluble
Bi ₄ Si ₃ O ₁₂	6.60	4.5 (Mohs)	(110)-i	Insoluble
BN	3.48	4600	(111)	Insoluble
BP	2.97	3600	—	Insoluble
C (diamond)	3.51	5700–10400	(111)	Insoluble
Ca ₁₂ Al ₁₄ O ₃₃	2.68	—	None	Insoluble
Ca ₂ LiMg ₂ V ₃ O ₁₂	3.447	—	—	—
Ca ₂ LiZn ₂ V ₃ O ₁₂	3.726	—	—	—
Ca ₂ NaMg ₂ V ₃ O ₁₂	3.414	—	—	—
Ca ₂ NaZn ₂ V ₃ O ₁₂	3.976	—	—	—
Ca ₂ Sb ₂ O ₇	—	—	None	Insoluble
Ca ₃ Al ₂ Ge ₃ O ₁₂	4.357	—	None	Insoluble
Ca ₃ Al ₂ Si ₃ O ₁₂	3.60	7 (Mohs)	None	Insoluble
Ca ₃ Ga ₂ Ge ₃ O ₁₂	4.837	—	None	Insoluble
Ca ₃ Gd(PO ₄) ₃	3.900	—	—	Insoluble
Ca ₃ In ₂ Ge ₃ O ₁₂	5.063	—	None	Insoluble
Ca ₃ La(PO ₄) ₃	3.678	—	—	Insoluble
Ca ₃ Lu ₂ Ge ₃ O ₁₂	5.668	—	None	Insoluble
Ca ₃ Sc ₂ Ge ₃ O ₁₂	4.203	—	None	Insoluble
Ca ₃ Sc ₂ Si ₃ O ₁₂	3.514	—	None	Insoluble
CaF ₂	3.180	158	(111)-p	1.6 × 10 ⁻³ (18)
CaLa ₂ S ₄	4.524	570	—	—
CaO	3.3	3.5	(100)-p	0.13(10)
CaTiO ₃	3.98	—	—	Insoluble
CaY ₂ Mg ₃ Ge ₃ O ₁₂	—	—	None	Insoluble
Cd ₂ Nb ₂ O ₇	6.216	—	None	Insoluble
Cd ₂ Sb ₂ O ₇	—	—	None	Insoluble
Cd ₃ Sc ₂ Ge ₃ O ₁₂	5.749	—	None	Insoluble
CdB ₂ O ₄	4.58	—	—	—
CdF ₂	6.64	—	(111)-p	4.4 (20)
CdGa ₂ O ₄	—	—	None	Insoluble
CdIn ₂ O ₄	7.00	—	None	—
CdO	8.24	3 (Mohs)	(111)	—
CdTe	6.20	56	(110)-p	Very slightly soluble
Cs ₂ KLaF ₆	3.95	—	None	Slightly soluble
Cs ₂ NaYF ₆	4.397	—	None	Slightly soluble
CsBr	4.44	19.5	None	124 (25)

Physical Properties of Isotropic Crystalline Materials—*continued*

Cubic material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
CsCaF ₃	4.123	—	—	Slightly soluble
CsCdF ₃	5.62	—	—	—
CsCl	3.9	—	None	186 (20)
CsF	4.638	—	(100)-p	367 (18)
CsI	4.510	1–2 (Mohs)	None	44 (0)
CsSrF ₃	4.299	—	—	—
Cu ₂ O	6.11	3.5 (Mohs)	(111)-i	Insoluble
CuBr	4.77	21	—	Very slightly soluble
CuCl	4.14	2.5 (Mohs)	(110)-p	6.1 × 10 ⁻³
CuI	5.68	2.5 (Mohs)	(110)-p	—
GaAs	5.316	721	(111)-p	<5 × 10 ⁻³ (25)
GaP	4.13	—	(111)-p	Insoluble
GaSb	5.619	—	(111)-p	Insoluble
Gd ₂ Ti ₂ O ₇	6.52	1114	None	Insoluble
Gd ₃ Ga ₅ O ₁₂	7.02	6.5–7 (Mohs)	None	Insoluble
Gd ₃ Sc ₂ Al ₃ O ₁₂	5.82	7.5 (Mohs)	None	Insoluble
Gd ₃ Sc ₂ Ga ₃ O ₁₂	—	7.0 (Mohs)	None	Insoluble
Ge	5.35	800	(111)	Insoluble
Hg ₂ Sb ₂ O ₇	—	—	None	Insoluble
HgSe	8.266	—	—	Insoluble
HgTe	—	—	—	—
InAs	5.66	330	(111)-p	Insoluble
InP	4.8	430	(111)-p	Insoluble
InSb	5.78	225	(111)-p	Insoluble
K ₂ Mg ₂ (SO ₄) ₃	2.83	3.5 (Mohs)	None	Slightly soluble
K ₂ NaAlF ₆	2.99	2.5 (Mohs)	None	Slightly soluble
K ₂ NaGaF ₆	3.34	—	None	Slightly soluble
K ₃ AlF ₆	—	—	None	Soluble
KBr	2.75	7.0(200)	(100)-p	65.2 (20)
KCaF ₃	2.709	—	—	—
KCdF ₃	4.264	—	—	—
KCl	1.984	9.3(200)	(100)-p	34.7 (20)
KF	2.48	2 (Mohs)	(100)-p	92.3 (18)
KI	3.12	5	(100)-p	144 (20)
KMgF ₃	3.15	2.5 (Mohs)	None	Insoluble
KTaO ₃	7.015	—	—	Insoluble
KY ₃ F ₁₀	4.312	4.5 (Mohs)	None	Insoluble
La ₃ Lu ₂ Ga ₃ O ₁₂	—	7.0 (Mohs)	None	Insoluble
Li ₂ BeF ₄	2.289	—	—	—
Li ₂ CdCl ₄	2.956	—	—	—
Li ₂ MgCl ₄	2.119	—	—	—
LiAl ₅ O ₈	3.625	—	None	Insoluble
LiBaF ₃	5.242	—	—	—

Physical Properties of Isotropic Crystalline Materials—*continued*

Cubic material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
LiBr	3.464	—	(100)-p	145 (4)
LiCl	2.068	—	(100)-p	63.7 (0)
LiF	2.635	110 (600)	(100)-p	0.27 (18)
LiGa ₅ O ₈	5.819	—	None	Insoluble
LiI	4.076	—	(100)-p	168 (20)
Lu ₂ O ₃	9.426	—	—	—
Lu ₂ Ti ₂ O ₇	7.31	1264	None	Insoluble
Lu ₃ Al ₅ O ₁₂	6.695	7.5 (Mohs)	None	Insoluble
Lu ₃ Ga ₅ O ₁₂	7.828	7.0 (Mohs)	None	Insoluble
Lu ₃ Sc ₂ Ga ₃ O ₁₂	—	7.0 (Mohs)	None	Insoluble
LuScO ₃	—	—	—	Insoluble
Mg ₂ TiO ₄	3.546	—	—	Insoluble
Mg ₃ Al ₂ Si ₃ O ₁₂	3.58	7.5 (Mohs)	None	Insoluble
MgAl ₂ O ₄	3.58	1140 (1000)	None	Insoluble
MgGa ₂ O ₄	5.37	7.0 (Mohs)	None	Insoluble
MgO	3.58	690 (600)	(100)-p	6.2 × 10 ⁻⁴
MnO	5.44	5.5 (Mohs)	(100)-p	Insoluble
Na ₂ BiMg ₂ V ₃ O ₁₂	4.388	—	—	—
Na ₂ BiZn ₂ V ₃ O ₁₂	4.919	—	—	—
Na ₂ CaSiO ₄	2.821	—	—	Insoluble
Na ₂ GdMg ₂ V ₃ O ₁₂	4.115	—	—	—
Na ₂ LuMg ₂ V ₃ O ₁₂	4.332	—	—	—
Na ₂ YMg ₂ V ₃ O ₁₂	3.668	—	—	—
Na ₃ Li ₃ Al ₂ F ₁₂	2.77	2 (Mohs)	(011)-i	—
Na ₃ Li ₃ Ga ₂ F ₁₂	3.20	2 (Mohs)	None	—
Na ₃ Li ₃ In ₂ F ₁₂	3.54	2 (Mohs)	None	—
Na ₃ Li ₃ Sc ₂ F ₁₂	2.66	2 (Mohs)	None	—
Na ₃ Sc ₂ V ₃ O ₁₂	3.342	—	—	—
Na ₈ Al ₆ Si ₆ O ₂₄ Cl ₂	2.27	5.5 (Mohs)	(110)-i	Insoluble
NaBr	3.203	—	(100)-p	91 (20)
NaCdMg ₂ F ₇	3.968	—	—	—
NaCdZn ₂ F ₇	4.838	—	—	—
NaCl	2.165	18 (200)	(100)-p	39.8 (0)
NaF	2.588	60	(100)-p	4.2 (18)
5NaF-9YF ₃	4.22	2 (Mohs)	None	Insoluble
NaI	3.667	—	(100)-p	179 (20)
Pb(NO ₃) ₂	4.530	—	—	—
Pb ₂ Sb ₂ O ₇	—	—	None	Insoluble
PbF ₂	8.24	200	(111)-p	0.064 (20)
PbS	7.5	2.5–2.75 (Mohs)	(100)-p	6.6 × 10 ⁻⁵
PbSe	8.10	—	(100)-p	Insoluble
PbTe	8.164	—	(100)-p	Insoluble
Rb ₂ KGaF ₆	3.751	—	None	—

Physical Properties of Isotropic Crystalline Materials—*continued*

Cubic material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
Rb ₂ NaInF ₆	4.302	—	None	—
RbBr	3.35	—	(100)-p	98 (5)
RbCaF ₃	3.632	—	—	—
RbCl	2.80	—	(100)-p	77 (0)
RbF	—	—	(100)-p	367 (18)
RbI	3.55	1.0 (Mohs)	(100)-p	152 (17)
RbZnF ₃	5.007	—	—	—
Sb ₂ O ₃	5.50	2–2.5 (Mohs)	(111)-i	Insoluble
Sc ₂ O ₃	3.840	—	—	Insoluble
Si	2.33	1150	(111)	Insoluble
β-SiC	3.214	2880	—	Insoluble
β-SiC (CVD)	3.21	2540	—	Insoluble
Sr ₃ Al ₂ O ₆	4.136	—	—	—
Sr ₃ Gd(PO ₄) ₃	—	—	—	Insoluble
Sr ₃ In ₂ Ge ₃ O ₁₂	5.632	—	None	Insoluble
Sr ₃ La(PO ₄) ₃	—	—	—	Insoluble
Sr ₃ Sc ₂ Ge ₃ O ₁₂	4.838	—	None	Insoluble
Sr ₆ Nb ₂ O ₁₁	5.0	—	—	Insoluble
Sr ₆ Ta ₂ O ₁₁	6.088	—	—	Insoluble
SrF ₂	4.24	130	(111)-p	0.012 (20)
SrSnO ₃	6.432	—	—	Insoluble
SrTiO ₃	5.122	595	None	Insoluble
SrVO ₃	5.46	—	—	—
ThO ₂	9.86	600	None	Insoluble
Tl(Br,I)	7.371	40 (500)	None	—
Tl(Cl,Br)	7.192	39 (500)	None	<0.32 (20)
Tl ₂ O ₃	10.35	—	—	Insoluble
TlBr	7.557	12 (500)	None	0.05 (25)
TlCl	7.604	13 (500)	None	0.32 (20)
Y ₂ O ₃	5.01	875	—	1.8 × 10 ⁻⁵ (20)
Y ₂ Ti ₂ O ₇	4.987	1099	None	Insoluble
Y ₃ Al ₅ O ₁₂	4.56	135 (200)	None	Insoluble
Y ₃ Ga ₅ O ₁₂	5.79	7.0 (Moh)	None	Insoluble
Y ₃ In ₂ Ga ₃ O ₁₂	6.03	—	None	Insoluble
Y ₃ Sc ₂ Al ₃ O ₁₂	4.55	—	None	Insoluble
Y ₃ Sc ₂ Ga ₃ O ₁₂	5.184	7.0 (Moh)	None	Insoluble
Zn ₄ B ₆ O ₁₃	4.19	—	—	—
ZnAl ₂ O ₄	4.62	7.5 (Moh)	None	Insoluble
ZnGa ₂ O ₄	6.089	7.0 (Moh)	None	Insoluble
β-ZnS	4.09	178	(110)-p	6.9 × 10 ⁻⁴ (18)
β-ZnS (CVD)	4.04	178	—	—
ZnSe	5.42	137	(110)-p	0.001(25)
ZnSiAs ₂	4.747	—	—	Insoluble

Physical Properties of Isotropic Crystalline Materials—*continued*

Cubic material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
ZnTe	6.34	82	(110)-p	Insoluble
ZrO ₂	5.64	990	None	Insoluble

1.2.2 Uniaxial Crystals

Physical Properties of Uniaxial Crystalline Materials

Uniaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
Ag ₂ HgI ₄	6.091	—	—	—
Ag ₃ AsS ₃	5.49	2–2.5 (Mohs)	(10\u2081\u2081)	Insoluble
Ag ₃ AsSe ₃	6.521	—	—	Insoluble
Ag ₃ SbS ₃	5.82	2.5 (Mohs)	(10\u2081\u2081)-i	Insoluble
AgAsS ₂	—	—	—	Insoluble
AgGaS ₂	4.702	—	(112)-p	Insoluble
AgGaSe ₂	5.70	—	(112)-p	Insoluble
AgI	5.7	1.5 (Mohs)	(0001)-p	Insoluble
Al ₂ O ₃	3.98	1370 (1000)	None	9.8 × 10 ⁻⁵
AlAsO ₄	3.359	—	—	Insoluble
AlF ₃	3.192	—	—	—
AlGaO ₃	4.78	—	(0001)-p	Insoluble
AlN	3.261	—	—	Insoluble
AlPO ₄	2.566	5 (Mohs)	None	Insoluble
AlTiTaO ₆	6.26	—	—	Insoluble
Ba ₂ B ₅ O ₉ Cl	3.762	—	—	Insoluble
Ba ₂ MgAlF ₉	4.157	—	—	—
Ba ₂ MgF ₆	5.08	—	—	Insoluble
Ba ₂ MgGe ₂ O ₇	4.79	—	(001)	Insoluble
Ba ₂ MgSi ₂ O ₇	4.265	—	(001)	Insoluble
Ba ₂ Sc ₄ O ₉	5.372	—	—	Insoluble
Ba ₂ TiSi ₂ O ₈	4.43	3.80	(001)-i	Insoluble
Ba ₂ ZnF ₆	5.514	—	—	Insoluble
Ba ₂ ZnGe ₂ O ₇	—	—	(001)	Insoluble
Ba ₂ ZnSi ₂ O ₇	—	—	(001)	Insoluble
Ba ₂ ZrSi ₂ O ₈	—	—	—	Insoluble
Ba ₃ (VO ₄) ₂	5.176	—	—	—
Ba ₃ Sc ₄ O ₉	5.318	—	—	Insoluble
Ba ₃ SrNb ₂ O ₉	—	—	—	Insoluble
Ba ₃ SrTa ₂ O ₉	—	—	—	Insoluble
Ba ₅ (AsO ₄) ₃ F	5.073	—	(10\u2081\u2081)-i	Insoluble

Physical Properties of Uniaxial Crystalline Materials—*continued*

Uniaxial material	Density (g/cm³)	Hardness (kg/mm²)	Cleavage plane	Solubility (°C) (g/100 g H₂O)
Ba ₅ (AsO ₄) ₃ Cl	5.086	4.5 (Mohs)	(0001)-i	Insoluble
Ba ₅ (PO ₄) ₃ Cl	4.802	—	—	Insoluble
Ba ₅ (PO ₄) ₃ F	4.81	—	(10 ₁ 1)-i	Insoluble
Ba ₅ (VO ₄) ₃ Cl	4.728	—	(10 ₁ 1)-i	Insoluble
Ba ₅ (VO ₄) ₃ F	4.766	—	(10 ₁ 1)-i	Insoluble
Ba ₆ Sc ₆ O ₁₅	5.115	—	—	Insoluble
BaAl ₁₂ O ₁₉	4.075	—	—	Insoluble
BaAl ₂ O ₄	4.080	—	—	Insoluble
β-BaB ₂ O ₄	3.85	4 (Mohs)	(0001)-i	Slightly soluble
BaBe(PO ₄)F	4.31	—	None	Insoluble
BaGe ₄ O ₉	—	—	None	Insoluble
BaMg ₂ (VO ₄) ₂	4.226	—	—	—
BaMoO ₄	4.946	—	—	—
BaSb ₂ O ₆	—	—	—	—
BaSnB ₂ O ₆	4.848	—	—	Insoluble
BaSnSi ₃ O ₉	4.03	6 (Mohs)	None	Insoluble
BaTiB ₂ O ₆	4.211	—	—	Insoluble
BaTiO ₃	6.02	5 (Mohs)	—	Insoluble
BaTiSi ₃ O ₉	3.64	6 (Mohs)	None	Insoluble
BaWO ₄	6.383	—	—	Insoluble
BaZnGeO ₄	5.12	—	—	Insoluble
BaZnSiO ₄	4.706	—	—	Insoluble
BaZrSi ₃ O ₉	3.85	—	None	Insoluble
Be ₂ GeO ₄	3.893	—	None	Insoluble
Be ₂ SiO ₄	2.96	1100	(10 ₁ 0)	Insoluble
Be ₃ Al ₂ Si ₆ O ₁₈	2.66	7.5–8 (Mohs)	None	Insoluble
Be ₃ Sc ₂ Si ₆ O ₁₈	2.77	6.5 (Mohs)	None	Insoluble
BeMg ₃ Al ₈ O ₁₆	3.60	8.5 (Mohs)	—	Insoluble
BeO(dreyerite)	3.01	1250	(10 ₁ 0)-i	2 × 10 ⁻⁵ (20)
Bi ₂ Ge ₃ O ₉	6.20	5.5 GPa	(0001)-p	Insoluble
BiVO ₄ (dreyerite)	6.25	—	(110)-p	Insoluble
Ca ₂ Al ₂ GeO ₇	3.421	—	(001)	Insoluble
Ca ₂ Al ₂ SiO ₇	3.04	5.5 (Mohs)	(001)	Insoluble
Ca ₂ Al ₃ O ₆ F	2.95	—	(10 ₁ 1)-i	Insoluble
Ca ₂ B ₅ O ₉ Cl	2.639	—	—	Insoluble
Ca ₂ BeSi ₂ O ₇	—	—	—	Insoluble
Ca ₂ Ga ₂ GeO ₇	4.14	—	(001)	Insoluble
Ca ₂ Ga ₂ SiO ₇	4.07	—	(001)	Insoluble
Ca ₂ MgSi ₂ O ₇	2.94	5.5 (Mohs)	(001)-i	Insoluble
Ca ₂ Te ₂ O ₅	5.05	4 (Mohs)	(001)-p	Insoluble
Ca ₂ ZnSi ₂ O ₇	3.39	3.5 (Mohs)	(001)	Insoluble
Ca ₃ B ₂ O ₆	3.09	—	—	Insoluble

Physical Properties of Uniaxial Crystalline Materials—continued

Uniaxial material	Density (g/cm³)	Hardness (kg/mm²)	Cleavage plane	Solubility (°C) (g/100 g H₂O)
Ca ₃ Ga ₂ Ge ₄ O ₁₄	4.590	—	None	Insoluble
Ca ₄ La(PO ₄) ₃ O	—	—	—	Insoluble
Ca ₄ Y ₆ (SiO ₄) ₆ O	—	—	None	Insoluble
Ca ₅ (AsO ₄) ₃ Cl	3.635	—	—	Insoluble
Ca ₅ (AsO ₄) ₃ F	3.5	4.5 (Mohs)	(10 ₁ 1)-i	Insoluble
Ca ₅ (PO ₄) ₃ Cl	2.90	5 (Mohs)	(0001)-i	Insoluble
Ca ₅ (PO ₄) ₃ F	3.20	540	(0001)-i	Insoluble
Ca ₅ (VO ₄) ₃ F	—	—	(10 ₁ 1)-i	Insoluble
Ca ₅ (VO ₄) ₃ Cl	3.174	—	(10 ₁ 1)-i	Insoluble
CaAl ₁₂ O ₁₉	3.78	—	—	Insoluble
CaAl ₂ B ₂ O ₇	2.44	—	—	—
CaCO ₃ -calcite	2.715	75–135	(10 ₁ 1)-p	1.4 × 10 ⁻³ (25)
CaCO ₃ -vaterite	2.68	3 (Mohs)	—	Insoluble
CaGd ₄ (SiO ₄) ₃ O	6.030	—	None	Insoluble
CaGdAlO ₄	5.97	716	(001)	Insoluble
CaGe ₄ O ₉	—	—	None	Insoluble
CaLa ₄ (SiO ₄) ₃ O	5.112	—	None	Insoluble
CaLaAlO ₄	—	—	(001)	Insoluble
CaLaBO ₄	4.136	—	—	Insoluble
CaMg(CO ₃) ₂	2.86	3.5 (Mohs)	(10 ₁ 1)-p	Insoluble
CaMg ₃ (CO ₃) ₄	3.71	335	(10 ₁ 1)-p	Insoluble
CaMoO ₄	4.25	4.0 (Mohs)	(112)(110)	—
CaSnB ₂ O ₆	4.22	5.5 (Mohs)	(0001)-p	Insoluble
CaWO ₄	6.062	4.5–5 (Mohs)	(101)-i	6.4 × 10 ⁻⁴ (15)
CaY ₄ (SiO ₄) ₃ O	4.47	702	None	Insoluble
CaYAlO ₄	—	—	—	Insoluble
CaZrBaI ₉ O ₁₈	4.01	8 (Mohs)	None	Insoluble
Cd ₅ (AsO ₄) ₃ Cl	5.917	—	(10 ₁ 1)-i	Insoluble
Cd ₅ (PO ₄) ₃ Cl	5.600	—	(10 ₁ 1)-i	Insoluble
Cd ₅ (PO ₄) ₃ F	5.784	—	(10 ₁ 1)-i	Insoluble
Cd ₅ (VO ₄) ₃ Cl	5.375	—	(10 ₁ 1)-i	Insoluble
CdCl ₂	4.047	—	—	140 (25)
CdCO ₃	5.02	—	(10 ₁ 1)-p	Insoluble
CdI ₂	5.670	—	—	86 (25)
CdS	4.82	122 (25)	(11 ₂ 2)-i	1.3 × 10 ⁻⁴ (18)
CdSe	5.81	44–90	—	Insoluble
CdSnB ₂ O ₆	5.479	—	—	Insoluble
CdTiO ₃	5.881	—	—	Insoluble
Cs ₂ AgF ₄	5.02	—	—	—
Cs ₂ CdCl ₄	3.697	—	—	—
Cs ₂ CdZnF ₆	5.342	—	—	—
Cs ₂ KAl ₃ F ₁₂	3.76	—	—	—
Cs ₂ LiAl ₃ F ₁₂	3.949	—	—	—

Physical Properties of Uniaxial Crystalline Materials—continued

Uniaxial material	Density (g/cm³)	Hardness (kg/mm²)	Cleavage plane	Solubility (°C) (g/100 g H₂O)
Cs ₂ LiAlF ₆	4.38	—	—	—
Cs ₂ LiGa ₃ F ₁₂	4.43	—	—	—
Cs ₂ LiGaF ₆	4.406	—	—	—
Cs ₂ NaAl ₃ F ₁₂	3.817	—	—	—
Cs ₂ NaAlF ₆	4.346	—	—	—
Cs ₂ NaGaF ₆	4.654	—	—	—
Cs ₂ SnGe ₃ O ₉	5.145	—	—	Insoluble
Cs ₂ TiGe ₃ O ₉	4.835	—	—	Insoluble
CsAl(SO ₄) ₂	3.382	—	—	—
CsH ₂ AsO ₄	3.747	1.5 (Mohs)	(101)-p	Very soluble
CsH ₂ PO ₄	3.253	1.5 (Mohs)	(101)-p	Very soluble
CsSc(MoO ₄) ₂	3.54	—	(1011)-p	—
CsSc(WO ₄) ₂	4.74	—	(1011)-p	—
α-GaN	6.109	750	—	Insoluble
GaPO ₄	2.995	4 (Mohs)	None	Insoluble
GaS	3.86	—	—	—
GaSe	5.03	—	—	—
GdAl ₃ (BO ₃) ₄	4.335	7 (Mohs)	(1011)	Insoluble
GdB ₃ O ₃	6.357	—	—	Insoluble
GdGa ₃ (BO ₃) ₄	5.257	—	(1011)	Insoluble
GdInO ₃	7.41	—	—	—
GdVO ₄	5.474	—	(110)-p	Insoluble
GeO ₂	6.239	—	None	Insoluble
HfSiO ₄	6.97	—	(110)-i	Insoluble
Hg ₂ Br ₂	7.68	1.5 (Mohs)	(110)	Insoluble
Hg ₂ Cl ₂	7.15	1.5 (Mohs)	(110)-i	3×10^{-4}
Hg ₂ I ₂	7.68	—	—	Insoluble
HgI ₂	6.28	—	—	0.0055 (35)
HgS	8.10	2–2.5 (Mohs)	(1010)-p	1×10^{-6} (18)
In ₂ O ₃	7.31	—	—	—
InBO ₃	5.555	—	(1011)-p	Insoluble
K ₂ BiNb ₅ O ₁₅	5.29	—	—	—
K ₂ CaZr(SiO ₃) ₄	3.10	5.5 (Mohs)	None	Insoluble
K ₂ GdNb ₅ O ₁₅	5.147	—	—	Insoluble
K ₂ LaNb ₅ O ₁₅	4.921	—	—	Insoluble
K ₂ MgCl ₄	2.13	—	—	—
K ₂ MgF ₄	2.839	—	(001)-p	—
K ₂ NaLi ₂ Nb ₅ O ₁₅	—	—	(001)-p	Insoluble
K ₂ SnGe ₃ O ₉	4.324	—	—	Insoluble
K ₂ SnSi ₃ O ₉	3.46	—	—	Insoluble
K ₂ Sr(SO ₄) ₂	3.20	2 (Mohs)	(0001)-p	Slightly soluble
K ₂ TiGe ₃ O ₉	3.945	—	—	Insoluble
K ₂ TiSi ₃ O ₉	3.239	—	—	Insoluble

Physical Properties of Uniaxial Crystalline Materials—continued

Uniaxial material	Density (g/cm³)	Hardness (kg/mm²)	Cleavage plane	Solubility (°C) (g/100 g H₂O)
K ₂ YNb ₅ O ₁₅	4.807	—	—	Insoluble
K ₂ ZnF ₄	3.378	—	(001)-p	—
K ₃ LiNb ₅ O ₁₅	4.376	—	(001)-p	Insoluble
K ₃ Sc(VO ₄) ₂	3.02	—	—	Slightly soluble
KAl(MoO ₄) ₂	3.42	—	(1011)-p	—
KAl(SO ₄) ₂	2.481	—	—	—
KAlF ₄	3.009	—	—	—
KAlGeO ₄	3.617	—	—	Insoluble
KAlSi ₂ O ₆	2.47	5.5 (Mohs)	None	Insoluble
KAlSiO ₄	2.59	6 (Mohs)	None	Insoluble
KD ₂ PO ₄	—	1.5 (Mohs)	(101)-p	Very soluble
KGaGeO ₄	4.261	—	—	Insoluble
KGaSiO ₄	3.691	—	—	Insoluble
KH ₂ PO ₄	2.338	1.5 (Mohs)	(101)-p	33 (25)
KIn(WO ₄) ₂	5.13	—	(1011)-p	—
KLa(MoO ₄) ₂	4.61	—	—	—
KLiBeF ₄	2.284	—	—	—
KSc(MoO ₄) ₂	3.23	—	(1011)-p	—
KSc(WO ₄) ₂	4.64	—	(1011)-p	—
KYF ₄	3.49	3 (Mohs)	None	Insoluble
KZnF ₃	4.018	2.5 (Mohs)	None	Insoluble
La ₂ GeBe ₂ O ₇	5.424	—	(001)	Insoluble
La ₂ MoO ₆	5.834	—	(100)-p	—
La ₂ O ₂ S	5.75	350–450	—	—
La ₂ O ₃	6.574	—	—	—
La ₂ WO ₆	7.44	—	—	—
La ₃ Ga ₅ GeO ₁₄	—	—	None	Insoluble
La ₃ Ga ₅ SiO ₁₄	5.754	—	None	Insoluble
La ₃ Nb _{0.5} Ga _{5.5} O ₁₄	5.934	—	None	Insoluble
La ₃ Ta _{0.5} Ga _{5.5} O ₁₄	6.164	—	None	Insoluble
LaAlO ₃	—	—	—	Insoluble
LaBaGa ₃ O ₇	5.60	—	(001)	Insoluble
LaBGeO ₅	5.04	—	—	Insoluble
LaBSiO ₅	4.58	—	—	Insoluble
LaCaAl ₃ O ₇	—	—	(001)	Insoluble
LaCaGa ₃ O ₇	—	—	(001)	Insoluble
LaCl ₃	3.85	—	—	—
LaF ₃	5.94	450	(0001)	Insoluble
LaMgAl ₁₁ O ₁₉	4.285	—	—	Insoluble
LaSrGa ₃ O ₇	5.64	—	(001)-i	Insoluble
Li ₂ B ₄ O ₇	2.44	—	None	Slightly soluble
Li ₂ CaGeO ₄	3.63	—	—	Insoluble
Li ₂ CaSiO ₄	2.935	—	—	Insoluble

Physical Properties of Uniaxial Crystalline Materials—continued

Uniaxial material	Density (g/cm³)	Hardness (kg/mm²)	Cleavage plane	Solubility (°C) (g/100 g H₂O)
Li ₃ InO ₃	4.394	—	—	—
LiAlGeO ₄	3.338	—	None	Insoluble
γ-LiAlO ₂	2.615	—	—	Insoluble
LiAlSiO ₄	2.66	6.5 (Mohs)	(10\u2011\u2011)	Insoluble
LiCaAlF ₆	2.983	3.5 (Mohs)	None	0.005
LiCaGaF ₆	3.517	—	None	Very slightly soluble
LiCaInF ₆	—	—	None	Very slightly soluble
LiCdBO ₃	4.53	—	—	—
LiCdInF ₆	—	—	None	Very slightly soluble
LiGaGeO ₄	4.077	—	None	Insoluble
LiGaSiO ₄	3.445	—	—	Insoluble
LiGd(MoO ₄) ₂	5.273	—	—	—
LiGd(WO ₄) ₂	7.19	—	—	—
LiGdF ₄	5.343	3.5 (Mohs)	None	Insoluble
LiIO ₃	4.487	3.5 (Mohs)	—	80 (18)
LiLa(WO ₄) ₂	6.57	—	—	—
LiLuF ₄	6.186	3.5 (Mohs)	None	Insoluble
LiMgAlF ₆	3.14	—	—	Insoluble
LiMgGaF ₆	3.772	—	—	Insoluble
LiMgInF ₆	4.267	—	—	—
LiNbO ₃	4.644	5 (Mohs)	(10\u2011\u2011)-p	Insoluble
LiSrAlF ₆	3.45	3.0 (Mohs)	None	0.05
LiSrGaF ₆	3.600	2.5 (Mohs)	None	0.10
LiTaO ₃	7.43	6 (Mohs)	(10\u2011\u2011)	Insoluble
LiYF ₄	3.99	260–325	None	Insoluble
LiZnInF ₆	—	—	None	Very slightly soluble
LiZnNbO ₄	4.504	—	—	—
LuAl ₃ (BO ₃) ₄	4.569	7 (Mohs)	(10\u2011\u2011)	Insoluble
LuBO ₃	6.871	—	—	Insoluble
LuPO ₄	—	—	—	Insoluble
LuVO ₄	6.263	—	(110)-p	Insoluble
Mg ₂ Al ₃ (Si ₅ Al)O ₁₈	2.53	7 (Mohs)	(10\u2011\u2010)-i	Insoluble
MgCO ₃	3.00	4 (Mohs)	(10\u2011\u2011)-p	Insoluble
MgF ₂	3.18	415	(010),(110)	< 2 × 10 ⁻⁴
MgTiO ₃	4.03	5.5 (Mohs)	(10\u2011\u2011)-i	Insoluble
MnF ₂	4.478	—	—	0.66 (40)
Na ₂ Al ₂ B ₂ O ₇	2.62	—	—	—
Na ₂ Ca ₂ Si ₃ O ₉	2.840	—	—	Insoluble
Na ₂ CO ₃	2.27	—	—	Very soluble
Na ₂ Mg(CO ₃) ₂	2.74	3.5 (Mohs)	(0001)-i	—
Na ₂ TiOSiO ₄	—	3.5 (Mohs)	(001)-p	Insoluble
Na ₃ Li ₂ Nb ₅ O ₁₅	—	—	(001)-p	Insoluble
Na ₃ YSi ₂ O ₇	3.063	—	—	Insoluble

Physical Properties of Uniaxial Crystalline Materials—continued

Uniaxial material	Density (g/cm³)	Hardness (kg/mm²)	Cleavage plane	Solubility (°C) (g/100 g H₂O)
Na ₅ Al ₃ F ₁₄	3.00	3.5 (Mohs)	(001)-p	—
Na ₅ GdGe ₄ O ₁₂	3.861	—	—	Insoluble
Na ₅ GdSi ₄ O ₁₂	3.213	—	—	Insoluble
Na ₅ InGe ₄ O ₁₂	3.831	—	—	Insoluble
Na ₅ InSi ₄ O ₁₂	3.134	—	—	Insoluble
Na ₅ LuGe ₄ O ₁₂	4.051	—	—	Insoluble
Na ₅ LuSi ₄ O ₁₂	3.348	—	—	Insoluble
Na ₅ ScGe ₄ O ₁₂	3.476	—	—	Insoluble
Na ₅ ScSi ₄ O ₁₂	2.743	—	—	Insoluble
Na ₅ Y ₄ (SiO ₄) ₄ F	3.938	—	—	—
Na ₅ YGe ₄ O ₁₂	3.548	—	—	Insoluble
Na ₅ YSi ₄ O ₁₂	2.863	—	—	Insoluble
NaAlSiO ₄	2.63	—	—	Insoluble
NaBaPO ₄	4.270	1.5 (Mohs)	—	—
NaGd(WO ₄) ₂	7.184	—	—	—
NaGdO ₂	6.162	—	—	Slightly soluble
NaInO ₂	5.711	—	—	Slightly soluble
NaLa(MoO ₄) ₂	4.773	—	—	—
NaLaO ₂	4.949	—	—	Soluble
NaNO ₃	2.261	19.2(200)	(1010)-p	92 (25)
NaSbBe ₄ O ₇	4.28	8 (Mohs)	(0001)-i	Insoluble
NaScO ₂	3.515	—	—	Slightly soluble
NaYF ₄	3.85	—	—	Insoluble
NbCaAlO ₄	5.56	—	—	Insoluble
Nd _x Y _{1-x} Al ₃ (BO ₃) ₄	—	8 (Mohs)	—	—
NH ₄ Al(SeO ₄) ₂	3.13	—	—	—
NH ₄ Al(SO ₄) ₂	2.472	—	—	—
NH ₄ Ga(SeO ₄) ₂	3.476	—	—	—
NH ₄ Ga(SO ₄) ₂	2.854	—	—	—
NH ₄ H ₂ PO ₄	1.803	1 (Mohs)	(101)-p	36.8 (20)
Pb ₂ InNbO ₆	8.567	—	—	Insoluble
Pb ₂ ZnSi ₂ O ₇	—	—	(001)	Insoluble
Pb ₃ Ca ₂ (AsO ₄) ₃ Cl	5.82	4.5 (Mohs)	(10 ₁ 1)-i	Insoluble
Pb ₃ Ge ₂ O ₇	—	—	—	Insoluble
Pb ₅ (AsO ₄) ₃ F	—	—	(10 ₁ 1)-i	Insoluble
Pb ₅ (AsO ₄) ₃ Cl	7.28	3.5 (Mohs)	(10 ₁ 1)-i	Insoluble
Pb ₅ (PO ₄) ₃ Cl	7.04	3.5 (Mohs)	(10 ₁ 1)-i	Insoluble
Pb ₅ (PO ₄) ₃ F	6.868	—	(10 ₁ 1)-i	Insoluble
Pb ₅ (VO ₄) ₃ Cl	6.88	3 (Mohs)	None	Insoluble
Pb ₅ (VO ₄) ₃ F	7.155	—	(10 ₁ 1)-i	Insoluble
PbAl ₁₂ O ₁₉	4.731	—	—	Insoluble
PbI ₂	6.16	—	—	0.076 (25)
PbMoO ₄	6.92	2.5–3 (Mohs)	(011)	Insoluble

Physical Properties of Uniaxial Crystalline Materials—continued

Uniaxial material	Density (g/cm³)	Hardness (kg/mm²)	Cleavage plane	Solubility (°C) (g/100 g H₂O)
PbO (litharge)	9.36	—	(110)-p	1.7×10^{-3} (20)
PbTiO ₃	—	—	—	Insoluble
PbWO ₄	8.23	2.5–3 (Mohs)	(001)-i	Insoluble
Rb ₂ LaNb ₅ O ₁₅	5.35	—	—	Insoluble
Rb ₂ LiAlF ₆	3.878	—	—	—
Rb ₂ LiGaF ₆	4.258	—	—	—
Rb ₂ MgCl ₄	2.791	—	—	—
Rb ₂ MgF ₄	3.972	—	(001)-p	—
Rb ₂ SnGe ₃ O ₉	4.850	—	—	Insoluble
Rb ₂ SnSi ₃ O ₉	4.103	—	—	Insoluble
Rb ₂ TiGe ₃ O ₉	4.425	—	—	Insoluble
Rb ₂ TiSi ₃ O ₉	3.626	—	—	Insoluble
Rb ₂ ZnF ₄	4.637	—	(001)-p	—
Rb ₃ Gd(VO ₄) ₂	4.50	—	—	Slightly soluble
Rb ₃ Lu(VO ₄) ₂	4.56	—	—	Slightly soluble
Rb ₃ NaBeF ₈	3.376	—	—	—
Rb ₃ Sc(VO ₄) ₂	3.83	—	—	Slightly soluble
Rb ₃ Y(VO ₄) ₂	3.76	—	—	Slightly soluble
RbAl(SeO ₄) ₂	3.725	—	—	—
RbAl(SO ₄) ₂	3.126	—	—	—
RbAlF ₄	3.792	—	—	—
RbAlSi ₂ O ₆	2.893	—	—	Insoluble
RbCdF ₃	4.836	—	—	—
RbGa(SeO ₄) ₂	4.088	—	—	—
RbGa(SO ₄) ₂	3.504	—	—	—
RbH ₂ AsO ₄	—	1.5 (Mohs)	(101)-p	Very soluble
RbH ₂ PO ₄	—	1.5 (Mohs)	(101)-p	Very soluble
RbIn(MoO ₄) ₂	3.88	—	(1011)-p	—
RbIn(WO ₄) ₂	5.19	—	(1011)-p	—
RbSc(MoO ₄) ₂	3.41	—	(1011)-p	—
RbSc(WO ₄) ₂	4.68	—	(1011)-p	—
ScBO ₃	3.45	5 (Moh)	(1011)-p	Insoluble
ScPO ₄	—	—	—	Insoluble
ScVO ₄	—	—	—	—
Se	4.81	2.6 (Moh)	(0112)-i	Insoluble
SeO ₂	4.16	—	—	—
α-SiC	3.219	3720	None	Insoluble
Si ₃ N ₄	3.24	3400	None	Insoluble
SiO ₂	2.65	741(500)	None	Insoluble
SnO ₂	6.95	6.5 (Mohs)	(100)-i	Insoluble
Sr ₂ Al ₂ SiO ₇	—	—	(001)	Insoluble
Sr ₂ B ₅ O ₉ Cl	3.250	—	—	Insoluble
Sr ₂ Ga ₂ SiO ₇	—	—	(001)	Insoluble

Physical Properties of Uniaxial Crystalline Materials—continued

Uniaxial material	Density (g/cm³)	Hardness (kg/mm²)	Cleavage plane	Solubility (°C) (g/100 g H₂O)
Sr ₂ MgGe ₂ O ₇	4.266	—	(001)	Insoluble
Sr ₂ MgSi ₂ O ₇	—	—	(001)	Insoluble
Sr ₂ ZnGe ₂ O ₇	—	—	(001)	Insoluble
Sr ₂ ZnSi ₂ O ₇	4.027	—	(001)	Insoluble
Sr ₃ (VO ₄) ₂	4.464	—	—	—
Sr ₃ B ₂ O ₆	4.257	—	—	Insoluble
Sr ₃ Ga ₂ Ge ₄ O ₁₄	5.087	—	None	Insoluble
Sr ₃ Ti ₂ O ₇	5.04	—	—	Insoluble
Sr ₅ (AsO ₄) ₃ F	4.538	—	(1011)-i	Insoluble
Sr ₅ (AsO ₄) ₃ Cl	4.525	—	—	Insoluble
Sr ₅ (PO ₄) ₃ Cl	4.095	—	—	Insoluble
Sr ₅ (PO ₄) ₃ F	4.14	380	(0001)-i	Insoluble
Sr ₅ (VO ₄) ₃ F	4.13	—	(1011)-i	Insoluble
Sr ₅ (VO ₄) ₃ Cl	4.122	—	(1011)-i	Insoluble
Sr ₅ Nb ₄ O ₁₅	5.46	—	—	—
Sr ₅ Ta ₄ O ₁₅	7.321	—	—	Insoluble
SrAl ₁₂ O ₁₉	3.985	—	—	Insoluble
SrAlF ₅	3.86	—	—	Insoluble
(Sr _{0.6} Ba _{0.4})Nb ₂ O ₆	5.4	5.5 (Mohs)	—	Insoluble
SrGaF ₅	4.40	—	—	Insoluble
SrGdAlO ₄	6.602	—	(001)-p	Insoluble
SrGdGa ₃ O ₇	5.64	—	—	Insoluble
SrLa ₄ (SiO ₄) ₃ O	—	—	None	Insoluble
SrLaAlO ₄	5.826	—	(001)-p	Insoluble
SrLaBO ₄	4.802	—	—	Insoluble
SrLaGaO ₄	5.372	—	(001)-p	Insoluble
SrMg ₂ (VO ₄) ₂	3.827	—	—	—
SrMoO ₄	4.701	—	—	—
SrSnB ₂ O ₆	—	—	—	Insoluble
SrTiB ₂ O ₆	—	—	—	Insoluble
SrWO ₄	6.354	—	—	Insoluble
SrY ₄ (SiO ₄) ₃ O	—	—	None	Insoluble
SrZrB ₂ O ₆	—	—	—	Insoluble
Ta ₂ O ₅	8.2	—	—	Insoluble
TaBO ₄	8.02	7.5 (Mohs)	(110)(010)	Insoluble
Te	6.25	18	None	Insoluble
ThSiO ₄	6.7	4.5 (Mohs)	None	Insoluble
TiO ₂	4.26	879 (500)	(110)-i	0.001
Tl ₂ SnGe ₃ O ₉	6.617	—	—	Insoluble
Tl ₂ TiGe ₃ O ₉	6.256	—	—	Insoluble
Tl ₃ AsS ₃	7.18	—	—	Insoluble
Tl ₃ AsSe ₃	7.834	—	—	Insoluble
TlAl(SeO ₄) ₂	4.894	—	—	—

Physical Properties of Uniaxial Crystalline Materials—continued

Uniaxial material	Density (g/cm³)	Hardness (kg/mm²)	Cleavage plane	Solubility (°C) (g/100 g H₂O)
TlAl(SO ₄) ₂	4.337	—	—	—
TlAlF ₄	6.131	—	—	—
TlGa(SeO ₄) ₂	5.163	—	—	—
TlGa(SO ₄) ₂	4.719	—	—	—
Y ₂ BeAl ₂ O ₇	—	—	(001)	Insoluble
Y ₂ GeBe ₂ O ₇	4.810	—	(001)	Insoluble
Y ₂ SiBe ₂ O ₇	4.423	—	(001)	Insoluble
YAl ₃ (BO ₃) ₄	3.724	1890	(10 $\overline{1}$ 1)	Insoluble
YAsO ₄	4.85	4.5 (Mohs)	—	Insoluble
YBO ₃	—	—	—	Insoluble
YCaAl ₃ O ₇	—	—	(001)	Insoluble
YGa ₃ (BO ₃) ₄	4.684	—	(10 $\overline{1}$ 1)	Insoluble
YInO ₃	6.032	—	—	—
YPO ₄	4.31	4.5 (Mohs)	(110)-p	Insoluble
YVO ₄	4.23	480	(110)-p	Insoluble
Zn ₂ GeO ₄	4.781	—	—	Insoluble
Zn ₂ SiO ₄	4.25	5.5 (Mohs)	(0001)-i	Insoluble
ZnCO ₃	4.43	4 (Mohs)	(10 $\overline{1}$ 1)-p	Insoluble
ZnCl ₂	2.907	—	—	408 (25)
ZnF ₂	4.95	—	—	1.62 (20)
ZnGeP ₂	—	—	—	Insoluble
ZnO	5.606	4 (Mohs)	(10 $\overline{1}$ 0)-p	1.6 × 10 ⁻⁴ (20)
ZnSb ₂ O ₆	6.64	6.5 (Mohs)	—	—
ZnSiP ₂	—	—	—	Insoluble
ZnS (wurtzite)	3.98	3.5 (Mohs)	(11 $\overline{2}$ 0)-i	Insoluble
ZrO ₂	5.861	—	—	Insoluble
ZrSiO ₄	4.56	1000	(110)-i	Insoluble

1.2.3 Biaxial Crystals

Physical Properties of Biaxial Crystalline Materials

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
Al ₂ (MoO ₄) ₃	3.495	—	—	Insoluble
Al ₂ (WO ₄) ₃	5.079	—	(010)-p	Insoluble
Al ₂ Ge ₂ O ₇	4.06	—	—	Insoluble
Al ₂ SiO ₄ F ₂	3.57	8 (Mohs)	(001)-p	Insoluble
Al ₂ SiO ₅ -andalusite	3.13	6.5 (Mohs)	(110)	Insoluble
Al ₂ SiO ₅ -kyanite	3.6	4–7.5 (Mohs)	(100)-p	Insoluble
Al ₂ SiO ₅ -sillimanite	3.25	6.5 (Mohs)	(010)-p	Insoluble
Al ₄ B ₂ O ₉	2.904	—	—	—
Al ₆ Ge ₂ O ₁₃	3.662	—	—	Insoluble
Al ₆ Si ₂ O ₁₃	3.19	1750	(010)-i	Insoluble
AlHfTaO ₆	8.33	—	—	Insoluble
AlNb ₁₁ O ₂₉	4.46	—	—	Insoluble
AlNbO ₄	4.673	—	—	Insoluble
AlTaO ₄	6.86	—	—	Insoluble
As ₂ S ₃	3.49	1.5 (Mohs)	(010)-p	Insoluble
AsS	3.56	1.5 (Mohs)	(010)-i	Insoluble
AsSbS ₃	3.92	1.5 (Mohs)	(001)-p	Insoluble
Ba ₂ CaMgAl ₂ F ₁₄	4.204	3.5 (Mohs)	(001)-p	—
Ba ₂ CdMgAl ₂ F ₁₄	4.735	—	—	—
Ba ₂ LiNb ₅ O ₁₅	—	—	—	Insoluble
Ba ₂ NaNb ₅ O ₁₅	5.41	—	—	Insoluble
Ba ₂ Zn ₃ F ₁₀	5.26	—	—	—
Ba ₂ ZnAlF ₉	4.909	—	—	—
Ba ₂ ZnGaF ₉	5.169	—	—	—
Ba ₃ Al ₂ F ₁₂	4.37	—	—	—
Ba ₃ TiAl ₁₀ O ₂₀	4.13	—	—	—
BaAl ₂ B ₂ O ₇	3.559	—	—	—
BaAl ₂ Ge ₂ O ₈	—	—	—	Insoluble
BaAl ₂ Si ₂ O ₈	3.96	6–6.5 (Mohs)	(001)-p	Insoluble
BaBe ₂ Si ₂ O ₇	4.00	7 (Mohs)	(001)(100)-p	Insoluble
BaCa ₂ Mg(SiO ₄) ₂	3.974	—	—	Insoluble
BaCa ₂ Si ₃ O ₉	3.73	3.5 (Mohs)	(011)(010)-p	Insoluble
BaCdAlF ₇	5.04	—	—	—
BaCdGaF ₇	5.406	—	—	—
BaCO ₃	4.31	3.5 (Mohs)	(010)-i	Very slightly soluble
BaGaF ₅	5.104	—	—	—
BaGe ₂ O ₅	5.85	—	—	Insoluble
BaGeAl ₆ O ₁₂	4.031	—	—	—
BaGeGa ₆ O ₁₂	5.201	—	—	—

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
BaGeO ₃	5.072	—	—	Insoluble
BaMgF ₄	4.538	—	—	—
BaNb ₂ O ₆	—	—	—	Insoluble
BaSO ₄	4.50	3 (Mohs)	(001)-p	Insoluble
BaTa ₂ O ₆	7.824	—	—	Insoluble
BaTi ₄ O ₉	4.52	—	—	Insoluble
BaTiAl ₆ O ₁₂	3.791	—	—	—
BaTiGa ₆ O ₁₂	4.981	—	—	—
BaY ₂ F ₈	5.047	250–350	—	—
BaY ₂ O ₄	5.806	—	—	—
BaZnF ₄	5.178	—	—	—
β-BaSi ₂ O ₅	3.77	5 (Mohs)	(001)	Insoluble
β-Ca ₂ SiO ₄	3.31	6 (Mohs)	(100)-i	Insoluble
Be ₂ BO ₃ F	2.37	7.5 (Mohs)	(010)-p	Insoluble
BeAl ₂ O ₄	3.75	1600–2300 (V)	None	Insoluble
BeAl ₆ O ₁₀	3.75	—	—	—
β-Ga ₂ O ₃	5.95	—	(010)-p	Insoluble
Bi ₂ Al ₄ O ₉	6.229	—	—	—
Bi ₂ GeO ₅	—	—	—	Insoluble
Bi ₂ Mo ₂ O ₉	6.518	—	—	Insoluble
Bi ₂ Mo ₃ O ₁₂	6.196	—	(100)-p	Insoluble
Bi ₂ O ₃	9.37	—	—	Very slightly soluble
Bi ₂ SiO ₅	—	—	—	Insoluble
Bi ₂ WO ₆	7.35	3.5 (Mohs)	—	—
Bi ₃ TiNbO ₉	—	—	—	Insoluble
Bi ₄ B ₂ O ₉	8.185	—	—	—
Bi ₄ Ti ₃ O ₁₂	8.045	313	—	Insoluble
γ-Bi ₂ MoO ₆	7.068	—	—	—
BiB ₃ O ₆	5.03	5–5.5 (Mohs)	—	Insoluble
BiNbO ₄	—	—	—	Insoluble
BiSbO ₄	8.48	—	—	Insoluble
BiTaO ₄	8.958	—	—	Insoluble
BiVO ₄ -clinobisvanite	6.95	—	—	—
BiVO ₄ -pucherite	6.63	4 (Mohs)	(001)-p	—
Ca(IO ₃) ₂	4.48	3.5 (Mohs)	(011)-i	—
Ca ₂ (AsO ₄)Cl	—	—	(010)-p	—
Ca ₂ (PO ₄)Cl	—	—	(010)-p	—
Ca ₂ (PO ₄)F	—	—	(010)-p	Insoluble
Ca ₂ (VO ₄)Cl	3.075	—	(010)-p	—
Ca ₂ Al ₂ O ₅	3.73	—	—	—
Ca ₂ B ₆ O ₁₁	2.85	—	—	—
Ca ₂ BO ₃ Cl	2.766	—	—	—

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
Ca ₂ Nb ₂ O ₇	—	—	—	Insoluble
Ca ₂ Sb ₂ O ₇	5.204	—	—	Insoluble
Ca ₂ V ₂ O ₇	3.36	5.5 (Mohs)	(110)-p	—
Ca ₃ (VO ₄) ₂	3.16	—	(110)(001)-p	—
Ca ₃ Al ₂ O ₆	3.017	—	—	—
Ca ₃ Ga ₄ O ₉	4.208	—	—	—
Ca ₃ MgSi ₂ O ₈	3.31	6 (Mohs)	None	Insoluble
Ca ₃ Si ₂ O ₇	2.96	5.5 (Mohs)	—	Insoluble
Ca ₅ Al ₆ O ₁₄	3.03	—	(001)-p	—
Ca ₅ Ga ₆ O ₁₄	4.18	5 (Mohs)	—	—
CaAl ₂ F ₈	2.89	4.5 (Mohs)	(111)-p	Insoluble
CaAl ₂ O ₄	2.942	—	—	—
CaAl ₂ Si ₂ O ₈	2.76	6–6.5 (Mohs)	(001)-p	Insoluble
CaAl ₄ O ₇	2.894	8.5 (Mohs)	—	—
CaAlB ₃ O ₇	3.44	7.5 (Mohs)	None	Insoluble
CaAlBO ₄	2.60	—	—	—
CaB ₂ O ₄	2.702	—	—	—
CaB ₂ Si ₂ O ₈	3.00	7 (Mohs)	None	Insoluble
CaB ₃ O ₅ F	2.729	—	—	Insoluble
CaB ₄ O ₇	2.69	—	—	—
CaBa(CO ₃) ₂	3.67	4 (Mohs)	(110)-i	Very slightly soluble
CaBe(PO ₄)F	2.95	5 (Mohs)	(110)-i	Insoluble
CaBe ₂ (PO ₄) ₂	2.89	6 (Mohs)	None	Insoluble
CaCO ₃ -aragonite	2.93	3.5–4 (Mohs)	(010)-i	Very slightly soluble
CaGa ₂ O ₄	4.333	—	—	—
CaGe ₂ O ₅	4.868	—	—	Insoluble
CaIn ₂ O ₄	6.15	—	—	—
CaMg(PO ₄)F	—	—	—	Insoluble
CaMgAsO ₄ F	3.77	5 (Mohs)	(101)-i	Very slightly soluble
CaMgB ₂ O ₅	3.02	4.5 (Mohs)	(010)-p	Very slightly soluble
CaMgGe ₂ O ₆	4.265	—	—	Insoluble
CaMgSi ₂ O ₆	3.26	6.5 (Mohs)	(110)-i	Insoluble
CaMgSiO ₄	3.06	5.5 (Mohs)	(010)-i	Insoluble
CaNb ₂ O ₆	4.78	5.5 (Mohs)	None	Insoluble
CaSc ₂ O ₄	3.897	—	—	Insoluble
CaSiO ₃	2.9	5 (Mohs)	(100)-p	Insoluble
CaSnO ₃	5.759	—	—	Insoluble
CaSnSiO ₅	4.56	4 (Mohs)	—	Insoluble
CaSO ₄	2.96	3.5 (Mohs)	(010)(100)	Very slightly soluble
CaTa ₂ O ₆	—	—	—	Insoluble
CaTiO ₃	4.04	—	—	Insoluble
CaTiSiO ₅	3.53	5.5 (Mohs)	(110)-i	Insoluble
CaV ₂ O ₆	3.59	—	(100)(001)-p	—

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
CaYBO ₄	3.783	—	—	—
CaZnGe ₂ O ₆	4.807	—	—	Insoluble
CaZnSiO ₄	4.25	5 (Mohs)	(010)(100)	Insoluble
CaZrSi ₂ O ₇	3.63	—	—	Insoluble
CaZrTi ₂ O ₇	4.407	—	—	Insoluble
Cd ₂ B ₂ O ₅	5.24	—	—	—
Cd ₂ GeO ₄	6.313	—	—	Insoluble
Cd ₄ B ₄ O ₇	3.51	—	—	—
CdWO ₄	8.005	—	—	—
Cs ₂ BeF ₄	4.128	—	—	—
Cs ₂ CdBr ₄	4.069	—	—	—
Cs ₂ HgI ₄	4.357	—	—	—
Cs ₂ MgCl ₄	2.952	—	—	—
Cs ₂ ZnBr ₄	4.034	—	—	—
Cs ₂ ZnCl ₄	3.357	—	—	—
CsB ₃ O ₅	3.39	—	—	Soluble
CsGd(MoO ₄) ₂	—	—	(100)-p	—
CsLiBeF ₄	3.411	—	—	—
CsLiSO ₄	3.455	—	—	Very soluble
CsNbB ₂ O ₆	—	—	(001)-p	Insoluble
CsLiSO ₄	3.455	—	—	Very soluble
CsNbB ₂ O ₆	—	—	(001)-p	Insoluble
CsTiOAsO ₄	4.511	—	None	Insoluble
CsZnAlF ₆	4.04	—	—	—
Ga ₂ (WO ₄) ₃	—	—	(010)-p	—
Ga ₂ GeO ₅	4.97	—	—	Insoluble
GaNbO ₄	5.01	—	—	Insoluble
Gd(BO ₂) ₃	4.84	—	—	—
Gd ₂ (MoO ₄) ₃	4.65	—	—	—
Gd ₂ (WO ₄) ₃	7.475	—	—	—
Gd ₂ GeO ₅	—	—	—	Insoluble
Gd ₂ MoO ₆	7.068	—	—	—
Gd ₂ O ₂ SO ₄	6.483	—	—	—
Gd ₂ O ₃	8.33	—	—	—
Gd ₂ SiO ₅	6.77	6 (Mohs)	(100)-p	Insoluble
Gd ₂ Sr ₃ (BO ₃) ₄	5.266	—	—	—
Gd ₂ WO ₆	8.339	—	—	—
Gd ₃ NbO ₇	7.459	—	—	Insoluble
Gd ₃ TaO ₇	8.414	—	—	Insoluble
Gd ₄ Al ₂ O ₉	6.467	—	—	—
α-Ga ₄ GeO ₈	5.65	—	—	Insoluble
GdAlGe ₂ O ₇	—	—	—	Insoluble
GdAlO ₃	7.437	—	—	Insoluble

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
GdGaGe ₂ O ₇	6.08	—	—	Insoluble
GdMg ₅ B ₅ O ₁₀	4.309	—	—	—
GdNbO ₄	—	—	—	Insoluble
GdP ₅ O ₁₄	3.55	—	—	Insoluble
GdPO ₄	5.986	470	—	Insoluble
GdScO ₃	6.642	—	—	Insoluble
HfO ₂	10.11	—	—	Insoluble
HgCl ₂	5.490	—	—	—
HgO	11.14	1.5–2.0 (Mohs)	(010)-p	—
HIO ₃	4.637	—	—	—
In ₂ (MoO ₄) ₃	3.92	—	—	—
In ₂ (WO ₄) ₃	5.619	—	(010)-p	—
InCaBO ₄	4.536	—	—	—
InGaO ₃	6.447	—	—	—
InNbO ₄	6.27	—	(010)-p	Insoluble
InPO ₄	4.830	—	—	Insoluble
InTaO ₄	8.296	—	(010)-p	Insoluble
InVO ₄	4.50	—	—	Insoluble
K ₂ CaSiO ₄	2.865	—	—	Insoluble
K ₃ Gd(VO ₄) ₂	3.15	—	—	Slightly soluble
K ₃ La(PO ₄) ₂	5.293	—	—	Insoluble
K ₃ Lu(VO ₄) ₂	3.15	—	—	Slightly soluble
K ₃ Y(VO ₄) ₂	3.15	—	—	Slightly soluble
KAlSi ₃ O ₈	2.57	6 (Mohs)	(001)-p	Insoluble
KAl ₃ Si ₃ O ₁₀ (OH) ₂	2.78	—	—	Insoluble
KBF ₄	2.51	—	—	Slightly soluble
KB ₅ O ₈ •4H ₂ O	1.740	2.5 (Mohs)	(010)-p	—
KGaSi ₃ O ₈	2.887	—	—	Insoluble
KIn(MoO ₄) ₂	4.17	—	—	—
KLaP ₄ O ₁₂	—	—	—	Insoluble
KLu(WO ₄) ₂	7.759	—	—	—
KNbB ₂ O ₆	3.151	—	(001)-p	Insoluble
KNbO ₃	4.617	—	—	Insoluble
KNO ₃	2.11	2 (Mohs)	(011)-p	Soluble
KPb ₂ Cl ₅	4.78	2.5 (Mohs)	—	Insoluble
KTaB ₂ O ₆	4.262	—	(001)-p	Insoluble
KTaO ₃	5.996 ?	—	—	Insoluble
KTi ₃ NbO ₉	3.88	—	—	Insoluble
KTiNbO ₅	3.82	—	—	Insoluble
KTiOAsO ₄	3.454	—	None	Insoluble
KTiOPO ₄	3.024	702	None	Insoluble
KVO ₃	2.879	—	(010)-p	—
KY(MoO ₄) ₂	5.40	—	—	—

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
KY(WO ₄) ₂	6.56	—	—	—
LaB ₃ O ₆	4.216	—	(010)-p	—
La ₂ (WO ₄) ₃	6.626	—	—	—
La ₂ Ba ₃ (BO ₃) ₄	5.353	—	—	—
La ₂ Be ₂ O ₅	6.061	900(100)	(010)-i	Insoluble
La ₂ Ca ₃ (BO ₃) ₄	4.157	—	—	—
La ₂ O ₂ SO ₄	5.467	—	—	—
La ₂ SiO ₅	—	—	—	Insoluble
La ₂ Sr ₃ (BO ₃) ₄	4.783	—	—	—
La ₂ Ti ₂ O ₇	5.782	648	(010)-p	Insoluble
La ₂ TiO ₅	5.5	—	—	Insoluble
La ₃ NbO ₇	6.25	—	—	Insoluble
La ₃ SbO ₇	6.558	—	—	Insoluble
La ₃ TaO ₇	7.139	—	—	Insoluble
LaAlGe ₂ O ₇	5.18	—	—	Insoluble
LaBMoO ₆	5.293	—	—	—
LaBO ₃	5.304	—	—	—
LaBWO ₆	6.185	—	—	—
LaGaGe ₂ O ₇	—	—	—	Insoluble
LaGaO ₃	7.21	—	—	Insoluble
LaInO ₃	—	—	—	—
LaMgB ₅ O ₁₀	3.923	—	—	—
LaNb ₅ O ₁₅	6.264	—	—	Insoluble
LaNbO ₄	5.914	—	—	Insoluble
LaP ₅ O ₁₄	3.290	—	—	Insoluble
LaPO ₄	5.067	5.5 (Mohs)	(100)-i	Insoluble
LaSbO ₄	6.30	—	—	Insoluble
LaScO ₃	5.79	—	—	Insoluble
LaVO ₄	—	—	—	Insoluble
LaY(WO ₄) ₃	6.53	—	—	—
Li ₂ BeSiO ₄	2.69	7 (Mohs)	(010)-i	Insoluble
Li ₂ CO ₃	2.097	—	—	Slightly soluble
Li ₂ GeO ₃	3.489	—	—	Insoluble
Li ₂ MgGeO ₄	3.31	—	—	Insoluble
Li ₂ SiO ₃	2.527	—	—	Insoluble
Li ₃ La ₂ (BO ₃) ₃	4.50	—	—	—
Li ₃ PO ₄	2.48	4 (Mohs)	(010)-p	Insoluble
Li ₃ VO ₄	2.645	—	—	Insoluble
Li ₃ Y ₂ (BO ₃) ₃	3.50	—	—	—
Li ₅ AlO ₄	2.251	—	—	—
Li ₆ Al ₂ (BO ₃) ₄	2.58	—	—	—
Li ₆ Lu(BO ₃) ₃	3.538	—	—	—
Li ₆ Y(BO ₃) ₃	2.76	—	—	—

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
LiAl(MoO ₄) ₂	3.95	—	—	—
LiAl(PO ₄)F	3.10	5.5 (Mohs)	(100)(110)-p	Insoluble
LiAlGe ₂ O ₆	4.354	—	—	Insoluble
LiAlSi ₂ O ₆	3.1	7 (Mohs)	(010)-p	Insoluble
LiAlSi ₄ O ₁₀	2.40	6.5 (Mohs)	(001)-p	Insoluble
LiBaAlF ₆	4.114	—	—	—
LiBaGaF ₆	4.526	—	—	—
LiBO ₂	2.883	—	—	—
LiB ₃ O ₅	2.474	7 (Mohs)	None	Insoluble
LiGa(WO ₄) ₂	7.44	—	—	—
LiGaGe ₂ O ₆	4.783	—	—	Insoluble
LiGaO ₂	4.175	—	—	Insoluble
LiGaSi ₂ O ₆	—	—	—	Insoluble
LiGdO ₂	6.246	—	—	—
LiGdP ₄ O ₁₂	—	—	—	Insoluble
LiIn(MoO ₄) ₂	4.149	—	—	—
LiIn(WO ₄) ₂	7.47	—	—	—
LiInGe ₂ O ₆	5.041	—	—	Insoluble
LiInSi ₂ O ₆	4.071	—	—	Insoluble
LiInSiO ₄	4.160	—	—	Insoluble
LiLa(MoO ₄) ₂	4.551	—	—	—
LiLaO ₂	6.18	—	—	Soluble
LiLaP ₄ O ₁₂	—	—	—	Insoluble
LiLu(WO ₄) ₂	8.02	—	—	—
LiLuGeO ₄	5.98	—	—	Insoluble
LiLuP ₄ O ₁₂	—	—	—	Insoluble
LiLuSiO ₄	5.46	—	—	Insoluble
LiSc(WO ₄) ₂	6.716	—	—	—
LiScGe ₂ O ₆	4.157	—	—	Insoluble
LiScGeO ₄	3.928	—	—	Insoluble
LiScSi ₂ O ₆	3.090	—	—	Insoluble
LiScSiO ₄	3.183	—	—	Insoluble
LiVO ₃	2.971	—	(100)-p	Insoluble
LiY(WO ₄) ₂	6.83	—	—	—
LiYGeO ₄	4.365	—	—	Insoluble
LiYO ₂	6.258	—	—	—
LiYSiO ₄	3.746	—	—	Insoluble
LiZnBO ₃	3.64	—	—	—
Lu ₂ MoO ₆	8.167	—	—	—
Lu ₂ O ₂ SO ₄	7.854	—	—	—
Lu ₂ SiO ₅	5.892	6.5 (Mohs)	None	Insoluble
Lu ₂ WO ₆	9.718	—	—	—
LuCaBO ₄	6.036	—	—	—

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
LuP ₅ O ₁₄	3.72	—	—	Insoluble
LuTaO ₄	9.761	—	—	Insoluble
Mg ₂ (PO ₄)F	3.15	5 (Mohs)	(100)-i	Insoluble
Mg ₂ B ₂ O ₅	2.910	5.5 (Mohs)	(hk0)-p	Insoluble
Mg ₂ BO ₃ F	2.784	—	—	Insoluble
Mg ₂ GeO ₄	4.028	—	—	Insoluble
Mg ₂ SiO ₄	3.22	7 (Mohs)	(010)-i	Insoluble
Mg ₃ (PO ₄) ₂	2.76	—	(100)(010)	Insoluble
Mg ₃ B ₂ O ₆	3.04	6.5 (Mohs)	(110)-p	Insoluble
Mg ₃ B ₇ O ₁₃ Cl	2.95	7 (Mohs)	None	Slightly soluble
Mg ₃ Ti ₂ B ₂ O ₈	3.35	3.5 (Mohs)	(100)-p	Insoluble
Mg ₄ Al ₈ Si ₂ O ₂₀	3.489	7.5 (Mohs)	(010)(001)-i	Insoluble
Mg ₄ Ga ₈ Ge ₂ O ₂₀	—	—	—	Insoluble
Mg ₅ (BO ₃) ₃ F	3.112	—	—	Insoluble
MgAl ₃ BSiO ₉	2.98	7.5 (Mohs)	(100)-p	Insoluble
MgAlBO ₄	3.45	7 (Mohs)	None	Insoluble
MgGaBO ₄	4.285	—	—	Insoluble
MgGeO ₃	4.282	—	—	Insoluble
MgMoO ₄	3.809	—	—	—
MgSiO ₃	3.21	5–6 (Mohs)	(110)-i	Insoluble
MgTi(SO ₄) ₃	2.82	—	—	—
MgTi ₂ O ₅	3.649	—	—	Insoluble
MgWO ₄	6.893	—	—	—
Na(Sr,Ba)PO ₄	2.919	—	—	Insoluble
Na ₂ BaTi ₂ Si ₄ O ₁₄	3.43	6 (Mohs)	(100)-i	Insoluble
Na ₂ BeF ₄	2.482	—	—	—
Na ₂ BeSi ₂ O ₆	2.70	6 (Mohs)	(100)-i	Insoluble
Na ₂ Ca(PO ₄)F	2.88	—	—	Insoluble
Na ₂ CaMg(PO ₄) ₂	3.10	4.5 (Mohs)	—	Insoluble
Na ₂ GeO ₃	3.319	—	—	Insoluble
Na ₂ KTiNbSi ₄ O ₁₄	2.968	6.5 (Mohs)	—	Insoluble
Na ₂ LiAlF ₆	2.98	—	(001)-p	Slightly soluble
Na ₂ LiYSi ₆ O ₁₅	2.76	—	—	Insoluble
Na ₂ MgAlF ₇	2.97	3.5 (Mohs)	(110)-i	Slightly soluble
Na ₂ MgGaF ₇	3.359	—	—	—
Na ₂ MgInF ₇	3.627	—	—	—
Na ₂ MgScF ₇	2.853	—	—	—
Na ₂ MgSiO ₄	2.75	—	—	Insoluble
Na ₂ Si ₂ O ₅	—	—	(100)-p	Slightly soluble
Na ₂ SiO ₃	2.64	—	—	Insoluble
Na ₂ Ti ₂ Si ₂ O ₉	3.44	6 (Mohs)	(010)-i	Insoluble
Na ₂ ZnCl ₄	2.382	—	—	—
Na ₃ AlF ₆	2.90	2.5 (Mohs)	(001)-p	Slightly soluble

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
Na ₃ GdSi ₃ O ₉	3.439	—	—	Insoluble
Na ₃ La(BO ₃) ₂	3.49	—	—	—
Na ₃ La ₂ (BO ₃) ₃	4.19	—	—	—
Na ₃ ScSi ₂ O ₇	2.861	—	—	Insoluble
Na ₃ YSi ₃ O ₉	2.962	—	—	Insoluble
NaAl(AsO ₄)F	3.64	5 (Mohs)	(110)-i	Slightly soluble
NaAl(PO ₄)F	3.126	4.5 (Mohs)	(111)-i	Insoluble
NaAlGeO ₄	3.337	—	(010)-p	Insoluble
NaAlSi ₃ O ₈	2.63	6–6.5 (Mohs)	(001)-p	Insoluble
NaBePO ₄	2.81	5.5 (Mohs)	(010)-p	Insoluble
NaBF ₄	2.53	3 (Mohs)	(100)(010)	Soluble
NaCaPO ₄	3.117	3 (Mohs)	—	—
NaCdPO ₄	4.10	—	—	—
NaGaGe ₂ O ₆	4.864	—	—	Insoluble
NaGaGeO ₄	4.028	—	(010)-p	Insoluble
NaGaSiO ₄	3.336	—	(010)-p	Insoluble
NaGdGeO ₄	5.366	—	—	Insoluble
NaGdP ₂ O ₇	4.287	—	—	Insoluble
NaGdP ₄ O ₁₂	3.45	—	—	Insoluble
NaGdSiO ₄	—	—	—	Insoluble
NaIn(MoO ₄) ₂	4.02	—	—	—
NaLaP ₂ O ₇	3.803	—	—	Insoluble
NaLaP ₄ O ₁₂	3.4	—	—	Insoluble
NaLiV ₂ O ₆	2.962	—	—	—
NaLuGeO ₄	6.025	—	—	Insoluble
NaLuP ₂ O ₇	4.114	—	—	Insoluble
NaLuSiO ₄	5.435	—	—	Insoluble
NaMgF ₃	3.06	—	—	—
NaNbO ₃	4.57	5.5 (Mohs)	—	Insoluble
NaScGeO ₄	3.39	—	—	Insoluble
NaScSi ₂ O ₆	3.22	—	—	Insoluble
NaSr ₃ Al ₃ F ₁₆	3.51	4 (Mohs)	None	Slightly soluble
NaTaO ₃	7.123	—	—	Insoluble
NaVO ₃	2.91	—	(110)-p	0.8
NaYGeO ₄	4.302	—	—	Insoluble
NaYO ₂	4.382	—	—	Slightly soluble
NaYSiO ₄	4.083	—	—	Insoluble
NaZnF ₃	4.105	—	—	—
NH ₄ B ₅ O ₈ •4H ₂ O	1.57	2.5 (Mohs)	(100)-p	—
Pb ₂ KNb ₅ O ₁₅	6.143	—	(001)	Insoluble
Pb ₂ NaNb ₅ O ₁₅	—	—	—	Insoluble
Pb ₂ V ₂ O ₇	6.46	3 (Mohs)	—	—
Pb ₃ (PO ₄) ₂	7.456	—	—	—

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
Pb ₃ (VO ₄) ₂	7.44	—	—	—
Pb ₃ GeO ₅	—	—	—	Insoluble
Pb ₃ MgNb ₂ O ₉	—	—	—	Insoluble
Pb ₃ ZnNb ₂ O ₉	—	—	—	Insoluble
PbBi ₂ Nb ₂ O ₉	6.684	—	—	Insoluble
PbBr ₂	6.693	—	(001)-p	—
PbCl ₂	5.85	31	(001)-p	0.99 (20)
PbCO ₃	6.55	3 (Mohs)	(110)(021)-i	Very slightly soluble
PbGeO ₃	6.968	—	—	Insoluble
PbO (massicot)	9.642	—	(100)-p	—
PbNb ₂ O ₆	—	—	—	Insoluble
PbSeO ₃	7.12	3.5 (Mohs)	(001)-p	—
PbSeO ₄	7.08	3.5 (Mohs)	None	—
PbSiO ₃	6.32	4.5 (Mohs)	(010)-p	Insoluble
PbSO ₄	6.32	3.5 (Mohs)	(001)(210)	Insoluble
PbTa ₂ O ₆	7.65	—	—	Insoluble
PbTiP ₂ O ₈	—	—	—	Insoluble
PbZnSiO ₄	6.13	3 (Mohs)	(120)-i	Insoluble
RbAlSiO ₄	—	—	—	Insoluble
RbB ₅ O ₈ •4H ₂ O	1.946	2.5 (Mohs)	—	—
Rb ₂ BeF ₄	3.749	—	—	—
RbBi(MoO ₄) ₂	5.52	—	—	—
RbGd ₂ Br ₇	4.79	—	—	Slightly soluble
RbLa(WO ₄) ₂	6.88	—	—	—
RbNbB ₂ O ₆	3.584	—	(001)-p	Insoluble
RbTaB ₂ O ₆	4.65	—	(001)-p	Insoluble
RbTiOAsO ₄	4.018	—	None	Insoluble
RbTiOPO ₄	3.647	—	None	Insoluble
Sb ₂ O ₃	5.83	2.5–3 (Mohs)	(110)-p	Insoluble
SbNbO ₄	5.68	5.5 (Mohs)	(010)-i	Insoluble
SbTaO ₄	7.53	5–5.5 (Mohs)	(010)-i	Insoluble
Sc(PO ₃) ₃	2.736	—	—	Insoluble
Sc ₂ (MoO ₄) ₃	3.102	—	—	—
Sc ₂ (WO ₄) ₃	4.566	—	(010)-p	Slightly soluble
Sc ₂ Si ₂ O ₇	—	—	—	Insoluble
(Sc,Y) ₂ Si ₂ O ₇	3.39	6.5 (Mohs)	(110)-i	Insoluble
Sc ₂ SiO ₅	3.49	—	—	Insoluble
Sc ₂ TiO ₅	3.611	—	—	Insoluble
ScAlBeO ₄	—	—	None	Insoluble
ScCaBO ₄	3.319	—	—	—
ScGaO ₃	5.10	—	(010)-p	Insoluble
ScGe ₂ O ₅	5.286	—	—	Insoluble
ScMgBO ₄	3.287	—	—	—

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
ScNbO ₄	4.843	—	(010)-p	Insoluble
ScTaO ₄	6.90	—	(010)-p	Insoluble
Sr ₂ (AsO ₄)Cl	—	—	(010)-p	—
Sr ₂ (VO ₄)Br	4.342	—	—	—
Sr ₂ (VO ₄)Cl	3.883	—	(010)-p	—
Sr ₂ KNb ₅ O ₁₅	—	—	—	Insoluble
Sr ₂ KTa ₅ O ₁₅	—	—	—	Insoluble
Sr ₂ NaNb ₅ O ₁₅	5.19	—	—	Insoluble
Sr ₂ Nb ₂ O ₇	5.204	—	—	Insoluble
Sr ₂ Ta ₂ O ₇	7.074	—	—	Insoluble
SrAl ₂ Ge ₂ O ₈	3.714	—	—	Insoluble
SrAl ₂ O ₄	3.554	—	—	—
SrAl ₂ Si ₂ O ₈	3.13	—	—	Insoluble
SrAl ₄ O ₇	3.266	—	—	—
SrB ₂ O ₄	3.350	—	—	—
SrCO ₃	3.79	3.5 (Mohs)	(010)-i	Very slightly soluble
SrGa ₂ O ₄	4.85	—	—	—
SrGa ₂ Si ₂ O ₈	3.797	—	—	Insoluble
SrGd ₂ O ₄	7.287	—	—	Insoluble
SrIn ₂ O ₄	6.854	—	—	—
SrLu ₂ O ₄	8.496	—	—	Insoluble
SrNb ₂ O ₆	—	—	—	Insoluble
SrSc ₂ O ₄	—	—	—	Insoluble
SrSiO ₃	3.66	—	—	Insoluble
SrSO ₄	3.97	3 (Mohs)	(001)-p	Insoluble
SrTa ₂ O ₆	—	—	—	Insoluble
SrY ₂ O ₄	5.344	—	—	—
SrZnGe ₂ O ₆	—	—	—	Insoluble
TeO ₂	6.00	2 (Mohs)	(010)-p	Very slightly soluble
TlNbB ₂ O ₆	—	—	(001)-p	Insoluble
TlTaB ₂ O ₆	—	—	(001)-p	Insoluble
V ₂ O ₅	3.37	—	—	—
Y ₂ (MoO ₄) ₃	3.3	—	—	Very soluble
Y ₂ (WO ₄) ₃	—	—	(010)-p	Very soluble
Y ₂ BeO ₄	4.582	—	—	Insoluble
Y ₂ GdSbO ₇	6.443	—	—	Insoluble
Y ₂ GdTaO ₇	7.102	—	—	Insoluble
Y ₂ GeO ₅	—	—	—	Insoluble
Y ₂ MgBe ₂ Si ₂ O ₁₀	4.152	6.5 (Mohs)	None	Insoluble
Y ₂ MoO ₆	5.366	—	—	—
Y ₂ O ₂ SO ₄	4.813	—	—	—
Y ₂ Si ₂ O ₇	4.3	6 (Mohs)	None	Insoluble
Y ₂ SiO ₅	4.543	6.5 (Mohs)	None	Insoluble

Physical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Density (g/cm ³)	Hardness (kg/mm ²)	Cleavage plane	Solubility (°C) (g/100 g H ₂ O)
Y ₂ Ti ₂ SiO ₉	—	—	—	Insoluble
Y ₂ WO ₆	6.818	—	—	—
Y ₃ SbO ₇	5.699	—	—	Insoluble
Y ₃ TaO ₇	6.413	—	—	Insoluble
Y ₄ Al ₂ O ₉	4.518	—	—	Insoluble
YAlO ₃	5.35	1030–1450	(110)-p	Insoluble
YCa ₄ O(BO ₃) ₃	—	6–6.5 (Mohs)	None	Insoluble
YCaGaBe ₂ Si ₂ O ₁₀	4.107	6.5 (Mohs)	None	Insoluble
YF ₃	5.056	—	—	—
YGd ₂ Nb ₂ O ₉	6.802	—	—	Insoluble
YHfTaO ₆	8.13	—	—	Insoluble
YNbO ₄	5.58	—	—	Insoluble
YP ₅ O ₁₄	—	—	—	Insoluble
YScO ₃	4.94	—	—	Insoluble
YTaO ₄	7.579	—	—	Insoluble
YTiTaO ₆	6.51	—	—	Insoluble
Zn ₃ (AsO ₃) ₂	4.27	5 (Mohs)	(110)-i	Insoluble
Zn ₃ (BO ₃) ₂	4.12	—	—	—
ZnB ₄ O ₇	3.07	—	—	—
ZnWO ₄	7.87	—	—	—
ZrO ₂	5.82	6.5 (Mohs)	(001)-p	Insoluble

1.3 Optical Properties*

The optical properties of crystals in this section are grouped into three tables: isotropic crystals, uniaxial crystals, and biaxial crystals. Materials are listed alphabetically in order of the chemical formulas. The following properties are included:

Transmission Range: Electronic and lattice absorption edges are given in terms of the wavelengths between which the transmission of a 1-mm-thick sample at 300 K is $\geq 10\%$. The values cited are approximate and are intended to be a general guide because many factors such as impurities, imperfections, temperature, crystallographic orientations, and compositional variations can affect the values.

Band Gap: Band gap data for transitions at room temperature unless noted otherwise. The energy gap depends on the structure of the material and varies with direction in anisotropic crystals. Optical transition: (D) – direct, (I) – indirect.

Refraction Index (n): For isotropic crystals, there is only one refractive index. Uniaxial crystals with tetragonal, hexagonal, and trigonal (or rhombohedral) symmetry exhibit a unique index of refraction (symbolized as e or ϵ) when light vibrates parallel to the c -axis (the extraordinary ray). For light vibrating at 90° to the c -axis (the ordinary ray), the refractive indices are the same (symbolized as o or ω) in all 360° directions. Biaxial crystals with orthorhombic, monoclinic, and triclinic symmetry possess three significant indices of refraction, commonly symbolized as x, y, z or α, β, γ in the order from smallest to largest.

Unless specified, the refraction indices are the average values for standard daylight or are the values measured at 632.8 nm at room temperature (the differences in the daylight and He-Ne values are within 0.1%). In a few instances, e.g., tellurides, these materials are opaque to visible light so that the refractive indices are measured with an infrared light source. In these cases, the wavelength used is listed with parentheses.

Birefringence (Δn): Birefringence of anisotropic materials is a measure of the maximum difference of the refractive indices within a crystal for a given wavelength.

Dispersion formulas: Refractive indices at specific wavelengths within specified ranges can be derived from dispersion formulas given in Section 1.3.4. Note that several different functional forms have been used to represent the dispersion of the refractive index.

Thermooptic coefficients (dn/dt): Thermooptic coefficients of optical crystals at various wavelengths are given in Section 1.3.5.

* This section was adapted from “Optical crystals” by B. H. T. Chai, *Handbook of Laser Science and Technology, Suppl. 2, Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 3 ff (with additions).

1.3.1 Isotropic Crystals

Optical Properties of Isotropic Crystalline Materials

Cubic material	Transmission (μm)	Band gap (eV)	Refractive index n
AgBr	0.49–35	2.7 (I), 4.3 (D)	2.242
AgCl	0.42–28	3.2 (I), 5.1 (D)	2.0568
AlAs	0.6–15	2.153 (I)	2.87
Al ₂₃ O ₂₇ N ₅ (ALON)	0.23–4.8	—	1.79
β -AlN	4.9	—	—
AlSb	—	1.63 (I), 2.22 (D)	—
As ₂ O ₃	—	4–5	1.755
Ba(NO ₃) ₂	—	—	1.5714
BaF ₂	0.14–13	9.1	1.4733
BaF ₂ –CaF ₂	0.15–12	—	—
Bi ₁₂ GeO ₂₀	0.47–7	—	2.5476
Bi ₁₂ SiO ₂₀	0.52–	—	—
Bi ₁₂ TiO ₂₀	—	—	2.5619
Bi ₄ Ge ₃ O ₁₂	0.31–6	4.2	1.835
Bi ₄ Si ₃ O ₁₂	—	—	2.051
BN	0.2–6	7.5 (I)	≈2.117
BP	0.5–6	2 (I)	2.8
Ca ₁₂ Al ₁₄ O ₃₃	0.35–6	—	1.643
Ca ₃ Al ₂ Si ₃ O ₁₂	—	—	1.734
Ca ₃ Ga ₂ Ge ₃ O ₁₂	—	—	1.814
C (diamond)	0.24–2.7	5.47	2.4175
CaF ₂	0.12–10	10	1.433
CaLa ₂ S ₄	0.65–14.3	—	2.7
CaO	0.2–10	7.7	1.838
CdF ₂	0.13–12	6	1.562
CdO	—	2.3	2.49
CdTe	0.9–30	1.56 (D)	2.817
CsBr	0.23–440	6.9	1.6929
CsCl	0.19–30	7.4	1.64
CsF	0.27–>15	10 (80 K)	1.48
CsI	0.25–62	6.2	1.7806
Cu ₂ O	—	2.1 (I), 2.6 (D)	—
CuBr	0.45–26	3.0 (80 K)	2.117
CuCl	0.4–19	3.3 (80 K)	1.97
CuI	—	3.1	2.346
GaAs	0.9–17.3	1.42 (D)	4.02
β -GaN	—	3.3	—
GaP	0.54–10.5	2.26 (I), 2.78 (D)	3.350
GaSb	1.7–20	0.726 (D)	3.82 (1.8 μm)
Gd ₂ Ti ₂ O ₇	—	—	2.36
Gd ₃ Ga ₅ O ₁₂	0.32–6	—	1.9637
Gd ₃ Sc ₂ Al ₃ O ₁₂	—	—	1.901

Optical Properties of Isotropic Crystalline Materials—*continued*

Cubic material	Transmission (μm)	Band gap (eV)	Refractive index n
Gd ₃ Sc ₂ Ga ₃ O ₁₂	—	—	1.9628
Ge	1.8–15	0.664 (I)	4.052 (2.8 μm)
HgS	—	—	2.5
HgSe	2.1–20	0.6	—
HgTe	6–30	0.17 (D)	—
InAs	3.8–15	0.354 (D)	4.10
β -InN	4.98	—	—
InP	0.93–14	1.344 (D)	3.43
InSb	6–25	0.17	5.13
K ₂ Mg ₂ (SO ₄) ₃	—	—	1.53
K ₂ NaAlF ₆	—	—	1.376
KBr	0.20–306	7.6 (D)	1.5566
KCl	0.18–25	8.5 (D)	1.4879
KF	0.146–16	10.9 (D)	1.362
KI	0.25–39	6.2 (D)	1.6581
KMgF ₃	—	—	1.404
KTaO ₃		3.5	2.2
LiBaF ₃	—	—	1.544
LiBr	—	7.9 (D)	1.78
LiCl	—	9.3 (D)	1.66
LiF	0.12–6.6	13.6 (D)	1.3912
LiI	—	6 (D)	1.95
Lu ₂ O ₃		3.9 (733 K)	—
Lu ₂ Ti ₂ O ₇	—	—	2.57
Lu ₃ Al ₅ O ₁₂	—	—	1.842
Mg ₃ Al ₂ Si ₃ O ₁₂	—	—	1.713
MgAl ₂ O ₄	0.21–5.3	—	1.715
MgGa ₂ O ₄	—	—	1.879
MgO	0.16–9	7.8 (D)	1.735
MnO	—	3.7	2.18
Na ₃ Li ₃ Al ₂ F ₁₂	0.15–13	—	1.3395
Na ₃ Li ₃ Ga ₂ F ₁₂	0.15–13	—	—
Na ₃ Li ₃ In ₂ F ₁₂	0.15–13	—	—
Na ₃ Li ₃ Sc ₂ F ₁₂	0.15–13	—	—
Na ₈ Al ₆ Si ₆ O ₂₄ Cl ₂	—	—	1.483
NaBr	0.2–24	7.5 (D)	1.64
NaCl	0.17–18	9.0 (D)	1.531
NaF	0.13–12	10.5	1.326
5NaF-9YF ₃	—	—	1.470
NaI	0.26–24	5.9 (D)	1.77
Pb(NO ₃) ₂	—	—	1.780
PbF ₂	0.29–12.5	5.0	1.7611
PbI ₂	—	2.4	—
PbS	3–7	0.42 (D)	4.1 (3 μm)

Optical Properties of Isotropic Crystalline Materials—*continued*

Cubic material	Transmission (μm)	Band gap (eV)	Refractive index n
PbSe	4.5–20	0.278 (D)	4.59 (3 μm)
PbTe	4–30	0.311 (D)	5.35 (3 μm)
RbBr	0.23–40	7.25 (D)	1.55
RbCaF ₃	—	—	—
RbCl	0.2–30	8.3 (D)	1.49
RbF	—	10.4 (80 K)	—
RbI	0.26–50	5.83 (D)	1.64
Sb ₂ O ₃	—	—	2.087
Sc ₂ O ₃	—	—	1.964
Si	1.1–6.5	1.124 (I)	3.4777 (1.55 μm)
β -SiC	0.5–4	2.6 (I)	~2.6
SrF ₂	0.13–12	9.4	1.4371
SrSnO ₃	—	—	1.90
SrTiO ₃	0.4–5.1	4.1	2.3878
ThO ₂	0.22–9	5.7	2.07
Tl(Br,I)	0.58–42	—	2.573
Tl(Cl,Br)	0.42–27	—	2.329
Tl ₂ O ₃	—	—	—
TlBr	0.44–38	3.1 (D)	2.384
TlCl	0.4–30	3.6	2.223
Y ₂ O ₃	0.29–7.1	5.6	1.92
Y ₂ Ti ₂ O ₇	—	—	2.34
Y ₃ Al ₅ O ₁₂	0.21–5.2	—	1.8289
Y ₃ Fe ₅ O ₁₂	—	—	2.25 (μm)
Y ₃ Ga ₅ O ₁₂	—	—	1.913
Y ₃ Sc ₂ Al ₃ O ₁₂	—	—	1.96
ZnAl ₂ O ₄	—	—	1.7902
β -ZnS	0.4–12.5	3.68 (D)	2.3505
β -ZnS(CVD)	—	—	2.36
ZnSe	0.5–20	2.71 (D)	2.5907
ZnSe (CVD)	—	—	2.59
ZnSiAs ₂	—	2.1	—
ZnTe	0.55–25	2.30 (D)	2.962
ZrO ₂	0.35–7	5.0	2.1226
ZrO ₂ :Y ₂ O ₃	0.38–6.0	~4.1	2.12

1.3.2 Uniaxial Crystals

Optical Properties of Uniaxial Crystalline Materials

Uniaxial material	Transmission (μm)	Band gap (eV)	Refractive index n_e	Refractive index n_o	Birefringence Δn
Ag ₃ AsS ₃	0.61–13.5	2.1	2.738	3.019	–0.281
Ag ₃ SbS ₃	0.7–14	–	2.67	2.86	–0.19
AgGaS ₂	0.5–13	2.6	2.507	2.554	–0.047
AgGaSe ₂	0.78–18	1.7	2.676	2.700	–0.024 (1 μm)
β -AgI	–	2.9	2.21	2.22	–0.01
Al ₂ O ₃	0.19–5.2	9.9	1.7579	1.7659	–0.008
AlF ₃	–	–	1.3765	1.3770	–0.0005
α -AlN	–	6.23 (D)	2.13	2.20	–0.07
AlPO ₄	0.2–3.6	–	1.5334	1.5243	0.0091
Ba ₂ TiSi ₂ O ₈	0.3–5	–	1.765	1.775	–0.001
Ba ₂ ZnSi ₂ O ₇	–	–	1.710	1.724	–0.014
Ba ₃ (VO ₄) ₂	0.3–5.6	–	–	–	–
Ba ₅ (AsO ₄) ₃ Cl	–	–	1.880	1.884	0.004
Ba ₅ (VO ₄) ₃ Cl	–	–	1.870	1.900	0.030
BaAl ₂ O ₄	–	–	1.657	?	–
β -BaB ₂ O ₄	0.19–3.5	6.2	1.54254	1.65510	0.11256
BaBe(PO ₄)F	–	–	1.632	1.629	0.003
BaGe ₄ O ₉	–	–	–	–	5.147
BaSnSi ₃ O ₉	–	–	1.674	1.685	–0.011
BaZrSi ₃ O ₉	–	–	1.6751	1.6850	–0.0099
Be ₂ GeO ₄	–	–	1.720	1.734	–0.014
Be ₂ SiO ₄	–	–	1.670	1.654	0.016
Be ₃ Al ₂ Si ₆ O ₁₈	–	–	1.5682	1.5746	–0.0064
Be ₃ Sc ₂ Si ₆ O ₁₈	–	–	1.607	1.627	0.02
BeMg ₃ Al ₈ O ₁₆	–	–	1.717	1.722	0.005
BeO	0.11–4.5	10.6 (D)	1.7322	1.7166	0.0156
Bi ₂ Ge ₃ O ₉	0.25–6.5	–	2.08	2.01	0.07
Ca ₂ Al ₂ SiO ₇	–	–	1.658	1.669	–0.011
Ca ₂ MgSi ₂ O ₇	–	–	1.64	1.632	0.008
Ca ₂ Te ₂ O ₅	–	–	2.00	1.89	0.11
Ca ₂ ZnSi ₂ O ₇	–	–	1.657	1.669	–0.012
Ca ₃ Ga ₂ Ge ₄ O ₁₄	0.26–6.5	–	1.822	1.795	0.027
Ca ₅ (AsO ₄) ₃ F	–	–	1.698	1.706	–0.008
Ca ₅ (PO ₄) ₃ Cl	–	–	1.647	1.650	–0.003
Ca ₅ (PO ₄) ₃ F	–	–	1.624	1.629	–0.005
Ca ₅ (VO ₄) ₃ Cl	–	–	1.865	1.893	0.028
CaAl ₁₂ O ₁₉	–	–	1.79	1.807	–0.017
CaAl ₂ B ₂ O ₇	–	–	–	1.563	–
CaCO ₃ –calcite	0.2–5.5	5.9	1.486	1.658	–0.172

Optical Properties of Uniaxial Crystalline Materials—*continued*

Uniaxial material	Transmission (μm)	Band gap (eV)	Refractive index n_e	Refractive index n_o	Birefringence Δn
CaCO ₃ —vaterite	—	—	1.65	1.55	0.10
CaGdAlO ₄	0.35–7	—	1.9564	1.9331	0.0233
CaGe ₄ O ₉	—	—	1.78	—	—
CaLa ₄ (SiO ₄) ₃ O	—	—	1.7637	1.7915	-0.028
CaLaAlO ₄	0.35–7	—	—	≈2.6	—
CaMg(CO ₃) ₂	—	—	1.503	1.680	-0.177
CaMg ₃ (CO ₃) ₄	—	—	1.609	1.708	0.099
CaMoO ₄	—	—	1.9796	1.9703	0.0093
CaSnB ₂ O ₆	—	—	1.660	1.778	-0.118
CaWO ₄	0.13–5.6	—	1.9375	1.9208	0.017
CaYAlO ₄	0.35–7	—	—	—	—
CaZrBaAl ₉ O ₁₈	—	—	1.7875	1.8159	-0.0284
CdCl ₂	—	5.7	1.681	1.719	-0.038
CdCO ₃	—	—	—	1.842	—
CdI ₂	—	3.9	—	1.574	—
CdS	0.51–14.8	2.42 (D)	2.529	2.506	0.023
CdSe	0.75–20	1.70 (D)	2.557	2.537	0.02
CsD ₂ AsO ₄	0.27–1.66	—	1.53	1.55	-0.02
CsD ₂ PO ₄	0.27–1.66	—	—	—	—
CsGa(SO ₄) ₂	—	—	—	—	—
CsH ₂ AsO ₄	0.26–1.43	—	1.53	1.55	-0.02
CsLiB ₆ O ₁₀	0.18–2.7	—	—	—	—
α-GaN	—	3.37 (D)	~2.25	~2.29	~0.04
GaS		2.3 (I), 3.8 (D)	—	—	—
GaSe	0.65–18	—	2.57	2.91	0.34 (1 μm)
Gd ₂ GeBe2O ₇	—	—	—	—	—
GdAl ₃ (BO ₃) ₄	—	—	1.720	1.780	-0.060
GdB ₃ O ₃	—	—	1.840	1.824	0.016
GeO ₂	0.25–5	5.6	—	1.6045	—
Hg ₂ Br ₂	0.4–30	2.6	—	—	—
Hg ₂ Cl ₂	0.36–20	3.9	2.656	1.973	0.683
Hg ₂ I ₂	0.45–40	2.4	—	—	—
HgI ₂	—	2.1	—	—	—
HgS	0.6–28	2	3.232	2.885	0.347
InN	—	1.99	~2.09	—	—
In ₂ O ₃	—	2.7 (I)	—	—	—
InBO ₃	—	—	1.773	1.873	-0.100
K ₂ Al ₂ B ₂ O ₇	0.18–3.6	—	—	—	—
K ₂ BiNb ₅ O ₁₅	—	—	2.253	2.237	0.016
K ₂ CaZr(SiO ₃) ₄	—	—	1.655	1.625	0.03
K ₂ Sr(SO ₄) ₂	—	—	1.549	1.569	-0.020
K ₃ LiNb ₅ O ₁₅	—	—	2.156	2.294	0.148
KAlSi ₂ O ₆	—	—	1.509	1.508	0.001

Optical Properties of Uniaxial Crystalline Materials—continued

Uniaxial material	Transmission (μm)	Band gap (eV)	Refractive index n_e	Refractive index n_o	Birefringence Δn
KAlSiO ₄	—	—	1.5372	1.541	-0.0038
KBe ₂ BO ₃ F ₂	0.155	—	1.406	1.472	-0.066
KD ₂ PO ₄	0.20–1.5	—	1.46	1.49	0.03
KH ₂ PO ₄	0.18–1.5	7.0	1.4669	1.5074	-0.0405
KZnF ₃	—	—	—	—	—
La ₂ GeBe ₂ O ₇	—	—	1.905	1.890	0.015
La ₂ O ₃	—	2.9 (530 K)	—	—	—
La ₂ WO ₆	—	—	2.18	2.16	0.02
La ₃ Ga ₅ GeO ₁₄	0.24–7.5	—	1.940	1.925	0.015
La ₃ Ga ₅ SiO ₁₄	0.35 —	—	1.9106	1.89965	0.01141
La ₃ Nb _{0.5} Ga _{5.5} O ₁₄	0.29–6.7	—	1.896	1.955	0.059
La ₃ Ta _{0.5} Ga _{5.5} O ₁₄	0.29–6.7	—	1.970	1.945	0.025
LaAlO ₃	—	—	—	—	—
LaBaGa ₃ O ₇	—	—	1.850	1.845	0.005
LaBSiO ₅	—	—	1.7753	1.7843	-0.009
LaCaGa ₃ O ₇	—	—	1.831	1.826	0.005
LaCl ₃	—	—	1.8929	1.8265	0.0664
LaF ₃	0.2–10	6.6	1.602	1.606	0.004
LaSrGa ₃ O ₇	—	—	1.820	1.806	0.014
Li ₂ B ₄ O ₇	—	—	1.560	1.605	-0.045
LiAlSiO ₄	—	—	1.572	1.56	0.012
LiCaAlF ₆	—	—	1.3852	1.3882	-0.003
LiGdF ₄	—	—	1.474	1.502	-0.028
LiIO ₃	0.38–5.5	4.0	1.7351	1.8815	-0.1464
LiLuF ₄	—	—	1.468	1.494	-0.026
LiNbO ₃	0.35–5.0	4.0	2.156	2.232	-0.076
LiSrAlF ₆	—	—	1.384	1.380	0.004
LiTaO ₃	—	—	2.188	2.183	-0.005
LiYF ₄	0.12–8	~11	1.4762	1.4535	0.0227
LuAl ₃ (BO ₃) ₄	—	—	1.712	1.771	-0.059
Mg ₂ Al ₃ (Si ₅ Al)O ₁₈	—	—	1.527	1.524	0.003
MgCO ₃	—	—	1.510	1.700	-0.190
MgF ₂	0.13–7.7	10.8	1.3886	1.3768	0.0118
MgTiO ₃	—	—	1.95	2.31	-0.36
MnF ₂	—	10.2	—	—	—
Na ₂ Al ₂ B ₂ O ₇	—	—	1.504	1.540	-0.036
Na(Li,Al) ₃ Al ₆ (BO ₃) ₃ -Si ₆ O ₁₈ (OH)	variable	—	1.615–1.632	1.635–1.65	0.0180–0.0200
NaNO ₃	0.35–3	—	1.3361	1.5874	-0.251
NaSbBe ₄ O ₇	—	—	1.770	1.772	0.002
NaScO ₂	—	—	—	—	—
NH ₄ H ₂ PO ₄	0.19–1.5	6.8	1.48	1.53	-0.0458
Pb ₃ Ca ₂ (AsO ₄) ₃ Cl	—	—	1.948	1.958	-0.010

Optical Properties of Uniaxial Crystalline Materials—*continued*

Uniaxial material	Transmission (μm)	Band gap (eV)	Refractive index n_e	Refractive index n_o	Birefringence Δn
Pb ₅ (AsO ₄) ₃ Cl	—	—	2.106	2.124	-0.018
Pb ₅ (PO ₄) ₃ Cl	—	—	2.408	2.058	-0.010
Pb ₅ (PO ₄) ₃ F	—	—	—	—	—
Pb ₅ (VO ₄) ₃ Cl	—	—	2.350	2.416	-0.066
PbAl ₁₂ O ₁₉	—	—	1.88	1.80	0.08
PbMoO ₄	0.4–5.9	3.6	2.2584	2.3812	-0.123
PbO-litharge	—	2.8	2.535	2.655	0.130
PbWO ₄	—	5.6	2.19	2.27	-0.08
RbH ₂ AsO ₄	0.26–1.46	—	1.50	1.55	-0.05
RbH ₂ PO ₄	0.22–1.4	—	1.47	1.50	-0.03
ScBO ₃	—	—	1.780	1.872	-0.092
Se	1–30	1.7	3.61	2.79	0.82 (1 μm)
α-SiC	0.5–4	2.8 (I)	~2.6	—	—
Si ₃ N ₄	0.3–4.6	5	—	2.04	—
α-SiO ₂	0.16–4.0	8.4	1.56	1.55	0.0095
SnO ₂	—(4.3)	2.5 (I), 3.4 (D)	2.091	1.990	0.010
Sr ₂ MgGe ₂ O ₇	—	—	1.800	1.816	-0.016
Sr ₃ Ga ₂ Ge ₄ O ₁₄	0.26–6.8	—	1.85	1.8336	0.0164
Sr ₅ (PO ₄) ₃ F	—	—	1.6252	1.6314	-0.062
Sr ₅ (VO ₄) ₃ F	—	—	1.809	1.824	-0.015
Sr ₅ (VO ₄) ₃ Cl	—	—	1.868	1.895	0.027
SrAlF ₅	0.16–7	—	—	—	—
(Sr _{0.6} Ba _{0.4})Nb ₂ O ₆	0.5–5.5	—	2.270	2.310	0.04
SrGdGa ₃ O ₇	—	—	1.830	1.838	0.008
SrLa ₄ (SiO ₄) ₃ O	—	—	1.8227	1.8567	-0.034
SrMoO ₄	—	—	1.9110	1.9064	0.0046
Ta ₂ O ₅	—(4.6)	—	2.21	2.20	0.01
TaBO ₄	—	—	> 2.12	> 2.12	—
Te	3.5–32	0.33	4.929	6.372	-1.45 (4 μm)
ThSiO ₄	—	—	1.79	1.78	0.01
TiO ₂ (rutile)	0.42–4.0	3.5 (D)	2.872	2.584	0.288
Tl ₃ AsS ₃	1.26–17	—	—	—	—
Tl ₃ AsSe ₃	1.3–16	—	3.227	3.419	-0.192
Y ₂ SiBe ₂ O ₇	—	—	1.80	1.83	-0.03
YAl ₃ (BO ₃) ₄	—	—	1.704	1.778	0.074
YAsO ₄	—	—	1.879	1.783	0.096
YBO ₃	—	—	1.802	1.788	0.014
YPO ₄	—	—	1.816	1.827	-0.011
YVO ₄	0.35–4.8	—	2.2148	1.9915	0.2233
Zn ₂ SiO ₄	—	—	1.719	1.691	0.028
ZnCO ₃	—	—	1.625	1.850	-0.275
ZnCl ₂	~0.4–~15	—	—	—	—
ZnF ₂	—	—	1.502	1.529	-0.027

Optical Properties of Uniaxial Crystalline Materials—continued

Uniaxial material	Transmission (μm)	Band gap (eV)	Refractive index n_e	Refractive index n_o	Birefringence Δn
ZnGeP ₂	0.74–15	—	3.28	3.23	0.05 (1 μm)
ZnO	0.37–	3.35 (D)	2.015	1.998	0.017
ZnSb ₂ O ₆	—	—	>1.95	>1.95	—
α -ZnS	—	—	2.378	2.356	0.022
ZrO ₂	—	4.99–	—	—	—
ZrSiO ₄	0.4–	—	1.967	1.920	0.042

1.3.3 Biaxial Crystals

Optical Properties of Biaxial Crystalline Materials

Biaxial material	Transmission (μm) [Band gap (eV)]	Refractive index n_x	Refractive index n_y	Refractive index n_z	Birefringence Δn
Al ₂ (WO ₄) ₃	0.3–5.0	—	—	—	—
Al ₂ SiO ₄ F ₂	—	1.630	1.631	1.638	0.008
Al ₂ SiO ₅ (andalusite)	—	1.629	1.633	1.638	0.009
Al ₂ SiO ₅ (kyanite)	—	1.712	1.720	1.727	0.015
Al ₂ SiO ₅	—	1.653	1.654	1.669	0.023
Al ₄ B ₂ O ₉	—	1.605	1.610	1.645	0.040
Al ₆ Ge ₂ O ₁₃	—	1.72	—	1.758	0.046
Al ₆ Si ₂ O ₁₃	0.21	1.642	1.644	1.654	0.012
AlNb ₁₁ O ₂₉	—	2.20	—	2.22	0.02
AlNbO ₄	—	1.985	—	2.005	0.02
As ₂ S ₃	[2.5]	2.4	2.81	3.02	~0.6
AsS	—	2.538	2.684	2.704	0.116
AsSbS ₃	—	—	>2.11	>2.73	>0.62
Ba ₂ CaMgAl ₂ F ₁₄	—	1.441	1.442	1.444	0.003
Ba ₂ NaNb ₅ O ₁₅	0.38–6.0	2.2177	2.3205	2.3222	0.1045
BaAl ₂ Si ₂ O ₈	—	1.587	1.593	1.600	0.013
BaBe ₂ Si ₂ O ₇	—	1.694	1.70	1.706	0.012
BaCa ₂ Mg(SiO ₄) ₂	—	1.731	—	1.752	0.021
BaCa ₂ Si ₃ O ₉	—	1.668	1.684	1.685	0.017
BaCO ₃	—	1.530	1.679	1.680	0.150
BaMgF ₄	0.185–10	1.4496	1.4661	1.4738	0.0242
β -BaSi ₂ O ₅	—	1.598	1.617	1.625	0.027
BaSO ₄	—	1.6362	1.6373	1.6482	0.012
BaY ₂ F ₈	0.2–9.5	1.5142	1.5232	1.5353	0.0211
Be ₂ BO ₃ F	—	1.554	1.587	1.628	0.074
BeAl ₂ O ₄	—	1.746	1.748	1.756	0.010
BiB ₃ O ₆	0.3–2.5	—	—	—	—

Optical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Transmission (μm) [Band gap (eV)]	Refractive index n_x	Refractive index n_y	Refractive index n_z	Birefringence Δn
Bi ₂ Mo ₃ O ₁₂	0.42–5.2 [2.9]	2.254	2.306	2.497	0.243
Bi ₂ O ₃	[2.8]	?	2.42	?	—
Bi ₂ WO ₆	—	—	2.2	—	—
BiSbO ₄	—	2.04	—	2.14	0.10
BiTaO ₄	—	—	2.35	—	—
BiVO ₄ (puucherite)	—	2.41	2.50	2.51	0.10
Ca(IO ₃) ₂	—	1.792	1.840	1.888	0.096
β -Ca ₂ SiO ₄	—	1.707	1.715	1.730	0.023
Ca ₂ (VO ₄)Cl	—	1.835	—	1.865	0.03
Ca ₂ Al ₂ O ₅	—	1.96	2.01	2.04	0.08
Ca ₂ V ₂ O ₇	—	1.942	2.00	2.132	0.19
Ca ₃ (VO ₄) ₂	—	1.864	1.885	1.890	0.026
Ca ₃ (Zr,Ti)Si ₂ O ₉	—	1.735	1.737	1.758	0.023
Ca ₃ MgSi ₂ O ₈	—	1.706	1.712	1.724	0.018
Ca ₃ Si ₂ O ₇	—	1.641	1.644	1.650	0.009
Ca ₅ Al ₆ O ₁₄	—	1.68	1.682	1.685	0.005
Ca ₅ Ga ₆ O ₁₄	0.255–6.5	—	—	—	—
CaAl ₂ F ₈	—	1.501	1.503	1.510	0.009
CaAl ₂ Si ₂ O ₈	—	1.577	1.585	1.590	0.013
CaAl ₄ O ₇	0.23–5.1	1.6178	1.6184	1.6516	0.0338
CaAlB ₃ O ₇	—	1.712	1.717	1.726	0.014
CaAlBO ₄	—	1.558	1.585	1.614	0.056
CaB ₂ Si ₂ O ₈	—	1.630	1.633	1.635	0.005
CaB ₃ O ₅ F	—	1.612	1.636	1.653	0.041
CaBa(CO ₃) ₂	—	1.5261	1.6710	1.6717	0.146
CaBe(PO ₄)F	—	1.580	1.600	1.610	0.030
CaBe ₂ (PO ₄) ₂	—	1.595	1.601	1.604	0.009
CaCO ₃ - α	—	1.530	1.6810	1.6854	0.1554
CaGe ₂ O ₅	—	1.84	—	1.88	0.04
CaMgAsO ₄ F	—	1.640	1.660	1.675	0.035
CaMgB ₂ O ₅	—	1.635	1.681	1.698	0.063
CaMgSi ₂ O ₆	—	1.664	1.671	1.694	0.030
CaMgSiO ₄	—	1.641	1.649	1.655	0.014
CaNb ₂ O ₆	0.3–5.5	2.07	2.10	2.19	0.12
CaSc ₂ O ₄	0.3–6.5	—	—	—	—
CaSiO ₃	—	1.615	1.627	1.629	0.014
CaSnSiO ₅	—	1.765	1.784	1.799	0.034
CaSO ₄	—	1.570	1.575	1.614	0.044
CaTiSiO ₅	—	1.84	1.870	1.943	0.103
CaV ₂ O ₆	—	1.916	1.995	2.13	0.214
CaZnSiO ₄	—	1.767	1.770	1.774	0.007
CaZrSi ₂ O ₇	—	1.720	1.736	1.738	0.018
Cd ₂ B ₆ O ₁₁	—	1.617	1.630	—	—

Optical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Transmission (μm) [Band gap (eV)]	Refractive index n_x	Refractive index n_y	Refractive index n_z	Birefringence Δn
CsB ₃ O ₆	0.17–3.0	1.5294	1.5588	1.5864	0.0570
CsNbO(SO ₄) ₂	—	1.597	1.604	1.703	0.106
CsTiOAsO ₄	0.35–5.3	1.8796	1.8961	1.9608	0.0812
β -Ga ₂ O ₃	0.3–4.5	—	1.962	—	—
Gd ₂ O ₃	[2.9, 933 K]	—	—	—	—
Gd ₂ (MoO ₄) ₃	0.32–5.2	1.8385	1.8390	1.8915	0.053
Gd ₂ SiO ₅	0.2–5	1.871	1.884	1.910	0.039
GdP ₅ O ₁₄	—	1.6094	1.6158	1.6298	0.0204
HfO ₂	[5.5]	—	—	—	—
HgCl ₂	—	1.725	1.859	1.965	0.240
HIO ₃	0.3–1.8	2.37	2.5	2.65	0.280
InPO ₄	—	1.608	1.618	1.623	0.015
KAl ₃ Si ₃ O ₁₀ (OH) ₂	—	1.552	1.582	1.587	0.036
KAlSi ₃ O ₈	—	1.518	1.520	1.523	0.005
KBF ₄	—	1.324	1.325	1.325	0.001
KB ₅ O ₈ •4H ₂ O	0.16–1.5	1.422	1.435	1.488	0.066
KLaP ₄ O ₁₂	—	1.592	1.600	1.608	0.016
KNbB ₂ O ₆	0.27–3.1	1.773	1.773	1.801	0.028
KNbO ₃	0.4–4.5	2.168	2.279	2.329	0.161
KNO ₃	—	1.332	1.505	1.509	0.172
KPbCl	0.3–20	n≈2			
KTiOAsO ₄	0.35–3.0	1.8079	1.8138	1.9044	0.0965
KTiOPO ₄	0.35–4.5 [3.5]	1.7614	1.7704	1.8636	0.1022
KVO ₃	0.4–5.5	—	—	—	—
La(BO ₂) ₃	—	1.694	1.769	1.791	0.097
La ₂ Be ₂ O ₅	0.3–4	1.9641	1.9974	2.0348	0.071
La ₂ Ti ₂ O ₇	—	2.17	2.24	2.265	0.095
LaBO ₃	—	1.800	1.877	1.882	0.082
LaP ₅ O ₁₄	—	1.5956	1.6015	1.6145	0.0189
LaPO ₄	—	1.774	1.77	1.828	0.054
Li ₂ BeSiO ₄	—	1.622	1.633	1.638	0.016
Li ₂ CO ₃	—	1.430	1.567	1.570	0.140
Li ₂ GeO ₃	—	?	1.686	?	—
Li ₃ PO ₄	—	1.550	1.557	1.566	0.016
Li ₃ VO ₄	0.32 —	—	—	—	—
LiAl(PO ₄)F	—	1.575	1.587	1.590	0.015
LiAlSi ₂ O ₆	—	1.648	1.655	1.662	0.014
LiAlSi ₄ O ₁₀	—	1.504	1.510	1.516	0.012
LiB ₃ O ₅	0.16–2.6	1.5742	1.6014	1.6163	0.0421
LiBO ₂	—	1.540	1.612	1.616	0.076
LiGaO ₂	0.25–6	1.730	1.758	1.761	0.031
LiVO ₃	0.5–5.5	1.850	1.970	2.13	0.28
Lu ₂ SiO ₅	0.2–5	1.797	1.803	1.825	0.028

Optical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Transmission (μm) [Band gap (eV)]	Refractive index n_x	Refractive index n_y	Refractive index n_z	Birefringence Δn
LuP ₅ O ₁₄	—	1.5950	1.6072	1.6125	0.0175
Mg ₂ (PO ₄)F	—	1.569	1.570	1.580	0.011
Mg ₂ B ₂ O ₅	—	1.596	1.639	1.670	0.074
Mg ₂ GeO ₄	—	1.698	1.717	1.765	0.067
Mg ₂ SiO ₄	—	1.635	1.651	1.670	0.035
Mg ₃ (PO ₄) ₂	—	1.540	1.544	1.559	0.015
Mg ₃ B ₂ O ₆	—	1.652	1.653	1.673	0.021
Mg ₃ B ₇ O ₁₃ Cl	—	1.658	1.662	1.668	0.010
Mg ₃ TiB ₂ O ₈	—	1.806	1.809	1.830	0.024
Mg ₄ Al ₈ Si ₂ O ₂₀	—	1.701	1.703	1.705	0.004
Mg ₅ (BO ₃) ₃ F	—	1.614	1.623	1.648	0.034
Mg ₂ SiO ₄	—	1.635	1.651	1.670	0.035
MgAl ₃ BSiO ₉	—	1.590	1.618	1.623	0.033
MgAlBO ₄	—	1.667	1.697	1.705	0.038
MgMoO ₄	—	1.82	1.83	1.84	0.02
MgSiO ₃	—	1.654	1.655	1.665	0.011
Na ₂ BaTi ₂ Si ₄ O ₁₄	—	1.727	1.732	1.789	0.062
Na ₂ BeSi ₂ O ₆	—	1.544	1.549	1.549	0.005
Na ₂ Ca(PO ₄)F	—	1.508	1.515	1.520	0.012
Na ₂ CaMg(PO ₄) ₂	—	1.598	1.605	1.608	0.010
Na ₂ MgAlF ₇	—	1.346	1.348	1.350	0.004
Na ₂ MgSiO ₄	—	1.534	1.536	1.543	0.009
Na ₂ Si ₂ O ₅	—	1.507	1.517	1.521	0.014
Na ₂ Ti ₂ Si ₂ O ₉	—	1.91	2.01	2.03	0.12
Na ₃ AlF ₆	—	1.338	1.338	1.339	0.001
NaAl(AsO ₄)F	—	1.634	1.672	1.685	0.051
NaAl(PO ₄)F	—	1.545	1.554	1.565	0.020
NaAlSi ₃ O ₈	—	1.527	1.531	1.538	0.011
NaBe ₂ BO ₃ F ₂	~0.15—	1.370	1.474	1.474	0.104
NaBePO ₄	—	1.552	1.558	1.561	0.009
NaBF ₄	—	1.301	1.3012	1.3068	0.0058
NaCaPO ₄	—	1.607	1.610	1.616	0.009
NaMgF ₃	—	—	1.364	—	—
NaNbO ₃	—	2.10	2.19	2.21	0.11
NaScSi ₂ O ₆	—	1.683	1.715	1.724	0.041
NaSr ₃ Al ₃ F ₁₆	—	1.429	1.433	1.436	0.007
NaVO ₃	0.4–5.5	—	—	—	—
NaZnF ₃	—	—	1.440	—	—
NH ₄ B ₅ O ₈ •4H ₂ O	—	1.42	1.43	1.48	0.06
Pb ₂ KNb ₅ O ₁₅	—	2.39	2.445	2.46	0.07
Pb ₂ V ₂ O ₇	—		2.2–2.6		0.279
PbBr ₂	0.36–30 [3.3]	—	—	—	—
PbCl ₂	0.35–20	2.1992	2.2172	2.2596	0.0604

Optical Properties of Biaxial Crystalline Materials—*continued*

Biaxial material	Transmission (μm) [Band gap (eV)]	Refractive index n_x	Refractive index n_y	Refractive index n_z	Birefringence Δn
PbCO ₃	—	1.803	2.074	2.076	0.273
PbO (massicot)	[1.7]	2.51	2.61	2.71	0.200
PbSeO ₃	—	2.12	2.14	2.14	0.02
PbSeO ₄	—	1.96	1.97	1.98	0.02
PbSiO ₃	—	1.947	1.961	1.968	0.021
PbSO ₄	—	1.878	1.883	1.895	0.017
PbZnSiO ₄	—	1.91	1.95	1.96	0.05
RbNbB ₂ O ₆	0.27–3.0	1.751	1.771	1.795	0.044
RbTiOAsO ₄	0.35–5.3	1.8294	1.838	1.9186	0.0892
RbTiOPO ₄	0.35–4.3	1.7884	1.7992	1.8859	0.0975
Sb ₂ O ₃	—	2.18	2.35	2.35	0.17
SbNbO ₄	—	2.3977	2.4190	2.4588	0.061
SbTaO ₄	—	2.3742	2.4039	2.4568	0.083
Sc ₂ (WO ₄) ₃	0.3–5.0	1.728	1.754	1.755	0.027
Sc ₂ Si ₂ O ₇	—	1.754	1.785	1.803	0.049
Sc ₂ SiO ₅	—	1.835	?	1.850	—
(Sc,Y) ₂ Si ₂ O ₇	—	1.756	1.793	1.809	0.053
Sr ₂ (VO ₄)Cl	—	1.785	—	1.816	0.03
Sr ₂ Nb ₂ O ₇	—	1.85	2.044	2.05	0.20
SrAl ₂ O ₄	—	1.638	—	1.656	0.018
SrAl ₄ O ₇	0.2–5.5	1.620	1.636	1.644	0.024
SrB ₂ O ₄	—	1.632	1.650	1.660	0.028
SrCO ₃	—	1.517	1.663	1.667	0.150
SrGa ₂ O ₄	—	1.737	—	1.767	0.03
SrSO ₄	—	1.6215	1.6237	1.6308	0.0057
SrZrO ₃	0.28–7.7	—	—	—	—
Ta ₂ O ₅	[4.6]	—	—	—	—
TeO ₂	0.33–5.0 [3]	2.00	2.18	2.35	0.35
V ₂ O ₅	[~2.3]	2.42	?	—	—
Y ₂ BeO ₄	—	1.840	—	1.855	0.015
Y ₂ MgBe ₂ Si ₂ O ₁₀	—	1.78	1.80	1.82	0.04
Y ₂ Si ₂ O ₇	—	1.731	1.738	1.744	0.013
Y ₂ SiO ₅	0.2–5	1.780	1.784	1.811	0.031
Y ₄ Al ₂ O ₉	—	1.826	1.830	1.832	0.006
YAlO ₃	0.2–7	1.9243	1.9387	1.9478	0.0235
Zn ₃ (AsO ₃) ₂	—	1.74	1.79	1.82	0.08
ZrO ₂	—	2.13	2.19	2.20	0.07

References:

- Berger, L. I. and Pamplin, B. R., Properties of semiconductors, *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12–87.
- Chai, B. H. T., Optical crystals, *Handbook of Laser Science and Technology, Suppl. 2, Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 3.
- Frederikse, H. P. R., Structure, melting point, density, and energy gap of simple inorganic compounds, *American Institute of Physics Handbook*, 3rd edition, Gray, D. E., Ed. (McGraw-Hill, New York, 1972), p. 9–16.
- Strehlow, W. H. and Cook, E. L., Compilation of energy band gaps in elemental and binary compound semiconductors and insulators, *J. Phys. Chem. Ref. Data* 2, 163 (1973).
- Tropf, W. J., Thomas, M. F., and Harris, T. J., Properties of crystals and glasses, *Handbook of Optics*, Vol. II (McGraw-Hill, New York, 1995), p. 33.51.

1.3.4 Dispersion Formulas for Refractive Indices

Dispersion formulas for the refractive indices of crystals at room temperature are given in the following pages. Tabulated values of refractive indices at many wavelengths are given in Refs. 1–4 for most of the crystals below. Dispersion formulas for several organic materials are given in Refs. 1 and 3.

Dispersion Formulas for Refractive Indices

Material	Dispersion formula (wavelength λ in μm)	Range (μm)	Ref.
Ag_3AsS_3	$n_o^2 = 7.483 + 0.474/(\lambda^2 - 0.09) - 0.0019\lambda^2$ $n_e^2 = 6.346 + 0.342/(\lambda^2 - 0.09) - 0.0011\lambda^2$	0.63–4.6 0.59–4.6	5
	$n_o^2 = 9.220 + 0.4454\lambda^2/(\lambda^2 - 0.1264) + 1733\lambda^2/(\lambda^2 - 1000)$ $n_e^2 = 7.007 + 0.3230\lambda^2/(\lambda^2 - 0.1192) + 660\lambda^2/(\lambda^2 - 1000)^2$	0.6–20	5
AgBr	$(n^2 - 1)/(n^2 - 2) = 0.452505 + 0.09939/(\lambda^2 - 0.070537) - 0.001509\lambda^2$	0.49–0.67	6
AgCl	$(n^2 - 1) = 2.062508\lambda^2/[\lambda^2 - (0.1039054)^2] + 0.9461465\lambda^2/[\lambda^2 - (0.2438691)^2] + 4.300785\lambda^2/[\lambda^2 - (70.85723)^2]$	0.54–21.0	7
AgGaS_2	$n_o^2 = 3.6280 + 2.1686\lambda^2/(\lambda^2 - 0.1003) + 2.1753\lambda^2/(\lambda^2 - 950)$ $n_e^2 = 4.0172 + 1.5274\lambda^2/(\lambda^2 - 0.1310) + 2.1699\lambda^2/(\lambda^2 - 950)$	0.49–12	8
AgGaSe_2	$n_o^2 = 4.6453 + 2.2057\lambda^2/(\lambda^2 - 0.1897) + 1.8377\lambda^2/(\lambda^2 - 1600)$ $n_e^2 = 5.2912 + 1.3970\lambda^2/(\lambda^2 - 0.2845) + 1.9282\lambda^2/(\lambda^2 - 1600)$	0.73–13.5	8
$\beta\text{-AgI}$	$n_o = 2.184; n_e = 2.200 @ 0.659 \mu\text{m}$ $n_o = 2.104; n_e = 2.115 @ 1.318 \mu\text{m}$	—	9
Ag_3SbS_3	$n_o^2 = 1 + 6.585\lambda^2/[\lambda^2 - (0.4)^2] + 0.1133\lambda^2/[\lambda^2 - (15)^2]$ $n_e^2 = 1 + 5.845\lambda^2/[\lambda^2 - (0.4)^2] + 0.0202\lambda^2/[\lambda^2 - (15)^2]$	1.5–10.6	10
Al_2O_3	$n_o^2 = 1 + 1.43134936\lambda^2/[\lambda^2 - (0.0726631)^2] + 0.65054713\lambda^2/[\lambda^2 - (0.1193242)^2] + 5.3414021\lambda^2/[\lambda^2 - (18.028251)^2]$ $n_e^2 = 1 + 1.5039759\lambda^2/[\lambda^2 - (0.0740288)^2] + 0.55069141\lambda^2/[\lambda^2 - (0.1216529)^2] + 6.59273791\lambda^2/[\lambda^2 - (20.072248)^2]$	0.22–5.0	13
AlAs	$n^2 = 2.0729 + 6.0840\lambda^2/[\lambda^2 - 0.2822]^2 + 1.900\lambda^2/[\lambda^2 - 27.62]^2$	0.56–2.2	11
AlN	$n_o^2 = 3.1399 + 1.3786\lambda^2/[\lambda^2 - (0.1715)^2] + 3.861\lambda^2/[\lambda^2 - (15.03)^2]$ $n_e^2 = 3.0729 + 1.6173\lambda^2/[\lambda^2 - (0.1746)^2] + 4.139\lambda^2/[\lambda^2 - (15.03)^2]$	0.22–5.0	12
ALON	$n^2 - 1 = 2.1375\lambda^2/[\lambda^2 - (0.10256)^2] + 4.582\lambda^2/[\lambda^2 - (18.868)^2]$	0.4–2.3	14

BaB ₂ O ₄	$n_o^2 = 2.7405 + 0.0184/(\lambda^2 - 0.0179) - 0.0155\lambda^2$ $n_e^2 = 2.3730 + 0.0128/(\lambda^2 - 0.0156) - 0.0044\lambda^2$	0.22–1.06	15
BaF ₂	$n_o^2 = 1 + 0.643356\lambda^2/[\lambda^2 - (0.057789)^2] + 0.506762\lambda^2/[\lambda^2 - (0.10968)^2] + 3.8261^2/[\lambda^2 - (14.3864)^2]$	0.27–10.3	16
BaTiO ₃	$n_o^2 = 1 + 4.187\lambda^2/[\lambda^2 - (0.223)^2]$ $n_e^2 = 1 + 4.064\lambda^2/[\lambda^2 - (0.211)^2]$	0.4–0.7	17
BaMgF ₄	$n_x^2 = 2.1462 + 0.00736\lambda^2/(\lambda^2 - 0.0090)$ $n_y^2 = 2.007 + 0.0076\lambda^2/(\lambda^2 - 0.00799)$ $n_z^2 = 2.1238 + 0.0086\lambda^2/(\lambda^2 - 0)$	0.53–1.06	18
Ba ₂ NaNb ₅ O ₁₂	$n_x^2 = 1 + 3.6008\lambda^2/(\lambda^2 - 0.032199)$ $n_y^2 = 1 + 3.9495\lambda^2/(\lambda^2 - 0.040140)$ $n_z^2 = 1 + 3.9495\lambda^2/(\lambda^2 - 0.040389)$	0.46–1.06	19, 20
BeO	$n_o^2 = 1 + 1.92274\lambda^2/[\lambda^2 - (0.07908)^2] + 1.24209\lambda^2/[\lambda^2 - (9.7131)^2]$ $n_e^2 = 1 + 1.96939\lambda^2/[\lambda^2 - (08590)^2] + 1.67389\lambda^2/[\lambda^2 - (10.4797)^2]$	0.44–7.0	38, 50
BiB ₃ O ₆	$n_x^2 = 3.6545 + 0.0511\lambda^2/(\lambda^2 - 0.0371) - 0.0226\lambda^2$ $n_y^2 = 3.0740 + 0.03233\lambda^2/(\lambda^2 - 0.0316) - 0.01337\lambda^2$ $n_z^2 = 3.1685 + 0.0373\lambda^2/(\lambda^2 - 0.0346) - 0.01750\lambda^2$		117
Bi ₄ Ge ₃ O ₁₂	$n^2 = 1 + 3.08959\lambda^2/(\lambda^2 - 0.01337)$	0.48–1.06	21
Bi ₁₂ GeO ₂₀	$n^2 = 1 + 4.601\lambda^2/[\lambda^2 - (0.242)^2]$	0.48–0.7	22, 32
Bi ₁₂ SiO ₂₀	$n^2 = 2.72777 + 3.01705\lambda^2/[\lambda^2 - (0.266)^2]$	0.4–0.7	23
BP	$n^2 = 1 + 6.841\lambda^2/[\lambda^2 - (0.267)^2]$	0.48–0.7	24
C (diamond)	$n^2 = 1 + 4.3356\lambda^2/[\lambda^2 - (0.160)^2] + 0.3306\lambda^2/[\lambda^2 - (0.1750)^2]$	0.225–∞	29

Dispersion Formulas for Refractive Indices—continued

Material	Dispersion formula (wavelength λ in μm)	Range (μm)	Ref.
Ca ₂ Al ₂ SiO ₇	$n_o^2 = 1 + 1.712/(\lambda^2 - 0.0196)$ $n_e^2 = 1 + 1.687/(\lambda^2 - 0.01133)$	0.31–1.06	26
Ca ₅ (PO ₄) ₃ F	$n_o^2 = 2.626769 + 0.014626/(\lambda^2 - 0.012833) - 0.007653\lambda^2$ $n_e^2 = 2.620175 + 0.014703/(\lambda^2 - 0.011037) - 0.007544\lambda^2$	0.4–1.0	27
CaCO ₃	$n_o = 1 + 0.8559\lambda^2/[\lambda^2 - (0.0588)^2] + 0.83913\lambda^2/[\lambda^2 - (0.141)^2] + 0.0009\lambda^2/[\lambda^2 - (0.197)^2] + 0.6845\lambda^2/[\lambda^2 - (7.005)^2]$ $n_e = 1 + 1.0856\lambda^2/[\lambda^2 - (0.07897)^2] + 0.0988\lambda^2/[\lambda^2 - (0.142)^2] + 0.317\lambda^2/[\lambda^2 - (1.468)^2]$	0.2–2.2	28
CaF ₂	$n^2 = 1 + 0.5675888\lambda^2/[\lambda^2 - (0.050263605)^2] + 0.4710914\lambda^2/[\lambda^2 - (0.1003909)^2] + 3.8484723\lambda^2/[\lambda^2 - (34.649040)^2]$	0.23–9.7	45
CaMoO ₄	$n_o^2 = 1 + 2.7840\lambda^2/[\lambda^2 - (0.1483)^2] + 1.2425\lambda^2/[\lambda^2 - (11.576)^2]$ $n_e^2 = 1 + 2.8045\lambda^2/[\lambda^2 - (0.1542)^2] + 1.0055\lambda^2/[\lambda^2 - (10.522)^2]$	0.45–3.8	30, 50
CaWO ₄	$n_o^2 = 1 + 2.5493\lambda^2/[\lambda^2 - (0.1347)^2] + 0.9200\lambda^2/[\lambda^2 - (10.815)^2]$ $n_e^2 = 1 + 2.6041\lambda^2/[\lambda^2 - (0.11379)^2] + 4.1237\lambda^2/[\lambda^2 - (21.371)^2]$	0.45–4.0	30, 50
CdGeAs ₂	$n_o^2 = 10.1064 + 2.2988\lambda^2/(\lambda^2 - 1.0872) + 1.6247\lambda^2/(\lambda^2 - 1370)$ $n_e^2 = 11.8018 + 1.2152\lambda^2/(\lambda^2 - 2.6971) + 1.6922\lambda^2/(\lambda^2 - 1370)$	2.4–11.5	8
CdGeP ₂	$n_o^2 = 5.9677 + 4.2286\lambda^2/(\lambda^2 - 0.2021) + 1.6351\lambda^2/(\lambda^2 - 671.33)$ $n_e^2 = 61573 + 4.0970\lambda^2/(\lambda^2 - 0.2330) + 1.4925\lambda^2/(\lambda^2 - 671.33)$	5.5–12.5	31
CdS	$n_o^2 = 1 + 3.96582820\lambda^2/[\lambda^2 - (0.23622804)^2] + 0.18113874\lambda^2/[\lambda^2 - (0.48285199)^2]$ $n_e^2 = 1 + 3.97478769\lambda^2/[\lambda^2 - (0.22426984)^2] + 0.26680809\lambda^2/[\lambda^2 - (0.46693785)^2] + 0.00074077\lambda^2/[\lambda^2 - (0.50915139)^2]$	0.51–1.4	93
CdSe	$n_o^2 = 4.2243 + 1.7680\lambda^2/(\lambda^2 - 0.2270) + 3.1200\lambda^2/(\lambda^2 - 3380)$ $n_e^2 = 4.2009 + 1.8875\lambda^2/(\lambda^2 - 0.2171) + 3.6461\lambda^2/(\lambda^2 - 3629)$	1–12	8

CdTe	$n^2 = 1 + 6.1977889\lambda^2/[\lambda^2 - (0.317069)^2] + 3.22438216\lambda^2/[\lambda^2 - (72.0663)^2]$	6–22	33
CsB ₃ O ₅	$n_x^2 = 2.2916 + 0.02105\lambda^2/(\lambda^2 - 0.06525) - 0.000031848\lambda^2$ $n_y^2 = 3.34498 + 1.04863\lambda^2/(\lambda^2 - 0.22044) - 0.01483\lambda^2$ $n_z^2 = 3.53666 + 1.10600\lambda^2/(\lambda^2 - 0.24988) - 0.01711\lambda^2$	0.35–1.06	117
CsBr	$n^2 = 1 + 0.9533786\lambda^2/[\lambda^2 - (0.0905643)^2] + 0.8303809\lambda^2/[\lambda^2 - (0.1671517)^2] + 2.847172\lambda^2/[\lambda^2 - (119.0155)^2]$	0.36–39	34
CsCl	$n^2 = 1.33013 + 0.98369\lambda^2/[\lambda^2 - (0.119)^2] + 0.00009\lambda^2/[\lambda^2 - (0.137)^2] + 0.00018\lambda^2/[\lambda^2 - (145)^2]$ + 0.30914 $\lambda^2/[\lambda^2 - (0.162)^2]$ + 4.320 $\lambda^2/[\lambda^2 - (100.50)^2]$	0.18–40	35
CsD ₂ AsO ₄	$n_o^2 = 1 + 1.40840\lambda^2/(\lambda^2 - 0.01299)$ $n_e^2 = 1 + 1.34731\lambda^2/(\lambda^2 - 0.01185)$	0.35–1.06	36
CsH ₂ AsO ₄	$n_o^2 = 1 + 1.39961\lambda^2/(\lambda^2 - 0.01156)$ $n_e^2 = 1 + 1.34417\lambda^2/(\lambda^2 - 0.01155)$	0.35–1.06	36
CsI	$n^2 = 1 + 0.34617251\lambda^2/[\lambda^2 - (0.0229567)^2] + 1.0080886\lambda^2/[\lambda^2 - (0.1466)^2] + 0.28551800\lambda^2/[\lambda^2 - (0.1830)^2]$ + 0.39743178 $\lambda^2/[\lambda^2 - (0.2120)^2]$ + 3.3605359 $\lambda^2/[\lambda^2 - (161.0)^2]$	0.29–50	37
CsLiB ₆ O ₁₀	$n_o^2 = 2.2049 + 0.0110259/(\lambda^2 - 0.0118119) - 0.0000695625\lambda^2$ $n_e^2 = 2.05936 + 0.00864948/(\lambda^2 - 0.0128929) - 0.0000267532\lambda^2$ $n_o^2 = 2.14318 + 0.0158749/(\lambda^2 + 1.37559) - 0.00062375\lambda^2$ $n_e^2 = 2.04195 + 0.0273245/(\lambda^2 + 0.286672) - 0.000342718\lambda^2$	0.24–0.63	118
CsTiOAsO ₄	$n_x^2 = 3.74440 + 0.70733\lambda^2/(\lambda^2 - 0.26033) - 0.01526\lambda^2$ $n_y^2 = 3.34498 + 1.04863\lambda^2/(\lambda^2 - 0.22044) - 0.01483\lambda^2$ $n_z^2 = 3.53666 + 1.10600\lambda^2/(\lambda^2 - 0.24988) - 0.01711\lambda^2$	0.45–1.55	91
CuCl	$n^2 = 3.580 + 0.03162\lambda^2/(\lambda^2 - 0.1642) + 0.09288/\lambda^2$	0.43–2.5	25
CuGaS ₂	$n_o^2 = 3.9064 + 2.3065\lambda^2/(\lambda^2 - 0.1149) + 1.5479\lambda^2/(\lambda^2 - 738.43)$ $n_e^2 = 4.3165 + 1.8692\lambda^2/(\lambda^2 - 0.1364) + 1.7575\lambda^2/(\lambda^2 - 738.43)$	0.55–11.5	39, 116

Dispersion Formulas for Refractive Indices—continued

Material	Dispersion formula (wavelength λ in μm)	Range (μm)	Ref.
CuGaS ₂	$n_o^2 = 3.9064 + 2.3065\lambda^2/(\lambda^2 - 0.1149) + 1.5479\lambda^2/(\lambda^2 - 738.43)$ $n_e^2 = 4.3165 + 1.8692\lambda^2/(\lambda^2 - 0.1364) + 1.7575\lambda^2/(\lambda^2 - 738.43)$	0.55–11.5	39, 116
GaAs	$n^2 = 3.5 + 7.4969\lambda^2/(\lambda^2 - 0.4082) + 1.9347\lambda^2/[(\lambda^2 - 37.17)^2]$	0.43–2.5	41
α -GaN	$n_o^2 = 3.6 + 1.75\lambda^2/[\lambda^2 - (0.256)^2] + 4.1\lambda^2/[\lambda^2 - (17.86)^2]$ $n_e^2 = 5.35 + 5.08\lambda^2/[\lambda^2 - (18.76)^2] + 1.0055\lambda^2/[\lambda^2 - (10.522)^2]$	<10	42
GaP	$n^2 = 1 + 1.390\lambda^2/[\lambda^2 - (0.172)^2] + 4.131\lambda^2/[\lambda^2 - (0.234)^2] + 2.570\lambda^2/[\lambda^2 - (345)^2] + 2.056\lambda^2/[\lambda^2 - (27.52)^2]$	0.8–10	43
GaSe	$n_o^2 = -0.05466\lambda^{-4} + 0.48605\lambda^{-2} + 7.8902 - 0.00824\lambda^2 - 0.00000276\lambda^4$ $n_e^2 = 6.0476 + 0.3423\lambda^2/(\lambda^2 - 0.16491) - 0.001042\lambda^2$	—	44
Gd ₂ (MoO ₄) ₃	$n_x^2 = 1 + 2.2450\lambda^2/(\lambda^2 - 0.022693)$ $n_y^2 = 1 + 2.24654\lambda^2/(\lambda^2 - 0.0226803)$ $n_z^2 = 1 + 2.41957\lambda^2/(\lambda^2 - 0.0245458)$	0.46–1.06	102
Gd ₃ Ga ₅ O ₁₂	$n^2 = 3.749719 + 1.7083005/(39.509089\lambda^2 - 1) + 0.01048372\lambda^2/(0.001855744\lambda^2 - 1)$	0.40–1.06	46
Gd ₃ Sc ₂ Al ₃ O ₁₂	$n^2 = 1 + 2.510\lambda^2/(\lambda^2 - 0.01537)$	0.54–0.64	47
Gd ₃ Sc ₂ Ga ₃ O ₁₂	$n^2 = 3.743782 + 1.9139566/(43.240392\lambda^2 - 1) + 0.01067490\lambda^2/(0.01558170\lambda^2 - 1)$	0.40–1.06	48
Ge	$n^2 = 9.28156 + 6.72880\lambda^2/(\lambda^2 - 0.44105) + 0.21307\lambda^2/(\lambda^2 - 3870.1)$	2–12	49, 120
α -HgS	$n_o^2 = 6.9443 + 0.3665/(\lambda^2 - 0.1351) - 0.0019\lambda^2$ $n_e^2 = 8.3917 + 0.5405/(\lambda^2 - 0.1380) - 0.0027\lambda^2$	0.62–11	51
InAs	$n^2 = 11.1 + 0.71\lambda^2/[\lambda^2 - (2.551)^2] + 2.75\lambda^2/[\lambda^2 - (44.66)^2]$	3.7–31.3	
InP	$n^2 = 7.255 + 2.316\lambda^2/[\lambda^2 - (0.6263)^2] + 2.765\lambda^2/[\lambda^2 - (32.935)^2]$	0.95–10	53, 122

KB ₅ O ₈ •4H ₂ O	$n_x^2 = 1 + 1/(0.852497 - 0.0087588\lambda^2)$ $n_y^2 = 1 + 1/(0.972682 - 0.0087757\lambda^2)$ $n_z^2 = 1 + 1/(1.008157 - 0.0094050\lambda^2)$	0.23–0.76	54, 121
KBr	$n^2 = 1.39408 + 0.79221\lambda^2/[\lambda^2 - (0.146)^2] + 0.01981\lambda^2/[\lambda^2 - (0.173)^2] + 0.15587\lambda^2/[\lambda^2 - (0.187)^2]$ + $0.17673\lambda^2/[\lambda^2 - (60.61)^2] + 2.06217\lambda^2/[\lambda^2 - (87.72)^2]$	0.2–40	35
KCl	$n^2 = 1.26486 + 0.30523\lambda^2/[\lambda^2 - (0.100)^2] + 0.41620\lambda^2/[\lambda^2 - (0.131)^2] + 0.18870\lambda^2/[\lambda^2 - (0.162)^2]$ + $2.6200\lambda^2/[\lambda^2 - (70.42)^2]$	0.18–35	35
KF	$n^2 = 1.55083 + 0.29162\lambda^2/[\lambda^2 - (0.126)^2] + 3.60001\lambda^2/[\lambda^2 - (51.55)^2]$	0.15–22	35
KD ₂ PO ₄	$n_o^2 = 1 + 1.2392348\lambda^2/(\lambda^2 - 0.83531147) + 14.78889\lambda^2/(\lambda^2 - 0.8851187)$ $n_e^2 = 1 + 1.125324\lambda^2/(\lambda^2 - 0.78980364) + 7.124567\lambda^2/(\lambda^2 - 1.190864)$	0.4–1.06	55, 56
KH ₂ AsO ₄	$n_o^2 = 1 + 1.411981\lambda^2/(\lambda^2 - 1.1955269) + 28.100751\lambda^2/(\lambda^2 - 1.00681)$ $n_e^2 = 1 + 1.260916\lambda^2/(\lambda^2 - 1.1188613) + 5.258787\lambda^2/(\lambda^2 - 1.055210)$	0.4–1.06	55, 56
KH ₂ PO ₄	$n_o^2 = 1 + 1.256618\lambda^2/(\lambda^2 - 0.84478168) + 33.89909\lambda^2/(\lambda^2 - 1.113904)$ $n_e^2 = 1 + 1.131091\lambda^2/(\lambda^2 - 0.8145980) + 5.75675\lambda^2/(\lambda^2 - 0.8117537)$	0.4–1.06	56
KI	$n^2 = 1.47285 + 0.16512\lambda^2/[\lambda^2 - (0.129)^2] + 0.41222\lambda^2/[\lambda^2 - (0.175)^2] + 0.44163\lambda^2/[\lambda^2 - (0.187)^2]$ + $0.16076\lambda^2/[\lambda^2 - (0.219)^2] + 0.33571\lambda^2/[\lambda^2 - (69.44)^2] + 1.92474\lambda^2/[\lambda^2 - (98.04)^2]$	0.25–50	35
K ₃ Li ₂ Nb ₅ O ₁₅	$n_o^2 = 1 + 3.708\lambda^2/(\lambda^2 - 0.04601)$ $n_e^2 = 1 + 3.349\lambda^2/(\lambda^2 - 0.03564)$	0.45–0.68	57
KNbO ₃	$n_x^2 = 1 + 2.49710\lambda^2/([\lambda^2 - (0.12909)^2] + 1.33660\lambda^2/[\lambda^2 - (0.25816)^2] - 0.025174\lambda^2)$ $n_y^2 = 1 + 2.54337\lambda^2/([\lambda^2 - (0.13701)^2] + 1.44122\lambda^2/[\lambda^2 - (0.27275)^2] - 0.028450\lambda^2)$ $n_z^2 = 1 + 2.37108\lambda^2/([\lambda^2 - (0.11972)^2] + 1.04825\lambda^2/[\lambda^2 - (0.25523)^2] - 0.019433\lambda^2)$	0.40–3.4	59
KTaO ₃	$n^2 = 1 + 3.591\lambda^2/([\lambda^2 - (0.193)^2]$	0.4–1.06	60

Dispersion Formulas for Refractive Indices—continued

Material	Dispersion formula (wavelength λ in μm)	Range (μm)	Ref.
KTiAsO ₄	$n_x^2 = 2.388887 + 0.77900\lambda^2/(\lambda^2 - (0.23784)^2 - 0.01501\lambda^2)$ $n_y^2 = 2.11055 + 1.03177\lambda^2/(\lambda^2 - (0.21088)^2 - 0.01064\lambda^2)$ $n_z^2 = 2.34723 + 1.10111\lambda^2/(\lambda^2 - (0.24016)^2 - 0.01739\lambda^2)$	0.45–1.55	58, 91
KTiOPO ₄	$n_x^2 = 2.16747 + 0.83733\lambda^2/([\lambda^2 - (0.04611)^2] - 0.01713\lambda^2)$ $n_y^2 = 2.19229 + 0.83547\lambda^2/([\lambda^2 - (0.04970)^2] - 0.01621\lambda^2)$ $n_z^2 = 2.25411 + 1.06543\lambda^2/([\lambda^2 - (0.05486)^2] - 0.02140\lambda^2)$	0.4–1.06	61–64
LaCl ₃	$n_o^2 = 1 + 2.235\lambda^2/(\lambda^2 - (0.01734))$ $n_e^2 = 1 + 2.469\lambda^2/(\lambda^2 - (0.017674))$	0.49–0.63	65
LaF ₃	$n_o^2 = 1 + 1.53763\lambda^2/(\lambda^2 - (0.0881)^2)$ $n_e^2 = 1 + 1.5148\lambda^2/(\lambda^2 - (0.08781)^2)$	0.35–0.70	66
La ₂ Be ₂ O ₅	$n_x^2 = 1 + 2.7990\lambda^2/(\lambda^2 + 0.01875)$ $n_y^2 = 1 + 2.9268\lambda^2/(\lambda^2 - 0.01918)$ $n_z^2 = 1 + 3.0725\lambda^2/(\lambda^2 - 0.01950)$	0.6–2	67
LiB ₃ O ₅	$n_x^2 = 2.45768 + 0.0098877\lambda^2/(\lambda^2 - (0.026095)^2) - 0.013847\lambda^2$ $n_y^2 = 2.52500 + 0.017123\lambda^2/(\lambda^2 - (0.0060517)^2) - 0.0087838\lambda^2$ $n_z^2 = 2.58488 + 0.012737\lambda^2/(\lambda^2 - (0.016293)^2) - 0.016293\lambda^2$	0.29–1.06	68
LiCaAlF ₆	$n_o^2 = 1.92552 + 0.00492/(\lambda^2 - 0.00569) - 0.00421\lambda^2$ $n_e^2 = 1.92155 + 0.00494/(\lambda^2 - 0.00617) - 0.00373\lambda^2$	0.4–1.0	69
LiF	$n^2 = 1 + 0.92549\lambda^2/[\lambda^2 - (0.7376)^2] + 6.96747\lambda^2/[\lambda^2 - (32.79)^2]$	0.1–10	35
LiIO ₃	$n_o^2 = 2.03132 + 1.37623\lambda^2/(\lambda^2 - 0.0350823) + 1.06745\lambda^2/(\lambda^2 - 169.0)$ $n_e^2 = 1.83086 + 1.08807\lambda^2/(\lambda^2 - 0.0313810) + 0.554582\lambda^2/(\lambda^2 - 158.76)$	0.5–5	71

LiNbO ₃	$n_o^2 = 2.39198 + 2.51118\lambda^2/[\lambda^2 - (0.217)^2] + 7.1333\lambda^2/[\lambda^2 - (16.502)^2]$ $n_e^2 = 2.32468 + 2.25650\lambda^2/[\lambda^2 - (0.210)^2] + 14.503\lambda^2/[\lambda^2 - (25.915)^2]$	0.4–3.1	72
LiSrAlF ₆	$n_o^2 = 1.97673 + 0.00309/(\lambda^2 - 0.00935) - 0.00828\lambda^2$ $n_e^2 = 1.98448 + 0.00235/(\lambda^2 - 0.10936) - 0.01057\lambda^2$	0.4–1.2	73
LiYF ₄	$n_o^2 = 1.38757 + 0.70757\lambda^2/(\lambda^2 - 0.00931) + 0.18849\lambda^2/(\lambda^2 - 50.99741)$ $n_e^2 = 1.31021 + 0.84903\lambda^2/(\lambda^2 - (0.00876)^2 + 0.53607\lambda^2/(\lambda^2 - 134.9566)^2)$	0.23–2.6	74
Lu ₃ Al ₅ O ₁₂	$n^2 = 3.3275151 - 0.0149248\lambda^2 + 0.0178355\lambda^{-2} + 0.0046614\lambda^{-4} - 0.0009334\lambda^{-6} + 0.0000737\lambda^{-8}$	0.44–1.2	75
MgAl ₂ O ₄	$n^2 = 1 + 1.8938\lambda^2/[\lambda^2 - (0.09942)^2] + 3.0755\lambda^2/[\lambda^2 - (15.826)^2]$	0.35–5.5	50, 76
MgF ₂	$n_o^2 = 1 + 0.48755108\lambda^2/[\lambda^2 - (0.04338408)^2] + 0.39875031\lambda^2/[\lambda^2 - (0.09461442)^2] + 2.3120353\lambda^2/[\lambda^2 - (23.793604)^2]$ $n_e^2 = 1 + 0.41344023^2/[\lambda^2 - (0.03684262)^2] + 0.50497499\lambda^2/[\lambda^2 - (0.09076162)^2] + 2.4904862\lambda^2/[\lambda^2 - (12.771995)^2]$	0.4–3.1	77
MgO	$n^2 = 1 + 1.111033\lambda^2/[\lambda^2 - (0.0712465)^2] + 0.8460085\lambda^2/[\lambda^2 - (0.1375204)^2] + 7.808527\lambda^2/[\lambda^2 - (26.89302)^2]$	0.36–5.4	78
NaBr	$n^2 = 1.06728 + 1.10463\lambda^2/[\lambda^2 - (0.125)^2] + 0.18816\lambda^2/[\lambda^2 - (0.145)^2] + 0.00243\lambda^2/[\lambda^2 - (0.176)^2]$ + 0.24454 $\lambda^2/[\lambda^2 - (0.188)^2]$ + 3.7960 $\lambda^2/[\lambda^2 - (74.63)^2]$	0.21–34	35
(Na,Ca)(Mg,Fe) ₃ B ₃ Al ₆ Si ₆ (O,OH,F) ₃₁ (tourmaline)	$n_o^2 = 1 + 1.6346\lambda^2/(\lambda^2 - 0.010734)$ $n_e^2 = 1 + 1.57256\lambda^2/(\lambda^2 - 0.011346)$	0.48–1.06	79
NaBrO ₃	$n^2 = 1 + 1.3194\lambda^2/[\lambda^2 - (0.09)^2] + 0.2357\lambda^2/[\lambda^2 - (0.2)^2] - 0.0174\lambda^2$	—	80
NaCl	$n^2 = 1.00055 + 0.19800\lambda^2/[\lambda^2 - (0.050)^2] + 0.48398\lambda^2/[\lambda^2 - (0.100)^2] + 0.38696\lambda^2/[\lambda^2 - (0.128)^2]$ + 0.25998 $\lambda^2/[\lambda^2 - (0.158)^2]$ + 0.08796 $\lambda^2/[\lambda^2 - (40.50)^2]$ + 3.17064 $\lambda^2/[\lambda^2 - (60.98)^2]$ + 0.30038 $\lambda^2/[\lambda^2 - (120.34)^2]$	0.2–30	35
NaClO ₃	$n^2 = 1 + 1.1825\lambda^2/[\lambda^2 - (0.09)^2] + 0.07992\lambda^2/[\lambda^2 - (0.185)^2] - 0.00864\lambda^2$	0.23–0.72	81
NaF	$n^2 = 1.41572 + 0.32785\lambda^2/[\lambda^2 - (0.117)^2] + 3.18248\lambda^2/[\lambda^2 - (40.57)^2]$	0.15–17	35

Dispersion Formulas for Refractive Indices—continued

Material	Dispersion formula (wavelength λ in μm)	Range (μm)	Ref.
$[\text{NH}_4]_2\text{CO}$	$n_o^2 = 2.1823 + 0.0125\lambda^2/(\lambda^2 - 0.0300)$ $n_e^2 = 2.51527 + 0.0240\lambda^2/(\lambda^2 - 0.0300) + 0.020(\lambda - 1.52)/[(\lambda - 1.52)^2 + 0.8771]$	0.3–1.06	82
$\text{NH}_4\text{D}_2\text{AsO}_4$	$n_o^2 = 1 + 1.418168\lambda^2/(\lambda^2 - 1.2246852) + 24.39162\lambda^2/(\lambda^2 - 1.175687)$ $n_e^2 = 1 + 1.262661\lambda^2/(\lambda^2 - 1.1728953) + 6.250606\lambda^2/(\lambda^2 - 0.9188848)$	0.4–1.06	55, 56
$\text{NH}_4\text{H}_2\text{AsO}_4$	$n_o^2 = 1 + 1.441185\lambda^2/(\lambda^2 - 1.2290244) + 30.08674\lambda^2/(\lambda^2 - 0.8843874)$ $n_e^2 = 1 + 1.274199\lambda^2/(\lambda^2 - 1.1750136) + 11.96164\lambda^2/(\lambda^2 - 1.041567)$	0.4–1.06	55, 56
$\text{NH}_4\text{H}_2\text{PO}_4$	$n_o^2 = 1 + 1.298990\lambda^2/(\lambda^2 - 0.0089232927) + 43.17364\lambda^2/(\lambda^2 - 1188.531)$ $n_e^2 = 1 + 1.162166\lambda^2/(\lambda^2 - 0.085932421) + 12.01997\lambda^2/(\lambda^2 - 831.8239)$	0.4–1.06	55, 56
NaI	$n^2 = 1.478 + 1.532\lambda^2/[\lambda^2 - (0.170)^2] + 4.27\lambda^2/[\lambda^2 - (86.21)^2]$	0.25–17	35
PbF_2	$n^2 = 1 + 0.66959342\lambda^2/[\lambda^2 - (0.00034911)^2] + 1.3086319\lambda^2/[\lambda^2 - (0.17144455)^2]$ $+ 0.01670641\lambda^2/[\lambda^2 - (0.28125513)^2] + 2007.8865\lambda^2/[\lambda^2 - (796.67469)^2]$	0.3–11.9	83
PbMoO_4	$n_o^2 = 1 + 3.54642\lambda^2/[\lambda^2 - (0.18518)^2] + 0.582703\lambda^2/[\lambda^2 - (0.33764)^2]$ $n_e^2 = 1 + 3.52555\lambda^2/[\lambda^2 - (0.17950)^2] + 0.20660\lambda^2/[\lambda^2 - (0.32537)^2]$	0.44–1.08	50, 84
$\text{PbNb}_4\text{O}_{11}$	$n_x^2 = 1 + 4.124\lambda^2/[(\lambda^2 - (0.202)^2]$ $n_y^2 = 1 + 4.139\lambda^2/[(\lambda^2 - (0.2011)^2]$ $n_z^2 = 1 + 4.246\lambda^2/[(\lambda^2 - (0.2014)^2]$	0.45–1.55	85
PbS	$n^2 = 1 + 15.9\lambda^2/[(\lambda^2 - (0.77)^2] + 133.2\lambda^2/[(\lambda^2 - (141)^2]$	3.5–10	86
PbSe	$n^2 = 1 + 21.1\lambda^2/[(\lambda^2 - (1.37)^2]$	5–10	86
PbTe	$n^2 = 1 + 30.046\lambda^2/[(\lambda^2 - (1.563)^2]$	4.0–12.5	87
PbTiO ₃	$n_o^2 = 1 + 5.363\lambda^2/[(\lambda^2 - (0.224)^2]$	0.45–1.15	

	$n_e^2 = 1 + 5.366\lambda^2/(\lambda^2 - (0.0217)^2]$		
RbD ₂ AsO ₄	$n_o^2 = 1 + 1.371661\lambda^2/(\lambda^2 - 1.1700309) + 16.30710\lambda^2/(\lambda^2 - 1.0114844)$ $n_e^2 = 1 + 1.269201\lambda^2/(\lambda^2 - 1.1202311) + 4.300136\lambda^2/(\lambda^2 - 1.149464)$	0.4–1.06	55, 56
RbD ₂ PO ₄	$n_o^2 = 1 + 1.237455\lambda^2/(\lambda^2 - 0.8274984) + 17.69334\lambda^2/(\lambda^2 - 0.8839832)$ $n_e^2 = 1 + 1.154309\lambda^2/(\lambda^2 - 0.81539261) + 585751\lambda^2/(\lambda^2 - 0.8927180)$	0.4–1.06	55, 56
RbH ₂ AsO ₄	$n_o^2 = 1 + 1.37723\lambda^2/(\lambda^2 - 0.01301)$ $n_e^2 = 1 + 1.272831\lambda^2/(\lambda^2 - 0.01157)$	—	89
RbH ₂ PO ₄	$n_o^2 = 1 + 1.2068\lambda^2/(\lambda^2 - 0.01539)$ $n_e^2 = 1 + 1.15123\lambda^2/(\lambda^2 - 0.010048)$	0.48–1.06	90
RbTiOAsO ₄	$n_x^2 = 1.97756 + 1.25726\lambda^2/[(\lambda^2 - (0.20448)^2] - 0.00865\lambda^2$ $n_y^2 = 2.22681 + 0.99616\lambda^2/[\lambda^2 - (0.21423)^2] - 0.01369\lambda^2$ $n_z^2 = 2.28779 + 1.20629\lambda^2/[(\lambda^2 - (0.23484)^2] - 0.01583\lambda^2$	0.45–1.55	91
RbTiOPO ₄	$n_x^2 = 2.38494 + 0.73603\lambda^2/[(\lambda^2 - (0.23891)^2] - 0.01583\lambda^2$ $n_y^2 = 2.15559 + 0.93307\lambda^2/[\lambda^2 - (0.20994)^2] - 0.01452\lambda^2$ $n_z^2 = 2.27723 + 1.11030\lambda^2/[(\lambda^2 - (0.23454)^2] - 0.01995\lambda^2$	0.45–1.55	91
Se	$n_o = 2.790$; $n_e = 3.608$ @ 1.06 μm $n_o = 2.64$; $n_e = 3.41$ @ 10.6 μm	—	92
Si	$n^2 = 1 + 10.66842933\lambda^2/[\lambda^2 - (0.3015116485)^2] + 0.003043475\lambda^2/[\lambda^2 - (1.13475115)^2]$ + 1.54133408λ ² /[λ ² - (1104.0) ²]	1.36–11	93, 94
α-SiC	$n_o^2 = 1 + 5.5515\lambda^2/[(\lambda^2 - (0.16250)^2]$ $n_e^2 = 1 + 5.7382\lambda^2/[(\lambda^2 - (0.16897)^2]$	0.49–1.06	95
β-SiC	$n^2 = 1 + 5.5705\lambda^2/[(\lambda^2 - (0.1635)^2]$	0.47–0.69	96

Dispersion Formulas for Refractive Indices—continued

Material	Dispersion formula (wavelength λ in μm)	Range (μm)	Ref.
SiO ₂ (α -quartz)	$n_o^2 = 1 + 0.663044\lambda^2/[\lambda^2 - (0.060)^2] + 0.517852\lambda^2/[\lambda^2 - (0.106)^2] + 0.175912\lambda^2/[\lambda^2 - (0.119)^2]$ $+ 0.565380\lambda^2/[\lambda^2 - (8.844)^2] + 1.675299\lambda^2/[\lambda^2 - (20.742)^2]$ $n_e^2 = 1 + 0.665721\lambda^2/[\lambda^2 - (0.060)^2] + 0.503511\lambda^2/[\lambda^2 - (0.106)^2] + 0.214792\lambda^2/[\lambda^2 - (0.119)^2]$ $+ 0.539173\lambda^2/[\lambda^2 - (8.792)^2] + 1.807613\lambda^2/[\lambda^2 - (197.709)^2]$	0.18–0.71	97
SrF ₂	$n^2 = 1 + 0.67805894\lambda^2/[\lambda^2 - (0.05628989)^2] + 0.37140533\lambda^2/[\lambda^2 - (0.10801027)^2]$ $+ 3.8484723\lambda^2/[\lambda^2 - (34.649040)^2]$	0.21–11.5	98
SrMoO ₄	$n_o^2 = 1 + 2.4839\lambda^2/[\lambda^2 - (0.1451)^2] + 0.1015\lambda^2/[\lambda^2 - (4.603)^2]$ $n_e^2 = 1 + 2.4923\lambda^2/[\lambda^2 - (0.1488)^2] + 0.1050\lambda^2/[\lambda^2 - (4.544)^2]$	0.45–2.4	30
SrTiO ₃	$n = 2.28355 + 0.035906/(\lambda^2 - 0.028) + 0.001666/(\lambda^2 - 0.028)^2 - 0.0061335\lambda^2 - 00001502\lambda^4$	0.4–5.4	99
Sr ₅ (VO ₄) ₃ F	$n_o^2 = 3.29417 + 0.047212/(\lambda^2 - 0.048260) - 0.008518\lambda^2$ $n_e^2 = 3.24213 + 0.043872/(\lambda^2 - 0.053139) - 0.008773\lambda^2$	0.5–1.0	100
Tb ₂ (MoO ₄) ₃	$n_x^2 = 1 + 2.273955\lambda^2/(\lambda^2 - 0.02333)$ $n_y^2 = 1 + 2.2724\lambda^2/(\lambda^2 - 0.023359)$ $n_z^2 = 1 + 2.4430166\lambda^2/[\lambda^2 - 0.05133)$	0.46–1.06	101
Te	$n_o^2 = 18.5346 + 4.3289\lambda^2/(\lambda^2 - 3.9810) + 3.7800\lambda^2/(\lambda^2 - 11813)$ $n_e^2 = 29.5222 + 9.3068\lambda^2/(\lambda^2 - 2.5766) + 9.2350\lambda^2/(\lambda^2 - 13521)$ $n_o^2 = 4.0164 + 18.8133\lambda^2/(\lambda^2 - 1.1572) + 7.3729\lambda^2/(\lambda^2 - 10000)$ $n_e^2 = 1.9041 + 36.8133\lambda^2/(\lambda^2 - 1.0803) + 6.2456\lambda^2/(\lambda^2 - 10000)$	4–14 8.5–30	8 8
TeO ₂	$n_o^2 = 1 + 2.584\lambda^2/[\lambda^2 - (0.1342)^2] + 1.157\lambda^2/[\lambda^2 - (0.2638)^2]$ $n_e^2 = 1 + 2.823\lambda^2/[\lambda^2 - (0.1342)^2] + 1.542\lambda^2/[\lambda^2 - (0.2631)^2]$	0.4–1	103
TiO ₂	$n_o^2 = 5.913 + 0.2441\lambda^2/(\lambda^2 - 0.0803)$	0.43–1.5	104

rutile	$n_e^2 = 7.097 + 0.3322\lambda^2/(\lambda^2 - 0.0843)$			
TlBr	$(n^2 - 1)/(n^2 - 2) = 0.48484 + 0.10279/(\lambda^2 - 0.090000) - 0.0047896\lambda^2$	0.54–0.65	6	
Tl[Br,Cl]	$n^2 = 1 + 3.821\lambda^2/[\lambda^2 - (0.02234)^2] - 0.000877\lambda^2$	0.6–24	106	
Tl[Br,I]	$n^2 = 1 + 1.8293958\lambda^2/[\lambda^2 - (0.150)^2] + 1.6675593\lambda^2/[\lambda^2 - (0.250)^2] + 1.1210424\lambda^2/[\lambda^2 - (0.350)^2]$ $+ 0.04513366\lambda^2/[\lambda^2 - (0.450)^2] + 12.380234\lambda^2/[\lambda^2 - (164.59)^2]$	0.58–39.4	107	
TlCl	$(n^2 - 1)/(n^2 - 2) = 0.47856 + 0.078588/(\lambda^2 - 0.08277) - 0.00881\lambda^2$	0.43–0.66	105	
Tl ₃ AsSe ₃	$n_o^2 = 1 + 10.210\lambda^2/[\lambda^2 - (0.444)^2] + 0.522\lambda^2/[\lambda^2 - (25.0)^2]$ $n_e^2 = 1 + 8.933\lambda^2/[\lambda^2 - (0.444)^2] + 0.308\lambda^2/[\lambda^2 - (25.0)^2]$	2–12	108	
Y ₂ O ₃	$n^2 = 1 + 2.578\lambda^2/[\lambda^2 - (0.1387)^2] + 3.935\lambda^2/[\lambda^2 - (22.936)^2]$	0.2–12	109	
YAlO ₃	$n_x^2 = 1 + 2.61960\lambda^2/(\lambda^2 + 0.012338)$ $n_y^2 = 1 + 2.67171\lambda^2/(\lambda^2 - 0.012605)$ $n_z^2 = 1 + 2.70381\lambda^2/(\lambda^2 - 0.012903)$	0.4–1.06	110	
Y ₂ SiO ₅	$n_x^2 = 3.0895 + 0.0334/(\lambda^2 + 0.0043) + 0.0199\lambda^2$ $n_y^2 = 3.1173 + 0.0283/(\lambda^2 - 0.0313)$ $n_z^2 = 3.1871 + 0.03022/(\lambda^2 - 0.138)$	0.44–0.64	111	
YVO ₄	$n_o^2 = 1 + 2.7665\lambda^2/(\lambda^2 - 0.026884)$ $n_e^2 = 1 + 3.5930\lambda^2/(\lambda^2 - 0.032103)$	0.5–1.06	112, 113	
Y ₃ Al ₅ O ₁₂	$n^2 = 1 + 2.293\lambda^2/[\lambda^2 - (0.1095)^2] + 3.705\lambda^2/[\lambda^2 - (17.825)^2]$	0.4–4.0	30	
Y ₃ Ga ₅ O ₁₂	$n^2 = 1 + 2.5297\lambda^2/(\lambda^2 - 0.019694)$	0.46–0.63	48	
Y ₃ Sc ₂ Al ₃ O ₁₂	$n^2 = 1 + 2.4118\lambda^2/(\lambda^2 - 0.01477)$	0.53–0.65	115	

Dispersion Formulas for Refractive Indices—*continued*

Material	Dispersion formula (wavelength λ in μm)	Range (μm)	Ref.
ZnGeP ₂	$n_o^2 = 4.4733 + 5.2658\lambda^2/(\lambda^2 - 0.1338) + 1.49090\lambda^2/(\lambda^2 - 662.55)$ $n_e^2 = 4.6332 + 5.3422\lambda^2/(\lambda^2 - 0.1426) + 1.4580\lambda^2/(\lambda^2 - 662.55)$	0.4–12	40
ZnO	$n_o^2 = 2.81419 + 0.87968\lambda^2/[\lambda^2 - (0.00569)^2] - 0.00711\lambda^2$ $n_e^2 = 2.80333 + 0.94470\lambda^2/[\lambda^2 - (0.3004)^2] - 0.00714\lambda^2$	0.45–4.0	30
α -ZnS	$n_o^2 = 4.4175 + 1.73968\lambda^2/[\lambda^2 - (0.2677)^2]$ $n_e^2 = 4.42643 + 1.7491\lambda^2/[\lambda^2 - (0.2674)^2]$	0.36–1.4	50, 105
β -ZnS	$n^2 = 1 + 0.3390426\lambda^2/[\lambda^2 - (0.31423026)^2] + 3.7606868\lambda^2/[\lambda^2 - (0.1759417)^2]$ + $2.7312353\lambda^2/[\lambda^2 - (33.886560)^2]$	0.55–10.5	98
ZnSe	$n^2 = 1 + 4.2980149\lambda^2/[\lambda^2 - (0.1920630)^2] + 0.62776557\lambda^2/[\lambda^2 - (0.37878260)^2]$ + $2.8955633\lambda^2/[\lambda^2 - (46.994595)^2]$	0.55–18	98
ZnTe	$n^2 = 9.921 + 0.42530\lambda^2/[\lambda^2 - (0.37766)^2] + 2.63580/[\lambda^2/(56.5)^2 - 1]$	0.55–30	114
ZrO ₂ : 12%Y ₂ O ₃	$n^2 = 1 + 1.347091\lambda^2/[\lambda^2 - (0.062543)^2] + 2.117788\lambda^2/[\lambda^2 - (0.166739)^2] + 9.452943\lambda^2/[\lambda^2 - (24.320570)^2]$	0.36–5.1	116

References:

1. Singh, S., Nonlinear optical materials, *Handbook of Laser Science and Technology, Vol. III: Optical Materials, Part 1* (CRC Press, Boca Raton, FL, 1986), p. 54.
2. DeShazer, L. G., Rand, S. C., and Wechsler, B. A., Laser crystals, *Handbook of Laser Science and Technology, Vol. V: Optical Materials, Part 3* (CRC Press, Boca Raton, FL, 2000), p. 281.
3. Singh, S., Nonlinear optical materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 237.
4. Wechsler, B. A. and Sumida, D. S., Laser crystals, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 595.
5. Hulme, K. F., Jones, O., Davies, P. H., and Hobden, M.V., Synthetic proustite (Ag_3AsS_3); a new crystal for optical mixing, *Appl. Phys. Lett.* 10, 133 (1967)
6. Schröter, H., On the refractive indices of some heavy metal halides in the visible and calculation of interpolation formulas for dispersion, *Z. Phys.* 67, 24 (1931).
7. Tilton, L. W., Plyler, E. K., and Stephens, R. E., Refractive index of silver chloride for visible and infrared radiant energy, *J. Opt. Soc. Am.* 66, 72 (1976).
8. Bhar, G. C., Refractive index interpolation in phase matching, *Appl. Opt.* 15, 305 (1976).
9. Levine, B. F., Nordland, W. A., and Silver, J. W., Nonlinear optical susceptibility of AgI , *IEEE J. Quantum Electron.* QE-9, 468 (1973).
10. Feichtner, J. D., Johannes, R. and Roland, G. W., Growth and optical properties of single crystal pyragyrite (Ag_3SbS_3), *Appl. Opt.* 9, 1716 (1970).
11. Fern, R. E. and Onton, A., Refractive index of AlAs , *J. Appl. Phys.* 42, 3499 (1971).
12. Pastrnak and Roslovcova, L., Refractive index measurements on AlN single crystals, *Phys. Stat. Sol.* 14, K8 (1966).
13. Malitson, I. H. and Dodge, M. J., Refractive index and birefringence of synthetic sapphire, *J. Opt. Soc. Am.* 62, 1405 (1972).
14. Tropf, W. J. and Thomas, M. E., Aluminum oxynitride (ALON) spinel, *Handbook of Optical Constants of Solids II*, Palik, E. D., Ed. (Academic Press, Orlando, FL, 1991), p. 775.
15. Eimerl, D., Davis, L., and Velsko, S., Optical, mechanical, and thermal properties of barium borate, *J. Appl. Phys.* 62, 1968 (1987).
16. Malitson, I. H., Refractive properties of barium fluoride, *J. Opt. Soc. Am.* 54, 628 (1964).
17. Wemple, S. H., DiDomenico, M., and Camlibel, I., Dielectric and optical properties of melt-grown BaTiO_3 , *J. Phys. Chem. Solids* 29, 1797 (1968).
18. Bechhold, P. S. and Haussühl, S., Nonlinear optical properties of orthorhombic barium formate and magnesium barium fluoride, *Appl. Phys.* 14, 403 (1977).
19. Singh, S., Draegert, D. A., and Geusic, J. E., Optical and ferroelectric of barium sodium niobate, *Phys. Rev. B* 2, 2709 (1970).
20. Potopowicz, J. R., Temperature dependence of the refractive indices of barium sodium niobate (unpublished).
21. Singh, S. and Pawelek, R. (unpublished).
22. Vedam, K. and Hennessey, P., Piezo- and thermal-optical properties of $\text{Bi}_{12}\text{GeO}_{20}$, *J. Opt. Soc. Am.*, 65, 442 (1975).
23. Gospodnov, M., Haussühl, S., Seveshtarov, P., Tashev, V., and Petkov, N., Physical properties of cubic $\text{Bi}_{12}\text{SiO}_{20}$, *Bulgarian J. Phys.* 15, 140 (1988).
24. Wettling, W. and Windscheif, J., Elastic constants and refractive index of boron phosphide, *Solid State Commun.*, 50, 33 (1854).
25. Feldman, A. and Horowitz, D., Refractive index of cuprous chloride, *J. Opt. Soc. Am.* 59, 1406 (1969).
26. Burshtein, Z., Shimony, Y., and Levy, I., Refractive-index anisotropy and dispersion in gehlenite, $\text{Ca}_2\text{Al}_2\text{SiO}_7$, between 308 and 1064 nm, *J. Opt. Soc. Am. A* 10, 2246 (1993).

27. Payne, S. A., Smith, L. K., DeLoach, L. D., Kway, W. L., Tassano, J. B., and Krupke, W. F., Laser, optical, and thermomechanical properties of Yb-doped fluorapatite, *IEEE J. Quantum Electron.* 30, 170–179 (1994).
28. Gray, D. E., (Ed.), *American Institute of Physics Handbook*, 3rd ed. (McGraw-Hill, New York, 1972).
29. Peter, F., Refractive indices and absorption coefficients of diamond between 644 and 226 micrometers, *Z. Phys.* 15, 358 (1923).
30. Bond, W. L., Measurement of the refractive index of several crystals, *J. Appl. Phys.* 36, 1674 (1965).
31. Boyd, G. D., Buehler, E., Stroz, F. G., and Wernick, J. H., Linear and nonlinear optical properties of ternary $A^{II}B^{IV}C_2^V$ chalcopyrite semiconductors, *IEEE J. Quantum Electron. QE-8*, 419 (1972).
32. Burattine, E., Cappuccio, G., Grandolfo, M., Vecchia, P., and Efendiev, Sh. M., Near-infrared refractive index of bismuth germanium oxide ($Bi_{12}GeO_{20}$), *J. Opt. Soc. Am.*, 73, 495 (1983).
33. DeBell, A. G., Dereniak, E. L., Harvey, J., et al., Cryogenic refractive indices and temperature coefficients of cadmium telluride from $6\text{ }\mu\text{m}$ to $22\text{ }\mu\text{m}$, *Appl. Opt.* 18, 3114 (1979).
34. Rodney, W. S. and Spindler, R. J., Refractive index of cesium bromide for ultraviolet, *J. Nat. Bur. Stand.* 51, 123 (1953).
35. Li, H. H., Refractive index of alkali halides and its wavelength and temperature derivatives, *J. Phys. Chem. Ref. Data* 5, 329 (1976).
36. Kato, K., Second harmonic generation in CDA and CD*A, *IEEE J. Quantum Electron. QE-10*, 616 (1974).
37. Rodney, W. S., Optical properties of cesium chloride, *J. Opt. Soc. Am.* 45, 987 (1955).
38. Edwards, D. F. and White, R. H., Beryllium oxide, *Handbook of Optical Constants of Solids II*, Palik, E. D. (Ed., (Academic Press, Orlando, 1991), p. 805.
39. Boyd, G. D., Kasper, H., and McFee, J. H., Linear and nonlinear optical properties of $AgGaS_3$, $CuGaS_3$, and $CuInS_3$, *IEEE J. Quantum Electron. QE-7*, 563 (1971).
40. Bhar, G. C. and Ghosh, G., Temperature-dependent Sellmeier coefficients and coherence lengths for some chalcopyrite crystals, *J. Opt. Soc. Am.* 69, 730 (1979).
41. Kachare, A. H., Spitzer, W. G., and Fredrickson, J. E., Refractive index of ion-implanted GaAs, *J. Appl. Phys.* 47, 4209 (1976).
42. Barker, A. S. and Hegems, M., Infrared lattice vibrations and free-electron dispersion in GaN, *Phys. Rev. B* 7, 743 (1977).
43. Parsons, D. F. and Coleman, P. D., Far infrared optical constants of gallium phosphide, *Appl. Opt.* 10, 1683 (1971).
44. Abdullaev, G. B., Kulevskii, L. A., Prokhorov, A. M., et al., a new effective material for nonlinear optics, *JETP Lett.* 16, 90 (1972).
45. Malitson, I. H., A redetermination of some optical properties of calcium fluoride, *Appl. Opt.* 2, 1103 (1963).
46. Hoefer, C. S., Kirby, K. W., and DeShazer, L. G., Thermo-optic properties of gadolinium garnet laser crystals, *J. Opt. Soc. Am.* (1985).
47. Wemple, S. H., and Tabor, W. J., Refractive index behavior of garnets, *J. Appl. Phys.* 44, 1395–1396 (1973).
48. Wang, H. L., Diamagnetic Faraday Effects in the Garnets YAG, YGG, and GGG, Ph.D. dissertation, University of Southern California, Los Angeles (1975).
49. Barnes, N. P. and Piltch, M. S., Temperature-dependent Sellmeier coefficients and nonlinear optics average power limit for germanium, *J. Opt. Soc. Am.* 69, 178 (1979).
50. Tropf, W. J., Thomas, M. F., and Harris, T. J., Properties of crystals and glasses, *Handbook of Optics*, Vol. 2 (McGraw-Hill, New York, 1995), p. 33.61.
51. Bond, W. L., Boyd, G. D. and Carter, H. L., Jr., Refractive indices of HgS (cinnabar) between 0.62 and $11\text{ }\mu$, *J. Appl. Phys.* 38, 4090 (1967).

52. Lorimor, O. G. and Spitzer, W. G., Infrared refractive index and absorption of InAs and CdTe, *IEEE J. Quantum Electron.* QE-9, 468 (1973).
53. Pettit, G. D. and Turner, W. J., Refractive index of InP, *J. Appl. Phys.* 36, 2081 (1965).
54. Dewey, C. F., Cook, W. R., Hodgson, R. T. and Wynne, J. J., Frequency doubling in $\text{KB}_5\text{O}_8 \cdot 4\text{H}_2\text{O}$ and $\text{NH}_4\text{B}_5\text{O}_8 \cdot 4\text{H}_2\text{O}$ to 217.3 nm, *Appl. Phys. Lett.* 26, 714 (1975).
55. Eimerl, D., Electro optic, linear, and non-linear optical properties of KDP and its isomorphs, *Ferroelectrics*. 72, 95 (1987)
56. Kirby, K.W., and Deshazer, L.G., Refractive indices of 14 nonlinear crystals isomorphic to KH_2PO_4 , *J. Opt. Soc. Am.* B4, 1072 (1987).
57. Van Uitert, L. G., Singh, S., Levinstein, H. J., Geusic, J. E., and Bonner, J. R., A new and stable nonlinear optical material, *Appl. Phys. Lett.* 11, 161 (1967); Van Uitert, L. G., et al., Errata, *Appl. Phys. Lett.* 12, 224 (1968).
58. Bierlein, J.D., Vanherzeele, H., and Ballman, A.A., Linear and nonlinear optical properties of flux grown KTiOAsO_4 , *Appl. Phys. Lett.* 54, 783 (1989).
59. Zysset, B., Biaggio, I., and Gunter, P., Refractive indices of orthorhombic KNbO_3 I: dispersion and temperature dependence. *J. Opt. Soc. Am.* B9, 380 (1992).
60. Fujii, Y. and Sakudo, T., Dielectric and optical properties of KTaO_3 , *J. Phys. Soc. Japan* 41, 888 (1976).
61. Bierlein, J. D., Vanherzeele, H., Potassium titanyl phosphate: properties and new applications, *J. Opt. Soc. Am.* B6, 622 (1989).
62. Vanherzeele, H., Bierlein, J. D., Magnitude of the nonlinear optical coefficients of KTiOPO_4 , *Opt. Lett.* 17, 982 (1992).
63. Fan, T.Y., Huang, C.E., Hu, B.Q., Eckardt, R.C., Fan, Y.X., Byer, R., and Feigelson, R.S., Second harmonic generation and accurate index of refraction measurements in flux-grown KTiOPO_4 , *Appl. Opt.* 26, 2390 (1987).
64. Shen, H.Y., Zhou, Y.P., Lin, W.X., Zeng Z.D., Zeng, R.R., Yu, G.F., Huang, C.H., Jiang, A.D., Jia, S.Q., and Shen, D.Z., Second harmonic generation and sum frequency mixing of dual wavelength Nd: YAlO_3 laser in flux grown KTiOPO_4 crystals, *IEEE J. Quantum Electron.* 28, 48 (1992).
65. LaFrance, T. S., Magnetic dipole radiation in crystals, Ph.D. dissertation, University of Southern California, Los Angeles (1970).
66. Laiho, R. and Lakkisto, M., Investigation of the refractive indices of LaF_3 , CeF_3 , PrF_3 , and NdF_3 , *Phil. Mag. B* 48, 203 (1983).
67. Jenssen, H. P., Begley, R. F., Webb, R., and Morris, R. C., Spectroscopic properties and laser performance of Nd^{3+} in lanthanum beryllate, *J. Appl. Phys.* 47, 1496 (1976).
68. Hanson, F. and Dick, D., Blue parametric generation from temperature-tuned LiB_3O_5 , *Opt. Lett.* 16, 205 (1991).
69. Woods, B. W., Payne, S. A., Marion, J. E., Hughes, R. S., and Davis, L. E., Thermomechanical and thermo-optical properties of the $\text{LiCaAlF}_6:\text{Cr}^{3+}$ laser material, *J. Opt. Soc. Am. B* 8, 970 (1991).
70. Chen, C., Wu, Y., Jiang, A. et al., *J. Opt. Soc. Am. B* 6, 6166 (1989).
71. Choy, M. M. and Byer, R. L., Accurate second-order susceptibility measurements of visible and infrared nonlinear crystals, *Phys. Rev. B* 14, 1693 (1976).
72. Nelson, D. F. and Mikulyak, R. M., Refractive indices of congruently melting lithium niobate, *J. Appl. Phys.* 45, 3688 (1974).
73. Perry, M. D., Payne, S. A., Ditmire, T., Beach, R., Quarles, G. J., Ignatuk, W., Olson, R., and Weston, J., Better materials trigger Cr:LISAF laser development, *Laser Focus World*, 85, (September 1993).
74. Barnes, N. P. and Gettemy, D. J., Temperature variation of the refractive indices of yttrium lithium fluoride, *J. Opt. Soc. Am.* 70, 1214 (1980).

75. Ovanesyan, K. L., Petrosyan, A. G., Shirinyan, G. O., and Avetisyan, A. A., Optical dispersion and thermal expansion of garnets, *Izv. Akad. Nauk SSSR Neorg. Mater.* 17(3), 459–462 (1981 (trans. in *Inorg. Mater.* 17(3), 308–310 (1981).
76. Tropf, W. J. and Thomas, M. E., Magnesium aluminum spinel ($MgAl_2O_4$) spinel, *Handbook of Optical Constants of Solids II*, Palik, E. D., Ed.. (Academic Press, Orlando, FL, 1991), p. 881.
77. Dodge, M. J., Refractive properties of magnesium fluoride, *Appl. Opt.* 23, 1980 (1984).
78. Stephens, R. E. and Malitson, I. H., Index of refraction of magnesium oxide, *J. Nat. Bur. Stand.* 49, 249 (1952).
79. Singh, S., Potopowicz, J. R., and Pawelek, R., Second harmonic properties of tourmaline (unpublished).
80. Chandrasekhar, S. and Madhav, M. S., Optical rotary dispersion of crystals of sodium chlorate and sodium bromate, *Acta Crystallogr.* 23, 911 (1967).
81. Chandrasekhar, S., Optical rotary dispersion of crystals, *Proc. Royal Soc. A*259, 531 (1961).
82. Rosker, M. J., Cheng, K., and Tang, C. L., Practical urea optical parametric oscillator for tunable generation throughout the visible and near-infrared, *IEEE J. Quantum Electron.* QE-21, 1600 (1985).
83. Malitson, I. H. and Dodge, M. J., Refraction and dispersion of lead fluoride, *J. Opt. Soc. Am.* 59, 500A (1969).
84. Malitson, I. H., quoted by Wolfe, W. L., in *Handbook of Optics*, (McGraw-Hill, New York, 1978).
85. Singh, S., Bonner, W. A., Potopowicz, J. R., and Van Uitert, L. G., Nonlinear optical properties of lead niobate, *Electrochem. Soc. Meeting*, Los Angeles, May 1970; Miller, R. C. (private communication).
86. Zemel, J. N., Jensen, J. D., and Scholar, R. B., Electrical and optical properties of epitaxial films of PbS, PbSe, PbTe, and SnTe, *Phys. Rev.* 140A, 330 (1965).
87. Weiting, F. and Yixun, Y., Temperature effects on the refractive index of lead telluride and zinc sulfide, *Infrared Phys.* 30, 371 (1990).
88. Singh, S., Remeika, J. P., and Potopowicz, J. R., Nonlinear optical properties of ferroelectric lead titanate, *Appl. Phys. Lett.* 20, 135 (1972).
89. Barnes, N. P. Gettemy, D. J., and Adhav, R. S., Variation of the refractive index with temperature and the tuning rate for KDP isomorphs, *J. Opt. Soc. Am.* 72, 895 (1982).
90. Singh, S., Potopowicz, J. R., Bonner, W. A., and Van Uitert, L. G., Nonlinear optical properties of rubidium dihydrogen phosphate (unpublished).
91. Cheng, L.T., Cheng, L.K., and Bierlein, J.D., Linear and nonlinear optical properties of the arsenate isomorphs of KTP, *Proc. SPIE* 1863 (1993).
92. Gample, L., and Johnson, F. M., Index of refraction of single-crystal selenium, *J. Opt. Soc. Am.* 59, 72 (1969)
93. Taitian, B., Fitting refractive index data with the Sellmeier dispersion formula, *Appl. Opt.* 23, 4477 (1984).
94. Edwards, D. F. and Ochoa, E., Infrared refractive index of silicon, *Appl. Opt.* 19, 4130 (1980).
95. Singh, S., Potopowicz, J. R., Van Uitert, L. G., and Wemple, S. H., Nonlinear optical properties of hexagonal silicon carbide, *Appl. Phys. Lett.* 19, 53 (1971).
96. Schaffer, P. T. B., Refractive index, dispersion, and birefringence of silicon carbide polytypes, *Appl. Opt.* 10, 1034 (1971).
97. Radhakrishnan, T., Further studies on the temperature variation of the refractive index of crystals, *Proc. Indian Acad. Sci.*, A33, 22 (1951).
98. Feldman, A., Horowitz, D., Walker, R.M., and Dodge, M. J., Optical Materials Characterization Final Report, February 1, 1978–September 30, 1978, NBS Technical Note 993, February 1979.
99. Driscoll, W. G. and Vaughan, W., Eds. *Handbook of Optics*, Optical Society of America, (McGraw-Hill, New York, 1978), p. 7.

100. Payne, S. A., Smith, L. K., Beach, R. J., Chai, B. H. T., Tassano, DeLoach, L. D., Kway, W. L., Solarz, R. W., and Krupke, W. F., Properties of Cr:LiSrAlF₆ crystals for laser operation, *Appl. Opt.* 33, 20 (1994).
101. Singh, S., Potopowicz, J. R., Bonner, W. A., and Van Uitert, L. G. (unpublished).
102. Singh, S., Potopowicz, J. R., Bonner, W. A., and Van Uitert, L. G., *Handbook of Lasers*, Pressley, R. J., Ed. (Chemical Rubber Co, Cleveland, 1971), p. 511.
103. Uchida, N., Optical properties of single crystal paratellurite (TeO₂), *Phys. Rev. B* 4, 3736 (1971).
104. DeVore, J. R., Refractive index of rutile and sphalerite, *J. Opt. Soc. Am.* 41, 416 (1951).
105. Bieniewski, T. M. and Czyzak, S. J., Refractive indexes of single hexagonal ZnS and CdS crystals, *J. Opt. Soc. Am.* 53, 496 (1963).
106. Hettner, G. and Leisegang, G., Dispersion of the mixed crystals TlBr-TlI (KRS-5) and TlCl-TlBr (KRS-6) in the infrared, *Optik* 3, 305 (1948).
107. Rodney, W. S. and Malitson, I. H., Refraction and dispersion of thallium bromide iodide, *J. Opt. Soc. Am.* 46, 956 (1956).
108. Ewbank, M. D., Newman, P. R., Moat, N. L., et al., The temperature dependence of optical and mechanical properties of Tl₃AsSe₃, *J. Appl. Phys.* 51, 3848 (1980) and *Appl. Opt.* 11, 993 (1972).
109. Nigara, Y., Measurement of the optical constants of yttrium oxide, *Jap. J. Appl. Phys.* 7, 404 (1968).
110. Martin, K. W. and DeShazer, L. G., Indices of refraction of the biaxial crystal YAlO₃, *Appl. Opt.* 12, 941 (1973).
111. Beach, R., Shinn, M. D., Davis, L., Solarz, R. W., and Krupke, W. F., Optical absorption and stimulated emission of neodymium in yttrium orthosilicate, *IEEE J. Quantum Electron.* 26(8), 1405–1412 (1990).
112. Maunder, E. A. and DeShazer, L. G., Use of yttrium orthovanadate for polarizers, *J. Opt. Soc. Am.* 61, 684A (1971).
113. Lomheim, T. S. and DeShazer, L. G., Optical absorption intensities of trivalent neodymium in the uniaxial crystal yttrium orthovanadate, *J. Appl. Phys.* 49, 5517 (1978).
114. Li, H. H., Refractive index of ZnS, ZnSe, and ZnTe and its wavelength and temperature derivatives, *J. Phys. Chem. Ref. Data* 13, 103 (1984).
115. Duncanson, A. and Stevenson, R. W. H., *Proc. Phys. Soc.* 72, 1001 (1958).
116. Wood, D. L. and Nassau, K., Refractive index of cubic zirconia stabilized with yttria, *Appl. Opt.* 21, 2978 (1982).
117. Wu, Y., Sasaka, T., Nakai, S., et al., CsB₃O₅: A new nonlinear optical crystal, *Appl. Phys. Lett.* 62, 24 (1993).
118. Producer's literature.
119. Dodge, M. J., Refractive index, *Handbook of Laser Science and Technology, VoL. IV: Optical Materials, Part 2* (CRC Press, Boca Raton, FL, 1986), p. 21.
120. Icenogle, H. W., Platt, B. C., and Wolfe, W. L., Refractive indexes and temperature coefficients of germanium and silicon, *Appl. Opt.* 15, 2348 (1976).
121. Cook, W. R., and Hubby, L. M., Indices of refraction of potassium pentaborate, *J. Opt. Soc. Am.* 66, 72 (1976).
122. Pikhtin, A. N. and Yas'kov, A. D., Dispersion of the refractive index of semiconductors with diamond and zinc-blende structures, *Sov. Phys. Semicond.* 12, 622 (1978).

1.3.5 Thermooptic Coefficients

Thermooptic Coefficients

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
AgBr	3390	-61	RT	1
	10600	-50	RT	1
AgCl	610	-61	298	4
	633	-61	RT	1
	3390	-58	RT	1
	10600	-35	RT	1
AgGaS ₂	600	258 (o) 255 (e)	RT RT	1 1
	1000	176 (o) 179 (e)	RT RT	1 1
	3390	154 (o) 155 (e)	RT RT	5 5
	10000	153 (o) 155 (e)	RT RT	1 1
	1064	98 (o) 66 (e)	RT RT	5 5
	3390	74 (o) 43 (e)	RT RT	5 5
	10600	58 (o) 46 (e)	RT RT	5 5
	457.9	1.8 (o) 1.9 (e) 11.7 (o) 12.8 (e) 15.4 (o) 16.9 (e)	93 93 293 293 473 473	4 4 4 4 4 4
Al ₂ O ₃	589	13.6 (o) 14.7 (e)	RT RT	1 1
	633	12.6	RT	1
Al ₂₃ O ₂₇ N ₅	633	11.7	RT	1
BaB ₂ O ₄	404.7	-16.4 (o) -9.4 (e)	RT RT	1 1
	579	-16.6 (o) -9.8 (e)	RT RT	1 1
	1014	-16.8 (o) -8.8 (e)	RT RT	1 1
	457.9	-7.8 -15.6	90 293	4 4

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
BaF ₂		-15.6	293	4
		-18.8	473	4
	632.8	-16.3	313	2
	1150	-8.1	90	4
		-16.2	293	4
		-19.3	473	4
	3390	-15.9	RT	1
	10600	-7.3	90	4
		-14.5	293	4
		-17.5	473	4
Ba ₂ NaNb ₅ O ₁₅	1064	-25 (y)	RT	5
		80 (z)		5
BeAl ₂ O ₄	1064	8	300	
BeO	458	8.2 (o)	RT	1
		13.4 (e)	RT	1
	633	8.2 (o)	RT	1
		13.4 (e)	RT	1
	1064	8.18 (o)	RT	5
		13.40 (e)	RT	5
Bi ₁₂ GeO ₂₀	510	-34.5	RT	1
	650	-34.9	RT	1
C (diamond)	546	10.1	RT	1
	587	10	300	4
	30000	9.6	RT	1
CaCO ₃	211	21.5 (o)	334	4
		22.0 (e)	334	4
	365	3.6 (o)	RT	1
		14.4 (e)	RT	1
	441	3.2 (o)	334	4
		13.2 (e)	334	4
	458	3.2 (o)	RT	1
		13.1 (e)	RT	1
	633	2.1 (o)	RT	1
		11.9 (e)	RT	1
CaF ₂	254	-7.5	RT	1
	457.9	-3.9		
		-11.0	93	4
		13.4	293	4
	632.8	-11.5		
	663	-10.4	473	4
	1150	-4.1	313	2

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
CaF ₂		−11.5	RT	1
		−14.1		
	3390	−8.1	93	4
			293	4
			473	4
			RT	1
CaMoO ₄	587.6	−9.6 (o) −10.0 (e)	273–373 273–373	4 4
Ca ₅ (PO ₄) ₃ F	500–1000	−10 (o) −8 (e)	293–338 293–338	3 3
CaWO ₄	546.1	−7.1 (o) −10.2 (e)	293 293	4 2
CdF ₂	457.9	−4.3 −9.2 −12.4	93 293 473	4 4 4
	1150	−5.7 −11.5 −15.1	93 293 473	4 4 4
	3390	−5.3 −11.1 −14.8	93 293 473	4 4 4
CdS	10600	58.6 (o) 62.4 (e)	RT RT	1 1
CdTe	1150	147	RT	1
	3390	98.2	RT	1
	10600	98.0	RT	1
CsBr	254	−82	RT	1
	288	−86	293	4
	400	−86	293	4
	633	−84.7	RT	1
	640	−85	293	4
	1150	−84	293	4
	3400	−84	293	4
	10600	−83	293	4
	17000	−82	293	4
	30000	−75.8	RT	1
CsCl	288	−79	293	4
	365	−78.7	293	1
	400	−78	293	4

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
CsCl	633	-77.4	293	1
	640	-77	293	4
	1150	-77	293	4
	3400	-76	293	4
	10600	-75	293	4
	17000	-72	293	4
	20000	-70.0	RT	1
CsF	288	-41	293	4
	400	-42	293	4
	640	-42	293	4
	1150	-42	293	4
	3400	-42	293	4
	10600	-39	293	4
	17000	-32	293	4
CsI	300	-79	288–307	4
	365	-87.5	RT	1
	633	-99.3	RT	1
	1000	-98.6	288–307	4
	10000	-91.7	288–307	4
	20000	-89.3	288–307	4
	30000	-88.0	288–307	4
	40000	-86.2	288–307	4
	50000	-78.5	288–307	4
GaAs	1150	250	RT	1
	3390	200	RT	1
	10600	200	RT	1
GaN	1150	61	RT	1
GaP	546	200	RT	1
	633	160	RT	1
GaSb	1550	380	80	4
	3700	312	100–400	4
$\text{Gd}_3\text{Sc}_2\text{Al}_3\text{O}_{12}$	543	8.9	298–308	3
	1152	5.05	308–313	3
$\text{Gd}_3\text{Sc}_2\text{Ga}_3\text{O}_{12}$	441.6	13.46	308–313	3
	543	13.3	298–308	3
	632.8	10.76	308–313	3
	1064	10.7	283–303	3
	1152	9.04	308–313	3
Ge	2500	462	RT	1
	5000	416	RT	1

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
Ge	20000	401	RT	1
InAs	3250	315	300–600	4
	4000	500	RT	1
	6000	400	RT	1
	10000	300	RT	1
InP	5000	83	RT	1
	10600	82	RT	1
	20000	77	RT	1
InSb	2000–40000	560	120–360	4
	5000–200000	460	100–400	4
KBr	457.9	-28.5	93	4
		-39.3	293	4
		-43.8	473	4
	1150	-30.5	93	4
		-41.9	293	4
		-46.3	473	4
	10600	30.6	93	4
		41.1	293	4
		45.6	473	4
KCl	457.9	-22.6	93	4
		-34.9	293	4
		-39.6	473	4
	1150	-23.5	93	4
		-36.2	293	4
		-41.1	473	4
	10600	-23.3	93	4
		-34.8	293	4
		-39.1	473	4
KF	254	-19.9	RT	1
	288	-21	293	4
	400	-22	293	4
	640	-23	293	4
	1150	-23	293	4
	3400	-23	293	4
	10600	-17	293	4
	17000	3	293	4
KH ₂ PO ₄	624	-39.6 (o)	RT	1
		-38.2 (e)	RT	1
KI	288	268	293	4
	400	5	293	4

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
KI	458	-41.5	RT	1
	640	-49	293	4
	1150	-66	293	4
	3400	-72	293	4
	10600	-66	293	4
	17000	-52	293	4
	30000	-30.8	RT	1
KNbO ₃	436	-67 (x) -26 (y) 125 (z)	RT RT RT	1 1 1
	1064	23 (x) -34 (y) 63 (z)	RT RT RT	1 1 1
	3000	21 (x) -23 (y) 55 (z)	RT RT RT	1 1 1
KTiOPO ₄	365	-6.5 (x)	RT	5
	532	-7.4 (x) -0.9 (y) -13.5 (z)	RT RT RT	5 5 5
	532	-1.9 (x) -13.0 (y) -7.4 (z)	RT RT RT	1 1 1
	1064	-1.9 (x) -13.0 (y) -8.3 (z)	RT RT RT	5 5 5
LiB ₃ O ₅	288	56	293	4
	355	2	293	4
	640	-39	293	4
	1150	-48	293	4
	3400	-50	293	4
	10600	-37	293	4
	17000	-1	293	4
LiCaAlF ₆	546, 764	-4.6 (o) -4.2 (e)	293–353 293–353	3 3
LiCl	288	9.9	293	4
	640	-32	293	4
	1150	-37	293	4
	3400	-38	293	4
	10600	-21	293	4
		-16	293	4

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
LiF	457.9	-3.3	93	4
		-21.6	473	4
	632.8	-17.0	313	2
	1150	-3.8	93	4
		-16.7	293	4
	3390	-19.9	473	4
		-4.0	93	4
		-14.5	293	4
		-18.0	473	4
LiI	288	268	293	4
	410	5	293	4
	640	-49	293	4
	1150	-66	293	4
	3400	-72	293	4
	10600	-66	293	4
	17000	-52	293	4
LiIO ₃	400	-74.5 (o)	RT	1
		-63.5 (e)	RT	1
	1000	-84.9 (o)	RT	1
		-69.2 (e)	RT	1
LiNbO ₃	660	4.4 (o)	RT	1
		37.9 (e)	RT	1
	3390	0.3 (o)	RT	1
		28.9 (e)	RT	1
LiSrAlF ₆	900	-4.0 (o)	293–353	3
		-2.5 (e)	293–353	3
LiTaO ₃	468	62 (o)	298	3
		12 (e)	298	3
	546	58 (o)	298	3
		7 (e)	298	3
	644	52 (o)	298	3
		5 (e)	298	3
LiYF ₄	436	-0.54 (o)	RT	1
		-2.44	RT	1
	546	-0.67 (o)	RT	1
		-2.30 (e)	RT	1
	578	-0.91 (o)	RT	1
		-2.86 (e)	RT	1
MgAl ₂ O ₄	589	9.0	RT	1
		1.8	93	4
		1.5	293	4

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
MgF ₂	457.9	2.4	93	4
		0.9	293	4
		0.6	473	4
		0.1	473	4
	632.8	1.12 (o)	293	2
		0.58 (e)	293	2
	1150	2.0	93	4
		1.4	93	4
		0.9	293	4
		0.3	293	4
		-0.1	473	4
		-0.7	473	4
	3390	2.0	93	4
		1.5	93	4
		1.1	293	4
		0.6	293	4
		0.3	473	4
		-0.3	473	4
MgO	365	19.5	RT	1
		18.9	293	4
		19.1	303	4
		19.3	313	4
	546	16.5	RT	1
		15.3	293	4
		15.5	303	4
		15.7	313	4
	767.9	13.6	293	4
		13.8	303	4
		14.0	313	4
Mg ₂ SiO ₄	488	2.8	298–313	3
NaBr	288	12.9	293	4
	350	-29	293	4
	365	-30.4	RT	1
	640	-39	293	4
	1150	-40	293	4
	3400	-40	293	4
	10600	-38	293	4
	17000	-32	293	4
NaCl	457.9	-20.6	93	4
		-34.2	293	4
		-39.2	473	4

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
NaCl	633	-35.4	RT	1
	1150	-22.2	93	4
		-36.4	293	4
		-41.4	473	4
	3390	22.4	93	4
		-36.6	293	4
		-41.8	473	4
NaF	457.9	-4.1	93	4
		-11.9	293	4
		-14.7	473	4
	632.8	-13.0	313	2
	1150	-4.5	93	4
		-13.2	293	4
		-15.9	473	4
	3390	-4.5	93	4
		-12.5	293	4
		-14.9	473	4
NaI	288	72	293	4
	325	3	293	4
	640	-46	293	4
	1150	-50	293	4
	3400	-50	293	4
	10600	-49	293	4
	17000	-44	293	4
$\text{NH}_4\text{H}_2\text{PO}_4$	624	-47.1 (o)	RT	1
		-4.3 (e)	RT	1
PbMoO_4	588	-75 (o)	273–373	4
		-41 (e)	273–373	4
PbS	3390	-2100	RT	1
	5000	-1900	RT	1
	10600	-1700	RT	1
PbSe	3390	-2300	RT	1
	5000	-1400	RT	1
	10600	-860	RT	1
PbTe	3390	-2100	RT	1
	5000	-1500	RT	1
	10600	-1200	RT	1
RbBr	288	-40	293	4
	400	-44	293	4
	640	-45	293	4

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
RbBr	1150	-45	293	4
	3400	-45	293	4
	10600	-44	293	4
	17000	-43	293	4
RbCl	288	-38	293	4
	400	-39	293	4
	640	-39	293	4
	1150	-39	293	4
	3400	-39	293	4
	10600	-38	293	4
	17000	-35	293	4
RbI	288	-37	293	4
	400	-55	293	4
	640	-56	293	4
	1150	-56	293	4
	3400	-56	293	4
	10600	-56	293	4
	17000	-55	293	4
Si	1407	206	291	4
	2500	166	RT	1
	3826	174	312	4
	5000	159	RT	1
	10600	157	RT	1
SiO_2 (α -quartz)	254	-2.9 (o) -4.0 (e)	RT	1
	365	-5.4 (o) -6.2 (e)	RT	1
	546	-6.2 (o) -7.0 (e)	RT	1
	750–1000	-11 (o) -8 (e)	293–338	3
	457.9	-54	93	4
	632.8	-12.0 -13.4	293 473	4
	1150	-12.5 -5.5 -12.6	313 93 293	2 4 4
$\text{Sr}_5(\text{VO}_4)_3\text{F}$	10600	-14.0 -3.5 -9.8 -12.0	473 93 293 473	4 4 4 4

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
TeO ₂	436	30 (o) 25 (e)	RT RT	1 1
	644	9 (o) 8 (e)	RT RT	1 1
TiO ₂ (rutile)	405	4 (o) −9 (e)	RT RT	1 1
Tl[Br,I] KRS-5	576.9	−254	292–304	4
	1014	−240	292–304	4
	11035	−233	292–304	4
	25970	−202	292–304	4
	39380	−154	292–304	4
Tl ₅ AsSe ₃	2–10	−45 (o) 36 (e)	RT RT	1 1
YVO ₄	—	3.9 (o) 8.5 (e)	— —	3 3
YVO ₄	—	3 (o) 8.5 (e)	— —	3 3
Y ₂ O ₃	633	8.3	RT	1
Y ₂ SiO ₅	546.1	9.05 (x) 5.70 (y) 6.73 (z)	298–343 298–343 298–343	3 3 3
Y ₃ Al ₅ O ₁₂	457.9	11.89	303–318	2
	476.5	12.00	303–318	2
	488.8	11.60	303–318	2
	496.5	11.38	303–318	2
	501.7	11.37	303–318	2
	514.5	10.57	303–318	2
	543	9.7	298–308	3
	632.8	10.35	303–318	2
	1064.2	9.05	303–318	2
YAlO ₃ b-axis rod	1064	9.8 (a) 14.5 (c)	— —	4 4
ZnGeP ₂	640	359 (o) 376 (e)	— —	1 1
	1000	212 (o) 230 (e)	— —	1 1
	10000	165 (o) 170 (e)	— —	1 1

Thermooptic Coefficients—*continued*

Material	Wavelength (nm)	dn/dt ($10^{-6}/\text{K}$)	Temperature (K)	Ref.
β -ZnS	633	63.5	RT	1
	1150	35	93	4
		46	293	4
		49.8	RT	1
		50	473	4
	3390	28	93	4
		42	293	4
		46	473	4
	10600	27	93	4
		41	293	4
		47	473	4
β -ZnS (CVD)	633	63.5	RT	6
	1150	49.8	RT	6
	3390	45.9	RT	6
	10600	46.3	RT	6
ZnSe	633	76	93	4
		106	293	4
		121	473	4
	1150	59.7	RT	1
	3390	50	93	4
		62	293	4
		67	473	4
	10600	49	93	4
		61	293	4
		69	473	4
ZnSe (CVD)	633	1.6	RT	6
	1150	70	RT	6
	3390	62	RT	6
	10600	61	RT	6
$\text{ZrO}_2:12\%\text{Y}_2\text{O}_3$			RT	1
	360	16	293–403	4
	458	10.0	RT	1
	633	7.9	RT	1
	800	7.2	293–403	4
	1690	6.2	293–403	4

(o) ordinary ray

(e) extraordinary ray

RT room temperature

References:

1. Topf, W. J., Thomas, M. F., and Harris, T. J., Properties of Crystals and glasses, *Handbook of Optics*, Vol. II (McGraw-Hill, New York, 1995), p. 33.57 and references cited therein.
2. DeShazer, L. G., Rand, S. C., and Wechsler, B. A., Laser crystals, *Handbook of Laser Science and Technology, Vol. V: Optical Materials, Part 3* (CRC Press, Boca Raton, FL, 1987), p. 595 and references cited therein.
3. Wechsler, B. A. and Sumida, D. S., Laser crystals, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 595 and references cited therein.
4. Dodge, M. J., Refractive index, *Handbook of Laser Science and Technology, Vol. IV: Optical Materials, Part 2* (CRC Press, Boca Raton, FL, 1986), p. 21 and references cited therein.
5. Singh, S., Nonlinear optical materials, *Handbook of Laser Science and Technology, Vol. III: Optical Materials, Part 1* (CRC Press, Boca Raton, FL, 1986), p. 54 ff.
6. Klein, C., Raytheon Company.

1.4 Mechanical Properties

1.4.1 Elastic Constants

The following tables are from the *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12–37, with additions from the *Handbook of Optics*, Vol. 2 (McGraw–Hill, New York, 1999) and the *Handbook of Laser Science and Technology*, Vol. IV and Suppl. (CRC Press, Boca Raton, FL, 1995).

The elastic constants C_{ij} for single crystals are given in units of 10^{11} N/m^2 (equivalent to 100 GPa or 10^{12} dyn/cm^2). The values are for room temperature.

A useful compilation of published values from various sources may be found in Simmons, G., and Wang, H., *Single Crystal Elastic Constants and Calculated Aggregate Properties: A Handbook*, 2nd edition, (The MIT Press, Cambridge, MA, 1971). Temperature and pressure coefficients of the elastic constants for many materials are included in *Landolt–Börnstein, New Series*, III/11, Hellwege, K.–H. and Hellwege, A. M., Eds. (Springer–Verlag, New York, 1979).

Cubic Crystals

Material	Temperature (K)	Elastic constants (10^{11} N/m^2)			Ref.
		C_{11}	C_{12}	C_{44}	
AgBr	300	0.5920	0.3640	0.0616	48
AlAs	RT	1.163	0.576	0.541	117
Al ₂₃ O ₂₇ N ₅	RT	3.93	1.08	1.19	117
AlSb	300	0.8939	0.4427	0.4155	2
Ba(NO ₃) ₂	293	0.2925	0.2065	0.1277	7
BaF ₂	298	0.9199	0.4157	0.2568	6
Bi ₄ Ge ₃ O ₁₂	RT	1.250	0.324	0.249	117
Bi ₄ Si ₃ O ₁₂	RT	1.298	0.297	0.247	117
BN	RT	7.83	1.46	4.18	117
BP	RT	3.15	1.00	1.60	117
C (diamond)	RT	10.40	1.70	5.50	117
CaF ₂	298	1.6420	0.4398	0.8406	8
CaLa ₂ S ₄	RT	0.98	0.47	0.50	117
CdTe	298	0.5351	0.3681	0.1994	9
CsBr	298	0.3063	0.0807	0.0750	11
CsCl	298	0.3644	0.0882	0.0804	11
CsI	298	0.2446	0.0661	0.0629	11
GaAs	298	1.1877	0.5372	0.5944	17
GaP	300	1.4120	0.6253	0.7047	18
GaSb	298	0.8839	0.4033	0.4316	16
Gd ₃ Ga ₅ O ₁₂	RT	2.85	1.14	0.897	118
Gd ₃ Sc ₂ Al ₃ O ₁₂	RT	2.99	1.01	0.89	119
Gd ₃ Sc ₂ Ga ₃ O ₁₂	RT	2.77	1.049	0.8036	119

Cubic Crystals—continued

Material	Temperature (K)	Elastic constants (10^{11} N/m 2)			Ref.
		C ₁₁	C ₁₂	C ₄₄	
Ge	298	1.2835	0.4823	0.6666	20
HgTe	290	0.548	0.381	0.204	36
InAs	293	0.8329	0.4526	0.3959	23
InP	RT	1.0220	0.5760	0.4600	24
InSb	298	0.6720	0.3670	0.3020	22
KBr	298	0.3468	0.0580	0.0507	11
KCl	298	0.4069	0.0711	0.0631	11
KCN	RT	0.1940	0.1180	0.0150	32
KF	295	0.6490	0.1520	0.1232	33
KI	300	0.2710	0.0450	0.0364	42
KMgF ₃	RT	1.32	0.396	0.485	118
KTaO ₃	RT	4.31	1.03	1.09	117
LiBr	RT	0.3940	0.1880	0.1910	32
LiCl	295	0.4927	0.2310	0.2495	33
LiF	RT	1.1397	0.4767	0.6364	34
LiI	RT	0.2850	0.1400	0.1350	32
Lu ₃ Al ₅ O ₁₂	RT	3.39	1.14	1.13	119
MgAl ₂ O ₄	298	2.9857	1.5372	1.5758	53
MgO	298	2.9708	0.9536	1.5613	20
MnO	298	2.23	1.20	0.79	35
NaBr	300	0.3970	0.1001	0.0998	33
NaBrO ₃	RT	0.5450	0.1910	0.1500	32
NaCl	298	0.4947	0.1288	0.1287	11
NaClO ₃	RT	0.4920	0.1420	0.1160	50
NaF	300	0.9700	0.2380	0.2822	51
NaI	300	0.3007	0.0912	0.0733	52
NH ₄ Br	300	0.3414	0.0782	0.0722	3
NH ₄ Cl	290	0.3814	0.0866	0.0903	4
Pb(NO ₃) ₂	293	0.3729	0.2765	0.1347	29
PbF ₂	300	0.8880	0.4720	0.2454	28
PbS	RT	1.26	0.162	0.171	117
PbSe	RT	1.178	0.139	0.1553	117
PbTe	303.2	1.0795	0.0764	0.1343	30
RbBr	300	0.3152	0.0500	0.0380	45
RbCl	300	0.3624	0.0612	0.0468	45
RbI	300	0.2556	0.0382	0.0278	45
Si	298	1.6578	0.6394	0.7962	46
β -SiC	RT	3.50	1.42	2.56	117
Sr(NO ₃) ₂	293	0.4255	0.2921	0.1590	29
SrF ₂	300	1.2350	0.4305	0.3128	54
SrO	300	1.601	0.435	0.590	55

Cubic Crystals—continued

Material	Temperature (K)	Elastic constants (10^{11} N/m 2)				Ref.
		C ₁₁	C ₁₂	C ₄₄		
SrTiO ₃	RT	3.4817	1.0064	4.5455	56	
ThO ₂	298	3.670	1.060	0.797	61	
TiC	RT	5.00	1.13	1.75	107	
TlBr	298	0.3760	0.1458	0.0757	59	
TlCl	RT	0.403	0.155	0.0769	117	
Tl[Br,I], KRS-5	RT	0.341	0.136	0.0579	117	
Tl[Br,Cl], KRS-6	RT	0.397	0.149	0.0723	117	
Y ₂ O ₃	RT	2.33	1.01	0.67	117	
Y ₃ Al ₅ O ₁₂	RT	3.49	1.21	1.14	119	
Y ₃ Fe ₂ (FeO ₄) ₃	298	2.680	1.106	0.766	19	
Y ₃ Sc ₂ Ga ₃ O ₁₂	RT	2.75	1.00	0.85	119	
Y _{2.25} Yb _{0.75} Al ₅ O ₁₂	RT	4.55	1.54	1.51	119	
ZnS	298	1.0462	0.6534	0.4613	68	
ZnSe	298	0.8096	0.4881	0.4405	68	
ZnTe	298	0.7134	0.4078	0.3115	68	
ZrC	298	4.720	0.987	1.593	63	

Trigonal Crystals—Point Groups 32, 3m, -3m

Material	Temp. (K)	Elastic constants (10^{11} N/m 2)						Ref.
		C ₁₁	C ₁₂	C ₁₃	C ₁₄	C ₃₃	C ₄₄	
Ag ₃ AsS ₃	RT	0.570	0.318	—	—	0.364	0.090	117
Al ₂ O ₃	300	4.9735	1.6397	1.1220	-0.2358	4.9911	1.4739	111
AlPO ₄	RT	1.0503	0.2934	0.6927	-0.1271	1.3353	0.2314	73
β -Ba ₃ B ₆ O ₁₂	RT	1.238	0.603	0.494	0.123	0.533	0.078	117
CaCO ₃	300	1.4806	0.5578	0.5464	-0.2058	0.8557	0.3269	113
Fe ₂ O ₃	RT	2.4243	0.5464	0.1542	-0.1247	2.2734	0.8569	82
LiCaAlF ₆	RT	1.18	0.412	0.535	\pm 0.192	1.07	0.504	119
LiNbO ₃	RT	2.030	0.530	0.750	0.090	2.450	0.600	114
LiSrAlF ₆	RT	1.17	—	—	—	0.94	—	119
LaF ₃	RT	1.80	0.88	0.59	<0.005	2.22	0.34	117
LiTaO ₃	RT	2.330	0.470	0.800	-0.110	2.750	0.940	114
NaNO ₃	RT	0.8670	0.1630	0.1600	0.0820	0.3740	0.2130	12
Se	RT	0.198	0.066	0.202	0.069	0.836	0.183	117
α -SiO ₂	298	0.8680	0.0704	0.1191	-0.1804	1.0575	0.5820	115
Te	RT	0.3257	0.0845	0.257	0.1238	0.717	0.3094	117
Tourmaline*	RT	2.7066	0.6927	0.0872	-0.0774	1.6070	0.6682	82

* Na₃Al₆Si₆O₁₈ (BO₃)₂(O,H,F)₄

Orthorhombic Crystals—Point Groups 222, m22, mmm

Material	Temp. (K)	Elastic constants (10^{11} N/m 2)									
		C ₁₁	C ₁₂	C ₁₃	C ₂₂	C ₂₃	C ₃₃	C ₄₄	C ₅₅	C ₆₆	Ref.
Al ₂ SiO ₃ (OH,F) ₂	RT	2.8136	1.2582	0.8464	3.8495	0.8815	2.9452	1.0811	1.3298	1.3089	82
BaSO ₄	RT	0.8941	0.4614	0.2691	0.7842	0.2676	1.0548	0.1190	0.2874	0.2778	82
BeAl ₂ O ₄	RT	4.32	—	—	4.64	—	5.11	1.45	1.52	1.42	120
CaCO ₃	RT	1.5958	0.3663	0.0197	0.8697	0.1597	0.8503	0.4132	0.2564	0.4274	82
CaSO ₄	RT	0.9382	0.1650	0.1520	1.845	0.3173	1.1180	0.3247	0.2653	0.0926	84
Cs ₂ SO ₄	293	0.4490	0.1958	0.1815	0.4283	0.1800	0.3785	0.1326	0.1319	0.1323	81
HIO ₃	RT	0.3030	0.1194	0.1169	0.5448	0.0548	0.4359	0.1835	0.2193	0.1736	73
K ₂ SO ₄	293	0.5357	0.1999	0.2095	0.5653	0.1990	0.5523	0.195	0.1879	0.1424	81
KB ₅ O ₈ ·4H ₂ O	RT	0.582	0.229	0.174	0.359	0.231	0.255	0.164	0.046	0.057	71
KNbO ₃	RT	2.26	0.96	—	2.70	—	2.80	0.743	0.250	0.955	117
KTiOPO ₄	RT	1.59	—	—	1.54	—	1.75	—	—	—	117
LiNH ₄ C ₄ H ₄ O ₆ ·4H ₂ O	RT	0.3864	0.1655	0.0875	0.5393	0.2007	0.3624	0.1190	0.0667	0.2326	12
(MgFe)SiO ₃	RT	1.876	0.686	0.605	1.578	0.561	2.085	0.700	0.592	0.544	78
(MgFe)SiO ₄	RT	3.240	0.590	0.790	1.980	0.780	2.490	0.667	0.810	0.793	87
Mg ₂ SiO ₄	298	3.2848	0.6390	0.6880	1.9980	0.7380	2.3530	0.6515	0.8120	0.8088	85
MgSO ₄ ·7H ₂ O	RT	0.325	0.174	0.182	0.288	0.182	0.315	0.078	0.156	0.090	86
(Na,Al)SiO ₃	RT	0.716	0.261	0.297	0.632	0.297	1.378	0.196	0.248	0.423	78
Na ₂ C ₄ H ₄ O ₆ ·2H ₂ O	RT	0.461	0.286	0.320	0.547	0.352	0.665	0.124	0.031	0.098	12
(NH ₄) ₂ SO ₄	293	0.3607	0.1651	0.1580	0.2981	0.1456	0.3534	0.1025	0.0717	0.0974	81
NaK(C ₄ H ₄ O ₆)·4H ₂ O	RT	0.255	0.141	0.116	0.381	0.146	0.371	0.134	0.032	0.098	71
NaNH ₄ C ₄ H ₄ O ₆ ·4H ₂ O	RT	0.3685	0.2725	0.3083	0.5092	0.3472	0.5541	0.1058	0.0303	0.0870	12
NiSO ₄ ·7H ₂ O	RT	0.353	0.198	0.201	0.311	0.201	0.335	0.091	0.172	0.099	86
Rb ₂ SO ₄	293	0.5029	0.1965	0.1999	0.5098	0.1925	0.4761	0.1626	0.1589	0.1407	81
Sr(CHO ₂) ₂ ·2H ₂ O	RT	0.4391	0.1037	-0.149	0.3484	-0.014	0.3746	0.1538	0.1075	0.1724	12

SrSO ₃	RT	1.044	0.773	0.605	1.061	0.619	1.286	0.135	0.279	0.266	12
TlSO ₄	293	0.4106	0.2573	0.2288	0.3885	0.2174	0.4268	0.1125	0.1068	0.0751	81
ZnSO ₄ •7H ₂ O	RT	0.3320	0.1720	0.2000	0.2930	0.1980	0.3200	0.0780	0.1530	0.0830	86

Tetragonal Crystals—Point Groups 4, -4, 422, 4/m

Material	Temperature (K)	Elastic constants (10 ¹¹ N/m ²)							Ref.
		C ₁₁	C ₁₂	C ₁₃	C ₁₆	C ₃₃	C ₄₄	C ₆₆	
CaMoO ₄	298	1.447	0.664	0.466	0.134	1.265	0.369	0.451	79
CaWO ₄	RT	1.44	0.648	0.448	-0.142	1.26	0.369	0.461	117
PbMoO ₄	RT	1.09	0.680	0.530	-0.140	0.920	0.267	0.335	117
SrMoO ₄	RT	1.19	0.620	0.480	-0.120	1.04	0.349	0.420	117
LiYF ₄	RT	1.21	0.609	0.526	-0.077	1.56	0.409	0.177	117

Tetragonal Crystals—Point Groups 4mm, -42m, 422, 4/mmm

Material	Temperature (K)	Elastic constants (10^{11} N/m 2)						Ref.
		C ₁₁	C ₁₂	C ₁₃	C ₃₃	C ₄₄	C ₆₆	
AgGaS ₂	RT	0.879	0.584	0.592	0.758	0.241	0.308	117
BaTiO ₃	298	2.7512	1.7897	1.5156	1.6486	0.5435	1.1312	70
CdGeAs ₂	RT	0.945	0.596	0.597	0.834	0.421	0.408	117
KH ₂ AsO ₄	RT	0.530	-0.060	-0.020	0.370	0.120	0.070	12
KH ₂ PO ₄	RT	0.7140	-0.049	0.1290	0.5620	0.1270	0.0628	71
MgF ₂	RT	1.237	0.732	0.536	1.770	0.552	0.978	72
NH ₄ H ₂ AsO ₄	298	0.6747	-0.106	0.1652	0.3022	0.0685	0.0639	69
NH ₄ H ₂ PO ₄	293	0.6200	-0.050	0.1400	0.3000	0.0910	0.0610	69
(NH ₄) ₃ CO	RT	0.217	0.089	0.24	0.532	0.0626	0.0045	117
NiSO ₄ ·6H ₂ O	RT	0.3209	0.2315	0.0209	0.2931	0.1156	0.1779	73
RbH ₂ PO ₄	298	0.5562	-0.064	0.0279	0.4398	0.1142	0.0350	74
TeO ₂	RT	0.5320	0.4860	0.2120	1.0850	0.2440	0.5520	76
TiO ₂	298	2.7143	1.7796	1.4957	4.8395	1.2443	1.9477	75
ZrSiO ₄	RT	2.585	1.791	1.542	3.805	0.733	1.113	78

Monoclinic Crystals

Material	Temp. (K)	Elastic Constants (10^{11} N/m 2)						Ref.
		C ₁₁	C ₁₂	C ₁₃	C ₁₅	C ₂₂		
(C ₆ H ₅ CH) ₂	RT	0.0930	0.0570	0.0670	-0.003	0.0920		94
(CaMg)Si ₂ O ₆	RT	2.040	0.884	0.0883	-0.193	1.750		91
C ₁₄ H ₁₀	RT	0.0852	0.0672	0.0590	-0.0192	0.1170		90
CoSO ₄ •7H ₂ O	RT	0.335	0.205	0.158	0.016	0.378		86
FeSO ₄ •7H ₂ O	RT	0.349	0.208	0.174	-0.020	0.376		86
K ₂ C ₄ H ₄ O ₆	RT	0.3110	0.1720	0.1690	0.0287	0.3900		32
KAlSi ₃ O ₈	RT	0.664	0.438	0.259	-0.033	1.710		92
KHC ₄ H ₄ O ₆	RT	0.4294	0.1399	0.3129	-0.0105	0.3460		12
Li ₂ SO ₄ •H ₂ O	RT	0.5250	0.1715	0.1730	-0.0196	0.5060		32
(NaFe)Si ₂ O ₆	RT	1.858	0.685	0.707	0.098	1.813		89
(NH ₂ CH ₂ COOH) ₃ •H ₂ SO ₄ (TGS)	RT	0.4550	0.1720	0.1980	-0.030	0.3210		32
Na ₂ S ₂ O ₃	RT	0.3323	0.1814	0.1875	0.0225	0.2953		12
Y ₂ SiO ₅	RT	0.658	—	—	±0.706	1.85		119

Monoclinic Crystals—continued

Material	Elastic Constants (10^{11} N/m 2)							
	C ₂₃	C ₂₅	C ₃₃	C ₃₅	C ₄₄	C ₄₆	C ₅₅	C ₆₆
(C ₆ H ₅ CH) ₂	0.0485	-0.005	0.0790	-0.005	0.0325	0.0050	0.0640	0.0245
(CaMg)Si ₂ O ₆	0.482	-0.196	2.380	-0.336	0.675	-0.113	0.588	0.705
C ₁₄ H ₁₀	0.0375	-0.0170	0.1522	-0.0187	0.0272	0.0138	0.0242	0.0399
CoSO ₄ •7H ₂ O	0.158	-0.018	0.371	-0.047	0.060	0.016	0.058	0.101
FeSO ₄ •7H ₂ O	0.172	-0.019	0.360	-0.014	0.064	0.001	0.056	0.096
K ₂ C ₄ H ₄ O ₆	0.1330	0.0182	0.5540	0.0710	0.0870	0.0072	0.1040	0.0826
KAlSi ₃ O ₈	0.192	-0.148	1.215	-0.131	0.143	-0.015	0.238	0.361
KHC ₄ H ₄ O ₆	0.1173	0.0176	0.6816	0.0294	0.0961	-0.0044	0.1270	0.0841
Li ₂ SO ₄ •H ₂ O	0.0368	0.0571	0.5400	-0.0254	0.1400	-0.0054	0.1565	0.2770
(NaFe)Si ₂ O ₆	0.626	0.094	2.344	0.214	0.692	0.077	0.510	0.474
(NH ₂ CH ₂ CO-OH) ₃ •H ₂ SO ₄	0.2080	-0.0036	0.2630	-0.0500	0.0950	-0.0026	0.1110	0.0620
Na ₂ S ₂ O ₃	0.1713	0.0983	0.4590	-0.0678	0.0569	-0.0268	0.1070	0.0598
Y ₂ SiO ₅	—	—	0.835	±0.330	0.465	±0.0014	1.87	0.656

Hexagonal Crystals—Point Groups 6, -6, 622, 6mm, -62m, 6/mmm

Material	Temp. (K)	Elastic Constants (10^{11} N/m 2)					Ref.
		C ₁₁	C ₁₂	C ₁₃	C ₃₃	C ₄₄	
β -AgI	RT	0.293	0.213	0.196	0.354	0.0373	117
AlN	RT	3.45	1.25	1.20	3.95	1.18	117
Be ₃ Al ₂ Si ₆ O ₁₈	RT	2.800	0.990	0.670	2.480	0.658	12
BeO	RT	4.70	1.68	1.19	4.94	1.53	96
Ca ₅ (PO ₄) ₃ (OH,F,Cl)	RT	1.667	0.131	0.655	1.396	0.663	12
CdS	298	0.8431	0.5208	0.4567	0.9183	0.1458	98
CdSe	298	0.7046	0.4516	0.3930	0.8355	0.1317	68
GaN	RT	2.96	1.30	1.58	2.67	2.41	117
LiTiO ₃	RT	0.8124	0.3184	0.0925	0.529	0.1783	117
α -SiC	RT	5.02	0.95	056	5.65	1.69	117
TiB ₂	RT	6.90	4.10	3.20	4.40	2.50	107
ZnO	298	2.0970	1.2110	1.0510	2.1090	0.4247	110
ZnS	298	1.2420	0.6015	0.4554	1.4000	0.2864	96

References:

- Thomas, J. F., *Phys. Rev.*, 175, 955–962 (1968).
- Bolef, D. I. and M. Menes, *J. Appl. Phys.*, 31, 1426–1427 (1960).
- Garland, C. W. and C. F. Yarnell, *J. Chem. Phys.*, 44, 1112–1120 (1966).
- Garland, C. W. and R. Renard, *J. Chem. Phys.*, 44, 1130–1139 (1966).
- Gsänger, M., H. Egger and E. Lüscher, *Phys. Letters*, 27A, 695–696 (1968).
- Wong, C. and D. E. Schuele, *J. Phys. Chem. Solids*, 29, 1309–1330 (1968).
- Haussühl, S., *Phys. Stat. Sol.*, 3, 1072–1076 (1963).
- Wong, C. and D. E. Schuele, *J. Phys. Chem. Solids*, 28, 1225–1231 (1967).
- McSkimin, H. J. and D. G. Thomas, *J. Appl. Phys.*, 33, 56–59 (1962).
- Kollarits, F. J. and J. Trivisonno, *J. Phys. Chem. Solids*, 29, 2133–2139 (1968).
- Slagle, D. D. and H. A. McKinstry, *J. Appl. Phys.*, 38, 446–458 (1967).
- Hearmon, R. F. S., *Adv. Phys.*, 5, 323–382 (1956).
- Sumer, A. and J. F. Smith, *J. Appl. Phys.*, 34, 2691–2694 (1963).
- Alexandrov, K. S. et al., *Sov. Phys. Sol. State*, 10, 1316–1321 (1968).
- Epstein, S. G. and O. N. Carlson, *Acta Metal.*, 13, 487–491 (1965).
- McSkimin, H. J., et al., *J. Appl. Phys.*, 39, 4127–4128 (1968).
- McSkimin, H. J., et al., *J. Appl. Phys.*, 38, 2362–2364 (1967).
- Weil, R. and W. O. Groves, *J. Appl. Phys.*, 39, 4049–4051 (1968).
- Bateman, T. B., *J. Appl. Phys.*, 37, 2194–2195 (1966).
- Bogardus, E. H., *J. Appl. Phys.*, 36, 2504–2513 (1965).
- Golding, B., S. C. Moss and B. L. Averbach, *Phys. Rev.*, 158, 637–645 (1967).
- Bateman, T. B., H. J. McSkimin and J. M. Whelan, *J. Appl. Phys.*, 30, 544–545 (1959).
- Gerlich, D., *J. Appl. Phys.*, 35, 3062 (1964).
- Hickernell, F. S. and W. R. Gayton, *J. Appl. Phys.*, 37, 462 (1966).
- MacFarlane, R. E., et al., *Phys. Letters*, 20, 234–235 (1966).
- Leese, J. and A. E. Lord Jr., *J. Appl. Phys.*, 39, 3986–3988 (1968).
- Miller, R. A. and D. E. Schuele, *J. Phys. Chem. Solids*, 30, 589–600 (1969).
- Wasilik, J. H. and M. L. Wheat, *J. Appl. Phys.*, 36, 791–793 (1965).
- Haussühl, S., *Phys. Stat. Sol.*, 3, 1072–1076 (1963).
- Houston, B., et al., *J. Appl. Phys.*, 39, 3913–3916 (1968).

31. Trivisonno, J. and C. S. Smith, *Acta Metal.*, 9, 1064–1071 (1961).
32. Alexandrov, K. S. and T. V. Ryzhova, *Sov. Phys. Cryst.*, 6, 228–252 (1961).
33. Lewis, J. T., A. Lehoczky and C. V. Briscoe, *Phys. Rev.*, 161, 877–887 (1967).
34. Drabble, J. R. and R. E. B. Strathen, *Proc. Phys. Soc.*, 92, 1090–1095 (1967).
35. Oliver, D. W., *J. Appl. Phys.*, 40, 893 (1969).
36. Alper, T., and G. A. Saunders, *J. Phys. Chem. Solids*, 28, 1637–1642 (1967).
37. Dickinson, J. M. and P. E. Armstrong, *J. Appl. Phys.*, 38, 602–606 (1967).
38. Bolef, D. I., *J. Appl. Phys.*, 32, 100–105 (1961).
39. Rayne, J. A., *Phys. Rev.*, 112, 1125–1130 (1958).
40. MacFarlane, R. E., et al., *Phys. Letters*, 18, 91–92 (1965).
41. Smith, P. A. and C. S. Smith, *J. Phys. Chem. Solids*, 26, 279–289 (1965).
42. Norwood, M. H. and C. V. Briscoe, *Phys. Rev.*, 112, 45–48 (1958).
43. Simmons, G. and F. Birch, *J. Appl. Phys.*, 34, 2736–2738 (1963).
44. Gutman, E. J. and J. Trivisonno, *J. Phys. Chem. Sol.*, 28, 805–809 (1967).
45. Ghafelehbashi, M., et al., *J. Appl. Phys.*, 41, 652–666 (1970).
46. McSkimin, H. J. and P. Andreatch Jr., *J. Appl. Phys.*, 35, 2161–2165 (1964).
47. Neighbours, J. R. and G. A. Alers, *Phys. Rev.*, 111, 707–712 (1958).
48. Hidshaw, W., J. T. Lewis, and C. V. Briscoe, *Phys. Rev.*, 163, 876–881 (1967).
49. Daniels, W. B., *Phys. Rev.*, 119, 1246–1252 (1960).
50. Viswanathan, R., *J. Appl. Phys.*, 37, 884–886 (1966).
51. Miller, R. A. and C. S. Smith, *J. Phys. Chem. Sol.*, 25, 1279–1292 (1964).
52. Claytor, R. N. and B. J. Marshall, *Phys. Rev.*, 120, 332–334 (1960).
53. Schreiber, E., *J. Appl. Phys.*, 38, 2508–2511 (1967).
54. Gerlich, D., *Phys. Rev.*, 136, A1366–A1368 (1964).
55. Johnston, D. L., P. H. Thrasher and R. J. Kearney, *J. Appl. Phys.*, 41, 427–428 (1970).
56. Poindexter, E. and A. A. Giardini, *Phys. Rev.*, 110, 1069 (1958).
57. Soga, N., *J. Appl. Phys.*, 37, 3416–3420 (1966).
58. Bartlett, R. W. and C. W. Smith, *J. Appl. Phys.*, 38, 5428–5429 (1967).
59. Morse, G. E. and A. W. Lawson, *J. Phys. Chem. Sol.*, 28, 939–950 (1967).
60. Armstrong, P. E., O. N. Carlson and J. F. Smith, *J. Appl. Phys.*, 30, 36–41 (1959).
61. Macedo, P. M., W. Capps and J. B. Wachtman, *J. Am. Cer. Soc.*, 47, 651 (1964).
62. Beattie, A. G., *J. Appl. Phys.*, 40, 4818–4821 (1969).
63. Chang, R. and L. J. Graham, *J. Appl. Phys.*, 37, 3778–3783 (1966).
64. Lowrie, R. and A. M. Gonatas, *J. Appl. Phys.*, 38, 4505–4509 (1967).
65. Graham, L. J., H. Nadler and R. Chang, *J. Appl. Phys.*, 34, 1572–1573 (1963).
66. Wachtman, J. B. Jr., et al., *J. Nucl. Mat.*, 16, 39–41 (1965).
67. Bolef, D. I., *J. Appl. Phys.*, 32, 100–105 (1961).
68. Berlincourt, D., H. Jaffe and L. R. Shiozawa, *Phys. Rev.*, 129, 1009–1017 (1963).
69. Adhav, R. S. J. *Acoust. Soc. Am.*, 43, 835–838 (1968).
70. Berlincourt, D. and H. Jaffe, *Phys. Rev.*, 111, 143–148 (1958).
71. Huntington, H. B., in *Solid State Physics*, Vol. 7, Seitz, F., and Turnbull, D., Ed., pp. 213–285; Academic Press, New York 1958.
72. Cutler, H. R., J. J. Gibson and K. A. McCarthy, *Sol. State Comm.*, 6, 431–433 (1968).
73. Mason, W. P., *Piezoelectric Crystals and Their Application to Ultrasonics*, D. Van Nostrand Co., Inc., New York (1950).
74. Adhav, R. S., *J. Appl. Phys.*, 40, 2725–2727 (1969).
75. Manghnani, M. H., *J. Geophys. Res.*, 74, 4317–4328 (1969).
76. Uchida, N. and Y. Ohmachi, *J. Appl. Phys.*, 40, 4692–4695 (1969).
77. House, D. G. and E. Y. Vernon, *Br. J. Appl. Phys.*, 11, 254–259 (1960).
78. Ryzhova, T. V., et al., *Bull. Acad. Sci. USSR, Earth Phys. Ser.*, Engl. Transl., 2, 111 (1966).
79. Alton, W. J. and A. J. Barlow, *J. Appl. Phys.*, 38, 3817–3820 (1967).

80. Michard, F., et al., *C. R. Acad. Sci., Paris*, 265, 565–567 (1967).
81. Haussühl, S., *Acta Cryst.*, 18, 839–842 (1965).
82. Hearmon, R. F. S., *Rev. Mod. Phys.*, 18, 409–440 (1946).
83. Heseltine, J. C. W., D. W. Elliott and O. B. Wilson, *J. Chem. Phys.*, 40, 2584–2587 (1964).
84. Schwerdtner, W. M., et al., *Canad. J. Earth Sci.*, 2, 673–683 (1965).
85. Kumazawa, M. and O. L. Anderson, *J. Geophys. Res.*, 74, 5961–5972 (1969).
86. Alexandrov, K. S., et al., *Sov. Phys. Cryst.*, 7, 753–755 (1963).
87. Verma, R. K., *J. Geophys. Soc.*, 65, 757–766 (1960).
88. McSkimin, H. J. and E. S. Fisher, *J. Appl. Phys.*, 31, 1627–1639 (1960).
89. Alexandrov, K. S. and T. V. Ryzhova, *Bull. Acad. Sci. USSR, Geophys. Ser.*, English Transl., no.8, 871–875 (1961).
90. Afanaseva, G. K., et al, *Phys. Stat. Sol.*, 24, K61–K63 (1967).
91. Alexandrov, K. S., et al., *Sov. Phys. Cryst.*, 8, 589–591 (1964).
92. Alexandrov, K. S. and T. V Ryzhova, *Bull Acad. Sci. USSR, Geophys. Ser.*, English Transl., no.2, 129–131 (1962).
93. Alexandrov, K. S., et al., *Sov. Phys. Cryst.*, 8, 164–166 (1963).
94. Teslenko, V. F., et al., *Sov. Phys. Cryst.*, 10, 744–747 (1966).
95. Smith, J. F. and C. L. Arbogast, *J. Appl. Phys.*, 31, 99–102 (1960).
96. Cline, C. F., H. L. Dunegan and G. M. Henderson, *J. Appl. Phys.*, 38, 1944–1948 (1967).
97. Chang, Y. A. and L. Himmel, *J. Appl. Phys.*, 37, 3787–3790 (1966).
98. Gerlich, D., *J. Phys. Chem. Solids*, 28, 2575–2579 (1967).
99. McSkimin, H. J., *J. Appl. Phys.*, 26, 406–409 (1955).
100. Fisher, E. S. and D. Dever, *Trans. Met. Soc. AIME*, 239, 48–57 (1967).
101. Fisher, E. S. and D. Dever, *Proc. Conf. Rare Earth Res.*, 6th, Gatlinburg, TN, 522 (1967).
102. Fisher, E. S. and C. J. Renken, *Phys. Rev.*, 135, A482–A494 (1964).
103. Proctor, T. M. Jr., *J. Acoust. Soc. Am.*, 39, 972–977 (1966).
104. Chandrasekhar, B. S. and J. A. Rayne, *Phys. Rev.*, 124, 1011–1041 (1961).
105. Wazzan, A. R. and L. B. Robinson, *Phys. Rev.*, 155, 586–594 (1967).
106. Ferris, R. W., et al., *J. Appl. Phys.*, 34, 768–770 (1963).
107. Gilman, J. J. and B. W. Roberts, *J. Appl. Phys.*, 32, 1405 (1961).
108. Smith, J. F. and J. A. Gjevre, *J. Appl. Phys.*, 31, 645–647 (1960).
109. Alers, G. A. and J. R. Neighbours, *J. Phys. Chem. Solids*, 7, 58–64 (1908).
110. Bateman, T. B., *J. Appl. Phys.*, 33, 3309–3312 (1962).
111. Tefft, W. E., *J. Res. Natl. Bur. Stand.*, 70A, 277–280 (1966).
112. DeBretteville, Jr., A. et al., *Phys. Rev.*, 148, 575–579 (1966).
113. Dandekar, D. P. and A. L. Ruoff, *J. Appl. Phys.*, 39, 6004–6009 (1968).
114. Warner, A. W., M. Onoe and G. A. Coquin, *J. Acoust. Soc. Am.*, 42, 1223–1231 (1967).
115. McSkimin, H. J., P. Andreatch and R. N. Thurston, *J. Appl. Phys.*, 36, 1624–1632 (1965).
116. Mort, J., *J. Appl. Phys.*, 38, 3414–3415 (1967).
117. Topf, W. J., M. F. Thomas, and T. J Harris, Properties of crystals and glasses, *Handbook of Optics*, Vol. II (McGraw–Hill, New York, 1995), p. 33.57 and references cited therein.
118. DeShazer, L. G., S. C. Rand, , and B. A. Wechsler, Laser crystals, *Handbook of Laser Science and Technology, Vol. V: Optical Materials, Part 3* (CRC Press, Boca Raton, FL, 2000), p. 595 and references cited therein.
119. Wechsler, B. A. and D. S. Sumida, Laser crystals, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 2000), p. 595.
120. Cline, C. F., R. C. Morris, M. Dutoit, and P. J. Harget, *J. Mater. Sci.* 14, 941 (1979).

1.4.2 Elastic Moduli

The mechanical response of a material to an applied force is described by various moduli. Young's modulus E (extension in tension) and the modulus of rigidity or shear G are related to Poisson's ratio μ (ratio of lateral to longitudinal strain under unilateral stress) by $\mu = E/2G - 1$. The bulk modulus B (1/isothermal compressibility) is related to the above moduli by $B = E/3(1 - \mu)$.

Elastic Moduli

Material	Poisson's ratio	Young's E (GPa)	Rigidity G (GPa)	Bulk B (GPa)
Moduli				
Ag ₃ AsS ₃	0.38	28	10	37
AgBr	0.39	24.7	8.8	40.5
AgCl	0.41	22.9	8.1	44.0
AgGaS ₂	0.37	52	19	67
β -AgI	0.4	12	4.4	24
AlAs	0.27	108	42.4	77.2
AlN	0.26	294	117	202
Al ₂ O ₃	0.23	400	162	250
ALON	0.24	317	128	203
BaB ₂ O ₄	0.41	30	11	60.6
BaF ₂	0.31	65.8	25.1	57.6
BaTiO ₃	0.36	145	53	174
BeAl ₂ O ₄	—	469	—	—
BeO	0.23	395	162	240
Bi ₁₂ GeO ₂₀	0.28	82	32	63.3
Bi ₁₂ SiO ₂₀	0.28	84	33	63.1
BN	0.11	833	375	358
BP	0.19	324	136	172
C (diamond)	0.10	1100	500	460
CaCO ₃	0.31	83	32	73.2
CaF ₂	0.29	110	42.5	85.7
CaLa ₂ S ₄	0.25	96	38.4	64
CaMoO ₄	0.29	103	40	80
CaWO ₄	0.29	96	37	78
CdGeS ₂	0.32	74	28	70
CdS	0.38	42	15	59
CdSe	0.37	42	15.3	53
CdTe	0.35	8.4	14.2	42.9
CsBr	0.27	22	8.8	15.8
CsCl	0.27	25	10.0	18.2
CsI	0.26	18	7.3	12.6
CuCl	0.30	24.8	8.9	39.3
GaAs	0.24	116	46.6	75.0
GaN	0.25	294	118	195
GaP	0.24	140	56.5	89.3

Elastic Moduli—*continued*

Material	Poisson's ratio	Moduli		
		Young's E (GPa)	Rigidity G (GPa)	Bulk B (GPa)
Ge	0.20	132	54.8	75.0
InAs	0.30	74	28	61
InP	0.30	89	34	72.7
KBr	0.30	18	7.2	15.2
KCl	0.29	22	8.5	18.4
KF	0.28	41	16	31.8
KH ₂ PO ₄	0.26	38	15	28
KI	0.30	14	5.5	11.9
KNbO ₃	0.22	250	71	95
KTaO ₃	0.27	316	124	230
LaF ₃	0.32	120	46	100
LiF	0.22	110	45	65.0
LiI ₀ ₃	0.23	55	22.4	33.5
LiNbO ₃	0.25	170	68	112
LiSrAlF ₆	0.3	109	—	—
LiYF ₄	0.32	85	32	81
MgAl ₂ O ₄	0.26	276	109	198
MgF ₂	0.26	137	53.9	99.1
MgO	0.18	310	131	163
NaBr	0.26	29	11.6	19.9
NaCl	0.26	37	14.5	25.3
NaF	0.24	76	30.7	48.5
NaI	0.28	22	8.4	16.1
[NH ₄] ₂ CO	0.41	~9	~3	17
NH ₄ H ₂ PO ₄	0.32	29	11	27.9
PbF ₂	0.33	59.8	22.4	60.5
PbMoO ₄	0.35	66	24	72
PbS	0.28	70.2	27.5	52.8
PbSe	0.28	64.8	25.4	48.5
PbTe	0.26	56.9	22.6	39.8
Se	0.27	24	9	17
Si	0.22	162	66.2	97.7
α-SiC	0.16	455	197	221
β-SiC	0.17	447	191	224
β-SiC (CVD)	0.21	466	—	—
SiO ₂ , α-quartz	0.08	95	44	38
SrF ₂	0.29	89	34.6	71.3
SrMoO ₄	0.30	87	33	73
SrTiO ₃	0.23	283	115	174
Te	0.25	35	14	24
TeO ₂	0.33	45	17	46
TiO ₂	0.27	293	115	215

Elastic Moduli—continued

Material	Poisson's ratio	Moduli		
		Young's E (GPa)	Rigidity G (GPa)	Bulk B (GPa)
TlBr	0.32	24	8.9	22.4
Tl[Br,I] KRS-5	0.34	19.6	7.3	20.4
TlCl	0.33	25	9.3	23.8
Tl[Br,Cl], KRS-6	0.33	24	9.0	32.2
Y ₃ Al ₅ O ₁₂	0.24	280	113	180
Y ₃ Fe ₅ O ₁₂	0.29	200	—	—
Y ₂ O ₃	0.30	173	67	145
ZnO	0.35	127	47	144
α-ZnS	0.30	87	33	74
β-ZnS	0.32	82.5	31.2	76.6
β-ZnS (CVD)	0.29	74.5	—	—
ZnSe	0.30	75.4	29.1	61.8
ZnSe (CVD)	0.28	70.3		
ZnTe	0.30	61.1	23.5	51.0
ZrO ₂ ; 12%Y ₂ O ₃	0.31	233	88.6	205

The above table was adapted from Tropf, W. J., Thomas, M. F., and Harris, T. J., Properties of crystals and glasses, *Handbook of Optics*, Vol. II (McGraw-Hill, New York, 1995), p. 33.48.

1.4.3 Engineering Data

The following engineering properties can depend on the production method and exhibit sample-to-sample variations. Material strength may also depend on subsurface damage resulting from grinding and polishing. Therefore, the data should be considered only as a guide.

Material	Engineering Data			
	Flexure strength (MPa)	Fracture toughness (MPa m ^{1/2})	Volume compressibility (Tpa ⁻¹)	Ref.
AgCl	26			1
AgSb			57.1	4
Al ₂ O ₃	1200	3	1.36 c 1.22 a	1
AlN	225	3		1
Al ₂₃ O ₂₇ N ₅	310	1.4		1
α-AgI			41	4
BaB ₂ O ₄		1.5		1
BaF ₂	27			1
Be ₃ Al ₂ Si ₆ O ₁₈			6.65	2
BeO	275			1
C (diamond)	2940	2.0		1

Engineering Data—continued

Material	Flexure strength (MPa)	Fracture toughness (MPa m^{1/2})	Volume compressibility (TPa⁻¹)	Ref.
Ca ₅ (PO ₄) ₃ F			13.2	2
CaF ₂	90	0.5	11.64	1,2
CaLa ₂ S ₄	81	0.68		1
CaMoO ₄			12.5	2
CaWO ₄			13.3	2
CdS	28			1
CdSe	21			1
CdSiAs ₂ S ₄			4.3	4
CdTe	26			1
CsBr	8.4			1
CsI	5.6			1
GaAs	55		77.1	1,4
GaN	70			1
GaP	100	0.9	11.0	1,4
GaSbs			45.7	4
Gd ₂ (MoO ₄) ₃			27.2	2
Gd ₃ Ga ₅ O ₁₂			5.88	2
Gd ₃ Sc ₂ Ga ₃ O ₁₂		1.2		3
Ge	100	0.66		1
InAs			54.9	4
InP			73.5	4
InSb			44.2	4
KBr	11			1
KCl	10			1
KMgO ₃			14.4	2
LaB ₃ O ₆		1.9 (111) 0.38 (10-1)		
LaF ₃	33			1
LiB ₃ O ₅		2.0		
LiCaAlF ₆		0.18 c 0.37 ⊥ c		3
LiF	27		15.05	1,2
LiNbO ₃			8.8	2
LiSrAlF ₆		0.40 c		3
LiYF ₄	35			1
Lu ₃ Al ₅ O ₁₂		1.1		3
MgAl ₂ O ₄	170	1.5		1
MgF ₂	100		10.1	1
MgO	130	1.0	6.2	1
MnF ₂			4.3 a 2.0 ⊥ c	2

Engineering Data—continued

Material	Flexure strength (MPa)	Fracture toughness (MPa m^{1/2})	Volume compressibility (TPa⁻¹)	Ref.
NaCl	9.6			1
Si	130	0.95		1
β-SiC	250			1
β-SiC (CVD)		3.3		
Sr ₅ (PO ₄) ₃ F		0.51		3
Sr ₅ (VO ₄) ₃ F		0.36 c		3
Te	11			1
Tl[Br,Cl], KRS-6	21			1
Tl[Br,I] KRS-5	26			1
Y _{2.25} Yb _{0.75} Al ₅ O ₁₂		1.3		3
Y ₂ O ₃	150	0.7		1
Y ₂ SiO ₅		0.54 a		3
		0.70 b		3
		0.78 c		3
Y ₃ Al ₅ O ₁₂		1.0, 1.4		3
Y ₃ Al ₅ O ₁₂			5.34	2
Y ₃ Fe ₅ O ₁₂			6.15	2
Y ₃ Ga ₅ O ₁₂			5.73	2
α-ZnS	69			1
β-ZnS (CVD)	60	0.8		1
ZnSe	55	0.32		1
ZnSe (CVD)	52	≈ 1		
ZnTe	24			1
ZrO ₂ ; 12%Y ₂ O ₃	200	2.0		1

References:

1. Tropf, W. J., Thomas, M. F., and Harris, T. J., Properties of crystals and glasses, *Handbook of Optics*, Vol. II 2 (McGraw-Hill, New York, 1995), p. 33.48.
2. DeShazer, L. G., Rand, S. C., and Wechsler, B. A., Laser crystals, *Handbook of Laser Science and Technology, Vol. IV: Optical Materials, Part 3* (CRC Press, Boca Raton, FL, 1987), p. 595.
3. Wechsler, B. A. and Sumida, D. S., Laser crystals, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 595.
4. Berger, L. I. and Pamplin, B. R., Properties of semiconductors, *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12–87.

1.5 Thermal Properties

1.5.1 Melting Point, Heat Capacity, Thermal Expansion, and Thermal Conductivity

Values for the heat capacity and the thermal expansion coefficient are those at or near room temperature; thermal conductivity values are for the temperatures T indicated.

Material	Thermal Properties					
	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10^{-6} K)	Thermal conductivity (W/ m K)	T (K)	Ref.
Ag ₃ AsS ₃	763					1
AgBr	705	0.2790	33.8	1.11	250	2
				0.93	300	2
				0.57	500	2
AgCl	728	0.3544	32.4	1.25	250	2
				1.12	295	1
				1.1	373	4
AgGaS ₂	1269	0.40	28.5 a	1.5	300	1
			-18.7 c			1
AgGaSe ₂	1129	0.30	35.5 a	1.1	300	1
			-15.0 c			1
AgGaTe ₂	990			1.0	300	3
β-AgI	423p	0.242		0.4	300	2
Al ₂ O ₃	2319	0.777	6.65 a	58	250	2
			7.15 c	46	300	2
				24.2	500	2
Al ₆ Si ₂ O ₁₃	2190	0.75				2
AlAs	2013	0.452	3.5			1
			3.1	84	300	3
AlN	3273	0.796	5.27 a	500	250	2
			4.15 c	320	300	2
				150	500	2
ALON	2323	0.830	5.66	12.6	300	2
				7.0	500	2
AlP	2820			92	300	3
AlPO ₄	>1730		2.9	~6	300	1
AlSb	1330		4.2	60	300	3

Thermal Properties—*continued*

Material	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10⁻⁶ K)	Thermal conductivity (W/m K)	T (K)	Ref.
BaB ₂ O ₄	1200p	0.49	4 a	1.2 a	300	2
	1370		34 c	1.6 c	300	2
BaF ₂	1550	0.4474	18.4	7.5	250	2
				12	300	2
				10.5	370	4
BaF ₂ -CaF ₂	1330	0.13	21.0			1
Ba ₃ Lu(BO ₃) ₃	1540					
BaTiO ₃	278p	0.439	16.8 a	6	300	2
	406p		−9.07 c			2
	1870					1
BaY ₂ F ₈	1230		17 a	6	300	5
			18.7 b			5
			19.4 c			5
Ba ₂ NaNb ₅ O ₁₂	1710	28.5 a	10.4 a,b			5
		−18.7 c	11.4 c			5
BeAl ₂ O ₄	2140	0.830	6.3 a	23	300	5
			6.0 b			5
			6.5 c			5
Be ₂ SiO ₄		0.84		3.3	300	2
Be ₃ Al ₂ Si ₆ O ₁₈	1730	0.84	2.1 a	5	300	1
			2.7 c			1
BeO	2373p	1.028	5.64 a	420	250	2
	2725		7.47 c	350	300	2
				200	500	2
BiB ₃ O ₆		0.5 (330 K)	48.1 (x) 44 (y) −26.9 (z)			
Bi ₄ Ge ₃ O ₁₂	1320		7			1
Bi ₁₂ GeO ₂₀	1200		16.8			1
Bi ₂ Te ₃	853			2.8	204	4
				3.6	303	4
				4.6	370	4
BN	1100p	0.513	3.5	760	300	2
	3240			36.2	1047	1,4
BP	1400d	0.71	3.65	460	250	2

Thermal Properties—*continued*

Material	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10^{-6} K)	Thermal conductivity (W/m K)	T (K)	Ref.
BP				360	300	2
C (diamond)	1770p	0.5169	1.25	2800 2200	250 300	2
C (diamond)				1300	500	2
Ca(NbO ₃) ₂	1830					5
Ca ₂ Al ₂ SiO ₇	1860		11.4 a	3 c 4.4 ⊥ c	300 300	6 6
Ca ₃ Gd ₂ (BO ₃) ₃	1680					
Ca ₃ Y ₂ (BO ₃) ₃	1630					
Ca ₅ (PO ₄) ₃ F	1920	0.745	9.4 a 10 c			5 5
CaCO ₃ (calcite)	323p 1610	0.8820	-3.7 a 25.1 c	5.1 a 6.2 c 4.5 a 5.4 c 3.4 a 4.2 c	250 250 300 300 500 500	2 2 2 2 2 2
CaF ₂	1424p 1630	0.9113	18.9	39.0 13 9.7 5.5	83 250 300 500	5 2 1,2 2
CaLa ₂ S ₄	2083	0.36	14.6	1.7 1.5	300 500	2 2
CaMoO ₄	1750	0.690	19 a 25 c	3.95 a 3.82 c	300 300	5 5
CaO	2890	0.75		18	450	1
CaTiO ₃	2250					7
CaWO ₄	1855	0.396	6.35 a 12.38 c	6 11.3	300 422	1,2 2,4
CaY ₄ (SiO ₄)O	2320		7.1 a 5.1 c			5 5
CdCl ₂	781					1
CdF ₂	1370		27			1
CdGeS ₂	900p 943		8.4 a 0.25 c			2 2

Thermal Properties—*continued*

Material	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10^{-6} K)	Thermal conductivity (W/m K)	T (K)	Ref.
CdI ₂	760					1
CdS	1560	0.3814	4.6 a 2.5 c	27 13	300 500	2 2
CdSe	1580	0.272	4.9 a 2.9 c	9	300	1,2 2
CdTe	1320	0.210	5.0	8.2 6.3	250 300	2 2
CsBr	908	0.2432	47.2	1.2 0.85 0.77	223 300 373	4 2 4
CsCl	918	0.3116	45.0	0.84	360	3
CsF	955	0.33	32	4.2	300	2
CsI	898	0.2032	48.6	1.4 1.05 0.95	223 300 373	4 2 4
CsLiB ₆ O ₁₀	1120					
Cu ₂ GeS ₃	1210	0.51	7.2	1.2	300	3
Cu ₂ GeSe ₃	1030	0.34	8.4	2.4	300	3
Cu ₂ SnS ₃	1110	0.44	7.8	2.8	300	3
Cu ₂ SnSe ₃	960	0.31	8.9	3.5	300	3
CuBr	777		19			1
CuCl	700	0.490	14.6	1.0 0.8 0.5	250 300 500	2 2 2
CuF	1181					3
CuGaS ₂	1553	0.452	11.2 a 6.9 c			2 2
CuGase ₂	1970		5.4	4.2	300	3
CuGaTe ₂	2400		6.9	2.7	300	3
CuInSe ₂	1600		6.6	3.7	300	3
CuInTe ₂	1660		7.1	4.9	300	3
CuSnTe ₃	680			14.4	300	3
Ga ₂ O ₃	2170	0.46				1

Thermal Properties—*continued*

Material	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10^{-6} K)	Thermal conductivity (W/m K)	T (K)	Ref.
Ga ₂ Se ₃	1020		8.9	50	300	3
Ga ₂ Te ₃	1063			47	300	3
GaAs	1511	0.345	5.0	65	250	2
				54	300	2
				27	500	2
α -GaN	1160d	0.49	3.17 a	130 c	300	2
	2370		5.59 c			2
GaP	1740	0.435	5.3	120	250	2
				100	300	2
				45	500	2
GaS	1240					7
GaSe	1235					7
GaSb	720	0.079	6.9	44	300	1,2
Gd ₂ (MoO ₄) ₃	1410	0.42				5
Gd ₃ Ga ₅ O ₁₂	2100			60	70	5
				9.0	300	1
Gd ₃ Sc ₂ Al ₃ O ₁₂	2110	0.424	6.9	5.6	300	6
Gd ₃ Sc ₂ Ga ₃ O ₁₂	2130	0.4023	7.32	6.1	300	6
Ge	1211	0.3230	5.7	74.9	250	2
				59.9	300	2
				33.8	500	2
GeO ₂	1360	0.54	4.5			1
HgI ₂	532					7
Hg ₂ I ₂	563					7
Gd ₂ (MoO ₄) ₃	1410	0.42				5
Gd ₃ Ga ₅ O ₁₂	2100			60	70	5
				9.0	300	1
Gd ₃ Sc ₂ Al ₃ O ₁₂	2110	0.424	6.9	5.6	300	6
Gd ₃ Sc ₂ Ga ₃ O ₁₂	2130	0.4023	7.32	6.1	300	6
Ge	1211	0.3230	5.7	74.9	250	2
				59.9	300	2
				33.8	500	2
GeO ₂	1360	0.54	4.5			1

Thermal Properties—*continued*

Material	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10^{-6} K)	Thermal conductivity (W/m K)	T (K)	Ref.
HgI ₂	532					7
Hg ₂ I ₂	563					7
HgInSe ₂	1053			3.0	300	3
HgInTe ₂	1053			3.0	300	3
HgS	857s	0.21				1
HgSe	Subl.		4.8	5.5	110	1
HgTe	943		4.8	12	100	1
InAs	1216	0.2518	4.4	50	250	2
				27.3	300	2
				15	500	2
α -InN	1373	0.32	2.9–3.8	55.6	300	3
InP	1345	0.3117	4.5	90	250	2
				68	300	2
				32	500	2
InSb	798	0.144	4.7	16	300	3
KAl ₃ Si ₃ O ₁₀ (OH) ₂	1473–1573	0.87	27	0.25–0.59	293	8
KBr	1007	0.4400	38.5	5.5	250	2
				4.8	300	2
				2.4	500	2
KCl	104	0.6936	36.5	8.5	250	2
				6.7	300	2
				3.8	500	2
KF	1131	0.8659	31.4	8.3	300	2
KH ₂ PO ₄	123p	0.88	22.0 a	2.0	250	2
	450p		39.2 c	2.1	300	2
	526					2
KI	954	0.3192	40.3	2.1	300	2
KNbO ₃	223p		37			2
	498p					2
KTaO ₃				0.2	250	2
KTaO ₃				0.17	300	2
KTiOPO ₄	1210p	0.728	11 a	2.0 a	300	2
	1423		9 b	3.0 b	300	2
			0.6 c	3.3 c	300	2

Thermal Properties—*continued*

Material	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10^{-6} K)	Thermal conductivity (W/m K)	T (K)	Ref.
K ₂ NaAlF ₆	1210					6
La ₂ B ₆ O ₁₀	1107p					2
La ₂ Be ₂ O ₅	1630		7–7.9 \perp 9.50 \parallel c	4.7	300	1
LaAlO ₃	2350		10			1
LaB ₃ O ₆	1420					
LaF ₃	1700	0.508	15.8 \parallel a 11.0 \parallel c	5.4 5.1	250 300	2
LaCl ₃	1130	0.422				5
La ₂ O ₂ S			6 \parallel c 3 \parallel a			5
LiBr	823					1
LiCaAlF ₆	1100	0.935	3.6 \parallel c 22 \parallel c	5.14 \parallel c 4.58 \perp c	300 300	6
LiCl	878	1.2	44			1
LiF	1115	1.6200	34.4	19 14 7.5	250 300 500	2
LiGdF ₄	1010					
LiI	720		58			2
LiIO ₃	520p 693		28 \parallel a 48 \parallel c			2
LiNbO ₃	1523	0.63	14.8 \parallel a 4.1 \parallel c	5.6	300	2
LiSrAlF ₆	1065		–10.0 \parallel c 18.8 \parallel c	3.09 \parallel c		6
LiTaO ₃	1932	0.42	4.1 \parallel c 16.1 \parallel c			6
LiYF ₄	1092	0.79	13.3 \parallel a	6.3	300	2
LiYF ₄			8.3 \parallel c			2
Lu ₃ Al ₅ O ₁₂	2260		8.8	31	300	6
MgAl ₂ O ₄	2408	0.8191	6.97	30 25	250 300	2

Thermal Properties—*continued*

Material	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10^{-6} K)	Thermal conductivity (W/m K)	T (K)	Ref.
Mg ₂ SiO ₄	2160	0.74	8.7 a			5
			15.4 b			5
			13.3 c			5
MgF ₂	1536	1.0236	9.4 a	30 a	300	2
			13.6 c	21 c	300	2
MgO	3073	0.9235	10.6	73	250	2
				59	300	2
				32	500	2
MnF ₂	1130	0.75	6.1			1
MnO	2112	0.67	13			1
Na ₃ AlF ₆	1000					1
NaBr	1028	0.5046	41.8	5.6	300	2
NaCl	1074	0.8699	41.1	8	250	2
				6.5	300	2
				4	500	2
NaF	1266	1.1239	33.5	22	250	2
				17	500	2
NaI	934	0.3502	44.7	4.7	500	2
NaNO ₃	580	1.05	11 a			1
			12 c			1
[NH ₄] ₂ CO	408	1.551				1
NH ₄ H ₂ PO ₄	148p	1.26	27.2 a	1.26 a	300	2
			10.7 c	0.71 c	300	1,2
PbCl ₂	774	0.27	31			1
PbF ₂	422p 1094	0.3029	29.0	28	300	2
						1
PbI ₂	685 1145d	0.27	31			7
PbMoO ₄	1338	0.326	8.7 a			2
PbMoO ₄			20.3 c			2
PbO (massicot)	1160	2.0				1
PbS	1390	0.209	19.0	2.5	300	2
PbSe	1338	0.175	19.4	2	250	2
				1.7	300	2

Thermal Properties—*continued*

Material	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10^{-6} K)	Thermal conductivity (W/m K)	T (K)	Ref.
PbSe				1	500	2
PbTe	1190	0.151	19.8	2.5	250	2
				2.3	300	2
				1.8	500	2
PbTiO ₃	763p			4	300	2
				2.8	500	2
RbBr	966	0.31		12.2	105	1
RbCl	991	0.42	36	7.6	124	1
RbI	920	0.24	39	9.9	84	1
Se	490	0.3212	69.0 a	1.5 a	250	2
			-0.3 c	5.1 c	250	2
				1.3 a	300	2
				4.5 c	300	2
Si	1680	0.7139	2.62	191	250	2
				140	300	2
				73.6	500	2
Si ₃ N ₄	>2300		1.1 a	33	300	1
			2.1 c			1
SiO ₂ (α -quartz)	845p	0.7400	12.38 a	7.5 a	250	2
			6.88 c	12.7 c	250	2
				6.2 a	300	2
				10.4 c	300	2
				3.9 a	500	2
				6.0 c	500	2
α -SiC	3110	0.690		450 a	300	2
β -SiC	3103d	0.670	2.77	490	300	2
SrF ₂	1710	0.6200	18.1	11	250	2
				8.3	300	2
SrGaO ₄	1870					
SrGdGa ₃ O ₇	1870					6
SrLaAlO ₄	1920					
SrMoO ₄	1763	0.619		4.0 a	300	2
				4.2 c	300	2
SrTiO ₃	110p	0.536	8.3	12.5	250	2
				11.2	300	2
Sr ₃ Y(BO ₃) ₃	1670					

Thermal Properties—*continued*

Material	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10^{-6} K)	Thermal conductivity (W/m K)	T (K)	Ref.
Sr ₃ Y ₄ (SiO ₄) ₃ O	2270					
Sr ₅ (PO ₄) ₃ F	2040	0.50		2.0	300	6
Sr ₅ (VO ₄) ₃ F	1920	0.513	7.3 a 10.8 ⊥ c			6
						6
Ta ₂ O ₅	2140					1
Te	621p 723	0.202	27.5 a −1.6 c	2.5 a 4.9 c 2.1 a 3.9 c 1.5 a 2.5 c	250 250 300 300 500 500	2 2 2 2 2 2
TeO ₂	1006	0.41	15.0 a 4.9 c	3	295	1,2 2
ThO ₂	3600	0.24	7.8	15	300	1
TiO ₂ rutile	2128	0.6910	6.86 a 8.97 c	8.3 a 11.8 c 7.4 a 10.4 c 5.5 a 8.0 c	250 250 300 300 500 500	2 2 2 2 2 2
Tl[Br,Cl]	697	0.201	51	0.50	300	2
Tl[Br,I]	687	0.16	58	0.32	300	2
Tl ₃ AsSe ₃	583	0.19	28 a 18 c	0.35	300	2 2
TlBr	740	0.1778	51	0.53	300	2
TlCl	703	0.2198	52.7	0.74	300	2
Y ₂ O ₃	2650	0.4567	6.56	13.5	300	2
YAlO ₃	2140	0.42	4.3–9.5 ⊥ c 11 c	11	323	1 1
YCa ₄ O(BO ₃) ₃			7.38 (ave)	2.60 a 2.33 b 3.01 c	300 300 300	
YVO ₄	~2100		11.4 a 4.4 ⊥ c	5.1 a 5.2 c	300 300	1,6 1,6
Y ₃ Al ₅ O ₁₂	2220	0.625	7.7	14.5 13.4	226 300	6 1,2

Thermal Properties—continued

Material	Melting point (K)	Heat capacity (J/g K)	Thermal expansion (10^{-6} K)	Thermal conductivity (W/m K)	T (K)	Ref.
				9.5	322	6
Y ₃ Fe ₅ O ₁₂	1830		10.4	41.0	70	5
				7.4	300	5
Y ₃ Ga ₅ O ₁₂	2100			39	70	5
				9.0	300	5
Y ₃ Sc ₂ Al ₃ O ₁₂	2170	0.57	6.5	11	300	6
Y ₃ Sc ₂ Ga ₃ O ₁₂	2180	0.534	8.1	7.3	300	6
ZnCl ₂	563	0.525		0.313	562.9	8
ZnF ₂	1140	0.63	9.8			1
ZnGeAs ₂	1150			11	300	3
ZnGeP ₂	1225p 1300		7.8 a	18	300	3
			5.0 c			3
ZnO	2248	0.495	6.5 a	30	300	2
			3.7 c	15	500	2
α -ZnS	2100	0.4723	6.54 a			2
			4.59 c			2
β -ZnS	1293p	0.4732	6.8	16.7	300	2
ZnSe	1790	0.339	7.1	13	300	2
ZnSnAs ₂	1048			15	300	3
ZnSnSb ₂	870			7.6	300	3
ZnTe	1510	0.218	8.4	10	300	1
ZrO ₂	~3000	0.42	8.8	10.5	260	1
ZrO ₂ :	3110	0.46	10.2	1.8	300	2
12%Y ₂ O ₃				1.9	500	2
ZrSiO ₄	2820	2.7		6.3	300	1

p – phase change, d – decomposes

References:

1. Ballard, S. S. and Browder, J. S., Thermal properties, *Handbook of Laser Science and Technology, Vol. IV, Optical Materials, Part 2* (CRC Press, Boca Raton, FL, 1986), p. 49.
2. Tropf, W. J., Thomas, M. F., and Harris, T. J., Properties of crystals and glasses, *Handbook of Optics, Vol. 2* (McGraw-Hill, New York, 1995), p. 33.51.
3. Berger, L. I. and Pamplin, B. R., Properties of semiconductors, *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12-87.
4. Powell, R. L. and Childs, G. E., *American Institute of Physics Handbook*, 3rd Edition, Gray, D. E., Ed. (McGraw-Hill, New York, 1972).

5. DeShazer, L. G., Rand, S. C., and Wechsler, B. A., Laser crystals, *Handbook of Laser Science and Technology, Vol. V: Optical Materials, Part 3* (CRC Press, Boca Raton, FL, 2000), p. 595.
6. Wechsler, B. A. and Sumida, D. S., Laser crystals, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 2000), p. 595.
7. Browder, J. S., Ballard, S. S., and Klocek, P., Physical property comparisons of infrared optical materials, *Handbook of Infrared Optical Materials* (Marcel Dekker, New York, 1991).

1.5.2 Temperature Dependence of Heat Capacity for Selected Solids

Temperature dependence of the molar heat capacity at constant pressure for representative crystalline solids and semiconductors in the range 200 to 600 K.

Molar Heat Capacity C_p in J/mol K

Name	200 K	250 K	300 K	400 K	500 K	600 K
Al ₂ O ₃	51.12	67.05	79.45	88.91	106.17	112.55
CaCO ₃	66.50	75.66	83.82	91.51	104.52	109.86
CaO	33.64	38.59	42.18	45.07	49.33	50.72
CsCl	50.13	51.34	52.48	53.58	56.90	59.10
Cu ₂ O	34.80	—	42.41	44.95	49.19	50.83
CuSO ₄	77.01	89.25	99.25	107.65	127.19	136.31
Ge	—	—	23.25	23.85	24.96	25.45
KCl	48.44	50.10	51.37	52.31	54.71	56.35
LiCl	43.35	46.08	48.10	49.66	53.34	55.59
MgO	—	—	37.38	40.59	45.56	47.30
NaCl	46.89	48.85	50.21	51.25	53.96	55.81
Si	15.64	18.22	20.04	21.28	23.33	24.15
SiO ₂	32.64	39.21	44.77	49.47	59.64	64.42

References:

- Chase, M. W., et al., *JANAF Thermochemical Tables, 3rd ed.*, *J. Phys. Chem. Ref. Data*, 14, (1985).
 Garvin, D., Parker, V. B., and White, H. J., *CODATA Thermodynamic Tables* (Hemisphere Press, New York, 1987).
DIPPR Database of Pure Compound Properties, Design Institute for Physical Properties Data, (American Institute of Chemical Engineers, New York, 1987).

1.5.3 Debye Temperature

References:

1. Tropf, W. J., Thomas, M. F., and Harris, T. J., Properties of crystals and glasses, *Handbook of Optics*, Vol. II (McGraw-Hill, New York, 1995), p. 33.51.
2. *Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12-87.

Debye			Debye		
Material	temperature (K)	Ref.	Material	temperature (K)	Ref.
AgBr	145	1	InSb	144	2
AgCl	162	1	KBr	174	1
AgGaS ₂	255	1	KCl	235	1
AgGaSe ₂	156	1	KF	336	1
AgGaTe ₂	212	2	KI	132	1
β -AgI	116	1	KTaO ₃	311	1
Al ₂ O ₃	1030	1	LaF ₃	392	1
AlAs	417	2	LiF	735	1
AlN	950	1	LiNbO ₃	560	1
AlP	588	2	MgAl ₂ O ₄	850	1
AlSb	292	2	MgF ₂	535	1
BaF ₂	283	1	MgO	950	1
BeO	1280	1	NaBr	225	1
BN	1900	1	NaCl	321	1
BP	985	1	NaF	492	1
C (diamond)	2240	1	NaI	164	1
CaF ₂	510	1	PbF ₂	225	1
CdGeS ₂	253	1	PbS	227	1
CdS	215	1	PbSe	138	1
CdSe	181	1	PbTe	125	1
CdSiP ₂	282	2	Se	151	1
CdSnP ₂	195	2	Si	645	1
CdTe	160	1	β -SiC	1000	1
CsBr	145	1	SiO ₂ , α -quartz	271	1
CsCl	175	1	SrF ₂	378	1
CsI	124	1	Te	152	1
Cu ₂ GeS ₃	254	2	TiO ₂	760	1
Cu ₂ GeSe ₃	168	2	Tl[Br,Cl], KRS-6	120	1
Cu ₂ SnS ₃	214	2	Tl[Br,I] KRS-5	110	1
Cu ₂ SnSe ₃	148	2	TlBr	116	1
Cu ₃ AsSe ₄	169	2	TlCl	126	1
Cu ₃ SbSe ₄	212	2	Y ₂ O ₃	465	1
CuCl	179	1	Y ₃ Al ₅ O ₁₂	754	1
CuGaS ₂	356	1	ZnGeAs ₂	271	2
CuInTe ₂	195	2	ZnGeP ₂	428	1
GaAs	344	1	ZnO	416	1
GaP	460	1	α -ZnS	351	1
GaSb	320	2	β -ZnS	340	1
Ge	380	1	ZnSe	270	1
HgTe	242	2	ZnTe	225	1
InP	321	2	ZrO ₂ :12%Y ₂ O ₃	563	1
InAs	249	2			

1.6 Magneto-optic Properties

1.6.1 Diamagnetic Materials

Verdet Constants V of Diamagnetic Crystals (room temperature)*

Crystal	Wavelength (nm)	V (rad/(m T))	CTE α ($10^{-6}/K$)	$(1/V)dVdT + \alpha$ ($10^{-4}/K$)	Ref.
AgBr	633	26.8			1
AgCl	633	22.8	30	3.2	1
Al ₂ O ₃	546	4.0			3
	589	3.5			3
BaF ₂	633	3.75	19	-0.2	1
Ba(NO ₃) ₂	633	2.9	17.5	0.7	1
BaTaO ₃ (403 K)	427	276			16
	496	111			16
	620	52.4			16
	826	21.0			16
BaTiO ₃	620	-51.0			3
Bi ₄ Ge ₃ O ₁₂	442	84.1			4
	633	30.1		2.0	2
	633	28.8			4
	1064	7.6			4
	1064	7.5			4
Bi ₁₂ GeO ₂₀	633	60.3			1
C (diamond)	589	6.8		1.4	5
	633	5.81	0.87		1
CaCO ₃	589	5.6		0	6
CaF ₂	589	5.6			4
	633	2.49	19	0.9	1
CsBr	633	10.8	47	0.8	1
CsCl	633	8.3	46	0.7	1
CsCN	633	5.51		3	1
CsF	633	4.71	33	0.3	1
CsH ₂ AsO ₄	633	6.49			7
CsI	633	17.4	49	2.5	1
CsNO ₂	633	4.24			1
CuCl	546	58.1			8
	633	31.9	30	3.0	1
Cu ₂ O	633	147	0	5.2	1
GaP	633	154	5.81	3.3	1
GaSe	633	22			9

Verdet Constants of Diamagnetic Crystals—continued

Crystal	Wavelength (nm)	V (rad/(m T))	CTE α (10⁻⁶/K)	(1/V)dVdT + α (10⁻⁴/K)	Ref.
Gd ₃ Al ₅ O ₁₂	633	13.3	3.35	-2.2	1
Hg ₃ Te ₂ Cl ₂	633	83			1
KAl(SO ₄) ₂ •12 H ₂ O	589	3.6			13
KBr	546	14.5			10
	589	12.4			10
	633	10.1			1
KCl	633	6.68	38.4	1.0	1
KCN	633	3.89	36.2	2.1	1
KH ₂ PO ₄	633	3.72	49	0.5	7
KH ₂ AsO ₄	633	69.3			7
KI	546	24.1			10
	589	20.4			10
	633	17.5		2.2	1
KTaO ₃	352	128			13
	413	55			13
	496	28			13
	620	-14	43		3
	826	6.4			13
LaF ₃	325	16			4
(H c)	442	8.1			4
	633	3.5			4
	1064	1.8			4
LiBaF ₃	633	3.72	27	0.7	1
LiBr	633	14.2	38	2	1
LiCl	633	9.3	35	1.3	1
LiF	633	2.33	25	3.0	1
LiH	633	24.6	32	1.7	1
MgAl ₂ O ₄	589	6.1			14
	633	7.6	8.82	0.9	1
MgO	633	9.2	13	1.7	1
NaBr	546	18.1			13
	633	13.2		1.8	1
NaCl	546	11.9			10
	589	10.0			10
	633	8.5	39.8	1.2	1
NaClO ₃	546	3.1			13
	589	2.4			13
NaI	633	22.5	43	1.9	1
NH ₄	633	12.6	53	2	1
NH ₄ Al(SO ₄) ₂ •12 H ₂ O	589	3.7			13
NH ₄ Br	589	14.7			13
	633	8.9	48	0.9	1

Verdet Constants V of Diamagnetic Crystals—continued

Crystal	Wavelength (nm)	V (rad/(m T))	CTE α (10⁻⁶/K)	(1/V)dVdT + α (10⁻⁴/K)	Ref.
NH ₄ Cl	546	11.9			13
	589	10.5			13
	633	6.60			7
NH ₄ H ₂ AsO ₄	633	69.3			15
NH ₄ H ₂ PO ₄	633	40.2			15
NH ₄ I	633	18.3	37	3.0	1
NiSO ₄ ·H ₂ O	546	7.4			14
	589	6.4			14
RbH ₂ PO ₄	633	3.72			7
RbH ₂ AsO ₄	633	6.17			7
SiO ₂	546	5.6			11
	589	4.9			11
Sm ₃ Ga ₅ O ₁₂	633	11.8	6.39	1.24	1
SrTiO ₃	413	227			16
	496	90.2			16
	633	-49.0	9.4	-1.8	1
	826	-19.2			3
TiO ₂	620	-45			3
Y ₃ Ga ₅ O ₁₂	633	11.7	5	1.23	1
ZnS	546	83.4			5
	589	65.8			5
	633	52.8		10.0	1
	476	436			12
ZnSe	496	302			12
	514	244			12
	587	154			12
	633	118			12
ZnTe	633	188		3.7	1

* The above table was adapted from Deeter, M. N., Day, G. W., and Rose, A. H., Magnetooptic materials: crystals and glasses, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 367, with additions.

References:

1. Haussühl, S., and Effgen, W., Faraday effect in cubic crystals, *Z. Kristallogr.*, 183, 153 (1988).
2. Baer, W. S., Intraband Faraday rotation in some perovskite oxides, *J. Phys. Chem. Solids*, 28, 677 (1977).
3. Ramaseshan, S., Faraday effect and birefringence, II—Corundum, *Proc. Indian Acad. Sci. A*, 34, 97 (1951).
4. Weber, M. J., Faraday rotator materials for laser systems, *Proc. Soc. Photo Opt. Instrum. Eng.*, 681, 75 (1986), and Weber, M. J., *Faraday Rotator Materials*, Lawrence Livermore Laboratory Report M-103 (1982).
5. Ramaseshan, S., The Faraday effect in diamond, *Proc. Indian Acad. Sci. A*, 24, 104 (1946).
6. Chauvin, J. *Physique*, 9, 5, 1890.

7. Munin, E., and Villaverde, A. B., Magneto-optical rotatory dispersion of some non-linear crystals, *J. Phys. Condens. Matter*, 3, 5099 (1991).
8. Gassmann, G., Negative Faraday effect independent of temperature, *Ann. Phys. (Leipzig)*, 35, 638 (1939).
9. Villaverde, A.B., and Donnati, D. A., GaSe Faraday rotation near the absorption edge, *J. Chem Phys.*, 72, 5341 (1980).
10. Ramaseshan, S., The Faraday effect and magneto-optic anomaly of some cubic crystals, *Proc. Ind. Acad. Sci. A*, 28, 360 (1948).
11. Ramaseshan, S., Determination of the magneto-optic anomaly of some glasses, *Proc. Ind. Acad. Sci. A*, 24, 426 (1946).
12. Wunderlich, J. A., and DeShazer, L. G., Visible optical isolator using ZnSe, *Appl. Opt.*, 16, 1584 (1977).
13. Ramaseshan, S., *Proc. Indian Acad. Sci.*, 28, 360 (1948).
14. O'Connor, Beck, and Underwood, *Phys. Rev.*, 60, 443 (1941).
15. Koralewski, M. *Phys. Status. Solidi A*, 65, K49 (1981).
16. Baer, W. S., *J. Chem. Solids* 28, 677 (1977).

1.6.2 Paramagnetic Materials

Verdet Constants for Representative Paramagnetic Crystals*

Crystal	Wavelength λ (nm)	Refractive index n	V (rad/(m T))	Ref.
CaF ₂ :Ce ³⁺ (30%)	325	1.516	-278	1
	442	1.502	-86.4	1
	633	1.494	-32.3	1
	1064	1.489	-10.2	1
CaF ₂ :Pr ³⁺ (5%)	266	1.471	-50.1	1
	325	1.461	-23.8	1
	442	1.451		1
	633	1.445	-4.9	1
	1064	1.441	-1.31	1
CeF ₃	442	1.613	-306	1
	633	1.598	-118	1
	1064		-33	1
EuF ₂	450		-1310	1
	500		-757	2
	550		-466	2
	600		-320	2
	633	1.544	-262	1
	650		-233	2
	1064	1.518	-55.3	1
LiTbF ₄	325	1.493	-553	3
	442	1.481	-285	3
	633	1.473	-128	3
	1064	1.469	-38	3
NdF ₃	442	1.60	-161	1
	633	1.59	-60.8	1
	1064	1.58	-28.2	1

Verdet Constants for Representative Paramagnetic Crystals—continued

Crystal	Wavelength λ (nm)	Refractive index n	V (rad/(m T))	Ref.
KTb ₃ F ₁₀	325	1.531	-633	3
	442	1.518	-272	3
	633	1.510	-112	3
	1064	1.505	-33.2	3
Tb ₃ Ga ₅ O ₁₂	500		-278	4
	570		-169	4
	633	1.976	-134	1
	830		-61	4
	1064	1.954	-35	1

* The above table was adapted from Deeter, M. N., Day, G. W., and Rose, A. H., *Magneto-optic materials: crystals and glasses, Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 367, with additions.

References:

1. Weber, M. J., Faraday rotator materials for laser systems, *Proc. Soc. Photo Opt. Instrum. Eng.*, 681, 75 (1986); Weber, M. J., *Faraday Rotator Materials*, Lawrence Livermore Laboratory Report M-103 (1982).
2. Suits, J. C., Argyle, B. E., and Freiser, M. J., Magneto-optical properties of materials containing divalent europium, *J. Appl. Phys.*, 37, 1391 (1966).
3. Weber, M. J., Morgret, R. Leung, S. Y., Griffin, J. A., Gabbe, D., and Linz, A., *J. Appl. Phys.* 49, 3464 (1978).
4. Dentz, D. J., Puttbach, R. C., and Belt, R. F., *Magnetism and Magnetic Materials*, AIP Conf. Proc. No. 18 (American Institute of Physics, New York, 1974).

Rare Earth Aluminum Garnets

Material	Temp. (K)	Verdet constant V (rad/T m) at wavelength in nm						Ref.
		405	450	480	520	578	670	
Tb ₃ Al ₅ O ₁₂	300	-659.4	-455.4	375.4	-302.3	-229	-158	1
	77	—	-29728	24284	-997	-757	-528	1
	4.2	—	—	—	-18860	-15650	-13140	2
	1.45	—	-58476	-50203	-40530	-32380	-27185	2
Dy ₃ Al ₅ O ₁₂	300	-361	-274	-234	-194	-151	-104	1
Ho ₃ Al ₅ O ₁₂	300	-206	-93.1	-75.7	-97.5	-87.0	-59.9	1
Er ₃ Al ₅ O ₁₂	300	-55.0	-69.8	-44.8	-47.1	-42.2	-25.9	1
Tm ₃ Al ₅ O ₁₂	300	43.9	30.0	27.1	22.1	17.2	—	1
Yb ₃ Al ₅ O ₁₂	298	83.5	62.6	54.1	40.7	33.8	—	3
	77	209	157	140	114	87.9	—	3

References:

1. Rubinstein, C. B., Van Uitert, L. G., and Grodkiewicz, W. H., *J. Appl. Phys.* 35, 3069 (1964).
2. Desorbo, W., *Phys. Rev.* 158, 839 (1967).
3. Rubinstein, C. B. and Berger, S. B., *J. Appl. Phys.* 36, 3951 (1965).

1.6.3 Ferromagnetic, Antiferromagnetic, and Ferrimagnetic Materials

The following symbols are used in the tables below:

T_c = Curie temperature	$4\pi M_S$ = saturation induction at 0 K, gauss
T_p = phase transition temperature	F = specific Faraday rotation, deg/cm
T_N = Neel temperature	α = absorption coefficient (cm^{-1})
T_∞ = compensation temperature	λ = measurement wavelength, nm

Transition Metals*

Material (structure)	Critical temp.	$4\pi M_S$ (gauss)	F (deg/cm)	Absorp. coeff. α (cm^{-1})	Temp. (K)	λ (nm)
Fe (bcc)	$T_c = 1043$	21800	4.4×10^5	6.5×10^5	300	500
			3.5×10^5	7.6×10^5	300	546
			6.5×10^5	5×10^5	300	1000
			7×10^5	4.2×10^5	300	1500
			7×10^5	3.5×10^5	300	2000
Co (hcp)	$T_c = 1390$	18200	2.9×10^5	—	300	500
			3.6×10^5	8.5×10^5	300	546
			5.5×10^5	6.1×10^5	300	1000
			5.5×10^5	4.5×10^5	300	1500
			4.8×10^5	3.6×10^5	300	2000
Ni (fcc)	$T_c = 633$	6400	0.8×10^5	—	300	500
			0.99×10^5	8.0×10^5	300	546
			2.6×10^5	5.8×10^5	300	1000
			1.5×10^5	4.8×10^5	300	1500
			1×10^5	4.1×10^5	300	2000
			7.2×10^5	4.2		4000

Binary Compounds*

Material (structure)	Critical temp.	$4\pi M_S$ (gauss)	F (deg/cm)	Absorp. coeff. α (cm^{-1})	Temp. (K)	λ (nm)
MnBi (NiAs)	$T_c = 639$	7700	4.2×10^5	6.1×10^5	300	450
		7500	5.0×10^5	5.8×10^5	300	500
		(300 K)	7.0×10^5	5.1×10^5	300	600
			7.7×10^5	4.5×10^5	300	700
			7.6×10^5	4.3×10^5	300	800
			7.5×10^5	4.2×10^5	300	900
			7.4×10^5	4.1×10^5	300	1000
MnAs (NiAs)	$T_c = 313$		0.44×10^5	5.0×10^5	300	500
			0.49×10^5	4.9×10^5	300	600

Binary Compounds*—continued

Material (structure)	Critical temp.	$4\pi M_s$ (gauss)	F (deg/cm)	Absorp. coeff. α (cm^{-1})	Temp. (K)	λ (nm)
MnAs			0.78×10^5	4.5×10^5	300	800
			0.62×10^5	4.4×10^5	300	900
CrTe (NiAs)	$T_c = 334$		0.5×10^5	2.0×10^5	300	550
			0.4×10^5	1.2×10^5	300	900
			0.4×10^5	0.6×10^5	300	2500
FeRh	$T_p = 334$		0.9×10^5	3.3×10^5	348	700

Ferrites*

Material (structure)	Critical temp.	$4\pi M_s$ (gauss)	F (deg/cm)	Absorp. coeff. α (cm^{-1})	Temp. (K)	λ (nm)
$\text{Y}_3\text{Fe}_5\text{O}_{12}$ (garnet)	$T_N = 560$	2500	2400	1500	300	555
			1750	1350	300	588
			1250	1400	300	625
			900	670	300	715
			800	1150	300	667
			750	450	300	770
			240	0.069	300	1200
			175	<0.06	300	5000– 1500
$\text{Gd}_3\text{Fe}_5\text{O}_{12}$ (garnet)	$T_N = 564$	7300	-2000	6000	300	500
	$T_\infty = 286$		-1050	900	300	600
			-450	400	300	700
			-300	100	300	800
			-220	230	300	900
			-80	70	300	1000
NiFeO_4 (spinel)	$T_N = 858$	3350	2.0×10^4	5.9×10^4	300	286
			2.4×10^4	7.4×10^4	300	330
			-0.75×10^4	16×10^4	300	400
			-1.0×10^4	10×10^4	300	500
			0.12×10^4	1×10^4	300	660
			-120	38	300	1500
			40	32	300	2000
			75	15	300	3000
			110	15	300	4000
			110	32	300	5000
CoFeO_4 (spinel)	$T_N = 793$	4930	2.75×10^4	12×10^4	300	286
			3.8×10^4	14×10^4	300	330
			3.6×10^4	17×10^4	300	400

Ferrites*—continued

Material (structure)	Critical temp.	$4\pi M_S$ (gauss)	F (deg/cm)	Absorp. coeff. α (cm^{-1})	Temp. (K)	λ (nm)
			1.3×10^4	13×10^4	300	500
			-2.5×10^4	6×10^4	300	660
MgFeO ₄ (spinel)			-60	100	300	2500
			-40	40	300	3000
			0	12	300	4000
			30	4	300	5000
			35	6	300	6000
			50	13	300	7000
BaFe ₁₂ O ₁₉ (hexagonal)			-50	38	300	2000
			75	20	300	3000
			130	13	300	4000
			150	20	300	5000
			160	20	300	6000
			165	22	300	7000
Ba ₂ Zn ₂ Fe ₁₂ O ₁₉ (hexagonal)			90	120	300	5000
			80	70	300	6000
			75	65	300	7000
			70	85	300	8000

Halides*

Material (structure)	Critical temp.	$4\pi M_S$ (gauss)	F (deg/cm)	Absorp. coeff. α (cm^{-1})	Temp. (K)	λ (nm)
RbNiF ₃ (perovskite)	T _N = 220	1250	360	35	77	450
			210	12	77	500
			70	10	77	600
			-70	30	77	700
			310	70	77	800
			100	60	77	900
			75	25	77	1000
RbFeF ₃ (perovskite)	T _p = 102		3400	7	82	300
			160	3	82	400
			950	4.6	82	500
			620	1.5	82	600
			420	1.2	82	700
			300	2.5	82	800
FeF ₃	T _c = 365 (300 K)	40	670	14	300	349
			415	8.2	300	404
			180	4.4	300	522.5

Halides*—continued

Material (structure)	Critical temp.	$4\pi M_S$ (gauss)	F (deg/cm)	Absorp. coeff. α (cm^{-1})	Temp. (K)	λ (nm)
CrBr ₃ (BiI ₃)	T _c = 32.5	3390	3×10^5 1.6×10^5	3×10^3 1.4×10^4	1.5	478 500
CrCl ₃ (BiI ₃)	T _c = 16.8	3880	2000 -500 -1000	20 3 30	1.5	410 450 590
CrI ₃ (BiI ₃)	T _c = 68	2690	1.1×10^5 0.8×10^5	6.3×10^3 3×10^3	1.5	970 1000

Borates*

Material (structure)	Critical temp.	$4\pi M_S$ (gauss)	F (deg/cm)	Absorp. coeff. α (cm^{-1})	Temp. (K)	λ (nm)
FeBO ₃ (calcite)	T _c = 115 (300 K)	115	3200 2300 1100 450	140 40 100 38	300 300 300 300	500 525 600 700

Chalcogenides*

Material (structure)	Critical temp.	$4\pi M_S$ (gauss)	F (deg/cm)	Absorp. coeff. α (cm^{-1})	Temp. (K)	λ (nm)
EuO (NaCl)	T _c = 69	23700 7500	-1.0×10^5 3.2×10^5 5×10^5 3.6×10^5 0.5×10^5 3×10^4 660	0.5×10^4 7.5×10^4 9.7×10^4 9.7×10^4 7.8×10^4 $>0.5^5$ ≥ 1.0	5 5 5 5 5 20 20	1100 800 700 600 500 2500 10600
EuS (NaCl)	T _c = 16.3		-1.6×10^5 -9.6×10^5 5.5×10^5 5.1×10^5	~ 0 3.3×10^4 1.2×10^5 1.0×10^5	6 6 6 6	825 690 563 495
EuSe (NaCl)	T _c = 7	13200	1.45×10^5 1.17×10^5 0.95×10^5	80 70 60	4.2 4.2 4.2	750 775 800

* The data in the above tables are from Di Chen, Magneto-optical materials, *Handbook of Laser Science and Technology, Vol. IV, Optical Materials, Part 2* (CRC Press, Boca Raton, FL, 1986), p. 287.

Room-Temperature Saturation Kerr Rotation Data for Ferromagnetic Materials

Material	T _c (K)	λ (nm)	θ _K (°)	Ref.
Fe	1043	633	-0.41	1
Co	1388	633	-0.35	1
Ni	627	633	-0.13	1
FeCo	NA	633	-0.54	1
MnBi	633	633	-0.70	2
PtMnSb	582	720	-1.27	3
CeSba	16	2500	14	4

Measured at T = 2 K.

Faraday Rotation Data For Nonmetallic Ferro- and Antiferromagnetic Materials

Material	T _c (K)	μ ₀ H (T)	λ (nm)	θ'F (°/cm)	Ref.	Comments
EuO	69	2.1	660	4.9 × 10 ⁵	5	1,4
EuSe	7	2.0	755	1.4 × 10 ⁵	6	1,2,4,8
EuS	16	0.675	670	5.5 × 10 ⁵	7	1,4
CrBr ₃	36		493	1 × 10 ⁵	8	1,5
CdCr ₂ S ₄	84	0.6	1000	3800	9	1,5
CdCr ₂ Se ₄	130	0.45	1050	5.5 × 10 ⁴	10	1,4
CoCr ₂ S ₄	221	0.4	10,600	320	11	ferri, 4
YFeO ₃			600	~8 × 10 ³	12	3,5,7
FeBO ₃	348		525	2300	13	3,5,7
UO ₂	30.8	4.0	276	4.8 × 10 ⁴	14	2,4,8

Comments: (1) ferromagnetic; (2) antiferromagnetic; (3) canted antiferromagnetic; (4) electrically semiconducting; (5) electrically insulating; (6) electrically conducting; (7) birefringent; (8) measured in unsaturated state. (The ferrimagnet CoCr₂S₄ is included because of its chemical similarity to the ferromagnets CdCr₂S₄ and CdCr₂Se₄.)

Saturation Kerr Rotation/Ellipticity Data for Nonmetallic Ferromagnetic Materials

Material	T _c (K)	μ ₀ H (T)	λ (nm)	θ _K [ε _K] (°)	Ref.	Comments
TmS	5.2	4	440	[-2.4]	15	1,6,8
TmSe	1.85	4	540	[-3.6]	15	1,6,8
US	177	4	350	[3.4]	16	1,6
USe	160	4	420	[4.0]	16	1,6
UTe	104	4	830	3.1	16	1,6
CuCr ₂ Se ₄	432	2	1290	[-1.19]	17	1,6
CoCr ₂ S ₄	221	1.5	1800	-4.6	18	ferri, 4

For materials which possess greater values of Kerr ellipticity than Kerr rotation, the ellipticity is reported in brackets [].

Comments: (1) ferromagnetic; (2) antiferromagnetic; (3) canted antiferromagnetic; (4) electrically semiconducting; (5) electrically insulating; (6) electrically conducting; (7) birefringent; (8) measured in unsaturated state.

**Room-Temperature Saturation Faraday Rotation and Absorption Data
for Selected Iron Garnets at $\lambda = 633$ nm**

Material	θ'_F (°/cm)	α (cm ⁻¹)	Growth technique	Ref.
Y ₃ Fe ₅ O ₁₂	835	870	LPE	25
Gd ₃ Fe ₅ O ₁₂	345	750	LPE	20
Bi ₃ Fe ₅ O ₁₂	-5.5×10^4		sputtering	21
Y ₃ Fe _{4.07} Ga _{0.93} O ₁₂	855	650	LPE	19
Y ₃ Fe _{3.54} Ga _{1.46} O ₁₂	645	530	flux method	19
Y _{2.3} Bi _{0.7} Fe ₅ O ₁₂	-1.25×10^4	1000	flux method	22
Y _{0.5} Bi _{2.5} Fe ₅ O ₁₂	-7.5×10^4		MOCVD	23
Y _{2.0} Ce _{1.0} Fe ₅ O ₁₂	2.2×10^4	540	sputtering	24

**Room-Temperature Saturation Faraday Rotation and Absorption Data for Selected
Iron Garnets at $\lambda = 1064$ nm**

Material	θ'_F (°/cm)	α (cm ⁻¹)	Growth technique	Ref.
Y ₃ Fe ₅ O ₁₂	280	9	flux method	25
Pr ₃ Fe ₅ O ₁₂	65	10	flux method	26
Nd ₃ Fe ₅ O ₁₂	535		flux method	26
Sm ₃ Fe ₅ O ₁₂	15		flux method	25
Eu ₃ Fe ₅ O ₁₂	107		flux method	25
Gd ₃ Fe ₅ O ₁₂	65	10	flux method	25
Tb ₃ Fe ₅ O ₁₂	535		flux method	25
Dy ₃ Fe ₅ O ₁₂	310		flux method	25
Ho ₃ Fe ₅ O ₁₂	135		flux method	25
Er ₃ Fe ₅ O ₁₂	120		flux method	25
Gd _{2.0} Bi _{1.0} Fe ₅ O ₁₂	-3300	< 10	flux method	27
Y _{2.0} Ce _{1.0} Fe ₅ O ₁₂	-22000	1700	sputtering	24

**Room-Temperature Saturation Faraday Rotation and Absorption Data
for Selected Iron Garnets at $\lambda = 1300$ nm**

Material	θ'_F (°/cm)	α (cm ⁻¹)	Growth technique	Ref.
Y ₃ Fe ₅ O ₁₂	210	0.3	flux method	28
Gd ₃ Fe ₅ O ₁₂	60	1.0	flux method	28
Tb ₃ Fe ₅ O ₁₂	320		flux method	26
Dy ₃ Fe ₅ O ₁₂	175		flux method	26
Tm ₃ Fe ₅ O ₁₂	110		flux method	26
Pr ₃ Fe ₅ O ₁₂	-1060	70	flux method	26
Nd ₃ Fe ₅ O ₁₂	-690	< 50	LPE	26
Y _{1.7} Bi _{1.3} Fe ₅ O ₁₂	-2100		LPE	29
Gd _{2.0} Bi _{1.0} Fe ₅ O ₁₂	-2100	< 10	flux method	27
Y _{2.0} Ce _{1.0} Fe ₅ O ₁₂	-120000	250	sputtering	24

LPE (liquid phase epitaxy), sputtering, and MOCVD (metal–organic chemical vapor deposition) are thin-film growth techniques. The flux method yields bulk crystals.

The preceding tables were adapted from Deeter, M. N., Day, G. W., and Rose, A. H., Magnetooptic materials: crystals and glasses, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 367 (with additions).

References:

1. Buschow, K. H. J., Van Engen, P. G., and Jongebreur, R., Magneto-optical properties of metallic ferromagnetic materials, *J. Magn. Magn. Mater.*, 38, 1 (1983).
2. Egashira, K., and Yamada, T., Kerr-effect enhancement and improvement of readout characteristics in MnBi film memory, *J. Appl. Phys.*, 45, 3643 (1974).
3. Van Engen, P. G., Buschow, K. H. J., and Jongebreur, R., PtMnSb, a material with very high magneto-optical Kerr effect, *Appl. Phys. Lett.*, 42, 202 (1983).
4. Reim, W., Schoenes, J., Hulliger, F., and Vogt, O., Giant Kerr rotation and electronic structure of $\text{CeSb}_x\text{Te}_{1-x}$, *J. Magn. Magn. Mater.*, 54–57, 1401 (1986).
5. Dimmock, J. O., Optical properties of the europium chalcogenides, *IBM J. Res. Dev.*, 14, 301 (1970), and references therein.
6. Suits, J. C., Argyle, B. E., and Freiser, M. J., Magneto-optical properties of materials containing divalent europium, *J. Appl. Phys.*, 37, 1391 (1966).
7. Guntherodt, G., Schoenes, J., and Wachter, P., Optical constants of the Eu chalcogenides above and below the magnetic ordering temperatures, *J. Appl. Phys.*, 41, 1083 (1970).
8. Dillon, J. F., Jr., Kamimura, H., and Remeika, J. P., Magneto-optical studies of chromium tribromide, *J. Appl. Phys.*, 34, 1240 (1963).
9. Ahrenkiel, R. K., Moser, F., Carnall, E., Martin, T., Pearlman, D., Lyu, S. L., Coburn, T., and Lee, T. H., Hot-pressed CdCr_2S_4 : an efficient magneto-optic material, *Appl. Phys. Lett.*, 18, 171 (1971).
10. Golik, L. L., Kun'kova, Z. É., Aminov, T. G., and Kalinnikov, V. T., Magnetooptic properties of CdCr_2Se_4 single crystals near the absorption edge, *Sov. Phys. Solid State*, 22, 512 (1980).
11. Jacobs, S. D., Faraday rotation, optical isolation, and modulation at $10.6 \mu\text{m}$ using hot-pressed CdCr_2S_4 and CoCr_2S_4 , *J. Electron. Mater.*, 4, 223 (1975).
12. Tabor, W. J., Anderson, A. W., and Van Uitert, L. G., Visible and infrared Faraday rotation and birefringence of single-crystal rare-earth orthoferrites, *J. Appl. Phys.*, 41, 3018 (1970).
13. Kurtzig, A. J., Wolfe, R., LeCraw, R. C., and Nielsen, J. W., Magneto-optical properties of a green room-temperature ferromagnet: FeBO_3 , *Appl. Phys. Lett.*, 14, 350 (1969).
14. Reim, W., and Schoenes, J., Magneto-optical study of the $5f^2 \rightarrow 5f^16d^1$ transition in UO_2 , *Solid State Commun.*, 39, 1101 (1981).
15. Reim, W., Hüsser, O. E., Schoenes, J., Kaldis, E., Wachter, P., Seiler, K., and W. Reim, , First magneto-optical observation of an exchange-induced plasma edge splitting, *J. Appl. Phys.*, 55, 2155 (1984).
16. Reim, W., Schoenes, J., and Vogt, O., Magneto-optics and electronic structure of uranium monochalcogenides, *J. Appl. Phys.*, 55, 1853 (1984).
17. Brändle, H., Schoenes, J., Wachter, P., Hulliger, F., and Reim, W., Large room-temperature magneto-optical Kerr effect in $\text{CuCr}_2\text{Se}_{4-x}\text{Br}_x$, $x = 0$ and 0.3 , *J. Magn. Magn. Mater.*, 93, 207 (1991).
18. Ahrenkiel R. K., and Coburn, T. J., Hot-pressed CoCr_2S_4 : a magneto-optical memory material, *Appl. Phys. Lett.*, 22, 340 (1973).
19. Hansen, P., and Witter, K., Magneto-optical properties of gallium-substituted yttrium iron garnets, *Phys. Rev. B*, 27, 1498 (1983).
20. Hansen, P., Witter, K., and Tolksdorf, W., Magnetic and magneto-optical properties of bismuth-substituted gadolinium iron garnet films, *Phys. Rev. B*, 27, 4375 (1983).
21. Okuda, T., Katayama, T., Satoh, K., and Yamamoto, H., Preparation of polycrystalline $\text{Bi}_3\text{Fe}_5\text{O}_{12}$ garnet films, *J. Appl. Phys.*, 69, 4580 (1991).

22. Scott, G. B., and Lacklison, D. E., Magnetooptic properties and applications of bismuth substituted iron garnets, *IEEE Trans. Magn.*, MAG-12, 292 (1976).
23. Okada, M., Katayama, S., and Tominaga, K., Preparation and magneto-optic properties of Bi-substituted yttrium iron garnet thin films by metalorganic chemical vapor deposition, *J. Appl. Phys.*, 69, 3566 (1991).
24. Gomi, M., Satoh, K., Furuyama, H., and Abe, M., Sputter deposition of Ce-substituted iron garnet films with giant magneto-optical effect, *IEEE Transl. J. Magn. Jpn.*, 5, 294 (1990).
25. Wemple, S. H., Dillon, J. F., Jr., Van Uitert, L. G., and Grodkiewicz, W. H., Iron garnet crystals for magneto-optic light modulators at 1.064 μm , *Appl. Phys. Lett.*, 22, 331 (1973).
26. Dillon, J. F., Jr., Albiston, S. D., and Fratello, V. J., Magnetooptical rotation of PrIG and NdIG, in *Advances in Magneto-Optics* (Magnetics Society of Japan, Tokyo, 1987), p. 241.
27. Takeuchi, H., Ito, S., Mikami, I., and Taniguchi, S., Faraday rotation and optical absorption of a single crystal of bismuth-substituted gadolinium iron garnet, *J. Appl. Phys.*, 44, 4789 (1973).
28. Booth, R. C. and White, E. A. D., Magneto-optic properties of rare earth iron garnet crystals in the wavelength range 1.1–1.7 μm & their use in device fabrication, *J. Phys. D.*, 17, 579 (1984).
29. Kamada, O., Minemoto, H., and Ishizuka, S., Application of bismuth-substituted iron garnet films to magnetic field sensors, In *Advances in Magneto-Optics* (The Magnetics Society of Japan, Tokyo, 1987), p. 401.

Faraday Rotation and Magnetooptic Properties of Orthoferrites^a

Material	$4\pi M_s^b$ (gauss)	Intrinsic specific Faraday rotation (deg/cm) at 300 K						Abs. coeff. (cm^{-1}) ^c
		600 nm	800 nm	1000 nm	1200 nm	1400 nm	1600 nm	
EuFeO ₃	83							~38
GdFeO ₃	94							~10
TbFeO ₃	137							~29
DyFeO ₃	128							~40
HoFeO ₃	91	8000	2200	1000	800	700	600	~10
ErFeO ₃	81							~15
TmFeO ₃	140							~5
YbFeO ₃	143							~12.5
LuFeO ₃	119							~5
SmFeO ₃	84							~50
YFeO ₃	105							~10
LaFeO ₃	83	3400	700	400	300	200	150	~10
PrFeO ₃	71							~35
NdFeO ₃	62							~10

^a Strong natural birefringence interferes with the Faraday effect.

^b Saturation induction.

^c At a wavelength of 1250 nm.

References:

- Bobeck, A. H., Fisher, R. F., Perneski, A. J., Remeika, J. P., and Van Uitert, L. G., *IEEE Trans. Magn.* MAG-5, 544 (1969).
Tabor, W. J., Anderson, A. W., and Van Uitert, L. G., *J. Appl. Phys.* 41, 3018 (1970).
Chetkin, M. V. and Shcherbakov, A., *Sov. Phys. Solid State* 11, 1313 (1969).

1.7 Electrooptic Properties

1.7.1 Linear Electrooptic Coefficients

The linear electrooptic effect occurs in acentric crystals. Only 21 acentric groups (those lacking a center of inversion) may have nonvanishing coefficients. Reduced electrooptic matrix forms are given in the two references below.

If the electrooptic coefficient r_{ij} is determined at constant strain (by making the measurement at high frequencies well above acoustic resonances of the sample) the crystal is clamped, as indicated by S. If the r_{ij} is determined at constant stress (at low frequencies well below the acoustic resonances of the sample) the sample is free, as indicated by T. The electrooptic coefficients are generally those for room temperature. Typical accuracies for r_{ij} are $\pm 15\%$. Unless shown explicitly, the signs of r_{ij} have not been determined. As a rule, r_{ij} has little optical wavelength dependence in the transparent region of the crystal.

The following tables were adapted from:

Kaminow, I. P., Linear Electrooptic Materials, *Handbook of Laser Science and Technology*, Vol. IV (CRC Press, Boca Raton, FL, 1986), p. 253.

Holland, W. R. and Kaminow, I. P., Linear Electrooptic Materials, *Handbook of Laser Science and Technology, Suppl. 2* (CRC Press, Boca Raton, FL, 1995), p. 133.

A comprehensive table of electrooptic constants including extensive data on refractive indices and curves of wavelength and temperature dependence of electrooptic coefficients is given in Cook, W. R., Hearmon, R. F. S., Jaffe, H., and Nelson, D. F., Piezooptic and electrooptic coefficient constants, *Landolt-Börstein*, Group III, Vol. 11, Hellewege, K.-H. and Hellewege, A. M., Eds. (Springer-Verlag, New York, 1979), p. 495.

The following tables are divided according to the general structure of the electrooptic materials, i.e., tetrahedally coordinated binary AB compounds that are semiconductors, ABO_3 -type compounds that are ferroelectric or pyroelectric, isomorphs of ferroelectric KH_2PO_4 and antiferroelectric $NH_4H_2PO_4$, other compounds that do not fit the previous categories, and organic compounds. Although nonlinear optic coefficients have been measured for many organic crystal and can be converted to equivalent electrooptic coefficients, only direct phase retardation measurements of the electrooptic effect are included in the last table.

AB-Type Compounds

Material	Symmetry	T/S	Electrooptic coeff.*	Wavelength $\lambda (\mu m)$
			$r_{ij} (10^{-12} m/V)$	
CdS	6mm	T	$r_c = 4$	0.589
		T	$r_{51} = 3.7$	0.589
		T	$r_c = 5.5$	10.6
		S	$r_{33} = 2.4$	0.633
		S	$r_{13} = 1.1$	
		T	$r_c = 4.8 \pm 0.2$	
		T	$r_{42} = 1.6 \pm 0.2$	

AB-Type Compounds—continued

Material	Symmetry	T/S	Electrooptic coeff.* r_{ij} (10^{-12} m/V)	Wavelength λ (μm)
CdS		T	$r_{33} = 3.2 \pm 0.2$	1.15
		T	$r_{13} = 3.1 \pm 0.2$	
		T	$r_c = 6.2 \pm 0.2$	
		T	$r_{42} = 2.0 \pm 0.2$	
		T	$r_{33} = 2.9 \pm 0.1$	3.39
		T	$r_{13} = 3.5 \pm 0.1$	
		T	$r_c = 6.5 \pm 0.2$	
		T	$r_{42} = 2.0 \pm 0.2$	
		T	$r_{33} = 2.75 \pm 0.08$	10.6
		T	$r_{13} = 2.45 \pm 0.08$	
CdSe	6mm	S	$r_{33} = 4.3$	3.39
		S	$r_{13} = 1.8$	
CdS _{0.75} Se _{0.25}	6mm	T	$n_1^3 r_c = 70$	0.63
CdTe	-43m	T	$r_{41} = 6.8$	3.39
		T	$r_{41} = 6.8$	10.6
		T	$r_{41} = 5.5$	23.35
		T	$r_{41} = 5.0$	27.95
		S	$n_0^3 r_{41} = 100 \pm 10$	10.6
CuBr	-43m	T	$r_{41} = 0.85$	0.525
		S	$r_{41} = -2.5$	0.63
		S	$r_{41} = -3.0$	1.15
		S	$r_{41} = -3.0$	3.39
CuCl	-43m	T	$r_{41} = 3.6$	0.633
		T	$r_{41} = 3.2$	10.6
		S	$r_{41} = 2.35$	0.633
		S	$r_{41} = 2.20$	3.39
		S	$r_{41} = -2.35$	0.63
		S	$r_{41} = -2.5$	3.39
		T	$r_{41} = -5$	0.55
CuI	-43m	T	$n_0^3 r_{41} = 30$	0.63
GaAs	-43m	S	$r_{41} = 1.2$	0.9–1.08
		S	$r_{41} = -1.5$	3.39
		S + T	$r_{41} = 1.2 - 1.6$	1.0 – 3.0
		T	$r_{41} = 1.0 - 1.2$	2.0 – 12.0
		T	$r_{41} = 1.6$	10.6
		S	$r_{41} = -1.33$	1.06

AB-Type Compounds—continued

Material	Symmetry	T/S	Electrooptic coeff.*	Wavelength
			$r_{ij} (10^{-12} \text{ m/V})$	$\lambda (\mu\text{m})$
GaAs		T	$r_{41} = 1.24 \pm 0.04$	3.39
		T	$r_{41} = 1.51 \pm 0.05$	10.6
GaP	-43m	S	$r_{41} = -1.07 - -0.97$	0.56 – 3.39
		T	$r_{41} = 0.79 - 0.80$ (200 Hz)	0.552 – 1.15
		S	$r_{41} = 0.95 - 0.87$ (9.45 GHz)	
GaSe	-6m2	T	$r_{22} = 22$	0.63
		T	$n_1^3 r_{22} = 27.5$	1.06
HgS	32	S	$r_{11} = 3.1$	0.633
		S	$r_{41} = 1.4$	0.633
		S	$r_{11} = 4.2$	3.39
		S	$r_{41} = 2.4$	3.39
InP	-43m	S	$r_{41} = -1.34$	1.06
		S	$r_{41} = -1.68$	1.50
β -SiC	43m	T	$r_{41,52,63} = 2.7 \pm 0.5$	0.633
ZnO	6mm	S	$r_{33} = +2.6$	0.633
			$r_{13} = -1.4$	0.633
		S	$r_{33} = +1.9$	3.39
			$r_{13} = +0.96$	3.39
			$r_{51} = -3.1$	0.4
		T	$r_{31} - r_{33} = -1.4$	0.4
ZnS	-43m	T	$r_{41} = 1.2$	0.4
		T	$r_{41} = 2.1$	0.65
		S	$r_{41} = 1.6$	0.633
		S	$r_{41} = 1.4$	3.39
		T	$r_{41} = -1.9$	0.63
ZnS	6mm	T	$r_{41} = 2.0$	0.546
		S	$r_{41} = 2.0$	0.633
		T	$r_{41} = 2.2$	10.6
		T	$r_{41} = 1.9$	0.55
ZnTe	-43m	T	$r_{41} = 4.45 - 3.95$	0.59 – 0.69
		T	$r_{41} = 1.4$	10.6
		S	$r_{41} = 4.3$	0.633
		S	$r_{41} = 3.2$	3.39
		T	$r_{41} = 4.2 \pm 0.3$	3.41
		T	$r_{41} = 3.9 \pm 0.2$	10.6

* $r_c = r_{33} - (n_1^3 / n_3^3) r_{33}$

ABO₃-Type Compounds

Material	Symmetry	T/S	Electrooptic coeff.*	Wavelength
			$r_{ij} (10^{-12} \text{ m/V})$	$\lambda (\mu\text{m})$
Ba _x NaNb ₅ O ₁₅	mm2		$r_C = 34$ $r_{33} = 48$ $r_{42} = 92$ $r_{13} = 15$ $r_{33} = +29$ $42 = 75$ $r_{13} = 6.1$ $n_3^3 r_{33} = 265$ $n_1^3 r_{13} = 76$	0.633
Ba _{2-y} Sr _y K _x Na _{1-x} Nb ₅ O ₁₅ (0.5 < x < 0.75) (0.6 < y < 1.8)	4mm		$n_o^3 r_o = 730$	0.561
Ba _{1.5} Sr _{0.5} K _{0.75} Na _{0.25} Nb ₅ O ₁₅	4mm		$r_{33} = 110$ $r_{51} = 250$	
Ba _{0.5} Sr _{1.5} K _{0.5} Na _{0.75} Nb ₅ O ₁₅	4mm		$r_{33} = 180$ $r_{51} = 300$	
Ba _{0.5} Sr _{1.5} K _{0.25} Na _{0.75} Nb ₅ O ₁₅	4mm		$r_{33} = 200$	
BaTiO ₃	4mm	T	$r_{13} = 19.5 \pm 1$ $r_{33} = 97 \pm 7$ $r_c = 76 \pm 7$ $r_c = 108$ $r_{51} = 1640$ S $r_c = 23$ S $r_{51} = 820$ S $r_c = 19$ S $r_{33} = 28$ S $r_{13} = 8$	0.5145 0.546 0.633
KNbO ₅	mm2	S	$r_{33} = 25 \pm 8$ $r_{42} = 270 \pm 40$ $r_{13} = 10 \pm 2$ $r_{51} = 23 \pm 3$ $r_{23} = 2 \pm 1$ T $r_{33} = 64 \pm 5$ T $r_{42} = 380 \pm 50$ T $r_{13} = 28 \pm 2$ T $r_{51} = 105 \pm 13$ $r_{23} = +1.3 \pm 0.5$	0.633
KS _x Nb ₅ O ₁₅	4mm or 4	T	$r_c = 130$	0.633

ABO_3 -Type Compounds—*continued*

Material	Symmetry	T/S	Electrooptic coeff.*	Wavelength
			$r_{ij} (10^{-12} \text{ m/V})$	$\lambda (\mu\text{m})$
LiIO ₃	6	S	$r_{33} = +6.4$	0.633
		S	$r_{41} = 1.4$	
		S	$r_{13} = +4.1$	
		S	$r_{51} = +3.3$	
LiNbO ₃	3m	T	$r_c = 17.4$	0.633
		T	$r_{22} = 6.8$	
		T	$r_{51} = 32$	
		T	$r_{33} = +32.2$	
		T	$r_{13} = +10$	
		T	$r_c = 17$	1.15
		T	$r_{22} = 5.7$	
		T	$r_c = 16$	3.39
		T	$r_{22} = 3.1$	
		S	$r_{33} = +30.6$	0.633
		S	$r_{13} = +8.6$	
		S	$r_{51} = +28$	
		S	$r_{33} = 28$	3.39
		S	$r_{22} = 3.1$	
		S	$r_{13} = 65$	
		S	$r_{51} = 23$	
LiTaO ₅	3m	S	$r_{33} = +28.8$	0.633
		S	$r_{51} = +18.2$	
		S	$r_{13} = +7.68$	
		S	$r_{33} = 27.2$	1.152
		S	$r_{13} = +6.65$	
		S	$r_{33} = +25.5$	3.391
		S	$r_{13} = +5.32$	
		T	$r_c = 22$	0.633
		S	$r_{33} = 30.3$	
		S	$r_{51} = 20$	
		S	$r_{33} = 27$	3.39
		S	$r_{51} = 15$	
		S	$r_{13} = 4.5$	
		S	$r_{22} = 0.3$	
		S	$r_{13} = 6.2$	
		S	$r_{33} = 26.7$	1.152
		S	$r_{51} = 8.9$	
		S	$r_{13} = 5.2$	
		S	$r_{33} = 25.2$	3.39
		S	$r_{13} = 4.4$	
		T	$r_{33} = 30.5 \pm 2$	0.633
		T	$r_{13} = 8.4 \pm 0.9$	

ABO₃-Type Compounds—continued

Material	Symmetry	T/S	Electrooptic coeff.*	Wavelength
			$r_{ij} (10^{-12} \text{ m/V})$	$\lambda (\mu\text{m})$
K ₅ Li ₂ Nb ₅ O ₁₅	4mm		$r_{33} = 78$ $r_{13} = 8.9$	0.633
KTa _x Nb _{1-x} O ₅	4mm	T	$r_c = 450$	0.633
		T	$r_{51} = +50$	
La _y (Sr _{0.5} Ba _{0.5}) _{1-1.5y} Nb ₂ O ₆ (0 < y < .03)	4mm		$r_c = 145-669$	0.6328
			$r_c = r_{33} - (n_1/n_3)^3 r_{13}$	
PbTiO ₅	4mm	S	$r_{33} = 5.9$	0.633
		S	$r_{13} = 13.8$	
Sr _{0.61} Ba _{0.39} Nb ₂ O ₆	4mm	T	$r_{13} = 47 \pm 5$	0.5145
		T	$r_{33} = 235 \pm 21$	
Sr _{0.75} Ba _{0.25} Nb ₂ O ₆	4mm	T	$r_c = 1410$	0.633
		T	$r_{33} = 1340$	
		T	$r_{51} = 42$	
		T	$r_{15} = 67$	
		S	$r_c = 1090$	
Sr _{0.5} Ba _{0.5} Nb ₂ O ₆	4mm	T	$r_c = 218$	0.633
Sr _{0.46} Ba _{0.54} Nb ₂ O ₆	4mm	T	$r_{33} = 35 \pm 3$	0.633
		T	$r_{13} = 180 \pm 30$	
Sr _{0.3} Ba _{0.79} Nb ₂ O ₆	4mm	T	$r_{13} = -266$	0.633
			$r_{33} = +113$	

$$* r_c = r_{33} - (n_1^3 / n_3^3) r_{33}$$

KDP- and ADP-Type Compounds

Material	Symmetry*	T/S	Electrooptic coeff.	Wavelength
			$r_{ij} (10^{-12} \text{ m/V})$	$\lambda (\mu\text{m})$
KH ₂ PO ₄ (KDP)	-42m	T	$r_{63} = 9.4 \pm 0.4$	0.633
		T	$r_{41} = +8.6$	
		S	$r_{63} = 8.8$	
KD ₂ PO ₄ (DKDP)	-42m	T	$r_{63} = 23.8 \pm 0.6$	0.633
		T	$r_{41} = 8.8$	
		T	$r_{61} < 0$	
		S	$r_{63} = 24.0$	
KH ₂ AsO ₄ (KDA)	-42m	T	$r_{63} = 10.9$	0.633
		T	$r_{41} = 12.5$	
KD ₂ AsO ₄ (DKDA)	-42m	T	$r_{63} = 18.2$	0.633

KDP- and ADP-Type Compounds –continued

Material	Symmetry*	T/S	Electrooptic coeff.	Wavelength λ (μm)
			$r_{ij} (10^{-12} \text{ m/V})$	
RbH ₂ PO ₄ (RDP)	-42m	T	$r_{63} = 15.5$	0633
		S	$r_{63} = 0.91$	
RbH ₂ AsO ₄ (RDA)	-42m	T	$r_{63} = 13.0$	0.633
RbD ₂ AsO ₄ (DRDA)	-42m	T	$r_{63} = 21.4$	0633
CsH ₂ AsO ₄ (CDA)	-42m	T	$r_{63} = 18.6$	0633
CsD ₂ AsO ₄ (DCDA)	-42m	T	$r_{63} = 36.6$	0633
NH ₄ H ₂ PO ₄ (ADP)	-42m	T	$r_{63} = -8.5$	0633
		T	$r_{41} = 24.5$	
		S	$r_{63} = 5.5$	
NH ₄ D ₂ PO ₄ (DADP)	-42m	T	$r_{63} = 11.9$	0633
NH ₄ H ₂ AsO ₄ (ADA)	-42m	T	$r_{63} = 9.2$	0633

* Above T_c

Other Compounds

Material	Symmetry	T/S	Electrooptic coeff..	Wavelength λ (μm)
			$r_{ij} (10^{-12} \text{ m/V})$	
AgGaS ₂	-42m	T	$r_{63} = 3.0$	0.633
		T	$r_{41} = 4.0$	
AgGaSe ₂	-42m	T	$r_{63} = 6.9$	1.15
		T	$r_{41} = 4.5$	
		T	$n^3 r_{63} = 76$	
		T	$n^3 r_{41} = 85$	
(CH ₃ NH ₃) ₅ Bi ₂ Br ₁₁	mm2	T	$1/2(n_3^3 r_{33} - n_2^3 r_{23}) = 5.8 \pm 0.8$	0.6328
		T	$1/2(n_3^3 r_{33} - n_1^3 r_{13}) = 3.5 \pm 0.7$	
BaB ₂ O ₄ (BBO)	3m	T	$r_{22} = 2.7 \pm 0.4$	0.6328
		T	$r_{31} = 0$	
		T	$r_{61} = 0.055$	
		T	$r_{22} = 2.5 \pm 0.1$	
		T	$r_c = 0.17 \pm 0.02$	
		S	$r_{22} = 2.1 \pm 0.3$	
		S	$r_c = 0.11 \pm 0.02$	
Bi ₄ Ge ₃ O ₂₀ (BGO)	23	T	$r_{41} = 1.03$	0.45–0.62
		T	$r_{41} = 0.95$	
Bi ₄ Si ₃ O ₂₀	23	T	$r_{41} = 0.54$	0.63
Bi ₄₀ Ga ₂ O ₆₃	23	T	$n_0^3 r_{41} = 54.9$	0.633

Other Compounds—continued

Material	Symmetry	T/S	Electrooptic coeff.. r_{ij} (10^{-12} m/V)	Wavelength λ (μm)
Bi ₁₂ GeO ₂₀ (BGO)	23		$r_{41} = 3.67 \pm 0.11$ $r_{41} = 3.29 \pm 0.10$	0.633 0.850
Bi ₁₂ SiO ₂₀ (BSO)	23	T	$r_{41} = 4.1 \pm 0.1$ $r_{41} = 4.25 \pm 0.13$	0.650 0.633
Bi ₁₂ TiO ₂₀ (BTO)	23	T	$r_{41} = 5.75 \pm 0.10$ $r_{41} = 3.81 \pm 0.11$	0.633
Ca ₂ Nb ₂ O ₇	2	T	$r_{22} - (n_1/n_2)^3 r_{12} = 12$	0.63
		T	$r_{22} - (n_1/n_3)^3 r_{32} = 14$	
		S	$r_{22} - (n_3/n_2)^3 r_{32} = 0.6$	
		S	$r_{12} = 6.7$	
		S	$r_{22} = 25.5$	
		S	$r_{32} = 6.4$	
		S	$r_{13} = 0.37$	
		S	$r_{41} = 2.7$	
			$r_{52} = <0.6$	
		S	$r_{63} = 0.9$	
CdGaS ₂	-4	T	$r_{13} = 0.37$	0.50
		T	$r_{63} = 3.5$	
CHI ₃ •3S ₈	3m		$r_{12} = 4.4 \pm 2.5$ $r_{13} = -0.512$ $r_{33} = 0.29 \pm 0.12$	0.633
Cs ₃ Sr[Cu ₂ (SCN) ₉]	42m	T	$r_{63} = +0.06 \pm .002$	0.633
CuGaS ₂	-42m	S	$r_{63} = +1.35$	0.63
		S	$r_{41} = +1.76$	
		S	$r_{63} = +1.66$	1.15
		S	$r_{41} = +1.9$	
		S	$r_{63} n_0^3 r_{41}$	3.39
		S	$r_{41} = +1.1$	
Gd ₂ (MoO ₄) ₃ (450 K)	-42m	T	$n_1^3 r_{63} = 17$	0.633
Gd ₂ (MoO ₄) ₃ (30 K)	mm2	T	$n_1^3 r_{13} - n_3^3 r_{33} = 17.5$	0.633
KTiOAsO ₄ (KTA)	mm2	T	$r_{33} = 40 \pm 1$	0.6328
		T	$r_{33} = 21 \pm 1$	
		T	$r_{13} = 15 \pm 1$	
KTiOPO ₄ (KTP)	mm2	T	$r_{13} = +9.5 \pm 0.5$	0.6328
		T	$r_{23} = +15.7 \pm 0.8$	
		T	$r_{42} = 9.3 \pm 0.9$	
		S	$r_{13} = +8.8 \pm 0.8$	
		S	$r_{23} = +13.8 \pm 1.4$	

Other Compounds—continued

Material	Symmetry	T/S	Electrooptic coeff.. r_{ij} (10^{-12} m/V)	Wavelength λ (μm)
KTiOPO ₄		S	$r_{33} = +35.0 \pm 3.5$	
		S	$r_{51} = 6.9 \pm 1.4$	
		S	$r_{42} = 8.8 \pm 1.8$	
K ₂ Mg ₂ (SO ₄) ₃	23	T	$r_{41} = 0.40$	0.546
K ₂ Mn ₂ (SO ₄) ₃	23	T	$r_{41} = 2.0$	0.453–0.642
K ₂ Ni ₂ (SO ₄) ₃	23	T	$r_{41} = 0.4$	0.453–0.642
K ₂ S ₂ O ₆	32	T	$r_{11} = 0.26$	0.546
LiInS ₂	mm2	T	$r_{33} - (n_1^3/n_3^3)r_{13} = +0.67$ $r_{33} - (n_2^3/n_3^3)r_{23} = +0.60$	0.63
LiInSe ₂	mm2	T	$r_{33} - (n_1^3/n_3^3)r_{13} = +1.39$ $r_{33} - (n_2^3/n_3^3)r_{23} = +1.55$	0.63
LiKSO ₄	6	T	$r_c = 1.6$	0.546
LiNaSO ₄	3m	T	$r_{22} = <0.02$	0.546
NaClO ₃	23	T	$r_{41} = 0.4$	0.589
NaNO ₂	mm2	T	$r_{22} - (n_1/n)^3 r_{32} = 4.1$	0.546
		T	$r_{32} - (n_1/n)^3 r_{12} = 4.2$	
		T	$r_{22} - (n_1/n_2)^3 r_{12} = 0.6$	
		T	$r_{43} = -1.9$	
		T	$r_{61} = -3.0$	
Na ₂ SbS ₄ •9H ₂ O	23	T	$n_1^3 r_{41} = 5.66$	0.42
		T	$n_1^3 r_{41} = 5.62$	1.08
		T	$r_{22} = 0.82$	0.52
		T	$r_{22} = 0.77$	0.60
(NH ₄) ₃ Cd ₂ (SO ₄) ₃	23	T	$r_{41} = 0.70$	0.546
(NH ₂) ₂ CO	-42m	T	$r_{63} = 0.52$	0.63
		T	$r_{41} = 0.50$	
(NH ₄) ₃ Mn ₂ (SO ₄) ₃	23	T	$r_{41} = 0.53$	0.546
Pb ₅ Ge ₃ O ₁₁	3	T	$r_{11} = 0.27$	0.63
		T	$r_{22} = 0.23$	
		T	$r_{13} = 10.5$	
		T	$r_{33} = 15.3$	
		T	$r_{41} = 0.6$	
		T	$r_{51} = 6$	
		T	$r_c = 5.3$	

Other Compounds—*continued*

Material	Symmetry	T/S	Electrooptic coeff..		Wavelength λ (μm)
			r_{ij} (10^{-12} m/V)		
Rb ₂ Mn ₂ (SO ₄) ₃	23	T	$r_{41} = 1.9$		0.453–0.642
SbSI	mm2	T	$r_{33} = 2 \times 10^4$ (293 K)		0.7
		T	$r_{33} = 2000$ (288 K)		
Se	32	S	$n_1^3 r_{11} = 89$		1.15
		S	$r_{11} = \sim 2.5$		10.6
SiO ₂	32	T	$r_{11} = -0.47$		0.409–0.605
		T	$r_{41} = 0.20$		
		S	$r_{11} = 0.174$		0.633
TeO ₂	422	T	$r_{41} = -0.76$		0.63
		S	$r_{41} = +0.62$		
Tl ₂ Mn ₂ (SO ₄) ₃	23	T	$r_{41} = 2.1$		0.453–0.642
Tl ₂ Cd ₂ (SO ₄) ₃	23	T	$r_{41} = 0.37$		0.546
tourmaline	3m	T	$r_{22} = 0.3$		0.589
		S	$r_{13} = 1.7$		0.633
ZnGeP ₂	-42m	S	$r_{63} = -0.8$		3.39
		S	$r_{41} = +1.6$		

Organic Compounds

Material	Symmetry	T/S	Electrooptic coeff.		Wavelength λ (μm)
			r_{ij} (10^{-12} m/V)		
$(\text{CH}_2)_6\text{N}_2:\text{HMT}$ -hexamethylenetetramine, hexamine	-43m	T	$r_{41} = 0.72 \pm 0.01$		0.5
		T	$r_{41} = 0.78$		0.633
		S	$r_{41} = <0.14$		
$\text{C}(\text{CH}_2\text{OH})_4$	2	T	$r_{52} = 1.45$		0.46–0.70
		T	$ r_{12} - r_{32} = 0.7$		
$\text{C}_6\text{H}_4(\text{NO}_2)_2\text{NH}_2$ meta-nitroaniline	mm2	T	$r_{33} = 16.7 \pm 0.2$		0.63
		T	$r_{23} = 0.1 \pm 0.6$		
		T	$r_{13} = 7.4 \pm 0.7$		
$\text{Cs}_2\text{C}_4\text{H}_4\text{O}_6$	32	T	$r_{11} = 1.0$		0.546
DBNMNA 2,6-dibromo- <i>N</i> -methyl-4-nitroaniline	mm2	T	$n_3 a r_{13} - n_3 c r_{33} = 148$		0.5145
		T	$r_{42} = 86$		
		T	$r_{51} = 83$		
		T	$n_3 a r_{13} - n_3 c r_{33} = 32$		0.6328
		T	$r_{42} = 20.4$		
		T	$r_{51} = 41.4$		

Organic Compounds—continued

Material	Symmetry	T/S	Electrooptic coeff. $r_{ij} (10^{-12} \text{ m/V})$	Wavelength $\lambda (\mu\text{m})$
DBNMNA		T	$n_3 a r_{13} - n_3 c r_{33} = 18.3$	0.810
		T	$r_{42} = 11.5$	
		T	$r_{51} = 31$	
MMONS 3-methyl-4-methoxy- 4;pr-nitrostilbene	mm2	T	$r_{53} = 39.9 \pm 8$	0.6328
		T	$r_{23} = 19.3 \pm 4$	
		T	$r_{c2} = 30.0 \pm 3$	
MNA 2-methyl-4-nitroaniline	m	—	$r_{11} = 67 \pm 25$	0.6328
POM 3methyl 4-nitropyridine 1-oxide	222	T	$63 = 2.6 \pm 0.3$	0.63
		T	$r_{52} = 5.1 \pm 0.4$	
		T	$r_{41} = 3.6 \pm 0.6$	
PNP 2-(N-Prolinol)- 5-nitropyridine	2	T	$r_{12} = 20.2 \pm 0.3$	0.514
		T	$r_{22} = 28.3 \pm 0.4$	
		T	$r_{12} = 13.1 \pm 0.2$	
		T	$r_{22} = 13.1 \pm 0.2$	
SPCD styrlpyridinium cyanine dye	mm2	—	$r_{33} = 430$	0.6328

1.7.2 Quadratic Electrooptic Materials

Kerr Constants of Ferroelectric Crystals^{1,2}

Material	T_{trans} (K)	λ (μm)	g_{11} (10^{10} esu)	g_{12} (10^{10} esu)	$g_{11} \cdot g_{12}$ (10^{10} esu)	g_{44} (10^{10} esu)
BaTiO ₃	406	0.633	1.33	-0.11	1.44	—
SrTiO ₃	—	0.633	—	—	1.56	—
KTa _{0.65} Nb _{0.35} O ₃	330	0.633	1.50	-0.42	1.92	1.63
KTaO ₃	13	0.633	—	—	1.77	1.33
LiNbO ₃	1483	—	0.94	0.25	0.7	0.6
LiTaO ₃	938	—	1.0	0.17	0.8	0.7
Ba _{0.8} Na _{0.4} Nb ₂ O ₆	833	—	1.55	0.44	1.11	—

References

1. Narasimhamurty, T. S., *Photoelastic and Electro-Optic Properties of Crystals*, Plenum Press, New York, 1981, p. 408.
2. Gray, D. E., Ed., *AIP Handbook of Physics*, McGraw Hill, New York, 1972, p. 6-241.

See, also, Cook, W. R., Hearmon, R. F. S., Jaffe, H., and Nelson, D. F., Piezooptic and electrooptic coefficient constants, *Landolt-Börstein*, Group III, Vol. 11, Hellewege, K.-H. and Hellewege, A. M., Eds. (Springer-Verlag, New York, 1979), p. 495.

1.8 Elastooptic Properties

1.8.1 Elastooptic Coefficients

The following tables of elastooptic coefficients (photoelastic constants) are from the *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12–180. Materials are listed alphabetically by chemical composition. Data have been measured at room temperature, except for rare gas crystals.

Cubic Crystals; Point Groups 43m, 432, m3m

Material	Wavelength (μm)	Elastooptic coefficients				
		p ₁₁	p ₁₂	p ₄₄	p ₁₁ –p ₁₂	Ref.
C (diamond)	0.540–0.589	−0.278	0.123	−0.161	−0.385	13
CaF ₂	0.55–0.65	0.038	0.226	0.0254	−0.183	11
CdTe	1.06	−0.152	−0.017	−0.057	−0.135	10
CuBr	0.633	0.072	0.195	−0.083	−0.123	12
CuCl	0.633	0.120	0.250	−0.082	−0.130	12
CuI	0.633	0.032	0.151	−0.068	−0.119	12
GaAs	1.15	−0.165	−0.140	−0.072	−0.025	15
GaP	0.633	−0.151	−0.082	−0.074	−0.069	15
Gd ₃ Ga ₅ O ₁₂	0.514	−0.086	−0.027	−0.078	−0.059	23
Ge	3.39	−0.151	−0.128	−0.072	−0.023	14
KBr	0.589	0.212	0.165	−0.022	0.047	5
KCl	0.633	0.22	0.16	−0.025	0.06	4
KF	0.546	0.26	0.20	−0.029	0.06	1
KI	0.590	0.212	0.171	—	0.041	6
LiCl	0.589	—	—	−0.0177	−0.0407	3
LiF	0.589	0.02	0.13	−0.045	−0.11	5
NaBr	0.589	0.148	0.184	−0.0036	−0.035	1
NaCl	0.589	0.115	0.159	−0.011	−0.042	2
NaF	0.633	0.08	0.20	−0.03	−0.12	1
NaI	0.589	—	—	0.0048	−0.0141	3
NH ₄ Cl	0.589	0.142	0.245	0.042	−0.103	9
RbBr	0.589	0.293	0.185	−0.034	0.108	7,8
RbCl	0.589	0.288	0.172	−0.041	0.116	7,8
RbI	0.589	0.262	0.167	−0.023	0.095	7,8
SrF ₂	0.633	0.080	0.269	0.0185	−0.189	16
SrTiO ₃	0.633	0.15	0.095	0.072	—	17
Tl(Br,Cl)	0.633	−0.451	−0.337	−0.164	−0.114	19,20
Tl(Br,I)	0.633	−0.140	0.149	−0.0725	−0.289	18,20
Y ₃ Al ₅ O ₁₂	0.633	−0.029	0.0091	−0.0615	−0.038	15
Y ₃ Fe ₅ O ₁₂	1.15	0.025	0.073	0.041	—	15
Y ₃ Ga ₅ O ₁₂	0.633	0.091	0.019	0.079	—	17
ZnS	0.633	0.091	−0.01	0.075	0.101	15

Cubic Crystals; Point Groups 23, m3

Material	Wavelength (μm)	Elastooptic coefficients				
		p_{11}	p_{12}	p_{44}	p_{13}	Ref.
Ba(NO ₃) ₂	0.589	—	$p_{11}-p_{22} =$ 0.992	-0.0205	$p_{11}-p_{13} =$ 0.713	13
NaBrO ₃	0.589	0.185	0.218	-0.0139	0.213	26
NaClO ₃	0.589	0.162	0.24	-0.0198	0.20	26
Pb(NO ₃) ₂	0.589	0.162	0.24	-0.0198	0.20	24,25
Sr(NO ₃) ₂	0.41	0.178	0.362	-0.014	0.316	27

Trigonal Crystals; Point Groups 3m, 32, -3m

Material	Wavelength (μm)	Elastooptic coefficients				
		p_{11}	p_{12}	p_{13}	p_{14}	p_{31}
Ag ₃ AsS ₃	0.633	± 0.10	± 0.19	± 0.22		± 0.24
Al ₂ O ₃	0.644	-0.23	-0.03	0.02	0.00	-0.04
CaCO ₃	0.514	0.062	0.147	0.186	-0.011	0.241
HgS	0.633			± 0.445		
LiNbO ₃	0.633	± 0.034	± 0.072	± 0.139	± 0.066	± 0.178
LiTaO ₃	0.633	-0.081	0.081	0.093	-0.026	0.089
NaNO ₃	0.633		± 0.21	± 0.215	± 0.027	± 0.25
SiO ₂	0.589	0.16	0.27	0.27	-0.030	0.29
Te	10.6	0.155	0.130	—	—	—

Trigonal Crystals; Point Groups 3m, 32, 3m –continued

Material	Wavelength (μm)	Elastooptic coefficients			
		P_{33}	P_{41}	P_{44}	Ref.
Ag ₃ AsS ₃	0.633	± 0.20	—	—	38
Al ₂ O ₃	0.644	-0.20	0.01	-0.10	15,32
CaCO ₃	0.514	0.139	-0.036	-0.058	33
α -HgS	0.633	± 0.115	—	—	36
LiNbO ₃	0.633	± 0.060	± 0.154	± 0.300	15,34
LiTaO ₃	0.633	-0.044	-0.085	0.028	15,35
NaNO ₃	0.633		0.055	-0.06	39
α -SiO ₂	0.589	0.10	-0.047	-0.079	37
Te	10.6	—	—	—	15

Tetragonal Crystals; Point Groups 4/mmm, -42m, 422

Material	Wavelength (μm)	Elastooptic coefficients			
		p ₁₁	p ₁₂	p ₁₃	p ₃₁
(NH ₄)H ₂ PO ₄	0.589	0.319	0.277	0.169	0.197
BaTiO ₃	0.633	0.425	—	—	—
CsH ₂ AsO ₄	0.633	0.267	0.225	0.200	0.195
MgF ₂	0.546	—	—	—	—
Hg ₂ Cl ₂	0.633	±0.551	±0.440	±0.256	±0.137
KH ₂ PO ₄	0.589	0.287	0.282	0.174	0.241
RbH ₂ AsO ₄	0.633	0.227	0.239	0.200	0.205
RDP	0.633	0.273	0.240	0.218	0.210
Sr _{0.75} Ba _{0.25} Nb ₂ O ₆	0.633	0.16	0.10	0.08	0.11
Sr _{0.5} Ba _{0.5} Nb ₂ O ₆	0.633	0.06	0.08	0.17	0.09
TeO ₂	0.633	0.0074	0.187	0.340	0.090
TiO ₂ (rutile)	0.633	0.017	0.143	-0.139	-0.080

Tetragonal Crystals; Point Groups 4/mmm, -42m, 422—continued

Material	Wavelength (μm)	Elastooptic coefficients			
		p ₃₃	p ₄₄	p ₆₆	Ref.
(NH ₄)H ₂ PO ₄	0.589	0.167	-0.058	-0.091	40
BaTiO ₃	0.633	—	—	—	41
CsH ₂ AsO ₄	0.633	0.227	—	—	42
MgF ₂	0.546	—	±0.0776	±0.0488	43
Hg ₂ Cl ₂	0.633	-0.010	—	±0.047	44
KH ₂ PO ₄	0.589	0.122	-0.019	-0.064	45
RbH ₂ AsO ₄	0.633	0.182	—	—	41
RDP	0.633	0.208	—	—	41
Sr _{0.75} Ba _{0.25} Nb ₂ O ₆	0.633	0.47	—	—	46
Sr _{0.5} Ba _{0.5} Nb ₂ O ₆	0.633	0.23	—	—	46
TeO ₂	0.633	0.240	-0.17	-0.046	47
TiO ₂ (rutile)	0.633	-0.057	-0.009	-0.060	48

Tetragonal Crystals; Point Groups 4, -4, 4/m

Material	Wavelength (μm)	Elastooptic coefficients				
		p ₁₁	p ₁₂	p ₁₃	p ₁₆	p ₃₁
CdMoO ₄	0.633	0.12	0.10	0.13	—	0.11
PbMoO ₄	0.633	0.24	0.24	0.255	0.017	0.175
NaBi(MoO ₄) ₂	0.633	0.243	0.205	0.25	—	0.21

Tetragonal Crystals; Point Groups 4, -4, 4/m—continued

Material	Wavelength (μm)	Elastooptic coefficients					
		p ₃₃	p ₄₄	p ₄₅	p ₆₁	p ₆₆	Ref.
CdMoO ₄	0.633	0.18	—	—	—	—	49
PbMoO ₄	0.633	0.300	0.067	-0.01	0.013	0.05	52
NaBi(MoO ₄) ₂	0.633	0.29	—	—	—	—	—

Hexagonal Crystals; Point Groups mmc, 6mm

Material	Wavelength (μm)	Elastooptic coefficients					
		p ₁₁	p ₁₂	p ₁₃	p ₃₁	p ₃₃	p ₄₄
Be ₃ Al ₂ Si ₆ O ₁₈	0.589	0.0099	0.175	0.191	0.313	0.023	-0.152
CdS	0.633	-0.142	-0.066	-0.057	-0.041	-0.20	-0.099
ZnO	0.633	±0.222	±0.099	-0.111	±0.088	-0.235	0.0585
ZnS	0.633	-0.115	0.017	0.025	0.0271	-0.13	-0.0627

Orthorhombic Crystals; Point Groups 222, m22, mmm

Material	Wavelength (μm)	Elastooptic coefficients					
		p ₁₁	p ₁₂	p ₁₃	p ₂₁	p ₂₂	p ₂₃
Al ₂ SiO ₄	—	-0.085	0.069	0.052	0.095	-0.120	0.065
(OH,F) ₂							
BaSO ₄	0.589	0.21	0.25	0.16	0.34	0.24	0.19
HIO ₃	0.633	0.302	0.496	0.339	0.263	0.412	0.304
NaKC ₄ H ₄ O ₆	0.589	0.35	0.41	0.42	0.37	0.28	0.34
NH ₄ ClO ₄	0.633	—	0.24	0.18	0.23	—	0.20
(NH ₄) ₂ SO ₄	0.633	0.26	0.19	±0.260	±0.230	±0.27	±0.254

Orthorhombic Crystals; Point Groups 222, m22, mmm –continued

Material	Elastooptic coefficients					
	p ₃₁	p ₃₂	p ₃₃	p ₄₄	p ₅₅	p ₆₆
Al ₂ SiO ₄ (OH,F) ₂	0.095	0.085	-0.083	-0.095	-0.031	0.098
BaSO ₄	0.28	0.22	0.31	0.002	-0.012	0.037
HIO ₃	0.251	0.345	0.336	0.084	-0.030	0.098
NaKC ₄ H ₄ O ₆	0.36	0.35	0.36	-0.030	0.0046	-0.025
NH ₄ ClO ₄	0.19	0.18	±0.02	<±0.02	—	±0.04
(NH ₄) ₂ SO ₄	0.20	±0.26	0.26	0.015	±0.0015	0.012

Rare Gas Crystals

Rare Gas	Elastooptic coefficients				Ref.
	p_{11}	p_{12}	p_{44}	$p_{11} - p_{12}$	
Ne (T = 24.3 K)	0.157	0.168	0.004	-0.011	59
Ar (T = 82.3 K)	0.256	0.302	0.015	-0.046	60
Kr (T = 115.6 K)	0.34	0.34	0.037	—	59
Xe (T = 160.5 K)	0.284	0.370	0.029	-0.086	60

Measured made at a wavelength of 488 nm.

References:

- Petterson, H. E., *J. Opt. Soc. Am.*, 63, 1243 (1973).
- Burstein, E. and Smith, P. L., *Phys. Rev.*, 74, 229 (1948).
- Pakhnev, A. V., et al., *Sov. Phys. J. (transl.)*, 18, 1662 (1975).
- Feldman, A., Horovitz, D., and Waxler, R. M., *Appl. Opt.*, 16, 2925 (1977).
- Iyengar, K. S., *Nature (London)*, 176, 1119 (1955).
- Bansigir, K. G. and Iyengar, K. S., *Acta Crystallogr.*, 14, 727 (1961).
- Pakhev, A. V., et al., *Sov. Phys. J. (transl.)*, 20, 648 (1975).
- Bansigir, K. G., *Acta Crystallogr.*, 23, 505 (1967).
- Krishna Rao, K. V. and Krishna Murty, V. G., *Ind. J. Phys.*, 41, 150 (1967).
- Weil, R. and Sun, M. J., *Proc. Int. Symp. CdTe (Detectors)*, XIX-1 Strasbourg, (1972).
- Schmidt, E. D. D. and Vedam, K., *J. Phys. Chem. Solids*, 27, 1563 (1966).
- Biegelsen, D. K., et al., *Phys. Rev. B*, 14, 3578 (1976).
- Hellwege, K. H., *Landolt-Börnstein, New Series III/II* (Springer–Verlag Berlin, 1979).
- Feldman, A., Waxler, R. M., and Horovitz, D., *J. Appl. Phys.*, 49, 2589 (1978).
- Dixon, R. W., *J. Appl. Phys.*, 38, 5149 (1967).
- Shabin, O. V., et al., *Sov. Phys. Solid State (transl.)*, 13, 3141 (1972).
- Reintjes, J. and Schultz, M. B., *J. Appl. Phys.*, 39, 5254 (1968).
- Rivoallan, L. and Favre, F., *Opt. Commun.*, 8, 404 (1973).
- Rivoallan, L. and Favre, F., *Opt. Commun.*, 11, 296 (1974).
- Afanasev, I. I., et al., *Sov. J. Opt. Technol.*, 46, 663 (1979).
- Rand, S. C., et al., *Phys. Rev. B*, 19, 4205 (1979).
- Sipe, J. E., *Can J. Phys.*, 56, 199 (1978).
- Christyi, I. L., et al., *Sov. Phys. Solid State (transl.)*, 17, 922 (1975).
- Narasimhamurty, T. S., *Curr. Sci. (India)*, 23, 149 (1954).
- Smith, T. M. and Korpel, A., *IEEE J. Quant. Electron.*, QE-1, 283 (1965).
- Narasimhamurty, T. S., *Proc. Indian Acad. Sci.*, A40, 164 (1954).
- Rabman, A., *Bhagarantam Commem. Vol.*, Bangalore Print. and Publ., 173 (1969).
- Eppendahl, R., *Ann. Phys. (IV)*, 61, 591 (1920).
- Laurenti, J. P. and Rouzeyre, M., *J. Appl. Phys.*, 52, 6484 (1981).
- Sasaki, H., et al., *J. Appl. Phys.*, 47, 2046 (1976).
- Uchida, N. and Saito, S., *J. Appl. Phys.*, 43, 971 (1972).
- Waxler, R. M. and Farabaugh, E. M., *J. Res. Natl. Bur. Stand.*, A74, 215 (1970).
- Nelson, D. F., Lazay, P. D., and Lax, M., *Phys. Rev.*, B6, 3109 (1972).
- O'Brien, R. J., Rosasco, G. J., and Weber, A., *J. Opt. Soc. Am.*, 60, 716 (1970).
- Avakyants, L. P., et al., *Sov. Phys.*, 18, 1242 (1976).
- Sapriel, J., *Appl. Phys. Lett.*, 19, 533 (1971).
- Narasimhamurty, T. S., *J. Opt. Soc. Am.*, 59, 682 (1969).
- Zubrinov, I. I., et al., *Sov. Phys. Solid State (transl.)*, 15, 1921 (1974).

39. Kachalov, O. V. and Shpilko, I. O., *Sov. Phys. JETP (transl.)*, 35, 957 (1972).
40. Narasimhamurty, T. S., et al., *J. Mater. Sci.*, 8, 577 (1973).
41. Tada, K. and Kikuchi, K., *Jpn. J. Appl. Phys.*, 19, 1311 (1980).
42. Aleksandrov, K. S., et al., *Sov. Phys. Solid State (transl.)*, 19, 1090 (1977).
43. Afanasev, I. I., et al., *Sov. Phys. Solid State (transl.)*, 17, 2006 (1975).
44. Silvestrova, I. M., et al., *Sov. Phys. Cryst. (transl.)*, 20, 649 (1975).
45. Veerabhadra Rao, K. and Narasimhamurty, T. S., *J. Mater. Sci.*, 10, 1019 (1975).
46. Venturini, E. L., et al., *J. Appl. Phys.*, 40, 1622 (1969).
47. Vehida, N. and Ohmachi, Y., *J. Appl. Phys.*, 40, 4692 (1969).
48. Grimsditch, M. H. and Ramdus, A. K., *Phys. Rev. B*, 22, 4094 (1980).
49. Schinke, D. P. and Viehman, W., unpublished data.
50. Coquin, G. A., et al., *J. Appl. Phys.*, 42, 2162 (1971).
51. Vasquez, F., et al., *J. Phys. Chem. Solids*, 37, 451 (1976).
52. Luspin, Y. and Hauret, G., *C.R. Ac. Sci. Paris*, B274, 995 (1972).
53. Narasimhamurty, T. S., *Phys. Rev.*, 186, 945 (1969).
54. Haussühl, S. and Weber, H. J., *Z. Kristallogr.*, 132, 266 (1970).
55. Vedam, K., *Proc. Ind. Ac. Sci.*, A34, 161 (1951).
56. Yano, T., Fukumoto, A., and Watanabe, A., *J. Appl. Phys.*, 42, 3674 (1971).
57. Manenkov, A. A. and Ritus, A. I., *Sov. J. Quant. Electr.*, 8, 78 (1978).
58. Eschler, H. and Weidinger, F., *J. Appl. Phys.*, 46, 65 (1975).
59. Rand, S. C., Rao, B. S., Enright, G. D., and Stoicheff, B. P., *Phys. Rev. B*, 19, 4205 (1979).
60. Sipe, J. E., *Can. J. Phys.*, 56, 199 (1978).

1.8.2 Acoustooptic Materials

A figure of merit for an acoustooptic material is $M = n^6 p^2 / \rho v^3$, where n is the refractive index, p is the photoelastic constant, ρ is the density, and v is the sound velocity.

Properties of Selected Acoustooptic Materials

Material	Transparency range (μm)	Acoustic mode/ direction	Acoustic velocity ((km/s))	Figure of merit
Ge	2–20	L <111>	5.5	840
Hg ₂ Br ₂	0.40–30	S <110>	0.273	2600
Hg ₂ Cl ₂	0.36–20	S <110>	0.347	700
Hg ₂ I ₂	0.45–40	S <110>	0.254	3200
LiNbO ₃	0.35–5.0	L <100>	6.5	4.6
PbBr ₂	0.36–60	S <010>	2.30	550
PbCl ₂	0.35–20	S <001>	2.51	136
PbMoO ₄	0.42–5.5	L <001>	3.63	36.3
SiO ₂	0.12–4.5	L <100>	5.72	2.38
TeO ₂	0.35–5.0	L <001>	4.2	34.5
		S <110>	0.62	793
Tl ₃ AsS ₃	1.3–17	L <001>	2.15	416

All measurements at 0.633 μm , except for Ge at 10.6 μm ; L = longitudinal, S = shear.

Reference:

Gottlieb, M. and Singh, N. B., Elastooptic materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 416.

1.9 Nonlinear Optical Properties

1.9.1 Nonlinear Refractive Index*

Nonlinear refraction is commonly defined either in terms of the optical field intensity I

$$n = n_0 + \gamma I$$

or in terms of the average of the square of the optical electric field $\langle E^2 \rangle$

$$n = n_0 + n_2 \langle E^2 \rangle,$$

where n_0 is the ordinary linear refractive index, γ is the nonlinear refractive coefficient, and n_2 is the nonlinear refractive index. The conversion between n_2 and γ is given by

$$n_2 [\text{cm}^3/\text{erg}] = (c n_0 / 40\pi) \gamma [\text{m}^2/\text{W}] = 238.7 n_0 \gamma [\text{cm}^2/\text{W}],$$

where c is the speed (in m/s) of light in vacuum.

In terms of third-order susceptibility tensor $\chi^{(3)}(-\omega, \omega, \omega, -\omega)$ of the medium, the nonlinear refractive indices for a linearly polarized wave and a circularly polarized wave in an isotropic material are

$$n_2(\text{LP}) = (12\pi/n_0)\chi_{1111}^{(3)}(-\omega, \omega, \omega, -\omega)$$

and

$$n_2(\text{CP}) = (24\pi/n_0)\chi_{1122}^{(3)}(-\omega, \omega, \omega, -\omega).$$

Whereas in a cubic material the linear refractive index is isotropic, n_2 is not. If θ is the angle made by the electric field vector with the [100] axis for a wave propagating along, say, [001], the effective value of $\chi^{(3)}$ is given by

$$n_2(\theta) = 12\pi/n_0 \left\{ \chi_{1111}^{(3)} [1 + \sigma \sin(\theta)^2/2] \right\},$$

where

$$\sigma = [\chi_{1111}^{(3)} - \chi_{1122}^{(3)} + 2\chi_{1212}^{(3)}]/\chi_{1111}^{(3)}.$$

For a circularly polarized beam propagating along [100]

$$n_2(\text{CP}, 100) = 6\pi/n_0 [\chi_{1111}^{(3)} + 2\chi_{1122}^{(3)} - \chi_{1212}^{(3)}]$$

and for a circularly polarized beam propagating along [111]

$$n_2(\text{CP}, 111) = 4\pi/n_0 [\chi_{1111}^{(3)} + 4\chi_{1122}^{(3)} - \chi_{1212}^{(3)}].$$

The nonlinear refractive index is not a unique quantity for a given material because several physical mechanisms contribute to the polarization that is cubic in the applied optical elec-

* This section was adapted from Chase, L. L. and Van Stryland, E. W., Nonlinear Refractive index: inorganic materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 269.

ric field. These physical mechanisms require a material response that can take place on various time scales. The mechanisms that contribute most strongly to n_2 , and their characteristic time scales (in parentheses) are bound electrons (10^{-15} s), optically created free carriers ($>10^{-12}$ s), Raman-active optical phonons (10^{-12} s), electrostriction ($>10^{-9}$ s), and thermal excitation ($\sim 10^{-9}$ s).

Several methods listed below have been employed to measure n_2 . The details of the measurements determine the relative contributions from the various possible physical mechanisms to the measured n_2 . In general, experiments done with picosecond pulses and nondegenerate mixing are less likely to be affected by the “slow” electrostrictive or thermal effects than those done in the nanosecond pulse regime and with degenerate mixing. Most of the measurements include the effects of both electronic and vibrational (Raman) contributions to n_2 .

Techniques for Measuring the Nonlinear Refractive Index

	Method	Ref.
DFWM	Degenerate four-wave mixing	2
DHG	Dynamic holographic grating	3
DTLC	Damage threshold for linear vs. circular polarization	4
ER	Ellipse rotation	5
KE	DC Kerr effect	6
NDFWM	Nondegenerate four-wave mixing	7,8
OKE	Optical Kerr effect	9
PDF	Power-dependent focus	10
PST	Power for self-trapping	11
RSS	Raman scattering spectroscopy	12
SFL	Self-focal length	13
SPA	Spatial profile analysis	14
SPM	Self-phase modulation	15
SSMG	Small-scale modulation growth	16
TBI	Two-beam interferometry	17
TII	Time-integrated interferometry	18
TRI	Time-resolved interferometry	19
TWR	Temporal waveform reshaping	20
WFC	Wavefront conjugation	21
ZS	Z-scan	22

In the following tables of nonlinear refractive parameters, values in parentheses were calculated by Chase and Van Stryland¹ from the quantities reported in the original references. Refractive indices in parentheses were obtained from extrapolation of available data. For noncubic crystals, or for cubic crystals where the polarization is not along a cube axis or is not specified in the original reference, the value tabulated for $\chi^{(3)}_{1111}$ is an effective value of $\chi^{(3)}$. Unless noted otherwise, measurements were made at room temperature.

Measured Nonlinear Refractive Parameters

Crystals	Method	Pulse duration	Linear				γ_{LP} ($10^{-16} \text{ cm}^2/\text{W}$)	Ref.
		(ns)	(nm)	refractive index	χ_{1111} ($10^{-13} \text{ cm}^3 \text{ erg}$)	$n_{2,LP}$ ($10^{-13} \text{ cm}^3 \text{ erg}$)		
AgCl	NDFWM	3	1064	2.02	(1.25)	23.3	(48.3)	23 ^a
Al ₂ O ₃	PDF	0.17	308	(1.814)	(0.088)	(1.82)	4.2	24
Al ₂ O ₃	ZS	0.02	532	1.8	(0.066)	(1.4)	3.3	25
Al ₂ O ₃	ZS	0.028	1064	1.75	(0.056)	(1.2)	2.9	25
Al ₂ O ₃	ZS	0.016	355	1.8	(0.076)	(1.6)	3.7	25
Al ₂ O ₃	NDFWM	3	560, 590	(1.76)	(0.11)	2.4	(5.7)	8
Al ₂ O ₃	PDF	0.030	1064	(1.76)	(0.060)	1.3	(3.1)	26
Al ₂ O ₃ (E c)	NDFWM	3	1064	1.75	(0.060)	1.3	(3.11)	7
Al ₂ O ₃ (E⊥c)	NDFWM	3	1064	1.75	(0.057)	1.23	(2.94)	7
Al ₂ O ₃ :Cr	TRI	~1	1064	1.76	(0.069)	1.48	(3.52)	27
AlGaAs	TRI	—	850–810	NA	—	-(2.2–3.3) × 10 ⁴	—	28 ^b
BaF ₂	ZS	0.027	532	(1.476)	(0.031)	0.8	(2.27)	29
BaF ₂	PDF	0.017	308	(1.500)	(0.077)	(1.94)	5.42	24
BaF ₂	NDFWM	4	592, 575	(1.47)	0.069	(1.8)	(5.0)	30
BaF ₂	TRI	0.125	1064	1.47	(0.39)	(1.00)	2.85	32
BaF ₂ (100)	DFWM	0.3	1064	1.468	(0.026)	0.67	(1.91)	7
BaF ₂ (100)	ZS	0.028	1064	1.47	0.019	(0.5)	1.4	25
BaF ₂ (100)	ZS	0.02	532	1.48	0.029	(0.73)	2.1	25
BaF ₂ (100)	ZS	0.016	355	1.5	0.039	(0.97)	2.7	25
BeAl ₂ O ₄	NDFWM	3	1064	1.73	(0.67)	1.46	(3.54)	7
Bi ₁₂ SiO ₂₀	OKE	1.5×10^{-4}	532	—	—	5	—	33
C (diamond)	NDFWM	4	545, 545-ε	(2.42)	0.46	(7.2)	(12.6)	31 ⁿ
CaCO ₃	NDFWM	3	560, 590	(1.66)	(0.14)	3.2	(8.1)	28 ^c

Measured Nonlinear Refractive Parameters—*continued*

Crystals	Method	Pulse duration	Wavelength	Linear refractive index	χ_{1111} ($10^{-13} \text{ cm}^3 \text{ erg}$)	$n_{2,\text{LP}}$ ($10^{-13} \text{ cm}^3 \text{ erg}$)	γ_{LP} ($10^{-16} \text{ cm}^2/\text{W}$)	Ref.
		(ns)	(nm)					
CaCO ₃ (E c)	NDFWM	3	1064	1.48	(0.033)	0.83	(2.35)	23
CaCO ₃ (E ⊥ c)	NDFWM	3	1064	1.643	(0.048)	1.11	(2.83)	23
CaF ₂	PDF	0.017	308	(1.453)	(0.026)	(0.67)	1.92	24
CaF ₂	NDFWM	4	592, 575	(1.43)	0.04	(1.1)	(3.1)	30
CaF ₂	NDFWM	3	560, 590	(1.43)	(0.055)	1.46	(4.3)	8
CaF ₂	TRI	0.125	1064	1.43	(0.025)	0.65	1.90	32,34
CaF ₂	PDF	0.030	1064	1.43	0.105	2.8	(8.1)	10
CaMg ₂ Si ₂ O ₆	NDFWM	3	1064	1.67	(0.077)	1.73	(4.34)	7
CaO (100)	NDFWM	3	1064	1.83	(0.25)	5.2	(11.9)	7
CaWO ₄ (E ⊥ c)	NDFWM	3	1064	1.89	(0.25)	4.2	(9.3)	7
CaWO ₄ (E c)	NDFWM	3	1064	1.91	(0.28)	5.6	(12.3)	7
CdF ₂	NDFWM	4	575, 575-ε	(1.57)	0.145	(3.48)	(9.29)	31
CdF ₂	TRI	0.125	1064	1.57	(0.061)	(1.46)	3.87	32
CdF ₂ (100)	NDFWM	3	1064	1.56	(0.16)	3.95	(10.6)	7
CdS	ZS	0.03	532	2.34	(−211)	−3400	(−6090)	35
CdS	SPA	20	694	(2.42)	(130)	2×10^3	(3.5×10^3)	36
CdS (E c)	NDFWM	3	1064	2.34	(17.5)	283	(507)	7
CdS(E ⊥ c)	NDFWM	3	1064	2.33	(18.8)	304	(547)	7
CdS _{0.18} Se _{0.82}	SPA	20	694	(2.6)	(1500)	2.2×10^4	(3.5×10^4)	36
CdS _{0.5} Se _{0.5}	ZS	0.03	1064	2.45	(65)	1000	(1710)	35
CdS _{0.5} Se _{0.5}	SPA	20	694	(2.5)	(230)	3.5×10^3	(5.9×10^3)	36
CdSe	ZS	0.03	1064	2.56	(−6.1)	−90	(−147)	35
CdTe	ZS	0.04	1064	2.84	(−150)	−2000	(−3000)	35

CdTe	DFWM	0.04	1064	2.84	± 150	± 2100	± 3100	37d
CdTe	WFC	15	1064	~ 3	2.5×10^5	(3.1×10^6)	(4.4×10^6)	38
CeF ₃	NDFWM	3	1064	~ 1.6	(0.055)	1.3	(3.4)	7
CeF ₃	TRI	0.125	1064	~ 1.6	(0.066)	(1.55)	4.06	32
CsCl	NDFWM	0.006	1064, 532	(1.64)	0.086	(2.0)	(5.1)	39
CsCl	NDFWM	0.006	1064, 532	—	0.029	—	—	39e
CuCl	NDFWM	—	773, 694	(1.94)	33	640	1400	40m
Er ₂ O ₃	NDFWM	3	1064	1.96	(0.24)	4.53	(9.7)	7
Ga ₂ O ₃	NDFWM	3	1064	1.96	(0.30)	5.8	(12.4)	7
GaAs	ZS	0.03	1064	3.47	(~249)	~2700	(~3260)	35
GaAs	NDFWM	~200	9200–11800	(3.3)	120	(1.4×10^3)	(1.7×10^3)	41
GaP	TDFWM	2.7×10^{-3}	577	(3.396)	2.1×10^3	(2.33×10^4)	(2.87×10^4)	42
Gd ₃ Ga ₅ O ₁₂	NDFWM	3	1064	1.945	(0.30)	5.8	(12.5)	7
Gd ₃ Sc ₂ Al ₃ O ₁₂	NDFWM	3	1064	1.891	(0.20)	4.0	(8.9)	7
Gd ₃ Sc ₂ Ga ₃ O ₁₂	NDFWM	3	1064	1.943	(0.28)	5.5	(11.9)	7
Ge	ZS	0.06	10600	3.47	(290)	2700	(2800)	35
Ge	NDFWM	~200	9200–11800	4.	1000	(9.4×10^3)	(9.9×10^3)	41
Ge	ER	2.3	10590	(4.)	250	(2.3×10^3)	(2.5×10^3)	43
Ge	NDFWM	—	10600	4.	—	—	—	44f
Ge	WFC	300	38000	4.0	400	(3.8×10^3)	(3.9×10^3)	45
HgCdTe	SPA	CW	10640	4.25	—	$[n = -7 \times 10^{-3} I^{1/3}]$	—	46g
InSb	SPA	CW	5313	(4)	$(-6. \times 10^{10})$	$(-6. \times 10^{11})$	-6×10^{11}	47l
InSb	SPA	CW	5405–5714	(4)	—	100	—	48h
InSb	NDFWM	—	10600	(4)	$\sim 2 \times 10^6$	$(\sim 2 \times 10^7)$	$(\sim 2 \times 10^7)$	49i
KBr	NDFWM	3	1064	1.544	(0.12)	2.93	(8.0)	7
KBr	PDF	0.030	1064	1.544	0.58	14.2	(38.5)	10
KCl	NDFWM	3	1064	1.479	(0.079)	2.01	(5.7)	7
KCl	PDF	0.030	1064	1.479	0.13	3.3	(9.3)	59

Measured Nonlinear Refractive Parameters—*continued*

Crystals	Method	Pulse duration	Wavelength	Linear refractive index	χ_{1111} (10^{-13} cm^3 erg)	$n_{2,\text{LP}}$ (10^{-13} cm^3 erg)	γ_{LP} ($10^{-16} \text{ cm}^2/\text{W}$)	Ref.
		(ns)	(nm)					
KF	NDFWM	0.006	1064, 532	(1.36)	0.014	(0.39)	(1.2)	39
KF	NDFWM	0.006	1064, 532	—	0.020	—	—	39e
KH_2PO_4	TRI	0.10	1064	(1.49)	(0.040)	1.0	(2.8)	34
KH_2PO_4	PDF	0.030	1064	1.49	0.14	3.6	(10)	7
$\text{KH}_2\text{PO}_4 (c)$	NDFWM	3	1064	1.460	(0.028)	0.72	(2.1)	7
$\text{KH}_2\text{PO}_4 (\perp c)$	NDFWM	3	1064	1.494	(0.031)	0.78	(2.2)	7
KI	NDFWM	0.006	1064, 532	(1.7)	0.38	(8.4)	(20)	39
KI	NDFWM	0.006	1064, 532		0.13	—	—	39e
KI	PDF	0.030	1064	1.638	0.49	11.2	(29)	10
KTaO_3	NDFWM	3	1064	2.25	(1.73)	29	(54)	7
KTiOPO_4	NDFWM	3	1064	1.74	(0.26)	5.73	(13.8)	7
KTiOPO_4	ZS	0.04	1064	1.78	(0.47)	(10)	24	50
$\text{La}_2\text{Be}_2\text{O}_5:\text{Nd}$	PDF	0.030	1064	(1.98)	(0.11)	2.1	(4.4)	26
$\text{La}_3\text{Lu}_2\text{Ga}_3\text{O}_{12}$	NDFWM	3	1064	1.930	(0.30)	5.8	(12.6)	10
LaF_3	TRI	0.125	1064	1.60(o)	(0.064)	1.51	3.95	86
$\text{LaF}_3 (c)$	NDFWM	3	1064	1.60	(0.059)	1.4	(3.7)	7
LAP, x + z	NDFWM	3	1064	1.51	(0.12)	3.0	(8.4)	7
LAP,y	NDFWM	3	1064	1.559	(0.077)	1.87	(5.0)	7
LiCl	NDFWM	0.006	1064,532	(1.67)	0.069	(1.56)	(3.9)	39
LiCl	NDFWM	0.006	1064,532	—	0.027	—	—	39e
LiF	ZS	0.028	1064	1.39	(0.01)	(0.27)	(0.81)	51
LiF	ZS	0.02	532	1.4	(0.011)	(0.3)	0.9	51
LiF	NDFWM	3	560, 590	(1.39)	(0.034)	0.92	(2.8)	8
LiF	TRI	0.125	1064	1.39	(0.013)	0.35	1.05	32,34

LiNbO ₃	NDFWM	5	577	(2.31(o))	—	—	—	52
LiYF ₄	TRI	0.125	1064	1.45(o)	(0.023)	0.60	1.72	32
MgAl ₂ O ₄	NDFWM	3	1064	1.72	(0.068)	1.5	(3.65)	7
MgF ₂	NDFWM	3	1064	1.374	(0.0091)	0.25	(0.76)	7
MgF ₂	ZS	0.028	1064	1.38	(0.0073)	(0.20)	0.61	51
MgF ₂	ZS	0.02	532	1.38	(0.008)	(0.22)	0.67	51
MgF ₂	ZS	0.016	355	1.4	(0.0085)	(0.23)	0.69	25
MgF ₂	TRI	0.125	1064	1.37(o)	(0.011)	0.30	0.92	32,34
MgO	NDFWM	3	1064	1.72	(0.073)	1.61	(3.92)	7
NaBr	NDFWM	3	1064	1.623	(0.14)	3.26	(8.41)	7
NaBr	PDF	0.030	1064	1.62	0.41	9.6	(25)	10
NaCl	NDFWM	3	1064	1.531	(0.065)	1.59	(4.35)	7
NaCl	PDF	0.030	1064	1.532	0.26	6.5	(18)	10
NaF	NDFWM	3	1064	1.321	(0.012)	0.34	(1.1)	7
NaF	TRI	0.125	1064	1.32	(0.015)	0.43	1.37	32
NaF	PDF	0.030	1064	1.321	0.03	0.9	(2.9)	10
PbF ₂	TRI	0.125	1064	1.76	(0.23)	4.94	11.7	32
Si	NDFWM	~200	9200–11800	(3.4)	60	660.	(820)	41
SiC	SPA,TWR	20	694	2.68	(36)	510	(800)	53
SiO ₂ ($\perp c$)	NDFWM	3	1064	1.534	(0.046)	1.12	(3.06)	7
SiO ₂ ($\parallel c$)	NDFWM	3	1064	1.543	(0.047)	1.16	(3.15)	7
SrF ₂	NDFWM	3	1064	1.433	(0.019)	0.50	(1.46)	7
SrF ₂	NDFWM	4	592, 575	(1.43)	0.052	(1.4)	(4.0)	30
SrF ₂	TRI	0.125	1064	1.43	(0.023)	0.60	1.76	32
SrO (110)	NDFWM	3	1064	1.81	(0.24)	5.07	(11.7)	7
SrTiO ₃	NDFWM	3	1064	2.31	(1.63)	26.7	(48)	7
TiO ₂	NDFWM	3	1064	2.48	(3.67)	55.8	(94)	7
TiO ₂	DFWM	0.08	1064	(2.48)	(7.75)	(118)	200	2

Measured Nonlinear Refractive Parameters—*continued*

Crystals	Method	Pulse	Linear			χ_{1111} (10^{-13} cm^3 erg)	$n_{2,\text{LP}}$ (10^{-13} cm^3 erg)	γ_{LP} ($10^{-16} \text{ cm}^2/\text{W}$)	Ref.
		duration (ns)	Wavelength (nm)	refractive index					
Y ₂ O ₃	NDFWM	3	1064	1.92	(0.27)	5.33	(11.6)	7	
Y ₃ Al ₅ O ₁₂	TRI	0.15	1064	(1.83)	(0.15)	3.16	(7.2)	54 ⁱ	
Y ₃ Al ₅ O ₁₂	NDFWM	3	560,590	(1.83)	(0.22)	4.5	(10)	8	
Y ₃ Al ₅ O ₁₂	TRI	~1	1064	1.83	(0.17)	3.47	(7.9)	27	
Y ₃ Al ₅ O ₁₂	ER	13	694	1.829	(0.21)	4.27	(9.8)	5 ^k	
Y ₃ Al ₅ O _{12:Nd}	PDF	0.030	1064	1.82	0.17	3.5	(8.1)	7	
Y ₃ Ga ₅ O ₁₂	NDFWM	3	1064	1.912	(0.26)	5.2	(11.4)	7	
YAlO ₃	NDFWM	3	1064	1.933	(0.17)	3.37	(7.3)	7	
ZnO (E \perp χ)	NDFWM	3	1064	1.99	(1.32)	25	(53)	7	
ZnO (E \parallel c)	NDFWM	3	1064	1.96	(1.20)	23	(49)	7	
ZnS	ZS	0.03	1064	2.40	(3.1)	48	(84)	35	
ZnS (E \parallel c)	NDFWM	3	1064	2.29	(2.98)	49	(90)	7	
ZnS (E \perp c)	NDFWM	3	1064	2.29	(2.85)	47	(87)	7	
ZnSe	ZS	0.03	1064	2.48	(11)	170	(290)	35	
ZnSe	DFWM	0.04	1064	2.48	18	(270)	(460)	37	
ZnSe	ZS	0.03	532	2.70	(−29)	−400	(−621)	35	
ZnSe	DFWM	0.03	532	2.70	±30	(±420)	(±650)	37 ^d	
ZnTe	ZS	0.03	1064	2.79	(61)	830	(1250)	35	
ZrO ₂	SFL	0.045	1064	(1.92)	(0.41)	8	(17)	55	
ZrO ₂	SFL	0.03	1064	(1.92)	(0.31)	6	(12.9)	56	
ZrO ₂	NDFWM	3	1064	2.12	(0.33)	5.8	(11.5)	7	

^a polycrystalline sample; ^b wavelength dependent; ^c E \parallel optic axis; ^d absolute values measured; ^e in 5 mol/O acq. sc; ^f relative spect; impurity; 175 K, I in W/cm²; ^g 175 K, I in W/cm²; ^h 77 K, free electrons; ⁱ 4 K, free electrons; ^j 4 K \parallel [111]; ^k E \parallel [100]; ^l 5 K, free electrons; ^m 15 K; ⁿ dispersion also given.

Dispersion of the Nonlinear Refractive Index^{*}

Material	Energy gap (eV)	$n_2 \times 10^{-14}$ esu			
		266 nm	355 nm	532 nm	1064 nm
LiF	13.6	4.0 ± 1.0	1.9 ± 0.4	1.9 ± 0.4	2.5 ± 0.5
MgF ₂	10.8	5.0 ± 1.0	2.2 ± 0.4	1.9 ± 0.4	1.9 ± 0.4
BaF ₂	9.1	11 ± 2	9.7 ± 1.9	7.5 ± 1.5	5.0 ± 1.0
SiO ₂	8.4	28 ± 6	8.5 ± 1.7	7.8 ± 1.6	7.4 ± 1.5
Al ₂ O ₃	9.9	26 ± 5	16 ± 3	14 ± 3	13 ± 3
BaB ₂ O ₄	6.2	1 ± 0.3	14 ± 3	21 ± 4	11 ± 2
KBr	7.6	—	—	47 ± 9	29 ± 6
CaCO ₃	5.9	46 ± 9	14 ± 3	11 ± 2	11 ± 2
LiNbO ₃	4.0	—	—	440 ± 70	48 ± 7
KTiOPO ₄	3.5	—	—	98 ± 15	100 ± 20

* DeSalvo, R., Said, A. A., Hagan, D. J., Van Stryland, E. W., and Sheik-Bahae, M., Infrared to ultraviolet measurements of two-photon absorption and n_2 in wide bandgap solids, *IEEE J. Quantum Electron.* 32, 1324 (1996).

See also, Adair, R., Chase, L. L., and Payne, S. A., dispersion of the nonlinear refractive index of optical crystals, *Opt. Mater.* 1, 185 (1992).

References:

- Chase, L. L., and Van Stryland, E. W., Nonlinear refractive index: inorganic materials, in *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 269.
- Friberg, S. R., and Smith, P. W., Nonlinear optical glasses for ultrafast optical switches, *IEEE J. Quantum Electron.* QE-23, 2089 (1987).
- Odulov, S. G., Reznikov, Y. A., Soskin, M. S., and Khizhnyak, A. I., Photostimulated transformation of molecules—A new type of “giant” optical nonlinearity in liquid crystals, *Sov. Phys. JETP* 55(5), 854 (1982).
- Feldman, A., Horowitz, D., and Waxler, R. M., Mechanisms for self-focusing in optical glasses, *IEEE J. Quantum Electron.* QE-9, 1054 (1973).
- Owyong, A., Ellipse rotation studies in laser host materials, *IEEE J. Quantum Electron.* QE-9(11), 1064 (1973).
- Hellwarth, R. W., and George, N., Nonlinear refractive indices of CS₂-CCl₄ mixtures, *Opt. Electron.* 1, 213 (1969).
- Adair, R., Chase, L. L., and Payne, S. A., Nonlinear refractive index of optical crystals, *Phys. Rev. B* 39, 3337 (1989).
- Levenson, M. D., Feasibility of measuring the nonlinear index of refraction by third-order frequency mixing, *IEEE J. Quantum Electron.* QE-10(2), 110 (1974).
- Ho, P. P., and Alfano, R. R., Optical Kerr effect in liquids, *Phys. Rev. A* 20(5), 2170 (1979).
- Smith, W. L., Bechtel, J. H., and Bloembergen, N., Dielectric-breakdown threshold and nonlinear-refractive-index measurements with picosecond laser pulses, *Phys. Rev. B* 12, 706 (1975).
- Wang, C. C., Nonlinear susceptibility constants and self-focusing of optical beams in liquids, *Phys. Rev.* 152(1), 149 (1966).
- Yang, T. T., Raman scattering and optical susceptibilities of Nd-doped glasses, *Appl. Phys.* 11, 167 (1976).

13. Hongyo, M., Sasaki, T., and Yamanaka, C., Nonlinear effects of POCl_3 liquid laser, *Technol. Rep. Osaka Univ.* 23 (1121–1154), 455 (1973).
14. Bjorkholm, J. E. and Ashkin, A., cw self-focusing and self-trapping of light in sodium vapor, *Phys. Rev. Lett.* 32(4), 129 (1974).
15. Stolen, R. H., and Lin, C., Self-phase-modulation in silica optical fibers, *Phys. Rev. A* 17(4), 1448 (1978).
16. Smith, W. L., Warren, W. E., Vercimak, C. L., and White, W. T., III, Nonlinear refractive index at 351 nm by direct measurement of small-scale self-focusing, Paper FB4, *Digest of Conference on Lasers and Electro Optic*, (Optical Society of America, Washington, DC, 1983), p. 17.
17. Owyong, A., and Peercy, P. S., Precise characterization of the Raman nonlinearity in benzene using nonlinear interferometry, *J. Appl. Phys.* 48(2), 674 (1977).
18. Witte, K. J., Galanti, M., and Volk, R., n_2 -Measurements at 1.32 μm of some organic compounds usable as solvents in a saturable absorber for an atomic iodine laser, *Opt. Commun.* 34(2), 278 (1980).
19. Milam, D., and Weber, M. J., Measurement of nonlinear refractive-index coefficients using time-resolved interferometry: application to optical materials for high-power neodymium laser, *J. Appl. Phys.* 47(6), 2497 (1976).
20. Hanson, E. G., Shen, Y. R., and Wong, G. K. L., Experimental study of self-focusing in a liquid crystalline medium, *Appl. Phys.* 14, 65 (1977); Self-focusing: from transient to quasi-steady-state, *Opt. Commun.* 20(1), 45 (1977); Wong, G. K. L., and Shen, Y. R., Transient self-focusing in a nematic liquid crystal in the isotropic phase, *Phys. Rev. Lett.* 32(10), 527 (1974).
21. Grischkowsky, D., Shiren, N. S., and Bennett, R. J., Generation of time-reversed wave fronts using a resonantly enhanced electronic nonlinearity, *Appl. Phys. Lett.* 33(9), 805 (1978).
22. Sheik-Bahae, M., Said, A. A., Wei, T. H., Hagan, D. J., and Van Stryland, E. W., Sensitive measurement of optical nonlinearities using a single beam, *IEEE J. Quantum Electron.* 26, 760 (1990).
23. Adair, R., Chase, L. L., and Payne, S. A., Nonlinear refractive index of optical crystals, *Phys. Rev. B* 39, 3337 (1989).
24. Kim, Y. P., and Hutchinson, M. H. R., Intensity-induced nonlinear effects in UV window materials, *Appl. Phys. B* 49, 469 (1989).
25. Sheik-Bahae, M., DeSalvo, J. R., Said, A. A., Hagan, D. J., Soileau, M. J., and Van Stryland, E. W., Nonlinear refraction in UV transmitting materials, *Laser-Induced Damage in Optical Materials: 1991, SPIE 1624*, 25 (1992).
26. Smith, W. L., and Bechtel, J. H., Laser-induced breakdown and nonlinear refractive index measurements in phosphate glasses, lanthanum beryllate, and Al_2O_3 , *Appl. Phys. Lett.* 28, 606 (1976).
27. Moran, M. J., She, C. Y., and Carman, R. L., Interferometric measurements of the nonlinear refractive index coefficient relative to CS_2 in laser-system-related materials, *IEEE J. Quantum Electron. QE-11(6)*, 159 (1975).
28. LaGasse, M. J., Anderson, K. K., Wang, C. A., Haus, H. A., and Fujimoto, J. G., Femtosecond measurements of the nonresonant nonlinear index in AlGaAs , *Appl. Phys. Lett.* 56, 417 (1990).
29. Sheik-Bahae, M. Said, A. A., and Van Stryland, E. W., High-sensitivity, single-beam n_2 measurements, *Opt. Lett.* 14, 955 (1989).
30. Lynch, R. T., Jr., Levenson, M. D., and Bloembergen, N., Experimental test for deviation from Kleinman's symmetry in the third order susceptibility tensor, *Phys. Lett.* 50A(1), 61 (1974).
31. Levenson, M. D., and Bloembergen, N., Dispersion of the nonlinear optical susceptibility tensor in centrosymmetric media, *Phys. Rev. B* 10(10), 4447 (1974).
32. Milam, D., Weber, M. J., and Glass, A. J., Nonlinear refractive index of fluoride crystals, *Appl. Phys. Lett.* 31(12), 822 (1977).
33. Le Saux, G., Salin, F., Georges, P., Roger, G., and Brun, A., Measurement of the nonlinear index n_2 of BSO crystals, *Appl. Opt.* 27, 2812 (1988).

34. Milam, D., and Weber, M. J., Time-resolved interferometric measurements of the nonlinear refractive index in laser materials, *Opt. Commun.* 18(1), 172 (1976).
35. Sheik-Bahae, M., Said, A. A., Wei, T. H., Wu, Y. Y., Hagan, D. J., Soileau, M. J., and Van Stryland, E. W., Z-scan: a simple and sensitive technique for nonlinear refraction measurements, *SPIE* 1148, 41 (1989).
36. Borshch, A. A., and Brodin, M. S., Nonlinear polarizability of some binary and mixed semiconductors, *Bull. Acad. Sci. U.S.S.R. Phys. Ser. (USA)* 43(2), 98 (1978); Borshch, A. A., Brodin, M. S., Krupa, N. N., Lukomiskii, V. P., Pisarenko, V.G., Petropavovskii, A.I., and Chernyi, V.V., Determination of the coefficients of the nonlinear refractive index of a CdS crystal by the nonlinear refraction method, *Sov. Phys. JETP* 48(1), 41 (1978).
37. Canto-Said, E. J., Hagan, D. J., Young, J., and Van Stryland, E. W., Degenerate four-wave mixing measurements of high-order nonlinearities in semiconductors, *IEEE J. Quantum Electron.* 27, 2274 (1991).
38. Kremenetskii, V., Odulov, S., and Soskin, M., Backward degenerate four-wave mixing in cadmium telluride, *Phys. Status Solidi (A)* 57, K71 (1980).
39. Penzkofer, A., Schmailzi, J., and Glas, H., Four-wave mixing in alkali halide crystals and aqueous solutions, *Appl. Phys. B* 29, 37 (1982).
40. Kramer, S. D., Parson, F. G., and Bloembergen, N., Interference of third-order light mixing and second-harmonic exciton generation in CuCl, *Phys. Rev. B* 9(4), 1853 (1974).
41. Wynne, J. J., Optical third-order mixing in GaAs, Ge, Si, InAs, *Phys. Rev.* 178, 1295 (1969).
42. Rhee, B. K., Bron, W. E., and Kuhl, J., Determination of third-order nonlinear susceptibility $\chi^{(3)}$ through measurements in the picosecond time domain, *Phys. Rev. B* 30, 7358 (1984).
43. Watkins, D. E., Phipps, C. R., and Thomas, S. J., Determination of the third-order nonlinear optical coefficients of germanium through eclipse rotation, *Opt. Lett.* 5(6), 248 (1980).
44. Wood, R. A., Kahn, M. A., Wolff, P. A., and Aggarwal, R. L., Dispersion of the nonlinear optical susceptibility of N-type germanium, *Opt. Commun.* 21(1), 154 (1977).
45. Depatie, D., and Haueisen, D., Multiline phase conjugation at 4 μm in germanium, *Opt. Lett.* 5(6), 252 (1980).
46. Hill, J. R., Parry, G., and Miller, A., Nonlinear refractive index changes in CdHgTe at 175 K with 10.6 μm radiation, *Opt. Commun.* 43(2), 151 (1982).
47. Weaire, D., Wherrett, D. S., Miller, D. A. B., and Smith, S. D., Effect of low-power nonlinear refraction on laser-beam propagation in InSb, *Opt. Lett.* 4(10), 331 (1979).
48. Miller, D. A. B., Seaton, C. T., Prise, M. E., and Smith, S. D., Band-gap-resonant nonlinear refraction in III-V semiconductors, *Phys. Rev. Lett.* 47(3) (1981).
49. Yuen, S. Y., and Wolff, P. A., Difference-frequency variation of the free-carrier-induced, third-order nonlinear susceptibility in n-InSb, *Appl. Phys. Lett.* 40(6), 457 (1982).
50. DeSalvo, R., Hagan, D. J., Sheik-Bahae, M., Stegeman, G., and Van Stryland, E. W., Self-focusing and self-defocusing by cascaded second-order effects in KTP, *Opt. Lett.* 17, 28 (1992).
51. Van Stryland, E. W., Dispersion of n_2 in solids, *Laser-Induced Damage in Optical Materials: 1990*, *SPIE* 1441, 430 (1991).
52. Wynne, J. J., Nonlinear optical spectroscopy of $\chi^{(3)}$ in LiNbO₃, *Phys. Rev. Lett.* 29, 650 (1972).
53. Borshch, A. A., Brodin, M. S., and Volkov, V. I., Self-focusing of ruby-laser radiation in single-crystal silicon carbide, *Sov. Phys. JETP* 45(3), 490 (1977).
54. Bliss, E. S., Speck, D. R., and Simmons, W. W., Direct interferometric measurements of the nonlinear refractive index coefficient n_2 in laser materials, *Appl. Phys. Lett.* 25(12), 728 (1974).
55. Mansour, N., Soileau, M. J., and Van Stryland, E. W., Picosecond damage in Y₂O₃ stabilized zirconia, in *Laser-Induced Damage in Optical Materials*, National Bureau of Standards Special Publication 727 (National Bureau of Standards, Washington, DC, 1984), p. 31.
56. Guha, S., Mansour, N., and Soileau, M. J., Direct n_2 measurement in yttria stabilized cubic zirconia, in *Laser-Induced Damage in Optical Materials*, National Bureau of Standards Special Publication 746 (National Bureau of Standards, Washington, DC, 1985), p. 80.

1.9.2 Two-Photon Absorption*

Two-photon absorption (2PA) occurs in all materials at sufficiently high irradiance when the combined energy of two quanta of light matches a transition energy between two states of the same parity. The fundamental equation describing this loss of irradiance I with depth z in a material is

$$dI/dz + \beta I^2,$$

where β is the two-photon absorption coefficient. The coefficient β is proportional to the imaginary part of $\chi^{(3)}(-\omega, \omega, \omega, -\omega)$. The relationship between n_2 , β , and $\chi^{(3)}$ is analogous to the relationship between n_0 , the linear absorption coefficient α , and the linear susceptibility χ .

The two-photon absorption coefficient β depends not only on the frequency arguments but also on the state of polarization, propagation direction, and crystal symmetry as β is derived from the imaginary part of the third-order susceptibility tensor $\chi^{(3)}$. Relations for $\chi^{(3)}$ for cubic crystals for several polarization orientations are presented in reference 1. These relations are valid for both the real and imaginary parts of $\chi^{(3)}$. For a linear or circularly polarized wave:

$$\beta(LP) = (32\pi^2 \omega/n^2 c^2) 3\chi_{1111}^{(3)}$$

and

$$\beta(CP) = (64\pi^2 \omega/n^2 c^2) 3\chi_{1122}^{(3)}.$$

Because these equations are in cgs units (esu), β is in cm s/erg rather than the more common mixed unit of cm/W.

Several methods have been used to measure the two-photon absorption coefficient in solids. Direct transmission measurements as a function of irradiance have been the primary method to determine absolutely calibrated values of β as well as two-photon absorption spectra. Several other techniques have been utilized to obtain calibrated as well as relative measurements and two-photon absorption spectra. These are listed in the table to follow. Many of these methods require calibration. Direct transmission experiments are best suited for absolute calibration. Because to give a value for β a measurement of the absolute irradiance is needed, single-beam experiments are most easily calibrated. Once absolute calibration is obtained at a single wavelength, relative measurements and spectral measurements can be calibrated.

* This section was adapted from Van Stryland, E. W. and Chase, L. L., Two-photon absorption: inorganic materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 299.

Techniques for Measuring Two-Photon Absorption

	Method	Ref.
AI1	Attenuation vs. irradiance for a single beam	3, 4
AI2	Attenuation vs. irradiance; two beams, usually one scanned in ω	5
AIS	Attenuation vs. irradiance; broad spectrum treated simultaneously	6
C	Calorimetry	7
CR	Comparison of 2-photon loss and Raman gain	8, 9
EPR	Elliptical polarization rotation	10
FCC	F-center coloration	11
GTA	Gain measurement in a 2-photon-pumped amplifier	12
IA	Intracavity absorption	13
L	Luminescence or fluorescence	14, 15
HGE	Harmonic generation efficiency	16
PA	Photoacoustics	17
PC	Photoconductivity or photo-Hall effect	18, 19
TCN	Two-channel normalization	20
TL	Thermal lensing	21
TRT	Time-resolved transmission	22
Z-scan	A propagation method to measure β and n_2	23

The experimental data on two-photon absorption coefficients (β in cm per GW) are presented in the following table. Materials are listed alphabetically. The method of measurement (using the above table), the pulse duration t_p , the input two-photon excitation energy $2\hbar\omega$ (or range of energies if spectra are given), band gap energy E_g (if given in the reference) or absorption cutoff energy for wide-gap materials, and linear index $n_0(\hbar\omega)$ are listed. The linear refractive indices are taken from reference 2.

The following shorthand notation is used in the table: Anisot. = anisotropy; β_l and $\beta_c = \beta$ measured with linearly or circularly polarized light, respectively; Cleartran = brand name of heat-treated ZnS that makes it water clear and is grown by CVD = chemical vapor deposition; Dir. = direct; K = Kelvin; L = length; Mag. = magnetic; Pol. = polarized; SHG = second harmonic generation; T = temperature; t = time; E for SHG, means that the electric field and propagation direction are aligned for SHG phase matching.

Two-Photon Absorption Data

Material	Method	Pulse τ_p (ns)	Bandgap E_g (eV)	$2\hbar\omega$ (eV)	Index $n_0(\hbar\omega)$	2PA coefficient (cm/GW)	Ref.	Additional information
Ag ₃ AsS ₃	AI2	10	2.1	2.7–3.2	~2.7	Abs. spectr. (10 @ 3.1 eV)	24, 25	
Ag ₃ AsS ₃	AI1	25		3.56	~2.7	20		26
Ag ₃ AsS ₃	AI1	20		2.34	~2.7	<3		26
AgCl	L		3.2	4.0–4.4	2.0	Abs. spectr. (0.5 @ 4.3 eV)	27	Indirect gap
AgCl	L	9		6.6–7.6	2.07	Relative spectrum	28	77 K
AgCl	L	9		3.3–4.2		Relative spectrum	28	80 K
AgGaSe ₂	AI1	~0.01	1.1	2.33	2.7	1.4		29
α -AgI	A12		2.9	3.0–3.06		Relative spectrum	30	1.6 K
A1As-GaAs	L		1.7	1.65–1.8		Relative spectrum	191	
Al ₂ O ₃	AI1	0.017	9.9	6.99	~1.79	<0.0016		3
Al ₂ O ₃	AI1	0.015		9.32	~1.84	0.27		3
Al ₂ O ₃	AI1	0.12		8.05	~1.8	0.0276		31
As ₂ S ₃	AI2	30	2.5	2.4–3.6	~2.6	Abs. spectr. (25 @ 3.4 eV)	32	
BaF ₂	AI1	0.017	9.1	6.99	1.49	<0.0036		33
BaF ₂	AI1	0.015		9.32	~1.5	<0.0040		33
BaF ₂	AI1	0.0007		10.0	~1.5	0.11		34
BaTiO ₃	AI2	17	3.5	3.4–4.2		Abs. spectr. (4 @ 4 eV)	35	392 K
BaTiO ₃	AI2	0.0012		4.16	~2.4	0.1		36
Bi ₄ Ge ₃ O ₁₂	L	~10	4.2	4.1–5.1	2.1	Relative spectrum	37	
Bi ₄ Ge ₃ O ₁₂	L	9		4.27–4.83	2.1	Abs. spectr. (50 @ 4.5eV)	38	80 K
Bi ₄ Ge ₃ O ₁₂	L	9		4.2–5	2.1	Relative spectrum	39	80 K
Bi ₄ Ge ₃ O ₁₂	AI2	10		4.8–5.7		Abs. spectr. (10 @ 5.6 eV)	40	80 K
C (diamond)	CR	4.0	5.47	4.55	2.42	<0.003		9
C (diamond)	AI1	0.021		4.66	2.42	<0.26		41

C (diamond)	AI1	0.000135		8.0	~2.5	0.74	42	Indirect gap
C (diamond)	Z-scan	0.015		6.99	~2.5	0.3	43	$k \parallel [001]$
CaCO ₃	AI1	0.015	5.9	9.32	~1.5–1.8	0.24	3	
CaF ₂	CR	4.0	10	4.31	1.43	<0.004	9	
CaF ₂	AI1	0.015		9.32	1.46	<0.02	3	
CaF ₂	AI1	0.0007		10.0	1.47	0.0083	34	
CaF ₂	AI1	0.12		8.05	1.46	0.00092	31	
CdF ₂	CR	4.0	6	4.31		<0.03	9	
CdF ₂	AI1	0.017		6.99		<0.042	33	
CdF ₂	AI1	0.015		9.32		1.6	33	
CdI ₂	L	9	3.9	3.5–4.4		Relative spectrum	39	Indirect gap
CdP ₂	TRT			2.34		160	44	
CdP ₂	TRT			3.56		800	44	
CdP ₂	AI2	15		2.4–3.2		Abs. spectr. (11 @ 2.9 eV)	45	
CdS	L	3×10^5	2.42	3.56	~2.42	12	46	123 K
CdS	AI2	30		2.5–3.5	2.35–2.42	Abs. spectr. (20 @ 2.8 eV)	47	
CdS	AI2	40		2.5–3.4	2.35–2.4	Abs. spectr. (14.7 @ 3.4 eV)	48	
CdS	AI1	30		3.56	~2.42	30	49	
CdS	AI2	30		2.5–3.5	2.3–2.4	Relative spectrum	50	Anisotropy
CdS	AI2			2.54–3.6	2.35–2.44	Abs. spectr. (30 @ 3.0 eV)	51	77 K
CdS	AI2			2.54–3.6	2.35–2.44	Abs. spectr. (30 @ 3.0 eV)	51	77 K
CdS	AI1	30		3.56	~2.42	100	52	β vs. length
CdS	AI2	30		2.65–3.45	2.35–2.4	Abs. spectr. (35 @ 4 eV)	53	
CdS	AI1	5		2.54–2.55	~2.35	Relative spectrum	54	
CdS	AI2	0.006		2.5–3.5	2.35–2.42	Abs. spectr. (18 @ 3.35 eV)	55	
CdS	L			2.550–2.554	~2.35	Relative spectrum	56	1.6 K
CdS	AI1	30		3.56	~2.42	15; 20	57	$E \parallel c; E \perp c$
CdS	AI2	300		2.5–2.6	~2.35	Abs. spect. (4000 @ 2.54 eV)	58	

Two-Photon Absorption Data—*continued*

Material	Method	Pulse τ_p (ns)	Bandgap E_g (eV)	$2\hbar\omega$ (eV)	Index $n_0(\hbar\omega)$	2PA coefficient (cm/GW)	Ref.	Additional information
CdS	L	~25	2.5	2.56–2.62	~2.35	Relative spectrum	107	
CdS	AI1	20	2.4	3.56	~2.42	56	106	Self-focusing
CdS	AI1	45	2.5	3.56	~2.42	120; 56	82	$E \parallel c; E \perp c$
CdS	AI2			2.5–3.6		Abs. spectr. (20 @ 3.2 eV)	62	β vs. pol.
CdS	PC	~10	2.58	~5.1–5.2	~2.8	Magnospectra $0 < B < 10$ Tesla	63	A-excitons 1.8 K
CdS	CR	8		3.91	~2.5	120; $k \parallel c$; 110 $k \perp c$, $E \perp c$ 140 $k \perp c$, $E \perp c$	65	β vs. T and resistance
CdS	AI1			4.66		0.9; 1.8	66	$E \parallel c; E \perp c$
CdS	AI1	0.027		4.66	~2.64	5.5	67	
$\text{CdS}_{0.25}\text{Se}_{0.75}$	AI1	0.038	1.78	2.33	2.51	15	67	
$\text{CdS}_{0.5}\text{Se}_{0.5}$	C	11; 26		2.33		32; 135	7	
$\text{CdS}_{0.5}\text{Se}_{0.5}$	AI1	0.038	1.93	2.33	2.45	10	67	
$\text{CdS}_{0.8}\text{Se}_{0.2}$	AI1	30		3.56		130	49	
$\text{CdS}_{0.9}\text{Se}_{0.1}$	AI1	30		3.56		70	49	
CdSe	AI1		1.7	2.33	2.56	950	68	
CdSe	AI1			2.33	2.56	900; 390	69	$E \perp z; E \parallel z$
CdSe	AI1			2.33	2.56	200	70	
CdSe	AI1	20		2.33	2.56	60–140	71	
CdSe	AI1	15		2.33	2.56	40	72	
CdSe	AI1	0.030		2.33	2.56	30	73	
CdSe	TRT	~20		1.88; 2.33	2.5; 2.56	2; <20	26	
CdSe	C	16		2.33	2.56	50	74	

CdSe	C	11; 26	2.33	2.56	25; 38	7
CdSe	PA	0.040	2.33	2.56	35	75
CdSe	C	79	1.88	~2.5	67	7
CdSe	AI1	0.038	2.33	2.56	18	67
CdSe	AI1	~200	3.65	~2.6	~10 ⁶	76
CdSe	AI1	0.006	2.36	2.56	18	77
CdS _x Se _{1-x}	AI1	30	1.9–2.4	3.56	100–1700	78
CdS _x Se _{1-x}	AI1			2.33, 3.56	Relative spectrum	79
CdTe	AI1		1.56	2.33	2.84	200
CdTe	AI1			2.33	2.84	180
CdTe	AI1	0.030		2.33	2.84	25
CdTe	TCN	0.030		2.33	2.84	$\beta_{\text{CdTe}}/\beta_{\text{GaAs}} = 0.78$
CdTe	C	16		2.33	2.84	130
CdTe	C	11; 38		2.33	2.84	53; 78
CdTe	C	79		1.88	~2.7	120
CdTe	PA	0.040		2.33	2.84	50
CdTe	TCN	20		2.33	2.84	170
CdTe	AI1	0.005		2.34	2.84	12; 8
CdTe	AI1	0.038		2.33	2.84	22; 15
CdTe	AI1	0.035		2.33	2.84	8
CdTe	Z-scan	0.040		2.33	2.84	26
CsBr	AI2	~10	6.9	7.2–8.0	~1.8–1.9	Abs. spectr. (10 @ 7.5 eV)
CsD ₂ AsO ₄	AI1	0.017		6.99	1.6	0.051; 0.080
CsH ₂ AsO ₄	AI1	0.017		6.99	1.6	0.028
CsI	AI2	~10 ⁶	6.2	5.7–6.8	~1.8–1.9	Relative spectrum
						86,87

Two-Photon Absorption Data—*continued*

Material	Method	Pulse τ_p (ns)	Bandgap E_g (eV)	$2\hbar\omega$ (eV)	Index $n_0(\hbar\omega)$	2PA coefficient (cm/GW)	Ref.	Additional information
CsI	AI2	~10		6.2–6.8	~1.8–1.9	Abs. spectr. (40 @ 6.5 eV)	85	20 K
CsI	AI2			6.0–6.8	~1.8–1.9	Relative spectrum	88	20 K
CsI	L	5		7.0	1.89	Relative spectrum	89	
CsI	AI1	6		6.99	1.89	6	90	
CsI	AI1	0.00035		8.05	~1.9	4.5	91	$3 \times 10^{18} \text{ Na}^+$
Cu_2O	AI2	40	2.1	2.0–2.8		Relative spectrum	92	
Cu_2O	AI2	0.0005		3.4–3.9		Relative spectrum	93	20 K
Cu_2O	AI2			2.03–2.17		Relative spectrum	94	Excitons
CuBr	AI2	30	3	2.97–3.10	2.1	Relative spectrum	95	
CuBr	AI1	45		3.56	2.1	200	62	
CuCl	AI2	~10	3.3	3.2–4.25	~2	Relative spectrum	96	20 K
CuCl	AI2			3.21–3.56	1.97	Relative spectrum	97	4.2 K
CuCl	AI1	16		3.16–3.20	1.95	1×10^6	98	4 K, 77 K
CuCl	AI2	~5		3.16–3.18	1.95	$\sim 3 \times 10^6$	4	4.2 K
CuCl	AI1	45		3.56	1.97	45	62	
CuCl	AI2	~10		3.2–5.4	~2	Relative spectrum	99	
CuCl	AI2			3.2–5.4	~2	Relative spectrum	100	4.3 K, β vs Pol
CuCl	EPR	5		3.18–3.19	1.95	Relative spectrum	10	4 K
CuCl	L	9		3.34–4.1	1.92	Abs. spectr. (30 @ 3.5 eV)	38	80 K
CuCl	L	9		3.34–4.1	1.92	Relative spectrum	39	80 K
CuI	AI1	45	3.1	3.56	1.97	89	62	
FeBO_3	AI2	12	~2.5	2.6–3.6		Abs. spectr. (5 @ 3.4 eV)	101	108 K
GaAs	AI1		1.42	2.33	3.43	300	68	
GaAs	AI1			2.33	3.43	20	70	

GaAs	AI1		2.33	3.43	800	49	n-type
GaAs	AI1, PC	22	2.33	3.43	360	102	
GaAs	AI1	~125	1.88	~3.4	33	103	
GaAs	AI1	30	2.33	3.43	230	104	
GaAs	AI1		2.33	3.43	80	80	300 K, 85 K
GaAs	AI1	~50	1.5–2.33	~3.4	Abs. spectr. (1100 @ 1.5eV)	105	
GaAs	AI1	15	2.33	3.43	60	72	
GaAs	AI1	0.030	2.33	3.43	28	46	E z
GaAs	AI1	~10	2.33	3.43	35; 78	106	
GaAs	L		1.4–1.8	~3.35	Abs. spectr. (5.1 @ 1.6eV)	107	
GaAs	L	5	2.33	3.43	70	108	
GaAs	AI1	0.008	2.33	3.43	15	109	
GaAs	C	0.030	2.33	3.43	30	7	
GaAs	AI1	30	2.33	3.43	100	110	
GaAs	AI1	~0.035	1.3–1.7		Relative spectrum	111	100 K
GaAs	AI1	0.038	2.33	3.43	23	67	
GaAs	AI1	0.045	2.33	3.43	26	112	
GaAs	AI2, L	0.005	2.34	3.43	45	113	295 K, 103 K
GaAs	AI2	0.035	2.33	3.43	27	114	Cross-pol.
GaAs	AI1	0.05	2.33	3.53	29	115	In Chinese
GaAs	A12	0.027	2.33	3.43	18, 22	116	
GaAs	AI1	0.08	2.33	3.43	26	117	
GaAs	Z-scan	0.040	2.33	3.43	26	84	No anisotropy
GaP	AI1	50	2.26	2.33	3.12	1.7	Indirect gap
GaP	AI1	0.030		2.33	3.12	0.2	E [110]
GaP	TCN			3.92	3.35	250	119
GaP	CR			3.18	3.18	250	59

Two-Photon Absorption Data—*continued*

Material	Method	Pulse	Bandgap		Index	2PA coefficient	Ref.	Additional information
		τ_p (ns)	E_g (eV)	$2\hbar\omega$ (eV)	$n_0(\hbar\omega)$	(cm/GW)		
GaS	AI1	20	2.8	3.56		100	120	Direct gap
GaS	PC	20	2.3	2.33		0.05	120	Indirect gap
GaSe	AI1	20	2.0	2.33		110	120	
Ge	AI1	80	0.66	1.06	~4	50	121	
Ge	AI1	100		0.8–1.0	~4	2500	122	
Ge	AI1; PC	~480		0.916	4.05	160	19	
Hg _{0.78} Cd _{0.22} Te	TRT	~200	0.17	0.233		14000	123	
Hg _{0.78} Cd _{0.22} Te	TRT	300		0.233		$1 \times 10^4, 3 \times 10^4$	124	300 K; 150 K
Hg ₂ Cl ₂	L	2	3.9	4.7–5.2		Relative spectrum	125	8.5 K, E c
Hg ₂ Cl ₂	L, AI1	2		4.1–5.7		Relative spectrum	126	8.5 K
Hg ₂ Cl ₂	L			4–5.5		Polarization dependence	127	8.5 K
InP	TRT	200	1.34	2.33	3.33	210	104	
InP	AI1, PC	22		2.33	3.33	260	102	
InP	AI1	30		2.33	3.33	1800	110	
InP	AI1	100		2.34	3.33	60	128	$\beta_l/\beta_c = 1.8$
InSb	PC	~200	0.17	0.233	3.95	59.6–119	129	77 K
InSb	PC	~200		0.233	3.95	0	129	2 K
InSb	PC	~200		0.257	3.95	1151–1419	129	77 K
InSb	AI1	~10		0.233	3.95	16000	130	
InSb	PC	~200		0.257	3.95	946–1850	129	2 K
InSb	AI1	30		0.233	3.95	15000	104	
InSb	AI1; PC	~150		0.233	3.95	220	19	
InSb	TRT	~200		0.233; 0258	3.95	8000; 14000	123	
InSb	TRT	300		0.233	3.95	4800	124	

InSb	TRT	300		0.233	3.95	220	124	77 K
InSb	AI2	130		0.233	3.95	2000–5600	130	
InSb	PC	CW		0.26	3.95	2900	131	Magnetic field
InSb	AI1	0.045		0.234; 0.258	3.95	2500; 1700	132,133	300 K
KBr	AI1	15	7.6	7.12	~1.6	3.3	134	
KBr	AI2	~10		7.0–8.0	~1.6	Relative spectrum	135	20 K, 80 K
KBr	AI1	0.015		9.32	~1.6	2.0	3	
KBr	CR	15		6.7	~1.6	8.0	136	
KBr	AI1	10		7.18	~1.6	$\beta_{\text{KBr}} = 0.64 \beta_{\text{KI}}$	137	
KCl	FCC	8	8.5	9.32	1.6	1.5	11	
KCl	AI1	0.015		9.32	1.6	2.2	3	
KCl	AI2	10		8.1–8.5	1.6	Abs. spectr. (400 @ 8.5eV)	138	20 K
KD ₂ AsO ₄	AI1	0.017		6.99	~1.6	0.027	3	
KD ₂ PO ₄	AI1	0.030		9.32	1.57–1.51	0.027	139	
KD ₂ PO ₄	AI1	0.030	7.0	9.32	1.57–1.51	0.027	140	k ⊥ c
KD ₂ PO ₄	AI1	0.017		6.99	1.53–1.49	0.0054	3	
KH ₂ AsO ₄	AI1	0.017		6.99	~1.6	0.048	3	
KH ₂ PO ₄	AI1	0.017	7.0	6.99	1.53–1.49	0.0059	3	
KH ₂ PO ₄	AI1	0.015		9.32	1.57–1.51	0.27	3	
KH ₂ PO ₄	Model	0.5		9.32	1.57–1.51	0.5	141	E ⊥ opt.axis
KI	AI1	15		7.12	~1.9	4.4	134	
KI	AI2			6.0–7.5	~1.7–1.9	Relative spectrum	142	
KI	AI2			6.1–7.7	~1.7–1.9	Relative spectrum	88	20 K
KI	AI2			6.23–6.36	~1.7–1.8	Relative spectrum	143	
KI	PC	20		7.12	~1.9	10	144	
KI	AI1	0.017		6.99	~1.9	7.3	3	
KI	AI1	0.015		9.32	2.0	3.7	3	
KI	CR	15		6.7	~1.9	18	136	

Two-Photon Absorption Data—*continued*

Material	Method	Pulse τ_p (ns)	Bandgap E_g (eV)	$2\hbar\omega$ (eV)	Index $n_0(\hbar\omega)$	2PA coefficient (cm/GW)	Ref.	Additional information
KI	AI1	0.024		7.12	~1.9	8	145	
KI	AI1	10		7.12	~1.9	Relative value	137	
KI	AI2	10		6.0–6.7		Abs. spectr. (300 @ 6.5 eV)	138	20 K
KRS-V	C	38		2.33	2.44	1.6	7	
KTa _{0.7} Nb _{0.3} O ₃	AI1	0.010		4.66		14	146	
KTaO ₃	AI2	17	3.5	3.9–4.6		Abs. spectr. (1 @ 4.4 eV)	35	
KTP	Z-scan	0.019	3.5	4.66	1.8	0.1	147	E for SHG
LiF	AI1	0.015	13.6	9.32	1.4	<0.02	3	
LiIO ₃	AI2	10	4.0	4.4–4.8	1.75–1.9	<0.4	148	
LiNbO ₃	AI1	30	4.0	3.56	~2.2	10.	49	
LiNbO ₃	AI1	0.025		4.66	2.3–2.2	3.4	149	
LiNbO ₃	AI2	10		4.4–4.8	2.3–2.2	Abs. spectr. (1.5 @ 4.66 eV)	148	
LiYF ₄	AI1	0.015	~11	9.32	1.5	<0.004	33	
MgF ₂	AI1	0.017	10.8	6.99	1.4	<0.0062	33	
MgF ₂	AI1	0.015		9.32	1.4	<0.0028	33	
NaBr	AI1	0.015	7.5	9.32	1.8	2.5	3	
NaCl	AI1	0.015	9.0	9.32	~1.64	3.5	3	
NaCl	AI2	10		8.1–8.6	~1.6	Abs. spectr. (200 @ 8.5 eV)	138	20 K
NH ₄ H ₂ AsO ₄	AI1	0.017		6.99		0.035	3	
NH ₄ H ₂ PO ₄	AI1	0.030	6.8	9.32	1.59–1.53	0.11	139	No pol., k ⊥ c
NH ₄ H ₂ PO ₄	AI1	0.015		9.32	1.59–1.53	0.24	3	
NH ₄ H ₂ PO ₄	AI1	0.017		6.99	1.55–1.50	0.0068	3	
NH ₄ H ₂ PO ₄	Model	0.5		9.32	1.59–1.53	0.35	141	E ⊥ opt. axis
NH ₄ H ₂ PO ₄	Model	0.5		4.67 + 5.83	~1.6	1	141	E for 5th harmonic

$\text{NH}_4\text{H}_2\text{PO}_4$	Model	0.5		11.66	~1.6	9.5	141	E for 5th harmonic
PbI_2	AI1	20	2.4	3.56		250	120	
PbI_2	AI2	~10		2.46–2.55		Relative spectrum	150	1.6–300 K
PbMoO_4	AI2	50	3.6	3.2–4.2		Abs. spectr. (5 @ 4 eV)	151–52	80 K, 300 K
RbBr	AI2	~10	7.25	7.0–8.0	~1.6	Relative spectrum	135	20 K, 80 K
RbBr	AI1	0.017		6.99	1.6	2.43	3	
RbBr	AI1	0.015		9.32	1.7	2.18	3	
RbBr	CR	15		6.7	1.6	11	136	
RbBr	AI1	10		7.12	1.6	$\beta_{\text{RbBr}} = 0.55 \beta_{\text{KI}}$	137	
RbCl	AI1	0.015	8.3	9.32	1.6	1.1	3	
RbH_2AsO_4	AI1	0.017		6.99		0.050	3	
RbH_2PO_4	AI1	0.017		6.99		0.059	3	
RbI	AI2	~10	5.83	6.1–7.0	1.7	Relative spectrum	135	20 K
RbI	AI1	0.017		6.99	1.73	5.1	3	
RbI	AI1	0.015		9.32	2.0	2.5	3	
RbI	AI1	10		7.12	1.73	$\beta_{\text{RbBr}} = 0.51 \beta_{\text{KI}}$	137	
Si	AI1	200	1.12	2.33	3.52	40	153	
Si	AI1		“1.1”	2.33	3.52	7300	70	T dependence
Si	AI2	25		1.62–2.2	~3.5	Relative spectrum	154	
Si	AI1	0.020		2.33	3.52	1.9; 1.5	155	20 K; 100 K
Si	C	79		1.88	~3.5	21	7	
Si	AI1	0.004–0.1		2.33–2.34	3.52	1.5	156	
Si	AI2	0.00009		4–4.5; 4.0	~3.8	15–36; 34.6	156,157	Dir. $E_g = 3.43$
SiC	AI1	30	2.6	3.56	2.6	200	49	
SiC	L	20		3.0–4.6	~2.6	Relative spectrum	159	$E \parallel c; E \perp c$
SiO_2 (quartz)	AI1	0.015	8.4	9.32	1.6	<0.045	3	
SnO_2	AI2	~10	3.4	3.555–3.573		Relative spectrum	160	

Two-Photon Absorption Data—*continued*

Material	Method	Pulse	Bandgap		Index	2PA coefficient		Additional information
		τ_p (ns)	E_g (eV)	$2\hbar\omega$ (eV)	n_0 ($\hbar\omega$)	(cm/GW)	Ref.	
SnO ₂	AI1	45		3.56		300; 34	62	$E \parallel c$; $E \perp c$
SrF ₂	AI1	0.017	9.4	6.99	1.45	<0.0057	33	
SrF ₂	AI1	0.015		9.32	1.47	<0.0054	33	
SrF ₂	AI1	0.0007		10.0	1.47	0.011	34	
SrTiO ₃	AI1	~30	4.1	3.56	2.38	2.9	161	
SrTiO ₃	CR			3.92	2.4	3	119	
SrTiO ₃	AI2	17		3.2–4.4	~2.4	Abs. spectr. (4 @ 4.2 eV)	35,162	
SrTiO ₃	AI2			4.1; 4.7; 5.0	2.4–2.5	1.3; 4.1; 10.2	163	
SrTiO ₃	PA	5		3.2–5.5	~2.4–2.5	Abs. spectr. (5 @ 5.0 eV)	17	
SrTiO ₃	AI2			3.3–4.2	~2.4	Abs. spectr (2 @ 4.1 eV)	164	
Te	AI2	200	0.33	0.342	~5–6	800	140	
TiO ₂	AI2		3.5	3.3–4.1	~2.5–2.9	Abs. spectr. (300 @ 4 eV)	166	
TiO ₂	AI1	0.004		4.66	~2.6–3	14	167	
TiO ₂	AI1	0.004		3.96	~2.6–2.9	6.5	167	
TiO ₂	CR			3.92	~2.6–2.9	23	119	
TiO ₂	CR			4.1; 4.7; 5.0	~2.6–3	12.7; 87; 170.	163	
TiO ₂	AI1	45		3.56	~2.5–2.9	150; 120	62	$E \parallel c$; $E \perp c$
TiCl	AI2	20	3.6	3.4–4.4	2.2–2.26	Abs. spectr. (0.45 @ 3.8 eV)	165	
TiCl	AI2	20		3.4–4.4	2.2–2.26	Abs. spectr. (4.7 @ 4.0 eV)	169	
TiCl	AI2	~10		3.39–3.56	2.2	Relative spectrum	170	4, 20, 77 K
V ₂ O ₅	AI1	60	~2.3	3.56		720	171	$E \parallel [001]$
Y ₃ Fe ₅ O ₁₂	AI2	17	2.66	2.5–3.5		Abs. spectr. (300 @ 3.51 eV)	172	T dep., β vs. pol.
Zn _{0.85} Cd _{0.15} Se	AI1	10	2.65	3.56		56	173	
Zn _{0.12} Cd _{0.88} Se	AI1	10	1.92	3.56		620; 260	173	$E \perp z$; $E \parallel z$

Zn _{0.5} Cd _{0.5} S	AI1	45	~3	3.56		60	62	
Zn _{0.5} Cd _{0.5} S	AI2	35	2.62	2.6–3.6		Abs. spectr. (20 @ 3.4 eV)	174	
Zn _{0.5} Cd _{0.5} S	AI2			2.6–3.4		Abs. spectr. (10 @ 3 eV)	63	β vs. pol.
ZnO	AI2	20	3.35	3.42–3.45	2.0	Relative spectrum	175	
ZnO	AI1:AI2			3.56		26; 21	176	$k \perp c$
ZnO	AI2			3.42–3.43	2.0	Abs. spectr. (2 @ 3.4 eV)	177	4.2 K in 42 kG field
ZnO	AI2	~10		3.42–3.48	2.0	Relative spectrum	88	1.6 K
ZnO	CR			4.1; 4.7; 5.0	2.0–2.1	19.8; 20.9; 47.8	163	
ZnO	AI1	45		3.56	2.0	34; 16	62	E c; E ⊥ c
ZnO	AI2	50		3.4–4.2	2.0	Abs. spectr. (10 @ 3.8 eV)	133	β vs. pol.
ZnO	AI1	0.027		4.67	2.05	5.0	67	
ZnO	L	9		3.4–4.2	2.0	Abs. Spectr. (10 @ 3.5 eV)	28,38	80 K
ZnP ₂	TRT			2.34		120	44	
ZnP ₂	TRT			3.56		650	44	
ZnP ₂	AI2	15		2.4–3.2		Abs. spectr. (10 @ 2.9 eV)	45	
ZnP ₂	AI2	25	2.22	2.2–2.7		Abs. spectr. (10 @ 2.6 eV)	179	
ZnP ₂	AI2	15		2.4–3.4		Relative spectrum	180	Impurities
ZnS	AI2		3.68	3.7–4.2	~2.36	Abs. spectr. (2.3 @ 4.0 eV)	154	
ZnS	AI2			3.6–4.0	~2.35	Relative spectrum	181	
ZnS	PC	20		3.56	~2.35	4.3	18	Cu-doped
ZnS	AI1	45		3.56	~2.35	20; 0	62	E c; E ⊥ c
ZnS	PA	5		3.65–5.5	2.35–2.5	Relative spectrum	17	E z
ZnS	AI2			3.7–5.3		Abs. spectrum (2 @ 4.1 eV)	63	β vs. pol
ZnS	AI1	0.027		4.67	2.4	2.0; 3.5	67	Cleartran, CVD
ZnSe	AI1	30	2.71	3.56	~2.6	40	49	
ZnSe	AI1	10		3.56	~2.6	45	173	
ZnSe	AI2	40		2.6–3.6	~2.5–2.6	Abs. spectr. (4 @ 3.0 eV)	182	

Two-Photon Absorption Data—*continued*

Material	Method	Pulse	Bandgap	Index	2PA coefficient	Ref.	Additional information	
		τ_p (ns)	E_g (eV)	$2\hbar\omega$ (eV)	n_0 ($\hbar\omega$)	(cm/GW)		
ZnSe	AI2	40		2.75–3.45	~2.5–2.6	Abs.spectr. (13 @ 3.45 eV)	183	Impurity resonances
ZnSe	CR			3.18	~2.53	60	59	
ZnSe	AI1	45		3.56	~2.6	17000	62	300 K, cubic
ZnSe	AI2	15		2.7–3.75	~2.5–2.6	Abs. spectr. (10 @ 3.5 eV)	45	
ZnSe	TCN	20		3.56	~2.6	80	81	
ZnSe	AI2			2.7–3.8	~2.5–2.6	Abs. spectr. (10 @ 3.4 eV)	63	β vs. pol
ZnSe	AI2	15		2.9–3.7	~2.5–2.6	Abs. spectr. (10 @ 3.4 eV)	184	β vs Cu doped
ZnSe	AI1	20		3.56	~2.6	4–15	185	β vs Cu doped
ZnSe	AI1	0.027		4.67	2.7	5.5	67	
ZnSe	Z-scan	0.03		4.67	2.7	5.8	84	
ZnTe	AI1	30	2.3	2.33	2.79	34	104	
ZnTe	AI1			3.56	2.91	500	186	77 K
ZnTe	AI1	0.030		2.33	2.79	8.0	73	$E \parallel z$
ZnTe	AI1, TCN	20		2.34; 3.56	2.79; 2.91	20; 300	187	T-tuned band gap
ZnTe	AI1	45		3.56	2.91	8000	62	Arb. pol.
ZnTe	AI2	30		2.8–4	~3	Abs. spectr. (4 @ 3.1 eV)	188	Time resolved
ZnTe	AI1	0.038		2.33	2.79	4.5	67	
ZnTe	Z-scan	0.040		2.33	2.79	4.2	84	
$Zn_xCd_{1-x}Se$	AI1		2.45–3.55	3.56		50–1	189	Anistropy
$Zn_{0.12}Cd_{0.88}Se$	AI1	10	1.92	3.56		620, 260	173	
$Zn_{0.5}Cd_{0.5}Se$	AI1	45	~3	3.5		60	62	
$Zn_{0.85}Cd_{0.15}Se$	AI1	10	2.65	3.56		56	173	
$ZrO_2-(Y_2O_3)$	AI1	0.03	~4.1	4.66	2.12	0.013	190	Independent of Y_2O_3

References:

1. Chase, L. L., and Van Stryland, E. W., Nonlinear refractive index: inorganic materials, in *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 269.
2. Dodge, M. J., Refractive index, *Handbook of Laser Science and Technology, Vol. IV: Optical Materials, Part 2* (CRC Press, Boca Raton, FL, 2000), p. 21
3. Liu, P., Smith, W. L., Lotem, H., Bechtel, J. H., Bloembergen, N., and Adhav, R. S., Absolute two-photon absorption coefficients at 355 and 266 nm, *Phys. Rev. B* 17(12), 4620 (1978).
4. Bivas, A., Levy, R., Phach, V. D., and Grun, J. B., Biexciton two-photon absorption in the nanosecond and picosecond range in copper halides, in *Physics of Semiconductors 1978*, Inst. Phys. Conf. Ser. No. 43, (AIP, New York, 1979).
5. Fröhlich, D., and Sondergeld, M., Experimental techniques in two-photon spectroscopy, *J. Phys. E* 10, 761 (1977).
6. Göppert-Mayer, M., Über Elementarakte mit zwei Quantensprünge, *Ann. Phys.* 9, 273 (1931).
7. Stewart, A. F., and Bass, M., Intensity-dependent absorption in semiconductors, *Appl. Phys. Lett.* 37(11), 1040 (1980).
8. Lotem, H., and Lynch, R. T., Jr., Destructive interference of imaginary resonant contributions to $\chi^{(3)}$, *Phys. Rev. Lett.* 37(6), 334 (1976).
9. Levenson, M. D., and Bloembergen, N., Dispersion of the nonlinear optical susceptibility tensor in centrosymmetric media, *Phys. Rev. B* 10, 4447 (1974).
10. Kuwata, M., and Nagasawa, N., Self-induced polarization rotation effect of an elliptically polarized beam in CuCl, *J. Phys. Soc. Jpn.* 51, 2591 (1982).
11. Mollenauer, L. F., Bjorklund, G. C., and Tomlinson, W. J., Production of stabilized coloration in alkali halides by a two-photon absorption process, *Phys. Rev. Lett.* 35(24), 1662 (1975).
12. Topp, M. R., and Rentzepis, P. M., Picosecond stimulated emission in a fluorescent solution following two-photon absorption, *Phys. Rev. A* 3(1), 358 (1971).
13. Reilly, J. P., and Clark, J. H., Broadband detection of two-photon absorption by intracavity dye laser spectroscopy, in *Advances in Laser Chemistry*, Zewail, A. H., Ed. (Springer-Verlag, Berlin 1978), p. 354.
14. Hermann, J. P., and Ducuing, J., Absolute measurement of two-photon cross sections, *Phys. Rev. A* 5(6), 2557 (1972).
15. Webman, I., and Jortner, J., Energy dependence of two-photon absorption cross sections anthracene, *J. Chem. Phys.* 50(6), 2706 (1969).
16. Begishev, I. A., Ganeev, R. A., Gulamov, A. A., Erfeev, E. A., Kamalov, Sh. R., Usmanov, T., and Khadzhaev, A. D., Generation of the fifth harmonic of a neodymium laser and two-photon absorption in KDP and ADP crystals, *Sov. J. Quantum Electron.* 18, 224–228 (1988).
17. Bae, Y., Song, J. J., and Kim, Y. B., Photoacoustic study of two-photon absorption in hexagonal ZnS, *J. Appl. Phys.* 53(1), 615 (1982).
18. Cingolani, A., Ferrero, F., Minafra, A., and Trigiante, D., Two-photon conductivity in ZnS and CdS, *Il Nuovo-Cimento* 4B, 217 (1971).
19. Gibson, A. F., Hatch, C. B., Maggs, P. N. D., Tilley, D. R., and Walker, A. C., Two-photon absorption in indium antimonide and germanium, *J. Phys. C* 9, 3259 (1976).
20. Lotem, H., Bechtel, J. H., and Smith, W. L., Normalization technique for accurate measurements of two-photon absorption coefficients, *Appl. Phys. Lett.* 28, 389 (1976).
21. Twarowski, A. J., and Klier, D. S., Multiphoton absorption spectra using thermal blooming, *Chem. Phys.* 20, 259 (1977).
22. Smith, W. L., Lawrence Livermore National Laboratory, 1981 Laser Program Annual Report, U.C.R.L. - 50021-81, p. 7–23.
23. Sheik-Bahae, M., Said, A. A., Wei, T. H., Hagan, D. J., and Van Stryland, E. W., Sensitive measurements of optical nonlinearities using a single beam, *IEEE J. Quantum Electron.* 26, 760–769 (1990).

24. Bredikhin, V. I., Genkin, V. N., and Soustov, L. V., Two-photon spectroscopy of proustite (Ag_3AsS_3), *Sov. J. Quantum Electron.* 6(4), 409 (1976).
25. Aleksandrov, A. P., Bredikhin, V. I., and Genkin, V. N., Two-photon absorption spectrum of proustite, *Sov. Phys. Solid State* 17(8), 1645 (1976).
26. Hanna, D. C., and Turner, A. J., Nonlinear absorption measurements in proustite (Ag_3AsS_3) and CdSe , *Opt. Quantum Electron.* 8, 213 (1976).
27. Casalboni, M., Crisanti, F., Francini, R., and Grassano, U. M., Two-photon spectroscopy in AgCl , *Solid State Commun.* 35, 833 (1980).
28. Catalano, I. M., Cingolani, R., and Lepore, M., Two-photon absorption spectra of direct and indirect materials: ZnO and AgCl , *Phys. Rev. B* 33, 7270–7273 (1986).
29. Miller, A., and Ash, G. S., Two-photon absorption and short pulse stimulated recombination in AgGaSe_2 , *Opt. Commun.* 33(3), 297 (1980).
30. Dinges, R., Fröhlich, D., and Uihlein, Ch., Two-photon absorption of anisotropic exitons in $\beta\text{-AgI}$, *Phys. Status Solidi (B)* 76, 613 (1976); Dinges, R., and Fröhlich, D., Polarizaton tuning by two-photon Stark effect in wurtzite AgI , *Solid State Commun.* 19, 61 (1976).
31. Kim, Y. P., and Hutchinson, M. H. R., Intensity-induced nonlinear effects in UV window materials, *Appl. Phys. B* 49, 469–478 (1989).
32. Nasirov, U., Two-photon absorption spectrum of crystalline and glassy As_2S_3 , *Sov. Phys. Semicond.* 12(6), 720 (1978).
33. Liu, P., Yen, R., and Bloembergen, N., Two-photon absorption coefficients in UV window and coating materials, *Appl. Opt.* 18(7), 1015 (1979).
34. Taylor, A. J., Gibson, R. B., and Roberts, J. P., Two-photon absorption at 248 nm in ultraviolet window materials, *Opt. Lett.* 13, 814–816 (1988).
35. Shablaev, S. I., Danishevskii, A. M., and Subashiev, V. K., The band structure of the oxygen-octahedral ferroelectrics BaTiO_3 , SrTiO_3 , and KTaO_3 , determined from data of two-photon spectroscopy, *Sov. Phys. JETP* 59, 1256–1263 (1985).
36. Boggess, T. F., White, J. O., and Valley, G. C., Two-photon absorption and anisotropic transient energy transfer in BaTiO_3 with 1-psec excitation, *J. Opt. Soc. Am. B* 7, 2255–2258 (1990).
37. Casalboni, M., Francini, R., Grassano, U. M., Musilli, C., and Pizzoferrato, R., Two-photon excitation of the luminescence in bismuth germanate, *J. Lumin.* 31–32, 93–95 (1984).
38. Catalano, I. M., Cingolani, R., and Lepore, M., Spectral behaviour of the two-photon absorption coefficient in ZnO , CuCl and $\text{Bi}_4\text{Ge}_3\text{O}_{12}$, *Il Nuovo Cimento* 9D, 1313–1322 (1987).
39. Catalano, I. M., Cingolani, A., Cingolani, R., and Lepore, M., Interband two-photon absorption mechanisms in direct and indirect gap materials, *Phys. Script.* 37, 579–582 (1988).
40. Casalboni, M., Francini, R., Lohmeier, F. J., and Grassano, U. M., Two-photon absorption of bismuth germanate, *Phys. Status. Solidi* B151, 347–352 (1989).
41. Liu, P., Yen, R., and Bloembergen, N., Dielectric breakdown threshold, two-photon absorption, and other optical damage mechanisms in diamond, *IEEE J. Quantum Electron.* QE-14(8), 574 (1978).
42. Dadap, J. I., Focht, G. B., Reitze, D. H., and Downer, M. C., Two-photon absorption in diamond and its application to ultraviolet femtosecond pulse-width measurement, *Opt. Lett.* 16, 499–501 (1991).
43. Sheik-Bahae, M., DeSalvo, J. R., Said, A. A., Hagan, D. J., Soileau, M. J., and Van Stryland, E. W., Nonlinear refraction in UV transmitting materials, *NIST Special Publication, Proceedings of the Boulder Damage Symposium*, Boulder, CO (1991).
44. Listsa, M. P. Mozol, P. E., and Fekeshagazi, I. V., Laser pulse lengthening with the aid of nonlinearly absorgin semiconductors CdP_2 and ZnP_2 , *Sov. J. Quantum Electron.* 4(1), 110 (1974).
45. Mozol, P. E., Patskun, I. I., Sal'kov, E. A., and Fekeshgazi, I. V., Two-photon and two-step transitions in the wide-band semiconductors CdP_2 , ZnP_2 , and ZnSe , *Bull. Acad. Sci. U.S.S.R. Phys. Ser.* 45(6), 1092 (1981).

46. Mak, P. S., Davis, C. C., Forster, B. J., and Lee, C. H., Measurements of picosecond light pulses with two-photon photoconductivity detector, *Rev. Sci. Instrum.* 51, 647 (1980).
47. Konyukhov, V. K., Kulveskii, L. A., and Prokhorov, A. M., Two-photon absorption spectrum by excitons in CdS near the fundamental absorption edge, *Sov. Phys. Doklady* 12(4) (1967).
48. Regensburger, P. J., and Panizza, E., Two-photon absorption spectrum of CdS, *Phys. Rev. Lett.* 18(4), 113 (1967).
49. Arsen'ev, V. V., Dneprovskii, V. S. Klyshko, D. N., and Penin, A. N., Nonlinear absorption and limitation of light intensity in semiconductors, *Sov. Phys. JETP* 29(3), 413 (1969).
50. Bespalov, M. S., Kulevskii, L. A., Makarov, V. P., Prokhorov, M. A., and Tikhonov, A. A., Anisotropy in the two-photon absorption spectrum in CdS, *Sov. Phys. JETP* 28, 77 (1969).
51. Pradere, F., and Mysyrowicz, A., Two-photon absorption spectrum by excitons in CdS, Proceedings Tenth International Conference on Physics of Semiconductors, Keller, S. P., Ed. (U.S. Atomic Energy Commission, 1970), p. 101.
52. Baltrameynas, R., Vaitkus, Y. Y., Vishchakas, Y. K., and Gavryushin, V. I., Dependence of the two-photon absorption coefficient on the thickness of CdS single crystals, *Opt. Spectrosc.* 36(6), 714 (1974).
53. Bredikhin, V. I., and Genkin, V. N., Two-photon absorption spectrum of CdS, *Sov. Phys. Solid State* 16(5), 860 (1974).
54. Svorec, R. W., and Chase, L. L., Two-photon absorption in the vicinity of the exciton absorption in CdS, *Solid State Commun.* 17, 803 (1975).
55. Penzkofer, A., Falkenstein, W., and Kaiser, W., Two-photon spectroscopy using picosecond light continua, *Appl. Phys. Lett.* 28(6), 319 (1976).
56. Itoh, T., Nozue, Y., and Ueta, M., Giant two-photon resonance Raman scattering in CdS, *J. Phys. Soc. Jpn.* 40(6), 1791 (1976).
57. Baltrameynas, R., Gavryushin, V., and Vaitkus, Yu., *Sov. Phys. Solid State* 18, 660 (1976).
58. Ngyen, V. T., Damen, T. C., and Gornik, E., Two-photon absorption spectroscopy of the intrinsic exciton fine structure in CdS, *Appl. Phys. Lett.* 30(1), 33 (1977).
59. de Araujo, C. B., and Lotem, H., New measurements of the two-photon absorption in GaP, CdS, and ZnSe relative to Raman cross sections, *Phys. Rev. B* 18(1), (1978).
60. Jackel, J., and Mahr, H., Nonlinear optical measurements in the excitonic region of CdS at 4.2 K, *Phys. Rev. B* 17(8), 3387 (1978).
61. Catalano, I. M., and Cingolani, A., Non-linear self-action and absolute two-photon absorption coefficient in CdS, *Solid State Commun.* 34, 761 (1980); Catalano, I. M., Cingolani, A., and Minafra, A., Transmittance, luminescence, and photocurrent in CdS under two-photon excitation, *Phys. Rev. B* 9(2), 707 (1974).
62. Kobbe, G., and Klingshirin, C., Quantitative investigation of the two-photon absorption of ruby-laser-light in various semiconductors, *Z. Phys.* B37, 9 (1980).
63. Baltrameynas, R., Vaitkus, Yu., Vishchakas, Yu., Gavryushin, V., Kubertavichus, V., and Rachyukaitus, G., Spectral and polarization investigations of two-photon absorption of group A²B⁶, *Bull. Acad. Sci. U.S.S.R. Phys. Ser.* 46, 1–9 (1982).
64. Seiler, D. G., Heiman, D., Feigenblatt, R., Aggarwal, R. L., and Lax, B., Two-photon magnetospectroscopy of A-exciton states in CdS, *Phys. Rev.* 25, 7666–7677 (1982).
65. de Souza, M. E., and De Araujo, C. B., Two-photon absorption in hexagonal-CdS, *Solid State Commun.* 48, 967–970 (1983).
66. Borshch, A. A., Brodin, M. S., Marchevskii, F. N., and Semioshko, V. N., Anisotropy of the nonlinear susceptibility of cadmium sulfide crystals, *Sov. J. Quantum Electron.* 14, 1367–1371 (1985).
67. Van Stryland, E. W., Vanherzele, H., Woodall, M. A., Soileau, M. J., Smirl, A. L., Guha, S., and Boggess, T. F., Two-photon absorption, nonlinear refraction, and optical limiting in semiconductors, *Opt. Eng.* 24, 613–623 (1985).

68. Basov, N. G., Grasyuk, A. Z., Efimov, V. F., Zubarev, I. G., Katulin, V. A., and Popov, J. M., Semiconductor lasers using optical pumping, *J. Phys. Soc. Jpn. Suppl.* 21, 276 (1966).
69. Grasyuk, A. Z., Zubarev, I. G., and Menster, A. N., Anistropy of two-photon absorption in optical excitation of CdSe semiconductor lasers, *Sov. Phys. Solid State* 10(2), 427 (1968).
70. Ralston, J. M., and Chang, R. K., Optical limiting in semiconductors, *Appl. Phys. Lett.* 15, 164 (1969); Nd:Laser induced absorption in semiconductors and aqueous PrCl_3 and NdCl_3 , *Opt. Electron.* 1, 182 (1969).
71. Bryukner, F., Dneprovskii, V. S., and Khattatov, Z. Q., Two-photon absorption in cadmium selenide, *Sov. J. Quantum Electron.* 4, 749 (1974).
72. Dneprovskii, V. S. and Ok, S. M., Role of absorption by nonequilibrium carriers in determination of two-photon absorption coefficient of CdSe and GaAs crystals, *Sov. J. Quantum Electron.* 6(3), 298 (1976).
73. Bechtel, J. H., and Smith, W. L., Two-photon absorption in semiconductors with picosecond laser pulses, *Phys. Rev. B* 13(8), 3515 (1976).
74. Bass, M., Van Stryland, E. W., and Stewart, A. F., Laser calorimetric measurement of two-photon absorption, *Appl. Phys. Lett.* 34(2), 142 (1979).
75. Van Stryland, E. W., and Woodall, M. A., Photoacoustic measurement of nonlinear absorption in solids, *NBS Spec. Publ.* 620, 50 (1980).
76. Ananchenko, V. V., Vlasenko, Yu. V., Onishchenko, N. A., Polishchuk, S. V., Stolyarenko, A. V., Pendyur, S. A., and Talenskii, O. N., Nonlinear absorption spectroscopy of CdSe single crystals, *Sov. J. Quantum Electron.* 18, 1195–1198 (1988).
77. Penzkofer, A., Schuffner, M., and Bao, X., Two-photon absorption and resonant non phase-matched second harmonic generation in CdSe, *Opt. Quantum Electron.* 22, 351–367 (1990).
78. Brodin, M. S., Demidenko, Z. A., Dmitrenko, K. A., and Rexnichenko, V. Y., Temperature dependence of the two-photon absorption coefficient of $\text{CdS}_x\text{Se}_{1-x}$ crystals near resonance, *Sov. J. Quantum Electron.* 5(7), 861 (1975); Brodin, M. S., Dmitrenko, K. A., and Rexnichenko, V. Y., Two-photon absorption in $\text{CdS}_x\text{Se}_{1-x}$ mixed crystals at ruby laser frequencies, *Sov. Phys. Solid State* 13(6), 1328 (1971).
79. Brodin, M. S., Demidenko, Z. A., Dmitrenko, K. A., Rexnichenko, V. Y., and Strshnikova, M. I., Frequency dependences of the one- and two-photon absorption of crystals with nonparabolic conduction bands similar to CdS, *Sov. Phys. Semicond.* 8, 43 (1974).
80. Bepko, S. J., Anistropy of two-photon absorption in GaAs and CdTe, *Phys. Rev. B* 12(2), 669 (1975).
81. Catalano, I. M., and Cigolani, A., Non-parabolic band effect on two-photon absorption in ZnSe and CeTe, *Solid State Commun.* 43(3), 213 (1982); Catalano, I.M., and Cingolani, A., Evidence of nonparabolic band effect on two photon spectrum of ZnSe, *Phys. Rev. B* 28, 1130–1131 (1983).
82. Baltrameynas, R., Vaitkus, Yu., and Pyatrauskas, M., Absorption of picosecond light pulses by CdTe single crystals, *Opt. Spectrosc. (USSR)* 53, 341–342 (1983).
83. Ruckmann, I., Kornack, J., Kolenda, J., and Petrauskas, M., Transient energy transfer in ps two-photon absorption in CdTe at room temperature, *Phys. Status Solidi* 158, 769–780 (1990).
84. Said, A. A., Sheik-Bahae, M., Hagan, D. J., Wei, T. H., Wang, J., Young, J., and Van Stryland, E. W., Determination of bound and free-carrier nonlinearities in ZnSe, GaAs, CdTe, and ZnTe, *J. Opt. Soc. Am. B* 9, 405–414 (1992).
85. Fröhlich, D., Staginnus, B., and Onodera, Y., Two-photon spectroscopy in CsI and CsBr, *Phys. Status Solidi* 40, 547 (1970).
86. Hopfield, J. J., Worlock, J. M., and Park, K., Two-quantum absorption spectrum of KI, *Phys. Rev. Lett.* 11(9), 414 (1963).
87. Hopfield, J. J., and Worlock, J. M., Two-quantum absorption spectrum of KI and CsI, *Phys. Rev.* 135(5A), A1455 (1965).

88. Fröhlich, D. M., Two-photon spectroscopy in solids, in *Proceedings Tenth International Conference On Physics of Semiconductors*, Keller, S. P., Ed., U.S. Atomic Energy Commission (1970, 95).
89. Chen, C. H., and McCann, M. P., Luminescence of alkali halide crystals by multiphoton excitation, *Chem. Phys. Lett.* 126, 54–57 (1986).
90. Chen, C. M., McCann, M. P., and Wang, J. C., Room temperature two-photon induced luminescence in pure CsI, *Solid State Commun.* 61, 559 (1987).
91. Deich, R., Noack, F., Rudolph W., and Postovalov, V., Two-photon luminescence in CsI(Na) under UV femtosecond pulse excitation, *Solid State Commun.* 74, 269–273 (1990).
92. Rustagi, K. C., Pradère, F., and Mysyrowicz, A., Two-photon absorption in Cu₂O, *Phys. Rev. B* 8(6), 2721 (1973).
93. Antonetti, A., Astier, R., Martin, J. L., Migus, A., Hulin, D., and Mysyrowicz, A., Picosecond spectroscopy in Cu₂O: exciton dynamics and two-photon absorption, *Opt. Commun.* 38, 431 (1981).
94. Fröhlich, D., Two- and three-photon spectroscopy in solids, *Phys. Script.* T35, 125–128 (1991).
95. Marange, C., Bivas, A., Levy, R., Grun, J. B., and Schwab, C., Two-photon absorption in CuBr, *Opt. Commun.* 6(2), 138 (1972).
96. Fröhlich, D., Staginnus, B., and Schönher, E., Two-photon absorption spectrum of CuCl, *Phys. Rev. Lett.* 19(18), 1032 (1967).
97. Bivas, A., Marange, C., Grun, J. B., and Schwab, C., Two-photon absorption in CuCl, *Opt. Commun.* 6(2), 142 (1972).
98. Gale, G. M., and Mysyrowicz, A., Direct creation of excitonic molecules in CuCl by giant two-photon absorption, *Phys. Rev. Lett.* 32(13), 727 (1974).
99. Fröhlich, D., and Volkenandt, H., Determination of r₃ valence band in CuCl by two-photon absorption, *Solid State Commun.* 43(3), 189 (1982).
100. Fröhlich, D., and Volkenandt, H., Determination of r₃ valence band in CuCl by two-photon absorption, *Solid State Commun.* 43, 189–191 (1982).
101. Shalaev, S. I., Two-photon spectroscopy of light absorption by electronic states in iron borate (FeBO₃), *Sov. Phys. JETP* 70, 1105–1108 (1990).
102. Lee, C. C., and Fan, H. Y., Two-photon absorption and photoconductivity in GaAs and InP, *Appl. Phys. Lett.* 20, 18 (1972).
103. Kleinman, D. A., Miller, R. C., and Nordland, W. A., Two-photon absorption of Nd laser radiation in GaAs, *Appl. Phys. Lett.* 23(5), 243 (1973).
104. Lee, C. C., and Fan, H. Y., Two-photon absorption with exciton effect for degenerate valence bands, *Phys. Rev. B* 9(8), 3502 (1974).
105. Grasyuk, A. Z., Zubarev, I. G., Mironov, A. B., and Poluektov, I. A., Spectrum of two-photon interband absorption of laser radiation in semiconducting GaAs, *Sov. J. Quantum Electron.* 5(8), 997 (1976).
106. Zubarev, I. G., Mironov, A. B., and Mikhailov, S. I., Influence of deep impurity levels on nonlinear absorption of light GaAs, *Sov. Phys. Semicond.* 11(2), 239 (1977).
107. van der Ziel, J. P., Two-photon absorption spectra of GaAs with 2ω near the direct band gap, *Phys. Rev. B* 16(6), 2775 (1977).
108. Saissy, A., Azema, A., Botineau, J., and Gires, F., Absolute measurement of the 1.06 μm two-photon absorption coefficient in GaAs, *Appl. Phys.* 15, 99 (1978).
109. Bosacchi, B., Bessey, J. S., and Jain, F. C., Two-photon absorption of neodymium laser radiation in gallium arsenide, *J. Appl. Phys.* 49(8), 4609 (1978).
110. Bendorius, R. A., and Mal dutis, E. K., Nonlinear absorption of laser radiation in InP and GaAs, *Sov. Phys.-Collection* 23, 69–72 (1983).
111. Akhmanov, S. A., Zheludev, N. I., and Zadoyan, R. S., New amplitude and polarization nonlinear effects for interaction of picosecond light pulses with semiconductor crystals, *Bull. Acad. Sci. U.S.S.R., Phys. Ser.* 48, 103–108 (1984).

112. Boggess, T. F., Smirl, A. L., Moss, S. C., Boyd, I. A. and Van Stryland, E. W., Optical limiting in GaAs, *IEEE J. Quantum Electron.* QE-21, 488–494 (1985).
113. Penzkofer, A., and Bugayev, A. A., Two-photon absorption and emission dynamics of bulk GaAs, *Opt. Quantum Electron.* 21, 283–306 (1989).
114. Valley, G. C., Boggess, T. F., Dubard, J., and Smirl, A. L., Picosecond pump-probe technique to measure deep-level, free-carrier, and two-photon cross sections in GaAs, *J. Appl. Phys.* 66, 2407–2413 (1989).
115. Hai-Mimg, Ma, Self-transitions of picosecond light pulses in GaAs, in Chinese, *Chin. J. Phys.* 38, 1530–1533 (1989).
116. Bugaev, A. A., Dunaeva, T. Yu., and Lukoshkin, V. A., Influence of nonlinear refraction, absorption by free carriers, and multiple reflection on the determination of the two-photon absorption coefficient of GaAs, *Sov. Phys. Solid State* 31, 2031–2034 (1990).
117. Aitchison, J. S., Oliver, M. K., Kapon, E., Colas E., and Smith, P. W. E., Role of two-photon absorption in ultrafast semiconductor optical switching devices, *Appl. Phys. Lett.* 56, 1305–1307 (1990).
118. Yee, J. H., and Chan, H. H. M., Two-photon indirect transitions in GaP crystal, *Opt. Commun.* 10, 56 (1974).
119. Lotem, H., and de Araujo, C. B., Absolute determination of the two-photon absorption coefficient relative to the inverse Raman cross section, *Phys. Rev. B* 16(4), 1711 (1977).
120. Catalano, I. M., Cingolani, A., and Minafra, A., Multiphoton processes in layered structures, *Il Nuovo Cimento* 38B(2), 579 (1977); Adduci, F., Catalano, I. M., Cingolani, A., and Minafra, A., Direct and indirect two-photon processes in layered semiconductors, *Phys. Rev. B* 15(2), 926 (1977).
121. Zubov, B. V., Murina, T. M., Olovyanin, B. R., and Prokhorov, A. M., Investigation of nonlinear absorption in germanium, *Sov. Phys. Semicond.* 4(4), 559 (1971).
122. Wenzel, R. G., Arnold, G. P., and Greiner, N. R., Nonlinear loss in Ge in the 2.5–4 μm range, *Appl. Opt.* 12(10), 2245 (1973).
123. Miller, A., Johnston, A., Dempsey, J., Smith, J., Pidgeon, C. R., and Holah, G. D., Two-photon absorption in InSb and $Hg_{1-x}Cd_xTe$, *J. Phys. C* 12, 4839 (1979).
124. Johnston, A. M., Pidgeon, C. R., and Dempsey, J., Frequency dependence of two-photon absorption in InSb and $Hg_{1-x}Cd_xTe$, *Phys. Rev. B* 22(2), 825 (1980).
125. Pelant, I., Ambroz, M., Hala, J., Kohlova, V., and Barta, C., Two-photon absorption in Hg_2Cl_2 crystals, *Phys. Lett.* 107A, 145–148 (1985).
126. Pelant, I., Lhotska, V., Hala, J., Ambroz, M., Kohlova, V., and Barta, C., Two-photon spectroscopy of Hg_2Cl_2 crystals, *J. Lumin.* 35, 37–42 (1986).
127. Pelant, I., Popova, M. N., Hala, J., Ambroz, M., Lhotska, V., and Vacek, K., Two-photon absorption and energy band structure of orthorhombic Hg_2Cl_2 crystals, *Czech. J. Phys.* B37, 1183–1197 (1987).
128. Areshev, I. P., Subashiev, V. K., and Faradzhev, B. G., Linear-circular dichroism of two-photon absorption and self-defocusing of neodymium laser radiation in n-type InP crystals, *Sov. Phys. Semicond.* 22, 199–200 (1987).
129. Fossom, H. J., and Chang, D. B., Two-photon excitation rate in indium antimonide, *Phys. Rev. B* 8(6), 2842 (1973).
130. Areshev, I. P., Guseinaliev, M. G., Danishevskii, A. M., Kochegarov, S. F., and Subashiev, V. K., Investigation of nonlinear absorption of light in indium antimonide by the two-beam method, *Sov. Phys. Solid State* 22(5), 849 (1980); Double-beam linear dichroism investigation of the two-photon absorption in InSb, *Phys. Status Solidi (B)* 102, 383 (1980).
131. Seiler, D. G., Goodwin, M. W., and Weiler, M. H., High-resolution two-photon spectroscopy in InSb at milliwatt cw powers in a magnetic field, *Phys. Rev. B* 23(12), 6806 (1981).
132. Sheik-bahae, M., Rossi, T., and Kwok, H. S., Frequency dependence of the two-photon absorption coefficient in InSb: tunneling effects, *J. Opt. Soc. Am. B* 4 1964–1969 (1987).

133. Sheik-bahae, M., and Kwok, H. S., Picosecond CO₂ laser-induced self-defocusing in InSb, *IEEE J. Quantum Electron.* QE-23 1974–1980 (1987).
134. Geller, M., DeTemple, T. A., and Taylor, H. F., Quantum efficiency for F-center production by two-photon absorption, *Solid State Commun.* 7, 1019 (1969).
135. Fröhlich, D., and Staginnus, B., New assignment of band gap in the alkali bromides by two-photon spectroscopy, *Phys. Rev. Lett.* 19(9), 496 (1967).
136. Prior, Y., and Vogt, H., Measurements of uv two-photon absorption relative to known Raman cross sections, *Phys. Rev. B* 19, 5388 (1979).
137. de Araujo, C. B., and Lotem, H., Ultraviolet two-photon absorption in alkali-halides, *Phys. Rev. B* 26, 1044 (1982).
138. Piacentini, M., Two-photon absorption using synchrotron radiation, *Phys. Script.* T19, 612–616 (1987).
139. Reintjes, J. F., and Eckardt, R. C., Two-photon absorption on ADP and KD*P at 266.1 nm, *IEEE J. Quantum Electron.* QE-13(9), 791 (1977); Efficient harmonic generation from 532 to 266 nm in ADP and KD*P, *Appl. Phys. Lett.* 30(2), 91 (1977).
140. Oudar, J., Schwartz, C. A., and Batifol, E. M., Influence of two-photon absorption on second-harmonic generation in semiconductors. II. Measurement of two-photon absorption in tellurium, *IEEE J. Quantum Electron.* QE-11(8), 623 (1975).
141. Penzkofer, A., and Kaiser, W., Nonlinear loss in Nd-doped laser glass, *Appl. Phys. Lett.* 21(9), 427 (1972).
142. Park, K., and Stafford, R. G., Evidence for an optical transition at a noncentrosymmetric point of the Brillouin zone in KI, *Phys. Rev. Lett.* 22(26), 1426 (1969).
143. Stafford, R. G., and Park, K., LO-phonon-assisted absorption in KI, *Phys. Rev. Lett.* 25(24), 1652 (1970); LO-phonon-assisted transitions in the two-photon absorption spectrum of KI, *Phys. Rev. B* 4(6), 2006 (1971).
144. Catalano, I. M., Cingolani, A., and Minafra, A., Multiphoton transitions in ionic crystals, *Phys. Rev. B* 5, 1629 (1972).
145. Blau, W., and Penzkofer, A., Intensity detection of picosecond ruby laser pulses by two-photon absorption, *Opt. Commun.* 36(5), 419 (1981).
146. von der Linde, D., Glass, A. M., and Rodgers, K. F., High sensitivity optical recording in KTN by two-photon absorption, *Appl. Phys. Lett.* 26(1), 22 (1975).
147. DeSalvo, R., Hagan, D. J., Sheik-Bahae, M., Stegeman, G., and Van Stryland, E. W., Self-focusing and self-defocusing by cascaded second-order effects in KTP, *Opt. Lett.* 17, 28–30 (1992).
148. Bityurin, N. M., Bredikhin, V. I., and Genkin, V. N., Nonlinear optical absorption and energy structure of LiNbO₃ and α -Li₂O₃ crystals, *Sov. J. Quantum Electron.* 8(11), 1377 (1978); Two-photon absorption and the characteristics of the energy spectrum of LiNbO₃ and α -Li₂O₃ crystals, *Bull. Acad. Sci. U.S.S.R. Phys. Ser. USA* 43(2), (1979).
149. Kurz, H., and Von der Linde, D., Nonlinear optical excitation of photovoltaic LiNbO₃, *Ferroelectrics* 21, 621 (1978).
150. Fröhlich, D., and Kenlies, R., Two-photon absorption in PbI₂, *Il Nuovo Cimento* 38B(2), 433 (1977).
151. Efendiev, Sh., Gavryushin, V., Raciukaitis, G., Puzonas, G., Kazlauskas, A., Darvishov, N., and Shakhdgan, S., Two-photon spectroscopy of PbMoO₄ single crystals, *Phys. Status Solidi* B156, 697–704 (1989).
152. Baltrameynas, R., Gavryushin, V., Rachyukaitis, G., Puzonas, G., Kaslauskas, A., Efendiev, Sh., Darvishov, N., and Bagiev, V., Indirect interband transitions in PbMoO₄ single crystals. Two-photon spectroscopy, *Sov. Phys. Solid State* 31, 1455–1456 (1990).
153. Geusic, J. E., Singh, S., Tipping, D. W., and Rich, T. C., Three-photon stepwise optical limiting in silicon, *Phys. Rev. Lett.* 19(19), 1126 (1967).
154. Panizza, E., Two-photon absorption in ZnS, *Appl. Phys. Lett.* 10(10), 265 (1967).

155. Reintjes, J. F., and McGroddy, J. C., Indirect two-photon transitions in Si at 1.06 μm , *Phys. Rev. Lett.* 30(19), 901 (1973).
156. Boggess, T. F., Bihnert, K. M., Mansour, K., Moss, S. C., Boyd, I. A., and Smirl, A. L., Simultaneous measurement of the two-photon coefficient and free-carrier cross section above the bandgap of crystalline silicon, *IEEE J. Quantum Electron.* QE-22, 360–368 (1986).
157. Reitze, D. H., Zhang, T. R., Wood, Wm. M., and Downer, M. C., Two-photon spectroscopy of silicon using femtosecond pulses at above-gap frequencies, *J. Opt. Soc. Am. B*7, 84–89 (1990).
158. Downer, M. C., Reitze, D. H., and Focht, G., Ultrafast laser probe of interband absorption edges in 3D and 2D semiconductors, *SPIE* 1282, 121–131 (1990).
159. Lisitsa, M. P., Kulish, N. R., and Stolyarenko, A. V., Two-photon absorption spectrum of α -SiC(6H), *Sov. Phys. Semicond.* 14(10), 1208 (1980).
160. Fröhlich, D., and Kenkliés, R., Band-gap assignment in SnO_2 by two-photon spectroscopy, *Phys. Rev. Lett.* 41(25), 1750 (1978).
161. Maker, P. D., and Terhune, R. W., Study of optical effects due to an induced polarization third order in the electric field strength, *Phys. Rev.* 137(3A), A801 (1965).
162. Shablaev, S. I., Danishevskii, A. M., Subashiev, V. K., and Babashkin, A. A., Investigation of the energy band structure of SrTiO_3 by the two-photon spectroscopy method, *Sov. Phys. Solid State* 21(4), 662 (1979).
163. Lee, J. H., Scarparo, M. A. F., and Song, J. J., Two-photon absorption measurements of crystals relative to the Raman cross section, Proceedings of the VIIth International Conference on Raman Spectroscopy, Ottawa, Canada (1980), p. 684.
164. Shablev, S. I., and Subashiev, V. K., Band structure change in the transition from the cubic to the tetragonal phase in single-domain SrTiO_3 , determined from two-photon absorption spectra, *Sov. Phys. JETP* 64, 846–850 (1986).
165. Matsuoka, M., and Yajima, T., Two-photon absorption spectrum in thallous chloride, *Phys. Lett.* 23(1), 54 (1966).
166. Waff, H. S., and Park, K., Structure in the two-photon absorption spectrum of TiO_2 (rutile), *Phys. Lett.* 32A(2), 109 (1970).
167. Penzkofer, A., and Falkenstein, W., Direct determination of the intensity of picosecond light pulses by two-photon absorption, *Opt. Commun.* 17(1) (1976).
168. Matsuoka, M., Angular dependence of two-photon absorption in thallous chloride, *J. Phys. Soc. Jpn.* 23(5), 1028 (1967).
169. Fröhlich, D., Staginnus, B., and Thurm, S., Symmetry assignments of two-photon transitions in TiCl , *Phys. Status Solidi* 40, 287 (1970).
170. Fröhlich, D., Treusch, J., and Kottler, W., Multiphonon processes in the two-photon absorption of TiCl and the temperature dependence of the band edge, *Phys. Rev. Lett.* 29(24), 1603 (1972).
171. Bakos, J. S., Foldes, I. B., Hevesi, I., Kovacs, J., Nanai L., and Szil, E., Two-photon absorption in V_2O_5 single crystals with q-switched ruby laser pulses, *Appl. Phys. Lett.* A37, 247–249 (1985).
172. Shablaev, S. I., and Pisarev, R. V., Nonlinear optical spectroscopy of electronic states in the yttrium iron garnet $\text{Y}_3\text{Fe}_5\text{O}_{12}$, *JETP Lett.* 45, 626–631 (1987).
173. Brodin, M. S., and Goer, D. B., Two-photon absorption of ruby laser radiation by semiconductor crystals of ZnSe and $\text{Zn}_x\text{Cd}_{1-x}\text{Se}$, *Sov. Phys. Semicond.* 5(2), 219 (1971).
174. Baltrameynas, R., Vaikus, Yu., Gavryushin, V. I., and Dmitrenko, K. A., Two-photon absorption spectra of mixed $\text{Zn}_{0.1}\text{Cd}_{0.9}\text{S}$ single crystals, *Sov. Phys. Semicond.* 11, 60–61 (1977).
175. Staginus, G., Fröhlich, D., and Caps, T., Automatic 2-photon spectrometer, *Rev. Sci. Instrum.* 39(8), 1129, (1968).
176. Mollwo, E., and Pensl, G., Two-photon absorption in ZnO -crystals, *Z. Phyzik* 228, 193 (1969).
177. Dinges, R., Fröhlich, D., Staginnus, G., and Staude, W., Two-photon magnetoabsorption in ZnO , *Phys. Rev. Lett.* 25(14), 922 (1970).

178. Kaule, W., Polarization dependence of the two quantum absorption spectrum of intrinsic excitons in ZnO, *Solid State Commun.* 9, 17 (1971).
179. Baltrameynas, R., Vishchakas, Yu., Gavryushin, V., Kubertavichyus, V., and Tichina, I., Investigation of the spectral dependences of two-photon absorption in tetragonal ZnP₂ single crystals, *Sov. Phys. Solid State* 25, 2131–2133 (1984).
180. Mozol, P. E., Patskun, I. I., Salkov, E. A., and Skubenko, N. A., Optical absorption induced by pulsed laser radiation in tetragonal ZnP₂ crystals, *Sov. Phys. Semicond.* 20, 313–315 (1986).
181. Park, K., and Waff, H. S., Two-photon absorption spectrum of ZnS, *Phys. Lett.* 28A(4), 305 (1968).
182. Baltrameynas, R., Gavryushin, V., and Vaitkus, Y., Frequency dependence of the coefficient of two-photon absorption in ZnSe, *Sov. Phys. Solid State* 17(10), 2020 (1976).
183. Baltrameynas, R., Vaitkus, Y., and Gavryushin, V., Influence of impurities on the two-photon absorption spectrum of ZnSe single crystals, *Sov. Phys. Solid State* 18(10), 1723 (1976).
184. Borshch, V. V., Mozol', P. E., Sal'kov, E. A., Patskun, I. I., and Fekeshgazi, I. V., Nonlinear absorption spectra of copper-doped ZnSe single crystals, *Sov. Phys. Semicond.* 16, 684–687 (1982).
185. Borshch, V. V., Mozol, P. E., Patskun, I. I., and Fekeshgazi, I. V., Influence of copper impurities on two-photon absorption of light in ZnSe, *Sov. Phys. Semicond.* 16, 213–214 (1982).
186. Yablonskii, G. N., Photoconductivity of laser-excited zinc telluride, *Sov. Phys. Semicond.* 8, 881–882 (1975).
187. Catalano, I. M., and Cingolani, A., Absolute two-photon absorption line shape in ZnTe, *Phys. Rev. B* 19(2), 1049 (1979).
188. Baltrameynas, R., Vaitkus, J., and Gavryushin, V., Light absorption by nonequilibrium, two-photon generated, free and localized carriers in ZnTe single crystals, *Sov. Phys. JETP* 60, 43–48 (1984).
189. Brodin, M. S., Shevel's, S. G., Kodzhespirov, F. F., and Mozharovskii, L. A., Two-photon absorption of ruby laser radiation in mixed Zn_xCd_{1-x}S crystals, *Sov. Phys. Semicond.* 5(12), 2047 (1972).
174. Mansour, N., Mansour, K., Soileau, M. J., and Van Stryland, E. W., Observation of two-photon absorption prior to laser induced damage in dielectric ZrO₂, *NIST Special Publication, No. 756, Proceedings of the Boulder Damage Symposium*, p. 501, Boulder, CO (1987).
191. van der Ziel, J. P., and Gossard, A. C., Two-photon absorption spectrum of AlAs-GaAs monolayer crystals, *Phys. Rev. B* 17(2), 765 (1978).

1.9.3 Second Harmonic Generation Coefficients

Crystal System—Cubic			
Cubic material	Symmetry class	dim (pm/V)	Wavelength λ (μm)
NaBrO ₃	23	$d_{14} = 0.19$	0.6943
NaClO ₃	23	$d_{14} = 0.46$	0.6943
AlSb	-43m	$d_{14} = 49 \pm 36$	1.058
Bi ₄ Ge ₃ O ₁₂	-43m	$d_{14} = 1.28$	1.064
CdTe	-43m	$d_{14} = 167.6 \pm 63$ $d_{14} = 59.0 \pm 24$	10.6 28.0
CuBr	-43m	$d_{14} = 8.04 \pm 30\%$ $d_{14} = -4.38 \pm 20\%$ $d_{14} = -6.37 \pm 20\%$ $d_{14} = -6.53 \pm 20\%$	10.6 1.318 1.064 0.946
CuCl	-43m	$d_{14} = 6.7 \pm 30\%$ $d_{14} = -4.0 \pm 20\%$ $d_{14} = -3.97 \pm 20\%$ $d_{14} = -3.47 \pm 20\%$	10.6 1.318 1.064 0.946
CuI	-43m	$d_{14} = 8.04 \pm 30\%$ $d_{14} = -5.47 \pm 20\%$ $d_{14} = -6.08 \pm 20\%$ $d_{14} = -6.04 \pm 20\%$	10.6 1.318 1.064 0.946
GaAs	-43m	$d_{14} = 134.1 \pm 41.9$ $d_{14} = 209.5 \pm 13.3$ $d_{14} = 256.5$	10.6 1.058 0.694
GaP	-43m	$d_{14} = 71.8 \pm 12.3$ $d_{36} = 59.5 \pm 6.0$ $d_{14} = +70.6$	1.058 1.318 3.39
GaSb	-43m	$d_{14} = +628 \pm 6.3$	10.6
InAs	-43m	$d_{14} = 364 \pm 47$ $d_{14} = 249 \pm 62$	1.058 10.6
InP	-43m	$d_{14} = 143$	1.058
InSb	-43m	$d_{14} = 520 \pm 47$ $d_{14} = 16345 \pm 503$ $d_{14} = 560 \pm 230$	1.058 10.6 28
N ₄ (CH ₂) ₆	-43m	$d_{14} = 4.1$	1.06
β -ZnS	-43m	$d_{14} = 30.6 \pm 8.4$ $d_{36} = 20.7 \pm 1.3$	10.6 1.058

Crystal System—Cubic—*continued*

Cubic material	Symmetry class	dim (pm/V)	Wavelength λ (μm)
ZnSe	−43m	$d_{14} = 78.4 \pm 29.3$ $d_{36} = 26.6 \pm 1.7$	10.6
ZnTe	−43m	$d_{14} = 92.2 \pm 33.5$ $d_{14} = 83.2 \pm 8.4$ $d_{36} = 89.6 \pm 5.7$	10.6 1.058 1.058

Crystal System—Hexagonal

Hexagonal material	Symmetry class	dim (pm/V)	Wavelength λ (μm)
LiIO ₃	6	$d_{31} = \pm 10.17 \pm 0.32$ $d_{33} = -5.15 \pm 0.32$ $d_{31} = -4.96 \pm 0.32$ $d_{33} = -5.54 \pm 0.61$ $d_{31} = -6.82$	0.5145 1.064 1.064 1.318 1.318
LiKSO ₄	6	$d_{31} = 0.38$ $d_{33} = 0.71$	0.6943 0.6943
GaS	6m2	$d_{16} = 135$	0.6943
GaSe	6m2	$d_{22} = 75.4 \pm 10.8$ $d_{16} = 972$	10.6 0.6943
InSe	6m2	$d_{16} = 281$	0.6943
AgI	6mm	$d_{31} = +8.2 \pm 20\%$ $d_{33} = -16.8 \pm 22\%$	1.318 1.318
AlN	6mm	$d_{31} = \leq 0.30$ $d_{33} = 7.42 \pm 35\%$	1.064 1.064
BeO	6mm	$d_{33} = -0.20 \pm 0.01$ $d_{31} = -0.15 \pm 0.01$	1.064 1.064
CdS	6 mm	$d_{33} = 25.8 \pm 1.6$ $d_{31} = -13.1 \pm 0.8$ $d_{15} = 14.4 \pm 0.8$ $d_{33} = +44.0 \pm 12.6$ $d_{31} = -26.4 \pm 6.31$ $d_{15} = 28.9 \pm 7.1$	1.058 1.058 1.058 1.064 1.064 1.064
CdSe	6 mm	$d_{33} = 66.9 \pm 4.2$ $d_{31} = -26.8 \pm 2.7$ $d_{33} = 54.5 \pm 12.6$	1.064 1.064 1.064

Crystal System—Hexagonal System—continued

Hexagonal material	Symmetry class	d_{im} (pm/V)	Wavelength λ (μm)
LiClO ₄ •3H ₂ O	6mm	$d_{31} = +0.22 \pm 20\%$	1.064
		$d_{33} = +0.25 \pm 20\%$	1.064
		$d_{15} = +0.25 \pm 20\%$	1.064
SiC	6mm	$d_{31} = +8.6 \pm 0.9$	1.064
		$d_{33} = -14.4 \pm 1.3$	1.064
		$d_{15} = +8.0 \pm 0.9$	1.064
Zn ₃ AgInS ₅	6mm	$d_{31} = +7.2 \pm 20\%$	1.064
		$d_{33} = \pm 15.9 \pm 20\%$	1.064
Zn ₅ AgInS ₇	6mm	$d_{31} = +9.22 \pm 20\%$	1.064
		$d_{33} = +20.95 \pm 20\%$	1.064
ZnO	6mm	$d_{33} = -5.86 \pm 0.16$	1.058
		$d_{31} = 1.76 \pm 0.16$	1.058
		$d_{15} = 1.93 \pm 0.16$	1.058
α -ZnS	6mm	$d_{33} = 11.37 \pm 0.07$	1.058
		$d_{33} = 37.3 \pm 12.6$	10.6
		$d_{31} = -18.9 \pm 6.3$	10.6
		$d_{15} = 21.37 \pm 8.4$	10.6
		$d_{15} = 6.7 \pm 1.0$	1.064
		$d_{31} = -7.6 \pm 1.5$	1.064
		$d_{33} = +13.8 \pm 1.7$	1.064

Crystal System—Tetragonal

Tetragonal material	Symmetry class	d_{im} (pm/V)	Wavelength λ (μm)
BaTiO ₃	4mm	$d_{33} = 6.8 \pm 1.0$	1.064
		$d_{31} = 15.7 \pm 1.8$	1.064
		$d_{15} = 17.0 \pm 1.8$	1.064
Ba ₆ Ti ₂ Nb ₈ O ₃	4mm	$d_{31} = 9.7 \pm 1.8$	1.064
		$d_{33} = 13.2 \pm 1.8$	1.064
K ₃ Li ₂ Nb ₅ O ₁₅	4mm	$d_{33} = 11.2 \pm 1.6$	1.064
		$d_{31} = 6.18 \pm 1.28$	1.064
		$d_{15} = 5.45 \pm 0.54$	1.064
K _{0.8} Na _{0.2} Ba ₂ Nb ₅ O ₁₅	4mm	$d_{31} = 13.6 \pm 1.6$	1.064
PbTiO ₃	4mm	$d_{33} = 7.5 \pm 1.2$	1.064
		$d_{31} = 37.6 \pm 5.6$	1.064
		$d_{15} = 33.3 \pm 5$	1.064

Crystal System—Tetragonal System—*continued*

Tetragonal material	Symmetry class	dim (pm/V)	Wavelength λ (μm)
SrBaNb ₅ O ₁₅	4mm	$d_{33} = 11.3 \pm 3.3$ $d_{31} = 4.31 \pm 1.32$ $d_{15} = 5.98 \pm 2$	1.064 1.064 1.064
AgGaS ₂	-42m	$d_{36} = 18 \pm 2.7$ $d_{36} = 23.36 \pm 3.52$	10.6 1.064
AgGaSe ₂	-42m	$d_{36} = 37.4 \pm 6.0$ $d_{36} = 67.7 \pm 13$	10.6 2.12
AgInSe ₂	-42m	$d_{36} = 55.9 \pm 10\%$	10.6
CdGeAs ₂	-42m	$d_{36} = 351 \pm 105$	10.6
BeSO ₄ •4H ₂ O	-42m	$d_{36} = 0.30$ $d_{36} = 0.29 \pm 0.03$	0.6328 0.5321
CdGeP ₂	-42m	$d_{36} = 162 \pm 30\%$	10.6
CsD ₂ AsO ₄	-42m	$d_{36} = 0.40 \pm 0.05$	1.064
CsH ₂ AsO ₄	-42m	$d_{36} = 0.22$ $d_{36} = 0.40 \pm 0.05$	0.6943 1.064
CuGaSe ₂	-42m	$d_{36} = 44.2 \pm 10\%$	10.6
CuGaS ₂	-42m	$d_{36} = 14.5 \pm 15\%$	10.6
CuInS ₂	-42m	$d_{36} = 10.6 \pm 15\%$	10.6
KD ₂ PO ₄ (KD*P)	-42m	$d_{36} = 0.38 \pm 0.016$ $d_{36} = 0.34 \pm 0.06$ $d_{14} = 0.37$	1.058 0.694 1.058
KH ₂ PO ₄ (KDP)	-42m	$d_{36} = 0.44$ $d_{36} = 0.47 \pm 0.07$	1.064 0.694
KD ₂ AsO ₄ (KD*A)	-42m	$d_{36} = 0.39$	1.064
KH ₂ AsO ₄ (KDA)	-42m	$d_{36} = 0.43 \pm 0.025$ $d_{36} = 0.39 \pm 0.4$	1.06 0.694
ND ₄ H ₂ PO ₄ (AD*P)	-42m	$d_{36} = 0.495 \pm 0.07$	0.6943
NH ₄ H ₂ PO ₄ (ADP)	-42m	$d_{36} = 0.762$ $d_{36} = 0.85$ $d_{36} = 0.85$	1.064 0.6943 0.694
(NH ₂) ₂ CO (urea)	-42m	$d_{36} = 1.35$	1.06
RbH ₂ AsO ₄ (RDA)	-42m	$d_{36} = 0.39 \pm 0.04$	0.6943

Crystal System—Tetragonal System—*continued*

Tetragonal material	Symmetry class	dim (pm/V)	Wavelength λ (μm)
RbH ₂ PO ₄ (RDP)	-42m	$d_{36} = 0.414 \pm 0.045$ $d_{36} = 0.38 \pm 0.04$	0.6943 1.064
ZnGeP ₂	-42m	$d_{36} = 111.2 \pm 30\%$	10.6
TeO ₂	422	$d_{14} = 0.34 \pm 0.05$ $d_{14} = 0.38 \pm 0.03$ $d_{14} = 4.13 \pm 1.03$	1.318 1.064 0.659
CdGa ₂ S ₄	-4	$d_{36} = 25.6 \pm 3.8$	1.064
HgGa ₂ S ₄	-4	$d_{36} = 25.6 \pm 7.7$	1.064
InPS ₄	-4	$d_{36} = 20.1 \pm 2.1$ $d_{31} = 26.3 \pm 2.58$	1.064 1.064

Crystal System—Trigonal

Trigonal material	Symmetry class	dim (pm/V)	Wavelength λ (μm)
PbGe ₃ O ₁₁	3	$d_{11} = 0.96 \pm 0.16$ $d_{22} = -2.1 \pm 0.3$ $d_{31} = +0.51 \pm 0.07$ $d_{33} = -0.79 \pm 0.12$	1.064 1.064 1.064 1.064
AlPO ₄	32	$d_{11} = 0.35 \pm 0.03$ $d_{14} < 0.008$	1.058 1.058
HgS	32	$d_{11} = 50.3 \pm 17$ $d_{11} = 47.2 \pm 4$	10.6 1.32
Nd _{0.2} Y _{0.8} Al ₃ (BO ₃) ₄	32	$d_{11} = d_{12} = 1.36 \pm 0.16$ $d_{14} = d_{12} < 0.01$	1.32 1.32
PbS ₂ O ₆ •4H ₂ O	32	$d_{11} = 0.096$ $d_{11} = 0.15$	1.0645 0.694
RbS ₂ O ₆	32	$d_{11} = 0.081 \pm 0.03$	0.6943
Se	32	$d_{11} = 79.6 \pm 42$	10.6
SrS ₂ O ₆ •4H ₂ O	32	$d_{11} = 0.06 \pm 0.02$	0.6943
Te	32	$d_{11} = 650 \pm 30$	10.6
SiO ₂ (quartz)	32	$d_{11} = 0.335$	1.064
(C ₆ H ₅ CO) ₂ (benzil)	32	$d_{11} = 3.6 \pm 0.5$	1.064

Crystal System—Trigonal—continued

Trigonal material	Symmetry class	dim (pm/V)	Wavelength λ (μm)
Ag ₃ AsS ₃ (proustite)	3m	$d_{31} = 16.8 \pm 1$ $d_{22} = 26.8 \pm 4$ $d_{22} = 20.0$ $d_{31} = 12.0$	10.6 10.6 1.152 1.152
Ag ₃ SbS ₃ (pyragerite)	3m	$d_{31} = 12.6 \pm 4$ $d_{22} = 13.4 \pm 4$	10.6 10.6
β -BaB ₂ O ₄ (BBO)	3m	$d_{22} = 13.4 \pm 4$ $d_{31} = 12.6 \pm 4$	1.06 1.06
(CN ₃ H ₆)As(SO ₄) ₂ •6H ₂ O (GASH)	3m	$d_{22} = -1.05 \pm 0.017$ $d_{31} = +0.008 \pm 0.017$ $d_{33} = +0.020 \pm 0.003$	1.064 1.064 1.064
LiNbO ₃	3m	$d_{33} = -34 \pm 8.6$ $d_{31} = -4.88 \pm 0.7$ $d_{22} = +2.58 \pm 0.25$ $d_{31} = -4.35 \pm 0.4$ $d_{22} = +2.1 \pm 0.8$ $d_{33} = -31.8$ $d_{31} = -29.1$	1.058 1.058 1.058 1.152 1.152 1.318 1.318
LiTaO ₃	3m	$d_{33} = -16.4 \pm 2$ $d_{31} = -1.07 \pm 0.2$ $d_{22} = +1.7 \pm 0.2$	1.058 1.058 1.058
(Na,Ca)(Mg,Fe)(BO ₃) ₃ -Al ₆ Si ₆ (OH,O,F) (tourmaline)	3m	$d_{15} = 0.24 \pm 0.04$ $d_{31} = 0.14 \pm 0.03$ $d_{22} = 0.07 \pm 0.01$ $d_{33} = 0.50 \pm 0.06$	1.064 1.064 1.064 1.064
TlIO ₃	3m	$d_{15} = 3.49 \pm 20\%$ $d_{31} = 3.36 \pm 20\%$ $d_{23} = 1.11 \pm 20\%$ $d_{24} = 3.85 \pm 20\%$ $d_{32} = 3.98 \pm 20\%$ $d_{33} = 6.85 \pm 20\%$	1.064 1.064 1.064 1.064 1.064 1.064
SbI ₃ •3S ₈	3m	$d_{22} = 5.2$ $d_{33} = 7.23$ $d_{31} = 4.8$	1.064 1.064 1.064

Crystal System—Orthorhombic

Orthorhombic material	Symmetry class	d₃₁ (pm/V)	Wavelength λ (μm)
Ba(COOH) ₂	222	d ₁₄ = 0.11 ± 11%	1.064
		d ₂₅ = 0.11 ± 14%	1.064
		d ₃₆ = 0.13 ± 11%	1.064
α-HIO ₃	222	d ₃₆ = 5.15 ± 0.16	1.064
NO ₂ •CH ₃ NOC ₅ H ₄ (POM)	222	d ₃₆ = 6.4 ± 1.0	1.064
Sr(COOH) ₂	222	d ₃₄ = 0.51	1.064
BaMgF ₄	mm2	d ₃₁ = 0.023 ± 20%	1.064
		d ₃₂ = ±0.035 ± 12%	1.064
		d ₃₃ = 0.0094 ± 14%	1.064
		d ₂₄ = 0.025 ± 17%	1.064
Ba ₂ NaNb ₅ O ₁₅	mm2	d ₃₃ = -17.6 ± 1.28	1.064
		d ₃₂ = -12.8 ± 0.64	1.064
		d ₃₁ = -12.8 ± 1.28	1.064
BaZnF ₄	mm2	d ₃₂ = 0.08 ± 20%	1.06
		d ₁₅ = 0.011 ± 20%	1.06
		d ₃₃ = 0.035 ± 20%	1.06
C ₆ H ₄ (NO ₂) ₂ [MDB]	mm2	d ₃₃ = 0.74	1.064
		d ₃₂ = 2.7	1.064
		d ₃₁ = 1.78	1.064
Gd ₂ (MoO ₄) ₃	mm2	d ₃₃ = -0.044 ± 0.008	1.064
		d ₃₂ = +2.42 ± 0.36	1.064
		d ₃₁ = -2.49 ± 0.37	1.064
KB ₅ O ₈ •4H ₂ O	mm2	d ₃₁ = 0.046	0.4342
		d ₃₂ = 0.003	0.4342
KIO ₂ F ₂	mm2	d ₃₁ = ±0.57 ± 25%	1.064
		d ₃₂ = ±0.16 ± 25%	1.064
		d ₃₃ = ±2.79 ± 25%	1.064
		d ₁₅ = 0.49 ± 25%	1.064
		d ₂₄ = 0.25 ± 25%	1.064
K ₂ La(No ₃) ₄ •2H ₂ O	mm2	d ₃₁ = d ₁₅ = -1.13 ± 0.15	1.064
		d ₃₂ = d ₂₄ = -1.10 ± 0.1	1.064
		d ₃₃ = 0.13 ± 0.1	1.064
KNbB ₂ O ₆	mm2	d ₂₄ = 6.10	1.064
		d ₃₂ = 3.00	1.064
		d ₃₃ = 1.44	1.064

Crystal System—Orthorhombic—continued

Orthorhombic material	Symmetry class	d_{im} (pm/V)	Wavelength λ (μm)
KNbO ₃	mm2	$d_{33} = -19.58 \pm 1.03$ $d_{32} = +11.34 \pm 1.03$ $d_{31} = -12.88 \pm 1.03$	1.064 1.064 1.064
KTiOPO ₄ [KTP]	mm2	$d_{33} = 13.7$ $d_{32} = \pm 5.0$ $d_{31} = \pm 6.5$ $d_{24} = 7.6$ $d_{15} = 6.1$	1.06 1.06 1.06 1.06 1.06
LiB ₃ O ₅	mm2	$d_{15} = +0.85$ $d_{24} = -0.67$ $d_{33} = +0.04$	1.064 1.064 1.064
LiGaO ₂	mm2	$d_{31} = d_{15} = -1.13 \pm 0.15$ $d_{33} = -0.59 \pm 0.06$	1.064 1.064
LiH ₂ PO ₃	mm2	$d_{31} = 0.03$ $d_{32} = 0.16$ $d_{33} = 0.43$ $d_{15} = 0.035$ $d_{24} = 0.17$	1.064 1.064 1.064 1.064 1.064
LiInO ₂	mm2	$d_{31} = 9.9 \pm 15\%$ $d_{32} = 8.58 \pm 15\%$ $d_{33} = 15.8 \pm 15\%$	1.064 1.064 1.064
Na(COOH)	mm2	$d_{15} = -0.22 \pm 0.11$ $d_{32} = d_{15} \approx 0.22$ $d_{33} = 0.33 \pm 0.16$	1.064 1.064 1.064
NaNO ₂	mm2	$d_{31} = 0.074 \pm 0.008$ $d_{32} = 1.89 \pm 0.25$ $d_{33} = 0.094 \pm 0.008$ $d_{15} = 0.04 \pm 0.008$ $d_{24} = 1.80 \pm 0.25$ $d_{31} = d_{15} = 0.18$ $d_{32} = d_{24} = 0.76$	1.064 1.064 1.064 1.064 1.064 1.153 1.153
NO ₂ •C ₆ H ₄ NH ₂ [mNA]	mm2	$d_{33} = 13.12 \pm 1.28$ $d_{32} = 1.02 \pm 0.22$ $d_{31} = 12.48 \pm 1.28$	1.064 1.064 1.064
PbNb ₂ O ₁₁	mm2	$d_{31} = +6.5 \pm 0.97$ $d_{32} = -5.87 \pm 0.88$ $d_{33} = -8.88 \pm 1.32$ $d_{15} = +5.89 \pm 0.88$ $d_{24} = -5.42 \pm 0.39$	1.064 1.064 1.064 1.064 1.064

Crystal System—Orthorhombic—continued

Orthorhombic material	Symmetry class	d_{im} (pm/V)	Wavelength λ (μm)
RbNbB ₂ O ₆	mm2	$d_{24} = 2.40$ $d_{32} = 2.30$ $d_{33} = 0.94$	1.064
Sr(COOH) ₂	222	$d_{34} = 0.51$	1.064
SbNbO ₄	mm2	$d_{32} = 4.72 \pm 0.82$	1.058
SbTaO ₄	mm2	$d_{32} = 4.1 \pm 0.82$	1.058
Tb ₂ (MoO ₄) ₃	mm2	$d_{31} = -2.99 \pm 0.35$ $d_{32} = +2.22 \pm 0.33$ $d_{33} = -0.11 \pm 0.03$	1.064 1.064 1.064
Tb ₂ (MoO ₄) ₃		$d_{15} = -2.52 \pm 0.38$ $d_{24} = +2.55 \pm 0.35$	1.064 1.064

Crystal System—Monoclinic

Monoclinic material	Symmetry class	d_{im} (pm/V)	Wavelength λ (μm)
GdCa ₄ O(BO ₃) ₄	Cm	$d_{11} = 0.04$ $d_{12} = 0.128$ $d_{13} = -0.17$ $d_{31} = 0.148$ $d_{32} = 0.64$ $d_{33} = 0.58$	1.064 1.064 1.064 1.064 1.064 1.064
GdCa ₄ O(BO ₃) ₄	Cm	$d_{11} = -0.104$ $d_{12} = 0.015$ $d_{13} = -0.253$ $d_{31} = 0.12$ $d_{32} = 1.36$ $d_{33} = -0.93$	1.064 1.064 1.064 1.064 1.064 1.064
CH ₃ -NH ₂ -NO ₂ -C ₆ H ₄ [MNA]	m	$d_{11} = 160 \pm 40$ $d_{12} = 24 \pm 6$	1.064 1.064
4-(CH ₃) ₂ N-C ₆ H ₄ [DAST]	m	$d_{11} = 600 \pm 200$ $d_{22} = 10 \pm 30$ $d_{12} = 30 \pm 10$	1.064 1.064 1.064
C ₁₀ H ₁₂ N ₃ O ₆ [MAP]	2	$d_{23} = 10.67 \pm 1.3$ $d_{22} = 11.7 \pm 1.3$ $d_{21} = 2.35 \pm 0.5$ $d_{25} = -0.35 \pm 0.3$	1.064 1.064 1.064 1.064

Crystal System—Monoclinic—continued

Monoclinic material	Symmetry class	d_{im} (pm/V)	Wavelength λ (μm)
C ₁₄ H ₁₇ NO ₂ [DMC]	2	$d_{21} = 4.1$ $d_{22} = 1.6$ $d_{23} = 0.53$	1.06 1.06 1.06
N'-(4-niophenyl)-(s)-proplinol (NPP)	2	$d_{21} = \sim 84$ $d_{22} = 29$	1.06 1.06
Li ₂ SO ₄ •H ₂ O	2	$d_{22} = 0.4 \pm 0.06$ $d_{23} = 0.29 \pm 0.04$ $d_{34} = 0.25 \pm 0.04$	1.064 1.064 1.064
(NH ₂ CH ₂ COOH) ₃ -H ₂ SO ₄ [TGS]	2	$d_{23} = 0.32$	0.694
PbHPO ₄	2	$d_{31} = 0.11$ $d_{11} = 0.4$ $d_{33} = 0.23$	1.064 1.064 1.064

The above data are from tables of S. Singh, Nonlinear optical materials, *Handbook of Laser Science and Technology, Vol. III: Optical Materials, Part 1* (CRC Press, Boca Raton, FL, 1986), p. 54 ff and S. Singh, Nonlinear optical materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL 1995), p. 237 ff. These references list the original sources of the data; they also contain additional nonlinear coefficients for other organic materials and powders.

1.9.4 Third-Order Nonlinear Optical Coefficients

Crystal	Nonlinear optical process	Coefficient $C_{jn} \times 10^{20} \text{ m}^2 \text{ V}^{-2}$	Wavelength (μm)
Al _{0.2} Ga _{0.8} As	(-2 ω_2 - ω_1 ; $\omega_1, \omega_1, -\omega_2$)	$\chi^{(3)} = 116.7$	0.84
Al ₂ O ₃	(-2 ω_1 + ω_2 ; $\omega_1, \omega_1, -\omega_2$) (- ω ; $\omega, \omega, -\omega$)	$C_{11} = 0.0159 \pm 0.002$ $C_{11} \leq 0.28$	0.5250 0.6943
BaF ₂	(-2 ω_1 + ω_2 ; $\omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.0387 \pm 0.00042$ $C_{18} = 0.0159 \pm 0.00014$	0.5750 0.5750
Bi _{1-x} Sb _x	(-2 ω_2 - ω_1 ; $\omega_1, \omega_1, -\omega_2$)	$\chi^{(3)} = 4.18 \times 10^8$	10.6
C (diamond)	(-3 ω ; $\omega, \omega, -\omega$) (-2 ω_1 + ω_2 ; $\omega_1, \omega_1, -\omega_2$)	$C_{11} + 3C_{18} = 0.1456 \pm 10\%$ $C_{11} + 3C_{18} = 0.163 \pm 0.046$ $C_{11} + 3C_{18} = 0.0738 \pm 0.0019$ $C_{18} = 0.01218 \pm 0.0009$ $C_{11} = 0.02147$ $C_{18} = 0.00803 \pm 0.0003$	1.06 1.06 0.407 0.407 0.545 0.545

Third-Order Nonlinear Optical Coefficients—*continued*

Crystal	Nonlinear optical process	Coefficient $C_{jn} \times 10^{20} \text{ m}^2 \text{ V}^{-2}$	Wavelength (μm)
CaCO ₃	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 0.0084 \pm 0.0037$	0.530
		$C_{11} = 0.0078 \pm 0.00033$	0.556
		$C_{33} = 0.0047 \pm 0.0009$	0.530
CaF ₂	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 0.002 \pm 0.0006$	0.575
		$C_{18} = 0.00089 \pm 0.00023$	0.575
		$C_{11} = 0.005$	0.6943
		$C_{18} = 0.0025$	0.6943
CdF ₂	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 0.0068 \pm 0.0010$	0.5750
		$C_{18} = 0.0022 \pm 0.0003$	0.5750
CdGeAs ₂	$(-3\omega; \omega, \omega, \omega)$	$C_{11} = 182 \pm 84$	10.6
		$C_{16} = 175$	10.6
		$C_{18} = -35$	10.6
CdS	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 2.24$	0.6943
GaAs	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 16.80 \pm 10\%$	10.6
		$C_{18} = 4.2 \pm 0.168$	10.6
Ge	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$ $(-3\omega; \omega, \omega, -\omega)$	$C_{11} = 140 \pm 50\%$	10.6
		$C_{18} = 85.4 \pm 2.8$	10.6
		$C_{11} = 42.8 \pm 80\%$	10.6
		$C_{18} = 12 \pm 3.6$	10.6
HgCdTe	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 1.75$	10.6
InAs	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 63$	10.6
KBr	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$ $(-3\omega; \omega, \omega, -\omega)$	$C_{11} = 0.042$	0.6943
		$C_{18} = 0.0154$	0.6943
		$C_{11} = 0.0392$	1.06
KCl	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$ $(-3\omega; \omega, \omega, -\omega)$	$C_{11} = 0.0266$	0.6943
		$C_{18} = 0.0081$	0.6943
		$C_{11} = 0.0168$	1.06
KH ₂ PO ₄	$(-3\omega; \omega, \omega, -\omega)$	$C_{11} - C_{18} = 0.04$	1.06
KI	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 0.0035$	0.6943
		$C_{18} = 0.00216$	0.6943
LiF	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$ $(-3\omega; \omega, \omega, -\omega)$	$C_{11} = 0.0048 \pm 0.0008$	0.5250
		$C_{11} = 0.0028$	0.6943
		$C_{18} = 0.00126$	0.6943
		$C_{11} = 0.0014 \pm 0.00002$	1.89
		$C_{11} = 0.0042$	1.06

Third-Order Nonlinear Optical Coefficients—continued

Crystal	Nonlinear optical process	Coefficient $C_{jn} \times 10^{20} \text{ m}^2 \text{ V}^{-2}$	Wavelength (μm)
LiIO ₃	($-3\omega; \omega, \omega, -\omega$)	$C_{12} = 0.2285$	1.06
		$C_{35} = 6.66 \pm 1$	1.06
MgO	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.014$	0.6943
		$C_{18} = 0.0077$	0.6943
NaCl	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 0.0336$	1.06
		$C_{11} = 0.0238$	0.6943
		$C_{18} = 0.0101$	0.6943
		$C_{11} = 0.0168$ $C_{18}/C_{11} = 0.4133$	1.06
NaF	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 0.0035$	1.06
NH ₄ H ₂ PO ₄	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 0.0104$	1.06
		$C_{18} = 0.0098$	1.06
Si	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 8.4 \pm 10\%$	10.6
		$C_{18} = 4.03 \pm 0.252$	10.6
	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 60.7 \pm 9.7$	1.06
α -SiO ₂	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.014$	0.6943
		$C_{11} = 0.0059 \pm 50\%$	1.89
SrF ₂	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.00205 \pm 0.0005$	0.575
		$C_{18} = 0.0014 \pm 0.00019$	0.575
SrTiO ₃	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 5.6$	0.6943
		$C_{18} = 2.63$	0.6943
Tb ₃ Al ₅ O ₁₂	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = (3.1 \pm 0.62) \times 10^6$	4.0
		$C_{18} = (0.95 \pm 0.2) \times 10^6$	4.0
Y ₃ Al ₅ O ₁₂	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.03052 \pm 0.0018$	0.5250
		$C_{18} = 0.0084$	0.694

The above data are from tables of S. Singh, Nonlinear optical materials, *Handbook of Laser Science and Technology, Vol. III: Optical Materials, Part 1* (CRC Press, Boca Raton, FL 1986), p. 54 ff and S. Singh, Nonlinear optical materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials*, (CRC Press, Boca Raton, FL, 1995), p. 237 ff. These references list the original sources of the data; they also contain additional nonlinear coefficients for other organic materials and powders.

1.9.5 Optical Phase Conjugation Materials*

Photorefractive and semiconducting media are widely used for optical phase conjugation. Photorefractive materials are electrooptic photoconductors in which a refractive index grating can be written by charge generation, transport, and trapping. The most general interaction used to produce phase conjugation in photorefractive materials is degenerate four-wave mixing (DFWM).

Photorefractive materials may be classified into several major structural categories.¹

Ferroelectric oxides, including LiNbO_3 , BaTiO_3 , KNbO_3 , and $\text{Sr}_{1-x}\text{Ba}_x\text{Nb}_2\text{O}_6$ (SBN). These materials have large electrooptic coefficients and are thus characterized by large values of diffraction efficiency, gain coefficient, and phase conjugate reflectivity. They are not effective photoconductors; thus the response times in these materials with typical CW beams are slow.

Cubic oxides or sillenites, including $\text{Bi}_{12}\text{SiO}_{20}$ (BSO), $\text{Bi}_{12}\text{GeO}_{20}$ (BGO) and $\text{Bi}_{12}\text{TiO}_{20}$ (BTO). These materials have relatively small electrooptic coefficients, but they are good photoconductors, thus their response times are fast. In order to improve the phase conjugate reflectivity of the sillenites, applied DC or AC electric fields are generally used.

Bulk compound semiconductors, including GaAs, InP, and CdTe. These materials have small electrooptic coefficients but they are excellent photoconductors, with response times approaching the fundamental limit for bulk photorefractive materials. As with the sillenites, both DC and AC electric fields have been used to enhance the gain and phase conjugate reflectivity of semiconductor conjugators.

Other photorefractive materials include multiple quantum wells in the GaAs/AlGaAs or CdZnTe/ZnTe systems. These materials require an applied AC electric field; the periodic space charge field is due to periodic screening of the applied field. Photorefractive multiple quantum wells are faster than bulk semiconductors, but are relatively inefficient, because of the small thickness (typically 1 mm) of the active layers.

Organic crystals. Organic crystals are in principle easier to grow than inorganics, but they are also more difficult to handle. Only limited work on these materials has been performed.

Polymer films. These materials are simple and inexpensive to fabricate. In addition, there is great flexibility in modifying the structure to separately optimize the electro-optic properties and the charge transport properties.

¹ Fisher, R. A., Phase conjugation materials, *Handbook of Laser Science and Technology*, vol. V, *Optical Materials*, Part 3, (CRC Press, Boca Raton, FL 1987), p. 261.

* This section was adapted from Pepper, D. M., Minden, M. L., Bruesselbach, H. W., and Klein, M. B., Nonlinear optical phase conjugation materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 467.

Semiconducting media possess a wide range of nonlinearities and materials are available at wavelengths from the visible spectral region to 10.6 μm and beyond. The variety of nonlinearities in semiconductors results from the presence of free carrier states, as well as the bound carrier states which are present in all optical materials. Large concentrations of free carriers can be created through doping or through optical excitation. Semiconductors are particularly useful materials in the infrared spectral region because in most cases the nonlinear susceptibility increases rapidly as the operating wavelength increases. In addition, the susceptibility is larger in materials with smaller values of band gap energy.

Nonlinear processes in semiconductors can be broadly divided into two categories: resonant and nonresonant. In general, nonresonant nonlinearities involve virtual transitions and are quite fast. By contrast, resonant nonlinearities involve real transitions (usually involving free carrier generation), and are thus slower. Nonlinear processes used for phase conjugation via DFWM in semiconductors include anharmonic response of bound electrons, nonlinear motion of free carriers, plasma generation by valence-to-conduction band transitions, interband population modulation through optically induced carrier temperature fluctuations, saturation of exciton absorption in multiple quantum wells, and saturation of intersubband transitions in multiple quantum wells.

General References on Nonlinear Optical Phase Conjugation

- Fisher, R. A., Ed., *Optical Phase Conjugation*, (Academic Press, New York, 1983).
- Pepper, D. M., Nonlinear optical phase conjugation, *The Laser Handbook*, Vol. 4, M. Bass and M. L. Stich, Eds. (North-Holland Press, Amsterdam, 1985).
- Zel'dovich, B. Ya., Pilipetsky, N. F., and Shkunov, V. V., *Principles of Phase Conjugation*, Springer Ser. Opt. Sci. 42, T. Tamir, Ed. (Springer-Verlag, Berlin, 1985).
- Pepper, D. M., Guest Ed., Special issue on nonlinear optical phase conjugation, *IEEE J. Quantum Electron.* 25, (1989).
- Günter, P., and Huignard, J.-P., Photorefractive materials and their applications I and II, *Topics in Applied Physics*, Vol. 61 (Springer-Verlag, Berlin, 1988).

Semiconductor Phase Conjugate Materials

Material	Wavelength	Nonlinearity	Temp.	Pulse width	Pump intensity	Reflectivity	$\chi^{(3)}$	Ref.
	(μm)	mechanism	(K)	(ns)	(W/cm 2)	(esu)		
Ge	10.6	AMBE	300	50	4×10^7	2%	2×10^{-10}	1
Ge	10.6	NLPlasma	300	1.5	1.2×10^8	800%	—	7
Ge	3.8	AMBE	300	—	1.2×10^7	0.14%	4×10^{-11}	3
Si	1.06	Plasma	300	10	10^6	1%**	—	4
Si	1.06	Plasma	300	15	10^7	150%	10^{-7}	5,6
Si	1.06	Plasma	300	15	7×10^6	100%	—	7
InAs	10.6	3PA-Plasma	300	~200	1.8×10^6	13%	2.5×10^{-7}	8,9
InSb	5.3	Plasma	5	CW	40	1%	—	10
InSb	5.3	Plasma	80	CW	1	20%	1.1	11
InSb	10.6	2PA-Plasma	300	~200	10^5	30%	2×10^{-5}	8,12,13
<i>n</i> -Hg _{0.768} Cd _{0.232} Te	10.6	CBNP	295	200	10^7	9%	4×10^{-8}	14
<i>n</i> -Hg _{0.78} Cd _{0.22} Te	10.6	Plasma	77	CW	1	8%	3×10^{-2}	15
<i>n</i> -Hg _{0.78} Cd _{0.22} Te	10.6	Plasma	120	CW	12	2%	5×10^{-2}	16
HgTe	10.6	Plasma*	300	~200	5×10^5	—	2×10^{-4}	17
CdTe	1.06	TSA-Plasma	300		10^7	200%		18
CdS	0.53	Plasma	300	15	2×10^7	—	3×10^{-9}	19
ZnSe	0.69	TSA-Plasma	300	15	5×10^7	200%	—	20

AMBE, anharmonic motion of bound electrons; Plasma, nonlinearity due to index change from free carriers; also known as band filling nonlinearity; NL Plasma, plasma nonlinearity induced by high-order nonlinear absorption; 2PA-Plasma, plasma nonlinearity induced by two-photon absorption; 3PA-Plasma, plasma nonlinearity induced by three-photon absorption; SIA, saturation of intersubband absorption; SEA, saturation of exciton absorption; CBNP, conduction band nonparabolicity; TSA-Plasma, plasma nonlinearity induced by two-step absorption via impurity states; *Fast (5 ps) interband population modulation; **Diffraction efficiency.

References:

1. Bergmann, E. E., Bigio, I. J., Feldman, B. J., and Fisher, R. A., *Opt. Lett.* 3, 82 (1978).
2. Watkins, D. E., Phipps, Jr., C. R., and Thomas, S. J., *Opt. Lett.* 6, 26 (1981).
3. DePatie, D., and Haueisen, D., *Opt. Lett.* 5, 252 (1980).
4. Woerdman, J. P., *Opt. Commun.* 2, 212–14 (1970).
5. Jain, R. K., and Klein, M. B., *Appl. Phys. Lett.* 35, 454 (1979).
6. Jain, R. K., Klein, M. B., and Lind, R. C., *Opt. Lett.* 4, 328 (1979).
7. Eichler, H. J., Chen, J., and Richter, K., *Appl. Phys. B* 42, 215 (1987).
8. Basov, N. G., Kovalev, V. I., and Faizulov, F. S., *Bull. Acad. Sci. U.S.S.R Phys. Ser.* 51, 67 (1987).
9. Basov, N. G., Kovalev, M. A., Musaev, M. A., and Faysullov, F. S. (Nova Science Publishers, Commack, NY, 1988).
10. Miller, D. A. B., Harrison, R. G., Johnston, A. M., Seaton, C. T., and Smith, S. D., *Opt. Commun.* 32, 478 (1980).
11. MacKenzie, H. A., Hagan, D. J., and Al-Attar, H. A., *Opt. Commun.* 51, 352 (1984).
12. Erokhin, A. I., Kovalev, V. I., and Shmelev, A. K., *Sov. J. Quantum Electron.* 17, 742 (1987).
13. An, A. A., and Kovalev, V. I., *Sov. J. Quantum Electron.* 17, 1075 (1987).
14. Khan, M. A., Kruse, P. W., and Ready, J. F., *Opt. Lett.* 5, 261 (1980).
15. Khan, M. A., Bennet, R. L. H., and Kruse, P. W., *Opt. Lett.* 6, 560 (1981).
16. Jain, R. K., and Steel, D. G., *Opt. Commun.*, 43, 72 (1982).
17. Wolff, P. A., Yuen, S. Y., Harris, Jr., K. A., Cook, J. W., and Schetzina, J. F., *Appl. Phys. Lett.* 50, 1858 (1987).
18. Kremenitskii, V., Odoulov, S. G., and Soskin, M. S., *Phys. Status Solidi A* 57, K71 (1980).
19. Jain, R. K., and Lind, R. C., *J. Opt. Soc. Am.* 73, 647 (1983).
20. Borshch, A., Brodin, M., Volkov, V., and Kukhtarev, N. V., *Opt. Commun.* 35, 287 (1980).

Photorefractive Phase Conjugation Materials

Structural category and material	Wavelength (μm)	Gain coeff. (cm^{-1})	Response time(s)	Intensity (W/cm^2)	Interaction	Reflectivity	Ref.	Notes
Ferroelectric oxide								
BaTiO ₃	0.515	—	—	—	DFWM	100 ($10^4\%$)	1	
	1.09	—	500	1	Ring	17%	2	
	0.532	15	10^{-8}	2×10^6	TWM	—	3	b
	0.532	—	3×10^{-11}	3×10^8	—	3×10^{-6}	4	c
	0.515	—	10^{-3}	4	—	—	5	d
BaTiO ₃ :Co	0.515	—	—	—	SPBS	60%	6	
	0.85	—	—	—	Internal	70%	7	a
	0.515	38	0.021	1	—	—	8	e
SBN:Ce	0.442	—	0.3	0.5	Internal	30%	9	
SBN:Rh	0.532	—	10^{-8}	10^6	Internal	29%	10	
	0.515	60	10	1	TWM	—	11	f
BSKNN:Ce	0.458	—	100	1	Internal	28%	12	g
KNbO ₃ :Fe	0.488	—	5×10^{-5}	1	—	—	13	h
KNbO ₃ :Fe	0.488	14	10^{-3}	300	Ring	60%	14	i
Sillenite								
BSO	0.568	—	0.2	0.1	DFWM	270%	15	j
	0.568	12	0.2	0.1	TWM	—	16	k
BTO	0.633	9	—	—	Mutual	40%	17	l
	0.633	35	—	0.1	Ring	7%	18	m
	0.633	35	10	0.1	TWM	—	19	n

Bulk semiconductor

InP:Fe	1.32	2.5	10^{-3}	0.1	Ring	11%	20	o
	1.064	11	0.1	0.07	Mutual	74%	21	p
	0.970	31	0.1	0.023	Ring	0.3%	18	q
GaP	0.633	0.4				0.3%	22	r
CdTe:V	1.32	10	10^{-3}	0.075	TWM	—	23	s
	1.5	2.4	2×10^{-3}	0.003	TWM	—	24	t
GaAs:Cr	1.064	6	0.040	0.050	TWM		25	u
GaAs	1.064	7.7	—	0.02	DFWM	500%	26	u
	1.064		—		Ring	3%	27	v
ZnTe:V	0.633	0.4	1.5×10^{-5}	4.7	TWM	—	28	

Organic crystal

COANP	0.676	0.1%	10^3	3.2	—	—	29
-------	-------	------	--------	-----	---	---	----

^a Reflectivity constant from 0.6–0.9 μm ; ^b Experiment performed with 10-ns pulses; ^c Experiment performed with 30-ps pulses; ^d Samples operated at 120°C; ^e 45-degree cut sample; ^f Rhodium concentration = 0.07 wt %; ^g Ba_{1.5}Sr_{0.5}K_{0.75}Na_{0.25}Nb₅O₁₅ (BSKNN-1) and Ba_{0.5}Sr_{1.5}K_{0.50}Na_{0.50}Nb₅O₁₅ (BSKNN-2); ^h Electrochemically reduced sample; ⁱ Reflection grating geometry; ^j DC electric field ($E=10$ kV/cm) with moving grating; beam ratio=10⁴; ^k DC electric field ($E=10$ kV/cm) with moving grating; beam ratio=10⁵; ^l AC square-wave electric field ($E=20$ kV/cm; $f=50$ Hz); ^{m,n} AC square-wave electric field ($E=10$ kV/cm; $f=60$ Hz); beam ratio=10⁵; ^o AC square-wave electric field ($E=10$ kV/cm); ^P DC electric field ($E=13$ kV/cm); temperature/intensity resonance; ^q DC electric field ($E=10$ kV/cm); beam ratio=10⁶; ^r band edge resonance and temperature/intensity resonance; ^s AC square-wave electric field ($E=23$ kV/cm; $f=230$ kHz); ^t beam ratio=10⁴; ^u DC electric field ($E=5$ kV/cm) with moving grating; beam ratio=10⁴; ^v DC electric field ($E=12$ kV/cm).

References:

1. Feinberg, J., and Hellwarth, R. W., *Opt. Lett.* 5, 519 (1980).
2. Cronin-Golomb, M., Lau, K. Y., and Yariv, A., *Appl. Phys Lett.* 47, 567 (1985).
3. Barry, N., and Damzen, M. J., *J. Opt. Soc. B* 9, 1488 (1992).
4. Smirl, A. L., Valley, G. C., Mullen, R. A., Bohnert, K., Mire, C. D., and Boggess, T. F., *Opt. Lett.* 12, 501 (1987).
5. Rytz, D., Klein, M. B., Mullen, R. A., Schwartz, R. N., Valley, G. C., and Wechsler, B. A., *Appl. Phys. Lett.* 52, 1759 (1988).
6. Mullen, R. A., Vickers, D. J., West, L., and Pepper, D. M., *J. Opt. Soc. Am. B* 9, 1726 (1992).
7. Rytz, D., Stephens, R. R., Wechsler, B. A., Keirstad, M. S., and Baer, T. M., *Opt. Lett.* 15, 1279 (1990).
8. Garrett, M. H., Chang, J. Y., Jenssen, H. P., and Warde, C., *Opt. Lett.* 17, 103 (1992).
9. Salamo, G., Miller, M. J., Clark III, W. W., Wood, G. L., and Sharp, E. J., *Opt. Commun.* 59, 417 (1986).
10. Monson, B., Salamo, G. J., Mott, A. G., Miller, III, M. J., Sharp, E. J., Clark, W. W., Wood, G. L., and Neurgaonkar, R. R., *Opt. Lett.* 15, 12 (1990).
11. Vasquez, R. A., Neurgaonkar, R. R., and Ewbank, M. D., *J. Opt. Soc. Am. B* 9, 1416 (1992).
12. Rodriguez, J., Siahmakoun, A., Salamo, G., Miller, III, M. J., Clark, W. W., Wood, G. L., Sharp, E. J., and Neurgaonkar, R. R., *Appl. Opt.* 26, 1732 (1987).
13. Voit, E., Zha, M. Z., Amrein, P., and Günter, P., *Appl. Phys. Lett.* 51, 2079 (1987).
14. Dyakov, V. A., Korolkov, S. A., Mamaev, A. V., Shkunov, V. V., and Zozulya, A. A., *Opt. Lett.* 16, 1614 (1991).
15. Rajbenbach, H., Huignard, J. P., and Refregier, P., *Opt. Lett.* 9, 558 (1984).
16. Refregier, P., Solymar, L., Rajbenbach, H., and Huignard, J. P., *J. Appl. Phys.* 58, 45 (1985).
17. Petrov, M. P., Sochava, S. L., and Stepanov, S. I., *Opt. Lett.* 14, 284 (1989).
18. Millerd, J. E., Garmire, E. M., and Klein, M. B., *J. Opt. Soc. Am. B* 9, 1499 (1992).
19. Millerd, J. E., Garmire, E. M., Klein, M. B., Wechsler, B. A., Strohkendl, F. P., and Brost, G. A., *J. Opt. Soc. Am. B* 9, 1449 (1992).
20. Bylsma, R. B., Glass, A. M., Olson, D. H., and Cronin-Golomb, M., *Appl. Phys. Lett.* 54 (1968) (1989).
21. Vieux, V., Gravey, P., Wolffer, N., and Picoli, G., *Appl. Phys. Lett.* 58, 2880 (1991).
22. Itoh, M., Kuroda, K., Shimura, T., and Ogura, I., *Jpn. J. Appl. Phys.* 29, L1542 (1990).
23. Ziari, M., Steier, W. H., Ranon, P. M., Klein, M. B., and Trivedi, S., *J. Opt. Soc. Am. B* 9, 1461 (1992).
24. Partovi, A., Millerd, J., Garmire, E. M., Ziari, M., Steier, W. H., Trivedi, S. B., and Klein, M. B., *Appl. Phys Lett.* 57, 846 (1990).
25. Imbert, B., Rajbenbach, H., Mallick, S., Herriau, J. P., and Huignard, J.-P., *Opt. Lett.* 13, 327 (1988).
26. Rajbenbach, H., Imbert, B., Huignard, J. P., and Mallick, S., *Opt. Lett.* 14, 78 (1989).
27. Chua, P. L., Liu, D. T. H., and Cheng, L. J., *Appl. Phys. Lett.* 57, 858 (1990).
28. Ziari, M., Steier, W. H., Ranon, P. M., Trivedi, S., and Klein, M. B., *Appl. Phys. Lett.* 60, 1052 (1992).
29. Sutter, K., Hulliger, J., and Günter, P., *Solid State Commun.* 74, 867 (1990); Sutter, K. and Günter, P., *J. Opt. Soc. Am. B* 7, 2274 (1990).

Section 2: Glasses

- 2.1 Introduction
- 2.2 Commercial Optical Glasses
- 2.3 Specialty Optical Glasses
- 2.4 Fused Silica
- 2.5 Fluoride Glasses
- 2.6 Chalcogenide Glasses
- 2.7 Magnetooptic Properties
- 2.8 Electrooptic Properties
- 2.9 Elastooptic Properties
- 2.10 Nonlinear Optical Properties
- 2.11 Special Glasses

Section 2

GLASSES

2.1 Introduction

Classification and Designation

Optical glasses are characterized and designated by their refractive index and dispersion. The most common measure is the refractive index at the wavelength of the He d line (587.6 nm) or the Na D line (589.3 nm). The difference in the refractive index at the hydrogen F (486.1 nm) and C (656.3 nm) lines, $n_F - n_C$ is called the average or principal dispersion. The ratio $(n_F - n_C)/(n_d - 1)$ is called the relative dispersion; the reciprocal of this quality is the Abbe number v_d , i.e.,

$$v_d = (n_d - 1)/(n_F - n_C).$$

A useful code for finding information on a specific optical glass composition is the mil spec designation. This is a six-digit number where the first three digits designate the refractive index n_d with the preceding “l” omitted and the last three digits designate the Abbe number v_d with the decimal point omitted. Thus a borosilicate glass BK 7 having an $n_d = 1.51680$ and $v_d = 64.17$ has a designation 517 642.

Glasses having $n_d > 1.60$, $v_d > 50$ or $n_d < 1.60$, $v_d > 55$ are called “crown” (K) glass; other glasses are called “flint” (F). These letters, plus others, are usually contained in the manufacturer's designation of optical glasses. Representative manufacturer's designations, glass types, and principal compositional components of commercial optical glasses are given in [Table 2.1.1](#). Designations vary with the country of origin and some alternate designations are given in parentheses. “Light” or “dense” indicate the relative amounts of heavy metal oxides such as PbO or La₂O₃. Glasses with prefixes U or IR denote extended ultraviolet or infrared transmitting glasses. Other designators are used for glasses for special applications such as LG—laser glass, FR—Faraday rotator glass, and AO—acoustooptic glass.

Various manufacturers of multicomponent optical glass use their own designations. [Table 2.1.2](#) relates these designations to actual composition in terms of major components. The table is comprehensive for Schott Optical Glass Inc. (Duryea, PA), Hoya Glass Works Ltd (Japan), Ohara Optical Glass Manufacturing Company, and Chance-Pilkington (England) glass designations. Corning Glass Works (France) uses another form of identification in which glass type does not play as significant a role in the name. A cross-reference chart from Corning is presented in [Table 2.1.2](#).

There are more than 200 types of optical glasses. Some are always available, others are generally available or available on short notice, and others are available on request. Section 2.2 presents properties of representative types of glasses that are generally preferred or standard glasses. Data are for Schott glasses; however, as indicated in [Table 2.1.2](#), comparable glasses are offered by other companies. Most optical glasses are oxides; only a few non-oxide optical glasses such as heavy metal fluorides and chalcogenides are available commercially. Some of these are included as specialty glasses in Section 2.3.

Table 2.1.1
Designation, Type, and Major Compositional Components
of Optical Glasses

Designation	Glass Type	Composition ^a
FB	Fluoroberyllate	BeF ₂ -AF ₃ -RF-MF ₂
FA	Fluoroaluminate	AlF ₃ -RF-MF ₂ -(Y,La)F ₃
FP(FK)	Fluorophosphate	P ₂ O ₅ -AlF ₃ -RF-MF ₂
FZ	Fluorozirconate	ZrF ₄ -RF-MF ₂ -(Al,La)F ₃
FK(FC)	Fluorocrown	SiO ₂ -B ₂ O ₃ -K ₂ O-KF
BK(BSC)	Borosilicate crown	SiO ₂ -B ₂ O ₃ -R ₂ O-BaO
PK(PC)	Phosphate crown	P ₂ O ₅ -B ₂ O ₃ -R ₂ O-BaO
PSK(DPC, PCD)	Dense phosphate crown	P ₂ O ₅ -(B,Al) ₂ O ₃ -R ₂ O-MO
K(C)	Crown	SiO ₂ -R ₂ O-(Ca,Ba)O
ZK(ZC, ZnC)	Zinc crown	SiO ₂ (B ₂ O ₃)-ZnO
BaK(BaC, LBC)	Barium crown	SiO ₂ (B ₂ O ₃)-BaO-R ₂ O
SK(DBC, BCD)	Dense barium crown	SiO ₂ -B ₂ O ₃ -BaO
SSK(EDBC, BCDD)	Extra-dense barium crown	SiO ₂ -B ₂ O ₃ -BaO
LaK(LaC, LaCL)	Lanthanum crown	B ₂ O ₃ (SiO ₂)-La ₂ O ₃ -ZnO-MO
LaSK	Dense lanthanum crown	B ₂ O ₃ (SiO ₂)-La ₂ O ₃ -ZnO-MO
LgSK	Special long crown	B ₂ O ₃ -Al ₂ O ₃ -MF ₂
TiK	Titanium crown	
TiF	Titanium flint	{ SiO ₂ (B ₂ O ₃)-TiO ₂ -Al ₂ O ₃ -KF }
TiSF(FF)	Dense titanium flint	
KzF(CHD, SbF)	Short flint	SiO ₂ -B ₂ O ₃ -R ₂ O-Sb ₂ O ₃
KzFS(ADF)	Dense short flint	B ₂ O ₃ (Al ₂ O ₃)-PbO-MO
KF(CF, CHD)	Crown flint	
LLF(BLF, FEL)	Extra light flint	
LF(FL)	Light flint	{ SiO ₂ -R ₂ O-PbO-MO }
F(DF, FD)	Flint	
SF(EDF, FDS)	Dense flint	
SFS	Special dense flint	{ SiO ₂ -R ₂ O-MO-TiO ₂ }
BaLF(LBC, BCL)	Light barium flint	
BaF(BF, FB)	Barium flint	{ SiO ₂ -B ₂ O ₃ -BaO-PbO-R ₂ O }
BaSF(DBF, FBD)	Dense barium flint	
LaF(LaFL)	Lanthanum flint	B ₂ O ₃ (SiO ₂)-La ₂ O ₃ -MO-PbO
LaSF	Dense lanthanum flint	B ₂ O ₃ (SiO ₂)-La ₂ O ₃ -MO-PbO
TaK	Tantalum crown	
TaF	Tantalum flint	B ₂ O ₃ -La ₂ O ₃ -(Gd,Y) ₂ O ₃ -(Ta,Nb) ₂ O ₅
TaSF	Dense tantalum flint	B ₂ O ₃ -La ₂ O ₃ -(Gd,Y) ₂ O ₃ -(Ta,Nb) ₂ O ₅
NbF	Niobium flint	B ₂ O ₃ -La ₂ O ₃ -ZnO-Nb ₂ O ₅
NbSF	Dense niobium flint	B ₂ O ₃ (SiO ₂)-La ₂ O ₃ -ZnO-(Ti,Zr)O ₂

^a R and M denote one or more alkali or alkaline earth elements, respectively.

Table 2.1.2
Designations for Equivalent Optical Glasses

Mil spec	Schott type	Hoya type	Corning type
465-657	FK 3	FC	A63-65
486-817	FK 52	PFC	A86-82
487-704	FK 5	FC	A87-70
510-635	BK 1	BSC	B10-63
511-604	K 7	C	B11-60
517-642	BK 7	BSC	B16-64
518-603	BaLK N3	C	B18-60
518-651	PK 2	BSC	B18-65
523-594	K 5	C	B23-59
529-518	KzF 2	CHD	B29-52
540-597	BaK 2	BCL	B39-59
548-457	LLF 1	FeL	B48-46
548-535	BaLF 5	FBL	B48-53
564-609	SK 11	BCD	B64-61
569-560	BaK 4	BCL	B69-56
573-575	BaK 1	BCL	B72-57
581-408	LF 5	FL	B81-41
589-612	SK 5	BCD	B89-61
604-381	F 5	FD	C04-38
606-439	BaF 4	FB	C06-44
607-566	SK 2	BCD	C07-57
609-590	SK 3	BCD	C09-59
613-443	KzFS N4	FSB	C13-44
613-585	SK 4	BCD	C13-58
614-564	SK 6	BCD	C13-56
618-551	SSK 4	BCD	C17-55
620-363	F 2	FD	C20-36
620-603	SK 16	BCD	C20-60
623-531	SSK 2	BCDD	C23-53
623-569	SK 10	BCD	C23-57
623-581	SK 15	BCD	C23-58
624-469	BaF 8	FB	C24-47
626-356	F 1	FD	C26-36
637-353	F 6	FD	C37-35
639-555	SK N18	BCD	C39-56

Table 2.1.2—continued
Designations for Equivalent Optical Glasses

Mil spec	Schott type	Hoya type	Corning type
641-601	LaK 21	BCS	C41-60
648-339	SF 2	FDD	C48-34
650-392	BaSF 10	FBD	C51-39
651-559	LaK22	BCS	C51-56
652-585	LaK N7	BCS	C52-58
658-572	LaK11	BCS	C57-57
659-510	SSK N5	BCDD	C58-51
667-331	SF 19	FDD	C67-33
667-484	BaF N11	FB	C67-48
670-471	BaF N10	FB	C70-47
678-555	LaK N12	BCS	C78-56
689-312	SF 8	FeD	C89-31
689-496	LaF 23	FBS	C90-50
691-548	LaK N9	BCS	C90-55
697-554	LaK N14	BCS	C97-55
699-301	SF 15	FeD	C99-30
702-411	BaSF 52	FBD	D01-41
713-538	LaK 8	BCS	D13-54
717-295	SF 1	FeD	D17-29
717-480	LaF N3	FBS	D17-48L
720-503	LaK 10	BCS	D20-50
724-380	BaSF 51	FBD	D23-38
728-284	SF 10	FeD	D28-28
734-514	LaK N16	BCS	D34-51
740-281	SF 3	FeD	D40-28
744-448	LaF N2	FBS	D44-45
755-276	SF 4	FeD	D56-27
762-269	SF 55	FeD	D62-27
785-258	SF 11	FeD	D85-25
785-259	SF 56	FeD	D85-26
788-474	LaF 21	FBS	D88-47
803-464	LaSF N30	FBS	E03-47
805-255	SF 6	FeD	E05-25
878-385	LaSF 15	FBS	E78-38




Figure 2.1.1 Glass map of the optical glass compositions in Table 2.1.1.

Refractive Index

Optical glasses cover a general range of refractive indices $n_d = 1.4$ to 2.0 and reciprocal dispersions $v_d = 20$ to 90 . These are almost exclusively oxide glasses. The location of the glasses is shown in the glass map above, where the lines divide the main compositional types. The range of $n_d - v_d$ in this figure is larger than that given in the ordinary glass catalogs so as to include low-index, low-dispersion fluoride glasses. Amorphous SiO_2 and BeF_2 are added to indicate the extrema for oxide and fluoride glasses. Many higher index chalcogenide glasses cannot be located in an $n_d - v_d$ plot because the absorption edge extends into the visible and it is not always possible to measure v_d . Therefore for infrared materials, plots are made using a reciprocal dispersion based on measurements of refractive index at longer wavelengths.

Manufacturer's data sheets usually report the refractive index (the mean value for a number of melts) at a number of specific wavelengths. Wavelengths of a number of commonly used spectral lines and laser wavelengths are given in Table 2.1.3.

For interpolating values of the refractive index at the other wavelengths, glass manufacturers use an approximate dispersion formula derived from a power series expansion of the form

$$n^2 = A_0 + A_1 \lambda^{-2} + A_2 \lambda^{-4} + A_3 \lambda^{-6} + A_4 \lambda^{-8},$$

where the constants A_i are determined from a least squared fit of the measured values.

Table 2.1.3
Principal Wavelengths Used for Refractive Index Measurements

Wavelength (nm)	Spectral line	Element	Wavelength (nm)	Spectral line	Element
365.0	i	Hg	656.3	C	H
404.7	n	Hg	706.6	r	He
435.8	g	Hg	768.2	A'	K
480.0	F'	Cd	852.1	s	Cs
486.1	F	H	1014.0	t	Hg
546.1	e	Hg	1060.0	Nd glass laser	
587.6	d	He	1064	Nd:YAG laser	
589.3	D	Na	1529.6		Hg
632.8	He-Ne laser		1970.1		Hg
643.8	C'	Cd	2325.4		Hg

Using the above equation, refractive indices in the wavelength range 365-1014 nm can be calculated to an accuracy of $\pm 5 \times 10^{-6}$ or better. The thermal coefficient of refractive index depends on the wavelength, temperature, and pressure.

Transmission

The transmission of optical glasses is frequently given in terms of the internal transmission T_i after correction for reflective losses R , that is, $T_i = T/R$. The deviation of T_i from 100% is a measure of absorption due to impurities and scattering due to defects. The internal transmittance is usually reported at a number of standard wavelengths from the ultraviolet to the infrared. The transmission (I/I_0) and the absorption coefficient α for a sample of length l are related by

$$\alpha l = \ln(I_0/I) = 2.303 OD,$$

where $OD = \log_{10}(I_0/I)$ is the absorbance or optical density. The absorption cross section σ is derived from $\alpha = \sigma N$, where N is the number of absorbing centers to unit volume.

Glasses exist that are optically transparent in the vacuum ultraviolet and in the mid-infrared. Variations of the ultraviolet and infrared absorption edges of representative optical glasses are illustrated below.




Figure 2.1.2. Ultraviolet absorption edge of representative optical glasses.
 Sample thicknesses: 5 mm except for SiO_2 and LG 810 which are 2 mm.




Figure 2.1.3. Infrared absorption edge of representative optical glasses. Sample thicknesses: 2 mm.

Thermal Properties

The temperature range in which a glass transforms from its solid state into a “plastic” state is called the transformation region. A transformation (annealing) temperature T_g is used to define this region and is determined from a standard thermal expansion measurement. The viscosity of the melt at T_g is approximately $10^{13.4}$ poise. The softening temperature is that temperature at which, in a standard test, the glass deforms under its own weight and corresponds to a melt viscosity of $10^{7.6}$ poise.

Thermal expansion varies the dimensions of glass and affects refractive optics subject to either uniform or gradient temperature variations. The coefficient of thermal expansion α of glass ranges from near zero for special low expansion glasses such as titania-doped SiO_2 and tailored glass ceramics to values greater than $20 \times 10^{-6}/\text{K}$. For optical glasses α ranges from about 4 to $16 \times 10^{-6}/\text{K}$. The thermal expansion coefficient increases with increasing temperature, exhibiting a nonlinear increase up to about room temperature, followed by an approximately linear range until the glass begins to exhibit plastic behavior, and then a rapid increase with increasing structural mobility in the glass. Therefore, mean thermal expansion coefficients are given for a specific temperature range.

Because of its disordered atomic structure, the thermal conductivity of glass is much lower than that for crystalline materials. The thermal conductivity of optical glasses ranges from about 0.5 to 1.5 W/m K , being high for silica and low for glasses containing large quantities of heavy elements such as lead, tantalum, barium, and lanthanum. The thermal conductivity of glass increases with temperature but only slightly above 300 K.

Mechanical Properties

The mechanical response of a glass to an applied force is described by various moduli. Optical glass catalogs usually list moduli such as Young's modulus E (extension in tension) and the modulus of rigidity or shear G which are important for thermal and mechanical stress determinations. These are related to Poisson's ratio μ (ratio of lateral to longitudinal strain under unilateral stress) by

$$\mu + 1 = E/2G.$$

The bulk modulus B (1/isothermal compressibility) is related to the above moduli by

$$B = E/3(1 - \mu).$$

Elastic moduli can also be expressed in terms of the longitudinal and transverse sound velocities and the density.

The hardness of a glass is usually measured from the indentation of Knoop or Vickers penetrators. Values (Knoop) for oxide glasses range from ~ 250 for high-lead-content glasses to >600 kg/mm² for lanthanum crown glasses. The Knoop hardness generally correlates with Young's modulus.

The stress-optical coefficient K varies with glass type and wavelength. It is usually positive, although it can become negative (so-called Pockels glasses) for silicate glasses having a high lead content. The stress-optical coefficient is measured in units of 1 Brewster = (TPa)⁻¹ = 10^{-12} m²/N. Values of K are included in the table and generally range from $-2 < K < 4$ TPa⁻¹ for oxide glasses to $-40 < K < 20$ TPa⁻¹ for chalcogenide glasses.

Chemical Properties

An important consideration for many optical glasses is their chemical reactivity with slurries during cutting and polishing of components such as lenses, windows, and prisms and with its environment where it may be subject to chemical attack by water, water vapor, gases, acids, etc. Corrosion, dimming, and straining occur and vary greatly depending on the chemical composition of the glass. No simple test and parameter is sufficient to characterize chemical reactivity under all conditions. Thus many terms and tests are used to rank glasses with respect to their resistance to acids, straining, climate, weathering, etc. Manufacturers typically list several categories of acid and alkali resistance to cover the above ranges.

2.2 Commercial Optical Glasses

Data for selected commercial optical glasses representative of the various glass types are presented in Sections 2.2 and 2.3 are from manufacturers' catalogs and data sheets and from the *Handbook of Optics*, Vol. II (McGraw-Hill, New York, 1995), chapter 33, and references cited therein.

2.2.1 Optical Properties

Glass type	Refractive index n_d	Abbe number v_d	Dispersion $n_F - n_C (x 10^{-3})$	$\frac{dn}{dT} (10^{-6}/K)^*$	
				435.8 nm	1060 nm
FK 5	1.48749	70.41	6.924	-1.1	-1.8
FK 51	1.48656	84.47	5.760	-5.9	-6.4
PK 2	1.51821	65.05	7.966	3.7	2.3
PSK 3	1.55232	63.46	8.704	-	-
PSK 53	1.62014	63.48	9.769	-1.7	-2.6
BK 7	1.51680	64.17	8.054	3.4	2.3
BaLK N3	1.51849	60.25	8.606	3.1	1.9
K 5	1.52249	59.48	8.784	2.4	1.1
UK 50	1.52257	60.38	8.654	-	-
ZK 1	1.53315	57.98	9.196	4.4	2.8
ZK N7	1.50847	61.19	8.310	6.8	6.1
BaK 50	1.56774	57.99	9.790	8.7	7.7
SK 2	1.60738	56.65	10.721	5.6	3.9
SK 14	1.60311	60.60	9.952	3.6	2.3
KF 9	1.52341	51.49	10.166	5.1	3.3
BaLF 4	1.57957	53.71	10.790	6.3	4.3
SSK 4	1.61765	55.14	11.201	4.0	2.2
SSK N5	1.65844	50.88	12.940	-	-
LaK N7	1.65160	58.52	11.134	1.7	0.5
LaK 10	1.72000	50.41	14.282	5.8	3.8
LLF 6	1.53172	48.76	10.905	4.4	2.6
BaF 4	1.60562	43.93	13.787	5.1	2.6
BaF N10	1.67003	47.11	14.222	-	-
LF 5	1.58144	40.85	14.233	4.4	1.6
F 2	1.62004	36.37	17.050	5.9	2.8
BaSF 2	1.66446	35.83	18.545	-	-
BaSF 51	1.72373	38.11	18.991	12.1	8.1
LaF N2	1.74400	44.77	16.618	3.4	1.1
LaF N21	1.78831	47.39	16.633	6.1	3.8
LaSF 30	1.80318	46.45	17.292	-	-
LaSF 31	1.88067	41.10	21.429	6.2	3.5
SF 2	1.64769	33.85	19.135	-1.8	-2.6
SF 59	1.95250	20.36	46.774	-	-
SF N64	1.70585	30.30	22.295	4.3	0.9
TiK 1	1.47869	58.70	8.155	-1.8	-2.6
TiF 1	1.51118	51.01	10.022	-0.1	-1.5
TiF 6	1.61650	30.97	19.904	-	-
KzF N1	1.55115	49.64	11.103	5.0	3.1
KzFS N4	1.61340	44.30	13.848	6.2	4.4
LgSK 2	1.58599	61.04	9.600	-2.5	-4.0
NbF 1	1.74330	59.23	-	7.9 (633 nm)	-

* dn/dT in air; 0/+20°C

2.2.2 Internal transmittance (5 mm)

Glass type	Wavelength				
	320 nm	400 nm	700 nm	1530 nm	2325 nm
FK 5	0.975	0.998	0.999	0.993	0.91
FK 51	0.87	0.996	0.999	0.999	0.999
PK 2	0.84	0.998	0.999	0.999	0.975
PSK 3	0.85	0.997	0.999	0.996	0.91
PSK 53	0.05	0.96	0.997	0.985	0.94
BK 7	0.81	0.998	0.999	0.997	0.89
UBK 7	0.920	0.998	0.999	0.997	0.88
BaLK N3	0.82	0.998	0.999	0.997	0.91
K 5	0.78	0.997	0.999	0.998	0.91
UK 50	0.92	0.998	0.997	0.996	0.92
ZK 1	0.77	0.996	0.999	0.995	0.92
ZK N7	0.69	0.992	0.999	0.995	0.92
BaK 50	0.36	0.998	0.999	0.994	0.93
SK 2	0.71	0.995	0.999	0.998	0.952
SK 14	0.73	0.994	0.999	0.994	0.90
KF 9	0.41	0.996	0.999	0.999	0.90
BaLF 4	0.08	0.995	0.999	0.997	0.94
SSK 4	0.4	0.994	0.999	0.997	0.94
SSK N5	—	0.981	0.998	0.997	0.93
LaK N7	0.46	0.992	0.999	0.997	0.89
LaK 10	0.20	0.981	0.999	0.998	0.87
LLF 6	0.84	0.998	0.999	0.998	0.90
BaF 4	0.15	0.994	0.999	0.999	0.951
BaF N10	—	0.965	0.999	0.997	0.93
LF 5	0.60	0.998	0.999	0.999	0.92
F 2	0.20	0.998	0.999	0.999	0.93
BaSF 2	—	0.963	0.999	0.998	0.959
BaSF 51	—	0.956	0.998	0.999	0.89
LaF N2	0.02	0.968	0.999	0.996	0.93
LaF 21	—	0.975	0.999	0.999	0.88
LaSF 30	—	0.975	0.999	0.999	0.87
LaSF 31	0.13	0.93	0.999	0.998	0.961
SF 2	0.01	0.994	0.999	0.999	0.94
SF 59	—	0.60	0.994	0.999	0.950
SF N64	—	0.93	0.999	0.998	0.950
TiK 1	0.17	0.94	0.998	0.999	—
TiF 1	—	0.981	0.998	0.999	0.89
TiF 6	—	0.90	0.996	0.998	0.68
KzF 1	0.46	0.986	0.999	0.990	0.92
KzFS N4	0.50	0.988	0.999	0.996	0.790
LgSK 2	0.07	0.970	0.996	0.979	—

2.2.3 Mechanical Properties

Glass type	Density (g/cm ³)	Young's modulus E (10 ³ N/mm ²)	Poisson's ratio μ	Knoop hardness (kg/mm ²)	Stress-optical coefficient K (TPa) ⁻¹
FK 5	2.45	62	0.205	450	2.91
FK 51	3.73	79	0.287	360	0.67
PK 2	2.51	84	0.209	520	—
PSK 3	2.91	84	0.226	510	—
PSK 53	3.60	77	0.287	370	—
BK 7	2.51	81	0.208	520	2.74
BaLK N3	2.61	72	0.212	470	—
K 5	2.59	71	0.227	450	—
UK 50	2.62	73	0.240	460	—
ZK 1	2.71	68	0.214	430	—
ZK N7	2.49	71	0.259	450	3.62
BaK 50	2.93	81	0.263	520	—
SK 2	3.55	78	0.261	460	—
SK 14	3.44	86	0.202	490	2.00
KF 9	2.71	67	0.244	440	—
BaLF 4	3.17	76	0.265	460	—
SSK 4	3.63	79	0.278	460	—
SSK N5	3.71	88	0.277	470	—
LaK N7	3.84	90	0.288	460	—
LaK 10	3.81	111	0.205	580	—
LLF 6	2.81	63	0.247	420	—
BaF 4	3.50	66	0.281	400	—
BaF N10	3.76	89	0.226	480	—
LF 5	3.22	59	0.225	410	2.81
F 2	3.61	58	0.245	370	—
BaSF 2	3.90	66	0.289	410	—
BaSF 51	4.31	80	0.293	450	—
LaF N2	4.54	87	0.294	450	1.65
LaF N21	4.44	120	0.290	630	—
LaSF 30	4.56	124	0.298	630	—
LaSF 31	5.24	123	0.231	620	—
SF 2	3.86	55	0.269	350	2.65
SF 59	6.26	51	0.250	250	-1.46
SF N64	3.00	93	0.254	500	—
TiK 1	2.39	40	0.239	330	—
TiF 1	2.47	58	0.263	440	—
TiF 6	2.79	65	0.225	410	—
KzF N1	2.71	60	0.276	500	—
KzFS N4	3.20	60	0.290	380	—
LgSK 2	4.15	76	0.308	340	—
NbF 1	4.17	108	—	675	—

2.2.4 Thermal Properties

Glass type	Thermal expansion* (10 ⁻⁶ /K)	Thermal conductivity (W/m K)	Specific heat (J/g K)	Transform. temp. (°C)	Softening temp. (°C)
FK 5	9.2	0.925	0.818	464	672
FK 51	16.9	—	—	403	—
PK 2	6.9	1.149	0.80	568	721
PSK 3	7.4	0.990	0.682	602	736
PSK 53	10.7	0.612	0.603	614	—
BK 7	7.1	1.114	0.858	563	766
BaLK N3	9.0	1.029	0.749	562	738
K 5	8.2	0.950	0.783	583	720
UK 50	8.1	0.964	—	554	735
ZK 1	7.5	0.894	0.77	562	732
ZK N7	5.4	1.042	0.770	528	721
BaK 50	4.6	1.044	0.758	629	820
SK 2	7.0	0.776	0.595	654	823
SK 14	7.0	0.851	0.636	649	773
KF 9	638	1.01	0.75	445	661
BaLF 4	6.4	0.827	0.67	569	731
SSK 4	6.1	0.806	0.57	639	791
SSK N5	7.9	—	0.574	641	751
LaK N7	8.2	—	—	618	716
LaK 10	6.9	—	—	620	703
LLF 6	8.5	—	—	422	627
BaF 4	8.8	0.766	0.557	521	694
BaF N10	7.9	0.798	0.595	630	745
LF 5	9.1	0.866	0.657	419	585
F 2	8.2	0.780	0.557	432	593
BaSF 2	9.3	—	—	493	640
BaSF 51	6.4	0.722	0.536	522	630
LaF N3	9.1	0.670	0.481	616	736
LaF N21	6.9	—	—	667	—
LaSF 30	7.1	—	—	684	—
LaSF 31	7.9	—	—	753	—
SF 2	9.2	0.735	0.498	441	600
SF 59	10.3	0.506	0.306	362	—
SF N64	9.7	—	—	578	666
TiK 1	10.3	0.773	0.842	340	—
TiF 1	9.1	0.953	0.81	443	—
TiF 6	16.7	—	—	410	494
KzF N1	7.5	—	—	470	675
KzFS N4	5.5	0.769	0.64	492	594
LgSK 2	12.1	0.866	0.51	515	—
NbF 1	5.3	0.845	0.48	590	625

* 20/300 °C

2.3 Specialty Optical Glasses

Designation	Glass type	Composition
Vycor® (Corning 7913)	silica	96% SiO ₂
Pyrex® (Corning 7740)	borosilicate	SiO ₂ –B ₂ O ₃ –Na ₂ O–Al ₂ O ₃
<i>Ultraviolet transmitting glasses</i>		
Corning 9741	alkali borosilicate	SiO ₂ –B ₂ O ₃ –Na ₂ O + ...
Schott UBK 7	borosilicate	SiO ₂ –B ₂ O ₃ –Na ₂ O–CaO + ...
ULTRAN 30 (Schott)		
Hoya UBS250		
<i>Infrared transmitting glasses</i>		
Fused germania	germanium oxide	100% GeO ₂
Corning 9753	calcium aluminate	SiO ₂ –CaO–Al ₂ O ₃
Corning 9754	calcium aluminate	GeO ₂ –CaO–Al ₂ O ₃ –BaO–ZnO
Barr&Stroud BS-39B	calcium aluminate	CaO–Al ₂ O ₃ –MgO
Kigre BGA	germanate	BaO–Ga ₂ O ₃ –GeO ₂
Schott IRG 2	germanate	
Schott IRG 9	fluorophosphate	P ₂ O ₅ + ...
Schott IRG 11	calcium aluminate	CaO–Al ₂ O ₃ + ...
Schott IRG 100	chalcogenide	
Arsenic trisulfide	chalcogenide	100% As ₂ S ₃
Arsenic triselenide	chalcogenide	100% As ₂ Se ₃
AMTIR-1	chalcogenide	Ge ₃₃ As ₁₂ Se ₅₅
AMTIR-3	chalcogenide	Ge ₂₈ As ₁₂ Se ₆₀
<i>Fluoride glass</i>		
Ohara HTF-1	fluoride	
<i>Low expansion glasses</i>		
CLEARCERAM 55 (Ohara)	glass ceramic	
CLEARCERAM 63 (Ohara)	glass ceramic	
LE30 (Hoya)	glass ceramic	aluminosilicate
Zerodur (Schott)	glass ceramic	SiO ₂ –Al ₂ O ₃ –P ₂ O ₅ + ...
ULE (Corning 7971)	glass ceramic	SiO ₂ –TiO ₂
<i>Athermal glasses</i>		
Schott PSK 54	dense phosphate crown	P ₂ O ₅ –(B,Al) ₂ O ₃ –R ₂ O–MO
Schott TiF 6	titanium flint	SiO ₂ (B ₂ O ₃)–TiO ₂ –Al ₂ O ₃ –KF
<i>Acoustooptic glasses</i>		
Hoya AOT-5	tellurite	TeO ₂ + ...
Hoya AOT-44B	tellurite	TeO ₂ + ...
<i>Low nonlinear refractive index glass</i>		
Schott FK 54	fluorophosphate	P ₂ O ₅ + ...

2.3.1 Optical Properties

Glass type	Transmission range (μm)	Refractive index n_d	Abbe number v_d	dn/dT ($10^{-6}/\text{K}$)
Vycor® (Corning 7913)	0.3–2.4			
Pyrex® (Corning 7740)		1.474		
<i>Ultraviolet transmitting glasses</i>				
Corning 9741	0.25–	1.47	65	
Schott UBK 7	0.32–2.1	1.5168	64.3	
ULTRAN 30 (Schott)	0.28–	1.5483	74.3	−5.8 (546 nm)
Hoya UBS250	0.27–	1.472	65.8	
<i>Infrared transmitting glasses</i>				
Fused germania	0.30–4.9	1.60832 (n_D)	41.2	
Corning 9753	0.38–4.3	1.60475 (n_D)		
Corning 9754	0.36–4.8	1.6601 (n_D)	46.5	
Barr&Stroud BS-39B	0.38–4.9	1.6764 (n_D)	44.5	7.4 (589.3 nm)
Kigre BGA	0.5–5.0	1.663 (n_D)	45.6	12
Schott IRG 2	0.44–5.1	1.8918	30.0	
Schott IRG 9	0.38–4.1	1.4861	81.0	
Schott IRG 11	0.44–4.75	1.6809	44.2	
Schott IRG 100	0.93–13	2.7235 (n_1)		103 (2.5 μm)
Arsenic trisulfide	0.62–11.0	2.47773 (n_1)		85 (0.6 μm)
Arsenic triselenide	0.87–17.2	2.7728 (n_{12})		55 (0.83 μm)
AMTIR-1	0.75–14.5	2.6055 (n_1)		101 (1 μm)
AMTIR-3	0.93–16.5	2.6366 (n_3)		98 (3 μm)
<i>Fluoride glass</i>				
Ohara HTF-1	0.21–6.9	1.44296	92.5	
<i>Low expansion glasses</i>				
CLEARCERAM 55 (Ohara)	0.42–	1.547	55.0	
CLEARCERAM 63 (Ohara)	0.40–	1.547	55.1	
LE30 (Hoya)	0.35–	1.532		
Zerodur (Schott)	0.4–2.3	1.5424	56.1	15.7
ULE (Corning 7971)	0.23–3.9	1.5418	75.2	−5.5
<i>Athermal glasses</i>				
Schott PSK 54		1.5860	64.6	
Schott TiF 6	0.4–1.7	1.6165	31.0	
<i>Acoustooptic glasses</i>				
Hoya AOT-5		2.10238	18.10	
Hoya AOT-44B		1.97961	20.58	
<i>Low nonlinear refractive index glass</i>				
Schott FK 54	0.35–2.5	1.4370	90.7	−5.68 (546 nm)

2.3.2 Mechanical Properties

Glass type	Density (g/cm ³)	Young's modulus E (10 ³ N/mm ²)	Poisson's ratio μ	Knoop hardness (kg/mm ²)	Stress-optic coefficient K (TPa) ⁻¹
Vycor® (Corning 7913)	2.18	68.8	0.19	487	
Pyrex® (Corning 7740)	2.23	62.8	0.200	418	3.9
<i>Ultraviolet transmitting glasses</i>					
Corning 9741	2.17	72	0.23		
Schott UBK 7	2.51	81	0.212	500	
ULTRAN 30 (Schott)	4.02	76	0.297	380	
Hoya UBS250	2.26	59.1	0.222	488	
<i>Infrared transmitting glasses</i>					
Fused germania	3.60	43.1	0.192		
Corning 9753	2.798	98.6	0.28	600	
Corning 9754	3.581	84.1	0.290	560	
Barr&Stroud BS-39B	3.1	104	0.29		
Kigre BGA	3.6	84.1	0.29	560	
Schott IRG 2	5.00	95.9	0.282	481	
Schott IRG 9	3.63	77.0	0.288	346	
Schott IRG 11	3.12	107.5	0.284	610	
Schott IRG 100	4.67	21	0.261	150	
Arsenic trisulfide	3.20	15.8	0.295	180	
Arsenic triselenide	4.69	18.3	0.288	120	
AMTIR-1	4.41	22.1	0.27	170	
AMTIR-3	4.67	21.4	0.26	150	
<i>Fluoride glass</i>					
Ohara HTF-1	3.94	64.2	0.28	320	
<i>Low expansion glasses</i>					
CLEARCERAM 55 (Ohara)	2.56	95.8	0.25	680	
CLEARCERAM 63 (Ohara)	2.57	95.5	0.25	660	
LE30 (Hoya)	2.58	75.4	0.159	657	2.9
Zerodur (Schott)	2.53	91	0.24	630	3.0
ULE (Corning 7971)	2.205	67.3	0.17	460	4.0
<i>Athermal glasses</i>					
Schott PSK 54	3.52			340	
Schott TiF 6	2.79	65	0.262	310	
<i>Acoustooptic glasses</i>					
Hoya AOT-5	5.87			290	
Hoya AOT-44B	5.06			226	
<i>Low nonlinear refractive index glass</i>					
Schott FK 54	3.18	76	0.286	320	

2.3.3 Thermal Properties

Glass type	Thermal expansion ($10^{-6}/\text{K}$)	Thermal conduct. (W/m K)	Specific heat (J/g K)	Transform. temp. (K)	Softening temp. (K)
Vycor® (Corning 7913)	0.75	1.38	0.75	890	1200
Pyrex® (Corning 7740)	3.25	1.13	1.05	560	821
<i>Ultraviolet transmitting glasses</i>					
Corning 9741	3.8			733	978
Schott UBK 7	8.3			563	716
ULTRAN 30 (Schott)	13.9	0.667	0.58	513	600
Hoya UBS250	5.6	0.96		449	645
<i>Infrared transmitting glasses</i>					
Fused germania	6.3		0.746	800	
Corning 9753	6.0	2.3	0.795	1015	
Corning 9754	6.2	0.81	0.54	1008	1147
Barr&Stroud BS-39B	6.3		0.865		970
Kigre BGA	6.3			741	873
Schott IRG 2	8.8	0.91	0.495	975	
Schott IRG 9	16.1	0.88	0.695	696	
Schott IRG 11	8.2	1.13	0.749	1075	
Schott IRG 100	15.0	0.3		550	624
Arsenic trisulfide	26.1	0.17	0.473	436	573
Arsenic triselenide	24.6	0.20	0.349		345
AMTIR-1	12.0	0.25	0.293	635	678
AMTIR-3	13.5	0.22	0.276	550	570
<i>Fluoride glass</i>					
Ohara HTF-1	16.1			658	
<i>Low expansion glasses</i>					
CLEARCERAM 55 (Ohara)	0.2	1.62	0.76		
CLEARCERAM 63 (Ohara)	-2.1	1.62	0.73		
LE30 (Hoya)	0.4			690	921
Zerodur (Schott)	0.5	1.64	0.821		
ULE (Corning 7971)	0.03	1.31	0.776	1000	1490
<i>Athermal glasses</i>					
Schott PSK 54	11.9			486	568
Schott TiF 6	16.7			410	494
<i>Acoustooptic glasses</i>					
Hoya AOT-5	16.1			332	347
Hoya AOT-44B	20.1			296	314
<i>Low nonlinear refractive index glass</i>					
Schott FK 54	16.9			403	

2.4 Fused (Vitreous) Silica*

Different types of silica have been commercially available from several suppliers (Corning Incorporated, Heraeus Amersil, Thermal Syndicate Ltd, General Electric Co., Quartz et Silice [France], Dynasil Corp. of America, NSG Quartz [Japan], Westdeutsche Quartzschmelze GmbH (Germany), Nippon Glass [Japan]). The glasses are compositionally the same except for metallic impurities, structural defects, and water content, but these differences and fabrication variations cause the properties of the silicas to differ significantly. The vitreous silicas can be distinguished by the source of raw material used and the process of melting or consolidating the raw material into bulk vitreous silica. It is produced commercially from naturally occurring quartz of high purity and from silicon tetrachloride liquid or vapor or from tetraethyl orthosilicate liquid. These precursors are processed in several different ways. Hetherington et al.¹ divided the different silicas into four types based on manufacturing method

In one method, naturally occurring quartz is purified to varying degrees by preselection of clean crystalline material, fragmented to a fine powder, and fused to bulk glass. The fusion is performed by electric melting in a refractory crucible or container under vacuum, an inert atmosphere, or a hydrogen atmosphere. This produces a type of vitreous silica designated as type I. If the same raw material is fused using an oxyhydrogen torch or an isothermal plasma torch, then the resultant vitreous silica is designated type II. The principal differences between these are the lower hydroxyl content and different impurities of type I.

Melting atmosphere influences the glass structure and properties. After fusion, various amounts of hot working are performed to homogenize the resultant silica glasses. The synthetic precursors, mainly SiCl_4 , are fused to a solid glass with an oxyhydrogen torch producing a very pure but wet material denoted type III. These precursors also can be used to produce vitreous silica under relatively dry conditions such as those present using an oxygen or argon plasma torch. This material has been designated type IV. The principal difference between types III and IV fused silica is OH content which introduces strong absorption around $2.8 \mu\text{m}$.

Using similar torches but depositing on a cooler bait, the synthetic material can also be formed into a porous boule that is subsequently consolidated to a fully dense silica boule in a furnace. Consolidation of the porous silica body can involve firing in different atmospheres and can be achieved at a temperature several hundred degrees below that used for fusion of the type III and type IV silica. The commercialization of this latter technology has occurred principally in the fabrication of optical fibers based on vitreous silica. Certain manufacturers have used this technology for the fabrication of bulk silica. This vitreous silica is similar to type III or IV depending on the method of consolidation, but the processing is sufficiently different that it should be considered in a class by itself. Although there is varied opinion on what kind of silica should be designated type V, there is general agreement that there are many types of vitreous silica which, because of the dependence on fabrication, do not fall into the earlier established four types. Fleming² has viewed the consolidated soot sufficiently close to type III and IV that it is designated type V in the following tables. Fluoride-doped, low-OH silica glass has recently been developed for deep UV and vacuum UV applications and is designated as modified silica.³ Optical, mechanical, and thermal properties of the various types of silicas are compared below.

* From Fleming, J. W., Optical glasses, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, 1995), p. 69 (with additions).

Glass Type	Brand name	Source
SiO ₂ I	IR-Vitreosil	4
	Infrasil	5
	Pursil 453, Ultra	6
	GE 104, 105, 201, 204, 124, 125	7
SiO ₂ II	Herasil, Homosil, Ultrasil, Optosil	5
	Vitreosil 055, 066, 077	4
SiO ₂ III	Suprasil	5
	Spectrosil	4
	7940, 7980 (HPFS)	8
	Dynasil	9
	Tetrasil	6
	NSG-ES	10
	GE 151	7
SiO ₂ IV	Synsil	11
	Suprasil W	5
SiO ₂ V	Spectrosil WF	4
	Nippon Sheet Glass	12
Sol gel SiO ₂	Gelsil	13

Refractive Index Properties¹⁴

λ (nm)	Refractive index			dn/dT ($10^{-6}/K$)		
	Suprasil	Homosil/ Herasil/ Infrasil	HPFS 7980	Suprasil	Homosil/ Herasil/ Infrasil	HPFS 7980
193	1.56077		1.560841	193		20.6
238				238	14.6	15.2
248	1.50855		1.508601	248		14.2
308	1.48564		1.485663	308		12.1
365	1.47447	1.47462	1.474555	365	11.0	11.5
405	1.46962	1.46975	1.469628	405		10.8
436	1.46669	1.46681	1.466701	436		10.6
486	1.46313	1.46324	1.463132	486		10.4
546	1.46008	1.46018	1.460082	546	9.9	10.6
588	1.45846	1.45856	1.458467	588	9.8	10.5
633	1.45702		1.457021	633		10.0
644				644	9.6	10.4
656	1.45637	1.45646	1.456370	656		9.9
1064			1.449633	1064		9.6
1500	1.44462	1.44473		1500		
2000	1.43809	1.43821		2000		
2500	1.42980	1.42995		2500		
3000	1.41925	1.41941		3000		
3500	1.40589	1.40605		3500		

Optical Properties

Glass type	Data source	Transmission range (μm)	Refractive index n_d	Abbe number v_d	dn/dT ($10^{-6}/\text{K}$)
SiO_2 I	4,5,7	0.21–2.8	1.45867	67.56	10.5
SiO_2 II	4,5	0.19–3.5	1.45857	67.6	—
SiO_2 III	5,8	0.17–2.2	1.45847	67.7	9.9
SiO_2 IV	5	0.18–3.5	—	—	—
SiO_2 V	12	0.18–3.5	1.45847	67.7	9.9
Sol gel SiO_2	13, 15	0.17–3.5	1.458–1.463	66.4–67.8	—
Mod. SiO_2	16,17	0.155–3.5	1.65423 (157 nm)	—	39 (157 nm)

Resistance to humidity: fused silica exhibits no or very little surface deterioration due to climatic conditions.

Dispersion formula¹⁸ (wavelength λ in μm)

$$n^2 = 1 + 0.6961663\lambda^2/[\lambda^2 - (0.0684043)^2] + 0.4079426\lambda^2/[\lambda^2 - (0.1162414)^2] + 0.8974794\lambda^2/[\lambda^2 - (9.896161)^2]$$

Range (μm)

Mechanical Properties					
Glass type	Density (g/cm^3)	Young's modulus E (10^3 N/mm^2)	Poisson's ratio μ	Hardness (Knoop) (kg/mm^2)	Stress-optical coefficient K (TPa^{-1})
SiO_2 I	2.203	72	0.17	570	3.5
SiO_2 II	2.203	70	0.17	600	—
SiO_2 III	2.201	70	0.17	610	—
SiO_2 IV	2.201	70	0.17	600	—
SiO_2 V	2.201	70	0.17	600	—
Sol gel SiO_2	2.204	73	—	—	—
Mod. SiO_2	2.201	69	0.17	—	—

Thermal Properties

Glass type	Thermal expansion ($10^{-6}/\text{K}$)	Thermal conductivity (W/m K)	Specific heat (J/g K)	Transformation temperature ($^\circ\text{C}$)	Softening temperature ($^\circ\text{C}$)
SiO_2 I	0.55	1.4	0.67	1215	1683
SiO_2 II	0.55	1.38	0.75	1175	1727
SiO_2 III	0.60	1.38	0.74	1080	1590
SiO_2 IV	0.55	1.38	0.75	1110	1650
SiO_2 V	0.60	1.38	0.74	1080	1590
Sol gel SiO_2	0.57	—	—	~1160	—
Mod. SiO_2	0.51*	1.37	0.77	—	—

* 0–300°C

Properties of Modified Silica¹⁹

Wavelength (nm)	Refractive Index Data For Fluorine-Doped Silica Blanks					
	0% F	0.17 wt.% F	0.67 wt.% F	0.8 wt.% F	1.12 wt.% F	1.48 wt.% F
435.8	1.4671	1.466	1.4638	1.4634	1.4618	1.4604
480	1.4639	1.4628	1.4606	1.4603	1.4586	1.4573
546.1	1.4605	1.4594	1.4573	1.4569	1.4553	1.4539
589.3	1.4588	1.4578	1.4556	1.4552	1.4537	1.4524
632.8	1.4576	1.4568	1.4546	1.4542	1.4529	1.4515
643.8	1.4572	1.4561	1.4539	1.4536	1.452	1.4507
777	1.4533	1.4526	1.4502	1.4499	1.4485	1.4474
1300	1.4472	1.4461	1.4444	1.4436	1.4423	1.4411
1541	1.4441	1.4433	1.4409	1.4405	1.4393	1.438
Coeff. thermal expansion (10⁻⁶/K)	0.59	—	—	0.51	—	0.43
Anneal point (°C)	1094	962	883	866	833	807

References:

1. Hetherington, G., Jack, K. H., and Kennedy, J. C., The viscosity of vitreous silica, *Phys. Chem. Glass* 5, 123 (1970).
2. Flerming, J. W., Optical glasses, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, 1995), p. 69.
3. Smith, C. M. and Moore, L. A., *Proc. SPIE* 3676, 834 (1999).
4. Thermal Syndicate Ltd, Montville, NJ
5. Heraeus Amersil, Duluth, GA
6. Quartz et Silice, France
7. General Electric Co., Cleveland, OH
8. Corning Incorporated
9. Dynasil Corp. of America, Berlin, NJ
10. NSG Quartz, Japan
11. Westdeutsche Quarzschmelze GmbH, Germany
12. Nippon Sheet Glass, Japan
13. Hench, L. L., Wang, S. H., and Nogues, J. L., Gel-silica optics, *Proc. SPIE* 878, 76 (1988).
14. Data from Heraeus Amersil (Suprasil, Homosil, Herasil, Infrasil) and Corning (HPFS, 7980).
15. Shoup, R. D., Gel-derived fused silica for large optics, *Ceramic Bull.* 70, 1505 (1991).
16. Smith, C. M., Modified silica transmits vacuum UV, *Optoelectronics World* (July 2001), p. S15.
17. Moore, L. A. and Smith, C. M., Fused silica for 157-nm transmittance, *Proc. SPIE* 3673, 392 (1999).
18. Rodney, W. S. and Spinder, R. J., Index of refraction of fused quartz glass for ultraviolet, visible, and infrared wavelengths, *J. Res. Natl. Bur. Stand.* 53, 185 (1954).
19. Moore, L. A. and Smith, C. M. (private communication, 2002).

2.5 Fluoride Glasses

2.5.1 Fluorozirconate Glasses

Fluorozirconate Glass Compositions

Glass	Composition (mol %)								
	ZrF ₄	BaF ₂	GdF ₃	LaF ₃	YF ₃	AlF ₃	ThF ₄	LiF	NaF
ZBL	62	33	—	5	—	—	—	—	—
ZBG	63	33	4	—	—	—	—	—	—
ZBGA	61	32	4	—	—	3	—	—	—
ZBT	60	33	—	—	—	—	7	—	—
ZTL	60	—	—	7	—	—	23	—	—
ZBAN	58	15	—	—	—	6	—	—	21
ZBLA	57	34	—	5	—	4	—	—	—
ZBGA	60	32	4	—	—	4	—	—	—
ZBLAL	52	20	—	5	—	3	—	20	—
ZBLYAL	49	22	—	3	3	3	—	20	—
ZBLAN	56	14	—	6	—	4	—	—	20

Optical Properties

Glass type	Transmission range (μm)	Refractive index n_D	Abbe number v_d	$\frac{\text{dn}}{\text{dT}} (10^{-6}/\text{K})$	
				435.8 nm	1060 nm
ZBL	0.25–7.0	1.523	—	—	—
ZBT	0.32–6.8	1.53	—	—	—
ZBLA	0.29–7.0	1.521	62	—	—
ZBLAN	0.25–6.9	1.480	64	—14.5 (633 nm)	—

Mechanical Properties

Glass type	Density (g/cm ³)	Young's modulus E	Poisson's ratio μ	Hardness (Knoop)	Stress-optical coeff. K (TPa) ⁻¹
					435.8 nm
ZBL	4.78	60	0.31	228	—
ZBT	4.8	60	0.28	250	—
ZBLA	4.61	60.2	0.25	235	—
ZBLAN	4.52	60	0.31	225	—

Thermal Properties

Glass type	Thermal expansion ($10^{-6}/\text{K}$)	Thermal conductivity (W/m K)	Specific heat (J/g K)	Transformation temperature (K)	Softening temperature (K)
					435.8 nm
ZBL	18.8	—	0.538	580	—
ZBT	4.3	—	0.511	568	723
ZBLA	18.7	—	0.534	588	—
ZBLAN	17.5	0.4	0.520	543	—

2.5.2 Fluorohafnate Glasses

Fluorohafnate Glass Composition (mol %)

Glass	HfF ₄	BaF ₂	LaF ₃	AlF ₃	ThF ₄
HBL	62	33	5	—	—
HBT	60	33	—	—	7
HBLA	58	33	5	4	—

Optical Properties

Glass type	Transmission range (μm)	Refractive index n_D	Abbe number v_d	$\frac{dn}{dT} (10^{-6}/\text{K})$	
				435.8 nm	1060 nm
HBL	0.25–7.3	1.498	—	—	—
HBT	0.22–7.7	1.53	—	—	—
HBLA	0.29–7.3	1.504	—	—	—

Mechanical Properties

Glass type	Density (g/cm ³)	Young's modulus E	Poisson's ratio μ	Hardness (Knoop)	Stress-optical coeff. K (TPa) ⁻¹
HBL	5.78	55	0.3	228	—
HBT	6.2	55	0.3	250	—
HBLA	5.88	56	0.3	240	—

Thermal Properties

Glass type	Thermal expansion ($10^{-6}/\text{K}$)	Thermal conductivity (W/m K)	Specific heat (J/g K)	Transformation temperature (K)	Softening temperature (K)
HBL	18.3	—	0.413	605	—
HBT	6.0	—	0.428	593	—
HBLA	17.3	—	0.414	580	—

Data in the tables of Sections 2.5.1 and 2.5.2 are from the *Handbook of Optics, Vol. II* (McGraw-Hill, New York, 1995), chapter 33, and references cited therein.

2.5.3 Other Fluoride Glasses

Fluoroberyllate Glasses

Glass	Composition (mol %)						
	BeF ₂	MgF ₂	CaF ₂	BaF ₂	AlF ₃	LiF	KF
BF	100	—	—	—	—	—	—
BLK	60	—	—	—	—	20	20
BACK	49	—	14	—	10	—	27
BAMCBa	35	19	10	14	22	—	—

Properties of Fluoroberyllate Glasses

Glass	Density (g/cm ³)	Refractive index n _D	Nonlinear index (m ² /W)	Abbe number	Hardness (kg/mm ²)
BF	2.122	1.275	0.75	105	300
BACK	2.621	1.3459	1.03	96	215
BAMCBa	3.247	1.3538	1.14 (calc.)	~95	315

Barium Indium Fluoride Glasses

Glass	Composition (mol %)						
	BaF ₃	InF ₃	GaF ₃	ZnF ₂	YbF ₃	ThF ₄	ZrF ₄
BlZnYbT	30	30	—	20	10	10	—
BlG	30	18	12	20	10	6	4

Aluminofluoride Glasses

	Composition (mol %)										
	AlF ₃	BaF ₂	CaF ₂	YF ₃	SrF ₂	MgF ₂	CdF ₂	LiF	NaF	ZrF ₄	PbF ₂
YABC	40	20	20	20	—	—	—	—	—	—	—
CLAP	30.6	—	—	—	—	—	26.1	10	—	—	33.3
ABC	30.2	9.9	19.2	8.3	12.4	3.5	—	—	3.8	10.2	2.5

2.6 Chalcogenide Glasses

Chalcogenide Glass-Forming Systems

System	Example glass (atomic %)
As-S	As 40, S 60
As-Se	As 40, Se 60
Ge-S	Ge 20, S 80
Ge-Se	Ge 20, Se 80
Ge-As-S	Ge 25, As 15, S 60
Ge-As-Se	Ge 33, As 12, Se 55
Ge-As-Te	Ge 10, As 20, Te 70
Ge-Se-Te	Ge 22, Se 20, Te 58
Ge-Sb-Se	Ge 28, Sb 12, Se 60
Ge-P-S	Ge 70, P 5, S 25
Ge-As-Se-Te	Ge 30, As 13, Se 27, Te 30

Refractive Indices of Chalcogenide Glasses

Glass (atomic %)	Refractive Index (n_λ), λ in μm							$[\text{dn/dT}]_\lambda$ (10^{-5}K^{-1})
	n_2	n_3	n_4	n_5	n_8	n_{10}	n_{12}	
As40, S60	2.4268	2.4152	2.4116	2.4074	2.3937	2.3822	—	[0.9]5
As40, Se60	—	—	—	—	2.7789	2.7789	2.7738	—
Ge20, Se80	—	—	—	—	2.4071	2.4027	2.3973	—
Ge25, As15, Se60	2.22	—	—	—	—	—	—	—
Ge10, As20, Se70	—	—	—	—	2.4649	2.4594	2.4526	—
Ge10, As30, Se60	—	—	—	—	2.6256	2.6201	2.6135	—
Ge10, As40, Se50	—	—	—	—	2.6108	2.6067	2.6016	—
Ge33, As13, Se55	2.5310	2.5184	2.5146	2.5112	2.5036	2.4977	2.4902	[7.2]10.6
Ge10, As20, Te70	—	—	—	3.55	—	—	—	—
Ge28, Sb12, Se60	—	2.6266	2.6210	2.6173	2.6088	2.6023	2.5942	[9.1]10
Ge30, As13, Se27, Te30	—	2.8818	2.8732	2.8688	2.8610	2.8563	2.8509	[15]10

Physical Properties of Chalcogenide Glasses

Glass (atomic %)	T_g (°C)	Thermal expansion ($10^{-6}/^\circ\text{C}$)	Density (g/cm^3)	Hardness (kg/mm^2)	Young's modulus (G Pa)	Fracture toughness ($\text{N mm}^{-3/2}$)
As40, S60	180	21.4	3.15	109(K)	15.9	—
As40, Se60	178	21.0	4.62	—	—	—
Ge20, Se80	154	24.8	4.37	147(V)	—	—
Ge25, As15, Se60	425	12.8	3.00	200(K)	—	—
Ge10, As20, Se70	159	24.8	4.47	154(V)	16.5	6.7 ± 0.4
Ge10, As30, Se60	210	190	4.51	176(V)	18.0	7.1 ± 0.6
Ge10, As40, Se50	222	20.9	4.49	173(V)	15.9	7.4 ± 0.8
Ge33, As13, Se55	362	12.0	4.40	170(K)	22.1	—
Ge10, As20, Te70	—	18.0	—	111(K)	—	—
Ge28, Sb12, Se60	277	13.5	4.67	159(K)	21.5	—
Ge30, As13, Se27, Te30	262	12.8	4.91	226(V)	—	—

K, Knoop; V, Vickers

Chalcohalide Glass-Forming Systems

As-based systems	Ge-based systems	Te-based systems	Other systems
As-S-Cl	Ge-S-Br	Te-Cl	Sb-S-Br
As-S-Br	Ge-S-I	Te-Br	Sb-S-I
As-S-I	Ge-S-Ag-I	Te-S-Cl	Sb-Se-I
As-Se-Br	Ge-As-S-I	Te-S-Br	Si-S-Cl
As-Se-I	Ge-Se-Br	Te-S-I	Si-S-I
As-Se-In-I	Ge-Se-I	Te-Se-Cl	Si-Se-I
As-Te-Br	Ge-Te-I	Te-Se-Br	Cs-Al-S-Cl
As-Te-I		Te-Se-I	Cs-Ga-S-Cl
		Te-Se-As-I	

Properties of Chalcohalide Glasses

Glass (atomic %)	T _g (°C)	Thermal expansion (10 ⁻⁶ /°C)	Density (g/cm ³)	Hardness (kg/mm ²)	n _λ (λ in μm)
As 30, S 60, Br 10	120	—	3.1	110	—
As 30, Se 60, Br 10	70	—	4.33	110	—
As 30, Te 60, Br 10	95	—	4.92	110	—
As 40, S 50, Cl 10	145	46.7	2.62	71	—
As 30, S 60, Cl 10	122	49.0	4.26	40	—
Ge 30, S 60, Br 10	322	—	—	—	1.883 (0.63)
Ge 30, S 60, I 10	370	—	2.90	—	2.0 (0.63)
Te 60, Cl 40	82	31.0	4.63	—	—
Te 60, Br 40	73	—	—	—	—
Te 60, I 40	44	—	—	—	—
Te 50, Sl6.7, Cl 33.3	80	33.0	—	—	—
Te 50, Se16.7, Cl 33.3	81	—	4.2	—	—
Te 30, S 50, Cl 20	73	74	—	—	—
Te 30, S 50, Br 20	64	60	—	—	—
Te 50, S 16.7, Br 33.3	71	33	—	—	—
Te 50, Se 30, Br20	—	—	—	—	2.86 (10.6)
Te10, Se 70, I 20	53	44.6	4.6	—	—
Te 30, Se 25, I 45	49	—	—	—	—
Te 30, Se 30, I 40	48	62.7	5.0	—	2.80 (10.6)
Te 20, Se 30, As 40 I 10	120	—	4.71	—	2.87 (10.6)

Tables in Section 2.6 are from Bruce, A. J., Optical waveguide materials:glasses, *Handbook of Laser Science and Technology, Suppl. 2* (CRC Press, Boca Raton, FL, 1998), p. 691.

2.7 Magneto-optic Properties

2.7.1 Diamagnetic Glasses

Verdet Constants and Dispersion of Commercial Diamagnetic Glasses¹

$$V = \frac{\pi}{\lambda} \frac{n^2(\lambda) - 1}{n(\lambda)} \left(A + \frac{B}{\lambda^2 - \lambda_0^2} \right)$$

Glass type ^a	n	V (633 nm) (rad/(m T))	λ_0 (nm)	A (10^{-7} rad/T)	B (10^{-19} m 2 rad/T)
FK 3	1.4630	4.1	95.3	7.2702	1.3333
FK 5	1.4860	4.7	92.3	7.3531	1.2647
FK 51	1.4853	3.5	84.7	5.4805	1.2695
FK 52	1.4848	3.2	86.2	4.1070	1.6842
PK 2	1.5165	4.7	96.4	7.1672	1.5350
BK 3	1.4967	4.4	96.1	6.8316	1.5282
BK 7	1.5151	4.9	97.0	5.5387	2.1116
BaLKN3	1.5167	5.2	100.0	5.9938	2.2601
K 3	1.5164	5.2	101.0	1.2978	3.8205
BaK 50	1.5657	5.8	102.6	7.2536	1.9887
SK 16	1.6182	5.5	101.2	5.5302	2.1438
SSK N 5	1.6557	5.8	110.6	8.3749	1.2103
LaKN12	1.6753	6.1	106.5	6.7875	1.8439
LaKN14	1.6941	4.9	106.5	6.4470	1.0542
LF 3	1.5793	8.4	120.4	9.4425	3.4867
F 2	1.6166	10.8	129.7	11.1061	4.0872
FN 11	1.6175	2.6	130.1	1.2158	1.2041
F 13	1.6188	10.8	130.4	10.6164	4.3176
LaSFN31	1.8762	5.5	125.4	7.0445	0.5728
LaSF 32	1.7981	2.6	143.9	0.9594	0.9845
SF 1	1.7124	15.4	144.7	13.4192	5.4231
SF 2	1.6438	11.6	134.6	7.0169	5.7546
SF 6	1.7988	20.1	156.4	15.7116	6.3430
SF 14	1.7561	15.1	152.8	12.3008	4.9536
SF 18	1.7165	15.7	145.2	12.2097	5.8514
SF 53	1.7232	15.1	146.7	11.0378	5.8444
SF 57	1.8396	21.8	161.7	16.7417	6.7168
SF 58	1.9091	27.1	170.5	18.2033	7.7697
SF 59	1.9432	28.5	175.3	22.6382	6.8410
SFN 64	1.7011	1.5	142.8	0.7433	37.1043
TiK 1	1.4770	4.7	100.8	9.1198	1.4464
TiF 3	1.5450	2.3	119.9	5.9402	0.0959
TiF 6	1.6125	2.3	140.6	0.9432	1.0387
KzFSN 4	1.6105	7.9	117.8	8.7691	2.8597
LgSK 2	1.5840	6.1	100.6	8.2800	1.7067

^aSchott glass designations. Similar glasses are available from other sources.

Verdet Constants V of Noncommercial Diamagnetic Glasses

Glass type	Composition (wt %)	V (rad/(m T), wavelength (nm))					Ref.
		442	633	700	853	1060	
B ₂ O ₃	100 B ₂ O ₃	—	3.77	—	—	—	2
Bi ₂ O ₃	95 Bi ₂ O ₃ , 5 B ₂ O ₃	—	—	25.0	14.8	9.6	3
PbO	95 PbO, 5 B ₂ O ₃	—	—	27.1	17.8	9.1	3
	82 PbO, 18 SiO ₂	—	—	22.3	13.1	7.9	3
	50 PbO, 15 K ₂ O, 35 SiO ₂	—	—	9.3	5.8	3.1	3
Tl ₂ O	95 Tl ₂ O, 5 B ₂ O ₃	—	—	26.7	17.8	9.3	3
	82 Tl ₂ O, 18 SiO ₂	—	—	29.1	19.5	12.6	3
	50 Tl ₂ O, 15 K ₂ O	—	—	10.5	6.5	3.5	3
SnO	76 SnO, 13 B ₂ O ₃ , 11 SiO ₂	—	—	20.6	13.4	7.5	3
CdO	47.5 CdO, 52.5 P ₂ O ₅	9.6	6.5	—	—	—	4
ZnO	36.4 ZnO, 63.6 P ₂ O ₅	12.7	5.8	—	—	—	4
TeO ₂	75 TeO ₂ , 25 Sb ₂ O ₃	—	—	22.2	15.2	9.3	3
	88.9 TeO ₂ , 11.1 P ₂ O ₅	57.1	22.2	—	—	6.5	3
	80 TeO ₂ , 20 ZnCl ₂	—	—	21.3	13.4	7.3	3
	84 TeO ₂ , 16 BaO	—	—	16.2	11.9	8.4	3
	70 TeO ₂ , 30 WO ₃	—	—	15.2	10.1	6.5	3
	20 TeO ₂ , 80 PbO	—	—	37.2	21.8	14.0	3
Sb ₂ O ₃	25 Sb ₂ O ₃ , 75 TeO ₂	—	—	22.2	15.2	9.3	3
	75 Sb ₂ O ₃ , 20 Cs ₂ O, 5 Al ₂ O ₃	—	—	21.5	12.7	7.3	3
	75 Sb ₂ O ₃ , 10 Cs ₂ O, 10 Rb ₂ O, 5 Al ₂ O ₃	—	—	22.7	15.2	8.7	3
ZrF ₄	63.1 ZrF ₄ , 14.9 BaF ₂ , 7.2LaF ₃ , 1.9 AlF ₃ , 9.1 PbF ₂ , 3.8 LiF	3.1	—	—	—	—	2

V (rad/(m T), wavelength (nm))

Chalcogenide glasses	500	633	700	1000	Ref.
As ₂ S ₃	—	0.28	0.21	0.081	5,6
As ₂₀ S ₈₀	0.22	0.12	0.093		6
As ₂ Se ₃	—	—	—	0.110	6
As ₄₀ S ₅₇ Se ₃	—	0.31	0.23		6
Ge ₂₀ As ₂₀ S ₆₀	—	0.20	0.155		6

Verdet Constants of SiO₂

$\lambda(\text{nm})$	V (rad/T m)	Ref.	$\lambda(\text{nm})$	V (rad/T m)	Ref.
254	29.8	7	500	7.2	8
410	11.0	8	578	4.35	9
436	7.68	9		4.40	11
	8.38	10	620	4.5	8
	8.12	11	633	3.67	11,12

Wavelength Dependence of Verdet Constants (300 K)

Glass type	V (rad/(m T))			
	435.8 nm	546.1 nm	632.8 nm	1060 nm
SF 59	69.8	37.2	25.9	8.1
SF 58	63.1	34.3	23.9	7.6
SF 57	52.4	28.8	20.1	6.7
SF 6	45.1	25.3	17.6	6.1
SF 1	34.9	19.8	13.7	4.9
SF 5	29.7	16.9	11.9	4.1
SF 2	27.1	15.4	11.1	3.8
F 2	24.2	13.7	9.9	3.5
BK 7	9.6	5.8	4.1	1.7

From Schott Optical Glass, Technical Information Optical Glass, Tl. No. 11.

Temperature Dependence of the Faraday Effect in Several Glasses^{13,14}

Glass	V (rad/(m T))	$\frac{1}{V_0} \frac{dV}{dT}$	$\frac{1}{(VL)_0} \frac{d(VL)}{dT}$	Experiment ($10^{-4}/\text{K}$)	α ($10^{-6}/\text{K}$)
		Theory ($10^{-4}/\text{K}$)	Experiment ($10^{-4}/\text{K}$)		
SF-57	21.8	1.29	1.26 ± 0.08	1.35 ± 0.08	9.2
SiO ₂	3.7	0.81	0.69 ± 0.03	0.69 ± 0.03	0.55
BK-7	4.9	0.56	0.63 ± 0.06	0.71 ± 0.06	8.3

Values for 633 nm.

References:

1. Faraday effect in optical glass—the wavelength dependence of the Verdet constant, *Tech. Information No. 17*, Schott Glaswerke, Postfach 2480, D-6500 Mainz, Germany.
2. Pye, L. D., Cherukuri, S. C., Mansfield, J., and Loretz, T., The Faraday rotation in some non-crystalline fluorides, *J. Non-Cryst. Solids*, 56, 99 (1983).
3. Borelli, N. F., Faraday rotation in glasses, *J. Chem. Phys.* 41, 3289 (1964).
4. Weber, M. J., Faraday Rotator Materials, Lawrence Livermore Laboratory Report M-103 (1982) and Faraday rotator materials for laser systems, *Proc. Soc. Photo Opt. Instrum. Eng.* 681, 75 (1986).
5. Robinson, C. C., The Faraday rotation of diamagnetic glasses from 0.334 μ to 1.9 μ , *Appl. Opt.* 3, 1163 (1964).
6. Qui, J., Kanbara, H., Nasu, H. and Hirao, K., *J. Ceram. Soc. Jpn.* 106, 228 (1998).

7. Dexter, J. L., Landry, J., Cooper, D. G., and Reintjes, J., *Opt. Commun.* 80, 115 (1990).
8. Khalilov, V. Kh., Malyshkin, S. F., Amosov, A. V., Kondratev, Yu. N., and Grigoreva, L. Z., Faraday effect in crystalline and vitreous SiO₂, *Opt. Spectrosc.* 38, 665 (1975).
9. Ramaseshan, S., Determination of the magneto-optic anomaly of some glasses, *Proc. Ind. Acad. Sci. A*, 24, 426 (1946).
10. Herlack, F., Knoepfel, H., Luppi, R., and Van Montfoort, J. E., *Proceedings of the Conference on Megagauss Magnetic Field Generation by Explosives and Related Experiments* (1965).
11. Garn, W. B., Caird, R. S., Fowler, C. M., and Thomson, D. B., Measurement of Faraday rotation in megagauss fields over the continuous visible spectrum, *Rev. Sci. Instrum.* 39, 1313 (1968).
12. George, N., Waniek, R. W., and Lee, S. W., Faraday effect at optical frequencies in strong magnetic fields, *Appl. Opt.* 4, 253 (1965).
13. Faraday effect in optical glass—the wavelength dependence of the Verdet constant, *Tech. Information No. 17*, Schott Glaswerke, Postfach 2480, D-6500 Mainz, Germany.
14. Williams, P.A., Rose, A. H., Day, G. W., Milner, T. E., and Deeter, M. N., Temperature dependence of the Verdet constant in several diamagnetic glasses, *Appl. Opt.* 30, 1176 (1991).

2.7.2 Paramagnetic Glasses

Verdet Constants V of Paramagnetic Glasses (295 K)

Rare earth ion	Ion conc. (10 ²¹ /cm ³)	V (rad/(m T), wavelength (nm))					Ref.
		400	500	633	700	1064	
Ce³⁺							
aluminoborate	8.33	—	—	-64	—	—	1
phosphate	6	-196 ^(a)	-94.9	-50.3 ^(b)	-38.4	—	2
silicophosphate	4.8	-169	—	39.9	—	-9.0	3
Pr³⁺							
aluminoborate	6.64	-178	—	—	—	—	3
borate	9.2	—	—	—	-59.1	-17.5	4
lanthanum borate	5.0	-111 ^(a)	-64.0	—	—	—	5
metaphosphate	3.32	—	-125 ^(c)	-39.6 ^(b)	—	-12.3	6
phosphate	5.3	-130	-76.0	-43.7 ^(b)	-35.8	—	1
silicate	3.79	—	—	—	-20.9	-7.9	4
Eu³⁺							
aluminoborate	4.1	-343	-86.7	-32.9 ^(d)	-26.5	—	7
Tb³⁺							
aluminosilicate	6.6	—	—	-73.6	—	-20.1	8
fluoroberyllate	2.92	—	-25.2 ^(c)	-10.7	—	-2.9	6
fluorophosphate	4.72	—	-52.4 ^(c)	-23.3	—	-5.4	6
lanthanum borate	5.5	-149 ^(a)	-83.8	-48.6 ^(b)	—	—	5
phosphate	5.4	-163 ^(a)	-94.0	-55.3 ^(b)	-43.6	—	2
Dy³⁺							
aluminoborate	8.6	-271	—	-70.1	—	—	3
borate	5.8	-127 ^(a)	-79.4	-46.3 ^(b)	—	—	5
phosphate	6.2	-157 ^(a)	-96.3	-57.3 ^(b)	-46.3	—	2
silicate	3.46	—	—	—	-19.5	-9.3	4

^(a) 405 nm, ^(b) 635 nm, ^(c) 442 nm, ^(d) 650 nm.

Verdet Constants of Commercial Paramagnetic Glasses (295 K)

Glass type	V (rad/(m T), wavelength (nm))					
	325	442	532	633	1064	Ref.
Hoya FR-4 (discontinued) (cerium phosphate)	—	-82.6	—	-30.5	-8.4	9
	-444	-174	—	-71.0	-20.6	9
Hoya FR-5 (terbium borosilicate)	—	-82.3	—	-34.9	-9.6	6
Hoya FR-7 (terbium fluorophosphate)	—	—	-74.8	—	-20.6	10
Kigre M-18 (terbium boroaluminosilicate)	—	—	-88.2	—	-26.1	10
Kigre M-24 (terbium boroaluminosilicate)	—	—	-98.4	—	-29.0	10
Kigre M-32 (terbium boroaluminosilicate)	-273	-98	—	-41.9	-11.9	6
Ownes-Illinois EY-1 (discontinued) (terbium silicate)	—	—	—	—	-11	6
Ownes-Illinois EY-2(discontinued) (terbium silicate)	—	—	—	—	—	6

References:

1. Asahara, Y. and Izumitani, T., *Proc. 1968 Meeting, Ceramic Assoc. of Jpn.* A10 (1968).
2. Berger, S. B., Rubenstein, C. B., Kurkjian, C. R., and Treptow, A. W., Faraday rotation of rare-earth (III) phosphate glasses, *Phys. Rev.* 133, A723 (1964).
3. Petrovskii, G. T., Edelman, I. S., Zarubina, T. V. et al., *J. Non-Cryst. Solids* 130, 35 (1991).
4. Borrelli, N. F., J. Faraday rotation in glasses, *Chem. Phys.* 41, 3289 (1964).
5. Rubenstein, C. B., Berger, S. B., Van Uitert, L. G., and Bonner, W. A., Faraday rotation of rare-earth (III) borate glasses, *J. Appl. Phys.* 35, 2338 (1964).
6. Weber, M. J., *Faraday Rotator Materials*, Lawrence Livermore Laboratory Report M-103 (1982) and Faraday rotator materials for laser systems, *Proc. Soc. Photo Opt. Instrum. Eng.* 681, 75 (1986).
7. Shafer, M. W., and Suits, J., Preparation and Faraday rotation of divalent europium glasses, *J. Am. Ceram. Soc.* 49, 261 (1966).
8. Ballato, J. and Snitzer, E., Fabrication of fibers with high rare-earth concentration for Faraday isolator applications, *Appl. Opt.* 34, 6848 (1995).
9. Data sheets, Hoya, Inc.
10. Data sheets, Kigre, Inc.

2.8 Electrooptic Properties

Electric-field-induced birefringence, the DC electrooptic Kerr effect, is given by

$$n = n_{||} - n_{\perp} = \lambda B E^2,$$

where λ is the wavelength in centimeters, E is the applied electric field strength in volts per centimeter, $n_{||}$ and n_{\perp} are the refractive indices in the directions parallel and perpendicular to the electric field, and B is the Kerr constant in centimeters per volt squared. In terms of the third-order nonlinear susceptibilities [in electrostatic units (esu)],

$$\chi_{\text{eff}}(-\omega, \omega, 0, 0) = \chi^{(3)}_{1111} - \chi^{(3)}_{1122} = (9\lambda B n / 24\pi) 10^4.$$

A positive electrooptic constant is obtained when the induced index change in the direction of the applied field is larger than the induced index change for the perpendicular direction. A negative sign for B implies that the major effect is a large decrease in the refractive index in the direction of the electric field.

DC Electrooptic Kerr Constants^{1,2}

		n_D	ϵ	$B(10^{-14} \text{ m/V}^2)$
Commercial glasses:				
Schott	SF 6	1.805	15.7	0.08
Schott	SF 57	1.847	16	0.11
Schott	SF 58	1.918	18	0.16
Schott	SF 59	1.962	23	0.30
Schott	LASF 7	1.850	19	-0.22
Corning	8310	-	-	0.07
Corning	8363	1.94	20	0.2
Corning	8391	-	-	0.06
Corning	8393	-	-	0.08
Corning	8427	-	-	0.09
Corning	8463	1.97	-	0.36
Arsenic trisulfide	As ₂ S ₃	2.48	-	8.7
Experimental glasses (mol %):				
40 SiO ₂ - 60 PbO		2.06	-	0.38
60 SiO ₂ - 40 Tl ₂ O		2.0	-	1.10
54 SiO ₂ - 41 Tl ₂ O - 5 PbO		-	-	0.96
76 SiO ₂ - 9 Tl ₂ O - 15 K ₂ O		-	-	0.30
73 SiO ₂ - 14 K ₂ O - 13 Ta ₂ O ₅		-	-	-0.57
85 TeO ₂ - 7.5 BaO - 7.5 ZnO		2.17	-	0.7
60 TeO ₂ - 20 BaO - 20 ZnO		2.02	-	0.5
36 TeO ₂ - 51 PbO - 12 SiO ₂		-	-	1.1
32 Tl ₂ O - 28 Bi ₂ O ₃ - 40 GeO ₂ -		-	1.15	

DC Electrooptic Kerr Constants^{1,2}—continued

	<i>n_D</i>	ϵ	<i>B(10⁻¹⁴ m/V²)</i>
57 PbO - 25 Bi ₂ O ₃ - 18 Ga ₂ O ₃	2.46	28.4	1.4
34 Nb ₂ O ₅ - 36 SiO ₂ - 30 Na ₂ O	—	—	2.80
70 PbO - 12 Ga ₂ O ₃ - 6 Tl ₂ O - 12 CdO	2.31	21	1.6
57 PbO - 18 Bi ₂ O ₃ - 18 Ga ₂ O ₃ - 7 Tl ₂ O	2.30	25.5	1.4
48 PbO - 14 Bi ₂ O ₃ - 10 Ga ₂ O ₃ - 14 Tl ₂ O - 14 CdO	2.27	23	1.4
43 SiO ₂ - 15.5 Li ₂ O - 11.5 K ₂ O - 4 Al ₂ O ₃ - 31 Ta ₂ O ₅	1.81	17.4	-0.8
20 SiO ₂ - 20 B ₂ O ₃ - 20 Na ₂ O - 20 Na ₂ O - 20 Nb ₂ O ₅ - 20 TiO ₂	1.93	15.3	-1.23
41 B ₂ O ₃ - 10 ZnO - 11 La ₂ O ₃ - 22 ThO ₂ - 5Ta ₂ O ₅ - 11 Nb ₂ O ₅	1.94	—	-0.18
23 PbO - 22 SiO ₂ - 11 MgO - 14 BaO - 16 TiO ₂ - 4 Al ₂ O ₃ - 8Nb ₂ O ₅	—	22	-0.4
46 PbO - 42 Bi ₂ O ₃ - 11 Ga ₂ O ₃ - 9 Tl ₂ O	2.46	29	1.4
46 PbO - 33 Bi ₂ O ₃ - 12 Ga ₂ O ₃ - 9 Tl ₂ O	2.31	26	1.2
71.6 PbO - 26.5 SiO ₂ - 0.5 Na ₂ O - 0.9 K ₂ O - 0.5 As ₂ S ₃	1.79	16	0.14
66.5 PbO - 28.1 SiO ₂ - 3.4 TiO ₂ - 0.5 Na ₂ O - 1.0 K ₂ O - 0.5 As ₂ S ₃	1.84	16	0
54.2 PbO - 32.0 SiO ₂ - 11.6 TiO ₂ - 0.6 Na ₂ O - 1.1 K ₂ O - 0.5 As ₂ S ₃	1.82	16	-0.22
71.6 PbO - 26.5 SiO ₂ - 3.4 TiO ₂ - 0.6 Na ₂ O - 1.2 K ₂ O - 0.5 As ₂ S ₃	1.86	16	0.25

Measured at 633 nm.

References:

1. Hall, D. W. and Borrelli, N. F., Nonlinear optical properties of glasses, *Optical Properties of Glass*, Kreidl, N. and Uhlmann, D. R., Eds., American Ceramic Society (1991), pp. 87–125.
2. Borrelli, N.F., Aitken, B.G., Newhouse, M.A., and Hall, D.W., Electric-field induced birefringence properties of high refractive under glasses exhibiting large Kerr nonlinearities, *J. Appl. Phys.* 70, 2774 (1991).

See, also, Borrelli, N.F., Electric field induced birefringence in glass, *Phys. Chem. Glass* 12, 9 (1971) and Paillette, M., Temperature dependent behavior of the Kerr constant in the vitreous state, *J. Non-Cryst. Solids* 91, 253 (1987).

2.9 Elastooptic Properties

The stress optic coefficients are defined as

$$K_p = dn_p/dP$$

and

$$K_s = dn_s/dP,$$

where the ordinary and extraordinary indices of refractive are designated n_s and n_p , respectively, according as the light polarization is perpendicular (s) or parallel (p) to the pressure vector. The elastooptic coefficients can be calculated from the experimentally determined values of the stress optic coefficients through the relations

$$p_{11} = 2E[2\mu K_s + (1 - \mu)K_p]/[n^3(2\mu - 1)(\mu + 1)]$$

and

$$p_{12} = 2E[\mu K_p + K_s]/[n^3(2\mu - 1)(\mu + 1)],$$

where E is the elastic modulus and μ is Poisson's ratio.

The elastooptic coefficients for several representative glasses are given below.

Glass	Wavelength (μm)	Elastooptic Coefficients			Ref.
		p_{11}	p_{12}	p_{44}	
fused silica (SiO_2)	0.633	0.121	0.270	-0.075	1
tellurite glass	0.633	0.257	0.241	0.0079	2
As_2S_3	1.15	0.308	0.299	0.0045	1
$\text{Ge}_{33}\text{Se}_{55}\text{As}_{12}$	1.06	0.21	0.21	—	1
LaSF	0.633	0.088	0.147	-0.030	3
SF4	0.633	0.215	0.243	-0.014	3
TaFd7	0.633	0.099	0.138	-0.020	3

1. Pinnow, D. A., Elasto-optical materials, *CRC Handbook of Lasers*, Pressley, R. J., Ed. (The Chemical Rubber Co., Cleveland, OH, 1971).
2. Yano, T., Fukomoto, A., and Watanabe, A., Tellurite glass: a new acousto-optic material, *J. Appl. Phys.* 42, 3671 (1971).
3. Eschler, H. and Weidinger, F., *J. Appl. Phys.*, 46, 65 (1975).

Two acoustooptic figures of merit, M_1 and M_2 , are:

$$M_{1i} = n^7 p_{1i}/\rho v_i$$

and

$$M_{2i} = n^6 p_{1i}/\rho v_i^3.$$

A compilation of these properties for most of the optical glasses carried in the Schott Optical Glass Catalog is given in Modification of the refractive index of optical glass by tensile and compressive stresses, *Schott Technical Information TI No. 20*, 4/88 and in Gottlieb, M. and Singh, N. B., Elastooptic materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 415.

Elastooptic Properties of Schott Glasses

Glass type	$-K_p^a$	$-K_s^a$	P_{11}	P_{12}	M_{11}^b	M_{12b}	M_{21}^c	M_{22}^c
FK 3	1.0	4.9	0.15	0.24	3	7	1	2
FK 5	0.9	3.8	0.14	0.23	2	6	1	1
FK 51	1.1	1.8	0.17	0.20	2	3	1	1
FK 52	1.1	1.8	0.16	0.19	2	3	1	1
FK 54	0.8	1.6	0.14	0.17	1	2	0	0
PK 1	0.8	3.9	0.14	0.25	2	7	0	1
PK 2	0.4	3.1	0.11	0.22	1	6	0	1
PK 3	0.5	3.1	0.11	0.21	2	6	0	1
PK 50	1.2	3.4	0.14	0.21	3	6	1	1
PK 51A	1.4	1.9	0.16	0.18	3	3	1	1
PSK 2	0.6	2.9	0.13	0.21	2	6	0	1
PSK 3	0.8	3.3	0.14	0.23	3	7	0	1
PSK 50	1.2	3.1	0.16	0.21	3	6	1	1
PSK 52	1.0	2.4	0.14	0.18	3	5	1	1
PSK 53A	1.5	2.6	0.17	0.20	5	6	1	1
BK 1	0.6	3.4	0.12	0.21	2	6	0	1
BK 3	0.5	3.8	0.12	0.24	2	7	0	1
BK 6	0.4	2.9	0.11	0.20	1	5	0	1
BK 7	0.5	3.3	0.12	0.22	2	6	0	1
UBK 7	0.5	3.3	0.12	0.23	2	6	0	1
BK 8	0.4	3.1	0.11	0.21	1	5	0	1
BK 10	0.7	3.9	0.13	0.24	2	7	0	1
BaLK 1	1.4	4.1	0.17	0.26	4	9	1	2
BaLK N3	0.7	4.0	0.13	0.24	2	8	0	2
K 3	1.2	4.1	0.16	0.26	3	9	1	2
K 4	0.8	3.5	0.12	0.21	2	6	0	1
K 5	0.6	3.7	0.13	0.23	2	7	0	1
K 7	0.7	3.8	0.12	0.23	2	7	0	1
K 10	1.4	4.6	0.15	0.26	3	8	1	2
K 11	1.1	4.1	0.14	0.24	2	7	1	2
K 50	0.5	3.7	0.12	0.23	2	7	0	1
UK 50	0.5	3.8	0.13	0.24	2	7	0	1
K 51	1.0	4.6	0.15	0.27	3	9	1	2
ZK 1	0.3	4.0	0.13	0.24	2	8	0	2
ZK 5	0.3	3.8	0.12	0.22	2	7	0	2

Elastooptic Properties of Schott Glasses—*continued*

Glass type	$-K_p^a$	$-K_s^a$	P_{11}	P_{12}	M_{11}^b	M_{12b}	M_{21}^c	M_{22}^c
ZK N7	0.3	3.8	0.11	0.23	2	7	0	1
BaK 1	0.7	3.2	0.13	0.20	2	6	1	1
BaK 2	1.0	3.6	0.14	0.22	3	7	1	2
BaK 4	0.5	3.2	0.12	0.21	2	6	0	1
BaK 5	0.9	3.6	0.15	0.23	3	7	1	2
BaK 6	0.8	3.2	0.14	0.21	3	6	1	1
BaK 50	0.0	3.0	0.11	0.21	2	6	0	1
SK 1	0.7	3.0	0.13	0.20	3	6	1	1
SK 2	0.8	3.0	0.14	0.20	3	6	1	1
SK 3	0.7	2.6	0.12	0.18	2	5	0	1
SK 4	0.6	2.5	0.12	0.18	2	5	0	1
SK 5	0.8	2.8	0.14	0.21	3	6	1	1
SK 6	0.7	3.0	0.14	0.20	3	6	1	1
SK 7	0.8	2.6	0.13	0.19	3	5	1	1
SK 8	0.8	3.1	0.14	0.21	3	7	1	2
SK 9	0.8	3.1	0.14	0.21	3	7	1	2
SK 10	0.8	2.6	0.13	0.19	3	5	1	1
SK 11	0.7	3.2	0.13	0.22	2	6	0	1
SK 12	0.5	2.8	0.11	0.19	2	5	0	1
SK 13	0.9	3.2	0.15	0.22	3	7	1	2
SK 14	0.8	2.6	0.13	0.19	3	5	1	1
SK 15	0.8	2.7	0.14	0.20	3	6	1	1
SK 16	1.0	2.8	0.16	0.22	4	7	1	1
SK N18	0.5	2.4	0.13	0.19	3	6	1	1
SK 19	1.0	2.8	0.14	0.20	3	6	1	1
SK 20	0.6	3.0	0.12	0.20	2	5	0	1
SK 51	1.1	2.7	0.15	0.20	4	6	1	1
SK 52	0.0	2.3	0.10	0.18	2	5	0	1
SK 55	0.2	2.2	0.10	0.17	1	4	0	1
KF 1	1.3	4.3	0.16	0.25	3	9	1	2
KF 3	0.8	3.8	0.13	0.22	2	6	0	1
KF 6	1.2	4.1	0.14	0.23	2	7	1	2
KF 9	1.4	4.5	0.16	0.25	3	9	1	2
KF 50	1.1	4.3	0.14	0.23	3	8	1	2
BaLF 3	0.8	3.9	0.15	0.24	3	8	1	2

Elastooptic Properties of Schott Glasses—*continued*

Glass type	$-K_p^a$	$-K_s^a$	P_{11}	P_{12}	M_{11}^b	M_{12b}	M_{21}^c	M_{22}^c
BaLF 4	0.2	3.3	0.11	0.20	2	6	0	1
BaLF 5	0.9	4.0	0.14	0.23	3	7	1	2
BaLF 6	0.4	3.1	0.11	0.19	2	6	0	1
BaLF 8	0.8	3.7	0.12	0.21	2	6	1	2
BaLF 50	0.6	2.9	0.12	0.19	2	5	0	1
BaLF 51	0.9	3.3	0.13	0.21	3	6	1	1
SSK 1	0.9	3.1	0.14	0.21	3	7	1	2
SSK 2	1.2	3.4	0.16	0.22	4	8	1	2
SSK 3	0.9	3.2	0.14	0.20	3	6	1	2
SSK 4	0.8	2.9	0.13	0.20	3	6	1	1
SSK N5	0.5	2.3	0.11	0.17	2	5	0	1
SSK N8	0.7	3.1	0.13	0.21	3	7	1	1
SSK 50	0.9	2.7	0.14	0.19	3	6	1	1
SSK 51	1.1	3.3	0.16	0.23	4	8	1	2
SSK 52	—	—	—	—	—	—	—	—
LaK N6	1.0	2.6	0.15	0.20	3	6	1	1
LaK .N7	0.6	2.1	0.11	0.16	2	4	0	1
LaK 8	0.1	1.9	0.10	0.16	2	5	0	1
LaK 9	0.3	2.0	0.11	0.17	2	5	0	1
LaK 10	0.1	2.0	0.10	0.16	2	5	0	1
LaK 11	0.5	2.3	0.12	0.17	2	5	0	1
LaK N12	0.8	2.3	0.13	0.17	3	5	1	1
LaK L12	0.0	1.6	0.07	0.13	1	3	0	0
LaK N13	1.2	2.5	0.15	0.19	4	6	1	1
LaK N14	0.2	2.0	0.10	0.17	2	5	0	1
LaK 16A	−0.1	1.8	0.08	0.15	1	4	0	1
LaK 21	1.0	2.8	0.16	0.22	4	7	1	1
LaK L21	0.0	2.0	0.09	0.17	1	5	0	1
LaK N22	0.7	2.5	0.13	0.18	3	5	1	1
LaK 23	0.7	2.2	0.12	0.16	2	4	1	1
LaK 28	0.2	2.0	0.11	0.17	2	6	0	1
LaK 31	0.1	1.7	0.09	0.15	1	4	0	1
LaK 33	0.3	1.7	0.10	0.15	2	5	0	1
LLF 1	1.7	4.7	0.15	0.23	3	8	1	2
LLF 2	1.6	4.6	0.15	0.23	3	8	1	2

Elastooptic Properties of Schott Glasses—*continued*

Glass type	$-K_p^a$	$-K_s^a$	P_{11}	P_{12}	M_{11}^b	M_{12b}	M_{21}^c	M_{22}^c
LLF 3	1.4	4.2	0.15	0.23	3	8	1	2
LLF 4	1.5	4.5	0.15	0.24	4	9	1	2
LLF 6	1.5	4.7	0.15	0.25	3	8	1	2
LLF 7	1.5	4.6	0.14	0.23	3	8	1	2
BaF 3	0.8	3.8	0.12	0.20	2	6	1	2
BaF 4	1.3	3.9	0.14	0.21	3	7	1	2
BaF 5	1.3	4.0	0.17	0.24	4	9	1	2
BaF N6	1.3	3.8	0.16	0.24	4	9	1	2
BaF 8	0.8	3.1	0.12	0.19	3	6	1	1
BaF 9	0.8	2.9	0.13	0.19	3	6	1	1
BaF N10	0.7	2.7	0.14	0.20	3	7	1	1
BaF N11	0.4	2.3	0.11	0.16	2	5	0	1
BaF 12	0.7	2.9	0.12	0.19	3	6	1	1
BaF 13	1.1	2.9	0.15	0.20	4	7	1	2
BaF 50	0.9	2.7	0.14	0.19	3	7	1	1
BaF 51	0.2	2.4	0.09	0.16	2	5	0	1
BaF 52	0.8	3.1	0.12	0.19	3	6	1	1
BaF 53	0.3	2.5	0.10	0.17	2	5	0	1
BaF 54	0.5	2.3	0.11	0.16	2	5	0	1
LF 1	1.9	4.9	0.17	0.24	4	9	1	3
LF 2	1.9	4.6	0.16	0.23	4	9	1	3
LF 3	1.8	4.6	0.16	0.23	4	9	1	3
LF 4	1.5	4.6	0.14	0.22	3	8	1	2
LF 5	2.3	5.2	0.18	0.25	6	11	2	3
LF 6	1.9	4.8	0.16	0.23	4	9	1	3
LF 7	2.2	5.3	0.18	0.25	5	10	2	3
LF 8	2.1	5.1	0.18	0.25	5	10	1	3
F 1	2.7	5.4	0.18	0.23	6	11	2	4
F 2	2.4	5.2	0.17	0.23	5	10	2	3
F 3	2.3	5.2	0.17	0.23	5	10	2	3
F 4	2.3	5.2	0.16	0.22	5	9	2	3
F 5	2.0	4.9	0.15	0.22	4	9	1	3
F 6	2.6	5.1	0.17	0.22	6	10	2	3
F 7	2.7	5.6	0.19	0.25	7	12	2	4
F 8	1.8	4.9	0.16	0.23	4	9	1	3

Elastooptic Properties of Schott Glasses—*continued*

Glass type	$-K_p^a$	$-K_s^a$	P_{11}	P_{12}	M_{11}^b	M_{12b}	M_{21}^c	M_{22}^c
F 9	2.0	4.7	0.16	0.23	5	9	1	3
F N11	0.3	3.4	0.10	0.20	2	7	0	1
F 13	2.9	5.8	0.19	0.25	7	12	2	4
F 14	1.9	4.9	0.15	0.22	4	9	1	3
F 15	2.4	5.3	0.17	0.24	5	10	2	3
BaSF 1	1.4	4.1	0.14	0.20	3	7	1	2
BaSF 2	1.7	4.1	0.15	0.20	4	8	1	3
BaSF 5	1.8	4.2	0.15	0.21	4	8	1	2
BaSF 6	1.2	3.2	0.15	0.20	4	8	1	2
BaSF 10	1.6	3.8	0.15	0.21	4	8	1	2
BaSF 12	1.4	3.5	0.15	0.20	4	8	1	2
BaSF 13	1.1	2.9	0.13	0.18	4	7	1	2
BaSF 14	1.8	3.8	0.17	0.22	6	10	2	3
BaSF 50	0.9	3.1	0.13	0.19	4	7	1	2
BaSF 51	0.6	2.8	0.12	0.17	3	6	1	1
BaSF 52	0.3	2.6	0.11	0.17	2	6	0	1
BaSF 54	2.5	3.9	0.18	0.21	8	11	2	3
BaSF 55	1.3	3.5	0.15	0.20	5	8	1	2
BaSF 56	1.9	4.3	0.17	0.22	5	10	2	3
BaSF 57	1.2	3.2	0.14	0.19	3	7	1	2
BaSF 64	−0.1	2.4	0.09	0.17	1	6	0	1
LaF 2	0.7	2.2	0.11	0.15	3	5	1	1
LaF 3	0.6	2.1	0.11	0.15	2	5	0	1
LaF N7	1.2	2.9	0.13	0.17	4	7	1	2
LaF N8	0.2	2.2	0.10	0.16	2	5	0	1
LaF 9	3.5	4.3	0.19	0.21	11	13	4	4
LaF N10	0.2	1.9	0.10	0.15	2	5	0	1
LaF 11A	2.6	4.1	0.18	0.21	8	11	2	3
LaF 13	1.2	2.6	0.15	0.18	5	8	1	2
LaF 20	0.8	2.6	0.14	0.19	3	7	1	1
LaF N21	0.1	1.4	0.07	0.12	1	3	0	0
LaF 22A	0.5	2.0	0.09	0.14	2	4	0	1
LaF N23	1.2	2.8	0.15	0.19	4	7	1	2
LaF N24	−0.2	1.6	0.06	0.13	1	3	0	0
LaF 25	−0.5	1.6	0.05	0.11	0	3	0	0

Elastooptic Properties of Schott Glasses—*continued*

Glass type	$-K_p^a$	$-K_s^a$	P_{11}	P_{12}	M_{11}^b	M_{12b}	M_{21}^c	M_{22}^c
LaF 26	0.1	2.1	0.09	0.14	2	4	0	1
LaF N28	0.1	1.4	0.07	0.12	1	3	0	0
LaSF 3	0.0	1.8	0.08	0.14	2	5	0	1
LaSF 8	2.0	3.5	0.17	0.21	8	12	2	3
LaSF N9	0.3	2.1	0.09	0.14	2	6	0	1
LaSF N15	0.3	1.5	0.08	0.11	2	4	0	1
LaSF N18	0.3	1.6	0.08	0.11	2	4	0	1
LaSF N30	0.3	1.7	0.10	0.14	2	5	0	1
LaSF N31	0.6	1.7	0.10	0.14	3	5	1	1
LaSF 32	−0.1	2.3	0.07	0.14	1	6	0	1
LaSF 33	0.7	2.5	0.11	0.16	3	7	1	1
SF 1	4.5	6.2	0.22	0.25	12	16	5	6
SF 2	3.3	5.9	0.19	0.25	8	13	3	5
SF 3	4.4	6.0	0.20	0.23	11	15	5	6
SF 4	4.6	5.9	0.20	0.23	12	15	5	6
SF 5	3.1	5.4	0.18	0.22	7	11	3	4
SF 6	6.0	6.8	0.24	0.25	19	21	8	9
SF L6	0.2	3.0	0.09	0.16	3	8	0	1
SF 7	2.7	5.5	0.17	0.23	6	11	2	4
SF 8	3.6	5.9	0.19	0.24	9	13	3	5
SF 9	3.2	5.8	0.20	0.25	8	13	3	5
SF 10	3.6	5.6	0.20	0.24	10	15	3	5
SF 11	3.8	5.0	0.19	0.21	10	13	4	5
SF 12	2.8	5.3	0.18	0.24	7	12	2	4
SF 13	3.3	5.2	0.18	0.22	9	13	3	4
SF 14	3.8	5.4	0.20	0.23	11	15	4	5
SF 15	3.0	5.1	0.18	0.22	7	11	3	4
SF 16	3.3	6.0	0.20	0.25	8	13	3	5
SF 17	3.3	6.1	0.20	0.25	8	13	3	5
SF 18	4.1	5.9	0.20	0.23	11	14	4	6
SF 19	3.1	5.5	0.18	0.23	7	12	3	4
SF 50	—	—	—	—	—	—	—	—
SF 51	2.3	4.7	0.16	0.21	5	9	2	3
SF 52	3.5	5.7	0.20	0.24	9	14	3	5
SF 53	3.8	5.4	0.19	0.22	10	13	4	5

Elastooptic Properties of Schott Glasses—*continued*

Glass type	$-K_p^a$	$-K_s^a$	P_{11}	P_{12}	M_{11}^b	M_{12b}	M_{21}^c	M_{22}^c
SF 54	4.7	6.4	0.22	0.26	14	18	5	7
SF 55	4.3	5.7	0.20	0.22	11	14	5	6
SF 56	4.8	5.8	0.21	0.22	13	16	5	6
SF L56	0.0	2.8	0.07	0.15	2	6	0	1
SF 57	6.7	6.7	0.23	0.23	20	20	9	9
SF 58	8.2	7.2	0.24	0.23	29	26	14	13
SF 59	9.0	7.6	0.25	0.24	34	30	17	15
SF 61	4.5	6.0	0.21	0.23	12	15	5	6
SF 62	3.5	5.8	0.19	0.24	8	13	3	5
SF 63	4.2	5.8	0.20	0.22	11	14	4	6
SF N64	0.2	3.1	0.10	0.18	2	8	0	1
TiK 1	2.3	6.1	0.19	0.27	5	10	2	3
TiF 1	1.1	4.2	0.15	0.23	3	7	1	2
TiF 2	1.1	4.5	0.15	0.25	4	9	1	2
TiF 3	1.1	4.4	0.15	0.24	4	9	1	2
TiF 4	0.9	4.2	0.14	0.23	3	9	1	2
TiF N5	0.6	3.9	0.12	0.21	3	8	1	2
TiF 6	0.7	3.0	0.11	0.16	2	5	0	1
KzF N1	1.0	4.2	0.13	0.21	3	7	1	2
KzF N2	1.3	5.0	0.14	0.24	3	9	1	2
KzF 6	1.7	5.8	0.16	0.26	4	10	1	3
KzFS1	1.0	4.2	0.15	0.21	4	8	1	2
KzFS N2	0.1	3.8	0.12	0.23	2	8	0	2
KzFS N4	0.6	3.8	0.13	0.20	3	7	1	2
KzFS N5	0.7	3.4	0.12	0.18	3	7	1	2
KzFS 6	0.6	4.0	0.14	0.22	3	8	1	2
KzFS N7	0.6	3.1	0.12	0.18	3	7	1	1
KzFS 8	1.5	3.7	0.15	0.20	5	9	1	2
KzFS N9	0.4	3.5	0.12	0.20	2	7	1	2
LgSK 2	1.1	2.2	0.15	0.18	3	4	1	1

^a 10^{-6} mm²/N; ^b 10^{-7} cm² s/g; ^c 10^{-18} s³/g.

2.10 Nonlinear Optical Properties

2.10.1 Nonlinear Refractive Index*

Nonlinear refraction is commonly defined either in terms of the optical field intensity I

$$n = n_0 + \gamma I$$

or in terms of the average of the square of the optical electric field $\langle E^2 \rangle$

$$n = n_0 + n_2 \langle E^2 \rangle,$$

where n_0 is the ordinary linear refractive index, γ is the nonlinear refractive coefficient, and n_2 is the nonlinear refractive index. The conversion between n_2 and γ is given by

$$n_2 [\text{cm}^3/\text{erg}] = (cn_0/40\pi) \gamma [\text{m}^2/\text{W}] = 238.7 n_0 \gamma [\text{cm}^2/\text{W}],$$

where c is the speed(in m/s) of light in vacuum. In terms of third-order susceptibility tensor $\chi^{(3)}(-\omega, \omega, \omega, -\omega)$ of a medium, the nonlinear refractive indices for a linearly polarized wave and for a circularly polarized wave in an isotropic material are

$$n_2(\text{LP}) = (12\pi/n_0) \chi^{(3)}_{1111}(-\omega, \omega, \omega, -\omega)$$

and

$$n_2(\text{CP}) = (24\pi/n_0) \chi^{(3)}_{1122}(-\omega, \omega, \omega, -\omega).$$

The two-photon absorption coefficient β is proportional to the corresponding imaginary part of $\chi^{(3)}(-\omega, \omega, \omega, -\omega)$. The relationship between n_2 , β , and $\chi^{(3)}$ is analogous to the relationship between n_0 , the linear absorption coefficient α , and the linear susceptibility χ .

The nonlinear refractive index is not a unique quantity for a given material because a number of physical mechanisms contribute to the polarization that is cubic in the applied optical electric field. The mechanisms that contribute most strongly to n_2 , and their characteristic time scales (in parentheses) are bound electrons (10^{-15} s), optically created free carriers ($>10^{-12}$ s), Raman-active optical phonons (10^{-12} s), electrostriction ($>10^{-9}$ s), and thermal excitation ($\sim 10^{-9}$ s).

Several methods listed below have been employed to measure n_2 . The details of the measurements determine the relative contributions from the various possible physical mechanisms to the measured n_2 . In general, experiments done with picosecond pulses and nondegenerate mixing are less likely to be affected by the “slow” electrostrictive or thermal effects than those done in the nanosecond pulse regime and with degenerate mixing. Most of the measurements include the effects of both electronic and vibrational (Raman) contributions to n_2 .


In the following tables values of the parameters in parentheses were calculated by Chase and Van Stryland¹ from the quantities reported in the original references. Refractive indices in parentheses were obtained from extrapolation of available data. For noncubic crystals, or for cubic crystals where the polarization is not along a cube axis or is not specified in the original reference, the value tabulated for $\chi^{(3)}_{1111}$ is an effective value of $\chi^{(3)}$.

* This section was adapted from Chase, L. L., and Van Stryland, E. W., Nonlinear refractive index: inorganic materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 269.

Techniques for Measuring the Nonlinear Refractive Index

Method		Ref.
DFWM	Degenerate four-wave mixing	2
DTLC	Damage threshold for linear vs. circular polarization	3
ER	Ellipse rotation	4
NDFWM	Non-degenerate four-wave mixing	5, 6
OKE	Optical Kerr effect	7
PDF	Power-dependent focus	8
RSS	Raman scattering spectroscopy	9
SPM	Self-phase modulation	10
SSMG	Small-scale modulation growth	11
TII	Time-integrated interferometry	12
TRI	Time-resolved interferometry	13
TWM	Three-wave mixing	5
TWR	Temporal waveform reshaping	14

Boling, Glass, and Owyong¹⁵ derived an empirical formula relating n_2 at wavelengths much longer than the interband absorption to the linear refractive index and its dispersion. This formula for estimating n_2 is accurate to within about 25% for a wide range of crystals and glasses.^{6,16} The equation is generally not applicable to chalcogenide glasses. Lines of constant n_2 predicted from this equation are plotted as a function of n_d and v_d in the figure below and are superimposed on regions of known oxide and fluoride glasses.



Measured Nonlinear Refractive Parameters of Glasses

Glass	Method	Pulse length (ns)	Wavelength (nm)	Refractive index	χ_{1111} ($10^{-13} \text{ cm}^3\text{erg}$)	$n_2 \text{ LP}$ ($10^{-13} \text{ cm}^3\text{erg}$)	$\gamma \text{ LP}$ ($10^{-16} \text{ cm}^2/\text{W}$)	Ref.
Aluminate L-65	NDFWM	3	1064	(1.6637)	(.116)	2.64	(6.6)	16
Beryllium fluoride	TRI	0.15	1064	1.28	(0.0078)	0.26	(0.75)	17
Borate L-109	NDFWM	3	1064	(1.606)	(0.080)	1.88	(4.9)	16
Borosilicate BK-7	NDFWM	3	1064	(1.5168)	(0.052)	1.30	(3.59)	16
Borosilicate 517	DTLC	20	1064	1.51	(1.150)	1.24	(3.44)	3 ^a
Borosilicate BK-7	ER	20	694	1.52	(0.056)	1.4	(3.86)	19 ^b
Borosilicate BK-7	TRI	0.125	1064	1.52	(0.050)	1.24	3.43	13
Borosilicate BK-10	TRI	0.17	355	1.50	(0.024)	0.6	1.7	20
Borosilicate BSC	TWM	3	560,590	1.51	(0.092)	2.3	(6.4)	5
Borosilicate BSC-2	TWR	12.	694	(1.50)	(0.080)	2.0	(5.6)	21
Flint SF-55	DTLC	20	1064	1.73	(0.38)	8.3	(20.)	3
Fluoroberyllate:Nd	TRI	0.15	1064	1.34	(0.012)	0.33	(1.0)	17
Fluorophosphate E-115	NDFWM	3	1064	(1.4899)	(0.032)	0.80	(2.25)	16
Fluorophosphate E-131	NDFWM	3	1064	(1.4372)	(0.023)	0.61	(1.78)	16
Fluorophosphate E-132	NDFWM	3	1064	(1.4423)	(0.027)	0.70	(2.03)	16
Fluorophosphate E-133	NDFWM	3	1064	(1.4511)	(0.026)	0.68	(1.96)	16
Fluorophosphate K-1172	NDFWM	3	1064	(1.4364)	(0.025)	0.65	(1.90)	16
Fluorophosphate A86-82	TRI	0.125	1064	1.49	(0.028)	0.71	2.0	21
Fluorophosphate FK-51	TRI	0.125	1064	1.49	(0.027)	0.69	1.94	13
Fluorosilicate FC-5	TRI	0.125	1064	1.49	(0.042)	1.07	3.01	13
Fluorozirconate 9028	NDFWM	3	1064	(1.5314)	(0.049)	1.21	(3.31)	16
Gallate "RN"	DFWM	0.09	1064	2.48	4.2	(227)	(383)	22
Germanate Q-5	DFWM	0.09	1064	2.30	0.8	(15.7)	(29)	22
Germanate VIR-3	DFWM	0.09	1064	1.84	0.48	(9.66)	(22)	77

Measured Nonlinear Refractive Parameters of Glasses—*continued*

Glass	Method	Pulse length (ns)	Wavelength (nm)	Refractive Index	χ_{1111} ($10^{-13} \text{ cm}^3/\text{erg}$)	$n_2 \text{LP}$ ($10^{-13} \text{ cm}^3/\text{erg}$)	γ_{LP} ($10^{-16} \text{ cm}^2/\text{W}$)	Ref.
Phosphate:Ce FR-4	TRI	0.15	1064	(1.56)	(0.081)	1.95	(5.2)	23
Phosphate EV-1	TRI	0.125	1064	1.51	(0.036)	0.91	2.53	24
Phosphate LHG-5	NDFWM	3	1064	(1.51)	(0.058)	1.44	(4.0)	16
Phosphate:Nd LHG-5	TRI	0.125	1064	1.54	(0.047)	1.16	3.15	24
Phosphate LHG-6	NDFWM	3	1064	(1.53)	(0.045)	1.12	(3.07)	19
Phosphate:Nd LHG-6	TRI	0.125	1064	1.53	(0.040)	1.01	2.76	24
Phosphate:Nd LHG-5	PDF	0.030	1064	1.54	(0.061)	1.5	(4.1)	25
Phosphate:Nd LHG-6	PDF	0.030	1064	1.53	(0.061)	1.5	(4.1)	25
Phosphate Q-88	NDFWM	3	1064	(1.5449)	(0.052)	1.27	(3.44)	16
Phosphate P-108	NDFWM	3	1064	(1.5312)	(0.052)	1.28	(3.50)	16
Phosphate 5037	NDFWM	3	1064	(1.5772)	(0.065)	1.56	(4.14)	16
Phosphate 5038	NDFWM	3	1064	(1.5915)	(0.072)	1.71	(4.50)	16
Silica (Dynasil 4000)	TRI	0.125	1064	1.46	(0.037)	0.95	2.73	13
Silica (fiber)	SPM	~0.15	514	(1.47)	(0.044)	1.14	(3.2)	10
Silica (Suprasil II)	TRI	0.17	355	1.50	(0.036)	0.9	2.5	20
Silica (Suprasil II)	SSMG	1.1	351	1.50	(0.024)	0.6	1.7	11
Silica, SiO ₂	NDFWM	3	1064	(1.46)	(0.033)	0.85	(2.44)	16
Silica, SiO ₂	OKE	10^{-4}	620	1.4519	0.024	0.62	(1.80)	26
Silica, SiO ₂	TII	20	1064	(1.46)	0.044	(1.1)	(3.3)	27
Silica, SiO ₂	TII/SPM/SS	0.004	249	(1.508)	(0.06–0.08)	1.5–2.0	(4.2–5.6)	28
Silica, SiO ₂	PDF	0.17	308	(1.489)	(0.042)	(1.07)	3.0	29
Silica, SiO ₂	ER	13	694	1.45	(0.039)	1.00	(2.88)	4
Silica, SiO ₂	NDFWM	3	560,590	1.46	(0.070)	1.8	(5.2)	5
Silica, SiO ₂	DTLC	20	1064	1.45	(0.036)	0.93	(2.7)	3 ^a

Silicate (Si-Nb-Ti-Na)	DFWM	0.08	1064	1.56–1.95	(0.072–0.97)	1.75–18.8	(4.7–40)	30
Silicate 8463	DFWM	0.09	1064	1.94	1.0	(19.4)	(42)	22
Silicate C835	TRI	~1	1064	1.50	(0.073)	1.83	(5.1)	31
Silicate C1020	TRI	~1	1064	1.50	(0.073)	1.83	(5.1)	31
Silicate C1020	RSS		647	1.51	(0.060)	1.5	(4.2)	9c
Silicate C-2828	NDFWM	3	1064	(1.5418)	(0.063)	1.54	(4.18)	16
Silicate C2828	TRI	~1	1064	1.53	(0.084)	2.08	(5.7)	31
Silicate E-0525	OKE	10 ⁻⁴	620	1.8050	0.48	(10.0)	(23.)	26
Silicate E-1	DFWM	0.08	1064	1.93	(1.16)	(22.6)	49	2
Silicate ED-2	NDFWM	3	1064	(1.57)	(0.066)	1.58	(4.22)	16
Silicate ED-2	TRI	~1	1064	(1.57)	(0.064)	1.53	(4.1)	31
Silicate ED-2	TRI	0.125	1064	1.57	(0.059)	1.41	3.77	21
Silicate ED-2:Nd	TRI	0.125	1064	1.57	(0.059)	1.41	3.77	13
Silicate ED-2:Nd	RSS		647	(1.57)	(0.075)	1.8	(4.8)	9c
Silicate ED-2:Nd	TRI	0.15	1064	(1.57)	(0.063)	1.52	(4.1)	23
Silicate ED-3	NDFWM	3	1064	(1.5714)	(0.064)	1.53	(4.08)	16
Silicate ED-4	NDFWM	3	560,590	1.55	(0.011)	2.6	(7.0)	5
Silicate ED-4	PDF	0.030	1064	1.55	(0.086)	2.1	(5.7)	25
Silicate ED-4	ER	13	694	1.56	(0.072)	1.73	(4.6)	4
Silicate ED-8	NDFWM	3	1064	(1.6008)	(0.072)	1.69	(4.42)	16
Silicate EY-1	ER	13	694	1.61	(0.088)	2.06	(5.4)	32
Silicate EY-1	TRI	0.15	1064	(1.61)	(0.076)	1.77	(4.6)	3
Silicate FD-6	DFWM	0.08	1064	1.77	(0.61)	(13.1)	31	2
Silicate FD-60	DFWM	0.08	1064	1.77	(0.39)	(8.4)	20	2
Silicate FD-60	OKE	10 ⁻⁴	620	1.8052	0.42	(8.77)	(20)	26
Silicate FDS-9	DFWM	0.08	1064	1.81	(0.46)	(9.5)	22	2
Silicate FR-5	NDFWM	3	1064			1.93		16
Silicate GLS-1	PDF	~1	1064			1.16		34

Measured Nonlinear Refractive Parameters of Glasses—*continued*

Glass	Method	Pulse length (ns)	Wavelength (nm)	Refractive index	χ_{1111} ($10^{-13} \text{ cm}^3/\text{erg}$)	$n_2 \text{ LP}$ ($10^{-13} \text{ cm}^3/\text{erg}$)	$\gamma \text{ LP}$ ($10^{-16} \text{ cm}^2/\text{W}$)	Ref.
Silicate La SF30	OKE	10^{-4}	620	1.8032	0.12	(2.51)	(5.83)	26
Silicate LG-650	NDFWM	3	1064	(1.5214)	(0.058)	1.44	(3.96)	16
Silicate K-8	TII	10	694		1.5			35
Silicate KGSS-1621	PDF	~1	1064			1.07		34
Silicate LGS-247	PDF	~1	1064			1.17	(3.25)	34
Silicate LSO	ER	13	694	1.51	(0.058)	1.44	(4.0)	4
Silicate Q-246	NDFWM	3	1064	(1.558)	(0.054)	1.31	(3.52)	16
Silicate "QR"	DFWM	0.09	1064	2.02	1.1	(20.7)	(43)	22
Silicate SF-56	DFWM	0.08	1064	1.75	(0.51)	(10.9)	26	2
Silicate SF-57	DFWM	0.08	1064	1.81	(0.85)	(17.7)	41	2
Silicate SF-57	OKE	10^{-4}	620	1.8467	0.51	(10.4)	(23.6)	26 ^d
Silicate SF-58	DFWM	0.09	1064	1.88	0.52	(10.3)	(23)	22
Silicate SF-58	DFWM	0.08	1064	1.88	(1.10)	(22)	49	2
Silicate SF-59	DFWM	0.09	1064	1.91	0.75	(14.6)	(32)	22
Silicate SF-59	OKE	10^{-4}	620	1.9176	0.78	(15.3)	(33.5)	26 ^d
Silicate SF-6	NDFWM	3	1064	(1.77)	(0.38)	8.0	(18.9)	16
Silicate SF-6	OKE	10^{-4}	620	1.8052	0.45	(9.40)	(21.8)	26 ^d
Silicate SF-6	TRI	~1	1064	1.77	(0.42)	9.0	(21)	31
Silicate SF-7	ER	20	694	1.67	(0.093)	5.9	(15)	19 ^b
Silicate:TB FR-5	TRI	0.125	1064			2.1	5.2	13
Silicate ZF-7	TII		532			0.7		35
Tellurite 3151	NDFWM	3	1064	2.05	(1.31)	24	(49)	16
Tellurite K-1261	NDFWM	3	1064	2.05	(1.25)	23	(47)	16

^a total n_2 ; ^b electronic assumption; ^c also nuclear/electronic ratio; ^d low frequency assumption.

References:

1. Chase, L. L., and Van Stryland, E. W., Nonlinear refractive index: inorganic materials, in *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 269.
2. Friberg, S. R., and Smith, P. W., Nonlinear optical glasses for ultrafast optical switches, *IEEE J. Quantum Electron.* QE-23, 2089 (1987).
3. Feldman, A., Horowitz, D., and Waxler, R. M., Mechanisms for self-focusing in optical glasses, *IEEE J. Quantum Electron.* QE-9, 1054 (1973).
4. Owyong, A., Ellipse rotation studies in laser host materials, *IEEE J. Quantum Electron.* QE-9(11), 1064 (1973).
5. Levenson, M. D., Feasibility of measuring the nonlinear index of refraction by third-order frequency mixing, *IEEE J. Quantum Electron.* QE-10, 110 (1974).
6. Adair, R., Chase, L. L., and Payne, S. A., Nonlinear refractive index of optical crystals, *Phys. Rev.* B39, 3337 (1989).
7. Ho, P. P., and Alfano, R. R., Optical Kerr effect in liquids, *Phys. Rev. A* 20(5), 2170 (1979).
8. Smith, W. L., Bechtel, J. H., and Bloembergen, N., Dielectric-breakdown threshold and nonlinear-refractive-index measurements with picosecond laser pulses, *Phys. Rev. B* 12, 706 (1975).
9. Yang, T. T., Raman scattering and optical susceptibilities of Nd-doped glasses, *Appl. Phys.* 11, 167 (1976).
10. Stolen, R. H., and Lin, C., Self-phase-modulation in silica optical fibers, *Phys. Rev. A* 17(4), 1448 (1978).
11. Smith, W. L., Warren, W. E., Vercimak, C. L., and White, W. T., III, Nonlinear refractive index at 351 nm by direct measurement of small-scale self-focusing, Paper FB4, *Digest of Conference on Lasers and Electro Optics* (Optical Society of America, Washington, DC, 1983), p. 17.
12. Witte, K. J., Galanti, M., and Volk, R., n_2 -Measurements at 1.32 μm of some organic compounds usable as solvents in a saturable absorber for an atomic iodine laser, *Opt. Commun.* 34(2), 278 (1980).
13. Milam, D., and Weber, M. J., Measurement of nonlinear refractive-index coefficients using time-resolved interferometry: application to optical materials for high-power neodymium laser, *J. Appl. Phys.* 47(6), 2497 (1976).
14. Hanson, E. G., Shen, Y. R., and Wong, G. K. L., Experimental study of self-focusing in a liquid crystalline medium, *Appl. Phys.* 14, 65 (1977); Self-focusing: from transient to quasi-steady-state, *Opt. Commun.* 20(1), 45 (1977); Wong, G. K. L., and Shen, Y. R., Transient self-focusing in a nematic liquid crystal in the isotropic phase, *Phys. Rev. Lett.* 32(10), 527 (1974).
15. Boling, N. L., Glass, A. J., and Owyong, A., Empirical relationships for predicting nonlinear refractive index changes in optical solids, *IEEE J. Quantum Electron.* QE-14, 601 (1978).
16. Adair, R., Chase, L. L., and Payne, S. A., Nonlinear refractive index measurements of glasses using three-wave frequency mixing, *J. Opt. Soc. Am. B* 4, 875 (1987).
17. Weber, M. J., Cline, C. F., Smith, W. L., Milam, D., Heiman, D., and Hellwarth, R. W., Measurements of the electronic and nuclear contributions to the nonlinear refractive index of beryllium fluoride glasses, *Appl. Phys. Lett.* 32(7), 403 (1978).
18. Owyong, A., Hellwarth, R. W., and George, N., Intensity-induced changes in optical polarizations in glasses, *Phys. Rev.* B5(2), 628 (1972).
19. White, W. T., III, Smith, W. L., and Milam, D., Direct measurement of the nonlinear refractive index coefficient γ at 355 nm in fused silica and in BK-10 glass, *Opt. Lett.* 9, 10 (1984).
20. Newham, B. E., and DeShazer, L. B., Direct nondestructive measurement of self-focusing in laser glass, *NBS Spec. Publ.* 356, 113 (1971).
21. Garaev, R. A., Vlasov, D. V., and Korobkin, V. V., Need to allow for slow nonlinearity in measurements of n_2 , *Sov. J. Quantum Electron.* 12(1), 100 (1982).
22. Hall, D. W., Newhouse, M. A., Borelli, N. F., Dumbaugh, W. H., and Weidman, D. L., Nonlinear optical susceptibilities of high-index glasses, *Appl. Phys. Lett.* 54, 1293 (1989).
23. Bliss, E. S., Speck, D. R., and Simmons, W. W., Direct interferometric measurements of the nonlinear refractive index coefficient n_2 in laser materials, *Appl. Phys. Lett.* 25(12), 728 (1974).
24. Milam, D., and Weber, M. J., Nonlinear refractive index coefficient for Nd phosphate laser glasses, *IEEE J. Quantum Electron.* QE-12, 512 (1976).
25. Smith, W. L., and Bechtel, J. H., Laser-induced breakdown and nonlinear refractive index measurements in phosphate glasses, lanthanum beryllate, and Al_2O_3 , *Appl. Phys. Lett.* 28, 606 (1976).
26. Thomazeau, I., Etcheparre, J., Grillon, G., and Migué, A., Electronic nonlinear optical susceptibilities of silicate glasses, *Opt. Lett.* 10, 223 (1985).

27. Altshuler, G. B., Barbashev, A. I., Karasev, V. B., Krylov, K. I., Ovchinnikov, V. M., and Sharlai, S. F., Direct measurement of the tensor elements of the nonlinear optical susceptibility of optical materials, *Sov. Tech. Phys. Lett.* 3(6), 213 (1977).
28. Ross, I. N., Toner, W. C., Hooker, C. J., Barr, J. R. M., and Coffey, I., Nonlinear properties of silica and air for picosecond ultraviolet pulses, *J. Mod. Opt.* 37, 555 (1990).
29. Kim, Y. P., and Hutchinson, M. H. R., Intensity-induced nonlinear effects in UV window materials, *Appl. Phys.* B49, 469 (1989).
30. Vogel, E. M., Kosinski, S. G., Krol, D. M., Jackel, J. L., Friberg, S. R., Oliver, M. K., and Powers, J. D., Structural and optical study of silicate glasses for nonlinear optical devices, *J. Non-Cryst. Solids* 107, 244 (1987).
31. Moran, M. J., She, C. Y., and Carman, R. L., Interferometric measurements of the nonlinear refractive index coefficient relative to CS_2 in laser-system-related materials, *IEEE J. Quantum Electron.* QE-11, 159 (1975).
32. Owyoung, A., Nonlinear refractive index measurements in laser media, *NBS Spec. Publ.* 387, 12 (1973).
33. Miller, D. A. B., Seaton, C. T., Prise, M. E., and Smith, S. D., Band-gap-resonant nonlinear refraction in III-V semiconductors, *Phys. Rev. Lett.* 47, 197 (1981).
34. Weaire, D., Wherrett, D. S., Miller, D. A. B., and Smith, S. D., Effect of low-power nonlinear refraction on laser-beam propagation in InSb, *Opt. Lett.* 4, 331 (1979).
35. Chi, K., Interferometric measurement of nonlinear refractive index of ZF-7 glass, *Laser J. (China)* 8, 48 (1981).
36. Veduta, A. P., and Kirsanov, B. P., Variation of refractive index of liquids and glasses in a high intensity field of a ruby laser, *Sov. Phys. JETP* 27, 736 (1968).

2.10.2 Two-Photon Absorption

Two-Photon Absorption Data

Glass	Pulse width t_p (ns)	Band gap E_g (eV)	$2\hbar\omega$ (eV)	Index $n_0(\hbar\omega)$	2PA coeff. β (cm/GW)	Ref.
As_2S_3	~30	—	3.56	~2.58	14	1
As_2S_3	30	2.3	2.4–3.6	2.5–2.6	(a)	2
BK 3 (Schott)	1.2	4.4	4.67	—	0.0006	3
BK 7 (Schott)	1.1, 7	3.9	7.07	1.54	0.0060	4
BK 7 (Schott)	1.2	4.0	4.67	—	0.0029	3
BK 10 (Schott)	1.1, 7	4.1	7.07	1.52	0.0045	4
BK 10 (Schott)	1.2	4.5	4.67	—	0.0004	3
Holmium oxide	—	—	4.26–4.32	—	(b)	5
LG630:Nd (Schott)	0.006	—	2.33	—	0.004	6
Silica 7940 (Corning)	1.1, 7	7.8	7.07	~1.6	<0.0005	4
Silica (Suprasil)	0.017	7.8	6.99	~1.6	<0.0012	7
Silica (Suprasil)	0.015	7.8	9.32	~1.6	<0.045	7
Silica (Suprasil)	0.015	7.8	9.32	~1.6	0.017	8
Silica (Suprasil)	0.00045	7.8	10.0	~1.6	0.058	9
Silica (fused)	0.0007	7.8	10.0	~1.6	0.045	10
Silica (fused)	~10	—	12.8	—	0.11	11
Silica (fused)	0.008	—	10.0	~1.6	0.08	12
Silica (fused)	0.00028	7.8	10.0	~1.6	0.014	13
Silica (fused)	0.004	—	10.0	~1.6	0.06	14

(a) Relative spectrum, (b) Absorption spectrum (30 @ 3.1 eV)

The preceding table was adapted from Van Stryland, E. W. and Chase, L. L., Two-photon absorption: inorganic materials, in *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 299.

References:

1. Maker, P. D., and Terhune, R. W., Study of optical effects due to an induced polarization third order in the electric field strength, *Phys. Rev.* 137(3A), A801 (1965).
2. Nasirov, U., Two-photon absorption spectrum of crystalline and glassy As_2S_3 , *Sov. Phys. Semicond.* 12(6), 720 (1978).
3. White III, W. T., Henesian, M. A., and Weber, M. J., Photothermal-lensing measurements of two-photon absorption and two-photon-induced color centers in borosilicate glasses at 532 nm, *J. Opt. Soc. Am. B* 2, 1402–1408 (1985).
4. Smith, W. L., Lawrence Livermore National Laboratory, 1981 Laser Program Annual Report, U.C.R.L. - 50021-81, p. 7–23.
5. Munir, Q., Wintner, E., and Schmidt, A. J., Optoacoustic detection of nonlinear absorption in glasses, *Opt. Commun.* 36(6), 467 (1981).
6. Penzkofer, A., and Kaiser, W., Nonlinear loss in Nd-doped laser glass, *Appl. Phys. Lett.* 21(9), 427 (1972).
7. Liu, P., Smith, W. L., Lotem, H., Bechtel, J. H., Bloembergen, N., and Adhav, R. S., Absolute two-photon absorption coefficients at 355 and 266 nm, *Phys. Rev. B* 17(12), 4620 (1978).
8. Liu, P., Yen, R., and Bloembergen, N., Two-photon absorption coefficients in UV window and coating materials, *Appl. Opt.* 18(7), 1015 (1979).
9. Simon, P., Gerhardt, H., and Szatmari, S., Intensity-dependent loss properties of window materials at 248 nm, *Opt. Lett.* 14, 1207–1209 (1989).
10. Taylor, A. J., Gibson, R. B., and Roberts, J. P., Two-photon absorption at 248 nm in ultraviolet window materials, *Opt. Lett.* 13, 814–816 (1988).
11. Devine, R. A. B., Defect creation and two-photon absorption in amorphous SiO_2 , *Phys. Rev. Lett.* 62, 340 (1989).
12. Tomie, T., Okuda, I., and Yano, M., Three-photon absorption in CaF_2 at 248.5 nm, *Appl. Phys. Lett.* 55, 325 (1989).
13. Hata, K., Watanabe, M., and Watanabe, S., Nonlinear processes in UV optical materials at 248 nm, *Appl. Phys. B* 50, 55–59 (1990).
14. Ross, I. N., Toner, W. T., Hooker, C. J., Barr, J. R. M., and Coffey, I. C., Nonlinear properties of silica and air for picosecond pulses, *J. Modern Opt.* 37, 555–573 (1990).

2.10.3 Third-Order Nonlinear Optical Coefficients

Glass	Nonlinear optical process	Coefficient $C_{jn} \times 10^{20} \text{ m}^2 \text{ V}^{-2}$	Wavelength (μm)
BK-7	$(-\omega; \omega, \omega, -\omega)$	$C_{11} = 0.00257$	0.6943
Borosilicate	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 0.0018$	0.6943
ED-4 glass	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 0.01498 \pm 0.0011$	0.525
K-8	$(-\omega; \omega, \omega, -\omega)$	$C_{11} = 0.21 \pm 0.042$	0.6943
LaSF-7	$(-\omega; \omega, \omega, -\omega)$	$C_{11} = 0.014$	0.694
LSO-glass	$(-\omega; \omega, \omega, -\omega)$	$C_{11} = 0.0026$	0.694
SF-7	$(-\omega; \omega, \omega, -\omega)$	$C_{11} = 0.01108$	0.694
Silica, SiO_2	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 0.098$	0.6943
	$(-\omega; \omega, \omega, -\omega)$	$C_{18} = 0.0017$	0.694
		$C_{11} = 0.672 \pm 0.126$	0.6943
TF-7	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 0.42 \pm 0.098$	0.6943

Table adapted from Singh, S., Nonlinear optical materials, *Handbook of Laser Science and Technology, Vol. III: Optical Materials, Part 1* (CRC Press, Boca Raton, FL, 1986), p. 54.

2.10.4 Brillouin Phase Conjugation

Glasses Used for Brillouin Phase Conjugation

Glass	Wavelength λ (nm)	Brillouin shift at λ (GHz)	Linewidth $\Delta\nu_b$ (MHz)	Gain g (cm/GW)	Ref.
Silica, SiO_2	1064		16	4.7, 5	1
			29–75(a)	2.5	2
			29	2.3	3
	532		43–162(b)	2.9	4
	488	25.18		4.48	5
Silicate glass	488	21.79–23.41	170–208	2.78–5.18	5
Borate glass	488	17.54–23.31	100–138	3.44–14.29	5
Halide glasses(c)					
ZBL	488	17.64	213.6	2.832	5
ZBLA	488	17.80	98.7	1.713	5
ZBLAN	488	18.82	96.0	3.608	5
HBL	488	15.83	151.4	1.127	5
HBLA	488	15.63	162.3	0.96	5
HBLAPC	488	17.82	179.5	1.023	5
BeF_2	488	17.19	52.5	16.06	5
95 BeF_2 -5 ThF_4	488	17.61	74.8	11.54	5
91 BeF_2 -9 ThF_4	488	19.33	42.8	12.44	5
88 BeF_2 -12 ThF_4	488	18.40	21.3	24.69	5

(a) The authors report gain narrowing.

(b) The authors report the transverse and longitudinal linewidth, respectively.

(c) Gain calculated from the authors measurements of other parameters.

The above table was adapted from Pepper, D. M., Minden, M. L., Bruesselbach, H. W. and Klein, M. B., Nonlinear optical phase conjugation materials, in *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 467.

References:

1. Bespalov, V. I., and Pasmanik, G. A., *Nonlinear Optics and Adaptive Laser Systems* (Nauka, Moscow, USSR, 1985). Trans. by Translation Division, Foreign Technology Division, Wright Patterson Air Force Base, OH, document FTD-ID(RS)T-0889-86.
2. Gaeta, A. L., and Boyd, R. W., Stochastic dynamics of stimulated Brillouin scattering in an optical fiber, *Phys. Rev. A (Atomic, Molecular, and Optical Physics)*, 44, 3205 (1 Sept. 1991).
3. Tsun, T.-O. Wada, A., Sakai, T., and Yamauchi, R., Novel method using white spectral probe signals to measure Brillouin gain spectra of pure silica core fibres, *Electron. Lett.* 28, 247–249 (30 Jan. 1992).
4. Faris, G. W., Jusinski, L. E., Dyer, M. J., Bischel, W. K., and Hickman, A. P., High-resolution Brillouin gain spectroscopy in fused silica, *Opt. Lett.* 15, 703–705 (15 June 1990).
5. Hwa, L.-G., et al., *J. Opt. Soc. Am. B (Opt. Phys.)*, Topical Meeting on Nonlinear Optical Properties of Materials, 833 (1989).

2.11 Special Glasses

2.11.1 Filter Glasses

There are three general types of filter glasses: (1) colorless—optical glasses with different ultraviolet cutoffs, (2) ionically colored by heavy metal or rare earth ions, and (3) colloidically colored. The optical, thermal, and mechanical properties, chemical resistance, and internal quality of these glasses are carefully controlled and are generally similar to those of optical glasses. Manufacturer's catalogs should be consulted for specific transmission curves and transmittance. Several of the colored filter glasses exhibit photoluminescence [see W. H. Turner, Photoluminescence of color filter glasses, *Appl. Opt.* 12, 480 (1973) and tables later in this section].

Glass filters may be classified according to their optical properties—short wavelength cutoff, long wavelength cutoff, bandpass, band blocking, and neutral density. Filter glasses produced by major manufacturers are listed by groups in the following table.

Commercial Filter Glasses

	Corning			
	Glass no.	C.S. no.	Hoya	Schott
UV cutoff filters (visible and IR transmitting)	7940 UV	9-57	—	—
	7940	9-58	—	—
	7910	9-54	UV-22	WG-230
	7906	9-30	UV-28	WG-280
	7058	0-56	—	—
	—	—	UV-30	WG-395
	7740	0-53	—	WG-305
	—	—	UV-32	WG-320
	9754	9-56	UV-34	WG-335
	7953	9-55	—	WG-345
	7380	0-52	UV-36	WG-360
Near UV and visible cutoff filters	—	—	L-36	—
	—	—	L-38	GG-375
	3850	0-51	L-39	GG-385
	—	—	L-40	GG-395
	3060	3075		GG-400
	3391	3-74	L-42	GG-420
	—	3-144	—	—
	3389	3-73	L-44	GG-435
	3387	3-72	Y-46	GG-455
	—	—	Y-48	GG-475
	3385	3-71	Y-50	GG-495
	3384	3-70	Y-52	OG-515
	3486	3-69	O-54	OG-530
	3484	3-68	O-56	OG-550
	3482	3-67	—	—
	3480	3-66	O-58	OG-570

Commercial Filter Glasses—continued

	Corning			
	Glass no.	C.S. no.	Hoya	Schott
Near UV and visible cutoff filters				
	2434	2-73	—	—
	2424	2-63	R-60	OG-590
	2418	2-62	—	RG-610
	2412	2-61	R-62	—
	2408	2-60	V	RG-630
	2404	2-59	—	—
	2403	2-58	R-64	RG-645
	2030	2-64	R-66	RG-665
			R-68	—
IR transmitting sharp cutoff filters	—	—	R-70	RG-695
	—	—	R-72	RG-715
	—	—	IR-76	—
	—	—	IR-80	RG-780
	—	—	IR-83	RG-830
	2550	7-57	IR-85	RG-850
	—	—	RM-86	—
	2563	7-99	RM-90	—
	2540	7-56	—	—
	—	—	RM-1000	RG-1000
	2600	7-69	—	—
UV transmitting, visible rejection (variable IR transmission)	5970	7-51	B-370	UG-1
	9863	7-54	U-330	UG-5
	—	—	U-340	UG-11
	5860	7-37	U-350	—
	5840	7-60	U-360	—
	5113	5-58	—	—
UV, IR transmitting, visible rejection (blue-violet glass)	5073	7-64	M-30	UG-3
	5071	7-63	M-50	—
	5330	1-64	B-380	BG-1
	5070	7-62	—	BG-1
	—	—	—	BG-3
	—	—	M-10	BG-24
	5030	5-57	M-30	—
	5113	5-58	M-50	—
	5850	7-59	—	—
	5874	7-39	—	—
	5031	5-56	B-410	—
Blue transmitting, red IR absorbing	5562	5-61	B-390	BG-12
	—	—	—	BG-25
	—	—	—	BG-37
	5900	1-62	LB-80	BG-34
	5900	1-62	LB-20	BG34

Commercial Filter Glasses—continued

	Corning			
	Glass no.	C.S. no.	Hoya	Schott
Blue transmitting, red IR absorbing	5900	1-62	LB-40	BG-34
	5900	1-62	LB-60	BG34
	5900	1-62	LB-100	BG-34
	5900	1-62	LB-120	BG34
	5900	1-62	LB-145	BG-34
	5900	1-62	LB-165	BG34
	5900	1-62	LB-200	BG-34
	5433	5-59	B-430	—
	5543	5-60	B-440	—
	4308	4-70	—	BG-14
	4303	4-72	B-460	BG-23
	4305	4-71	—	BG-26
	—	—	B-480	BG-28
	—	—	—	BG-13
	4060	4-67	—	BG-7
	4-74	4-74	—	BG-7
Blue, green transmitting, red, IR absorbing	4309	4-39	CS-500	BG-38
	9788	4-97	C-500	—
	9782	4-96	CM-500	BG-39
	—	—	C-500	—
	—	—	CL-500	—
	—	—	CC-500	—
	—	—	—	BG-40
	9780	4-76	—	—
	4784	4-94	—	BG-18
Green transmitting	—	—	—	VG-4
	4015	4-65	—	VG-5
	5300	4-106	—	—
	—	—	—	VG-6
	—	—	G-530	—
	4010	4-64	G-5633	VG-9
	—	—	G-545	—
	—	—	G-550	VG-10
	—	—	—	VG-14
	—	—	—	GG-4
	—	—	—	GG-10
	4084	4-68	—	GG-19
	9830	4-77	—	—
IR absorbing, visible transmitting	3961	1-56	—	KG-1
	3962	1-57	—	KG-2
	3965	1-58	—	KG-3

Commercial Filter Glasses—continued

	Corning			
	Glass no.	C.S. no.	Hoya	Schott
IR absorbing, visible transmitting	3966	1-59	HA-20	KG-4
	4605	1-75	HA-30	—
	—	—	HA-50	KG-5
IR transmitting, visible absorbing filters	2600	7-69	HA-60	RG-9
	2540	7-56	RT-830	RG-1000
	2550	7-57	RM-86	—
	—	—	RM-89	—
	—	—	RM-100	—
Neutral density filters	—	—	—	NG-1
	—	—	ND-03	NG-3
	—	—	ND-25	—
	8364	7-98	ND-40	NG-4
	—	—	ND-50	NG-5
	—	—	—	NG-9
	—	—	ND-13	—
	3390	7-58	ND-0	NG-10
	—	—	ND-70	NG-4
	—	—	—	NG-12
Fluorescent color compensating filters	—	—	FLD-60	—
	—	—	FLW-85	—
Signal yellow and uranium yellow filters	3304	3-76	—	—
	3307	3-77	—	—
	3750	3-79	—	—
	3780	3-80	—	—
	3718	3-94	—	—
Color conversion filters	5572	1-61	—	FG-3
	—	—	LA-20	—
	—	—	—	FG-6
	—	—	LA-40	FG-13
	—	—	LA-60	FG-15
	—	—	—	FG-16
	—	—	LA-80	—
	—	—	LA-100	—
	—	—	LA-120	—
	—	—	LA-140	—
	—	—	1-1B	—
Calibration filters	5121	1-60	—	—
	311	3-142	HY-1	—
	—	—	V-10	BG-20
	—	—	V-30	BG-36

Table from Cook, L. M. and Stokowski, S. E., Filter materials, *Handbook of Laser Science and Technology, Vol. IV, Optical Materials, Part 2* (CRC Press, Boca Raton, FL, 1986), p. 93.

Fluorescence Data for Schott Filter Glasses

Filter type	Xenon-arc lamp		Mercury-arc lamp	
	Emission max. (nm)	Intensity relative to GG-17	Emission max. (nm)	Intensity relative to GG-17
UG-3	520	0.2	432	0.3
UG-10	515	2.7	450	1.4
BG-13	542	0.7	525	0.4
BG-14	522	1.9	490	0.8
BG-23	520	0.3	490	0.3
BG-38	520	4.1	505	2.8
BG-39	515	0.3	460	0.2
BG-39	480	0.1	510	0.2
BG-38	490	0.04	500	0.2
VG-3	515	0.5	520	0.05
VG-13	515	5.2	515	0.1
GG-17	532	100	532	100
GG-21	532	87	535	72
GG-375	432	2.5	460	0.5
GG-400	565	12.4	548	0.9
GG-420	570	30	575	4.1
GG-435	590	13	580	1.6
GG-455	620	30	580	1.7
GG-475	620	30	580	3.2
GG-495	630	19	590	1.9
OG-515	660	8.2	575	1.4
OG-530	670	4.5	585	0.4
OG-550	650	4.1	595	0.6
OG-570	670	2.1	605	0.6
OG-590	680	0.6	625	0.3
WG-9	440	21	460	0.6
WG-10	465	0.02	465	1.7
WG-230	540	0.03	420	1.6
WG-280	530	0.08	530	1.1
WG-295	515	0.08	525	1.0
WG-305	425	0.02	435	6.4
WG-320	430	0.2	455	2.8
WG-335	450	0.3	455	3.3
WG-345	460	0.1	500	0.5
WG-360	530	0.4	490	0.6
FG-1	555	0.05	610	0.2
FG-4	515	1.8	450	0.7
FG-5	515	0.9	460	0.5
FG-12	515	2.5	455	1.4
RG-610	660	0.6	660	0.2

Fluorescence Data for Schott Filter Glasses—continued

Filter type	Xenon-arc lamp		Mercury-arc lamp	
	Emission max. (nm)	Intensity relative to GG-17	Emission max. (nm)	Intensity relative to GG-17
RG-630	660	0.8	660	0.18
RG-645	635	3.3	680	0.4
RG-665	690	0.3		
RG-695	710	0.08		
RG-715	680	1.0		

Fluorescence Data for Corning Filter Glasses

Filter number	Excitation wavelength (nm)	Emission peak (nm)	Fluorescence intensity
0-54	300	405	1.0
0-51	350	560	0.0031
0-52	345	420	0.286
0-53	225	420	0.077
3-75	350	560	0.0064
3-74	400	570	0.104
3-73	420	570	0.108
3-72	420	620	0.065
3-71	450	630	0.065
3-70	470	680	0.022
3-69	440	685	0.014
3-68	420	730	0.0024
3-67	440	735	0.0008
3-66	450	740	0.0005
2-73	450	740	0.0004
2-63	450	780	0.0003
2-62	450	780	0.0002
2-61	450	790	0.0002
3-79	300	535	1.513
3-94	400	535	0.098
4-69	345	510	0.0014
4-69	250	500	0.111
4-71	345	500	0.0059
9-30	250	390	0.314
9-54	250	395	0.154

Preceding two tables are from Cook, L. M. and Stokowski, S. E., Filter materials, *Handbook of Laser Science and Technology, Vol. IV, Optical Materials, Part 2* (CRC Press, Boca Raton, FL, 1986), p. 93.

2.11.2 Laser Glasses

Compositions of commercial laser glasses are rarely published. Most current glasses are similar to the following:

- Silicate glasses of the $\text{Li}_2\text{O}-\text{CaO}-\text{SiO}_2$ or $\text{Li}_2\text{O}-\text{Na}_2\text{O}-\text{SrO}-\text{SiO}_2$ type. Examples of these glasses include the Schott LG-680, Kigre Q-246, and Hoya LSG-91H. These glasses generally have excellent physical properties and, because of their high Li_2O content, can be strengthened by ion exchange. Therefore, these glasses can be very resistant to thermal shock.
- Potassium-barium-phosphate glasses with a high cross section for stimulated emission. Examples of these glasses include Schott LG-760, Hoya LGH-80, and Kigre Q-98. These glasses are often modified with Na_2O , Li_2O , Al_2O_3 , etc. to produce a glass with a near-zero optical distortion. Examples of these athermal glasses include Schott LG-LG-760, Hoya LGH-8, and Kigre Q-98.
- Lithium-aluminum-phosphate glasses with a relatively high thermal shock resistance for high average power applications. These glasses can usually be ion exchanged to further improve their resistance to breakage. Examples of these glasses include Schott APG-1 and Hoya HAP-4.
- Fluorophosphate glasses feature a low nonlinear refractive index which reduces spatial beam breakup due to small scale self-focusing. An example is Schott LG-810.

In addition to commercial laser glasses, a large number of different glasses have been used in experimental lasers. Below is a summary of the range of spectroscopic properties that have been obtained for the ${}^4\text{F}_{3/2}-{}^4\text{I}_{11/2}$ transition of Nd^{3+} . For additional data of glass lasers, see the *Handbook of Lasers* (CRC Press, Boca Raton, FL, 2000), p. 161.

Spectroscopic Properties for Nd^{3+} Observed in Different Glasses at 295 K

Host glass	Refractive index (n_d)	Cross section (pm^2)	Peak wavelength (μm)	Effective linewidth (nm)	Radiative lifetime (μs)
Oxides					
Silicate	1.46–1.75	0.9–3.6	1.057–1.088	34–55	170–1090
Germinate	1.61–1.71	1.7–2.5	1.060–1.063	36–43	300–460
Tellurite	2.0–2.1	3.0–5.1	1.056–1.063	26–31	140–240
Phosphate	1.49–1.63	2.0–4.8	1.052–1.057	22–35	280–530
Borate	1.51–1.69	2.1–3.2	1.054–1.062	34–38	270–450
Halides					
Beryllium fluoride	1.28–1.38	1.6–4.0	1.046–1.050	19–29	460–1030
Aluminum fluoride	1.39–1.49	2.2–2.9	1.049–1.050	28–32	540–650
Heavy metal fluoride	1.50–1.56	2.5–3.4	1.048–1.051	25–29	360–500
Chloride	1.67–2.06	6.0–6.3	1.062–1.064	19–20	180–220
Oxyhalides					
Fluorophosphate	1.41–1.56	2.2–4.3	1.049–1.056	27–34	310–570
Chlorophosphate	1.51–1.55	5.2–5.4	1.055	22–23	290–300
Chalcogenides					
Sulfide	2.1–2.5	6.9–8.2	1.075	21	64–100
Oxysulfide	2.4	4.2	1.075	28	92

Properties of Hoya Laser Glasses

Glass designation	LHG-5	LHG-8	LHG-80
Glass type	Nd-doped phosphate	Nd-doped phosphate	Nd-doped phosphate
Lasing Properties			
Peak laser wavelength (nm)	1054	1054	1054
Stimulated emission cross section (pm^2)	4.1	4.2	4.8
Specific gain coefficient ($\text{cm}^{-1}/\text{J}/\text{cm}^3$)	0.217	0.223	0.255
Loss at lasing wavelength (cm^{-1})	0.0015	0.0015	0.0015
Fluorescence linewidth			
FWHM (nm)	22.0	21.8	20.2
Effective (nm)	—	—	—
Fluorescence lifetime (μs)	290	315	320
at $[\text{Nd}^{3+}] (10^{20} / \text{cm}^3)$	3.2	3.1	3.1
Optical properties			
Refractive index at			
lasing wavelength (nm)	1.5308	1.5200	1.5329
633	1.5391	1.5279	1.5415
587 nm, n_d	1.5410	1.5296	1.5429
Abbe value	63.5	66.5	64.7
Nonlinear refractive index, $n_2 (10^{-13} \text{ esu})$	1.28	1.13	1.24
Temperature coefficient of refractive index, $dn/dT (20-40^\circ\text{C}) (10^{-6}/^\circ\text{C})$	-0.4	-5.3	-3.8
Temperature coefficient of optical path length, $w = \text{CTE} (n - 1) + dn/dT (20-40^\circ\text{C}) (10^{-6}/^\circ\text{C})$	4.2	0.6	1.8
Stress optical coefficient ($\text{nm}/\text{cm}/\text{kgf}/\text{cm}^2$)	2.26	1.93	1.77
Thermal Properties			
Coefficient of thermal expansion,			
$dl/dT (10^{-6}/^\circ\text{C}) (20-40^\circ\text{C})$	8.4	11.2	10.2
(100–300°C)	9.8	12.7	13.0
Thermal conductivity ($\text{W}/\text{m K}$)	0.77	0.58	0.63
Specific heat ($\text{J}/\text{g K}$)	0.71	0.75	0.63
Glass transformation temperature, $T_g (\text{°C})$	455	485	402
Other Properties			
Density (g/cm^3)	2.68	2.83	2.92
Young's modulus, $E (\text{kgf}/\text{mm}^2)$	6910	5110	5100
Poisson's ratio	0.237	0.258	0.267
Knoop hardness (kgf/mm^2)	429	350	342

Properties of Hoya Laser Glasses—*continued*

Glass designation	LSG-91H	HAP-4	LEG-30
Glass type	Nd-doped silicate	Nd-doped phosphate	Er-doped phosphate
Lasing Properties			
Peak laser wavelength (nm)	1062	1054	1535
Stimulated emission cross section (pm^2)	2.7	3.6	0.77
Specific gain coefficient ($\text{cm}^{-1}/\text{J}/\text{cm}^3$)	0.144	0.197	—
Loss at lasing wavelength (cm^{-1})	0.0015	0.0015	—
Fluorescence linewidth			
FWHM (nm)	27.4	27.0	32.0
Effective (nm)	—	—	—
Fluorescence lifetime (μs) at $[\text{Nd}^{3+}] (10^{20} / \text{cm}^3)$	300 3.0	350 3.2	8.7 —
Optical properties			
Refractive index at			
lasing wavelength (nm)	1.5498	1.5331	1.527
632.8 nm	1.5590	1.5416	1.5402
587 nm, n_d	1.5611	1.5433	1.5419
Abbe value	56.6	64.6	65.4
Nonlinear refractive index, $n_2 (10^{-13} \text{ esu})$	1.58	1.25	1.22
Temperature coefficient of refractive index, dn/dT (20–40°C) ($10^{-6}/^\circ\text{C}$)	1.6	1.8	−3.0
Temperature coefficient of optical path length, $w = \text{CTE} (n - 1) + dn/dT (20\text{--}40^\circ\text{C}) (10^{-6}/^\circ\text{C})$	6.6	5.7	2.2
Stress optical coefficient ($\text{nm}/\text{cm}/\text{kgf}/\text{cm}^2$)	2.16	2.44	—
Thermal Properties			
Coefficient of thermal expansion, $dl/dT (10^{-6}/^\circ\text{C})$			
(20–40°C)	9.0	7.2	9.6
(100–300°C)	10.5	8.5	10.9
Thermal conductivity (W/m K)	1.03	1.02	—
Specific heat (J/g K)	0.63	0.71	0.55
Glass transformation temperature, T_g (°C)	465	486	515
Other Properties			
Density (g/cm^3)	2.81	2.70	3.09
Young's modulus, E (kgf/mm^2)	8890	7020	5640
Poisson's ratio	0.237	0.236	0.26
Knoop hardness (kgf/mm^2)	590	470	346

Properties of Kigre Laser Glasses

Glass designation	Q-88	Q-98	Q-100
Glass type	Nd-doped phosphate	Nd-doped phosphate	Nd-doped phosphate
Lasing Properties			
Peak laser wavelength (nm)	1054	1053	1054
Stimulated emission cross section (pm^2)	4.0	4.5	4.4
Specific gain coefficient ($\text{cm}^{-1}/\text{J}/\text{cm}^3$)	—	—	—
Loss at lasing wavelength (cm^{-1})	0.0008	0.0008	0.0008
Fluorescence linewidth			
FWHM (nm)	21.9	21.1	21.2
Effective (nm)	26.3	25.5	25.1
Fluorescence lifetime (μs) at $[\text{Nd}^{3+}] (10^{20} / \text{cm}^3)$	326	308	357
Optical properties			
Refractive index at			
lasing wavelength (nm)	1.504	1.516	1.508
632.8 nm	1.513	1.524	1.514
587 nm, n_D	1.515	1.526	1.519
Abbe value	67.5	68.2	69.2
Nonlinear refractive index, $n_2 (10^{-13} \text{ esu})$	1.08	1.08	1.02
Temperature coefficient of refractive index, dn/dT			
($20\text{--}40^\circ\text{C}$) ($10^{-6}/^\circ\text{C}$)	-3.2	-5.1	-6.8
Temperature coefficient of optical path length, $w = \text{CTE} (n - 1) + dn/dT (20\text{--}40^\circ\text{C}) (10^{-6}/^\circ\text{C})$			
w	2.3	0.8	-0.4
Stress optical coefficient ($\text{nm}/\text{cm}/\text{kgf}/\text{cm}^2$)	2.1	1.8	2.0
Thermal Properties			
Coefficient of thermal expansion dl/dT			
($10^{-6}/^\circ\text{C}$) ($20\text{--}40^\circ\text{C}$)	10.9	11.4	12.5
($100\text{--}300^\circ\text{C}$)	—	—	—
Thermal conductivity ($\text{W}/\text{m K}$)	0.69	0.52	0.60
Specific heat ($\text{J}/\text{g K}$)	0.84	0.72	0.75
Glass transformation temperature, T_g ($^\circ\text{C}$)	458	450	350
Other Properties			
Density (g/cm^3)	2.63	2.83	2.60
Young's modulus, E (kgf/mm^2)	6181	5110	5477
Poisson's ratio	0.243	0.256	0.267
Knoop hardness (kgf/mm^2)	320	290	310

Properties of Kigre Laser Glasses—continued

Glass designation	Q-246	MM-2	QE-7S
Glass type	Nd-doped phosphate	Er-doped phosphate	Er-doped phosphate
Lasing Properties			
Peak laser wavelength (nm)	1054.5	1535	1.535
Stimulated emission cross section (pm^2)	3.5	0.8	0.8
Specific gain coefficient ($\text{cm}^{-1}/\text{J}/\text{cm}^3$)	0.186	—	—
Loss at lasing wavelength (cm^{-1})	0.0015	—	0.002
Fluorescence linewidth			
FWHM (nm)	23.0	55	30
Effective (nm)	26.65		
Fluorescence lifetime (μs) at $[\text{Nd}^{3+}] (10^{20} / \text{cm}^3)$	350 2.0	7900 —	8000 —
Optical properties			
Refractive index at			
lasing wavelength (nm)	1.526	1.53	1.531
632.8 nm	1.535	—	—
587 nm, n_D	1.537	1.54	1.542
Abbe value	67.7	—	—
Nonlinear refractive index, $n_2 (10^{-13} \text{ esu})$	1.13	—	—
Temperature coefficient of refractive index, dn/dT			
(20–40°C) ($10^{-6}/^\circ\text{C}$)	1.2	-3.8	6.3
Temperature coefficient of optical path length, $w = \text{CTE} (n-1) + dn/dT (20-40^\circ\text{C}) (10^{-6}/^\circ\text{C})$			
5.2	3.3	0.3	
Stress optical coefficient ($\text{nm}/\text{cm}/\text{kgf}/\text{cm}^2$)	2.2	2.1	
Thermal Properties			
Coefficient of thermal expansion dl/dT			
($10^{-6}/^\circ\text{C}$) (20–40°C)	7.6	7.3	11.4
(100–300°C)	—	8.4	—
Thermal conductivity (W/m K)	0.83	0.85	0.82
Specific heat (J/g K)	0.84		0.80
Glass transformation temperature, T_g (°C)	450	506	462
Other Properties			
Density (g/cm^3)	2.64	2.70	2.94
Young's modulus, E (kgf/mm^2)	7242	7100	7210
Poisson's ratio	0.239	0.24	0.24
Knoop hardness (kgf/mm^2)	315	435	556

Properties of Kigre Laser Glasses—continued

Glass designation	QX/Nd	QX/Er	QX/Yb
Glass type	Nd-doped phosphate	Nd-doped phosphate	Nd-doped phosphate
Lasing Properties			
Peak laser wavelength (nm)	1054	1535	1025-1060
Stimulated emission cross section (pm^2)	3.8	0.8	1.4
Specific gain coefficient ($\text{cm}^{-1}/\text{J}/\text{cm}^3$)	—	—	—
Loss at lasing wavelength (cm^{-1})	—	—	—
Fluorescence linewidth	—	—	—
FWHM (nm)	27.2	55.0	56.5
Effective (nm)	—	—	—
Fluorescence lifetime (μs)	353	7900	2000
at $[\text{Nd}^{3+}] (10^{20} / \text{cm}^3)$	—	—	—
Optical properties			
Refractive index at			
lasing wavelength (nm)	1.53	1.521	1.52
632.8 nm	—	—	—
589.3 nm, n_D	1.538	1.538	1.535
Abbe value	66.0	64.5	61.1
Nonlinear refractive index, $n_2 (10^{-13} \text{ esu})$	1.17	1.22	1.22
Temperature coefficient of refractive index dn/dT			
($20-40^\circ\text{C}$) ($10^{-6}/^\circ\text{C}$)	-0.4	0	0
Temperature coefficient of optical path length, $w = \text{CTE} (n - 1) + dn/dT (20-40^\circ\text{C}) (10^{-6}/^\circ\text{C})$	5.1	3.3	3.3
Stress optical coefficient ($10^{-6} \text{ mm}^2/\text{N}$)	2.1	2.3	2.3
Thermal Properties			
Coefficient of thermal expansion dl/dT			
($10^{-6}/^\circ\text{C}$) ($20-40^\circ\text{C}$)	7.2	8.2	8.3
($20-100^\circ\text{C}$)	8.4	9.4	9.5
Thermal conductivity (W/m K)	0.85	0.85	0.85
Specific heat (J/g K)	—	—	—
Glass transformation temperature, T_g ($^\circ\text{C}$)	—	—	—
Other Properties			
Density (g/cm^3)	2.66	2.90	2.81
Young's modulus, $E (10^3 \text{ N}/\text{mm}^2)$	7100	6700	6700
Poisson's ratio	0.24	0.24	0.24
Knoop hardness (kgf/mm^2)	503	435	435

Properties of Schott Laser Glasses

Glass designation	LG-700	LG-750	LG-760
Glass type	Nd-doped phosphate	Nd-doped phosphate	Nd-doped phosphate
Lasing Properties			
Peak laser wavelength (nm)	1053	1053.5	1053.5
Stimulated emission cross section (pm^2)	3.7	4.0	4.2
Specific gain coefficient ($\text{cm}^{-1}/\text{J}/\text{cm}^3$)	0.195	0.212	0.223
Loss at lasing wavelength (cm^{-1})	0.0015	0.0020	—
Fluorescence linewidth			
FWHM (nm)	22.3	21.5	19.6
Effective (nm)	26.6	25.5	23.6
Fluorescence lifetime (μs) at $[\text{Nd}^{3+}] (10^{20} / \text{cm}^3)$	350 2.0	360 2.0	350 2.0
Optical properties			
Refractive index at			
lasing wavelength (nm)	1.504	1.516	1.508
632.8 nm	1.513	1.524	1.514
587 nm, n_d	1.515	1.526	1.519
Abbe value	67.5	68.2	69.2
Nonlinear refractive index, $n_2 (10^{-13} \text{ esu})$	1.08	1.08	1.02
Temperature coefficient of refractive index dn/dT (20–40°C) ($10^{-6}/^\circ\text{C}$)	-3.2	-5.1	-6.8
Temperature coefficient of optical path length, $w = \text{CTE} (n - 1) + dn/dT (20-40^\circ\text{C}) (10^{-6}/^\circ\text{C})$	2.3	0.8	-0.4
Stress optical coefficient ($\text{nm}/\text{cm}/\text{kgf}/\text{cm}^2$)	2.1	1.8	2.0
Thermal Properties			
Coefficient of thermal expansion dl/dT			
($10^{-6}/^\circ\text{C}$) (20–40°C)	10.9	11.4	12.5
(100–300°C)	—	—	—
Thermal conductivity (W/m K)	0.69	0.52	0.60
Specific heat (J/g K)	0.84	0.72	0.75
Glass transformation temperature, T_g (°C)	458	450	350
Other Properties			
Density (g/cm^3)	2.63	2.83	2.60
Young's modulus, $E (10^3 \text{ N}/\text{mm}^2)$	6181	5110	5477
Poisson's ratio	0.243	0.256	0.267
Knoop hardness (N/mm^2)	320	290	310

Properties of Schott Laser Glasses—continued

Glass designation	LG-660	LG-670 (ED-2)	LG-680 (ED-3)
Glass type	Nd-doped silicate	Nd-doped silicate	Nd-doped silicate
Lasing Properties			
Peak laser wavelength (nm)	1057	1061	1061
Stimulated emission cross section (pm^2)	2.0	2.7	2.9
Specific gain coefficient ($\text{cm}^{-1}/\text{J}/\text{cm}^3$)	0.106	0.144	0.155
Loss at lasing wavelength (cm^{-1})	0.002	<0.003	0.002
Fluorescence linewidth			
FWHM (nm)	24.9	27.8	28.2
Effective (nm)	33.3	34.4	34.7
Fluorescence lifetime (μs) at $[\text{Nd}^{3+}] (10^{20} / \text{cm}^3)$	480 1.4	330 1.4	≥ 350 2.0
Optical properties			
Refractive index at			
lasing wavelength (nm)	1.509	1.561	1.560
632.8 nm	1.517	1.570	1.568
587 nm, n_d	1.519	1.572	1.570
Abbe value	58.2	57.5	57.7
Nonlinear refractive index, $n_2 (10^{-13} \text{ esu})$	1.34	1.41	1.6
Temperature coefficient of refractive index			
$dn/dT (20\text{--}40^\circ\text{C}) (10^{-6}/^\circ\text{C})$	1.1	2.9	2.9
Temperature coefficient of optical path length, $w = \text{CTE} (n - 1) + dn/dT (20\text{--}40^\circ\text{C}) (10^{-6}/^\circ\text{C})$			
w	6.5	8.0	8.1
Stress optical coeff. (546 nm) ($\text{nm}/\text{cm}/\text{N}/\text{mm}^2$)	29	21.0	20
Thermal Properties			
Coefficient of thermal expansion dl/dT			
$(10^{-6}/^\circ\text{C}) (20\text{--}40^\circ\text{C})$	10.7	9.26	9.3
$(100\text{--}300^\circ\text{C})$	12.2	10.3	—
Thermal conductivity ($\text{W}/\text{m K}$)	1.05	1.35	1.35
Specific heat ($\text{J}/\text{g K}$)	0.72	0.92	0.92
Glass transformation temperature, T_g ($^\circ\text{C}$)	395	468	468
Other Properties			
Density (g/cm^3)	2.60	2.54	2.54
Young's modulus, $E (10^3 \text{ N}/\text{mm}^2)$	69.4	90.1	9190
Poisson's ratio	0.233	0.242	0.242
Knoop hardness (N/mm^2)	4415	5876	599

Properties of Schott Laser Glasses—*continued*

Glass designation	APG-1	LG-810	LG-812
Glass type	Nd-doped phosphate	Nd-doped fluoro- phosphate	Nd-doped fluoro- phosphate*
Lasing Properties			
Peak laser wavelength (nm)	1054.5	1051	1051
Stimulated emission cross section (pm^2)	3.5	2.6	2.7
Specific gain coefficient ($\text{cm}^{-1}/\text{J/cm}^3$)	0.186	0.138	0.15
Loss at lasing wavelength (cm^{-1})	0.0015	<0.002	0.005
Fluorescence linewidth			
FWHM (nm)	23.0	26.1	22
Effective (nm)	26.65	31.0	—
Fluorescence lifetime (μs) at $[\text{Nd}^{3+}]$ ($1020 / \text{cm}^3$)	350	470	400
	2.0	1.4	2.86
Optical properties			
Refractive index at			
lasing wavelength (nm)	1.526	1.429	1.428
632.8 nm	1.535	1.434	—
587 nm, nd	1.537	1.435	1.435
Abbe value	67.7	91	91.0
Nonlinear refractive index, $n^2 (10^{-13} \text{ esu})$	1.13	0.52	0.5
Temperature coefficient of refractive index			
dn/dT (20–40°C) ($10^{-6}/^\circ\text{C}$)	1.2	-7.7	-7.7
Temperature coefficient of optical path length, $w = \text{CTE} (n - 1) + dn/dT$ (20–40°C) ($10^{-6}/^\circ\text{C}$)			
	5.2	-1.4	-1.4
Stress optical coeff. (546 nm) ($\text{nm}/\text{cm}/\text{N/mm}^2$)	2.2	9.3	9.3
Thermal Properties			
Coefficient of thermal expansion dl/dT			
($10^{-6}/^\circ\text{C}$) (20–40°C)	7.6	14.5**	14.5**
(100–300°C)	—	16.5	—
Thermal conductivity (W/m K)	0.83	1.06	1.06
Specific heat (J/g K)	0.84	0.71	0.71
Glass transformation temperature, T_g (°C)	450	395	401
Other Properties			
Density (g/cm^3)	2.64	3.19	3.19
Young's modulus, E ($10^3 \text{ N}/\text{mm}^2$)	7242	75.3	75.3
Poisson's ratio	0.239	0.275	0.275
Knoop hardness (N/mm^2)	315	3237	330

* Properties are not final.

** -30–+70°C

2.11.3 Faraday Rotator Glasses

Diamagnetic Glasses

The Verdet constant of diamagnetic glasses is proportional to the dispersion of the refractive index, $dn/d\lambda$. Thus high index, large dispersion glasses are generally used for Faraday rotation applications. Data for representative diamagnetic glasses are given below.*

	Wavelength (nm)				
Schott BK 7	435.8	480.0	546.1	632.8	1060
Verdet constant, V(rad/T m)	9.6	7.6	5.8	4.1	1.7
Loss coefficient, α (cm ⁻¹)	0.0017	—	0.0016	—	—
Index of refraction, n	1.5267	1.5228	1.5187	1.5151	1.5067

	Wavelength (nm)				
Schott SF 6	435.8	480.0	546.1	632.8	1060
Verdet constant, V(rad/T m)	48.1	34.9	25	18	6.1
Loss coefficient, α (cm ⁻¹)	0.024	0.008	0.002	—	—
Index of refraction, n	1.8470	1.8297	1.8126	1.7988	1.7738

	Wavelength (nm)				
Schott SF 57	435.8	480.0	546.1	632.8	1060
Verdet constant, V(rad/T m)	52.4	39.6	29	20	6.7
Loss coefficient, (cm ⁻¹)	0.0205	—	0.002	0.002	0.002
Index of refraction, n	1.8939	1.8742	1.8550	1.8396	1.8118

	Wavelength (nm)				
Schott SF 59	435.8	480.0	546.1	632.8	1060
Verdet constant, V(rad/T m)	69.8	—	37.2	25.9	8.1
Loss coefficient, α (cm ⁻¹)	—	—	—	—	—
Index of refraction, n	2.0156	1.9890	1.9635	1.9432	1.9078

	Wavelength (nm)				
As ₂ S ₃	435.8	480.0	546.1	632.8	1060
Verdet constant, V(rad/T m)	86.7	56.4	38.7	19	13
Loss coefficient, α (cm ⁻¹)	—	—	—	—	—
Index of refraction, n	2.636	2.562	2.521	2.465	2.448

* Schott glass designations. Similar glasses are available from other sources.

Paramagnetic Glasses

Data from manufacturer's data sheets.

	Wavelength (nm)			
	325	442	632.8	1064
Hoya FR 4 (discontinued)				
Verdet constant, V(rad/T m)	—	-82.6	-30.5	-8.4
Loss coefficient, α (cm $^{-1}$)	—		0.00597	0.0054
Index of refraction, n	—	1.584	1.570	1.561
Hoya FR 5	Wavelength (nm)			
	325	442	632.8	1064
Verdet constant, V(rad/T m)	-444	-174	-71.0	-20.6
Loss coefficient, α (cm $^{-1}$)	—	—	0.0291	0.0086
Index of refraction, n	1.731	1.701	1.684	1.673
Hoya FR 7	Wavelength (nm)			
	325	442	632.8	1064
Verdet constant, V(rad/T m)	—	-82.3	-34.9	-9.6
Loss coefficient, α (cm $^{-1}$)	—	—	—	—
Index of refraction, n	—	1.540	1.530	1.524
Kigre M-18	Wavelength (nm)			
	543.1	632.8	830.0	1064
Verdet constant, V(rad/T m)	-103	-70.9	-37.9	-21.3
Loss coefficient, α (cm $^{-1}$)	—	—	—	—
Index of refraction, n	—	1.6845 (n _D)	—	1.664
Verdet constant relative to FR 5 measured at 21.7 rad/T m.				
Kigre M-24	Wavelength (nm)			
	532	1064		
Verdet constant, V(rad/T m)	-87	-26		
Loss coefficient, α (cm $^{-1}$)	—	—		
Index of refraction, n	1.701 (n _D)	1.687		
Kigre M-32	Wavelength (nm)			
	532	1064		
Verdet constant, V(rad/T m)	-98	-29		
Loss coefficient, α (cm $^{-1}$)	—	—		
Index of refraction, n	1.727 (n _D)	1.713		

O-I EY-1 (discontinued)	Wavelength (nm)			
	325	442	632.8	1064
Verdet constant, V(rad/T m)	-273	-98.0	-41.9	-11.9
Loss coefficient, α (cm ⁻¹)	—	—	—	<0.005
Index of refraction, n	1.665	1.639	1.624	1.615

O-I EY-2 (discontinued)	Wavelength (nm)			
	325	442	632.8	1064
Verdet constant, V(rad/T m)	—	—	—	-11
Loss coefficient, α (cm ⁻¹)	—	—	—	<0.010
Index of refraction, n	—	—	—	1.607

Optical Properties of Paramagnetic Faraday Rotator Glasses

Glass type	Transmission range (μm)	Refractive index n _D	Abbe number v _D	dn/dT (10 ⁻⁶ /K)	Nonlinear index n ₂ calc. (10 ⁻¹³ esu)
FR-4	~0.4–2.0	1.5732	58.0	2.8	1.59
FR-5	~0.4–1.5*	1.6864	53.5	7.5	2.45
FR-7	~0.4–1.5*	1.5316	74.9	—	0.95
M-18	~0.4–1.5*	1.682	48.8	7.5	2.7
M-24	~0.4–1.5*	1.701	52.0	—	2.6
M-32	~0.4–1.5*	1.727	51.1	—	2.9

* Tb³⁺ absorption line at ~0.54 μm.

Mechanical and Thermal Properties of Paramagnetic Faraday Rotator Glasses

Glass type	Density (g/cm ³)	Young's modulus E (10 ³ N/mm ²)	Poisson's ratio μ	Knoop hardness (N/mm ²)	Thermal expansion (10 ⁻⁶ /°C)	Transform. temp (°C)
FR-4	3.10	65.2	0.244	6020	98	625
FR-5	4.28	108	0.22	7310	47	756
FR-7	4.32	—	—	5070	17.1	398
M-18	4.33	113	0.339	7380	5.63	757
M-24	4.45	121	0.326	7500	5.59	775
M-32	4.85	120	0.306	7930	6.00	774

Data from manufacturers' sheets.

2.11.4 Gradient-Index Glasses

Gradient-index (GRIN) glasses are ones in which the index of refraction varies spatially within the glass. A radial gradient is one that is symmetric about a line; therefore the surfaces of constant index of refraction are cylinders. There are two commonly used mathematical representations for such gradients. The first, used to specify products manufactured by Nippon Sheet Glass, is $N(r) = N_0(1 - Ar^2/2 + h_4r^4 + h_6r^6 + \dots)$; the second is $N(r) = N_{00} + N_{10}r^2 + N_{20}r^4 + \dots$. In both cases, the quadratic coefficient determines the focal length, numerical aperture, and other first-order properties of the lens. The higher-order coefficients determine the image quality.

The tables below present catalog data for Nippon Sheet Glass (NSG) materials and those of Gradient Lens Corporation(GLC) together with calculated maximum numerical aperture (NA) and quarter-pitch length. Other diameters and numerical apertures may be available; the reader should contact the appropriate vendor for current data.

NSG Radial Gradient Lenses (Selfoc)

	SLS	SLS	SLW	SLW	SLW	SLW	SLH
Numerical aperture	0.37	0.37	0.46	0.46	0.46	0.46	0.6
Diameter (mm)	1	2	1	1.8	2	31.8	
Wavelength (μm)	0.63	0.63	0.63	0.63	0.63	0.63	0.634
	2.49E ⁻¹	6.10E ⁻²	3.70E ⁻¹	1.15E ⁻¹	9.24E ⁻²	4.24E ⁻²	1.85E ⁻¹
Square root A	0.499	0.247	0.608	0.339	0.304	0.206	0.43
N_{00}	1.5637	1.5637	1.6075	1.6075	1.6075	1.6075	1.6576
N_{10}	-1.95E ⁻¹	-4.77E ⁻²	-2.97E ⁻¹	-9.24E ⁻²	-7.43E ⁻²	-3.41E ⁻²	-1.53E ⁻¹
ΔN	-4.87E ⁻²	-4.77E ⁻²	-7.43E ⁻²	-7.48E ⁻²	-7.43E ⁻²	-7.67E ⁻²	-1.24E ⁻¹
Index at edge	1.515	1.516	1.5332	1.5326	1.5332	1.5307	1.5334
Quarter-pitch length	3.15	6.36	2.58	4.63	5.17	7.63	3.65

Data from SELFOC Product Guide, NSG America, Inc., Somerset, NJ 08873.

GLC Radial Gradient Lenses (BIG GRINS)

	BG 30	BG 40	BG 50
Numerical aperture	0.19	0.19	0.19
Diameter (mm)	3	4	5
Wavelength (μm)	0.63	0.63	0.63
A	5.78E ⁻³	3.25E ⁻³	2.12E ⁻³
Square root A	0.076	0.057	0.046
N_{00}	1.643	1.643	1.643
N_{10}	-4.74E ⁻³	-2.67E ⁻³	-1.74E ⁻³
ΔN	-1.07E ⁻²	-1.07E ⁻²	-1.09E ⁻²
Index at edge	1.6323	1.6323	1.6321
Quarter-pitch length	20.67	27.56	34.15

Data from Gradient Lens Corporation Data Sheets, Rochester, NY 14608.

Tables from Moore, D. T., Gradient-index materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, 1995), p. 499.

2.11.5 Mirror Substrate Glasses

Properties of Mirror Substrate Glasses

Material (supplier)	Density (g/cm ³)	Thermal expansion coefficient (10 ⁻⁶ /K)	Knoop hardness (kg/mm ²)	Stress-optical coefficient (TPa ⁻¹)
BK 7 (various)	2.51	8.3	520	2.7
fused silica*	2.20	0.55	635	3.5
LE30 (Hoya)	2.58	0.4	657	2.9
Pyrex (Corning)	2.23	3.2	418	3.9
ULE (Corning)	2.21	0.03	460	4.0
Zerodur® (Schott)	2.53	0.10	630	3.0

* For a list of suppliers, see the section on fused silica.

2.11.6 Athermal Glasses

Athermal glass compositions are selected such that the optical path length, defined as the refractive index times the actual geometric distance the light traverses in the glass, is independent of temperature. The change in optical path length ΔW with temperature is

$$\Delta W = s[\alpha(n - 1) + dn/dT]\Delta T = sGT,$$

where s is the actual distance in the glass, α is the coefficient of thermal expansion, n is the refractive index, and T is the temperature. G is the thermo-optical coefficient. For ΔW to approach zero, the gradient of the refractive index as a function of temperature must be negative. Examples of glasses with this property can be found in the FK, PK, PSK, SSK, BaLF, F, TiF, and BaSF families on the glass map. Data for several representative athermal optical and laser glasses are given in the table (see, also, sections 2.2.2 and 2.9.2).

Properties of Athermal Glasses

Glass type	n _d	v _d	Thermal expansion coefficient α (10 ⁻⁶ /K)*	dn/dT (10 ⁻⁶ /K)**
<i>Optical glasses</i>				
Ultran (Schott)	1.5483	74.2	11.9	-6.5
PSK 54 (Schott)	1.5860	64.6	11.9	-7.0
TiF 6 (Schott)	1.6165	31.0	13.9	-6.4
FK 54 (Schott)	1.4370	90.7	14.6	-5.9
ATF4 (Hoya)	1.65376	44.72	12.9	-6.6
<i>Nd-doped laser glasses</i>				
LHG-8 (Hoya)	1.530	66.5	11.2	-5.3
Q-98 (Kigre)	1.555	63.6	9.9	-4.5
LG-760 (Schott)	1.519	69.2	12.5	-6.8
LG-810 (Schott)	1.537	67.7	14.5	-7.7

* -30 – +70°C; ** +20 – +40°C

2.11.7 Acoustooptic Glasses

Acoustic waves create a time-varying refractive index grating in a material via the photoelastic effect. The grating spacing is equal to the acoustic wavelength; the grating depth is determined by the drive power of the transducer. A light beam traversing the medium is deflected by the grating at the Bragg angle Θ_B from the normal to the sound propagation direction given by

$$\sin \Theta_B = (1/2)\lambda/\Lambda,$$

where λ and Λ are the wavelengths of the light and sound beams. The diffraction efficiency for a transducer of height H and interaction length L is

$$I/I_0 = (\pi^2/2)(L/H)(n^6 p^2/vn^3)P_a/\lambda^2$$

where P_a is the acoustic power, p is the photoelastic constant, ρ is the density, and v is the sound velocity. Thus an acoustooptic material, in addition to having low losses at the acoustic and optical wavelengths, should also have a large index of refraction and small sound velocity.

A figure of merit for an acoustooptic material is $M = n^6 p^2 / \rho v^3$. Properties and figures of merit for several glasses are compared below.

Properties of Acoustooptic Glasses						
Glass	Transmission range (μm)	Acoustic wave polar.	Sound velocity (km/sec)	Optical wave polar.	Refract. index (632.8 nm)	Relative merit ^(a)
fused silica (SiO_2)	0.2–4.0	long.	5.96	\perp	1.46	1.0
lead silicate (Schott SF 4)	0.38–1.8	long.	3.63	\perp	1.62	3.0
lead silicate (Schott SF 59)	0.46–2.5	long.	3.20	\parallel or \perp	1.95	12.6
tellurite (Hoya AOT 5)	0.47–2.7	long. shear	3.40 1.96	\perp \parallel or \perp	2.090	23.9
tellurite (Hoya AOT 44B)	0.43–2.5	long.	3.33	\parallel	1.971	20.9
arsenic trisulfide (As_2S_3)	0.6–11	long.	2.6	\parallel	2.61	256
$\text{Ge}_{55}\text{As}_{12}\text{S}_{33}$	1.0–14	2.52	2.52	\perp		54

(a) Figure of merit relative to that of SiO_2 .

Data from Gottlieb, M., Elastooptic materials, *Handbook of Laser Science and Technology*, Vol. 4 (CRC Press, Boca Raton, FL, 1986), p. 319.

2.11.8 Abnormal Dispersion Glass

Various relative partial dispersions


$$P_{x,y} = (n_x - n_y)/(n_F - n_C)$$

are defined for other wavelengths x and y. The relative partial dispersion of most glasses obeyed a linear relationship on v_d of the form

$$P_{x,y} \approx a_{xy} + b_{xy} v_d ,$$

where a and b are constants. It is not possible to correct for second-order chromatic aberrations using so-called “normal” glasses that satisfy this equation. Because of the linear relationship between the relative partial dispersions and Abbe number, the difference in partial dispersions will always be the same for normal glasses.

Correction for second-order chromatic aberration (secondary spectrum) is accomplished using glasses with equal partial dispersions for different Abbe values (the corrected systems are called apochromats). These abnormal dispersion glasses depart from the “normal line” and the linear relationship above. The relative dispersion $(n_g - n_F)/(n_F - n_C)$ of optical glasses is plotted in the figure below and shows the magnitude of the deviations from the normal line that are possible. The deviations can be either positive or negative. Optical glass catalogs list deviations of the relative partial dispersions from the normal for glasses covering a wide range of v_d values.



Deviation of the relative partial dispersion $P_{g,f}$ of optical glasses from the normal line (Schott Optical Glass Catalog).

Section 3: Polymeric Materials

- 3.1 Optical Plastics
- 3.2 Index of Refraction
- 3.3 Nonlinear Optical Properties
- 3.4 Thermal Properties
- 3.5 Engineering Data

Section 3

POLYMERIC MATERIALS

Of the large number of known polymers, several exhibit useful optical properties. Various properties of optical plastics are compared with those of glasses below. The documentation of optical properties and the accuracy of data on plastics are generally not comparable to that of optical glasses. In addition, mechanical and chemical resistance properties should be checked with the material supplier because they may vary widely within a polymer group. Numerous caveats about the use and application of plastics in optical systems are noted in reference 1.

Property	Plastic	Glass
Optical		
Refractive index (n_d)	1.31–1.65	1.28–1.95
Abbe number (v_d)	92–20	91–20
Index homogeneity	$\pm 1 \times 10^{-4}$	$\pm 1 \times 10^{-6}$
Index change with temperature (10^{-6} K^{-1})	−143 to −100	−8.5 to 6.0
Birefringence (nm/cm)	60–80,000	5
Transmission range (nm)	200–2500	150–3500
Mechanical		
Density (g/cm^3)	0.83–1.46	2.3–6.3
Young modulus ($10^3 \text{ N}/\text{mm}^2$)	1–10	46–129
Poisson's ratio		0.192–0.309
Thermal		
Expansion coefficient (10^{-6} K^{-1})	25–130	3.7–14.6
Heat capacity ($\text{J g}^{-1} \text{ K}^{-1}$)	1–2	0.31–0.89
Thermal conductivity ($\text{W m}^{-1} \text{ K}^{-1}$)	0.1–0.3	0.51–1.28
Softening temperature (°C)	360–430	750–1100

From Cook, L. M. and Stokowski, S. E., Filter materials, *Handbook of Laser Science and Technology, Volume IV: Optical Materials, Part 2* (CRC Press, Boca Raton, FL, 1995), p. 151.

Common optical plastics include:

- polymethyl methacrylate (PMMA) (acrylic)
- polystyrene (styrene) (PS)
- methyl methacrylate styrene copolymer (NAS)
- styrene acrylonitrile (SAN), acrylic/styrene copolymer
- polycarbonate (PC)
- polymethylpentene (TPX)
- acrylonitrile, butadiene, and styrene terpolymer (ABS)
- nylon, amorphous polyamide
- polyetherimide (PEI)
- polysulfone
- allyl diglycol carbonate (CR-39)
- Telfon (Telfon AF®) (TPFE), fluorinated-(ethylenic-cyclo oxyaliphatic substituted ethylenic) copolymer

In the following tables properties of these and other optical plastics are given in order of decreasing index of refraction.

3.1 Optical Plastics

Properties of Optical Plastics—I


Polymer	Trade name	Manufacturer	Density (g/cm ³)	Index <i>n_D</i>	Abbe <i>v_D</i>
Polyetherimide (PEI)	Ultem	G.E. Plastics	1.27	1.658	
Polyarylsulfone	Radel	Amoco Performance	1.37	1.651	
Polyurethane	Isoplast 301	Dow	1.2	1.64–1.65	
Polysulfone	Udel P-1700	Amoco Performance	1.24	1.633	22.5
Polyarylate	Durel 400	Hoecsht Celanese	1.21	1.61	
	Ardel D-100	Amoco Performance	1.21	1.61	
Poly α -methylstyrene	Resin 18	Amoco Chemical	1.075	1.61	
Polyamide, amorphous nylon	Durethan T40	Miles Inc.	1.185	1.590	
Aliphatic/aromatic		(Bayer AG)			
Polystyrene (PS)	Styron	Dow	1.06	1.589	31
Polyamide, amorphous nylon	Zytel 330	DuPont	1.18	1.588	
Polycarbonate (PC)	Calibre	Dow	1.20	1.586	30
	Lexan	G.E. Plastics	1.20	1.586	30.3
	Makrolon	Miles Inc.	1.2	1.586	30
Polystyrene co-maleic anhydride (SMA)	Dylark 232	Arco	1.08	1.586	31.8
Modified polyestercarbonate	Lexan SP	G.E. Plastics	1.18	1.582	
Polystyrene-butadiene copolymer	K Resin	Phillips 66	1.01	1.571	
Polystyrene-coacrylonitrile (SAN)	Lustran	Monsanto	1.07	1.57	35.3
	Lustran Sparkle	Monsanto	1.07	1.57	
	Tyril 990	Dow	1.07	1.57	
Polyester (PETG)	Kodar 6763	Eastman	1.27	1.567	
Polyamide, amorphous (nylon type 6/3)	Trogamid T	Huls-America	1.12	1.566	
Polystyrene co-methylmethacrylate (2:1) (SMMA)	NAS 30	Novacor	1.09	1.564	35
Epoxy casting resin	OS-4000	Dexter Corp. (Hysol)	A = 1.15 B = 1.22	A = 1.563 B = 1.565	
Amorphous polyolefin from dicyclopentadiene	APO	Mitsui Petrochem.	1.05	1.54	
Acrylonitrile-butadiene-styrene terpolymer (ABS)	Cycolac CTBZ	G.E. Plastics	1.07	1.536	35
Polyamide, amorphous (nylon type 12)	Grilamid	EMS-America-Grilon	1.06	1.535	
Polystyrene co-methylmethacrylate (1:2) (SMMA)	NAS-55	Novacor	1.13	1.535	41.15
Amorphous polyolefin (APO)	ZEONEX	Zeon Chemicals	1.01	1.528	55.7

Properties of optical plastics—I—continued

Polymer	Trade name	Manufacturer	Density (g/cm ³)	Index n _D	Abbe v _D
Dicyclopolyolefin	Telene	B F Goodrich	1.0	1.528	55.3
Epoxy molding compound	MG-18	Dexter Corp. (Hysol)	1.35	1.52	
Tricyclodecyl co-methacrylate (TCDMA)	OZ-1000	Hitachi Chemical	1.16	1.500	57
Low moisture acrylic	WF-201	Mitsubishi Rayon		1.495	58
Allyl diglycol carbonate	CR-39	PPG Industries	1.32	1.498	59.3
Polymethylmethacrylate	Plexiglas	Rohm and Haas	1.19	1.491	57.4
PMMA, acrylic	Acrylite	Cyro	1.19	1.491	57.4
	CP	ICI	1.18	1.491	57.4
	Perspex	ICI	1.18	1.491	57.4
	Shinkolite P	Mitsubishi Rayon	1.19	1.491	57.4
Polymethylmethacrylate impact modified, 20%	MI-7	Rohm and Haas	1.17	1.49	
	DR-G	Rohm and Haas	1.15	1.49	
Poly(4-methylpentene-1)	TPX RT-18	Mitsui Plastics	0.833	1.463	56.3
Cellulose acetate butyrate (CAB)	Tenite	Eastman	1.15–1.2	1.46–1.49	51.9
Fluoropolymer (TPFE)	Teflon AF 1600	DuPont	1.8	1.32	92

Optical Transmission

Optical plastics transmit well in the visible and the near infrared, but absorb strongly in the ultraviolet (fluoropolymers are an exception) and throughout the infrared. Most plastics degrade somewhat both in physical and optical properties when exposed to ultraviolet radiation.



Transmission spectra of optical plastics. sample thickness: 3.2 mm.

Properties of Optical Plastics-II

Polymer	Relative haze ^a	Hue ^b	Deflect. ^c temp. (°C)	Comments
Polyetherimide (PEI)	light	amber	200	Good thermal/chemical resistance, high color but good in near IR
Polyarylsulfone	light	yellow	204	Tough
Polyurethane	light	colorless	88	Can be custom tailored, good chemical resistance
Polysulfone	light	yellow	174	Good thermal and moisture stability, high temperature
Polyarylate	noticeable	light straw	158	High temperature, good UV resistance
Poly α -methylstyrene	slight	colorless	n/a	Brittle, can be modifier for K resin
Polyamide, amorphous nylon	slight	light straw	110	Tough, hard
Polystyrene (PS)	low	colorless	82110	Low haze grades available
Polyamide, amorphous nylon	noticeable	colorless	123	Good abrasion resistance, moisture sensitive
Polycarbonate (PC)	slight	light straw	123129	Very tough, high impact
Polystyrene co-maleic anhydride (SMA)	slight	colorless	96	Brittle
Modified polyestercarbonate	slight	light straw	107	Processes at lower temperature
Polystyrene-butadiene copolymer	noticeable	light straw	76	Tough
Polystyrene-coacrylonitrile δ 8 (SAN)	slight	light straw	93104	Tougher than polystyrene
Polyester (PETG)	slight	light straw	70	Film extruding
Polyamide, amorphous (nylon type 6/3)	noticeable	straw	124	Good abrasion resistance
Polystyrene co-methyl-methacrylate (2:1) (SMMA)	slight	colorless	98	Optical quality
Amorphous polyolefin from dicyclopentadiene	n/a	n/a	$T_g = 141$	Optical quality, very low moisture
Acrylonitrile-butadiene-styrene terpolymer (ABS)	noticeable	yellow	79	Tough
Polyamide, amorphous (nylon type 12)	noticeable	straw	150	Good abrasion resistance
Polystyrene co-methyl-ethacrylate (1:2) (SMMA)	slight	colorless	99	Optical quality
Amorphous polyolefin (APO)	slight	light straw	123	Optical quality
Dicyclopolyolefin	slight	light straw	107	Very low moisture (0.01%)
Epoxy molding compound	slight	colorless	120	Semiconductor embedment
Epoxy casting resin			$T_g = 110$	Two-part casting resin
Tricyclodecyl co-methacrylate (TCDMA)	low	colorless		Lower moisture than PMMA (1.2%)
Low moisture acrylic	slighth	light straw	103	Optical quality
Allyl diglycol carbonate	low	light straw	91 55–65	Cast thermoset, hard Ophthalmic use

Properties of optical plastics-II—continued

Polymer	Relative haze ^a	Hue ^b	Deflect. ^c temp. (°C)	Comments
Polymethylmethacrylate PMMA, acrylic	low to slight	light straw to colorless	72–102	Optical quality, hard, widely used, scratch resistant
Impact modified, 20%	light	colorless	85	Tougher than PMMA
Impact modified, 40%	light	colorless	79	Tough, will creep with mild force
Poly(4-methylpentene-1)	slight	colorless	90 at 66 psi	Unusual properties, lowest density of all thermoplastics, infrared transmission, very tough
Cellulose acetate butyrate (CAB)	noticeable	light straw	43–88	Tough
Fluoropolymer (TPFE)	noticeable	colorless	154	Very low index of refraction, good ultraviolet transmission.

^aRelative haze estimates: low (<0.7%); slight (to 1.5 %); light (to 3%); noticeable (>3%).

^bHue (yellowness) estimates: colorless, light straw, straw, yellow, amber.

^cHeat deflection temperature at 264 psi.

The above tables are from D. Keyes, Optical plastics, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), pp. 85–94.

Loss Contributions (in dB/km) for PS, PMMA, and PMMA-d8 Core Fibers

Core material	PS				PMMA				PMMA-d8	
	552	580	624	672	518	567	650	680	780	850
Wavelength (nm)										
Total loss	162	138	129	114	57	55	128	20	25	50
Absorption	0	4	22	24	1	7	88	0	9	36
Electronic transition tail	22	11	4	2	0	0	0	0	0	0
Rayleigh scattering	95	78	58	43	28	20	12	10	6	4
Structural imperfections	45	45	45	45	28	28	28	10	10	10
Loss limit	117	93	84	69	29	27	100	10	15	40

Source: Kaino, T., Fujiki, M., and Jinguji, K., Preparation of plastic optical fibers, *Rev. Electr. Commun. Lab.* 32, 478 (1984).


3.2 Index of Refraction

Index of Refraction of Common Optical Plastics

Wavelength (nm)	PMMA	Poly-styrene	Poly-carb.	SAN	PEI	NAS	TPFE
365.0	1.5136	1.6431	1.6432	1.6125	—	—	—
404.7	1.5066	1.6253	1.6224	1.5971	—	—	—
435.8	1.5026	1.6154	1.6115	1.5886	—	—	—
480.0	1.4983	1.6052	1.6007	1.5800	1.687	—	—
486.1	1.4978	1.6041	1.5994	1.5790	—	1.574	—
546.1	1.4938	1.5950	1.5901	1.5713	1.668	—	—
587.6	1.4918	1.5905	1.5855	1.5674	1.660	—	—
589.3	1.4917	1.5903	1.5853	1.5673		10564	1.31
643.9	1.4896	1.5858	1.5807	1.5634	1.651	—	—
656.3	1.4892	1.5849	1.5799	1.5627	—	1.558	—
706.5	1.4878	1.5820	1.5768	1.5601	—	—	—
852.1	1.4850	1.5762	1.5710	1.5551	—	—	—
1014.0	1.4831	1.5726	1.5672	1.5519	—	—	—
Abbe number	57.4	30.9	29.9	34.8	18.3	34.7	92

Adapted from a table of J. D. Lytle, *Handbook of Optics*, Vol. II (McGraw-Hill, New York, 1995), Chapter 34 (with additions).

Being carbon-based materials, the index of refraction and dispersion of polymers differ significantly from those of glasses and crystals. The locations of optical plastics relative to optical glasses are shown in the refractive index–Abbe number diagram below.



3.3 Nonlinear Optical Properties

Abbreviations	Material
3-BCMUr	Red form of poly-3-BCMU
3-DDCTP	Poly(3-dodecythiophene)
4-BCMUr	Red form of poly-4-BCMU
4-BCMUy	Yellow form of poly-4-BCMU
AO	Acridine orange
AY	Acridine yellow
BBB	Poly(6,9-dihydro-6,9-dioxobisbenzimidazo[2,1b:1',2'j]benzo[1mn] [3,8]phenanthroline-3,12-diyl)
BBL	Poly{(7-oxo-7,10H-benz[de]imidazo[4',5':5,6]benzimidazo[2,1-a]isoquinoline 3,4:10,11-tetrayl)-10-carbonyl}
BBPEN	Bis[n-butyl, 2-phenyl-1,2-ethenedithiolato(2-)S,S] nickel
BSQ	1,3-Bis(4'-N,N-dibutylamino-2'-hydroxyphenyl)-cyclobutene-2,4-dione
DCV	4-N,N-Diethylamino-4'-b,b-dicyanovinyl (azobenzene)
DEANS	4-Diethylamino-4'-nitrostilbene
DNBA	4-Nitrobenzylideny (4'-N,N-dimethylaminoanilide)
DNTA	4-Nitrophenylideny (4'-N,N-dimethylaminoanilide)
DR1	Disperse red 1
ISQ	1,3-Bis(3',3'-dimethyl-2'-indoleninyldenyl)-cyclobutene-2,4-dione
LTFPG	Lead-tin fluorophosphate glass
MDCB	m-Dicyanobenzene
MDNB	m-Dinitrobenzene
Mg:OPTAP	Magnesium octaphenyl tetra-azaporphyrin
MNA	2-Methyl-4-nitroaniline
MV757	MV757 commercial epoxy resin
NFAI	5-Nitro(2-furanacroleindenyl (4'-N,N-dimethylaminoanilide)
NPCV	4-N,N-Dibutylamino-4'-(b-cyano-b-(4-nitrophenyl) vinyl) (azobenzene)
OMPS	Poly(n-octylmethylpolysilane)
PBT	Poly-p-phenylenebenzobisthiazole
PC	Polycarbonate
PDES	Polydiethynylsilane
PDTT	Polydithieno(3,2-b,2',3'-b)thiophene
PMMA	Poly(methyl) methacrylate
PPMS	Polyphenylmethylsilane
PPV	Poly (p-phenylene vinylene)
PS	Polysilane
PT	Polythiophene
PTS	Bis-(p-toluene sulfonate) of 2,4-hexadiyne-1,6 diol (polydiacetylene)
PTS-PDA	Single crystal poly PTS polydiacetylene
PVK	Poly-N-ninyl carbazole
rB	Rhodamine B
SiNc	Silicon naphthalocyanine
SiPc	Silicon phthalocyanine
TCDU:	Bis-(phenylurethane) of 5,7-dodecadiyne-1,2-diol (polydiacetylene)
TCV	4-N,N-Diethylamino-4'-tricyanovinyl (azobenzene)
TNF	2,4,7-Trinitrofluorenone
TPO-N	Thiophene oligomer with N units

Bulk Two-Photon Absorption Coefficients

Material	Excitation duration(ns)	Applied two-photon energy (eV)	Two-photon cross section (cm/GW)	Ref.	Additional information
3-BCMU	0.033	2.33	0.52	33	Benzene chloride 2.3% blue gel
4-BCMU	0.033	2.33	0.76	33	Benzene chloride 1.7% red gel
4-BCMU	0.033	2.33	<0.1	33	14% yellow form solution in DMF
4-BCMU	0.06	1.88	<0.25	34	Polymer waveguide
PPV	0.00006	4	6.8	35	PPV in silica sol-gel
PTS	0.015	2.28	28	36	Pump @1.17 eV
PTS	0.015	2.55	300	36	Pump @1.17 eV
PTS	0.015	2.78	500	36	Pump @1.17 eV
PTS	0.015	2.96	900	36	Pump @1.17 eV
TCDU	0.015	2.2	1	36	Pump @0.81 eV
TCDU	0.015	2.3	14	36	Pump @1.17 eV
TCDU	0.015	2.4	3	36	Pump @0.81 eV
TCDU	0.015	2.6	6.4	36	Pump @0.81 eV
TCDU	0.015	2.6	54	36	Pump @1.17 eV
TCDU	0.015	2.9	80	36	Pump @1.17 eV

From Garito, A. E. and Kuzyk, M. G., Two-photon absorption: organic materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 329.

Techniques for Measuring Nonlinear Refraction

Abbreviation	Method	Ref.
DFWM	Degenerate four-wave mixing	1
KE	DC Kerr effect	2
MSI	Modified Sagnac interferometry	3
OKE	Optical Kerr effect	4
SA	Saturated absorption	5
TBC	Two-beam coupling	5
TRI	Time-resolved interferometry	6

All measurements in the following tables were made at room temperature.

Nonlinear Refraction Data for Polymers

Material	Meth.	Pulse duration (ns)	Wave-length (nm)	Linear index n	$\chi_{1111}^{(3)}$ (10^{-12} cm 3 /erg)	$\chi_{1111}^{(3)} - \chi_{1122}^{(3)}$ (10^{-12} cm 3 /erg)	Ref.
3-DDCTP	DFWM	0.0004	620		330		7
3-DDCTP	DFWM	0.00006	620		55		7
3-DDCTP ^a	DFWM	0.00035	590	1.585	450		8
3-DDCTP ^a	DFWM	0.00035	602	1.585	330		8
3-DDCTP ^a	DFWM	0.00035	705	1.585	40		8
3-DDCTP ^b	DFWM	0.00035	590	1.61	700		8
3-DDCTP ^b	DFWM	0.00035	602	1.61	500		8
3-DDCTP ^b	DFWM	0.00035	705	1.61	40		8
4-BCMU _r	DFWM	0.0005	605		400		9
4-BCMU _y	DFWM	0.0005	605		25		9
4-BCMU _y	DFWM	0.033	1064			$\chi_{1212}^{(3)} = 1.4$	10
4-BCMU _y	DFWM	0.033	1064			$\chi_{1212}^{(3)} = 9.0$	10
4-BCMU _y	DFWM	0.033	1064			$\chi_{1212}^{(3)} = 13$	10
BBB	DFWM	0.035	1064		5.5	3.7	11
BBL	DFWM	0.025	532		2000	1300	11
BBL	DFWM	0.035	1064		15	10	11
BBL ^c	DFWM	0.035	1064		20	13	11
OMP ^S	DFWM	10	532		2.9		12
PBT	DFWM	0.0005	585–604		9		13
PDES	DFWM	0.00009	620		3000		14
PDTT	DFWM	0.008	530	2	11,400		15
PDTT	DFWM	0.008	585	2	7,700		15
PDTT	DFWM	0.008	605	2	5,500		15
PDTT	DFWM	0.008	630	2	1,300		15
PDTT	DFWM	0.008	1060	2	30		15
Poly(4-BCMU)	TRI	0.06	1319		0.456		16
PPMS	OKE	0.003	1060,532		2.0		17
PS	OKE	0.008	1060,532		2		18
PT	DFWM	0.008	530	2	6,680		15
PT	DFWM	0.008	585	2	5,000		15
PT	DFWM	0.008	605	2	3,000		15
PT	DFWM	0.008	630	2	700		15
PT	DFWM	0.008	1060	2	30		15
PTS-PDA	DFWM	0.006	651.5	3	9,000		19
PTS-PDA	DFWM	0.006	661	3	7,275		19
PTS-PDA	DFWM	0.006	671	3	2,317		19
PTS-PDA	DFWM	0.006	681	3	1,025		19
PTS-PDA	DFWM	0.006	691	3	380		19
PTS-PDA	DFWM	0.006	701.5	3	500		19
PTS-PDA	MSI	0.06	1060	3	1250		3
PTS-PDA ^a	TRI	0.1	1060	3	6840		20
TPO-1	DFWM	0.0004	602	1.529	0.14		21
TPO-2	DFWM	0.0004	602		0.50		21
TPO-3	DFWM	0.0004	602	1.562	2.6		21
TPO-4	DFWM	0.0004	602	1.581	11		21
TPO-5	DFWM	0.0004	602	1.600	30		21
TPO-6	DFWM	0.0004	602	1.623	100		21

^a Chemically prepared; ^b Electrochemically prepared; ^c Electrochemically doped; ^d Single crystal waveguides.

Nonlinear Refraction Data for Solid Solutions and Copolymers

Dye	Host	Dye density (10^{22} cm $^{-3}$)	Meth.	Pulse (ns)	Wave-length (nm)	Linear index	$\chi_{1111}^{(3)}$ (10^{-12} cm 3 /erg)	Ref.
AO	LTFPG	0.00008	SA	15,000	514	1.77	3×10^{10}	22
AO	LTFPG	0.00008	TBC	15,000	514	1.77	4×10^{10}	22
AY	LTFPG	0.000077	SA	15,000	514	1.77	6×10^{10}	22
AY	LTFPG	0.000077	TBC	15,000	514	1.77	2×10^{10}	22
BBPEN	PMMA	saturation	DFWM	0.1	1064	1.49	29.9	23
BEPEN	PMMA	saturation	DFWM	0.1	1064	1.49	131	23
BSQ	PMMA	0.0028	MSI ^b	0.06	1064	1.48	2.8	24
BSQ	PMMA	0.0028	KE	8 kHz	799	1.5	0.97 ^a	25
DCV	PMMA	0.0148	KE	8 kHz	632.8	1.5	1.8 ^a	26
DCV	PMMA	0.0148	KE	8 kHz	676	1.5	0.53 ^a	26
DCV	PMMA	0.0148	KE	8 kHz	799	1.5	0.156 ^a	26
DEANS	PC	17	KE	500 Hz	597		6	27
DNBA	PMMA	0.0137	KE	8 kHz	632.8	1.5	0.093 ^a	26
DNTA	PMMA	0.0276	KE	8 kHz	632.8	1.5	0.282 ^a	26
DR1	PMMA	0.01	KE	8 kHz	632.8	1.5	0.23 ^a	26
DR1	PMMA	0.0244	KE	8 kHz	632.8	1.5	0.51 ^a	26
DR1	PMMA	0.04	KE	8 kHz	632.8	1.5	0.84 ^a	26
ISQ	PMMA	0.0019	KE	8 kHz	479	1.5	0.263 ^a	26
ISQ	PMMA	0.0019	KE	8 kHz	570	1.5	0.341 ^a	26
ISQ	PMMA	0.0019	KE	8 kHz	632.8	1.5	0.155 ^a	26
ISQ	PMMA	0.0019	KE	8 kHz	680	1.5	0.418 ^a	26
ISQ	PMMA	0.0019	KE	8 kHz	799	1.5	0.387 ^a	26
MDCB	PMMA	0.109	KE	8 kHz	632.8	1.5	0.0274 ^a	26
MDNB	PMMA	0.124	KE	8 kHz	632.8	1.5	0.0205 ^a	26
Mg:OPTAP	PMMA	5 wt%	DFWM	0.001	598	1.48	11.7	28
MNA	PMMA	0.143	OKE ^b		1064	1.5	2.08	29
NFAI	PMMA	0.0240	KE	8 kHz	632.8	1.5	0.471 ^a	26
NPCV	PMMA	0.0119	KE	8 kHz	632.8	1.5	0.315 ^a	26
PPV	Sol-gel silica	1:1 by weight	DFWM	0.00006	620		45	30
PPV	Sol-gel silica	1:1 by weight	DFWM	0.0004	608		91	30
PPV	Sol-gel silica	1:1 by weight	OKE	0.00006	620		38	30
rB	MV757	0.0077 M/l	DFWM	0.00035	595	1.81	10.7	31
SiNc	PMMA	30 wt%	DFWM	0.001	598	1.434	20.9	28
SiPc ^c	PMMA	10 wt%	DFWM	0.001	598	1.42	94	28
TCV	PMMA	0.0218	KE	8 kHz	632.8	1.5	3.9 ^a	26
TNF	PVK	1:2 molar ratio	DFWM	0.002	602		20	32
TNF	PVK	1:4 molar ratio	DFWM	0.002	602		12	32
TNF	PVK	1:8 molar ratio	DFWM	0.002	602		7.4	32
TNF	PVK	1:16 molar ratio	DFWM	0.002	602		3.4	32
TNF	PVK	1:32 molar ratio	DFWM	0.002	602		2.0	32

^a Assumes $\chi_{1111}^{(3)} = 3 \chi_{1133}^{(3)}$. ^b Waveguide measurement; ^c Copolymer.

From Garito, A. E. And Kuzyk, M. G., Nonlinear refractive index: organic materials, *Handbook of Laser Science and Technology, Suppl. 2* (CRC Press, Boca Raton, FL 1995), p. 289.

References:

1. Friberg, S. R., and Smith, P. W., Nonlinear optical glasses for ultrafast optical switches, *IEEE J. Quantum Electron.* QE-23, 2089 (1987).
2. Hellwarth, R. W., and George, N., Nonlinear refractive indices of CS₂-CCl₄ mixtures, *Opt. Electron.* 1, 213 (1969).
3. Gabriel, M. C., Whitaker, Jr., N. A., Dirk, C. W., Kuzyk, M. G., and Thakur, M., Measurement of ultrafast optical nonlinearities using a modified Sagnac Interferometer, *Opt. Lett.* 16 (17), 1334 (1991).
4. Ho, P. P., and Alfano, R. R., Optical Kerr effect in liquids, *Phys. Rev. A* 20(5), 2170 (1979).
5. Tompkin, W. R., Boyd, R. W., Hall, D. W., Tick, P. A., *J. Opt. Soc. Am. B* 4 (6), 1030 (1987).
6. Milam, D., and Weber, M. J., Measurement of nonlinear refractive-index coefficients using time-resolved interferometry: application to optical materials for high-power neodymium laser, *J. Appl. Phys.* 47(6), 2497 (1976).
7. Pang, Y., and Prasad, P. N., Photoinduced processes and resonant third-order nonlinearity in poly(3-dodecylthiophene) studied by femtosecond time resolved degenerate four wave mixing, *J. Chem. Phys.* 93(4), 2201 (1990).
8. Singh, B. P., Samoc, M., Nalwa, H. S., and Prasad, P. N., Resonant third-order nonlinear optical properties of poly(3-dodecylthiophene), *J. Chem. Phys.* 92 (5), 2756 (1990).
9. Rao, D. N., Chopra, P., Goshal, S. K., Swiatkiewicz, J., and Prasad, P. N., Third-order nonlinear optical interaction and conformational transition in poly-4-BCMU polydiacetylene studied by picosecond and subpicosecond degenerate four wave mixing, *J. Chem. Phys.* 84(12), 7049 (1986).
10. Nunzi, J. M., and Grec, D., Picosecond phase conjugation in polydiacetylene gels, *J. Appl. Phys.* 62(6), 2198 (1987).
11. Lindle, J. R., Bartoli, F. J., Hoffman, C. A., Kim, O.-K., Lee, Y. S., Shirk, J. S., and Kafafi, Z. H., Nonlinear optical properties of benzimidazobenzophenanthroline type ladder polymers, *Appl. Phys. Lett.* 56(8), 712 (1990).
12. McGraw, D. J., Siegman, A. E., Wallraff, G. M., and Miller, R. D., Resolution of the nuclear and electronic contributions to the optical nonlinearity in polysilanes, *Appl. Phys. Lett.* 54(18), 1713 (1989).
13. Rao, D. N., Swiatkiewicz, J., Chopra, P., Ghoshal, S. K., and Prasad, P. N., Third order nonlinear optical interactions in thin films of poly-p-phenylenebenzobisthiazole polymer investigated by picosecond and subpicosecond degenerate four wave mixing, *Appl. Phys. Lett.* 48(18), 1187 (1986).
14. Wong, K. S., Han, S. G., Vardeny, Z. V., Shinar, J., Pang, Y., Ijadi-Maghsoodi, S., Barton, T. J., Grigoras, S., and Parbhoo, B., Femtosecond dynamics of nonlinear optical response in polydiethynylsilane, *Appl. Phys. Lett.* 58(16), 1695 (1991).
15. Dorsinville, R., Yang, L., Alfano, R. R., Zamboni, R., Danieli, R., Ruani, G., and Taliani, C., Nonlinear-optical response of polythiophene films using four-wave mixing techniques, *Opt. Lett.* 14(23), 1321 (1989).
16. Rochford, K., Zanoni, R., Stegeman, G. I., Krug, W., Miao, E., and Beranek, M. W., Measurement of nonlinear refractive index and transmission in polydiacetylene waveguides at 1.319 μm, *Appl. Phys. Lett.* 58(1), 13 (1991).
17. Yang, L., Wang, Q. Z., Ho, P. P., Dorsinville, R., Alfano, R. R., Zou, W. K., and Yang, N. L., Ultrafast time response of optical nonlinearity in polysilane polymers, *Appl. Phys. Lett.* 53(14), 1245 (1988).
18. Yang, L., Dorsinville, R., Wang, Q. Z., Zou, W. K., Ho, P. P., Yang, N. L., and Alfano, R. R., Third-order optical nonlinearity in polycondensed thiophene-based polymers and polysilene polymers, *J. Opt. Soc. Am. B* 6(4), 753 (1989).

19. Carter, G. M., Thakur, M. K., Chen, Y. J., and Hryniecic, J. V., Time and wavelength resolved nonlinear optical spectroscopy of a polydiacetylene in the solid state using picosecond dye laser pulses, *Appl. Phys. Lett.* 47 (5), 457 (1986).
20. Krol, D. M., and Thakur, M., Measurement of the nonlinear refractive index of single-crystal polydiacetylene channel waveguides, *Appl. Phys. Lett.* 56(15), 1406 (1990).
21. Zhao, M.-T., Singh, B. P., and Prasad, P. N., A systematic study of polarizability and microscopic third-order optical nonlinearity in thiophene oligomers, *J. Chem. Phys.* 89 (9), 5535 (1988).
22. Tompkin, W. R., Boyd, R. W., Hall, D. W., Tick, P. A., *J. Opt. Soc. Am. B* 4, 1030 (1987).
23. Winter, C. S., Oliver, S. N., Rush, J. D., Hill, C. A. S., and Underhill, A. E., Large third-order optical nonlinearities of nickel-dithiolene-doped polymethylmethacrylate, *J. Appl. Phys.* 71(1), 512 (1992).
24. Gabriel, M. C., Whitaker, Jr., N. A., Dirk, C. W., Kuzyk, M. G., and Thakur, M., Measurement of ultrafast optical nonlinearities using a modified Sagnac Interferometer, *Opt. Lett.* 16(17), 1334 (1991).
25. Kuzyk, M. G., Paek, U. C., and Dirk, C. W., *Appl. Phys. Lett.* 59(8), 902 (1991).
26. Kuzyk, M. G., Sohn, J. E., and Dirk, C. W., Mechanisms of quadratic electrooptic modulation of dye-doped polymer systems, *J. Opt. Soc. Am. B* 5(5), 842 (1990).
27. Uchiki, H., and Kobayashi, T., New determination method of electro-optic constants and relevant nonlinear susceptibilities and its application to doped polymer, *J. Appl. Phys.* 64(5), 2625 (1988).
28. Norwood, R. A., and Sounik, J. R., Third-order nonlinear-optical response in polymer thin films incorporating porphyrin derivatives, *Appl. Phys. Lett.* 60(3), 295 (1992).
29. Goodwin, M. J., Edge, C., Trundle, C., and Bennion, I., Intensity-dependent birefringence in nonlinear organic polymer waveguides, *J. Opt. Soc. Am. B* 5(2), 419 (1988).
30. Pang, Y., Samoc, M., and Prasad, P. N., Third-order nonlinearity and two-photon-ionduced molecular dynamics: femtosecond time-resolved transient absorption, Kerr gate, and degenerate four-wave mixing studies in poly (*p*-phenylene vinylene)/sol-gel silica film, *J. Chem. Phys.* 94(8), 5282 (1991).
31. Rossi, B., Byrne, H. J., and Blau, W., Degenerate four-wave mixing in rhodamine doped epoxy waveguides, *Appl. Phys. Lett.* 58(16), 1712 (1991).
32. Ghoshal, S. K., Chopra, P. C., Singh, B. P., Swiatkiewicz, J., and Prasad, P. N., Picosecond degenerate four-wave mixing study of nonlinear optical properties of the poly-*N*-vinyl carbazole: 2,4,7-trinitrofluorenone composite polymer photoconductor, *J. Chem. Phys.* 90(9), 5078 (1989).
33. Nunzi, J. M., and Grec, D., Picosecond phase conjugation in polydiacetylene gels, *J. Appl. Phys.* 62(6), 2198 (1987).
34. Rockford, K., Zanoni, R., Stegeman, G. I., Krug, W., Miao, E., and Beranek, M. W., Measurement of nonlinear refractive index and transmission in polydiacetylene waveguides, *Appl. Phys. Lett.* 58(1), 13 (1991).
35. Pang, Y., Samoc, M., and Prasad, P. N., Third-order nonlinearity and two-photon-induced molecular dynamics: femtosecond time-resolved transient absorption, Kerr gate, and degenerate four-wave mixing studies in poly(*p*-phenylene vinylene)/sol-gel silica film, *J. Chem. Phys.* 94(8), 5282 (1991).
36. Lequime, M. and Hermann, J. P., Reversible creation of defects by light in one dimensional conjugated polymers, *Chem. Phys.* 26, 431 (1977).

3.4 Thermal Properties

Thermal Properties of Common Plastics				
Material	Thermal conductivity (W m ⁻¹ K ⁻¹)	Linear thermal expansion (10 ⁻⁵ K ⁻¹)	Refractive index dn/dT (10 ⁻⁴ K ⁻¹)	Maximum service temp. (K)
polymethylmethacrylate	0.16–0.24	3.6–6.5	–1.05	360
polystyrene	0.10–0.13	6.0–8.0	–1.2– –1.4	350
NAS	0.18	5.6–6.5		360
styrene acrylonitrile (SAN)	0.11	6.4–6.7	–1.1	350
polycarbonate	0.19	6.6–7.0	–1.07– –1.43	390
polymethyl pentene (TPX)	0.16	11.7		385
Polyamide (Nylon)	0.2–0.23	8.2		350
Polyarylate	0.28	6.3		
polysulfone	0.11	2.5		430
polystyrene co-butadiene		7.8–12		
Polyallyl diglycol carbonate	0.20	12.0		370
cellulose acetate butyrate	0.16–0.32			
Polyethersulfone	0.13–0.17	5.5		470
Polychloro-trifluoroethylene	0.25	4.7		470
Polyvinylidene fluoride		7.4–13		420
Polyetherimide		5.6		440

From a table of J. D. Lytle, *Handbook of Optics*, Vol. II (McGraw-Hill, New York, 1995), Chapter 34 (with additions).

3.5 Engineering Data

Engineering Data for Transparent Polymers—I						
Generic family	Trade name	Manufacturer	Tensile strength yield psi	Tensile modulus 10 ⁵ , psi	Flexural modulus 10 ⁵ , psi	Impact strength (Izod)
Transparent ABS	Magnum	Dow	7300	3.8	4.2	2
	Cycolac	GE Plastics				
Acrylic (PMMA)	Plexiglas	Rohm & Haas	9400–10800	4.5–4.7	2.5–4.5	0.4–1.2
	CP	ICI				
	Acrylite	CYRO				
Allyl diglycol carbonate	Lucite	Dupont				
	CR-39	PPG	5500	3	2.5–3.3	0.2–0.4
	Cellulosics (acetate, butyrate, propionate)	Tenite	2000–7800	0.6–2.15	1.5–3.4	1.5–7.8
Nylon, amorphous	Zytel 330	Dupont	9800–11000	4.05	3.86	1.8–2.8
	Grilamid	EMS				
	Trogamid T	Huls America				

Engineering Data for Transparent Polymers—I—continued

Generic family	Trade name	Manufacturer	Tensile strength yield psi	Tensile modulus 10^5 , psi	Flexural modulus 10^5 , psi	Impact strength (Izod)
PET	Kodapak	Eastman	8500–10500	4–6	3.5–4.5	0.25–0.7
	Petlon	Miles Inc.				
	Selar	Dupont				
PETG	Kodar	Eastman	7100	2.5	2.9	1.7
Polyarylate	Durel	Hoescht Celanese	9500–10500	2.9–3.05	3.3	4.2–5.5
	Arylon	Dupont				
	Ardel	Amoco				
Polycarbonate		Performance				
	Calibre	Dow	9000–10500	3.4	3.5	14–18
	Markrolon	Miles Inc. (Bayer)				
Polyetherimide	Lexan	GE Plastics				
	Ultem	GE Plastics	15200	4.3	4.8	0.6–1.0
	Lexan PPC	GE Plastics	9500	n/a	2.94–3.38	10
Polyethersulfone	Victrex	ICI	12200	n/a	3.73	1.6
Poly-4-methylpentene-1	TPX	Mitsui Plastics	3000	2	n/a	2.0–3.0
Polyphenylsulfone	Radel	Amoco	10400	3.1	0.124	12
		Performance				
	Styron	Dow	5000–12000	4–5	4–4.7	0.25–0.4
Polystyrene	Polystyrol	BASF				
	Hostyren	Hoescht Celanese				
	Bapolan	Bamberger				
	polystyrene	Chevron				
	polystyrene	Dart, Mobil				
	polystyrene	Amoco, Novacor				
	polystyrene	Huntsman				
Polysulfone	Udel	Amoco	10200	3.6	3.9	1.3
PVC, rigid	Geon	B.F. Goodrich	6000–7700	3.6–3.7	3.6–5	0.5–1.6
	PVC, rigid	Georgia Gulf				
	Oxyblend	Occidental				
	Unichem	Colorite				
Styrene acrylonitrile) (SAN	Tyril	Dow	9000–1200	4–5.6	5–5.5	0.35–0.5
	Lustran	Monsanto				
	Luran	BASF				
	Blendex	GE Plastics				
Styrene butadiene	K Resin	Phillips	4000	1.8	2.4	0.25–0.40
Styrene maleic anhydride	Dylark	Arco	7400	4.4	4.6–4.9	0.4
Styrene methylmethacrylate	NAS	Novacorp	9000	4.5–5.0	3.5–3.9	0.2–0.3
Thermoplastic polyurethane, rigid	Isoplast 301	Dow	9000	2.6	3.4	1.5

Engineering Data for Transparent Polymers-II

Generic family	Trade name	Chemical resistance					
		Aliph. HC	Arom. HC	Conc. base	Dilute base	Conc. inorg. acid	Dilute inorg. acid
Transparent ABS	Magnum Cycolac	F	P	G	G	P	G
Acrylic (PMMA)	Plexiglas CP Acrylite Lucite	G	P	F/P	G	P	G
Allyl diglycol carbonate	CR-39	G	G	G	G	G	G
Cellulosics (acetate, butyrate, propionate)	Tenite	F	P	P	F	P	F
Nylon, amorphous	Zytel 330 Grilamid Trogamid T	EX	EX	G	EX	P	F
PET	Kodapak Petlon Selar	G	P/F	P	F	G/F	G
PETG	Kodar	G	P/F	P	F	G/F	G
Polyarylate	Durel Arylon Ardel	P/F	P	P	N/A	F	G
Polycarbonate	Calibre Markrolon Lexan	F	P	P	P/F	F	G
Polyetherimide	Ultem	EX	EX	N/A	N/A	EX	EX
Polyester (polyphthalate) carbonate	Lexan PPC	F	F/P	P	F	F	G
Polyethersulfone	Victrex	G	F	G	G	G	G
Poly-4-methylpentene-1	TPX	F	P	EX	EX	EX	EX
Polyphenylsulfone	Radel	G	P	G	G	N/A	N/A
Polystyrene	Styron Polystyrol Hostyren Bapolan polystyrene	P	P	G	G	EX	G
Polysulfone	Udel	P/F	P	EX	EX	EX	EX
PVC, rigid	Geon Oxyblend Unichem	G	P	EX	EX	G	EX

Engineering Data for Transparent Polymers-II—continued

Generic family	Trade name	Chemical resistance					
		Aliph. HC	Arom. HC	Conc. base	Dilute base	Conc. inorg. acid	Dilute inorg. acid
Polyarylate	Durel	P/F	P	P	N/A	F	G
	Arylon						
	Ardel						
Polycarbonate	Calibre	F	P	P	P/F	F	G
	Markrolon						
	Lexan						
Polyetherimide	Ultem	EX	EX	N/A	N/A	EX	EX
Polyester (polyphthalate carbonate)	Lexan PPC	F	F/P	P	F	F	G
Polyethersulfone	Victrex	G	F	G	G	G	G
Poly-4-methylpentene-1	TPX	F	P	EX	EX	EX	EX
Polyphenylsulfone	Radel	G	P	G	G	N/A	N/A
Polystyrene	Styron	P	P	G	G	EX	G
	Polystyrol						
	Hostyren						
	Bapolan						
	polystyrene						
Polysulfone	Udel	P/F	P	EX	EX	EX	EX
PVC, rigid	Geon	G	P	EX	EX	G	EX
	PVC, rigid						
	Oxyblend						
	Unichem						
Styrene acrylonitrile (SAN)	Tyril	G	P	G	G	G	G
	Lustran						
	Luran						
	Blendex						
Styrene butadiene	K Resin	P	P	P	F/G	P	F/G
Styrene maleic anhydride (SMA)	Dylark	F/G	P	G	P	F	G
Styrene methylmethacrylate (SMMA)	NAS	F/P	P	F	G	F	G
Thermoplastic polyurethane, rigid	Isoplast 301	EX	EX	EX	EX	F/G	EX

Chemical resistance codes: Aliphatic hydrocarbons; aromatic hydrocarbons; concentrated base; dilute base; concentrated inorganic acid; dilute inorganic acid. Excellent; Good; Fair; Poor.

The above tables are from Keyes, D., Optical plastics, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), pp. 85–94.

Section 4: Metals

- 4.1 Physical Properties of Selected Metals
- 4.2 Optical Properties
- 4.3 Mechanical Properties
- 4.4 Thermal Properties
- 4.5 Mirror Substrate Materials

Section 4

METALS

Metals are used in optical systems as reflective optical components, optical thin films, structural elements, and mirror substrates. For these optical applications only a limited number of metals are useful. The materials and properties included in this section are therefore necessarily selective.

Depending upon the application, various physical, optical, mechanical, and thermal properties are of interest; for example, structural stiffness with low mass, thermal diffusivity to reduce thermal gradients and associated distortions, and smooth surface finish to accept of optical coatings. Thermal, elastic, electrical and magnetic properties may be anisotropic, thus crystal structure is also important.

4.1 Physical Properties of Selected Metals

Metal	Symbol	Crystal structure	Space group	Atomic weight	Density (g/cm ³)
Aluminum	Al	cubic	Fm3m	26.98	2.70
Beryllium	Be	hexagonal	P6 ₃ /mmc	9.01	1.85
Chromium	Cr	cubic	Im3m	52.00	7.15
Copper	Cu	cubic	Fm3m	63.55	8.96
Germanium	Ge	cubic	Fd3m	72.61	5.32
Gold	Au	cubic	Fm3m	196.97	19.3
Iridium	Ir	cubic	Fm3m	192.22	22.5
Iron	Fe	cubic	Im3m	55.85	7.87
Magnesium	Mg	hexagonal	P6 ₃ /mmc	24.30	1.74
Molybdenum	Mo	cubic	Im3m	95.94	10.2
Nickel	Ni	cubic	Fd3m	58.69	8.9
Niobium	Nb	cubic	Im3m	92.91	8.57
Osmium	Os	hexagonal	P6 ₃ /mmc	190.23	22.59
Palladium	Pd	cubic	Fm3m	106.42	12.0
Platinum	Pt	cubic	Fm3m	195.08	21.5
Rhenium	Re	cubic	Fm3m	186.21	20.8
Rhodium	Rh	cubic	Fm3m	102.91	12.4
Silicon	Si	cubic	Fd3m	28.09	2.33
Silver	Ag	cubic	Fm3m	107.87	10.50
Tantalum	Ta	cubic	Im3m	180.95	16.4
Tin	Sn	tetragonal	Fd3m	118.71	7.28
Titanium	Ti	cubic	Im3m	47.88	4.5
Tungsten	W	cubic	Im3m	183.84	19.3
Zinc	Zn	hexagonal	P6 ₃ /mmc	65.39	7.14
Zirconium	Zr	hexagonal	P6 ₃ /mmc	91.22	6.51

Electrical Resistivity of Pure Metals (nohm m)

Temp. (K)	10	20	80	200	300	400	600
Aluminum	0.0010	0.00755	2.45	15.87	27.33	38.7	61.3
Beryllium	0.332	0.336	0.75	12.9	376	67.6	132
Chromium	—	—	—	77	127	158	247
Copper	0.0200	0.0280	2.15	10.46	17.25	24.02	37.92
Gold	0.226	0.35	4.81	14.62	22.71	31.07	48.7
Iron	0.238	0.287	6.93	52.0	99.8	161	329
Molybdenum	0.0089	0.0261	4.82	31.3	55.2	80.2	131
Nickel	0.057	0.140	5.45	36.7	72.0	118	255
Palladium	0.0242	0.0563	1.75	6.88	10.80	14.48	21.2
Platinum	0.154	1.17	19.22	67.7	108	146	219
Silver	0.0115	0.042	2.89	10.29	16.29	22.41	35.3
Tantalum	1.02	1.46	26.2	86.6	135	182	274
Tungsten	0.00137	0.0196	6.06	31.8	54.4	78.3	130
Zinc	0.112	0.387	11.5	38.3	60.6	83.7	134.9
Zirconium	0.253	0.357	6.64	26.3	43.3	60.3	91.5

From the *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12-45. Values of resistivity at other temperatures are given in this reference.

4.2 Optical Properties

The following tables list the index of refraction n , the extinction coefficient k , and the normal incidence reflection $R(\phi = 0)$ as a function of photon energy E expressed in electron volts (eV). The dielectric function $\epsilon = \epsilon_1 + i\epsilon_2$ can be computed from the complex index of refraction $N = n + ik$ using $\epsilon_1 = n^2 - k^2$ and $\epsilon_2 = 2nk$.

The tables are from Weaver, J. H. and Frederikse, H. P. R., Optical properties of selected elements, in *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12-133. The optical constants in these tables are abridged from three more extensive tabulations.¹⁻³ For critical applications the reader should refer to the original work. References for individual metals are listed at the end of the tables. Generally tabulated values for the optical properties are accurate to better than 10%. Data in parentheses are extrapolated or interpolated values. For most elements the spectral range covered is from the far infrared (0.010 or 0.10 eV) to the far ultraviolet (10, 30, or 300 eV). The intervals between successive energies in the tables are chosen in such a way that the major spectral features are preserved.

Tables of n , k , and $R(\phi = 0)$ are given for the following metals:

Aluminum	Iron	Palladium	Tantalum
Chromium	Magnesium	Platinum	Titanium
Copper	Molybdenum	Rhenium	Tungsten
Germanium	Nickel	Rhodium	Zinc
Gold	Niobium	Silicon	Zirconium
Iridium	Osmium	Silver	

Aluminum⁴

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.040	98.595	203.701	0.9923	4.400	0.244	3.380	0.9249
0.050	74.997	172.199	0.9915	4.600	0.223	3.222	0.9249
0.060	62.852	150.799	0.9906	4.800	0.205	3.076	0.9249
0.070	53.790	135.500	0.9899	8.000	0.072	1.663	0.9269
0.080	45.784	123.734	0.9895	8.500	0.063	1.527	0.9272
0.090	39.651	114.102	0.9892	9.000	0.056	1.402	0.9277
0.100	34.464	105.600	0.9889	9.500	0.049	1.286	0.9282
0.125	24.965	89.250	0.9884	10.000	0.044	1.178	0.9286
0.150	18.572	76.960	0.9882	10.500	0.040	1.076	0.9293
0.175	14.274	66.930	0.9879	11.000	0.036	0.979	0.9298
0.200	11.733	59.370	0.9873	11.500	0.033	0.883	0.9283
0.250	8.586	48.235	0.9858	12.000	0.033	0.791	0.9224
0.300	6.759	40.960	0.9844	12.500	0.034	0.700	0.9118
0.350	5.438	35.599	0.9834	13.000	0.038	0.609	0.8960
0.400	4.454	31.485	0.9826	13.500	0.041	0.517	0.8789
0.500	3.072	25.581	0.9817	14.000	0.048	0.417	0.8486
0.600	2.273	21.403	0.9806	14.200	0.053	0.373	0.8312
0.700	1.770	18.328	0.9794	14.400	0.058	0.327	0.8102
0.800	1.444	15.955	0.9778	14.600	0.067	0.273	0.7802
0.900	1.264	14.021	0.9749	14.800	0.086	0.211	0.7202
1.000	1.212	12.464	0.9697	15.000	0.125	0.153	0.6119
1.100	1.201	11.181	0.9630	15.200	0.178	0.108	0.4903
1.200	1.260	10.010	0.9521	15.400	0.234	0.184	0.3881
1.300	1.468	8.949	0.9318	15.600	0.280	0.073	0.3182
1.400	2.237	8.212	0.8852	15.800	0.318	0.065	0.2694
1.500	2.745	8.309	0.8678	16.000	0.351	0.060	0.2326
1.600	2.625	8.597	0.8794	16.200	0.380	0.055	0.2031
1.700	2.143	8.573	0.8972	16.400	0.407	0.050	0.1789
1.800	1.741	8.205	0.9069	16.750	0.448	0.045	0.1460
1.900	1.488	7.821	0.9116	17.000	0.474	0.042	0.1278
2.000	1.304	7.479	0.9148	17.250	0.498	0.040	0.1129
2.200	1.018	6.846	0.9200	17.500	0.520	0.038	0.1005
2.400	0.826	6.283	0.9228	17.750	0.540	0.036	0.0899
2.600	0.695	5.800	0.9238	18.000	0.558	0.035	0.0809
2.800	0.598	5.385	0.9242	18.500	0.591	0.032	0.0664
3.000	0.523	5.024	0.9241	19.000	0.620	0.030	0.0554
3.200	0.460	4.708	0.9243	19.500	0.646	0.028	0.0467
3.400	0.407	4.426	0.9245	20.000	0.668	0.027	0.0398
3.600	0.363	4.174	0.9246	20.500	0.689	0.025	0.0342
3.800	0.326	3.946	0.9247	21.000	0.707	0.024	0.0296
4.000	0.294	3.740	0.9248	21.500	0.724	0.023	0.0258
4.200	0.267	3.552	0.9248	22.000	0.739	0.022	0.0226
4.400	0.244	3.380	0.9249	22.500	0.753	0.021	0.0199
4.600	0.223	3.222	0.9249	23.000	0.766	0.021	0.0177
4.800	0.205	3.076	0.9249	23.500	0.778	0.020	0.0157
4.000	0.294	3.740	0.9248	24.000	0.789	0.019	0.0140
4.200	0.267	3.552	0.9248	24.500	0.799	0.018	0.0126

Aluminum⁴—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
25.000	0.809	0.018	0.0113	85.000	1.007	0.028	0.0002
25.500	0.817	0.017	0.0102	90.000	1.005	0.031	0.0002
26.000	0.826	0.016	0.0092	95.000	0.999	0.036	0.0003
27.000	0.840	0.015	0.0076	100.000	0.991	0.030	0.0002
28.000	0.854	0.014	0.0063	110.000	0.994	0.025	0.0002
29.000	0.865	0.014	0.0053	120.000	0.991	0.024	0.0002
30.000	0.876	0.013	0.0044	130.000	0.987	0.021	0.0001
35.000	0.915	0.010	0.0020	140.000	0.989	0.016	0.0001
40.000	0.940	0.008	0.0010	150.000	0.990	0.015	0.0001
45.000	0.957	0.007	0.0005	160.000	0.989	0.014	0.0001
50.000	0.969	0.006	0.0003	170.000	0.989	0.011	0.0001
55.000	0.979	0.005	0.0001	180.000	0.990	0.010	0.0000
60.000	0.987	0.004	0.0000	190.000	0.990	0.009	0.0000
65.000	0.995	0.004	0.0000	200.000	0.991	0.007	0.0000
70.000	1.006	0.004	0.0000	220.000	0.992	0.006	0.0000
72.500	1.025	0.004	0.0002	240.000	0.993	0.005	0.0000
75.000	1.011	0.024	0.0002	260.000	0.993	0.004	0.0000
77.500	1.008	0.025	0.0002	280.000	0.994	0.003	0.0000
80.000	1.007	0.024	0.0002	300.000	0.995	0.002	0.0000

Chromium⁵

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.06	21.19	42.00	0.962	2.80	1.80	4.06	0.703
0.10	11.81	29.76	0.955	3.00	1.54	3.71	0.695
0.14	15.31	26.36	0.936	3.20	1.44	3.40	0.670
0.18	8.73	25.37	0.953	3.40	1.39	3.24	0.657
0.22	5.30	20.62	0.954	3.60	1.26	3.12	0.661
0.26	3.91	17.12	0.951	3.80	1.12	2.95	0.660
0.30	3.15	14.28	0.943	4.00	1.02	2.76	0.651
0.42	3.47	8.97	0.862	4.20	0.94	2.58	0.639
0.54	3.92	7.06	0.788	4.40	0.90	2.42	0.620
0.66	3.96	5.95	0.736	4.50	0.89	2.35	0.607
0.78	4.13	5.03	0.680	4.60	0.88	2.28	0.598
0.90	4.43	4.60	0.650	4.70	0.86	2.21	0.586
1.00	4.47	4.43	0.639	4.80	0.86	2.13	0.572
1.12	4.53	4.31	0.631	4.90	0.86	2.07	0.557
1.24	4.50	4.28	0.629	5.00	0.85	2.01	0.542
1.36	4.42	4.30	0.631	5.10	0.86	1.94	0.523
1.46	4.31	4.32	0.632	5.20	0.87	1.87	0.503
1.77	3.84	4.37	0.639	5.40	0.93	1.80	0.466
2.00	3.48	4.36	0.644	5.60	0.95	1.74	0.443
2.20	3.18	4.41	0.656	5.80	0.97	1.74	0.437
2.40	2.75	4.46	0.677	6.00	0.94	1.73	0.444
2.60	2.22	4.36	0.698	6.20	0.89	1.69	0.446

Chromium⁵—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
6.40	0.85	1.66	0.447	16.50	0.31	0.75	0.134
6.60	0.80	1.59	0.444	17.00	0.90	0.73	0.132
6.80	0.75	1.51	0.439	17.50	0.88	0.72	0.130
7.00	0.74	1.45	0.425	18.00	0.87	0.70	0.129
7.20	0.71	1.39	0.414	18.50	0.84	0.69	0.130
7.40	0.69	1.33	0.404	19.00	0.82	0.68	0.131
7.60	0.66	1.23	0.378	20.00	0.77	0.64	0.130
7.80	0.67	1.15	0.347	20.5	0.76	0.63	0.129
8.00	0.68	1.07	0.315	21.0	0.74	0.58	0.121
8.20	0.71	1.00	0.278	21.5	0.72	0.55	0.116
8.50	0.74	0.92	0.235	22.0	0.71	0.52	0.112
9.0	0.83	0.81	0.170	22.5	0.70	0.50	0.109
9.50	0.92	0.74	0.132	23.0	0.69	0.48	0.105
10.00	0.98	0.73	0.120	23.5	0.68	0.45	0.101
10.50	1.01	0.72	0.112	24.0	0.68	0.43	0.096
11.00	1.05	0.69	0.103	24.5	0.67	0.39	0.089
11.50	1.09	0.69	0.100	25.0	0.68	0.36	0.080
12.00	1.13	0.70	0.101	25.5	0.68	0.33	0.072
12.50	1.15	0.73	0.108	26.0	0.70	0.31	0.063
13.00	1.15	0.77	0.119	26.5	0.71	0.28	0.055
13.50	1.12	0.80	0.128	27.0	0.72	0.26	0.048
14.00	1.09	0.82	0.135	27.5	0.73	0.25	0.043
14.50	1.03	0.82	0.142	28.0	0.75	0.23	0.037
15.00	1.00	0.82	0.143	29.0	0.77	0.22	0.032
15.50	0.96	0.80	0.141	30.0	0.78	0.21	0.030
16.00	0.92	0.77	0.139				

Copper⁶

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	29.69	71.57	0.980	3.00	1.18	2.21	0.509
0.50	1.71	17.63	0.979	3.20	1.23	2.07	0.468
1.00	0.44	8.48	0.976	3.40	1.27	1.95	0.434
1.50	0.26	5.26	0.965	3.60	1.31	1.87	0.407
1.70	0.22	4.43	0.958	3.80	1.34	1.81	0.387
1.75	0.21	4.25	0.956	4.00	1.34	1.72	0.364
1.80	0.21	4.04	0.952	4.20	1.42	1.64	0.336
1.85	0.22	3.85	0.947	4.40	1.49	1.64	0.329
1.90	0.21	3.67	0.943	4.60	1.52	1.67	0.334
2.00	0.27	3.24	0.910	4.80	1.53	1.71	0.345
2.10	0.47	2.81	0.814	5.00	1.47	1.78	0.366
2.20	0.83	2.60	0.673	5.20	1.38	1.80	0.380
2.30	1.04	2.59	0.618	5.40	1.28	1.78	0.389
2.40	1.12	2.60	0.602	5.60	1.18	1.74	0.391
2.60	1.15	2.50	0.577	5.80	1.10	1.67	0.389
2.80	1.17	2.36	0.545	6.00	1.04	1.59	0.380

Copper⁶—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
6.50	0.96	1.37	0.329	38.00	0.93	0.18	0.010
7.00	0.97	1.20	0.271	39.00	0.93	0.17	0.009
7.50	1.00	1.09	0.230	40.00	0.93	0.17	0.009
8.00	1.03	1.03	0.206	41.00	0.94	0.16	0.008
8.50	1.03	0.98	0.189	42.00	0.94	0.16	0.007
9.00	1.03	0.92	0.171	43.00	0.94	0.15	0.007
9.50	1.03	0.87	0.154	44.00	0.95	0.15	0.007
10.00	1.04	0.82	0.139	45.00	0.95	0.15	0.006
11.00	1.07	0.75	0.118	46.00	0.95	0.15	0.006
12.00	1.09	0.73	0.111	47.00	0.95	0.14	0.006
13.00	1.08	0.72	0.109	48.00	0.95	0.14	0.006
14.00	1.06	0.72	0.111	49.00	0.95	0.14	0.005
14.50	1.03	0.72	0.111	50.00	0.95	0.13	0.005
15.00	1.01	0.71	0.111	51.00	0.95	0.13	0.005
15.50	0.98	0.69	0.109	52.00	0.95	0.13	0.005
16.00	0.95	0.67	0.106	53.00	0.96	0.12	0.004
17.00	0.91	0.62	0.097	54.00	0.96	0.12	0.004
18.00	0.89	0.56	0.084	55.00	0.96	0.12	0.004
19.00	0.88	0.51	0.071	56.00	0.96	0.11	0.004
20.00	0.88	0.45	0.059	57.00	0.96	0.11	0.004
21.00	0.90	0.41	0.048	58.00	0.96	0.11	0.004
22.00	0.92	0.38	0.040	59.00	0.97	0.11	0.003
23.00	0.94	0.37	0.035	60.00	0.97	0.11	0.003
24.00	0.96	0.37	0.035	61.00	0.97	0.11	0.003
25.00	0.96	0.40	0.040	62.00	0.97	0.11	0.003
26.00	0.92	0.40	0.044	63.00	0.96	0.10	0.003
27.00	0.88	0.38	0.043	64.00	0.96	0.10	0.003
28.00	0.86	0.35	0.039	65.00	0.97	0.10	0.003
29.00	0.85	0.30	0.032	66.00	0.97	0.10	0.003
30.00	0.86	0.26	0.025	67.00	0.97	0.09	0.003
31.00	0.88	0.24	0.020	68.00	0.97	0.09	0.002
32.00	0.89	0.22	0.017	69.00	0.97	0.09	0.002
33.00	0.90	0.21	0.015	70.00	0.97	0.09	0.002
34.00	0.91	0.20	0.014	75.00	0.98	0.09	0.002
35.00	0.92	0.20	0.013	80.00	0.98	0.09	0.002
36.00	0.92	0.19	0.012	85.00	0.97	0.09	0.002
37.00	0.92	0.19	0.011	90.00	0.96	0.08	0.002

Germanium⁷

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.01240	(4.0065)	3.00E-03	0.361	0.01736	(4.0060)	1.50E-03	0.361
0.01364	4.0063	2.40E-03	0.361	0.01860		1.50E-03	
0.01488	(4.0060)	1.70E-03	0.361	0.01984		1.60E-03	
0.01612	(4.0060)	1.55E-03	0.361	0.02108		1.60E-03	

Germanium⁷—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.02232		1.55E-03		0.08266	4.0013	9.78E-05	0.360
0.02356		1.53E-03		0.08551	4.0015	5.77E-05	0.360
0.02480		1.50E-03		0.08920		3.98E-05	
0.02604		1.25E-03		0.09460		4.59E-05	
0.02728		8.50E-04		0.09840		3.51E-05	
0.02852		6.50E-04		0.1	4.0063	3.70E-05	0.361
0.02976		7.00E-04		0.2	4.0108		0.361
0.03100	3.9827	8.50E-04	0.358	0.3	4.0246		0.362
0.03224		1.55E-03		0.4	4.0429		0.364
0.03348		2.75E-03		0.5	(4.074)		0.367
0.03472		3.55E-03		0.6	(4.104)	6.58E-07	0.370
0.03596	(3.9900)	3.05E-03	0.359	0.7	4.180	1.27E-04	0.377
0.03720		2.75E-03		0.8	4.275	5.67E-03	0.385
0.03844		2.70E-03		0.9	4.285	7.45E-02	0.386
0.03968	(3.9930)	2.90E-03	0.359	1.0	4.325	8.09E-02	0.390
0.04092		2.95E-03		1.1	4.385	0.103	0.395
0.04215		3.20E-03		1.2	4.420	0.123	0.398
0.04339		6.30E-03		1.3	4.495	0.167	0.405
0.04463		3.40E-03		1.4	4.560	0.190	0.411
0.04587	(3.9955)	2.50E-03	0.360	1.5	4.635	0.298	0.418
0.04711		2.10E-03		1.6	4.763	0.345	0.428
0.04835		2.00E-03		1.7	4.897	0.401	0.439
0.04959		8.00E-04		1.8	5.067	0.500	0.453
0.05083		1.40E-03		1.9	5.380	0.540	0.475
0.05207		1.35E-03		2.0	5.588	0.933	0.495
0.05331		1.10E-03		2.1	5.748	1.634	0.523
0.05455		8.00E-04		2.2	5.283	2.049	0.516
0.05579		6.00E-04		2.3	5.062	2.318	0.519
0.05703		9.0 E-04		2.4	4.610	2.455	0.508
0.05827		6.5 E-04		2.5	4.340	2.384	0.492
0.05951		4.6 E-04		2.6	4.180	2.309	0.480
0.06075		4.0 E-04		2.7	4.082	2.240	0.471
0.06199	3.9992	3.98E-04	0.360	2.8	4.035	2.181	0.464
0.06323		4.0 E-04		2.9	4.037	2.140	0.461
0.06447		4.3 E-04		3.0	4.082	2.145	0.463
0.06571		4.4 E-04		3.1	4.141	2.215	0.471
0.06695	(4.0000)	4.3 E-04	0.360	3.2	4.157	2.340	0.482
0.06819		3.1 E-04		3.3	4.128	2.469	0.490
0.06943		3.3 E-04		3.4	4.070	2.579	0.497
0.07067		3.8 E-04		3.5	4.020	2.667	0.502
0.07191		3.3 E-04		3.6	3.985	2.759	0.509
0.07315		2.5 E-04		3.7	3.958	2.863	0.517
0.07439		1.9 E-04		3.8	3.936	2.986	0.527
0.07514		1.58E-04		3.9	3.920	3.137	0.539
0.07749	4.0009	9.55E-05	0.360	4.0	3.905	3.336	0.556
0.07999	4.0011	1.71E-04	0.360	4.1	3.869	3.614	0.579

Germanium⁷—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
4.2	3.745	4.009	0.612	6.5	1.10	2.05	0.489
4.3	3.338	4.507	0.659	7.0	1.00	1.80	0.448
4.4	2.516	4.669	0.705	7.5		1.60	
4.5	1.953	4.297	0.713	8.0	0.92	1.40	0.348
4.6	1.720	3.960	0.702	8.5	0.92	1.20	0.282
4.7	1.586	3.709	0.690	9.0	0.92	1.14	0.262
4.8	1.498	3.509	0.677	9.5		1.00	
4.9	1.435	3.342	0.664	10.0	0.93	0.86	0.167
5.0	1.394	3.197	0.650	20.0		0.237	
5.1	1.370	3.073	0.636	22.0		0.179	
5.2	1.364	2.973	0.622	24.0		0.144	
5.3	1.371	2.897	0.609	26.0		0.110	
5.4	1.383	2.854	0.600	28.0		0.0747	
5.5	1.380	2.842	0.598	30.0		0.1020	
5.6	1.360	2.846	0.602	32.0		0.0999	
5.7	1.293	2.163	0.479	34.0		0.0856	
5.8	1.209	2.873	0.632	36.0		0.0740	
5.9	1.108	2.813	0.641	38.0		0.0651	
6.0	1.30	2.34	0.517	40.0		0.0604	

Gold⁸

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	8.17	82.83	0.995	2.90	1.50	1.79	0.368
0.20	2.13	41.73	0.995	3.00	1.54	1.80	0.369
0.30	0.99	27.82	0.995	3.10	1.54	1.81	0.371
0.40	0.59	20.83	0.995	3.20	1.54	1.80	0.368
0.50	0.39	16.61	0.994	3.30	1.55	1.78	0.362
0.60	0.28	13.78	0.994	3.40	1.56	1.76	0.356
0.70	0.22	11.75	0.994	3.50	1.58	1.73	0.349
0.80	0.18	10.21	0.993	3.60	1.62	1.73	0.346
0.90	0.15	9.01	0.993	3.70	1.64	1.75	0.351
1.00	0.13	8.03	0.992	3.80	1.63	1.79	0.360
1.20	0.10	6.54	0.991	3.90	1.59	1.81	0.366
1.40	0.08	5.44	0.989	4.00	1.55	1.81	0.369
1.60	0.08	4.56	0.986	4.10	1.51	1.79	0.368
1.80	0.09	3.82	0.979	4.20	1.48	1.78	0.367
2.00	0.13	3.16	0.953	4.30	1.45	1.77	0.368
2.10	0.18	2.84	0.925	4.40	1.41	1.76	0.370
2.20	0.24	2.54	0.880	4.50	1.35	1.74	0.370
2.40	0.50	1.86	0.647	4.60	1.30	1.69	0.364
2.50	0.82	1.59	0.438	4.70	1.27	1.64	0.354
2.60	1.24	1.54	0.331	4.80	1.25	1.59	0.344
2.70	1.43	1.72	0.356	4.90	1.23	1.54	0.332
2.80	1.46	1.77	0.368	5.00	1.22	1.49	0.319

Gold⁸—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
5.20	1.21	1.40	0.295	10.00	1.37	0.80	0.126
5.40	1.21	1.33	0.275	10.20	1.36	0.80	0.127
5.60	1.21	1.27	0.256	10.40	1.35	0.80	0.125
5.80	1.21	1.20	0.236	10.60	1.34	0.79	0.123
6.00	1.22	1.14	0.218	10.80	1.34	0.77	0.120
6.20	1.24	1.09	0.203	11.00	1.34	0.76	0.116
6.40	1.25	1.05	0.190	11.20	1.34	0.74	0.113
6.60	1.27	1.01	0.177	11.40	1.35	0.73	0.111
6.80	1.30	0.97	0.167	11.60	1.36	0.72	0.109
7.00	1.34	0.95	0.162	11.80	1.38	0.71	0.108
7.20	1.36	0.95	0.161	12.00	1.39	0.71	0.109
7.40	1.38	0.96	0.164	12.40	1.44	0.73	0.115
7.60	1.38	0.98	0.169	12.80	1.45	0.79	0.127
7.80	1.35	0.99	0.171	13.20	1.42	0.84	0.137
8.00	1.31	0.96	0.165	13.60	1.37	0.86	0.140
8.20	1.30	0.92	0.155	14.00	1.33	0.86	0.140
8.40	1.30	0.89	0.147	14.40	1.29	0.86	0.139
8.60	1.31	0.88	0.144	14.80	1.26	0.84	0.135
8.80	1.31	0.86	0.140	15.20	1.24	0.83	0.132
9.00	1.30	0.83	0.133	15.60	1.22	0.81	0.127
9.20	1.31	0.81	0.126	16.00	1.21	0.79	0.123
9.40	1.33	0.78	0.122	16.40	1.20	0.78	0.119
9.60	1.36	0.78	0.121	16.80	1.19	0.76	0.116
9.80	1.37	0.79	0.124	17.20	1.19	0.75	0.114
5.60	1.21	1.27	0.256	17.60	1.19	0.74	0.111
5.80	1.21	1.20	0.236	18.00	1.19	0.74	0.109
6.00	1.22	1.14	0.218	18.40	1.19	0.73	0.109
6.20	1.24	1.09	0.203	18.80	1.20	0.74	0.110
6.40	1.25	1.05	0.190	19.20	1.21	0.76	0.116
6.60	1.27	1.01	0.177	19.60	1.21	0.80	0.125
6.80	1.30	0.97	0.167	20.00	1.18	0.83	0.133
7.00	1.34	0.95	0.162	20.40	1.14	0.85	0.141
7.20	1.36	0.95	0.161	20.80	1.10	0.87	0.149
7.40	1.38	0.96	0.164	21.20	1.05	0.88	0.156
7.60	1.38	0.98	0.169	21.60	1.00	0.88	0.162
7.80	1.35	0.99	0.171	22.00	0.94	0.86	0.164
8.00	1.31	0.96	0.165	22.40	0.89	0.83	0.163
8.20	1.30	0.92	0.155	22.80	0.85	0.79	0.157
8.40	1.30	0.89	0.147	23.20	0.82	0.75	0.149
8.60	1.31	0.88	0.144	23.60	0.80	0.70	0.138
8.80	1.31	0.86	0.140	24.00	0.80	0.66	0.125
9.00	1.30	0.83	0.133	24.40	0.80	0.62	0.113
9.20	1.31	0.81	0.126	24.80	0.80	0.58	0.101
9.40	1.33	0.78	0.122	25.20	0.82	0.56	0.090
9.60	1.36	0.78	0.121	25.60	0.83	0.54	0.084
9.80	1.37	0.79	0.124	26.00	0.84	0.52	0.079

Gold⁸—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
26.40	0.85	0.51	0.074	28.40	0.88	0.48	0.062
26.80	0.85	0.50	0.071	28.80	0.88	0.48	0.062
27.20	0.86	0.49	0.068	29.20	0.88	0.48	0.062
27.60	0.86	0.49	0.065	29.60	0.87	0.48	0.064
28.00	0.87	0.48	0.063	30.00	0.86	0.48	0.064

Iridium⁹

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	28.49	60.62	0.975	3.40	1.53	3.05	0.610
0.15	15.32	45.15	0.973	3.60	1.52	2.81	0.573
0.20	9.69	35.34	0.972	3.80	1.61	2.69	0.541
0.25	6.86	28.84	0.969	4.00	1.64	2.68	0.535
0.30	5.16	24.25	0.967	4.20	1.58	2.71	0.549
0.35	4.11	20.79	0.964	4.40	1.45	2.68	0.561
0.40	3.42	18.06	0.960	4.60	1.31	2.60	0.567
0.45	3.05	15.82	0.954	4.80	1.18	2.49	0.570
0.50	2.98	14.06	0.944	5.00	1.10	2.35	0.559
0.60	2.79	11.58	0.925	5.20	1.04	2.22	0.543
0.70	2.93	9.78	0.895	5.40	1.00	2.09	0.522
0.80	3.14	8.61	0.862	5.60	0.98	1.98	0.499
0.90	3.19	7.88	0.840	5.80	0.96	1.86	0.474
1.00	3.15	7.31	0.822	6.00	0.95	1.78	0.454
1.10	3.04	6.84	0.808	6.20	0.94	1.68	0.427
1.20	2.96	6.41	0.791	6.40	0.94	1.59	0.401
1.30	2.85	6.07	0.779	6.60	0.94	1.50	0.375
1.40	2.72	5.74	0.767	6.80	0.95	1.42	0.345
1.50	2.65	5.39	0.750	7.00	0.97	1.34	0.318
1.60	2.68	5.08	0.728	7.20	0.99	1.27	0.290
1.70	2.69	4.92	0.716	7.40	1.02	1.20	0.262
1.80	2.64	4.81	0.710	7.60	1.03	1.14	0.241
1.90	2.57	4.68	0.704	7.80	1.08	1.06	0.208
2.00	2.50	4.57	0.699	8.00	1.13	1.03	0.191
2.10	2.40	4.48	0.697	8.20	1.18	1.00	0.179
2.20	2.29	4.38	0.695	8.40	1.22	0.98	0.171
2.30	2.18	4.26	0.692	8.60	1.26	0.96	0.164
2.40	2.07	4.14	0.689	8.80	1.29	0.95	0.160
2.50	1.98	4.00	0.682	9.00	1.33	0.94	0.157
2.60	1.91	3.86	0.673	9.20	1.36	0.95	0.159
2.70	1.85	3.73	0.665	9.40	1.39	0.95	0.161
2.80	1.81	3.61	0.655	9.60	1.42	0.97	0.163
2.90	1.77	3.51	0.646	9.80	1.44	0.99	0.169
3.00	1.73	3.43	0.640	10.00	1.45	1.01	0.175
3.20	1.62	3.26	0.629	10.20	1.45	1.04	0.182

Iridium⁹—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
10.40	1.44	1.07	0.187	19.60	1.15	1.05	0.197
10.60	1.43	1.09	0.193	20.00	1.10	1.06	0.205
10.80	1.41	1.12	0.200	20.50	1.04	1.05	0.210
11.00	1.38	1.13	0.206	21.00	0.99	1.04	0.215
11.20	1.34	1.14	0.208	21.50	0.94	1.02	0.220
11.40	1.31	1.13	0.208	22.00	0.89	1.00	0.222
11.60	1.28	1.12	0.206	22.50	0.84	0.99	0.228
11.80	1.25	1.10	0.203	23.00	0.79	0.96	0.232
12.00	1.24	1.08	0.199	23.50	0.76	0.92	0.228
12.40	1.21	1.05	0.191	24.00	0.73	0.87	0.223
12.80	1.19	1.01	0.181	24.50	0.70	0.83	0.218
13.20	1.18	0.98	0.173	25.00	0.69	0.79	0.209
13.60	1.17	0.95	0.165	25.50	0.68	0.76	0.200
14.00	1.16	0.91	0.155	26.00	0.67	0.72	0.192
14.40	1.17	0.88	0.147	26.50	0.67	0.69	0.181
14.80	1.18	0.87	0.142	27.00	0.66	0.66	0.174
15.20	1.19	0.84	0.136	27.50	0.66	0.63	0.166
15.60	1.20	0.83	0.133	28.00	0.66	0.61	0.158
16.00	1.21	0.83	0.131	28.50	0.66	0.59	0.151
16.40	1.23	0.82	0.129	29.00	0.65	0.57	0.148
16.80	1.25	0.82	0.127	29.50	0.64	0.55	0.145
17.20	1.28	0.83	0.131	30.00	0.64	0.53	0.140
17.60	1.30	0.87	0.140	32.00	0.62	0.44	0.119
18.00	1.30	0.93	0.154	34.00	0.64	0.35	0.091
18.40	1.27	0.97	0.166	36.00	0.69	0.27	0.059
18.80	1.24	1.00	0.176	38.00	0.73	0.24	0.044
19.20	1.20	1.03	0.187	40.00	0.76	0.22	0.034

Iron¹⁰

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	6.41	33.07	0.978	1.20	3.24	4.26	0.641
0.15	6.26	22.82	0.956	1.30	3.16	4.07	0.626
0.20	3.68	18.23	0.958	1.40	3.12	3.87	0.609
0.26	4.98	13.68	0.911	1.50	3.05	3.77	0.601
0.30	4.87	12.05	0.892	1.60	3.00	3.60	0.585
0.36	4.68	10.44	0.867	1.70	2.98	3.52	0.577
0.40	4.42	9.75	0.858	1.80	2.92	3.46	0.573
0.50	4.14	8.02	0.817	1.90	2.89	3.37	0.563
0.60	3.93	6.95	0.783	2.00	2.85	3.36	0.563
0.70	3.78	6.17	0.752	2.10	2.80	3.34	0.562
0.80	3.65	5.60	0.725	2.20	2.74	3.33	0.563
0.90	3.52	5.16	0.700	2.30	2.65	3.34	0.567
1.00	3.43	4.79	0.678	2.40	2.56	3.31	0.567
1.10	3.33	4.52	0.660	2.50	2.46	3.31	0.570

Iron¹⁰—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
2.60	2.34	3.30	0.576	9.50	0.90	1.02	0.226
2.70	2.23	3.25	0.575	9.67	0.90	1.00	0.221
2.80	2.12	3.23	0.580	9.83	0.89	0.99	0.218
2.90	2.01	3.17	0.580	10.00	0.88	0.97	0.213
3.00	1.88	3.12	0.583	10.17	0.87	0.94	0.203
3.10	1.78	3.04	0.580	10.33	0.87	0.91	0.196
3.20	1.70	2.96	0.576	10.50	0.87	0.89	0.189
3.30	1.62	2.87	0.572	10.67	0.88	0.87	0.179
3.40	1.55	2.79	0.565	10.83	0.89	0.85	0.170
3.50	1.50	2.70	0.556	11.00	0.91	0.83	0.162
3.60	1.47	2.63	0.548	11.17	0.92	0.83	0.159
3.70	1.43	2.56	0.542	11.33	0.93	0.84	0.159
3.83	1.38	2.49	0.534	11.50	0.93	0.84	0.160
4.00	1.30	2.39	0.527	11.67	0.93	0.84	0.162
4.17	1.26	2.27	0.510	11.83	0.92	0.84	0.163
4.33	1.23	2.18	0.494	12.00	0.91	0.84	0.163
4.50	1.20	2.10	0.482	12.17	0.90	0.84	0.165
4.67	1.16	2.02	0.470	12.33	0.89	0.83	0.164
4.83	1.14	1.93	0.451	12.50	0.98	0.83	0.165
5.00	1.14	1.87	0.435	12.67	0.87	0.82	0.166
5.17	1.12	1.81	0.425	12.83	0.86	0.81	0.166
5.33	1.11	1.75	0.408	13.00	0.85	0.80	0.162
5.50	1.09	1.17	0.401	13.17	0.84	0.79	0.161
5.67	1.09	1.65	0.383	13.33	0.84	0.78	0.160
5.83	1.10	1.61	0.373	13.50	0.83	0.77	0.159
6.00	1.09	1.59	0.366	13.67	0.82	0.76	0.157
6.17	1.08	1.57	0.365	13.83	0.81	0.75	0.154
6.33	1.04	1.55	0.365	14.00	0.81	0.73	0.151
6.50	1.02	1.51	0.358	14.17	0.80	0.72	0.149
6.67	1.00	1.47	0.351	14.33	0.80	0.71	0.146
6.83	0.97	1.43	0.346	14.50	0.79	0.79	0.144
7.00	0.96	1.39	0.333	14.67	0.79	0.69	0.141
7.17	0.94	1.35	0.327	14.83	0.78	0.67	0.138
7.33	0.94	1.30	0.311	15.00	0.78	0.66	0.135
7.50	0.94	1.26	0.298	15.17	0.78	0.65	0.131
7.67	0.94	1.23	0.288	15.33	0.78	0.64	0.238
7.83	0.94	1.21	0.279	15.50	0.77	0.63	0.126
8.00	0.94	1.18	0.272	15.67	0.77	0.62	0.123
8.17	0.94	1.16	0.265	15.83	0.77	0.61	0.119
8.33	0.94	1.14	0.258	16.00	0.77	0.60	0.116
8.50	0.94	1.12	0.251	16.17	0.78	0.58	0.112
8.67	0.94	1.10	0.246	16.33	0.78	0.58	0.110
8.83	0.92	1.08	0.240	16.50	0.78	0.57	0.107
9.00	0.93	1.07	0.236	16.67	0.77	0.56	0.106
9.17	0.92	1.06	0.233	16.83	0.78	0.55	0.103
9.33	0.91	1.04	0.231	17.00	0.78	0.55	0.102

Iron¹⁰—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
17.17	0.78	0.54	0.100	21.67	0.72	0.38	0.071
17.33	0.78	0.54	0.098	21.83	0.72	0.37	0.070
17.50	0.77	0.53	0.097	22.00	0.72	0.36	0.068
17.67	0.77	0.52	0.095	22.17	0.71	0.35	0.067
17.83	0.78	0.51	0.092	22.33	0.72	0.34	0.064
18.00	0.78	0.51	0.091	22.50	0.72	0.34	0.063
18.17	0.78	0.51	0.090	22.67	0.72	0.33	0.062
18.33	0.78	0.50	0.089	22.83	0.72	0.32	0.059
18.50	0.77	0.50	0.089	23.00	0.72	0.31	0.058
18.67	0.77	0.50	0.088	23.17	0.72	0.30	0.056
18.83	0.77	0.49	0.087	23.33	0.72	0.29	0.054
19.00	0.77	0.49	0.087	23.50	0.73	0.28	0.050
19.17	0.76	0.49	0.088	23.67	0.73	0.28	0.049
19.33	0.76	0.48	0.087	23.83	0.74	0.27	0.047
19.50	0.75	0.47	0.086	24.00	0.74	0.27	0.045
19.67	0.75	0.47	0.085	24.17	0.74	0.26	0.044
19.83	0.75	0.46	0.084	24.33	0.74	0.26	0.043
20.00	0.74	0.45	0.083	24.50	0.74	0.25	0.042
20.17	0.74	0.44	0.081	24.67	0.75	0.25	0.040
20.33	0.74	0.44	0.081	24.83	0.75	0.24	0.039
20.50	0.74	0.42	0.080	25.00	0.75	0.24	0.038
20.67	0.73	0.43	0.079	26.00	0.76	0.21	0.031
20.83	0.73	0.42	0.078	27.00	0.78	0.18	0.026
21.00	0.73	0.41	0.077	28.00	0.79	0.16	0.021
21.17	0.72	0.40	0.076	29.00	0.81	0.14	0.017
21.33	0.72	0.39	0.074	30.00	0.82	0.13	0.014
21.50	0.72	0.38	0.073				

Magnesium¹¹ (evaporated)

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
2.145	0.48	3.71	0.880	5.636	0.15	1.50	0.832
2.270	0.57	3.47	0.843	6.200	0.20	1.40	0.765
2.522	0.53	2.92	0.805	6.889	0.25	1.30	0.693
2.845	0.52	2.65	0.777	7.750	0.20	1.20	0.722
3.064	0.52	2.05	0.681	8.857	0.15	0.95	0.730
5.167	0.10	1.60	0.894	10.335	0.25	0.40	0.419

Molybdenum¹²

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	18.53	68.51	0.985	3.50	3.06	3.21	0.543
0.15	8.78	47.54	0.985	3.60	3.05	3.23	0.546
0.20	5.10	35.99	0.985	3.70	3.04	3.27	0.550
0.25	3.36	28.75	0.984	3.80	3.04	3.31	0.554
0.30	2.44	23.80	0.983	3.90	3.04	3.40	0.564
0.34	2.00	20.84	0.982	4.00	3.01	3.51	0.576
0.38	1.70	18.44	0.980	4.20	2.77	3.77	0.610
0.42	1.57	16.50	0.978	4.40	2.39	3.88	0.640
0.46	1.46	14.91	0.975	4.60	2.06	3.84	0.658
0.50	1.37	13.55	0.971	4.80	1.75	3.76	0.678
0.54	1.35	12.36	0.966	5.00	1.46	3.62	0.695
0.58	1.34	11.34	0.960	5.20	1.22	3.42	0.706
0.62	1.38	10.44	0.952	5.40	1.07	3.20	0.706
0.66	1.43	9.67	0.942	5.60	0.96	2.99	0.700
0.70	1.48	8.99	0.932	5.80	0.89	2.80	0.688
0.74	1.51	8.38	0.921	6.00	0.85	2.64	0.674
0.78	1.60	7.83	0.906	6.20	0.81	2.50	0.660
0.82	1.64	7.35	0.892	6.40	0.79	2.36	0.641
0.86	1.70	6.89	0.876	6.60	0.78	2.24	0.619
0.90	1.74	6.48	0.859	6.80	0.78	2.13	0.592
1.00	1.94	5.58	0.805	7.00	0.80	2.04	0.568
1.10	2.15	4.85	0.743	7.20	0.81	1.98	0.548
1.20	2.44	4.22	0.671	7.40	0.81	1.95	0.542
1.30	2.77	3.74	0.608	7.60	0.75	1.90	0.552
1.40	3.15	3.40	0.562	7.80	0.71	1.81	0.542
1.50	3.53	3.30	0.550	8.00	0.69	1.73	0.530
1.60	3.77	3.41	0.562	8.20	0.67	1.65	0.512
1.70	3.84	3.51	0.570	8.40	0.66	1.57	0.495
1.80	3.81	3.58	0.576	8.60	0.65	1.49	0.475
1.90	3.74	3.58	0.576	8.80	0.65	1.41	0.450
2.00	3.68	3.52	0.571	9.00	0.65	1.33	0.420
2.10	3.68	3.45	0.565	9.20	0.67	1.25	0.385
2.20	3.76	3.41	0.562	9.40	0.69	1.19	0.355
2.30	3.79	3.61	0.578	9.60	0.71	1.12	0.320
2.40	3.59	3.78	0.594	9.80	0.74	1.05	0.285
2.50	3.36	3.73	0.591	10.00	0.77	0.99	0.250
2.60	3.22	3.61	0.582	10.20	0.81	0.93	0.217
2.70	3.13	3.51	0.573	10.40	0.86	0.88	0.188
2.80	3.08	3.42	0.565	10.60	0.91	0.83	0.162
2.90	3.05	3.33	0.566	10.80	0.98	0.79	0.138
3.00	3.04	3.27	0.550	11.00	1.05	0.77	0.125
3.10	3.03	3.21	0.544	11.20	1.12	0.78	0.123
3.20	3.05	3.18	0.540	11.40	1.18	0.80	0.125
3.30	3.06	3.18	0.540	11.60	1.23	0.85	0.135
3.40	3.06	3.19	0.541	11.80	1.25	0.89	0.145

Molybdenum¹²—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
12.00	1.26	0.92	0.154	23.60	0.58	0.53	0.166
12.40	1.25	0.98	0.168	24.00	0.58	0.49	0.151
12.80	1.23	1.00	0.178	24.60	0.60	0.43	0.124
13.20	1.20	1.02	0.185	25.00	0.62	0.39	0.106
13.60	1.17	1.02	0.187	25.60	0.66	0.35	0.085
14.00	1.15	1.01	0.185	26.00	0.68	0.33	0.072
14.40	1.13	1.00	0.182	26.50	0.71	0.31	0.060
14.80	1.13	0.99	0.179	27.00	0.73	0.29	0.050
15.00	1.14	0.99	0.179	27.50	0.76	0.28	0.041
15.60	1.15	1.01	0.184	28.00	0.79	0.27	0.036
16.00	1.14	1.04	0.194	28.50	0.81	0.26	0.031
16.60	1.10	1.10	0.216	29.00	0.83	0.26	0.028
17.00	1.04	1.12	0.233	29.50	0.86	0.26	0.025
17.60	0.94	1.14	0.257	30.00	0.88	0.26	0.023
18.00	0.87	1.12	0.270	31.00	0.92	0.29	0.024
18.60	0.77	1.08	0.283	32.00	0.92	0.32	0.030
19.00	0.71	1.02	0.284	33.00	0.90	0.33	0.032
19.60	0.66	0.94	0.275	34.00	0.91	0.34	0.034
20.00	0.64	0.89	0.264	35.00	0.87	0.37	0.043
20.60	0.62	0.81	0.245	36.00	0.82	0.34	0.043
21.00	0.61	0.77	0.234	37.00	0.81	0.30	0.038
21.60	0.61	0.71	0.215	38.00	0.81	0.27	0.033
22.00	0.60	0.69	0.207	39.00	0.82	0.25	0.029
22.60	0.59	0.63	0.195	40.00	0.83	0.23	0.025
23.00	0.58	0.60	0.185				

Nickel¹³

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	9.54	45.82	0.983	1.20	2.85	5.10	0.721
0.15	5.45	30.56	0.978	1.30	2.74	4.85	0.708
0.20	4.12	22.48	0.969	1.40	2.65	4.63	0.695
0.25	4.25	17.68	0.950	1.50	2.53	4.47	0.688
0.30	4.19	15.05	0.934	1.60	2.43	4.31	0.679
0.35	4.03	13.05	0.918	1.70	2.28	4.18	0.677
0.40	3.84	11.43	0.900	1.80	2.14	4.01	0.670
0.50	4.03	9.64	0.864	1.90	2.02	3.82	0.659
0.60	3.84	8.35	0.835	2.00	1.92	3.65	0.649
0.70	3.59	7.48	0.813	2.10	1.85	3.48	0.634
0.80	3.38	6.82	0.794	2.20	1.80	3.33	0.620
0.90	3.18	6.23	0.774	2.30	1.75	3.19	0.605
1.00	3.06	5.74	0.753	2.40	1.71	3.06	0.590
1.10	2.97	5.38	0.734	2.50	1.67	2.93	0.575

Nickel¹³—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
2.60	1.65	2.81	0.557	10.40	0.95	0.80	0.145
2.70	1.64	2.71	0.542	10.60	0.97	0.76	0.129
2.80	1.63	2.61	0.525	10.80	0.99	0.75	0.123
2.90	1.62	2.52	0.509	11.00	1.01	0.73	0.115
3.00	1.61	2.44	0.495	11.25	1.04	0.72	0.111
3.10	1.61	2.36	0.480	11.50	1.05	0.71	0.109
3.20	1.61	2.30	0.467	11.75	1.07	0.71	0.108
3.30	1.61	2.23	0.454	12.00	1.07	0.71	0.108
3.40	1.62	2.17	0.441	12.25	1.07	0.71	0.107
3.50	1.63	2.11	0.428	12.50	1.08	0.71	0.106
3.60	1.64	2.07	0.416	12.75	1.08	0.71	0.106
3.70	1.66	2.02	0.405	13.00	1.08	0.71	0.105
3.80	1.69	1.99	0.397	13.25	1.08	0.71	0.105
3.90	1.72	1.98	0.393	13.50	1.07	0.70	0.105
4.00	1.73	1.98	0.392	13.75	1.07	0.70	0.105
4.20	1.74	2.01	0.396	14.00	1.07	0.71	0.106
4.40	1.71	2.06	0.409	14.25	1.06	0.70	0.106
4.60	1.63	2.09	0.421	14.50	1.05	0.70	0.106
4.80	1.53	2.11	0.435	14.75	1.04	0.70	0.107
5.00	1.40	2.10	0.449	15.00	1.03	0.70	0.107
5.20	1.27	2.04	0.454	15.25	1.02	0.69	0.106
5.40	1.16	1.94	0.449	15.50	1.01	0.69	0.105
5.60	1.09	1.83	0.435	15.75	1.00	0.68	0.104
5.80	1.04	1.73	0.417	16.00	0.99	0.67	0.103
6.20	1.00	1.54	0.371	16.50	0.98	0.66	0.101
6.40	1.01	1.46	0.345	17.00	0.96	0.64	0.098
6.60	1.01	1.40	0.325	17.50	0.94	0.63	0.096
6.80	1.02	1.35	0.308	18.00	0.92	0.61	0.092
7.00	1.03	1.30	0.291	18.50	0.91	0.58	0.087
7.20	1.03	1.27	0.282	19.00	0.90	0.56	0.082
7.40	1.03	1.24	0.273	19.50	0.90	0.54	0.077
7.60	1.02	1.22	0.265	20.00	0.89	0.51	0.071
7.80	1.01	1.18	0.256	20.50	0.89	0.49	0.066
8.00	1.01	1.15	0.248	21.00	0.90	0.47	0.061
8.20	1.00	1.13	0.242	21.50	0.91	0.46	0.057
8.40	0.99	1.11	0.235	22.00	0.91	0.45	0.055
8.60	0.98	1.08	0.228	22.50	0.91	0.44	0.053
8.80	0.97	1.05	0.220	23.00	0.92	0.44	0.051
9.00	0.97	1.01	0.211	23.50	0.91	0.44	0.052
9.20	0.96	0.99	0.203	24.00	0.90	0.43	0.051
9.40	0.95	0.96	0.194	24.50	0.90	0.43	0.051
9.60	0.95	0.93	0.185	25.00	0.89	0.42	0.050
9.80	0.95	0.89	0.175	26.00	0.88	0.39	0.046
10.00	0.95	0.87	0.166	27.00	0.87	0.37	0.042
10.20	0.95	0.83	0.155	28.00	0.87	0.35	0.040

Nickel¹³—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
29.00	0.86	0.34	0.037	65.00	0.98	0.09	0.002
30.00	0.86	0.32	0.034	68.00	0.96	0.12	0.004
35.00	0.86	0.24	0.022	70.00	0.94	0.11	0.004
40.00	0.87	0.18	0.014	75.00	0.94	0.09	0.003
45.00	0.88	0.13	0.008	80.00	0.94	0.07	0.002
50.00	0.92	0.10	0.004	90.00	0.94	0.06	0.002
60.00	0.96	0.08	0.002				

Niobium¹⁴

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.12	15.99	53.20	0.979	3.00	2.51	2.68	0.485
0.20	7.25	34.14	0.976	3.10	2.48	2.60	0.475
0.24	5.47	28.88	0.975	3.20	2.45	2.53	0.465
0.28	4.26	24.95	0.974	3.30	2.44	2.45	0.453
0.35	3.11	20.03	0.970	3.40	2.46	2.38	0.442
0.45	2.28	15.58	0.964	3.50	2.48	2.33	0.435
0.55	1.83	12.67	0.956	3.60	2.52	2.29	0.428
0.65	1.57	10.59	0.947	3.70	2.56	2.27	0.426
0.75	1.41	9.00	0.935	3.80	2.59	2.28	0.427
0.85	1.35	7.74	0.918	3.90	2.62	2.29	0.429
0.95	1.35	6.70	0.893	4.00	2.64	2.33	0.434
1.05	1.44	5.86	0.857	4.20	2.64	2.42	0.447
1.15	1.55	5.18	0.814	4.40	2.53	2.56	0.467
1.25	1.65	4.63	0.768	4.60	2.39	2.56	0.470
1.35	1.76	4.13	0.715	4.80	2.32	2.52	0.465
1.45	1.95	3.68	0.650	5.00	2.26	2.57	0.475
1.55	2.15	3.37	0.595	5.20	2.16	2.62	0.487
1.65	2.36	3.13	0.552	5.40	2.00	2.68	0.505
1.75	2.54	2.99	0.527	5.60	1.81	2.67	0.518
1.85	2.69	2.89	0.510	5.80	1.63	2.60	0.522
1.95	2.82	2.86	0.505	6.00	1.49	2.49	0.520
2.05	2.89	2.87	0.505	6.20	1.38	2.38	0.512
2.15	2.92	2.87	0.505	6.40	1.31	2.25	0.496
2.25	2.93	2.87	0.505	6.60	1.26	2.14	0.480
2.35	2.92	2.88	0.506	6.80	1.24	2.04	0.460
2.45	2.89	2.90	0.509	7.00	1.23	1.96	0.441
2.55	2.83	2.92	0.512	7.20	1.22	1.91	0.430
2.65	2.74	2.90	0.511	7.40	1.20	1.88	0.427
2.75	2.66	2.86	0.507	7.60	1.14	1.85	0.430
2.85	2.58	2.80	0.500	7.80	1.07	1.78	0.428

Niobium¹⁴—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
8.00	1.02	1.69	0.412	17.80	0.75	0.87	0.217
8.20	1.00	1.60	0.390	18.00	0.74	0.85	0.209
8.40	0.99	1.51	0.365	18.60	0.73	0.77	0.185
8.60	0.99	1.43	0.340	19.00	0.72	0.72	0.170
8.70	0.99	1.39	0.328	19.60	0.72	0.66	0.150
8.80	1.00	1.36	0.315	20.00	0.72	0.62	0.137
9.00	1.01	1.29	0.290	20.60	0.71	0.55	0.119
9.20	1.04	1.22	0.265	21.00	0.72	0.50	0.100
9.40	1.07	1.18	0.245	21.60	0.75	0.43	0.075
9.60	1.10	1.13	0.227	22.00	0.78	0.40	0.063
9.80	1.13	1.09	0.209	22.60	0.82	0.35	0.045
10.00	1.18	1.05	0.194	23.00	0.85	0.33	0.038
10.20	1.23	1.04	0.187	23.60	0.88	0.30	0.029
10.40	1.27	1.04	0.185	24.00	0.91	0.29	0.025
10.60	1.30	1.06	0.190	24.60	0.94	0.28	0.022
10.80	1.32	1.08	0.195	25.00	0.96	0.27	0.020
11.00	1.32	1.10	0.200	25.60	0.99	0.26	0.018
11.20	1.31	1.12	0.204	26.00	1.00	0.26	0.017
11.40	1.30	1.13	0.207	26.60	1.03	0.25	0.016
11.60	1.28	1.13	0.209	27.00	1.04	0.25	0.015
11.80	1.27	1.13	0.210	27.60	1.06	0.25	0.015
12.00	1.25	1.12	0.209	28.00	1.08	0.24	0.015
12.40	1.24	1.10	0.204	28.60	1.11	0.24	0.016
12.80	1.24	1.09	0.200	29.00	1.13	0.25	0.017
13.20	1.24	1.09	0.201	29.60	1.16	0.26	0.020
13.60	1.23	1.12	0.208	30.00	1.18	0.28	0.023
14.00	1.20	1.13	0.216	31.00	1.18	0.31	0.026
14.40	1.16	1.15	0.225	32.00	1.20	0.34	0.031
14.80	1.11	1.16	0.234	33.00	1.21	0.38	0.038
15.00	1.08	1.16	0.238	34.00	1.20	0.42	0.044
15.60	0.99	1.14	0.247	35.20	1.17	0.47	0.051
16.00	0.92	1.11	0.250	36.00	1.15	0.50	0.056
16.60	0.85	1.04	0.245	37.50	1.07	0.53	0.064
17.00	0.80	0.99	0.240	39.50	0.95	0.50	0.063
17.20	0.79	0.96	0.236	40.50	0.92	0.47	0.059
17.40	0.77	0.93	0.230				

Osmium (polycrystalline)¹⁵

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	4.08	50.23	0.994	4.40	2.24	3.44	0.599
0.15	2.90	33.60	0.990	4.60	2.01	3.31	0.598
0.20	2.44	25.11	0.985	4.80	1.88	3.19	0.592
0.25	2.35	19.99	0.977	5.00	1.74	3.12	0.596
0.30	2.23	16.54	0.969	5.20	1.58	3.00	0.597
0.35	2.33	14.06	0.955	5.40	1.46	2.88	0.593
0.40	2.45	12.32	0.940	5.60	1.36	2.77	0.589
0.45	2.43	11.02	0.927	5.80	1.27	2.65	0.582
0.50	2.41	9.97	0.913	6.00	1.20	2.54	0.575
0.55	2.33	9.12	0.901	6.20	1.13	2.44	0.571
0.60	2.21	8.37	0.890	6.40	1.06	2.33	0.562
0.65	2.11	7.68	0.877	6.60	1.01	2.21	0.548
0.70	2.02	7.04	0.862	6.80	0.97	2.11	0.532
0.75	2.00	6.46	0.842	7.00	0.95	2.00	0.514
0.80	2.00	5.95	0.820	7.20	0.92	1.91	0.497
0.85	2.01	5.51	0.796	7.40	0.91	1.81	0.476
0.90	2.03	5.10	0.769	7.60	0.90	1.72	0.451
0.95	2.05	4.74	0.742	7.80	0.90	1.63	0.426
1.00	2.09	4.41	0.712	8.00	0.91	1.55	0.400
1.10	2.15	3.84	0.651	8.20	0.91	1.48	0.375
1.20	2.16	3.35	0.592	8.40	0.94	1.40	0.344
1.30	2.25	2.77	0.506	8.60	0.96	1.34	0.319
1.40	2.49	2.23	0.419	8.80	0.98	1.29	0.296
1.50	2.84	1.80	0.369	9.00	1.01	1.24	0.274
1.60	3.36	1.62	0.379	9.20	1.04	1.19	0.255
1.70	3.70	1.75	0.411	9.40	1.08	1.16	0.238
1.80	3.78	1.83	0.423	9.60	1.10	1.14	0.229
1.90	3.81	1.75	0.418	9.80	1.13	1.11	0.217
2.00	3.98	1.60	0.418	10.00	1.16	1.10	0.209
2.10	4.26	1.54	0.432	10.20	1.19	1.08	0.203
2.20	4.58	1.62	0.457	10.30	1.20	1.08	0.201
2.30	4.84	1.76	0.479	10.40	1.22	1.08	0.200
2.40	5.10	2.01	0.506	10.50	1.23	1.09	0.201
2.50	5.28	2.38	0.532	10.60	1.24	1.10	0.203
2.60	5.36	2.82	0.557	10.80	1.25	1.11	0.206
2.70	5.30	3.29	0.580	11.00	1.24	1.13	0.213
2.80	5.07	3.78	0.603	11.20	1.23	1.14	0.217
2.90	4.65	4.18	0.624	11.40	1.19	1.15	0.223
3.00	4.05	4.40	0.639	11.60	1.17	1.12	0.216
3.20	3.29	3.96	0.614	11.80	1.16	1.10	0.211
3.40	2.93	3.79	0.607	12.00	1.15	1.08	0.205
3.60	2.75	3.45	0.577	12.40	1.14	1.03	0.191
3.80	2.73	3.32	0.562	12.80	1.15	1.01	0.183
4.00	2.71	3.34	0.565	13.20	1.16	0.98	0.174
4.20	2.53	3.44	0.584	13.60	1.17	0.97	0.170

Osmium (polycrystalline)¹⁵—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
14.00	1.17	0.96	0.169	24.00	0.73	0.84	0.209
14.40	1.16	0.94	0.165	24.40	0.72	0.82	0.207
14.80	1.16	0.91	0.156	24.80	0.70	0.80	0.205
15.20	1.17	0.89	0.148	25.20	0.69	0.77	0.202
15.60	1.20	0.86	0.140	25.60	0.67	0.75	0.199
16.00	1.25	0.87	0.140	26.00	0.66	0.72	0.195
16.40	1.28	0.90	0.147	26.40	0.65	0.69	0.189
16.80	1.28	0.94	0.157	26.80	0.63	0.66	0.183
17.20	1.27	0.97	0.167	27.20	0.65	0.62	0.165
17.60	1.26	1.01	0.178	28.00	0.64	0.59	0.156
18.00	1.23	1.04	0.189	28.40	0.64	0.57	0.148
18.40	1.19	1.08	0.200	28.80	0.65	0.55	0.140
18.80	1.14	1.10	0.210	29.20	0.65	0.53	0.134
19.20	1.10	1.10	0.219	29.60	0.65	0.51	0.128
19.60	1.05	1.11	0.227	30.00	0.65	0.49	0.121
20.00	0.96	1.10	0.239	31.00	0.65	0.45	0.111
20.40	0.93	1.09	0.240	32.00	0.66	0.41	0.095
20.80	0.89	1.05	0.240	33.00	0.68	0.37	0.079
21.20	0.86	1.02	0.237	34.00	0.70	0.34	0.068
21.60	0.83	0.99	0.235	35.00	0.72	0.31	0.057
22.00	0.80	0.96	0.230	36.00	0.74	0.29	0.048
22.40	0.78	0.93	0.226	37.00	0.77	0.27	0.040
22.80	0.77	0.90	0.220	38.00	0.79	0.26	0.035
23.20	0.75	0.88	0.217	39.00	0.81	0.26	0.031
23.60	0.75	0.86	0.211	40.00	0.84	0.26	0.026

Palladium¹⁵

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	4.13	54.15	0.994	1.20	2.65	6.10	0.790
0.15	3.13	35.82	0.990	1.30	2.50	5.78	0.781
0.20	3.07	26.59	0.983	1.40	2.34	5.50	0.774
0.26	3.11	20.15	0.971	1.50	2.17	5.22	0.767
0.30	3.56	17.27	0.955	1.60	2.08	4.95	0.755
0.36	3.98	14.41	0.932	1.70	2.00	4.72	0.745
0.40	4.27	13.27	0.916	1.80	1.92	4.54	0.737
0.46	4.27	12.11	0.902	1.90	1.82	4.35	0.729
0.50	4.10	11.44	0.896	2.00	1.75	4.18	0.721
0.56	3.92	10.49	0.883	2.10	1.67	4.03	0.714
0.60	3.80	9.96	0.876	2.20	1.60	3.88	0.707
0.72	3.51	8.70	0.854	2.30	1.53	3.75	0.700
0.80	3.35	8.06	0.840	2.40	1.47	3.61	0.693
1.00	2.99	6.89	0.811	2.50	1.41	3.48	0.685
1.10	2.81	6.46	0.800	2.60	1.37	3.36	0.676

Palladium¹⁵—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
2.70	1.32	3.25	0.668	8.80	1.04	0.65	0.094
2.80	1.29	3.13	0.658	9.00	1.07	0.64	0.090
2.90	1.26	3.03	0.648	9.50	1.12	0.65	0.089
3.00	1.23	2.94	0.639	10.00	1.14	0.65	0.088
3.10	1.20	2.85	0.630	10.50	1.16	0.65	0.087
3.20	1.17	2.77	0.622	11.00	1.18	0.64	0.086
3.30	1.14	2.68	0.613	11.50	1.19	0.65	0.087
3.40	1.12	2.60	0.602	12.00	1.20	0.66	0.089
3.50	1.10	2.52	0.591	12.50	1.19	0.67	0.091
3.60	1.08	2.45	0.581	13.00	1.18	0.67	0.091
3.70	1.07	2.38	0.570	13.50	1.18	0.67	0.092
3.80	1.06	2.31	0.558	14.00	1.17	0.67	0.093
3.90	1.05	2.25	0.547	14.50	1.15	0.68	0.095
4.00	1.03	2.19	0.537	15.00	1.13	0.69	0.098
4.20	1.04	2.09	0.510	15.50	1.10	0.68	0.096
4.40	1.03	2.01	0.493	16.00	1.08	0.66	0.092
4.60	1.03	1.94	0.476	16.50	1.06	0.63	0.086
4.80	1.01	1.90	0.470	17.00	1.07	0.61	0.081
5.00	0.96	1.86	0.472	17.50	1.06	0.61	0.080
5.20	0.90	1.79	0.474	18.00	1.07	0.59	0.077
5.40	0.85	1.70	0.463	18.50	1.07	0.59	0.077
5.60	0.81	1.62	0.449	19.00	1.08	0.59	0.077
5.80	0.78	1.54	0.437	19.50	1.08	0.61	0.080
6.00	0.76	1.45	0.418	20.00	1.07	0.65	0.090
6.20	0.74	1.37	0.397	20.50	1.03	0.67	0.098
6.40	0.73	1.29	0.375	21.00	0.99	0.67	0.103
6.60	0.72	1.21	0.350	21.50	0.95	0.66	0.103
6.80	0.73	1.13	0.316	22.00	0.91	0.64	0.103
7.00	0.73	1.05	0.287	22.50	0.88	0.62	0.101
7.20	0.75	0.98	0.255	23.00	0.86	0.59	0.097
7.40	0.77	0.91	0.223	23.50	0.85	0.56	0.091
7.60	0.79	0.85	0.195	24.00	0.84	0.54	0.086
7.80	0.83	0.78	0.163	25.00	0.81	0.51	0.084
8.00	0.88	0.73	0.133	26.40	0.80	0.43	0.066
8.20	0.94	0.70	0.117	27.80	0.81	0.38	0.052
8.40	0.96	0.70	0.114	29.20	0.82	0.35	0.046
8.60	1.00	0.65	0.097				

Platinum¹⁶

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	13.21	44.72	0.976	4.40	1.43	2.04	0.432
0.15	8.18	31.16	0.969	4.60	1.39	1.95	0.415
0.20	5.90	23.95	0.962	4.80	1.38	1.85	0.392
0.25	4.70	19.40	0.954	5.00	1.36	1.76	0.372
0.30	3.92	16.16	0.945	5.20	1.36	1.67	0.350
0.35	3.28	13.66	0.936	5.40	1.36	1.61	0.332
0.40	2.81	11.38	0.922	5.60	1.36	1.54	0.315
0.45	3.03	9.31	0.882	5.80	1.36	1.47	0.295
0.50	3.91	7.71	0.813	6.00	1.38	1.40	0.276
0.55	4.58	7.14	0.777	6.20	1.39	1.35	0.261
0.60	5.13	6.75	0.753	6.40	1.42	1.29	0.246
0.65	5.52	6.66	0.746	6.60	1.45	1.26	0.236
0.70	5.71	6.83	0.751	6.80	1.48	1.24	0.231
0.75	5.57	7.02	0.759	7.00	1.50	1.24	0.230
0.80	5.31	7.04	0.762	7.20	1.50	1.25	0.231
0.85	5.05	6.98	0.763	7.40	1.49	1.23	0.228
0.90	4.77	6.91	0.765	7.60	1.48	1.22	0.225
0.95	4.50	6.77	0.763	7.80	1.48	1.20	0.221
1.00	4.25	6.62	0.762	8.00	1.47	1.18	0.216
1.10	3.86	6.24	0.753	8.20	1.47	1.17	0.212
1.20	3.55	5.92	0.746	8.40	1.47	1.15	0.209
1.30	3.29	5.61	0.736	8.60	1.47	1.14	0.205
1.40	3.10	5.32	0.725	8.80	1.47	1.13	0.202
1.50	2.92	5.07	0.716	9.00	1.48	1.12	0.200
1.60	2.76	4.84	0.706	9.20	1.49	1.11	0.198
1.70	2.63	4.64	0.697	9.40	1.49	1.12	0.200
1.80	2.51	4.43	0.686	9.60	1.49	1.13	0.203
1.90	2.38	4.26	0.678	9.80	1.48	1.15	0.207
2.00	2.30	4.07	0.664	10.00	1.46	1.15	0.209
2.10	2.23	3.92	0.654	10.20	1.43	1.16	0.211
2.20	2.17	3.77	0.642	10.40	1.40	1.15	0.210
2.30	2.10	3.67	0.636	10.60	1.37	1.14	0.207
2.40	2.03	3.54	0.626	10.80	1.35	1.12	0.203
2.50	1.96	3.42	0.616	11.00	1.33	1.10	0.199
2.60	1.91	3.30	0.605	11.20	1.31	1.08	0.194
2.70	1.87	3.20	0.595	11.40	1.30	1.06	0.188
2.80	1.83	3.10	0.585	11.60	1.29	1.04	0.183
2.90	1.79	3.01	0.575	11.80	1.29	1.01	0.177
3.00	1.75	2.92	0.565	12.00	1.29	1.00	0.173
3.20	1.68	2.76	0.546	12.40	1.29	0.97	0.165
3.40	1.63	2.62	0.527	12.80	1.29	0.94	0.158
3.60	1.58	2.48	0.507	13.20	1.31	0.93	0.155
3.80	1.53	2.37	0.491	13.60	1.31	0.93	0.155
4.00	1.49	2.25	0.472	14.00	1.31	0.93	0.155
4.20	1.45	2.14	0.452	14.40	1.30	0.93	0.156

Platinum¹⁶—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
14.80	1.27	0.93	0.157	22.50	0.81	0.98	0.235
15.20	1.27	0.93	0.155	23.00	0.77	0.92	0.226
15.60	1.25	0.92	0.151	23.50	0.75	0.87	0.213
16.00	1.24	0.89	0.146	24.00	0.74	0.82	0.201
16.50	1.24	0.87	0.142	24.50	0.73	0.77	0.187
17.00	1.25	0.86	0.138	25.00	0.73	0.73	0.174
17.50	1.27	0.85	0.135	25.50	0.73	0.70	0.162
18.00	1.31	0.88	0.142	26.00	0.74	0.67	0.150
18.50	1.30	0.94	0.157	26.50	0.74	0.65	0.142
19.00	1.28	0.99	0.171	27.00	0.74	0.63	0.136
19.50	1.23	1.03	0.184	27.50	0.74	0.62	0.130
20.00	1.18	1.06	0.197	28.00	0.75	0.60	0.125
20.50	1.11	1.09	0.212	28.50	0.75	0.59	0.121
21.00	1.03	1.10	0.226	29.00	0.75	0.58	0.118
21.50	0.94	1.08	0.238	29.50	0.74	0.58	0.120
22.00	0.87	1.04	0.240	30.00	0.73	0.58	0.124

Rhenium (single crystal)⁸ E || c

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	6.06	51.03	0.991	1.60	2.59	3.49	0.587
0.15	4.66	33.96	0.984	1.70	2.70	3.27	0.557
0.20	4.16	25.36	0.975	1.80	2.82	3.10	0.535
0.25	4.03	20.10	0.962	1.90	2.90	3.00	0.520
0.30	4.37	16.69	0.943	2.00	2.97	2.91	0.510
0.35	4.50	14.53	0.925	2.10	3.03	2.86	0.504
0.40	4.53	12.96	0.909	2.20	3.06	2.84	0.501
0.45	4.53	11.78	0.893	2.30	3.07	2.82	0.499
0.50	4.53	10.88	0.878	2.40	3.06	2.81	0.498
0.55	4.50	10.26	0.867	2.50	3.02	2.80	0.497
0.60	4.29	9.75	0.861	2.60	2.96	2.77	0.493
0.65	4.07	9.35	0.856	2.70	2.89	2.68	0.482
0.70	3.80	8.94	0.853	2.80	2.89	2.57	0.468
0.75	3.48	8.55	0.850	2.90	2.99	2.47	0.457
0.80	3.21	8.10	0.846	3.00	3.11	2.57	0.470
0.85	2.96	7.68	0.841	3.20	2.90	2.68	0.482
0.90	2.73	7.24	0.835	3.40	2.83	2.50	0.459
0.95	2.56	6.79	0.826	3.60	2.93	2.48	0.457
1.00	2.45	6.36	0.813	3.80	2.86	2.56	0.467
1.10	2.38	5.61	0.778	4.00	2.81	2.51	0.460
1.20	2.35	5.02	0.742	4.20	2.86	2.55	0.466
1.30	2.39	4.54	0.702	4.40	2.81	2.74	0.489
1.40	2.44	4.13	0.662	4.60	2.56	2.83	0.504
1.50	2.50	3.79	0.624	4.80	2.41	2.71	0.493

Rhenium (single crystal)⁸ E || c—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
5.00	2.39	2.68	0.488	16.40	1.19	1.27	0.259
5.20	2.34	2.75	0.500	16.80	1.14	1.29	0.269
5.40	2.20	2.81	0.515	17.00	1.12	1.30	0.275
5.60	2.02	2.84	0.530	17.40	1.07	1.30	0.286
5.80	1.83	2.80	0.538	18.00	0.99	1.30	0.300
6.00	1.65	2.71	0.541	18.40	0.93	1.29	0.311
6.20	1.54	2.59	0.532	18.80	0.87	1.28	0.321
6.40	1.45	2.50	0.526	19.20	0.81	1.25	0.330
6.80	1.32	2.31	0.508	19.60	0.77	1.21	0.332
7.00	1.26	2.23	0.500	20.00	0.73	1.18	0.333
7.20	1.20	2.15	0.493	20.40	0.70	1.14	0.332
7.40	1.16	2.06	0.480	20.80	0.67	1.11	0.332
7.60	1.12	1.99	0.470	21.20	0.64	1.08	0.334
7.80	1.08	1.89	0.454	21.60	0.61	1.04	0.335
8.00	1.05	1.80	0.435	22.00	0.58	1.01	0.340
8.20	1.05	1.71	0.411	22.40	0.55	0.97	0.341
8.40	1.05	1.62	0.386	22.80	0.53	0.93	0.338
8.60	1.06	1.55	0.360	23.20	0.51	0.89	0.334
8.80	1.09	1.48	0.336	23.60	0.50	0.85	0.329
9.00	1.11	1.43	0.317	24.00	0.48	0.80	0.319
9.20	1.13	1.39	0.301	24.40	0.48	0.76	0.207
9.40	1.16	1.34	0.281	24.80	0.47	0.72	0.296
9.60	1.18	1.32	0.274	25.20	0.47	0.68	0.282
9.80	1.20	1.29	0.264	25.60	0.47	0.65	0.270
10.00	1.23	1.26	0.252	26.00	0.47	0.61	0.255
10.20	1.25	1.25	0.246	26.40	0.48	0.57	0.240
10.40	1.28	1.25	0.242	26.80	0.48	0.54	0.225
10.60	1.29	1.25	0.242	27.20	0.49	0.51	0.208
10.80	1.30	1.26	0.244	27.60	0.50	0.48	0.193
11.00	1.30	1.27	0.247	28.00	0.51	0.45	0.176
11.20	1.29	1.28	0.249	29.00	0.54	0.39	0.145
11.40	1.28	1.28	0.252	30.00	0.57	0.33	0.114
11.60	1.26	1.28	0.252	31.00	0.62	0.29	0.086
11.80	1.24	1.26	0.249	32.00	0.66	0.26	0.065
12.00	1.23	1.24	0.244	33.00	0.68	0.24	0.054
12.40	1.22	1.21	0.237	34.00	0.72	0.21	0.041
12.80	1.21	1.18	0.230	35.00	0.76	0.20	0.031
13.20	1.22	1.16	0.222	36.00	0.79	0.20	0.025
13.60	1.22	1.13	0.215	37.00	0.82	0.19	0.021
14.00	1.24	1.12	0.209	38.00	0.85	0.20	0.018
14.40	1.27	1.11	0.204	39.00	0.89	0.21	0.016
14.80	1.29	1.15	0.213	40.00	0.88	0.26	0.022
15.20	1.29	1.19	0.225	42.00	0.88	0.26	0.022
15.60	1.26	1.22	0.236	44.00	0.89	0.29	0.026
16.00	1.23	1.25	0.248	46.00	0.85	0.32	0.035

Rhenium (single crystal)⁸ E || c —continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
48.00	0.82	0.30	0.036	54.00	0.72	0.30	0.055
50.00	0.80	0.30	0.038	56.00	0.66	0.24	0.061
52.00	0.78	0.30	0.044	58.00	0.65	0.16	0.055

Rhenium (single crystal)⁸ E ⊥ c

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	4.25	42.83	0.991	2.90	3.49	2.75	0.497
0.15	3.28	28.08	0.984	3.00	3.53	2.71	0.493
0.20	3.28	20.66	0.971	3.20	3.55	2.84	0.506
0.25	3.47	16.27	0.951	3.40	3.34	2.88	0.508
0.30	3.73	13.44	0.926	3.60	3.25	2.83	0.501
0.35	3.93	11.54	0.900	3.80	3.24	2.84	0.502
0.40	3.99	10.15	0.875	4.00	3.19	2.94	0.513
0.45	4.17	9.03	0.846	4.20	3.05	3.06	0.526
0.50	4.34	8.26	0.821	4.40	2.88	3.15	0.539
0.55	4.45	7.73	0.801	4.60	2.67	3.18	0.548
0.60	4.53	7.40	0.788	4.80	2.44	3.17	0.554
0.65	4.44	7.26	0.784	5.00	2.25	3.12	0.556
0.70	4.13	7.09	0.784	5.20	2.10	3.04	0.555
0.75	3.77	6.75	0.779	5.40	1.96	2.96	0.553
0.80	3.55	6.32	0.766	5.60	1.84	2.88	0.551
0.85	3.39	5.95	0.752	5.80	1.73	2.81	0.549
0.90	3.26	5.61	0.737	6.00	1.61	2.74	0.549
0.95	3.17	5.27	0.719	6.20	1.51	2.64	0.545
1.00	3.09	4.96	0.701	6.40	1.42	2.56	0.541
1.10	3.05	4.39	0.658	6.80	1.28	2.37	0.526
1.20	3.08	3.89	0.613	7.00	1.22	2.28	0.517
1.30	3.20	3.56	0.578	7.20	1.16	2.19	0.508
1.40	3.23	3.38	0.559	7.40	1.12	2.08	0.493
1.50	3.23	3.12	0.532	7.60	1.12	1.98	0.468
1.60	3.29	2.88	0.507	7.80	1.08	1.93	0.463
1.70	3.38	2.72	0.491	8.00	1.05	1.83	0.443
1.80	3.47	2.59	0.480	8.20	1.05	1.74	0.418
1.90	3.54	2.50	0.473	8.40	1.05	1.66	0.397
2.00	3.63	2.43	0.469	8.60	1.06	1.58	0.372
2.10	3.74	2.40	0.470	8.80	1.07	1.52	0.351
2.20	3.83	2.38	0.472	9.00	1.09	1.46	0.327
2.30	3.93	2.44	0.481	9.20	1.11	1.41	0.309
2.40	4.00	2.55	0.492	9.40	1.14	1.36	0.290
2.50	4.01	2.70	0.505	9.60	1.17	1.31	0.273
2.60	3.90	2.84	0.514	9.80	1.20	1.27	0.258
2.70	3.74	2.92	0.517	10.00	1.24	1.24	0.244
2.80	3.57	2.88	0.511	10.20	1.29	1.22	0.234

Rhenium (single crystal)⁸ E ⊥ c —continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
10.40	1.33	1.23	0.233	23.20	0.53	0.89	0.322
10.60	1.36	1.25	0.238	23.60	0.52	0.85	0.317
10.80	1.38	1.28	0.245	24.00	0.50	0.82	0.314
11.00	1.37	1.31	0.253	24.40	0.49	0.79	0.309
11.20	1.36	1.33	0.259	24.40	0.49	0.79	0.309
11.40	1.33	1.34	0.264	24.80	0.48	0.75	0.303
11.60	1.31	1.34	0.266	25.20	0.47	0.72	0.295
11.80	1.28	1.33	0.266	25.60	0.47	0.68	0.286
12.00	1.26	1.32	0.264	26.00	0.46	0.64	0.276
12.40	1.23	1.29	0.257	26.40	0.46	0.61	0.263
12.80	1.22	1.26	0.251	26.80	0.46	0.57	0.249
13.20	1.20	1.23	0.245	27.20	0.47	0.53	0.231
13.60	1.19	1.20	0.236	27.60	0.48	0.50	0.216
14.00	1.20	1.16	0.225	28.00	0.49	0.47	0.198
14.40	1.22	1.13	0.214	29.00	0.51	0.41	0.164
14.80	1.27	1.12	0.207	30.00	0.55	0.34	0.129
15.20	1.31	1.17	0.218	31.00	0.59	0.29	0.097
15.60	1.31	1.23	0.234	32.00	0.64	0.26	0.072
16.00	1.28	1.28	0.251	33.00	0.67	0.24	0.060
16.40	1.24	1.33	0.270	34.00	0.70	0.22	0.047
16.80	1.17	1.37	0.288	35.00	0.74	0.20	0.036
17.00	1.14	1.38	0.297	36.00	0.77	0.19	0.029
17.40	1.06	1.39	0.314	37.00	0.80	0.19	0.023
18.00	0.95	1.38	0.334	38.00	0.84	0.19	0.018
18.40	0.88	1.36	0.346	39.00	0.88	0.21	0.016
18.80	0.82	1.33	0.355	40.00	0.87	0.25	0.023
19.20	0.76	1.29	0.360	42.00	0.87	0.25	0.023
19.60	0.72	1.25	0.363	44.00	0.88	0.28	0.026
20.00	0.67	1.21	0.369	46.00	0.84	0.31	0.035
20.40	0.64	1.15	0.364	48.00	0.82	0.30	0.036
20.80	0.61	1.10	0.357	50.00	0.80	0.30	0.039
21.20	0.60	1.06	0.349	52.00	0.77	0.30	0.044
21.60	0.58	1.02	0.342	54.00	0.71	0.29	0.055
22.00	0.57	0.98	0.336	56.00	0.66	0.23	0.061
22.40	0.56	0.95	0.328	58.00	0.64	0.16	0.055

Rhodium⁹

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	18.48	69.43	0.986	0.70	3.67	11.72	0.908
0.20	8.66	37.46	0.977	0.80	3.63	10.34	0.887
0.30	5.85	25.94	0.967	0.90	3.62	9.36	0.867
0.40	4.74	19.80	0.955	1.00	3.71	8.67	0.848
0.50	4.20	16.07	0.941	1.10	3.67	8.26	0.837
0.60	3.87	13.51	0.925	1.20	3.51	7.94	0.832

Rhodium⁹—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
1.30	3.26	7.63	0.829	7.80	0.68	1.20	0.363
1.40	3.01	7.31	0.827	8.00	0.69	1.12	0.329
1.50	2.78	6.97	0.823	8.20	0.71	1.04	0.288
1.60	2.60	6.64	0.818	8.40	0.74	0.97	0.252
1.70	2.42	6.33	0.813	8.60	0.78	0.89	0.212
1.80	2.30	6.02	0.805	8.80	0.83	0.83	0.179
1.90	2.20	5.76	0.798	9.00	0.88	0.77	0.148
2.00	2.12	5.51	0.789	9.20	0.95	0.73	0.125
2.10	2.05	5.30	0.780	9.40	1.01	0.71	0.110
2.20	2.00	5.11	0.772	9.60	1.07	0.69	0.102
2.30	1.94	4.94	0.765	9.80	1.12	0.69	0.098
2.40	1.90	4.78	0.756	10.00	1.17	0.69	0.098
2.50	1.88	4.65	0.748	10.60	1.26	0.73	0.106
2.60	1.85	4.55	0.743	11.00	1.29	0.76	0.113
2.70	1.80	4.49	0.742	11.60	1.32	0.80	0.124
2.90	1.63	4.36	0.748	12.00	1.32	0.82	0.127
3.00	1.53	4.29	0.753	12.60	1.32	0.82	0.129
3.10	1.41	4.20	0.760	13.00	1.32	0.83	0.131
3.20	1.30	4.09	0.764	13.60	1.32	0.85	0.134
3.30	1.20	3.97	0.767	14.00	1.32	0.86	0.138
3.40	1.11	3.84	0.769	14.60	1.30	0.89	0.144
3.50	1.04	3.71	0.768	15.00	1.28	0.90	0.147
3.60	0.99	3.58	0.764	15.60	1.25	0.90	0.147
3.70	0.95	3.45	0.759	16.00	1.24	0.89	0.147
3.80	0.91	3.34	0.753	16.50	1.23	0.88	0.145
3.90	0.88	3.23	0.747	17.00	1.22	0.88	0.144
4.00	0.86	3.12	0.739	17.50	1.22	0.87	0.143
4.20	0.83	2.94	0.722	18.00	1.23	0.88	0.145
4.40	0.80	2.76	0.706	18.50	1.25	0.92	0.155
4.60	0.78	2.60	0.684	19.00	1.24	0.98	0.172
4.80	0.79	2.46	0.659	19.50	1.18	1.05	0.193
5.00	0.79	2.34	0.635	20.00	1.10	1.09	0.213
5.20	0.79	2.23	0.613	20.50	1.00	1.09	0.230
5.40	0.80	2.14	0.591	21.00	0.91	1.05	0.234
5.60	0.80	2.06	0.573	21.50	0.86	1.00	0.228
5.80	0.79	2.00	0.561	22.00	0.83	0.95	0.219
6.00	0.76	1.93	0.556	22.50	0.81	0.92	0.214
6.20	0.73	1.85	0.544	23.00	0.79	0.90	0.213
6.40	0.70	1.77	0.534	23.50	0.75	0.87	0.214
6.60	0.68	1.69	0.518	24.00	0.73	0.84	0.210
6.80	0.67	1.60	0.498	24.50	0.70	0.81	0.208
7.00	0.66	1.52	0.476	25.00	0.69	0.77	0.202
7.20	0.66	1.43	0.452	25.50	0.67	0.74	0.195
7.40	0.66	1.35	0.423	26.00	0.66	0.70	0.188
7.60	0.67	1.27	0.394	26.50	0.65	0.66	0.176

Rhodium⁹—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
27.00	0.65	0.64	0.168	33.00	0.60	0.37	0.110
27.50	0.65	0.61	0.159	34.00	0.65	0.30	0.074
28.00	0.65	0.59	0.152	35.00	0.69	0.28	0.058
29.00	0.65	0.54	0.137	36.00	0.73	0.27	0.049
30.00	0.66	0.51	0.127	37.00	0.74	0.28	0.047
31.00	0.64	0.49	0.127	38.00	0.74	0.27	0.045
32.00	0.61	0.44	0.126	39.00	0.75	0.25	0.041

Silicon (single crystal)¹⁷

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.01240	0.65	2.90E-04	0.300	0.2170			4.05E-07
0.01488	3.4190	2.30E-04	0.300	0.2232			3.94E-07
0.01736	3.4192	1.90E-04	0.300	0.2294			3.26E-07
0.01984	3.4195	1.70E-04	0.300	0.2356			2.97E-07
0.02480	3.4197		0.300	0.2418			2.82E-07
0.03100	3.4199		0.300	0.2480	3.4261	1.99E-07	0.300
0.04092	3.4200		0.300	0.3100	3.4294		0.301
0.04463		1.08E-04		0.3626	3.4327		0.301
0.04959	3.4201	9.15E-05	0.300	0.4568	3.4393	2.50E-09	0.302
0.05703		1.56E-04		0.6199	3.4490		0.303
0.06199	3.4204	2.86E-04	0.300	0.8093	3.4784		0.306
0.06943		3.84E-04		1.033	3.5193		0.311
0.07439		7.16E-04		1.1	(3.5341)	1.30E-05	0.312
0.08059	(3.4207)	1.52E-04	0.300	1.2			1.80E-04
0.08679		1.02E-04		1.3			2.26E-03
0.09299		2.59E-04		1.4			7.75E-03
0.09919		1.77E-04		1.5	3.673	5.00E-03	0.327
0.1054		1.53E-04		1.6	3.714	8.00E-03	0.331
0.1116		2.02E-04		1.7	3.752	1.00E-02	0.335
0.1178		1.22E-04		1.8	3.796	0.013	0.340
0.1240	3.4215	6.76E-05	0.300	1.9	3.847	0.016	0.345
0.1364		5.49E-05		2.0	3.906	0.022	0.351
0.1488		2.41E-05		2.1	3.969	0.030	0.357
0.1612		2.49E-05		2.2	4.042	0.032	0.364
0.1736	(3.4230)	1.68E-05	0.300	2.3	4.123	0.048	0.372
0.1798		2.45E-05		2.4	4.215	0.060	0.380
0.1860		2.66E-06		2.5	4.320	0.073	0.390
0.1922		1.74E-06		2.6	4.442	0.090	0.400
0.1984		8.46E-07		2.7	4.583	0.130	0.412
0.2046		5.64E-07		2.8	4.753	0.163	0.426
0.2108	(3.4244)	4.17E-07	0.300	2.9	4.961	0.203	0.442

Silicon (single crystal)¹⁷—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
3.0	5.222	0.269	0.461	5.7	1.180	3.112	0.673
3.1	5.570	0.387	0.486	5.8	1.133	3.045	0.672
3.2	6.062	0.630	0.518	5.9	1.083	2.982	0.673
3.3	6.709	1.321	0.561	6.0	1.010	2.909	0.677
3.4	6.522	2.705	0.592	6.5	0.847	2.73	0.688
3.5	5.610	3.014	0.575	7.0	0.682	2.45	0.691
3.6	5.296	2.987	0.564	7.5	0.563	2.21	0.693
3.7	5.156	3.058	0.563	8.0	0.478	2.00	0.691
3.8	5.065	3.182	0.568	8.5	0.414	1.82	0.688
3.9	5.016	3.346	0.577	9.0	0.367	1.66	0.683
4.0	5.010	3.587	0.591	9.5	0.332	1.51	0.672
4.1	5.020	3.979	0.614	10.0	0.306	1.38	0.661
4.2	4.888	4.639	0.652	12.0	0.257	0.963	0.590
4.3	4.086	5.395	0.703	14.0	0.275	0.641	0.460
4.4	3.120	5.344	0.726	16.0	0.345	0.394	0.297
4.5	2.451	5.082	0.740	18.0	0.455	0.219	0.159
4.6	1.988	4.678	0.742	20.0	0.567	0.0835	0.079
4.7	1.764	4.278	0.728	22.14	0.675	0.0405	0.038
4.8	1.658	3.979	0.710	24.31	0.752	0.0243	0.020
4.9	1.597	3.749	0.693	26.38	0.803	0.0178	0.012
5.0	1.570	3.565	0.675	28.18	0.834	0.0152	0.008
5.1	1.571	3.429	0.658	30.24	0.860	0.0138	0.006
5.2	1.589	3.354	0.646	31.79	0.877	0.0132	0.004
5.3	1.579	3.353	0.647	34.44	0.899	0.0121	0.003
5.4	1.471	3.366	0.663	36.47	0.913	0.0113	0.002
5.5	1.340	3.302	0.673	38.75	0.925	0.0104	0.002
5.6	1.247	3.206	0.675	40.00	0.930	0.0100	0.001

Silver⁶

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	9.91	90.27	0.995	3.60	0.23	1.13	0.671
0.20	2.84	45.70	0.995	3.70	0.30	0.77	0.475
0.30	1.41	30.51	0.994	3.77	0.53	0.40	0.154
0.40	0.91	22.89	0.993	3.80	0.73	0.30	0.053
0.50	0.67	18.32	0.992	3.90	1.30	0.36	0.040
1.00	0.28	9.03	0.987	4.00	1.61	0.60	0.103
1.50	0.27	5.79	0.969	4.10	1.73	0.85	0.153
2.00	0.27	4.18	0.944	4.20	1.75	1.06	0.194
2.50	0.24	3.09	0.914	4.30	1.73	1.13	0.208
3.00	0.23	2.27	0.864	4.50	1.69	1.28	0.238
3.25	0.23	1.86	0.816	4.75	1.61	1.34	0.252
3.50	0.21	1.42	0.756	5.00	1.55	1.36	0.257

Silver⁶—continued

Energy eV	n	k	R($\phi = 0$)	Energy eV	n	k	R($\phi = 0$)
5.50	1.45	1.34	0.257	29.00	0.92	0.56	0.079
6.00	1.34	1.28	0.246	30.00	0.93	0.54	0.074
6.50	1.25	1.18	0.225	31.00	0.93	0.53	0.072
7.00	1.18	1.06	0.196	32.00	0.92	0.53	0.072
7.50	1.14	0.91	0.157	33.00	0.90	0.51	0.071
8.00	1.16	0.75	0.114	34.00	0.88	0.49	0.067
9.00	1.33	0.56	0.074	35.00	0.86	0.45	0.061
10.00	1.46	0.56	0.082	36.00	0.89	0.44	0.055
11.00	1.52	0.56	0.088	38.00	0.89	0.39	0.043
12.00	1.61	0.59	0.100	40.00	0.90	0.37	0.039
13.00	1.66	0.64	0.112	42.00	0.90	0.35	0.036
14.00	1.72	0.78	0.141	44.00	0.90	0.33	0.033
14.50	1.64	0.88	0.152	46.00	0.90	0.32	0.031
15.00	1.56	0.92	0.156	48.00	0.89	0.31	0.030
16.00	1.42	0.91	0.151	50.00	0.88	0.29	0.027
17.00	1.33	0.86	0.139	52.00	0.89	0.28	0.024
18.00	1.28	0.80	0.124	54.00	0.88	0.17	0.024
19.00	1.27	0.75	0.111	56.00	0.87	0.26	0.024
20.00	1.29	0.71	0.103	58.00	0.87	0.24	0.021
21.00	1.35	0.75	0.112	60.00	0.87	0.22	0.018
21.50	1.37	0.80	0.124	62.00	0.88	0.21	0.016
22.00	1.34	0.87	0.141	64.00	0.88	0.21	0.016
22.50	1.26	0.93	0.157	66.00	0.88	0.21	0.016
23.00	1.17	0.94	0.163	68.00	0.87	0.21	0.017
23.50	1.10	0.93	0.165	70.00	0.83	0.20	0.021
24.00	1.04	0.90	0.165	72.00	0.85	0.18	0.016
24.50	0.99	0.87	0.160	74.00	0.85	0.17	0.014
25.00	0.95	0.83	0.154	76.00	0.85	0.16	0.013
25.50	0.91	0.78	0.144	78.00	0.85	0.15	0.013
26.00	0.90	0.74	0.133	80.00	0.85	0.14	0.012
26.50	0.89	0.69	0.121	85.00	0.85	0.11	0.011
27.00	0.89	0.65	0.109	90.00	0.85	0.08	0.009
27.50	0.89	0.62	0.099	95.00	0.86	0.06	0.007
28.00	0.90	0.59	0.090	100.00	0.87	0.04	0.005

Tantalum¹²

Energy eV	n	k	R($\phi = 0$)	Energy eV	n	k	R($\phi = 0$)
0.10	10.14	66.39	0.9380	0.50	1.37	14.26	0.974
0.15	9.45	46.41	0.983	0.58	1.15	12.19	0.970
0.20	5.77	35.46	0.982	0.70	0.96	9.92	0.962
0.26	3.67	27.53	0.981	0.78	0.89	8.77	0.956
0.30	2.87	23.90	0.980	0.90	0.84	7.38	0.942
0.38	2.03	18.87	0.978	1.00	0.89	6.47	0.996

Tantalum¹²—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
1.10	0.93	5.75	0.899	8.60	1.14	1.45	0.317
1.20	0.98	5.14	0.872	8.80	1.17	1.41	0.301
1.30	1.00	4.62	0.842	9.00	1.19	1.40	0.294
1.40	1.04	4.15	0.805	9.20	1.21	1.38	0.289
1.50	1.09	3.73	0.762	9.40	1.21	1.38	0.287
1.60	1.15	3.33	0.707	9.60	1.21	1.38	0.285
1.70	1.24	2.95	0.640	9.80	1.21	1.37	0.285
1.80	1.35	2.60	0.560	10.00	1.20	1.37	0.286
1.90	1.57	2.24	0.460	10.20	1.19	1.37	0.286
2.00	1.83	1.99	0.388	10.40	1.18	1.37	0.287
2.10	2.10	1.84	0.354	10.60	1.16	1.36	0.288
2.20	2.36	1.81	0.351	10.80	1.15	1.36	0.289
2.30	2.56	1.86	0.365	11.00	1.13	1.35	0.290
2.40	2.68	1.92	0.378	11.20	1.11	1.35	0.292
2.50	2.75	1.98	0.388	11.40	1.09	1.34	0.293
2.60	2.80	2.02	0.395	11.60	1.07	1.33	0.294
2.70	2.84	2.08	0.405	11.80	1.05	1.32	0.295
2.80	2.85	2.14	0.412	12.00	1.02	1.31	0.296
2.90	2.84	2.20	0.420	12.20	1.00	1.29	0.295
3.00	2.81	2.24	0.425	12.40	0.98	1.28	0.294
3.20	2.73	2.31	0.432	12.60	0.96	1.26	0.292
3.40	2.61	2.33	0.435	12.80	0.94	1.24	0.289
3.60	2.49	2.30	0.430	13.00	0.93	1.22	0.286
3.80	2.40	2.22	0.418	13.60	0.91	1.16	0.272
4.00	2.36	2.14	0.406	14.00	0.90	1.15	0.272
4.20	2.35	2.06	0.392	14.60	0.85	1.15	0.285
4.40	2.39	2.01	0.384	15.00	0.80	1.13	0.293
4.60	2.45	2.00	0.384	15.60	0.72	1.08	0.301
4.80	2.53	2.06	0.394	16.00	0.68	1.04	0.304
5.00	2.58	2.20	0.416	16.60	0.63	0.97	0.301
5.20	2.52	2.44	0.450	17.00	0.60	0.92	0.296
5.40	2.31	2.61	0.480	17.60	0.60	0.92	0.296
5.60	2.06	2.67	0.501	18.00	0.55	0.79	0.274
5.80	1.83	2.63	0.510	18.60	0.53	0.71	0.254
6.00	1.63	2.56	0.515	19.00	0.53	0.65	0.236
6.20	1.48	2.45	0.512	19.60	0.53	0.57	0.207
6.40	1.37	2.33	0.504	20.00	0.54	0.52	0.185
6.60	1.29	2.22	0.492	20.60	0.55	0.44	0.152
6.80	1.23	2.11	0.478	21.00	0.57	0.39	0.127
7.00	1.18	2.01	0.462	21.60	0.64	0.34	0.089
7.20	1.15	1.91	0.445	22.00	0.64	0.32	0.081
7.40	1.13	1.82	0.425	22.60	0.69	0.27	0.058
7.60	1.12	1.75	0.406	23.00	0.73	0.24	0.043
7.80	1.11	1.68	0.390	23.60	0.80	0.26	0.033
8.00	1.11	1.61	0.370	24.00	0.80	0.26	0.034
8.20	1.12	1.55	0.350	24.60	0.82	0.25	0.029
8.40	1.13	1.50	0.332	25.00	0.83	0.25	0.026

Tantalum¹²—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
25.60	0.86	0.24	0.022	31.00	0.97	0.23	0.014
26.00	0.88	0.25	0.022	32.00	0.98	0.24	0.015
26.60	0.87	0.26	0.023	33.00	0.98	0.25	0.015
27.00	0.87	0.25	0.022	34.00	0.99	0.25	0.016
27.60	0.89	0.23	0.019	35.00	0.99	0.26	0.017
28.00	0.90	0.23	0.017	36.00	0.99	0.27	0.018
28.60	0.91	0.22	0.015	37.00	0.99	0.28	0.019
29.00	0.92	0.22	0.014	38.00	0.98	0.28	0.021
29.60	0.94	0.22	0.014	39.00	0.97	0.29	0.022
30.00	0.95	0.22	0.014	40.00	0.95	0.29	0.023

Titanium (polycrystalline)¹⁸

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	5.03	23.38	0.965	2.30	1.86	2.56	0.495
0.15	3.00	15.72	0.954	2.40	1.81	2.47	0.483
0.20	2.12	11.34	0.939	2.50	1.78	2.39	0.471
0.25	2.05	8.10	0.890	2.60	1.75	2.34	0.462
0.30	6.39	9.94	0.833	2.70	1.71	2.29	0.456
0.35	2.74	6.21	0.792	2.80	1.68	2.25	0.451
0.40	2.49	4.68	0.708	2.90	1.63	2.21	0.447
0.45	3.35	3.25	0.545	3.00	1.59	2.17	0.444
0.50	4.43	3.22	0.555	3.10	1.55	2.15	0.442
0.60	4.71	3.77	0.597	3.20	1.50	2.12	0.442
0.70	4.38	3.89	0.603	3.30	1.44	2.09	0.442
0.80	4.04	3.82	0.596	3.40	1.37	2.06	0.443
0.90	3.80	3.65	0.582	3.50	1.30	2.01	0.443
1.00	3.62	3.52	0.570	3.60	1.24	1.96	0.441
1.10	3.47	3.40	0.560	3.70	1.17	1.90	0.436
1.20	3.35	3.30	0.550	3.80	1.11	1.83	0.430
1.30	3.28	3.25	0.546	3.85	1.08	1.78	0.423
1.40	3.17	3.28	0.549	3.90	1.06	1.73	0.413
1.50	2.98	3.32	0.557	4.00	1.04	1.62	0.389
1.60	2.74	3.30	0.559	4.20	1.05	1.45	0.333
1.70	2.54	3.23	0.557	4.40	1.13	1.33	0.284
1.80	2.36	3.11	0.550	4.60	1.17	1.29	0.265
1.90	2.22	2.99	0.540	4.80	1.21	1.23	0.244
2.00	2.11	2.88	0.530	5.00	1.24	1.21	0.236
2.10	2.01	2.77	0.520	5.20	1.27	1.20	0.228
2.20	1.92	2.67	0.509	5.40	1.17	1.16	0.228

Titanium (polycrystalline)¹⁸—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
5.60	1.24	1.21	0.234	14.40	0.77	0.42	0.069
5.80	1.21	1.22	0.241	14.80	0.79	0.38	0.058
6.00	1.15	1.21	0.244	15.20	0.79	0.36	0.052
6.20	1.11	1.18	0.240	15.60	0.79	0.32	0.045
6.40	1.08	1.14	0.232	16.00	0.83	0.31	0.037
6.60	1.04	1.06	0.212	16.40	0.84	0.28	0.030
6.80	1.05	1.02	0.198	16.80	0.87	0.27	0.025
7.00	1.06	0.97	0.182	17.20	0.90	0.25	0.020
7.20	1.07	0.95	0.175	17.60	0.93	0.25	0.017
7.40	1.11	0.94	0.167	18.00	0.94	0.24	0.016
7.60	1.09	0.92	0.165	18.40	0.94	0.23	0.017
7.80	1.11	0.93	0.165	18.80	0.95	0.24	0.016
8.00	1.10	0.94	0.169	19.20	0.96	0.25	0.016
8.20	1.10	0.95	0.171	19.60	0.97	0.25	0.017
8.40	1.08	0.95	0.175	20.00	0.98	0.27	0.018
8.60	1.04	0.96	0.181	20.40	0.98	0.27	0.019
8.80	1.02	0.95	0.181	20.60	1.00	0.29	0.020
9.00	1.00	0.94	0.182	21.20	0.99	0.31	0.023
9.20	0.97	0.93	0.182	21.60	0.99	0.31	0.024
9.40	0.95	0.91	0.181	22.00	0.98	0.32	0.025
9.60	0.94	0.90	0.179	22.40	0.98	0.33	0.027
9.80	0.91	0.88	0.179	22.80	0.97	0.33	0.028
10.00	0.89	0.88	0.180	23.20	0.96	0.34	0.030
10.20	0.86	0.85	0.178	23.60	0.95	0.35	0.031
10.40	0.85	0.83	0.175	24.00	0.92	0.35	0.033
10.60	0.81	0.79	0.167	24.5	0.91	0.34	0.032
10.80	0.80	0.76	0.162	25.0	0.91	0.33	0.032
11.00	0.79	0.72	0.152	25.5	0.89	0.33	0.032
11.20	0.81	0.69	0.139	26.0	0.89	0.33	0.032
11.40	0.81	0.69	0.139	26.5	0.88	0.32	0.032
11.60	0.79	0.68	0.139	27.0	0.86	0.31	0.032
11.80	0.78	0.67	0.137	27.5	0.85	0.30	0.033
12.00	0.77	0.65	0.132	28.0	0.84	0.29	0.033
12.80	0.76	0.55	0.106	28.5	0.82	0.26	0.029
13.20	0.76	0.52	0.097	29.0	0.83	0.25	0.027
13.60	0.76	0.48	0.087	30.0	0.84	0.22	0.022
14.00	0.77	0.45	0.077				

Tungsten¹⁹

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	14.06	54.71	0.983	3.40	3.39	2.66	0.485
0.20	3.87	28.30	0.981	3.50	3.24	2.70	0.488
0.25	2.56	22.44	0.980	3.60	3.13	2.67	0.482
0.30	1.83	18.32	0.979	3.70	3.05	2.62	0.476
0.34	1.71	15.71	0.973	3.80	2.99	2.56	0.468
0.38	1.86	13.88	0.963	3.90	2.96	2.50	0.460
0.42	1.92	12.63	0.954	4.00	2.95	2.43	0.451
0.46	1.69	11.59	0.952	4.20	3.02	2.33	0.440
0.50	1.40	10.52	0.952	4.40	3.13	2.32	0.442
0.54	1.23	9.45	0.948	4.60	3.24	2.41	0.455
0.58	1.17	8.44	0.938	4.80	3.33	2.57	0.475
0.62	1.28	7.52	0.917	5.00	3.40	2.85	0.505
0.66	1.45	6.78	0.888	5.20	3.27	3.27	0.548
0.70	1.59	6.13	0.856	5.40	2.92	3.58	0.586
0.74	1.83	5.52	0.810	5.60	2.43	3.70	0.618
0.78	2.12	5.00	0.759	5.80	2.00	3.61	0.637
0.82	2.36	4.61	0.710	6.00	1.70	3.42	0.643
0.86	2.92	4.37	0.661	6.20	1.47	3.24	0.646
0.90	3.11	4.44	0.660	6.40	1.32	3.04	0.640
0.94	3.15	4.43	0.658	6.60	1.21	2.87	0.631
0.98	3.15	4.36	0.653	6.80	1.12	2.70	0.619
1.00	3.14	4.32	0.649	7.00	1.06	2.56	0.607
1.10	3.05	4.04	0.627	7.20	1.01	2.43	0.593
1.20	3.00	3.64	0.590	7.40	0.98	2.30	0.573
1.30	3.12	3.24	0.545	7.60	0.95	2.18	0.556
1.40	3.29	2.96	0.515	7.80	0.93	2.06	0.533
1.50	3.48	2.79	0.500	8.00	0.94	1.95	0.505
1.60	3.67	2.68	0.494	8.20	0.94	1.86	0.481
1.70	3.84	2.79	0.507	8.40	0.96	1.76	0.449
1.80	3.82	2.91	0.518	8.60	0.99	1.70	0.422
1.90	3.70	2.94	0.518	8.80	1.01	1.65	0.401
2.00	3.60	2.89	0.512	9.00	1.01	1.60	0.388
2.10	3.54	2.84	0.506	9.20	1.02	1.55	0.369
2.20	3.49	2.76	0.497	9.40	1.03	1.50	0.352
2.30	3.49	2.72	0.494	9.60	1.05	1.44	0.329
2.40	3.45	2.72	0.493	9.80	1.09	1.38	0.307
2.50	3.38	2.68	0.487	10.00	1.13	1.34	0.287
2.60	3.34	2.62	0.480	10.20	1.19	1.33	0.274
2.70	3.31	2.55	0.472	10.40	1.24	1.34	0.270
2.80	3.31	2.49	0.466	10.60	1.27	1.36	0.274
2.90	3.32	2.45	0.461	10.80	1.29	1.39	0.282
3.00	3.35	2.42	0.459	11.00	1.28	1.42	0.290
3.10	3.39	2.41	0.460	11.20	1.27	1.44	0.297
3.20	3.43	2.45	0.465	11.40	1.25	1.46	0.305
3.30	3.45	2.55	0.476	11.60	1.22	1.48	0.313

Tungsten¹⁹—continued

Energy eV	n	k	R($\phi = 0$)	Energy eV	n	k	R($\phi = 0$)
11.80	1.20	1.48	0.318	22.80	0.49	0.69	0.272
12.00	1.16	1.48	0.323	23.20	0.49	0.66	0.263
12.40	1.10	1.47	0.329	23.60	0.48	0.62	0.252
12.80	1.04	1.44	0.333	24.00	0.49	0.57	0.234
13.20	0.98	1.40	0.332	24.40	0.50	0.53	0.213
13.60	0.94	1.35	0.325	24.80	0.51	0.49	0.191
14.00	0.91	1.28	0.312	25.20	0.53	0.46	0.171
14.40	0.90	1.23	0.296	25.60	0.55	0.43	0.150
14.80	0.90	1.17	0.276	26.00	0.57	0.40	0.132
15.20	0.93	1.13	0.255	26.40	0.59	0.38	0.117
15.60	0.97	1.12	0.246	26.80	0.61	0.37	0.105
16.00	0.98	1.14	0.249	27.00	0.62	0.36	0.099
16.40	0.97	1.17	0.260	27.50	0.64	0.34	0.085
16.80	0.94	1.19	0.273	28.00	0.67	0.32	0.073
17.20	0.90	1.21	0.289	28.50	0.69	0.31	0.065
17.60	0.85	1.21	0.304	29.00	0.71	0.30	0.057
18.00	0.80	1.20	0.317	29.50	0.73	0.30	0.052
18.40	0.74	1.18	0.330	30.00	0.75	0.29	0.047
18.80	0.69	1.15	0.340	31.00	0.78	0.29	0.042
19.20	0.64	1.11	0.347	32.00	0.79	0.29	0.040
19.60	0.60	1.07	0.353	33.00	0.82	0.28	0.033
20.00	0.56	1.02	0.354	34.00	0.84	0.29	0.032
20.40	0.54	0.97	0.350	35.00	0.85	0.31	0.033
20.80	0.52	0.92	0.342	36.00	0.85	0.32	0.036
21.20	0.50	0.87	0.331	37.00	0.84	0.33	0.039
21.60	0.50	0.82	0.318	38.00	0.83	0.33	0.040
22.00	0.49	0.77	0.303	39.00	0.81	0.33	0.042
22.40	0.49	0.73	0.287	40.00	0.80	0.33	0.045

Zinc, E || c²⁰

Energy eV	n	k	R($\phi = 0$)	Energy eV	n	k	R($\phi = 0$)
0.7514	1.9241	7.5619	0.883	1.377	2.9459	3.5761	0.584
0.827	1.7921	6.9973	0.874	1.459	3.2523	4.2447	0.640
0.866	1.5571	6.7753	0.881	1.550	3.8086	4.6212	0.657
0.952	1.4824	6.2296	0.868	1.653	3.7577	4.6239	0.659
0.992	1.5762	5.8843	0.847	1.722	3.5908	4.4614	0.650
1.033	1.5407	5.3192	0.823	1.823	3.4234	4.3232	0.642
1.078	1.5853	4.9013	0.793	1.937	3.0132	3.9974	0.624
1.127	1.7768	4.5307	0.748	1.984	1.8562	3.9706	0.690
1.181	1.9808	4.2004	0.701	2.066	1.4856	4.0555	0.737
1.240	2.8821	3.4766	0.575	2.094	1.2525	3.9961	0.762
1.305	3.2039	3.0042	0.520	2.119	1.0017	3.8683	0.789

Zinc, E || c²⁰—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
2.275	0.7737	3.9129	0.832	3.220	0.3069	2.5088	0.847
2.445	0.6395	3.4013	0.821	3.594	0.2737	2.1737	0.828
2.666	0.4430	3.1379	0.851	4.065	0.2510	1.8528	0.799
2.917	0.3589	2.8140	0.853	4.678	0.2354	1.6357	0.776

Zinc, E ⊥ c²⁰

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.751	1.4469	7.4158	0.905	1.722	3.9369	4.6356	0.657
0.827	1.4744	6.9688	0.892	1.823	3.7549	4.3042	0.635
0.866	1.3628	6.6886	0.892	1.937	3.4512	4.1942	0.631
0.952	1.3165	6.2212	0.881	1.984	3.2515	4.2980	0.644
0.992	1.3835	5.8910	0.863	2.066	2.0802	4.7231	0.738
1.033	1.2889	5.4001	0.850	2.094	1.7084	4.7923	0.774
1.078	1.3095	4.9025	0.822	2.119	1.3329	4.4751	0.791
1.127	1.6897	4.4062	0.746	2.275	0.9725	4.2879	0.825
1.181	1.9701	4.0176	0.684	2.255	0.7568	3.7627	0.824
1.240	2.8717	3.2873	0.555	2.666	0.5470	3.4277	0.845
1.305	3.3991	2.7684	0.497	2.917	0.4774	3.0476	0.834
1.377	3.1807	3.4709	0.569	3.220	0.3911	2.7463	0.835
1.459	3.5064	4.1994	0.630	3.594	0.3147	2.3041	0.821
1.550	4.1241	4.7768	0.664	4.06	0.3013	2.0077	0.789
1.653	4.0269	4.8027	0.667	4.678	0.2806	1.7997	0.770

Zirconium (polycrystalline)²⁰

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
0.10	6.18	1.76	0.300	0.50	4.13	1.44	0.175
0.15	3.37	1.30	0.123	0.56	5.01	1.58	0.231
0.20	2.34	1.08	0.058	0.60	5.18	1.61	0.242
0.26	2.24	1.06	0.052	0.70	4.54	1.51	0.202
0.30	2.59	1.14	0.073	0.80	4.03	1.42	0.168
0.36	3.17	1.26	0.110	0.90	3.74	1.37	0.149
0.40	3.09	1.24	0.105	0.96	3.69	1.36	0.145
0.46	3.36	1.30	0.123	1.00	3.66	1.35	0.143

Zirconium (polycrystalline)²⁰—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
1.10	3.65	1.35	0.142	8.00	1.66	0.91	0.026
1.20	3.53	1.33	0.134	8.20	0.67	0.91	0.026
1.30	3.25	1.27	0.116	8.40	1.68	0.92	0.026
1.40	3.10	1.25	0.106	8.60	1.68	0.92	0.026
1.50	3.02	1.23	0.100	8.80	1.66	0.91	0.026
1.60	2.88	1.20	0.091	9.00	1.65	0.91	0.025
1.70	2.68	1.16	0.078	9.20	1.63	0.90	0.025
1.80	2.49	1.12	0.067	9.40	1.60	0.89	0.024
2.00	2.14	1.03	0.047	9.60	1.57	0.89	0.023
2.10	1.99	1.00	0.040	9.80	1.52	0.87	0.021
2.20	1.87	0.97	0.034	10.00	1.47	0.86	0.020
2.30	1.78	0.94	0.030	10.20	1.42	0.84	0.018
2.40	1.71	0.92	0.027	10.40	1.35	0.82	0.016
2.50	1.62	0.90	0.024	10.50	1.32	0.81	0.016
2.60	1.54	0.88	0.022	10.60	1.28	0.80	0.015
2.70	1.46	0.86	0.019	10.80	1.23	0.78	0.014
2.80	1.40	0.84	0.018	11.00	1.19	0.77	0.014
2.90	1.34	0.82	0.016	11.20	1.16	0.76	0.013
3.00	0.30	0.81	0.016	11.40	1.13	0.75	0.013
3.10	1.26	0.80	0.015	11.60	1.11	0.74	0.013
3.30	1.19	0.77	0.014	11.80	1.09	0.74	0.013
3.40	1.16	0.76	0.013	12.00	1.08	0.73	0.013
3.50	1.13	0.75	0.013	12.40	1.05	0.72	0.012
3.60	1.10	0.74	0.013	12.80	1.01	0.71	0.012
3.70	1.07	0.73	0.013	13.20	0.98	0.70	0.012
3.80	1.04	0.72	0.012	13.60	0.95	0.69	0.013
3.90	1.01	0.71	0.012	14.00	0.92	0.68	0.013
4.00	0.98	0.70	0.012	14.40	0.89	0.67	0.013
4.20	0.94	0.68	0.013	14.80	0.90	0.67	0.013
4.40	0.89	0.67	0.013	15.20	0.92	0.68	0.013
4.60	0.85	0.65	0.014	15.60	0.95	0.69	0.013
4.80	0.81	0.64	0.014	16.00	0.98	0.70	0.012
5.00	0.78	0.63	0.015	16.40	1.01	0.71	0.012
5.20	0.77	0.62	0.016	16.80	1.04	0.72	0.012
5.40	0.77	0.62	0.016	16.40	1.01	0.71	0.012
5.60	0.80	0.63	0.014	16.80	1.04	0.72	0.012
5.80	0.87	0.66	0.013	17.20	1.09	0.74	0.013
6.00	1.00	0.71	0.012	17.60	1.13	0.75	0.013
6.20	1.11	0.75	0.013	18.00	1.17	0.76	0.014
6.40	1.23	0.78	0.014	18.40	1.21	0.78	0.014
6.60	1.33	0.81	0.016	18.80	1.24	0.79	0.014
6.80	1.42	0.84	0.018	19.20	1.27	0.80	0.015
7.00	1.49	0.86	0.020	19.60	1.29	0.80	0.015
7.20	1.54	0.88	0.022	20.00	1.30	0.81	0.015
7.40	1.58	0.89	0.023	20.60	1.29	0.80	0.015
7.60	1.61	0.90	0.024	21.00	1.27	0.80	0.015
7.80	1.63	0.90	0.025	21.60	1.23	0.78	0.014

Zirconium (polycrystalline)²⁰—continued

Energy				Energy			
eV	n	k	R($\phi = 0$)	eV	n	k	R($\phi = 0$)
22.00	1.20	0.77	0.014	26.60	0.91	0.67	0.013
22.60	1.15	0.76	0.013	27.00	0.88	0.66	0.013
23.00	1.12	0.75	0.013	27.60	0.84	0.65	0.014
23.60	1.08	0.73	0.013	28.00	0.83	0.64	0.014
24.00	1.05	0.73	0.013	28.60	0.82	0.64	0.014
24.60	1.02	0.71	0.012	29.00	0.81	0.64	0.014
25.00	1.00	0.71	0.012	29.60	0.82	0.64	0.014
25.60	0.97	0.69	0.012	30.00	0.82	0.64	0.014
26.00	0.95	0.69	0.013				

References:

1. Weaver, J. H. Kafka, C., Lynch, D. W. and Koch, E. E., *Optical Properties of Metals*, Volumes I and II, *Physics Data*, Nr. 18-1 and 18-2, (Fachinformationzentrum, Karlsruhe, Germany).
2. Palik, E. D., Ed., *Handbook of Optical Constants*, Vol. I and Vol. II (Academic Press, New York, 1985 and 1991).
3. Gray, D. E., Coord. Ed., *American Institute of Physics Handbook*, 3rd Edition (McGraw-Hill Book Co., New York, 1972).
4. Shiles, E., Sasaki, T., Inokuti, M., and Smith, D. Y., *Phys. Rev. Sect. B*, 22, 1612 (1980).
5. Bos, L. W., and Lynch, D. W., *Phys. Rev. Sect. B*, 2, 4567 (1970).
6. Hagemann, H. J., Gudat, W., and Kunz, C., *J. Opt. Soc. Am.*, 65, 742 (1975).
7. Potter, R. F., *Handbook of Optical Constant*, Vol. I (Academic Press, New York, 1985), p. 465.
8. Olson, C. G., Lynch, D. W., and Weaver, J. H., unpublished.
9. Weaver, J. H., Olson, C. G., and Lynch, D. W., *Phys. Rev. Sect. B*, 15, 4115 (1977).
10. Weaver, J. H., Colavita, E., Lynch, D. W., and Rosei, R., *Phys. Rev. Sect. B*, 19, 3850 (1979).
11. Priol, M. A., Daudé, A., and Robin, S., *Compt. Rend.*, 264, 935 (1967).
12. Weaver, J. H., Lynch, D. W., and Olson, D. G., *Phys. Rev. Sect. B*, 10, 501 (1973).
13. Lynch, D. W., Rosei, R., and Weaver, J. H., *Solid State Commun.*, 9, 2195 (1971).
14. Weaver, J. H., Lynch, D. W., and Olson, C. G., *Phys. Rev. Sect. B*, 7, 431 (1973).
15. Weaver, J. H., and Benbow, R. L., *Phys. Rev. Sect. B*, 12, 3509 (1975).
16. Weaver, J. H., *Phys. Rev. B*, 11, 1416 (1975).
17. Edwards, D. F., in *Handbook of Optical Constants*, Vol. I (Academic Press, New York, 1985), p. 547.
18. Johnson, P. B., and Christy, R. W., *Phys. Rev. Sect. B*, 9, 5056 (1974).
19. Weaver, J. H., Lynch, D. W., and Olson, C. G., *Phys. Rev. Sect. B*, 12, 1293 (1975).
20. Lanham, A. P., and Terherne, D. M., *Proc. Phys. Soc.*, 83, 1059 (1964).

Spectra

Spectra of n and k and of the normal incidence absorptance A and reflectance R are shown graphically in Figures 4.2.1–4.2.24 for the following metals [figures are from Lynch, D. W., Mirror and reflector materials, *Handbook of Laser Science and Technology*, Vol. IV, *Optical Materials*, Part 2 (CRC Press, Boca Raton, FL, 1986), p. 185].

Aluminum	Gold	Nickel	Silicon
Copper	Iron	Niobium	Silver
Germanium	Molybdenum	Platinum	Tungsten




Figure 4.2.1 Real (n) and imaginary (k) part of the index of refraction for aluminum.




Figure 4.2.2 Reflectance and absorptance (A) for aluminum calculated for normal incidence from the data of Figure 4.2.1. Note that $A = 1 - R$ and a semi-infinite sample is assumed, i.e., the sample is thick enough to be opaque.




Figure 4.2.3 Real (n) and imaginary (k) part of the index of refraction for copper.




Figure 4.2.4 Reflectance and absorptance (A) for copper calculated for normal incidence from the data of Figure 4.2.3. Note that $A = 1 - R$ and a semi-infinite sample is assumed, i.e., the sample is thick enough to be opaque.




Figure 4.2.5 Real (n) and imaginary (k) part of the index of refraction for germanium.




Figure 4.2.6 Reflectance (R) for germanium calculated for normal incidence from the data of Figure 4.2.4. Germanium is transparent for wavelengths $>1.8 \mu\text{m}$ and no effect from a second surface has been considered in calculating R .




Figure 4.2.7 Real (n) and imaginary (k) part of the index of refraction for gold.




Figure 4.2.8 Reflectance and absorptance (A) for gold calculated for normal incidence from the data of Figure 4.2.7. Note that $A = 1 - R$ and a semi-infinite sample is assumed, i.e., the sample is thick enough to be opaque.




Figure 4.2.9 Real (n) and imaginary (k) part of the index of refraction for iron.




Figure 4.2.10 Reflectance and absorptance (A) for iron calculated for normal incidence from the data of Figure 4.2.9. Note that $A = 1 - R$ and a semi-infinite sample is assumed, i.e., the sample is thick enough to be opaque.




Figure 4.2.11 Real (n) and imaginary (k) part of the index of refraction for molybdenum.




Figure 4.2.12 Reflectance and absorptance (A) for molybdenum calculated for normal incidence from the data of Figure 4.2.11. Note that $A = 1 - R$ and a semi-infinite sample is assumed, i.e., the sample is thick enough to be opaque.




Figure 4.2.13 Real (n) and imaginary (k) part of the index of refraction for nickel.




Figure 4.2.14 Reflectance and absorptance (A) for nickel calculated for normal incidence from the data of Figure 4.2.13. Note that $A = 1 - R$ and a semi-infinite sample is assumed, i.e., the sample is thick enough to be opaque.




Figure 4.2.15 Real (n) and imaginary (k) part of the index of refraction for niobium.




Figure 4.2.16 Reflectance and absorptance (A) for niobium calculated for normal incidence from the data of Figure 4.2.15. Note that $A = 1 - R$ and a semi-infinite sample is assumed, i.e., the sample is thick enough to be opaque.




Figure 4.2.17 Real (n) and imaginary (k) part of the index of refraction for platinum.




Figure 4.2.18 Reflectance and absorptance (A) for platinum calculated for normal incidence from the data of Figure 4.2.17. Note that $A = 1 - R$ and a semi-infinite sample is assumed, i.e., the sample is thick enough to be opaque.




Figure 4.2.19 Real (n) and imaginary (k) part of the index of refraction for silicon.




Figure 4.2.20 Reflectance and absorptance (A) for silicon calculated for normal incidence from the data of Figure 4.2.19. Silicon is transparent for wavelengths $> 1.2 \mu\text{m}$ and no effect from a second surface has been considered in calculating R .




Figure 4.2.21 Real (n) and imaginary (k) part of the index of refraction for silver.




Figure 4.2.22 Reflectance and absorptance (A) for silver calculated for normal incidence from the data of Figure 4.2.21. Note that $A = 1 - R$ and a semi-infinite sample is assumed, i.e., the sample is thick enough to be opaque.




Figure 4.2.23 Real (n) and imaginary (k) part of the index of refraction for tungsten.




Figure 4.2.24 Reflectance and absorptance (A) for tungsten calculated for normal incidence from the data of Figure 4.2.23. Note that $A = 1 - R$ and a semi-infinite sample is assumed, i.e., the sample is thick enough to be opaque.

Emittance

Emittance is the ratio of radiated emitted power of a surface (W/m^2) to the emissive power of a blackbody at the same temperature. The total emittance is an integral over all wavelengths; the spectral emittance is given as a function of wavelength at constant temperature.

Normal Spectral Emittance (650 nm)	
Metal	Emissivity
Beryllium	0.61
Chromium	0.34
Copper	0.10
Gold	0.14
Iron	0.35
Iron (cast)	0.37
Molybdenum	0.37
Nickel	0.36
Nickel (80) -chromium (20)	0.35
Palladium	0.33
Platinum	0.30
Silver	0.07
Steel	0.35
Tantalum	0.49
Titanium	0.63
Tungsten	0.43
Zirconium	0.32

From the *CRC Handbook of Chemistry and Physics*,
75th edition, Lide, D. R., Ed. (CRC Press, Boca
Raton, FL, 1994), p. 10-296.

Total Emittance		
Metal	Temperature (°C)	Emissivity
Aluminum	50–500	0.04–0.06
	200	0.11
	600	0.19
Chromium	50	0.1
	500–1000	0.28–0.38
Copper	50	0.6–0.7
	500	0.88
	100	0.02
	50–100	0.02
Gold	200–600	0.02–0.03
	100	0.02
	600	0.64
Iron, cast	200	0.78
	100	0.21
	600–1000	0.08–0.13
Molybdenum	200	0.64
	100	0.78
	500	0.12
	1000	0.19
	200–400	0.07–0.09
Nickel	25	0.045
	100	0.06
	500	0.12
	1000	0.19
Nickel (80) -chromium (20)	100	0.87
	600	0.87
	200–600	0.05–0.1
Platinum	25	0.017
	100	0.047
	500	0.096
	200–600	0.02–0.03
Silver	100	0.02
	500	0.035
	200–600	0.02
Steel	500	0.35
	750–1050	0.52–0.56
	200–600	0.8
	100	0.08
Tantalum	1500	0.21
Tungsten	25	0.024
	100	0.032
	500	0.071
Zinc	200–300	0.04–0.05
	300	0.05
	200–600	0.02–0.03

From the *CRC Handbook of Chemistry and Physics*, 75th edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 1994), p. 10-295.

Reflectance of Freshly Evaporated Mirror Coatings

λ (nm)	Normal Incidence Reflectance (%)					
	Aluminum	Copper	Gold	Platinum	Rhodium	Silver
220	91.5	40.4	27.5	40.5	57.8	28.0
240	91.9	39.0	31.6	46.9	63.2	29.5
260	92.2	35.5	35.6	51.5	67.7	29.2
280	92.3	33.0	37.8	54.9	70.7	25.2
300	92.3	33.6	37.7	57.6	73.4	17.6
320	92.4	36.3	37.1	60.0	75.5	8.9
340	92.5	38.5	36.1	62.0	76.9	72.9
360	92.5	41.5	36.3	63.4	78.0	88.2
380	92.5	44.5	37.8	64.9	78.1	92.8
400	92.4	47.5	38.7	66.3	77.4	95.6
450	92.2	55.2	38.7	69.1	76.0	97.1
500	91.8	60.0	47.7	71.4	76.6	97.9
550	91.5	66.9	81.7	73.4	78.2	98.3
600	91.1	93.3	91.9	75.2	79.7	98.6
650	90.5	96.6	95.5	76.4	81.1	98.8
700	89.7	97.5	97.0	77.2	82.0	98.9
750	88.6	97.9	97.4	77.9	82.6	99.1
800	86.7	98.1	98.0	78.5	83.1	99.2
850	86.7	98.3	98.2	79.5	83.4	99.2
900	89.1	98.4	98.4	80.5	83.6	99.3
950	92.4	98.4	98.5	80.6	83.9	99.3
1000	94.0	98.5	98.6	80.7	84.2	99.4
1500	97.4	98.5	99.0	81.8	87.7	99.4
2000	97.8	98.6	99.1	81.8	91.4	99.4
3000	98.0	98.6	99.3	90.6	95.0	99.4
4000	98.2	98.7	99.4	93.7	95.8	99.4
5000	98.4	98.7	99.4	94.9	96.4	99.5
6000	98.5	98.7	99.4	95.6	96.8	99.5
7000	98.6	98.7	99.4	95.9	97.0	99.5
8000	98.7	98.8	99.4	96.0	97.2	99.5
9000	98.7	98.8	99.4	96.1	97.4	99.5
10000	98.7	98.9	99.4	96.2	97.6	

Reference: Hass, G., in *Applied Optics and Optical Engineering*, vol. III, Kingslake, R., Ed., (Academic Press, New York, 1965), p. 309. See also, Palmer, J. M., *Handbook of Optics* (McGraw-Hill, New York, 1995), Chapter 25 and references cited therein.

4.3 Mechanical Properties

Elastic Constants

Metal	Elastic stiffness constants (10^{11} N/m 2)				
Cubic crystals	C_{11}	C_{12}	C_{44}		
Aluminum	1.0675	0.6041	0.2834		
Chromium	3.398	0.586	0.990		
Copper	1.683	1.221	0.757		
Germanium	1.2835	0.4823	0.6666		
Gold	1.9244	1.6298	0.4200		
Iridium	5.80	2.42	2.56		
Iron	2.26	1.40	1.16		
Molybdenum	4.637	1.578	1.092		
Nickel	2.841	1.529	1.242		
Niobium	2.4650	1.3450	0.2873		
Palladium	2.2710	1.7604	0.7173		
Platinum	3.4670	2.5070	0.7650		
Silicon	1.6578	0.6394	0.7962		
Silver	1.2399	0.9367	0.4612		
Tantalum	2.6023	1.5446	0.8255		
Tungsten	5.2239	2.0437	1.6083		
Hexagonal crystals	C_{11}	C_{12}	C_{13}	C_{33}	C_{55}
Beryllium	2.923	0.267	0.140	3.364	1.625
Magnesium	0.5950	0.2612	0.2180	0.6155	0.1635
Zinc	1.6368	0.3640	0.5300	0.6347	0.3879
Zirconium	1.434	0.728	0.657	1.648	0.320

Reference: Frederikse, H. P. R., Elastic constants of single crystals, *Handbook of Chemistry and Physics*, 82nd edition (CRC Press, Boca Raton, FL, 1994), p. 12-37.

Elastic Moduli and Poisson's Ratio

Material	Young's modulus (GN/m 2)	Shear modulus (GN/m 2)	Bulk modulus (GN/m 2)	Poisson's ratio
Aluminum				
5086-O	71.0	26.4	—	0.33
6061-T6	68.9	25.9	—	0.33
Beryllium (I-701-H)	315.4	148.4	115.0	0.043
Copper	129.8	48.3	137.8	0.343
Germanium	79.9	29.6	—	0.32
Gold	78.5	26.0	171.0	0.42
Invar 36	144.0	26.0	99.4	0.259
Iron	211.4	57.2	169.8	0.293

Elastic Moduli and Poisson's Ratio—*continued*

Material	Young's modulus (GN/m²)	Shear modulus (GN/m²)	Bulk modulus (GN/m²)	Poisson's ratio
Molybdenum	324.8	81.6	261.2	0.293
Nickel	199.5	125.6	177.3	0.312
Platinum	170.0	76.0	276.0	0.39
Silicon	113.0	60.9	—	0.42
Silicon carbide				
CVD	461.0	39.7		0.21
reaction sintered	413.0	—	—	0.24
Silver	82.7	30.3	103.6	0.367
Stainless steel		77.0		
304	193.0	83.9	—	0.27
416	215.0	80.0	166.0	0.283
430	200	62.2	—	0.27
Tantalum	185.7	160.2	196.3	0.342
Tungsten	411		311.0	0.28

Table adapted from Palmer, J. M., *Handbook of Optics*, Vol.II (McGraw-Hill, New York, 1995), p. 35.73.

Strength Properties

Material	Yield strength (MN/m²)	Microyield strength (MN/m²)	Elongation (in 50 mm) %	Hardness
Aluminum				
5086-O	115	40	22	55 (Rockwell B)
6061-T6	276	160	15	95 (Rockwell B)
Beryllium (I-701-H)	276	30	4	80 (Rockwell B)
Copper	195	12	42	10 (Rockwell B)
Gold	125		30	30 (Knoop*)
Invar 36	276	37	35	70 (Rockwell B)
Molybdenum	600		47	150 (Knoop*)
Nickel	148		35	109 (Rockwell B)
Platinum	150			40 (Knoop*)
Silver	130		47	32 (Knoop*)
Stainless steel				
304	241		60	80 (Rockwell B)
416	950		12	41 (Rockwell C)
430	380		25	86 (Rockwell B)
Tantalum	220		30	120 (Knoop*)
Tungsten	780		2	350 (Knoop*)

* kg/mm²

Table adapted from Palmer, J. M., *Handbook of Optics*, Vol.II (McGraw-Hill, New York, 1995), p. 35.74.

4.4 Thermal Properties

Metal	Thermal Properties				
	Density ^(a) (g/cm ³)	Melting point (°C)	Coeff. linear expansion ^(a) (10 ⁻⁶ K ⁻¹)	Specific heat capacity (J/g K)	Thermal conductivity ^(b) (W/m K)
Aluminum	2.70	660.3	23.1	0.897	237
Beryllium	1.85	1287	11.3	1.825	200
Chromium	7.15	1907	4.9	0.449	93.7
Copper	8.96	1084.6	16.5	0.385	401
Gold	19.3	1064.3	14.2	0.129	317
Iridium	22.5	2446	6.4	0.131	147
Iron	7.87	1538	11.8	0.449	80.2
Magnesium	1.74	650	24.8	1.023	156
Molybdenum	10.2	2623	4.8	0.251	138
Nickel	8.9	1455	13.4	0.444	90.7
Niobium	8.57	2477	7.3	0.265	53.7
Osmium	22.59	3033	5.1	0.130	87.6
Palladium	12.0	1555	11.8	0.246	71.8
Platinum	21.5	1768.4	8.8	0.133	71.6
Rhenium	20.8	3186	6.2	0.137	47.9
Rhodium	12.4	1964	8.2	0.243	150
Silver	10.5	961.8	18.9	0.235	429
Tantalum	16.4	3017	6.3	0.140	57.5
Tin	7.28	231.9	22.0	0.228	66.6
Titanium	4.5	1668	8.6	0.523	21.9
Tungsten	19.3	3422	4.5	0.132	174
Zinc	7.14	419.5	30.2	0.388	116
Zirconium	6.52	1855	5.7	0.278	27.7

(a) 25°C, (b) 27°C. From the *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12-219.

Temperature Dependence of Linear Thermal Expansion Coefficient (ppm/K)

Temperature (K)	100	200	293	400	500	600
Aluminum (6061)	12.2	20.9	22.5	25.0	27.5	30.1
Beryllium	1.32	7.00	11.3	13.6	15.1	16.6
Copper	10.3	15.2	16.5	17.6	18.3	18.9
Gold	11.8	13.7	14.2	14.8	15.4	15.9
Iron	506	10.1	11.8	13.4	14.4	15.1
Molybdenum	2.8	4.6	4.8	4.9	5.1	5.3
Nickel	6.6	11.3	13.4	14.5	15.3	15.9
Silicon	-0.4	1.5	2.6	3.2	3.5	3.7
Silicon carbide (α)	0.14	1.5	3.3	4	4.2	4.5
Silver	14.2	17.8	18.9	19.7	20.6	21.5
Stainless steel (304)	11.4	13.2	14.7	16.3	17.5	18.6
Stainless steel (416)	6	7.9	9.5	10.9	12.1	12.9

Adapted from Palmer, J. M., Properties of metals, in *Handbook of Optics, Vol.II* (McGraw-Hill, New York, 1995), p. 35.60.

Temperature Dependence of Molar Heat Capacity (J/mol K)

Temp. (K)	200	250	300	350	400	500	600
Aluminum	21.33	23.08	24.25	25.11	25.78	26.84	27.89
Beryllium	9.98	13.58	16.46	18.53	19.95	21.94	23.34
Chromium	19.86	22.30	23.47	24.39	25.23	26.63	27.72
Copper	22.63	23.77	24.48	24.95	25.33	25.91	26.48
Germanium	—	—	23.25	23.85	24.31	24.96	25.45
Gold	—	—	25.41	25.37	25.51	26.06	26.65
Iron	21.95	23.94	25.15	26.28	27.39	29.70	32.05
Magnesium	22.72	24.02	24.90	25.57	26.14	27.17	28.18
Silicon	15.64	18.22	20.04	21.28	22.14	23.33	24.15
Silver			25.36	25.55	25.79	26.36	26.99
Tantalum	24.08	24.86	25.31	25.60	25.84	26.35	26.84
Titanium	22.37	24.07	25.28	26.17	26.86	27.88	28.60
Tungsten	22.49	23.69	24.30	24.65	24.92	25.36	25.79
Zinc	24.05	25.02	25.45	25.88	26.35	27.39	28.59
Zirconium	23.87	24.09	25.22	25.61	25.93	26.56	27.28

From the *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12-218.

Temperature Dependence of Thermal Conductivity (W/m K)

Temp. (K)	4	20	80	200	300	400	600
Aluminum	15700	11700	432	237	237	240	231
Chromium	160	593	184	111	93.7	90.9	80.7
Copper	16200	10800	557	413	401	393	379
Germanium	877	1490	325	96.8	59.9	43.2	27.3
Gold	2090	1580	332	323	317	311	298
Iron	677	1540	175	94	80.2	69.5	54.7
Nickel	859	1650	210	107	90.7	80.2	65.6
Platinum	880	495	81.5	72.6	71.6	71.8	73.2
Silicon	297	4810	1340	264	148	98.9	61.9
Silver	14700	5100	471	430	429	425	412
Tin	18100	320	91.5	73.3	66.6	62.2	—
Titanium	5.75	27.5	32.6	24.5	21.9	20.4	19.4
Tungsten	5630	4050	229	185	174	159	137

From the *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 12-221.

4.5 Mirror Substrate Materials

Tables adapted from Palmer, J. M., Properties of metals, in *Handbook of Optics*, Vol.II (McGraw-Hill, New York, 1995), p. 35.11.

Mirror Substrate Materials			
Material	Density (g/cm ³)	Young's modulus (GN/m ²)	Specific stiffness (arbitrary units)
Fused silica	2.19	72	33
Beryllium (I-70)	1.85	287	155
Aluminum (6061)	2.70	68	25
Copper	8.94	117	13
Stainless steel (304)	8.00	193	24
Invar (36)	8.05	141	18
Silicon	2.33	131	56
Silicon carbide (30% Si)	2.89	330	114
Silicon carbide CVD)	3.21	465	145

Thermal Properties of Substrate Materials				
Material	Coeff. linear expansion (10 ⁶ K ⁻¹)	Specific heat capacity (J/g K)	Thermal conductivity (W/m K)	Thermal diffusivity (10 ⁻⁶ m ² /s)
Fused silica	0.50	750	1.4	0.85
Beryllium (I-70)	11.3	1925	216	57.2
Aluminum (6061)	22.5	896	167	69
Copper	16.5	385	391	115.5
Stainless steel (304)	14.7	500	16.2	4.0
Invar (36)	1.0	515	10.4	2.6
Silicon	2.6	710	156	89.2
Silicon carbide (30% Si)	2.6	670	155	81.0
Silicon carbide CVD)	2.4	733	198	82.0

Thermal Distortion of Substrate Materials		
Material	Steady state distortion coefficient ^(a) (μm/W)	Transient distortion coefficient ^(b) (s/ m ² K)
Fused silica	0.36	0.59
Beryllium (I-70)	0.05	0.20
Aluminum (6061)	0.13	0.33
Copper	0.53	0.14
Stainless steel (304)	0.91	3.68
Invar (36)	0.10	0.38
Silicon	0.02	0.03
Silicon carbide (30% Si)	0.02	0.03
Silicon carbide CVD)	0.01	0.03

(a) Linear expansion coefficient/thermal conductivity.

(b) Linear expansion coefficient/thermal diffusivity.

Section 5: Liquids

5.1 Introduction

5.2 Water

5.3 Physical Properties of Selected Liquids

5.4 Index of Refraction

5.5 Nonlinear Optical Properties

5.6 Magnetooptic Properties

5.7 Commercial Optical Liquids

Section 5

LIQUIDS

5.1 Introduction

Liquids in this section include water (H_2O), heavy water (D_2O), and the following selected organic materials (CAS – Chemical Abstract Service Registry Number):

CAS no.	Liquid	CAS no.	Liquid
100	acetic acid, $\text{C}_2\text{H}_4\text{O}_2$	5672	ethanol, $\text{C}_2\text{H}_6\text{O}$
10411	acetone, $\text{C}_3\text{H}_6\text{O}$	5569	ethylene glycol, $\text{C}_2\text{H}_6\text{O}_2$
867	benzene, C_6H_6	10186	glycerine (glycerol), $\text{C}_3\text{H}_8\text{O}_3$
998	bromobenzene, $\text{C}_6\text{H}_5\text{Br}$	6355	heptane, C_7H_{16}
3993	carbon disulfide, CS_2	6632	hexadecane, $\text{C}_{16}\text{H}_{34}$
7540	carbon tetrachloride, CCl_4	6731	hexane, C_6H_{14}
7554	chloroform, CHCl_3	7581	methanol, CH_4O
4305	cyclohexane, C_6H_{12}	4426	methylcyclohexane, C_7H_{14}
5529	1,2-dichloroethane, $\text{C}_2\text{H}_4\text{Cl}_2$	7915	1-methylnaphthalene, $\text{C}_{11}\text{H}_{10}$
7499	dichloromethane, CH_2Cl_2	2049	nitrobenzene, $\text{C}_6\text{H}_5\text{NO}_2$
7529	dimethylsulfoxide, $\text{C}_2\text{H}_6\text{OS}$	1947	toluene, C_7H_8
5187	1,4-dioxane, $\text{C}_4\text{H}_8\text{O}_2$	8848	2,2,4-trimethylpentane, C_8H_{18}

5.2 Water

5.2.1 Physical Properties

Density, specific heat capacity at constant pressure (C_p), viscosity, vapor pressure, thermal conductivity, dielectric constant, and surface tension of water. All values (except vapor pressure) at for a pressure of 100 kPa (1 bar). Temperature scale is IPTS-68.

Temp. (°C)	Density (g/cm ³)	C_p (J/g K)	Visc. (μPa s)	Vapor press. (kPa)	Therm. cond. (mW/m K)	Diel. const.	Surf. tens. (mN/m)
0	0.99984	4.2176	0.6113	1793	561.0	87.90	75.64
10	0.99970	4.1921	1.2281	1307	580.0	83.96	74.23
20	0.99821	4.1818	2.3388	1002	598.4	80.20	72.75
30	0.99565	4.1784	4.2455	797.7	615.4	76.60	71.20
40	0.99222	4.1785	7.3814	653.2	630.5	73.17	69.60
50	0.98803	4.1806	12.344	547.0	643.5	69.88	67.94
60	0.98320	4.1843	19.932	466.5	654.3	66.73	66.24
70	0.97778	4.1895	31.176	404.0	663.1	63.73	64.47
80	0.97182	4.1963	47.373	354.4	670.0	60.86	62.67
90	0.96535	4.2050	70.117	314.5	675.3	587.12	60.82
100	0.95840	4.2159	101.325	281.8	679.1	55.51	58.91

From the *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 6-3.

5.2.2 Absorption

Linear Absorption Coefficient α of Water*

λ (nm)	α (10^{-4} cm $^{-1}$)	Ref.	λ (nm)	α (10^{-4} cm $^{-1}$)	Ref.
185	14600	1	660	40.7	2
186	9700	1	665	41.9	2
187	6000	1	670	42.5	2
188	3800	1	675	43.8	2
189	2300	1	680	44.7	2
190	1400	1	685	46.7	2
400	5.8	2	690	49	4
410	4.7	2	690	51.5	2
420	3.8	2	694.2	52.6	3
430	4.0	2	695	56.9	2
440	3.2	2	700	64.8	2
450	3.3	2	702	69	4
460.7	2.11	3	705	75.0	2
469.4	2.05	3	710	90.4	2
480.7	1.86	3	714	98	4
490.1	1.89	3	715	111.4	2
499.9	2.33	3	720	137.5	2
510.1	3.13	3	725	134	4
520.7	3.80	3	725	175.6	2
529.0	4.09	3	730	230.9	2
540.4	4.80	3	735	238	4
546.3	5.28	3	735	260.8	2
574.5	8.05	3	740	269.8	2
580	10.9	2	745	271.2	2
585	11.9	2	746	275	4
590	17.2	2	750	268.3	2
595	21.4	2	752	281	4
598.6	19.25	3	755	269.6	2
600	27.2	2	758	272	4
602.2	23.2	3	760	268.5	2
605	29.3	2	769	251	4
610	29.3	2	770	251.9	2
615	30.0	2	780	234.6	2
620	30.9	2	781	230	4
625	30.5	2	790	205.2	2
630	32.0	2	794	210	4
635	32.5	2	806	195	4
640	33.4	2	813	191	4
645	33.9	2	820	199	4
649.2	32.3	3	833	308	4
650	35.1	2	847	387	4
655	38.7	2	862	428	4

Linear Absorption Coefficient α of Water*—continued

λ (nm)	α (10^{-4} cm $^{-1}$)	Ref.	λ (nm)	α (10^{-4} cm $^{-1}$)	Ref.
877	506	4	1370	54500	4
893	609	4	1389	91300	4
909	750	4	1408	215000	4
926	1190	4	1429	310000	4
935	1580	4	1443	317000	4
943	2140	4	1471	285000	4
952	3220	4	1493	217000	4
962	4710	4	1515	156000	4
973	5140	4	1538	121000	4
980	5020	4	1563	96800	4
990	4690	4	1587	80700	4
1000	4160	4	1613	68000	4
1010	3510	4	1639	60700	4
1020	2850	4	1667	56500	4
1031	2310	4	1695	56500	4
1042	1900	4	1724	62300	4
1053	1640	4	1754	76000	4
1070	1480	4	1786	91800	4
1087	1660	4	1802	94800	4
1099	1920	4	1818	94400	4
1111	2320	4	1852	108000	4
1124	3230	4	1887	575000	4
1136	5480	4	1927	1240000	4
1149	9700	4	1961	1090000	4
1163	11800	4	2000	692000	4
1176	12300	4	2041	450000	4
1190	12500	4	2083	310000	4
1205	12500	4	2128	236000	4
1220	12200	4	2198	193000	4
1235	11700	4	2273	230000	4
1250	11100	4	2326	293000	4
1266	10700	4	2381	418000	4
1282	11300	4	2439	635000	4
1299	13400	4	2500	957000	4
1316	16700	4	2564	1110000	4
1333	22500	4	2632	1930000	4
1351	38700	4			

* Measurements made at room temperature (Ref. 1 – 298 K; Ref. 2 – 296 ± 1.5 K; Ref. 4 – 300 K).

References:

1. Barrett, J. and Mansell, A. L., Ultra-violet absorption spectra of the molecules H₂O, HDO and D₂, *Nature* 187, 138 (1960).

2. Sullivan, S. A., Experimental study of the absorption in distilled water, artificial sea water, and heavy water in the visible region of the spectrum, *J. Opt. Soc. Am.* 53, 962 (1963). This reference contains additional values of α at wavelengths intermediate to those given above.
3. Tam, A. C. and Patel, C. K. N., Optical absorption of light and heavy water by laser optoacoustic spectroscopy, *Appl. Opt.* 18, 3348 (1979).
4. Palmer, K. F. and Williams, D., Optical properties of water in the near infrared, *J. Opt. Soc. Am.* 64, 1107 (1974).

Absorption Coefficient α for Water in the Infrared (T = 298 K)

λ (nm)	α (cm $^{-1}$)	λ (nm)	α (cm $^{-1}$)	λ (nm)	α (cm $^{-1}$)
0.700	0.00602	3.45	481	7.1	566
0.725	0.0159	3.50	338	7.2	560
0.750	0.0261	3.6	180	7.3	554
0.775	0.0240	3.7	122	7.4	550
0.800	0.0196	3.8	112	7.5	546
0.825	0.0277	3.9	122	7.6	542
0.850	0.0433	4.0	145	7.7	540
0.875	0.0562	4.1	172	7.8	540
0.900	0.0678	4.2	206	7.9	539
0.925	0.144	4.3	247	8.0	539
0.950	0.374	4.4	294	8.2	538
0.975	0.449	4.5	374	8.4	540
1.00	0.363	4.6	402	8.6	544
1.20	1.04	4.7	420	8.8	550
1.40	12.4	4.8	393	9.0	557
1.60	67.2	4.9	351	9.2	567
1.80	80.3	5.0	312	9.4	579
2.00	69.1	5.1	274	9.6	594
2.20	16.5	5.2	244	9.8	614
2.40	50.1	5.3	232	10.0	639
2.60	153	5.4	240	10.5	793
2.65	318	5.5	265	11.0	1110
2.70	845	5.6	319	11.5	1550
2.75	2700	5.7	448	12.0	2080
2.80	5120	5.8	715	12.5	2600
2.85	8160	5.9	1330	13.0	2950
2.90	11600	6.0	2240	13.5	3190
2.95	12700	6.1	2700	14.0	3320
3.00	11400	6.2	1800	14.5	3360
3.05	9890	6.3	1140	15.0	3370
3.10	7780	6.4	882	15.5	3360
3.15	5390	6.5	758	16.0	3320
3.20	3630	6.6	678	16.5	3260
3.25	2360	6.7	632	17.0	3170
3.30	1400	6.8	604	17.5	3060
3.35	979	6.9	579	18.0	2970
3.40	720	7.0	575	18.5	2860

Absorption Coefficient α for Water in the Infrared (T = 298 K)—continued

λ (nm)	α (cm ⁻¹)	λ (nm)	α (cm ⁻¹)	λ (nm)	α (cm ⁻¹)
19.0	2740	32	1270	90	749
19.5	2600	34	1220	100	669
20.0	2470	36	1200	110	607
21.0	2290	38	1190	120	551
22	2130	40	1210	130	497
23	2010	42	1220	140	449
24	1890	44	1250	150	415
25	1780	46	1260	160	390
26	1690	48	1280	170	367
27	1600	50	1290	180	348
28	1520	60	1230	190	331
29	1440	70	1030	200	317
30	1370	80	859		

Reference:

Hale, G M. and Querry, M. R., Optical constants of water in the 200-nm to 200- μ m wavelength region, *Appl. Opt.* 12, 555 (1973).

Heavy Water

Absorption Coefficient α for Heavy water*

λ (nm)	α (10 ⁻⁴ cm ⁻¹)	λ (nm)	α (10 ⁻⁴ cm ⁻¹)	λ (nm)	α (10 ⁻⁴ cm ⁻¹)
400	31.8	540	6.3	680	3.2
410	28.5	550	5.8	690	3.3
420	26.3	560	5.3	700	4.5
430	23.4	570	5.4	710	5.1
440	20.8	580	4.9	720	5.4
450	18.2	590	4.4	730	5.9
460	15.6	600	4.2	740	6.7
470	14.1	610	4.0	750	6.9
480	13.1	620	4.0	760	6.9
490	11.6	630	3.3	770	6.5
500	10.1	640	3.2	780	6.7
510	8.9	650	3.4	790	7.4
520	8.6	660	2.9		
530	7.4	670	3.5		

Temperature: 296 ± 1.5 K

* 99.7% D₂O

Reference:

Sullivan, S. A., Experimental study of the absorption in distilled water, artificial sea water, and heavy water in the visible region of the spectrum, *J. Opt. Soc. Am.* 53, 962 (1963). This reference contains additional values of α at wavelengths intermediate to those given above.

5.2.3 Index of Refraction

Index of Refraction n of Water (298 K)

λ (μm)	n(λ)	λ (μm)	n(λ)	λ (μm)	n(λ)
0.200	1.396	2.70	1.188	6.0	1.265
0.225	1.373	2.75	1.157	6.1	1.319
0.250	1.362	2.80	1.142	6.2	1.363
0.275	1.354	2.85	1.149	6.3	1.357
0.300	1.349	2.90	1.201	6.4	1.347
0.325	1.346	2.95	1.292	6.5	1.339
0.350	1.343	3.00	1.371	6.6	1.334
0.375	1.341	3.05	1.426	6.7	1.329
0.400	1.339	3.10	1.467	6.8	1.324
0.425	1.338	3.15	1.483	6.9	1.321
0.450	1.337	3.20	1.478	7.0	1.371
0.475	1.336	3.25	1.467	7.1	1.314
0.500	1.335	3.30	1.1450	7.2	1.312
0.525	1.334	3.35	1.432	7.3	1.309
0.550	1.333	3.40	1.420	7.4	1.307
0.575	1.333	3.45	1.410	7.5	1.304
0.600	1.332	3.50	1.400	7.6	1.302
0.625	1.332	3.6	1.385	7.7	1.299
0.650	1.331	3.7	1.374	7.8	1.297
0.675	1.331	3.8	1.364	7.9	1.294
0.700	1.331	3.9	1.357	8.0	1.291
0.725	1.330	4.0	1.351	8.2	1.286
0.750	1.330	4.1	1.346	8.4	1.281
0.775	1.330	4.2	1.342	8.6	1.275
0.800	1.329	4.3	1.338	8.8	1.269
0.825	1.329	4.4	1.334	9.0	1.262
0.850	1.329	4.5	1.332	9.2	1.255
0.875	1.328	4.6	1.330	9.4	1.247
0.900	1.328	4.7	1.330	9.6	1.239
0.925	1.328	4.8	1.330	9.8	1.229
0.950	1.327	4.9	1.328	10.0	1.218
0.975	1.327	5.0	1.325	10.5	1.185
1.00	1.327	5.1	1.322	11.0	1.153
1.20	1.324	5.2	1.317	11.5	1.126
1.40	1.321	5.3	1.312	12.0	1.111
1.60	1.317	5.4	1.305	12.5	1.123
1.80	1.312	5.5	1.298	13.0	1.146
2.00	1.306	5.6	1.289	13.5	1.177
2.20	1.296	5.7	1.277	14.0	1.210
2.40	1.279	5.8	1.262	14.5	1.241
2.60	1.242	5.9	1.248	15.0	1.270
2.65	1.219	6.0	1.265	15.5	1.197

Index of Refraction n of Water (298 K)—continued

λ (μm)	n(λ)	λ (μm)	n(λ)	λ (μm)	n(λ)
-----------------------------	----------------	-----------------------------	----------------	-----------------------------	----------------

15.5	1.197	26	1.539	60	1.703
16.0	1.325	27	1.545	70	1.821
16.5	1.351	28	1.549	80	1.886
17.0	1.376	29	1.551	90	1.924
17.5	1.401	30	1.551	100	1.957
18.0	1.423	32	1.546	110	1.966
18.5	1.443	34	1.536	120	2.004
19.0	1.461	36	1.527	130	2.036
19.5	1.476	38	1.522	140	2.056
20.0	1.480	40	1.519	150	2.069
21.0	1.487	42	1.522	160	2.081
22	1.500	44	1.530	170	2.094
23	1.511	46	1.541	180	2.107
24	1.521	48	1.555	190	2.119
25	1.531	50	10587	200	2.130

Reference:

Hale, G M. and Querry, M. R., Optical constants of water in the 200-nm to 200-μm wavelength region, *Appl. Opt.* 12, 555 (1973).

Index of refraction n of water (300 K)

λ (nm)	n	Ref.	λ (nm)	n	Ref.
214.44	1.4032	1	746	1.332	3
303.4	1.3581	1	752	1.332	3
360	1.353	3	758	1.332	3
404.66	1.342742	2	769	1.331	3
408	1.344	3	781	1.331	3
435.84	1.340210	2	794	1.331	3
449	1.337	3	806	1.331	3
486.13	1.337123	2	813	1.331	3
508.6	1.3360	1	820	1.330	3
546.07	1.334466	2	833	1.330	3
556	1.333	3	847	1.330	3
587.56	1.333041	2	862	1.330	3
589.3	1.332988	2	877	1.330	3
632.8	1.331745	2	893	1.329	3
656.28	1.331151	2	909	1.329	3
670.8	1.3308	1	926	1.329	3
690	1.332	3	935	1.329	3

Index of Refraction n of Water (300 K)—continued

λ (nm)	n	Ref.	λ (nm)	n	Ref.
990	1.328	3	1471	1.321	3
1000	1.328	3	1493	1.320	3
1010	1.328	3	1515	1.320	3
1020	1.328	3	1538	1.319	3
1031	1.328	3	1563	1.319	3
1042	1.328	3	1587	1.318	3
1053	1.328	3	1613	1.318	3
1070	1.328	3	1639	1.317	3
1087	1.327	3	1667	1.316	3
1099	1.327	3	1695	1.315	3
1111	1.327	3	1724	1.314	3
1124	1.327	3	1754	1.314	3
1136	1.326	3	1786	1.313	3
1149	1.326	3	1802	1.312	3
1163	1.326	3	1818	1.312	3
1176	1.326	3	1852	1.311	3
1190	1.325	3	1887	1.310	3
1205	1.325	3	1927	1.309	3
1220	1.325	3	1961	1.307	3
1235	1.325	3	2000	1.306	3
1250	1.324	3	2041	1.305	3
1266	1.324	3	2083	1.303	3
1282	1.324	3	2128	1.301	3
1299	1.324	3	2198	1.296	3
1316	1.324	3	2273	1.291	3
1333	1.323	3	2326	1.285	3
1351	1.323	3	2381	1.281	3
1370	1.323	3	2439	1.276	3
1389	1.322	3	2500	1.268	3
1408	1.322	3	2564	1.257	3
1429	1.321	3	2632	1.239	3
1443	1.321	3			

References:

1. Kaye, G. W. and Laby, T. H., *Tables of Physical and Chemical Constants* (Longmans, Green & Co., London, 1959).
2. James, A. M. and Lord, M. P., *Macmillan's Chemical and Physical Data* (Macmillan, London, 1992).
3. Palmer, K. F. and Williams, D., *J. Opt. Soc. Am.* 64, 1107 (1974).

Index of Refraction of Water at Different Temperatures and Wavelengths

T (°C)	Wavelength (nm)					
	226.50	361.05	404.41	589.00	632.80	1013.98
0	1.39450	1.34896	1.34415	1.33432	1.33306	1.32612
10	1.39422	1.34870	1.34389	1.33408	1.33282	1.32591
20	1.39336	1.34795	1.34315	1.33336	1.33211	1.32524
30	1.39208	1.34682	1.34205	1.33230	1.33105	1.32424
40	1.39046	1.34540	1.34065	1.33095	1.32972	1.32296
50	1.38854	1.34373	1.33901	1.32937	1.32814	1.32145
60	1.38636	1.34184	1.33714	1.32757	1.32636	1.31974
70	1.38395	1.33974	1.33508	1.32559	1.32438	1.31784
80	1.38132	1.33746	1.33284	1.32342	1.32223	1.31576
90	1.37849	1.33501	1.33042	1.32109	1.31991	1.31353
100	1.37547	1.33239	1.32784	1.31861	1.31744	1.31114

Reference:

From Schiebener, P., Straub, J. Levert Sengers, J. M. H., and Gallagher, J. S., *J. Phys. Chem. Ref. Data* 19, 677 (1990) and the *CRC Handbook of Chemistry and Physics*, 75th edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 1994).

Temperature Derivative of the Index of Refraction n of Water

λ (nm)	dn/dT × 10 ⁶ (K ⁻¹)	Ref.	λ (nm)	dn/dT × 10 ⁶ (K ⁻¹)	Ref.
226.50	-128 (293–303 K)	1	589.3	-80 (293 K)	4
361.05	-113 (293–303 K)	1		-97 (293–298 K)	2
404.41	-110 (293–303 K)	1	632.8	-96 (293–298 K)	2
404.66	-101 (293–298 K)	2		-98.5 (298 K)	3
435.84	-100 (293–303 K)	1		-106 (293–303 K)	1
486.13	-99 (293–298 K)	2	656.28	-96 (293–298 K)	2
546.07	-98 (293–298 K)	2	706.52	-95 (293–298 K)	2
	-100 (298 K)	3	1013.98	-100 (293–303 K)	1
587.56	-97 (293–298 K)	2			

References:

1. Schiebener, P., Straub, J., Levert Sengers, J. M. H., and Gallagher, J. S., *J. Phys. Chem. Ref. Data* 19, 677 (1990).
2. Kaye, G. W. and Laby, T. H., *Tables of Physical and Chemical Constants* (Longman Group, London, 1986).
3. Hauf, W. and Grigull, U., *Optical Methods in Heat Transfer* (Academic Press, New York, 1970).
4. Kaye, G. W. and Laby, T. H., *Tables of Physical and Chemical Constants* (Longmans, Green & Co., London, 1959).

5.3 Physical Properties of Selected Liquids

Data in the following tables are in large part from the *CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL). Physical and chemical property data for many additional organic and inorganic liquids are given in this reference.

Liquid	Molecular weight	Density (g/cm ³)	Dielectric constant ϵ	Electric dipole moment (D)
acetic acid, C ₂ H ₄ O ₂	60.05	1.0492	6.20	1.74
acetone, C ₃ H ₆ O	58.08	0.7856	21.01	2.88
benzene, C ₆ H ₆	78.11	0.8765	2.2825	0
bromobenzene, C ₆ H ₅ Br	157.01	1.4950	5.45	—
carbon disulfide, CS ₂	76.14	1.2556	2.6320	0
carbon tetrachloride, CCl ₄	153.82	1.5833	2.2379	0
chloroform, CHCl ₃	119.38	1.4800	4.8069	1.01
cyclohexane, C ₆ H ₁₂	84.16	0.7731	2.0243	0
1,2-dichloroethane, C ₂ H ₄ Cl ₂	98.96	1.2457	10.10	—
dichloromethane, CH ₂ Cl ₂	84.93	1.3266	8.93	1.6
dimethylsulfoxide, C ₂ H ₆ OS	78.14	1.0955	47.24	3.96
1,4-dioxane, C ₄ H ₈ O ₂	88.11	1.0286	2.2189	—
ethanol, C ₂ H ₆ O	46.07	0.7873	25.3	1.69
ethylene glycol, C ₂ H ₆ O ₂	76.10	0.9598	41.4	2.28
glycerine (glycerol), C ₃ H ₈ O ₃	92.10	1.2567	46.53	—
heptane, C ₇ H ₁₆	100.20	0.6837	1.9209	\approx 0
hexadecane, C ₁₆ H ₃₄	226.45	0.7733	2.0460	—
hexane, C ₆ H ₁₄	86.18	0.6563	1.8865	—
methanol, CH ₄ O	32.04	0.7872	33.0	1.70
methylcyclohexane, C ₇ H ₁₄	98.19	0.7694	2.024	\approx 0
1-methylnaphthalene, C ₁₁ H ₁₀	142.20	1.0202	2.915	—
nitrobenzene, C ₆ H ₅ NO ₂	123.11	1.1985	35.6	—
toluene, C ₇ H ₈	92.14	0.8647	2.379	—
2,2,4-trimethylpentane, C ₈ H ₁₈	114.23	0.6877	1.943	—
water, H ₂ O	18.01528	0.99705	80.100	—
heavy water, D ₂ O	20.02748	1.1044	79.754	—

Density at 298 K.

1 D = 3.33564 × 10⁻³⁰ C m

Dielectric Strength of Liquids*

Liquid	Dielectric strength (kV/mm)	Ref.
carbon tetrachloride, CCl ₄	5.5	1
chlorobenzene, C ₆ H ₅ Cl	7.1	1
helium, He, liquid, 4.2 K	10	2
carbon tetrachloride, CCl ₄	16.0	3

Dielectric Strength of Liquids*—continued

Liquid	Dielectric strength (kV/mm)	Ref.
chlorobenzene, C_6H_5Cl	18.8	3
nitrogen, N_2 , liquid, 77 K:		
coaxial cylinder electrodes	20	4
sphere to plane electrodes	60	4
cyclohexane, C_6H_{12}	42–48	5
hexane, C_6H_{14}	42.0	5
water, H_2O	65–70	6
2,2,4-trimethylpentane, C_8H_{18}	140	7,8
benzene, C_6H_6	163	7,8
heptane, C_7H_{16}	166	7,8
toluene, $C_6H_5CH_3$:		
	199	7,8
	46	5
	20.4	3
	12.0	1

* The dielectric strength (or breakdown voltage) of a material depends on the specimen thickness, the electrode shape, and the rate of the applied voltage increase.

References:

1. Nitta, Y. and Ayhara, Y., *IEEE Trans. EI-1*, 91 (1976).
2. Okubo, H. Wakita, M., Chigusa, S., Nayakawa, N., and Hikita, M., *IEEE Trans. DEI-4*, 120 (1997).
3. Gallagher, T. J., *IEEE Trans. EI-12*, 249 (1977).
4. Hayakawa, H., Sakakibara, H., Goshina, H., Hikita, M., and Okubo, H., *IEEE Trans. DEI-4*, 127 (1997).
5. Wong, P. P. and Forster, E. O., *Dielectric Materials. Measurements and Applications*, IEE Conf. Publ. 177, 1 (1979).
6. Jones, H. M. and Kunhard, E. E., *IEEE Trans. DEI-1*, 1016 (1994).
7. Kao, K. C., *IEEE Trans. EI-11*, 121 (1976).
8. Sharbaugh, A. H., Rowe, R. W., and Cox, C. B., *J. Appl. Phys.* 27, 806 (1956).

Physical Properties

Liquid	Melting point (°C)	Boiling point (°C)	Specific heat capacity (J/g K)	Volume thermal expan. coeff. B_t ($10^3 K^{-1}$)
acetic acid, $C_2H_4O_2$	16.6	117.9	2.05	1.1
acetone, C_3H_6O	−94.8	56.05	2.17	1.43
benzene, C_6H_6	5.53	80.09	1.74	1.23
bromobenzene, C_6H_5Br	−30.6	156	—	—
carbon disulfide, CS_2	−111.5	46	1.00	1.19
carbon tetrachloride, CCl_4	−23	76.8	0.85	1.22
chloroform, $CHCl_3$	−63.6	61.17	0.96	1.28
cyclohexane, C_6H_{12}	6.6	80.73	1.84	1.1 ^a
1,2-dichloroethane, $C_2H_4Cl_2$	−35.5	83.5	1.30	1.16 ^a

Physical Properties—continued

Liquid	Melting point (°C)	Boiling point (°C)	Specific heat capacity (J/g K)	Volume thermal expan. coeff. β_t (10^3 K^{-1})
dichloromethane, CH_2Cl_2	-95.1	40	1.19	—
dimethylsulfoxide, $\text{C}_2\text{H}_6\text{OS}$	—	—	1.96	—
1,4-dioxane, $\text{C}_4\text{H}_8\text{O}_2$	11.8	101.5	4.9	1.03 ^a
ethanol, $\text{C}_2\text{H}_6\text{O}$	-114.1	78.29	2.44	1.10
ethylene glycol, $\text{C}_2\text{H}_6\text{O}_2$	-13	—	2.39	0.566
glycerine (glycerol), $\text{C}_3\text{H}_8\text{O}_3$	18.2	—	2.38	0.53
heptane, C_7H_{16}	-90.6	98.5	2.24	—
hexadecane, $\text{C}_{16}\text{H}_{34}$	18.1	286.8	—	—
hexane, C_6H_{14}	-95.3	68.73	2.26	1.35
methanol, CH_4O	-97.68	64.6	2.53	1.19
methylcyclohexane, C_7H_{14}	-126.6	100.9	1.88	—
1-methylnaphthalene, $\text{C}_{11}\text{H}_{10}$	-30.4	244.7	—	—
nitrobenzene, $\text{C}_6\text{H}_5\text{NO}_2$	5.7	210.8	1.51	0.83
toluene, C_7H_8	-94.99	110.63	1.71	1.06
2,2,4-trimethylpentane, C_8H_{18}	-107.3	99.2	—	—
water, H_2O	0.00	100.00	4.1818	0.256
heavy water, D_2O	3.82	101.42	—	—

Specific heat capacity and volume thermal expansion coefficients measured at 298 K except for ^a measured at 293 K.

5.3.1 Thermal conductivity

Thermal conductivity values correspond to a nominal pressure of 1 atmosphere. The values for water, benzene, and toluene are particularly well determined and can be used for calibration purposes.

Liquid	Thermal conductivity (W/m K)					
	-25°C	0°C	25°C	50°C	75°C	100°C
acetic acid, $\text{C}_2\text{H}_4\text{O}_2$			0.158	0.153	0.149	0.144
acetone, $\text{C}_3\text{H}_6\text{O}$		0.169	0.161			
benzene, C_6H_6			0.1411	0.1329	0.1247	
carbon disulfide, CS_2		0.154	0.149			
carbon tetrachloride, CCl_4		0.104	0.099	0.093	0.088	
chlorobenzene, $\text{C}_6\text{H}_5\text{Cl}$	0.136	0.131	0.127	0.122	0.117	0.112
chloroform, CHCl_3	0.127	0.122	0.117	0.112	0.107	0.102
cyclohexane, C_6H_{12}	0.137	0.129	0.121	0.113		
dibromomethane, CH_2Br_2	0.120	0.114	0.108	0.103	0.097	
1,4-dioxane, $\text{C}_4\text{H}_8\text{O}_2$			0.159	0.147	0.135	0.123
ethanol, $\text{C}_2\text{H}_6\text{O}$		0.176	0.169	0.162		
ethylene glycol, $\text{C}_2\text{H}_6\text{O}_2$		0.256	0.256	0.256	0.256	0.256

Thermal conductivity (W/m K)—continued						
Liquid	-25°C	0°C	25°C	50°C	75°C	100°C
glycerine (glycerol), C ₃ H ₈ O ₃			0.292	0.295	0.297	0.300
heavy water, D ₂ O				0.618		0.636
heptane, C ₇ H ₁₆	0.1378	0.1303	0.1228	0.1152	0.1077	
hexadecane, C ₁₆ H ₃₄	0.144	0.140	0.136	0.133	0.129	0.125
hexane, C ₆ H ₁₄	0.137	0.128	0.120	0.111	0.102	0.093
methanol, CH ₄ O	0.214	0.207	0.200	0.193		
nitrobenzene, C ₆ H ₅ NO ₂						
toluene, C ₇ H ₈	0.1461	0.1386	0.1311	0.1236	0.1161	
water, H ₂ O		0.5610	0.6071	0.6435	0.6668	0.6791

From the table in *CRC Handbook of Chemistry and Physics*, 75th edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 1994), p. 6–249. Thermal conductivity data for additional organic and inorganic liquids are given in this reference.

5.3.2 Viscosity

Liquid	Viscosity (mPa s)					
	-25°C	0°C	25°C	50°C	75°C	100°C
acetic acid, C ₂ H ₄ O ₂			1.056	0.786	0.599	0.464
acetone, C ₃ H ₆ O	0.540	0.395	0.306	0.247		
benzene, C ₆ H ₆		0.604	0.436	0.335		
bromobenzene, C ₆ H ₅ Br			10.74	0.798	0.627	0.512
carbon disulfide, CS ₂		0.429	0.352			
carbon tetrachloride, CCl ₄		1.0321	0.908	0.656	0.494	
chloroform, CHCl ₃	0.988	0.706	0.537	0.427		
cyclohexane, C ₆ H ₁₂			0.894	0.615	0.447	
1,2-dichloroethane, C ₂ H ₄ Cl ₂			0.464	0.362		
dichloromethane, CH ₂ Cl ₂	0.727	0.533	0.413			
dimethylsulfoxide, C ₂ H ₆ OS			1.987	1.290		
1,4-dioxane, C ₄ H ₈ O ₂			1.177	0.787	0.569	
ethanol, C ₂ H ₆ O	3.262	1.786	1.074	0.694	0.476	
ethylene glycol, C ₂ H ₆ O ₂			16.1	6.554	3.340	1.975
glycerine (glycerol), C ₃ H ₈ O ₃			934	152	39.8	14.8
heptane, C ₇ H ₁₆	0.757	0.523	0.378	0.301	0.243	
hexadecane, C ₁₆ H ₃₄				2.487	1.609	1.132
hexane, C ₆ H ₁₄		0.405	0.300	0.240		
methanol, CH ₄ O	1.258	0.793	0.544			
methylcyclohexane, C ₇ H ₁₄		0.991	0.679	0.501	0.390	0.316
nitrobenzene, C ₆ H ₅ NO ₂		3.036	1.863	1.262	0.918	0.704
toluene, C ₇ H ₈	1.165	0.778	0.560	0.424	0.333	0.270
water, H ₂ O		1.793	0.890	0.547	0.378	0.282

Viscosity values correspond to a nominal pressure of 1 atmosphere.

5.3.3 Surface Tension

Liquid	Surface tension σ (mN/m)				
	10°C	25°C	50°C	75°C	100°C
acetic acid, C ₂ H ₄ O ₂		27.10	24.61	22.13	
acetone, C ₃ H ₆ O		23.46	20.66		
benzene, C ₆ H ₆		28.22	25.00	21.77	
bromobenzene, C ₆ H ₅ Br	36.98	35.24	32.34	29.44	26.54
carbon disulfide, CS ₂	33.81	31.58	27.87		
carbon tetrachloride, CCl ₄		26.43	23.37	20.31	17.25
chloroform, CHCl ₃		26.67	23.44	20.20	
cyclohexane, C ₆ H ₁₂	26.43	24.65	21.68		
1,2-dichloroethane, C ₂ H ₄ Cl ₂		31.86	28.29	24.72	
dichloromethane, CH ₂ Cl ₂		27.20			
dimethylsulfoxide, C ₂ H ₆ OS		42.92	40.06		
1,4-dioxane, C ₄ H ₈ O ₂		32.75	29.28	25.80	22.32
ethanol, C ₂ H ₆ O	23.22	21.97	19.89		
ethylene glycol, C ₂ H ₆ O ₂		47.99	45.76	43.54	41.31
heptane, C ₇ H ₁₆	21.12	19.65	17.20	14.75	
hexadecane, C ₁₆ H ₃₄		27.05	24.91	22.78	20.64
hexane, C ₆ H ₁₄	19.42	17.89	15.33		
methanol, CH ₄ O	23.23	22.07	20.14		
methylcyclohexane, C ₇ H ₁₄	24.989	23.29	20.46		
nitrobenzene, C ₆ H ₅ NO ₂			40.56	37.66	34.77
toluene, C ₇ H ₈	29.71	27.93	24.96	21.98	19.01
water, H ₂ O	74.23	71.99	67.94	63.57	58.91

5.3.4 Absorption

Ultraviolet Absorption of Pure Liquids:

The following tables present data on the UV absorption edge of several common liquids. The data were obtained using a 1.00-cm pathlength cell and a water reference. From Bruno, T. J. and Svoronos, P. D. N., *CRC Handbook of Basic Tables for Chemical Analysis* (CRC Press, Boca Raton, FL, 1989), p. 213.


Acetone		Benzene	
Wavelength (nm)	Maximum absorbance	Wavelength (nm)	Maximum absorbance
330	1.000	278	1.000
340	0.060	300	0.020
350	0.010	325	0.010
375	0.005	350	0.005
400	0.005	400	0.005

Carbon tetrachloride		Chloroform	
Wavelength (nm)	Maximum absorbance	Wavelength (nm)	Maximum absorbance
263	1.000	245	1.000
275	0.100	250	0.300
300	0.005	275	0.005
350	0.005	300	0.005
400	0.005	400	0.005
Cyclohexane		Dimethyl sulfoxide	
Wavelength (nm)	Maximum absorbance	Wavelength (nm)	Maximum absorbance
200	1.000	268	1.000
225	0.170	275	0.500
250	0.020	300	0.200
300	0.005	350	0.020
400	0.005	400	0.005
1,4-Dioxane		Hexadecane	
Wavelength (nm)	Maximum absorbance	Wavelength (nm)	Maximum absorbance
215	1.000	190	1.000
250	0.300	200	0.500
300	0.020	250	0.020
350	0.005	300	0.005
400	0.005	400	0.005
Hexane		Methanol	
Wavelength (nm)	Maximum absorbance	Wavelength (nm)	Maximum absorbance
195	1.000	205	1.000
225	0.050	225	0.160
250	0.010	250	0.020
275	0.005	300	0.005
300	0.005	400	0.005
Toluene		Water	
Wavelength (nm)	Maximum absorbance	Wavelength (nm)	Maximum absorbance
284	1.000	190	0.010
300	0.120	200	0.010
325	0.020	250	0.005
350	0.005	300	0.005
400	0.005	400	0.005

Transmission Limits*

Liquid	Limit (nm)	Liquid	Limit (nm)
acetone, C ₃ H ₆ O	200	heptane, C ₇ H ₁₆	196
benzene, C ₆ H ₆	270	n-hexane, C ₆ H ₁₄	202
carbon tetrachloride, CCl ₄	2250	methanol, CH ₄ O	183
chloroform, CHCl ₃	220	methylcyclohexane, C ₇ H ₁₄	206
cyclohexane, C ₆ H ₁₂	211	1-octene, C ₈ H ₁₆	210
n-decane, C ₁₀ H ₂₂	173	n-pentane, C ₅ H ₁₂	205
p-dioxane, C ₄ H ₈ O ₂	203	toluene, C ₇ H ₈	274
ethanol, C ₂ H ₆ O	189	water, H ₂ O	178

* Transmission limits are the wavelengths of the last visible blackening on a spectrogram for reasonable exposure and development time. From Klevens, H. B. and Platt, J. R., Ultraviolet transmission limits of some liquids and solids, *J. Am. Chem. Soc.* 69, 3055 (1947).



Spectral transmission ranges of several fluids used for liquid filters. The end points are for 50% transmission through 1 mm of the liquid [from Cook, L. M. and Stokowski, S. E., Filter materials, in *Handbook of Laser Science and Technology, Volume IV: Optical Materials, Part 2* (CRC Press, Boca Raton, 1995), p. 151].

For other organic and inorganic filter solutions, see Pellicori, S. F., Transmittances of some optical materials for use between 1900 and 3400 Å, *Appl. Opt.* 3, 361 (1964); Bass, A. M., Short wavelength cut-off filters for the ultraviolet, *J. Opt. Soc. Am.* 38, 977 (1948); Ingersoll, K. A., Liquid filters for the visible and near infrared, *Appl. Opt.* 10, 2473 (1971); Ingersoll, K. A., Liquid filters for the ultraviolet, visible, and near infrared, *Appl. Opt.* 11, 2781 (1972).


5.4 Index of Refraction

5.4.1 Organic Liquids

Index of Refraction of Selected Liquids (293 K)

Liquid	n_D	Liquid	n_D
methanol, CH ₄ O	1.3288	ethylene glycol, C ₂ H ₆ O ₂	1.4318
acetone, C ₃ H ₆ O	1.3588	hexadecane, C ₁₆ H ₃₄	1.4345
ethanol, C ₂ H ₆ O	1.3611	1,2-dichloroethane, C ₂ H ₄ Cl ₂	1.4448
acetic acid, C ₂ H ₄ O ₂	1.3720	chloroform, CHCl ₃	1.4459
hexane, C ₆ H ₁₄	1.3749	carbon tetrachloride, CCl ₄	1.4601
heptane, C ₇ H ₁₆	1.3878	glycerine (glycerol), C ₃ H ₈ O ₃	1.4746
2,2,4-trimethylpentane, C ₈ H ₁₈	1.3915	toluene, C ₇ H ₈	1.4961
dimethylsulfoxide, C ₂ H ₆ OS	1.4170	benzene, C ₆ H ₆	1.5011
1,4-dioxane, C ₄ H ₈ O ₂	1.4224	nitrobenzene, C ₆ H ₅ NO ₂	1.5562
methylcyclohexane, C ₇ H ₁₄	1.4231	bromobenzene, C ₆ H ₅ Br	1.5597
dichloromethane, CH ₂ Cl ₂	1.4242	1-methylnaphthalene, C ₁₁ H ₁₀	1.6170
cyclohexane, C ₆ H ₁₂	1.4266	carbon disulfide, CS ₂	1.6319

Measured at a wavelength of 589 nm (sodium D line).



Comparison of selected liquids and optical glasses in an index of refraction Abbe number plot.

Index of Refraction *n* of Selected Liquids

Acetic acid ¹		Acetone ¹		Carbon tetrachloride ¹	
<i>λ</i> (nm)	<i>n</i> (296.05 K)	<i>λ</i> (nm)	<i>n</i> (292.55 K)	<i>λ</i> (nm)	<i>n</i> (285.45 K)
434.05	1.38003	434.05	1.36750	434.05	1.4835
486.13	1.37610	486.13	1.36366	486.13	1.4726
589.3	1.37152	589.3	1.35886	589.3	1.4656
656.28	1.36944	656.28	1.35672	656.28	1.4599

Benzene ¹		Carbon disulfide ¹		Toluene ²	
<i>λ</i> (nm)	<i>n</i> (293.15 K)	<i>λ</i> (nm)	<i>n</i> (291.15 K)	<i>λ</i> (nm)	<i>n</i> (293.15 K)
276.3	1.625	361.0	1.740	404.66	1.526120
298.1	1.598	394.4	1.704	434.05	1.51970
313.3	1.582	434.05	1.67665	435.84	1.517830
361.0	1.548	441.6	1.673	479.99	1.509285
434.05	1.52361	479.99	1.656	486.13	1.508315
486.13	1.51327	486.13	1.6539	546.07	1.500715
508.6	1.509	508.6	1.647	589.3	1.49693
589.3	1.50144	533.8	1.640	632.8	1.493680
656.28	1.49663	589.3	1.6295	656.28	1.49365
0.8	1.489	656.28	1.62011	706.52	1.489795
1.0	1.485				
1.5	1.480				
1.85	1.478				

Chloroform ¹		Cyclohexane ¹		1,4-Dioxane ²	
<i>λ</i> (nm)	<i>n</i> (293.15 K)	<i>λ</i> (nm)	<i>n</i> (293.15 K)	<i>λ</i> (nm)	<i>n</i> (293.15 K)
265.5	1.5051	265.5	1.4741	265.5	1.4699
289.4	1.4911	289.4	1.4631	289.4	1.4583
313.1	1.4806	313.1	1.4549	313.1	1.4500
486.13	1.45024	486.13	1.36662	546.07	1.4330
589.3	1.44432	589.3	1.36242	589.3	1.4311
656.28	1.44189	656.28	1.36062		

1,2-Dichloroethane ²		Ethanol ¹		Ethylene glycol ²	
<i>λ</i> (nm)	<i>n</i> (293.15 K)	<i>λ</i> (nm)	<i>n</i> (291.5 K)	<i>λ</i> (nm)	<i>n</i> (293.15 K)
434.05	1.45528	434.05	1.37011	435.83	1.4400
486.13	1.45024	486.13	1.36662	546.07	1.4330
589.3	1.44432	589.3	1.36242	589.3	1.4311
656.28	1.44189	656.28	1.36062		

Index of Refraction n of Selected Liquids—*continued*

Glycerine ¹		Hexane ¹		Methanol ¹	
λ (nm)	n (293.15 K)	λ (nm)	n (293.15 K)	λ (nm)	n (287.65 K)
434.05	1.4839	434.05	1.38365	434.05	1.33801
486.13	1.4795	486.13	1.37988	486.13	1.33490
589.3	1.4740	589.3	1.37536	589.3	1.33118
656.28	1.4717	656.28	1.37337	656.28	1.32948

Nitrobenzene ¹	
λ (nm)	n (293.15 K)
486.13	1.57124
589.3	1.55291
656.28	1.54593

References:

1. *International Critical Tables of Numerical Data, Physics and Chemistry and Technology*, Vol. VII, Washburn, E. W., Ed. (McGraw-Hill, New York, 1930).
2. James, A. M. and Lord, M. P., *Macmillan's Chemical and Physical Data* (Macmillan, London, 1992).

Temperature Derivative of the Index of Refraction

Methanol			Ethanol		
λ (nm)	$dn/dT \times 10^4$ (K $^{-1}$)	Ref.	λ (nm)	$dn/dT \times 10^4$ (K $^{-1}$)	Ref.
434.05	-3.90 (T = 288 K)	1			
486.13	-4.00 (T = 288 K)	1			
546.07	-4.05 (T = 298 K)	2	546.07	-4.05 (T = 298 K)	2
600	-4.68 (T = 278–298 K)	3	600	-4.38 (T = 278–298 K)	3
632.8	-4.00 (T = 288 K)	2	632.8	-4.00 (T = 298 K)	2
656.28	-4.00 (T = 298 K)	1			

Ethylene glycol			Glycerine		
λ (nm)	$dn/dT \times 10^4$ (K $^{-1}$)	Ref.	λ (nm)	$dn/dT \times 10^4$ (K $^{-1}$)	Ref.
486.13	-2.70 (T = 288 K)	1	486.13	-2.30 (T = 288 K)	1
600	-3.06 (T = 278–298 K)	3			
656.28	-2.60 (T = 288 K)	1	656.28	-2.20 (T = 288 K)	1

Temperature Derivative of the Index of Refraction—*continued*

Hexane			Cyclohexane		
λ (nm)	$dn/dT \times 10^4$ (K^{-1})	Ref.	λ (nm)	$dn/dT \times 10^4$ (K^{-1})	Ref.
434.05	-5.60 (T = 298 K)	1	434.05	-5.60 (T = 298 K)	1
486.13	-5.50 (T = 298 K)	1	486.13	-5.50 (T = 298 K)	1
546.07	-5.43 (T = 298 K)	2	546.07	-5.46 (T = 298 K)	2
632.8	-5.40 (T = 298 K)	2	589.3	-5.40 (T = 298 K)	3
656.28	-5.30 (T = 298 K)	1	632.8	-5.43 (T = 298 K)	2
			656.28	-5.40 (T = 298 K)	1
Benzene			Carbon tetrachloride		
λ (nm)	$dn/dT \times 10^4$ (K^{-1})	Ref.	λ (nm)	$dn/dT \times 10^4$ (K^{-1})	Ref.
434.05	-6.70 (T = 293 K)	4	434.05	-5.60 (T = 288 K)	1
486.13	-6.60 (T = 293 K)	4	486.13	-5.60 (T = 288 K)	1
546.07	-6.42 (T = 298 K)	2	546.07	-5.99 (T = 298 K)	2
589.3	-6.50 (T = 293 K)	4	589.3	-5.50 (T = 288 K)	1
632.8	-6.40 (T = 298 K)	2	632.8	-5.98 (T = 298 K)	2
656.28	-6.40 (T = 293 K)	4	656.28	-5.40 (T = 288 K)	1
Carbon disulfide			Toluene		
λ (nm)	$dn/dT \times 10^4$ (K^{-1})	Ref.	λ (nm)	$dn/dT \times 10^4$ (K^{-1})	Ref.
267.7	-17.50 (T = 291 K)	4	404.66	-5.97 (T = 293 K)	5
274.9	-15.00 (T = 291 K)	4	435.84	-5.88 (T = 293 K)	5
361.0	-9.60 (T = 291 K)	4	479.99	-5.77 (T = 293 K)	5
394.4	-9.00 (T = 291 K)	4	486.13	-5.76 (T = 293 K)	5
434.1	-8.70 (T = 291 K)	4	546.07	-5.65 (T = 293 K)	5
441.6	-8.60 (T = 291 K)	4	587.56	-5.60 (T = 293 K)	5
467.8	-8.40 (T = 291 K)	4	589.00	-5.60 (T = 293 K)	5
479.99	-8.30 (T = 291 K)	4	589.59	-5.60 (T = 293 K)	5
508.6	-8.20 (T = 291 K)	4	632.8	-5.56 (T = 293 K)	5
533.8	-8.10 (T = 291 K)	4		-5.55 (T = 298 K)	2
546.07	-7.96 (T = 298 K)	2	643.85	-5.55 (T = 293 K)	5
589.3	-8.00 (T = 291 K)	4	656.28	-5.54 (T = 293 K)	5
632.8	-7.96 (T = 298 K)	2	706.52	-5.51 (T = 293 K)	5
656.28	-7.80 (T = 291 K)	4			
Acetic acid			Chloroform		
λ (nm)	$dn/dT \times 10^4$ (K^{-1})	Ref.	λ (nm)	$dn/dT \times 10^4$ (K^{-1})	Ref.
486.13	-3.80 (T = 288 K)	1	546.07	-5.98 (T = 298 K)	2
656.28	-3.70 (T = 288 K)	1	632.8	-5.98 (T = 298 K)	2
			656.28	-5.30 (T = 298 K)	1

Acetone			Nitrobenzene		
λ (nm)	$dn/dT \times 10^4$ (K $^{-1}$)	Ref.	λ (nm)	$dn/dT \times 10^4$ (K $^{-1}$)	Ref.
486.13	-5.00 (T = 288 K)	1	486.13	-4.80 (T = 288 K)	1
546.07	-5.31 (T = 298 K)	2	546.07	-4.68 (T = 298 K)	2
589.3	-5.00 (T = 288 K)	1			
632.8	-5.31 (T = 298 K)	2	632.8	-4.68 (T = 298 K)	2
656.28	-4.90 (T = 288 K)	1	656.28	-4.60 (T = 288 K)	1

References:

1. Timmermans, J., *Physico-Chemical Constants of Pure Organic Compounds* (Elsevier, New York, 1950).
2. Hauf, W. and Grigull, U., *Optical Methods in Heat Transfer* (Academic Press, New York, 1970).
3. Lusty, M. E. and Dunn, M. H., *Appl. Phys. B* 44, 193 (1987).
4. *International Critical Tables of Numerical Data, Physics and Chemistry and Technology*, Vol. VII, Washburn, E. W., Ed., (McGraw-Hill, New York, 1930).
5. Kaye, G. W. and Laby, T. H., *Tables of Physical and Chemical Constants* (Longman Group, London, 1986).

5.4.2 Inorganic Liquids

Name	Formula	Temperature (°C)	n_D (589 nm)
ammonium	NH ₃	-77	1.3944 (578 nm)
antimony pentachloride	SbCl ₅	22	1.5925
argon	Ar	-188	1.2312
arsenic trichloride	AsCl ₃	16	1.604
bromine tribromide	BrF ₃	16	1.312
carbon disulfide	CS ₂	20	1.62774
germanium tetrabromide	GeBr ₄	26	1.6269
germanium tetrachloride	GeCl ₄	25	1.4614
helium	He	-269	1.02451 (546 nm)
hydrogen peroxide	H ₂ O ₂	28	1.4061
oxygen	O ₂	-183	1.2243 (578 nm)
phosphorus tribromide	PBr ₃	25	1.687
phosphorus trichloride	PCl ₃	21	1.5122
sulfur dichloride	SCl ₂	14	1.557
sulfur trioxide	SO ₃	20	1.40965
tetrabromosilane	SiBr ₄	31	1.5685
tetrachlorosilane	SiCl ₄	25	1.41156
tin tetrabromide	SnBr ₄	31	1.6628
tin tetrachloride	SnCl ₄	25	1.5086
xenon	Xe	-112	1.3918 (578 nm)

Reference:

Wohlfarth, C. and Wohlfarth, B., *Landolt-Börnstein, Numerical Data and Functional Relationships in Science and Technology, New Series*, III/38A, Martienssen, W., Ed. (Springer-Verlag, Heidelberg, 1996). The index of refraction at other temperatures and wavelengths may be found in this reference.

5.4.3 Calibration Liquids

The six liquids below are available in highly pure form and their index of refraction has been accurately measured as a function of wavelength and temperature. They are therefore useful for calibration of refractometers. The estimated uncertainties in the values are:

2,2,4-Trimethylpentane	± 0.00003
Hexadecane	± 0.00008
<i>trans</i> -Bicyclo[4.0.0]decane	± 0.00008
1-Methylnaphthalene	± 0.00008
Toluene	± 0.00003
Methylcyclohexane	± 0.00003

Further details are given in the references below. This table is reprinted from Reference 1 by permission of the International Union of Pure and Applied Chemistry.

References:

1. Marsh, K. N., Ed., *Recommended Reference Materials for the Realization of Physicochemical Properties* (Blackwell Scientific Publications, Oxford, 1987).
2. Tilton, L. W., *J. Opt. Soc. Am.* 32, 71 (1941).

λ (nm)	2,2,4-Trimethylpentane			Hexadecane		
	20°C	25°C	30°C	20°C	25°C	30°C
667.81	1.38916	1.38670	1.38424	1.43204	1.43001	1.42798
656.28	1.38945	1.38698	1.38452	1.43235	1.43032	1.42829
589.26	1.39145	1.38898	1.38650	1.43453	1.43250	1.43047
546.07	1.39316	1.39068	1.38820	1.43640	1.43436	1.43232
501.57	1.39544	1.39294	1.39044	1.43888	1.43684	1.43480
486.13	1.39639	1.39389	1.39138	1.43993	1.43788	1.43583
435.83	1.40029	1.39776	1.39523	1.44419	1.44213	1.44007

λ (nm)	<i>trans</i> -Bicyclo[4.0.0]decane			1-Methylnaphthalene		
	20°C	25°C	30°C	20°C	25°C	30°C
667.81	1.46654	1.46438	1.46222	1.60828	1.60592	1.60360
656.28	1.46688	1.46472	1.46256	1.60940	1.60703	1.60471
589.26	1.46932	1.46715	1.46498	1.61755	1.61512	1.61278
546.07	1.47141	1.46923	1.46705	1.62488	1.62240	1.62005
501.57	1.47420	1.47200	1.46980	1.63513	1.63259	1.63022
486.13	1.47535	1.47315	1.47095	1.63958	1.63701	1.63463
435.83	1.48011	1.47789	1.47567		1.65627	1.65386

λ (nm)	Toluene			Methylcyclohexane		
	20°C	25°C	30°C	20°C	25°C	30°C
667.81	1.49180	1.48903	1.48619	1.42064	1.41812	1.41560
656.28	1.49243	1.48966	1.48682	1.42094	1.41#42	1.41591
589.26	1.49693	1.49413	1.49126	1.42312	1.42058	1.41806
546.07	1.50086	1.49803	1.49514	1.42497	1.42243	1.41989
501.57	1.50620	1.50334	1.50041	1.42744	1.42488	1.42233
486.13	1.50847	1.50559	1.50265	1.42847	1.42590	1.42334
435.83	1.51800	1.51506	1.51206	1.43269	1.43010	1.42752


5.4.4 Abnormal Dispersion Liquids

Chromatic aberrations in complex lens systems can be corrected by combining lenses made of materials having different refractive indices and dispersions. When the partial dispersion of a material (refractive index for a pair of wavelengths) is plotted versus its Abbe number, most materials lie along a straight line, the so-called “normal” line. (Plots of relative dispersions showing the deviation of various glass types from the normal curve are included in most optical glass catalogs.) To correct for the secondary spectrum in apochromatic lens system (one corrected for three wavelengths), at least one of the materials must have an abnormal dispersion, that is, one lying off the normal line.

The wavelength dependence of the refractive index of a material can be described by the Buchdahl equation $N(\omega) = N_0 + v_1\omega + v_2\omega^2 + \dots v_j\omega^j$, where N_0 is the refractive index at the wavelengths λ , v_1, v_2, \dots characterize the dispersion, and ω is the chromatic coordinate $\omega = (\lambda - \lambda_0/[1 + 5/2(\lambda - \lambda_0)])$. The dispersive power of a material in this model is given by

$$D(\lambda) = \delta N(\lambda) / (N_0 - 1) = \sum_{i=1}^n \eta_i \omega,$$

where n is the order of the Buchdahl dispersion equation. The dispersion coefficients η are defined by $\eta_i = v_i/(N_0 - 1)$. Below is a plot of the primary and secondary dispersion properties of 178 Schott optical glasses and 300 Cargille optical liquids (courtesy of R. D. Sigler).



References:

1. Sigler, R. D., Apochromatic color correction using liquid lenses, *Appl. Opt.* 29, 2451 (1990).
2. Petrova, M. V., Petrovskii, G. T., Tolstoi, M. N., and Volynkin, V. M., Abnormal dispersion liquids, *Opt. Eng.* 31, 664 (1992).

5.5 Nonlinear Optical Properties

Abbreviations for Materials

Abbreviations	Material
4-BCMUy	Yellow form of poly-4-BCMU
4ABP	4-Aminobiphenyl
123TB	1,2,3-Trimethyl benzene
124TB	1,2,4-Trimethyl benzene
1234TB	1,2,3,4-Tetramethyl benzene
1235TB	1,2,3,5-Tetramethyl benzene
α -NPA	α -NPO (2-(1-naphthyl)-5-phenyloxazole)
BBPEN	Bis[<i>n</i> -butyl, 2-phenyl-1,2-ethenedithiolato(2-)- <i>S,S'</i>] nickel
BEEDT	Bis(1,2-diethyl-1,2-ethenedithiolato(2-)- <i>S,S'</i>) nickel
bis-MSB	<i>p</i> -Bis(<i>o</i> -methylstyryl)benzene
BP4B	Benzopurpurin 4B
BPDDT	<i>trans</i> -(Bis-(1-decyl-2-phenylethenedithiolato- <i>S,S'</i>) nickel
BRD	Bacteriorhodopsin
BSQ	1,3-Bis(4'- <i>N,N</i> -dibutylamino-2'-hydroxyphenyl)-cyclobutene-2,4-dione
BTMSF	Bis(trimethylsilyl) ferrocene
DCV	4- <i>N,N</i> -Diethylamino-4'- <i>b,b</i> -dicyanovinyl (azobenzene)
DEANS	4-Diethylamino-4'-nitrostilbene
DMF	Dimethylformamide
DMSM	4'-Dimethylamino- <i>N</i> -methyl-4-stilbazolium methylsulfate
DNTA	4-Nitrophenyldenyl (4'- <i>N,N</i> -dimethylaminoanilide)
DPA	Diphenyl amine
DQCI	1,3'-Diethyl 1,2,2-quinolylthiacarbocyanine iodide
DR1	Disperse red 1
ISQ	1,3-Bis(3',3'-dimethyl-2'-indoleninylidenyl)-cyclobutene-2,4-dione
MDCB	<i>m</i> -Dicyanobenzene
MDNB	<i>m</i> -Dinitrobenzene
Mg:OPTAP	Magnesium octaphenyl tetraazaporphyrin
MNA	2-Methyl-4-nitroaniline
MNTPM	Zinc meso-tetra-(<i>p</i> -methoxphenyl) tetrabenzporphyrin
MNTPMP	Zinc meso-tetra-(<i>p</i> -methylphenyl) tetrabenzporphyrin
MOMT	Magnesium octamethyltetrabenzporphyrin
NFAI	5-Nitro(2-furanacroleindenyl (4'- <i>N,N</i> -dimethylaminoanilide)
NPCV	4- <i>N,N</i> -Dibutylamino-4'-(<i>b</i> -cyano- <i>b</i> -(4'-nitrophenyl) vinyl) (azobenzene)
P(4ABP)	Poly(4-amino biphenyl) with 1.5% tetrafluoroborate doping
P(DPA)	Poly(diphenyl amine) with 1.5% tetrafluoroborate doping
PBPC	Pb-phthalocyanine
PMTBQ	Nonconjugated derivative of a polythiophene
PPV	Poly(<i>p</i> -phenylene vinylene)
PTPC	Pt-phthalocyanine
R6G	Rhodamine 6G
RB	Rhodamine B
rB	Rhodamine B

Abbreviations for Materials—continued

Abbreviations	Material
Retinal	6- <i>s-cis</i> and completely <i>trans</i> retinal
retinal	<i>trans</i> -Retinal, malononitrile Knoevenagel adduct
Retinyl acetate	6- <i>s-cis</i> and completely <i>trans</i> retinyl 1,2-
SiNc	Silicon naphthalocyanine
SiPc	Silicon phthalocyanine
TBPP	Tetrabenzporphyrin
TCV	4- <i>N,N</i> -Diethylamino-4'-tricyanovinyl (azobenzene)
TKCPPC	Tetrakis(cumylphenoxy)phthalocyanines
TNF	2,4,7-Trinitrofluorenone
ZHDFT	Zinc hexadecafluorotetrabenzporphyrin
ZMTM	Zinc meso-tetramethyltetrabenzporphyrin
ZMTMF	Zinc meso-tetra-(<i>m</i> -fluorophenyl) tetrabenzporphyrin
ZMTP	Zinc meso-tetraphenyltetrabenzporphyrin
ZMTPDMAP	Zinc meso-tetra-(<i>p</i> -dimethylaminohenyl) tetrabenzporphyrin

Experimental Methods

Abbreviation	Method	Ref.
AFRS	anharmonic forced Rayleigh scattering	1
AI1	attenuation vs. irradiance for a single beam	2,3
DFWM	degenerate four-wave mixing	4
ID	ionization decay	5
KE	DC Kerr effect	6
L	luminescence or fluorescence	7,8
MSI	modified Sagnac interferometry	9
OKE	optical Kerr effect	10
OL	optical limiting	11
PS	polarization spectroscopy	12
PST	power for self-trapping	13
SA	saturated absorption	14
SFL	self-focal length	15
TBC	two-beam coupling	14
TL	thermal lensing	16
TPDR	two-photon double resonance spectroscopy	17
TPIF	two-photon induced fluorescence	18
TRI	time-resolved interferometry	19

References:

- Lequime, M., and Hermann, J. P., Reversible creation of defects by light in one dimensional conjugated polymers, *Chem. Phys.* 26, 431 (1977).
- Liu, P., Smith, W. L., Lotem, H., Bechtel, J. H., Bloembergen, N., and Adhav, R. S., Absolute two-photon absorption coefficients at 355 and 266 nm, *Phys. Rev. B* 17(12), 4620 (1978).
- Bivas, A., Levy, R., Phach, V. D., and Grun, J. B., Biexciton two-photon absorption in the nanosecond and picosecond range in copper halides, in *Physics of Semiconductors 1978*, Inst. Phys. Conf. Ser. No. 43 (AIP, New York, 1979).

4. Friberg, S. R., and Smith, P. W., Nonlinear optical glasses for ultrafast optical switches, *IEEE J. Quantum Electron.* QE-23, 2089 (1987).
5. McGraw, D. J., Michaekson, J., and Harris, J. M., Anharmonic forced Rayleigh scattering: A technique for study of saturated absorption in liquids, *J. Chem. Phys.* 86, 2536 (1987).
6. Hellwarth, R. W., and George, N., Nonlinear refractive indices of $\text{CS}_2\text{-CCl}_4$ mixtures, *Opt. Electron.* 1, 213 (1969).
7. Hermann, J. P., and Ducuing, J., Absolute measurement of two-photon cross sections, *Phys. Rev. A* 5(6), 2557 (1972).
8. Webman, I., and Jortner, J., Energy dependence of two-photon absorption cross sections anthracene, *J. Chem. Phys.* 50(6), 2706 (1969).
9. Gabriel, M. C., Whitaker, Jr., N. A., Dirk, C. W., Kuzyk, M. G., and Thakur, M., Measurement of ultrafast optical nonlinearities using a modified Sagnac Interferometer, *Opt. Lett.* 16 (17), 1334 (1991).
10. Ho, P. P., and Alfano, R. R., Optical Kerr effect in liquids, *Phys. Rev. A* 20(5), 2170 (1979).
11. Winter, C. S., Oliver, S. N., and Rush, J. D., n_2 measurements on various forms of ferrocene, *Opt. Commun.* 69, 45 (1988).
12. Marcano, O., A., Abreu, R. A., and Garcia-Golding, F., Electronic and thermal contributions to the polarization spectrum of DQCI, *J. Phys. B: At. Mol. Phys.* 17, 2151 (1984).
13. Wang, C. C., Nonlinear susceptibility constants and self-focusing of optical beams in liquids, *Phys. Rev.* 152(1), 149 (1966).
14. Tompkin, W. R., Boyd, R. W., Hall, D. W., Tick, P. A., *J. Opt. Soc. Am. B* 4, 1030 (1987).
15. Hongyo, M., Sasaki, T., and Yamanaka, C., Nonlinear effects of POCl_3 liquid laser, *Technol. Rep. Osaka Univ.* 23(1121–1154), 455 (1973).
16. Twarowski, A. J., and Kliger, D. S., Multiphoton absorption spectra using thermal blooming, *Chem. Phys.* 20, 259 (1977).
17. Chen, C. H., and McCann, M. P., Measurements of two-photon absorption cross sections for liquid benzene and methyl benzenes, *J. Chem. Phys.* 88 (8), 4671 (1988).
18. Rice, J. K., and Anderson, R. W., Two-photon, thermal lensing spectroscopy of monosubstituted benzenes in ${}^1\text{B}_{2u}({}^1\text{L}_b) - {}^1\text{A}_{1g}({}^1\text{A})$ and ${}^1\text{B}_{1u}({}^1\text{L}_a) - {}^1\text{A}_{1g}({}^1\text{A})$ transition regions, *J. Chem. Phys.* 90, 6793 (1986).
19. Milam, D., and Weber, M. J., Measurement of nonlinear refractive-index coefficients using time-resolved interferometry: application to optical materials for high-power neodymium laser, *J. Appl. Phys.* 47, 2497 (1976).

5.5.1 Two-Photon Absorption Cross Sections

The two-photon absorption cross section σ_2 is related to the two-photon absorption coefficient β by $\sigma_2 = (hv/N)\beta$, where N is the number density of molecules.

Two-Photon Absorption Coefficient β

Liquid	Wavelength (nm)	Pulse length (ns)	$\beta \times 10^{11}$ (m/W)	Ref.
benzene, C_6H_6	354.7	5	1.5	1
	532.1	5	4.5×10^{-5}	1
cyclohexane, C_6H_{12}	694.3	14	1.9	2
toluene, C_7H_8	354.7	5	1.2	1
	532.1	5	6.3×10^{-4}	1

References:

1. Chen, C. H. and McCann, M. P., *J. Phys. Chem.* 88, 4671 (1988).
2. Lotem, H. and de Araujo, C. B., *Phys. Rev. B* 16, 1711 (1977).

Two-Photon Absorption Cross Sections

Material	Method	Excitation duration (ns)	Applied two-photon energy (eV)	Two-Photon cross section σ_2	
				$10^{-50} \text{ cm}^4 \text{ s/phot. mol.}$	Ref.
123TB	TPIF	5	4.66	0.0021	1
124TB	TPIF	5	4.66	0.075	1
1234TB	TPIF	5	4.66	0.076	1
1235TB	TPIF	5	4.66	0.18	1
α -NPA	L	0.002–0.003	3.57–4.62	Relative spectrum	2
Aniline	TL		3.96–5.69	Relative spectrum ($8.8 \times$ benzene @ 4.10 eV)	3
Anthracene	L	40	3.57	14	4
Azulene	AFRS	42–67	4.66	1070	5
Benzene	TL		4.46–5.69	Relative spectrum ($49.0 \times$ benzene @ 4.98 eV)	3
	TPIF	5	4.66	0.00025	1
Bis-MSB	L	0.002–0.003	3.57–4.62	Relative spectrum (690 @ 4.24 eV)	2
BRD	TPDR	6	2.07	169	6
	TPDR	6	2.12	207	6
	TPDR	6	2.16	247	6
	TPDR	6	2.21	289	6
	TPDR	6	2.30	288	6
	TPDR	6	2.36	244	6
	TPDR	6	2.56	201	6
	TPDR	6	2.70	167	6
	TPDR	6	2.78	127	6
	TPDR	6	2.92	174	6
	TPDR	6	3.02	199	6
Fluorobenzene	TL		4.46–5.69	Relative spectrum ($1.5 \times$ benzene @ 4.65 eV and $5.5 \times$ benzene @ 5.69 eV)	3
Mesitylene	TPIF	5	4.66	0.096	1
<i>m</i> -Xylene	TPIF	5	4.66	0.028	1
<i>o</i> -Xylene	TPIF	5	4.66	0.035	1
<i>p</i> -Xylene	TPIF	5	4.66	0.052	1

Two-Photon Absorption Cross Sections—*continued*

Material	Method	Excitation duration (ns)	Applied two-photon energy (eV)	Two-Photon cross section σ_2 $10^{-50}\text{cm}^4\text{s/phot. mol.}$		Ref.
Phenol	TL		4.21–5.69	Relative spectrum (0.8 × benzene @ 4.39 eV and 8.6 × @ 5.45 eV)		3
Pyridine	TL		4–6.2	Relative spectrum (0.27 @ 4.5 eV)		7
R6G	AI1	0.015	3.57	180		8
RB	AI1	0.015	3.57	120		8
Retinal	L	40	3.57	27 (in ethanol)		4
Retinyl acetate	L	40	3.57	26 (in n-hexane)		4
	L	40	3.57	29 (in EPIP)		4
Toluene	TL		4.46–5.69	Relative spectrum (2.1 × benzene @ 4.59 eV and 3.3 × @ 5.62 eV)		3
TPIF	5		4.66	0.0036		1

Table from Garito, A. F. and Kuzyk, M G., Two-photon absorption, organic materials, in *Handbook of Laser Science and Technology, Supplement 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 329.

References:

- Chen, C. H., and McCann, M. P., Measurements of two-photon absorption cross sections for liquid benzene and methyl benzenes, *J. Chem. Phys.* 88, 4671 (1988).
- Kennedy, S. M., and Lytle, F. E., *p*-bis(*o*-Methylstyryl)benzene as a power-squared sensor for two-photon absorption measurements between 537 and 694 nm, *Anal. Chem.* 58, 2643 (1986).
- Rice, J. K., and Anderson, R. W., Two-photon, thermal lensing spectroscopy of monosubstituted benzenes in ${}^1\text{B}_{2u}({}^1\text{L}_b) \leftarrow {}^1\text{A}_{1g}({}^1\text{A})$ and ${}^1\text{B}_{1u}({}^1\text{L}_a) \leftarrow {}^1\text{A}_{1g}({}^1\text{A})$ transition regions, *J. Chem. Phys.* 90, 6793 (1986).
- Bachilo, S. M., and Bondarev, S. L., Spectral and polarization features of two-photon absorption in retinal and retinyl acetate, *J. Appl. Spectrosc.* 45, 1078 (1986); translated from *Zhurnal Prikladnoi Spektroskopii* 45, 623 (1986).
- McGraw, D. J., Michaekson, J., and Harris, J. M., Anharmonic forced Rayleigh scattering: A technique for study of saturated absorption in liquids, *J. Chem. Phys.* 86, 2536 (1987).
- Birge, R. R., and Zhang, C. F., Two-photon double resonance spectroscopy of bacteriorhodopsin. Assignment of the electronic and dipolar properties of the low-lying ${}^1\text{A}_{\text{g}}^{*-}$ -like and ${}^1\text{B}_{\text{g}}^{*+}$ -like π , π^* states, *J. Chem. Phys.* 92, 7178 (1990).
- Salvi, P. R., Foggi, P., Bini, R., and Castellucci, E., The two-photon spectrum of liquid pyridine by thermal lensing techniques, *Chem. Phys. Lett.* 141, 417 (1987).
- Sperber, P., and Penzkofer, H., $\text{S}_0\text{-S}_n$ two-photon absorption dynamics of rhodamine dyes, *Opt. Quantum Electron.* 18, 281 (1986).

5.5.2 Nonlinear Refraction

Nonlinear Refractive Index γ

Liquid	Wavelength (μm)	$\gamma \times 10^{20}$ (m^2/W)	Ref.
acetic acid, $\text{C}_2\text{H}_4\text{O}_2$	0.6943	22.6	1
acetone, $\text{C}_3\text{H}_6\text{O}$	0.6943	13.3	1
benzene,* C_6H_6	0.57	38	4,7
	0.6943	35	1
carbon disulfide,* CS_2	0.53	310 ± 30	3
	0.6943	390 ± 50	4
	1.0642	290 ± 30	5
	1.32	330	4
	10.6	390 ± 150	6
carbon tetrachloride, CCl_4	0.53	10.2	4,7
	0.56-0.59	8.0	8
	0.6943	5.8	1
chloroform, CHCl_3	0.53	20	4,7
	0.6943	17	1
cyclohexane, C_6H_{12}	0.53	7.6	4,7
	0.55-0.58	12.3 ± 0.9	9
1,2-dichloroethane, $\text{C}_2\text{H}_4\text{Cl}_2$	0.53	24	4,7
ethanol, $\text{C}_2\text{H}_6\text{O}$	0.53	5.2	4,7
glycerine (glycerol), $\text{C}_3\text{H}_8\text{O}_3$	0.53	4.7	4,7
heavy water, D_2O	1.06	6.4	10
methanol, CH_4O	0.53	4.7	4,7
nitrobenzene, $\text{C}_6\text{H}_5\text{NO}_2$	0.53	450	4,7
	0.6943	240	1
toluene, C_7H_8	0.53	113	4,7
	0.6943	85	1
water, H_2O	0.53	2.7	4,7
	0.6943	2.8	1
	1.0642	5.4(?)	10

Measurements made at room temperature.

* Materials used for liquid optics based on nonlinear self-focusing [Ramanthan, D. and Molian, P. A., Laser micromachining using liquid optics, *Appl. Phys. Lett.* 78, 1484 (2001)].

References:

- Smith, W. L., Nonlinear refractive index, in *CRC Handbook of Laser Science and Technology, Vol. III, Optical Materials: Part 1* (CRC Press, Boca Raton, FL, 1986), p. 259.
- Owyong, A. and Peercy, P. S., *J. Appl. Phys.* 48, 674 (1977).
- Bennett, H. E., Guenther, A. H., Milam, D., and Newnam, B. E., *Appl. Opt.* 26, 813 (1987).
- Witte, K. J., Galanti, M., and Volk, R., *Opt. Commun.* 34, 278 (1980).
- Cherlow, J. M., Yang, T. T., and Hellwarth, R. W., *IEEE J. Quantum Electron.* QE-12, 644 (1976).

6. Sheik-Bahae, M., Said, A. A., Wei, T.-H., Hagan, D. J., and Van Stryland, E. W., *IEEE J. Quantum Electron.* 26, 760 (1990).
7. Ho, P. P. and Alfano, R. R., *Phys. Rev. A* 20, 2170 (1979).
8. Levenson, M. D. and Bloembergen, N., *J. Chem. Phys.* 60, 1323 (1974).
9. Song, J. J. and Levenson, M. D., *J. Appl. Phys.* 48, 3496 (1977).
10. Smith, W. L., Liu, P., and Bloembergen, N., *Phys. Rev. A* 15, 2396 (1977).

Nonlinear Refraction Data for Solutions

Material	Solvent	Dye weight fract.(%)	Method	Pulse length (ns)	Wave-length (nm)	Linear refract. index	$\chi_{1111}^{(3)}, \chi_{1212}^{(3)}$ ($10^{-12}\text{cm}^3/\text{erg}$)	Ref.
4-BCMUy	DMF	14	DFWM	0.033	1064	1.43	1.4	7
DEANS	DMF	3	OKE	6	700, 830		^a 0.2	8
DMSM	Ethanol	5	OKE	6	700, 830		0.46	8
DMSM	Formamide	20	OKE	6	700, 830		3	8
MNA	Ethanol	5	OKE	6	700, 830		^a 0.2	8
P(4ABP)	DMF	10^{-2} – 10^{-3} M/l	DFWM	0.040	1064	1.43	0.31, 0.17	9
P(DPA)	DMF	10^{-2} – 10^{-3} M/l	DFWM	0.040	1064	1.43	0.48, 0.22	9
PBPC ^a	CHCl ₃	0.73 M/l	DFWM	0.035	1064		200	10
PMTBQ ^a	DCM	100	DFWM	0.030	532		4600	11
PTPC ^a	CHCl ₃	0.73 M/l	DFWM	0.035	1064		20	10
Retinal	DMSO	10^{-3} M/l	DFWM	6	532		4.3	12
TKCPPC ^a	CHCl ₃	0.73 M/l	DFWM	0.035	1064		4.0	10

^aExtrapolated from solution measurement.

Nonlinear Refraction Data for Dye Solutions

Dye	Solvent	Dye conc. (10^{22}cm^{-3})	Method	Pulse length (ns)	Wave-length (nm)	Linear refract. index	$\chi_{1111}^{(3)}$ ($10^{-20}\text{m}^2/\text{V}^2$)	Ref.
A9860	1,2-dichloroethane	0.58	DFWM	0.16	532	1.45	1.8	2,3
b-Carotene	EtOH	20	DFWM	0.16	532	1.3	0.2	1,3
BDN	Toluene	1.6	DFWM	0.16	532	1.49	1.7	2,3
BEEDT	Dichloromethane	0.0001	DFWM	0.1	1064		0.36	4
BPDDT	Dichloromethane	0.0001	DFWM	0.1	1064		1.36	4
DNTPC	MtOH	4.3	DFWM	0.16	532	1.3	1.0	2,3
DTTC	MtOH	25	DFWM	0.16	532	1.3	0.8	2,3
IR5	1,2-Dichloroethane	1	DFWM	0.16	532	1.45	2.1	2,3
Nigrosine	H ₂ O	42	DFWM	0.16	532	1.33	2.6	2,3
S501	<i>o</i> -Dichlorobenzene	0.5	DFWM	0.16	532	1.55	1.25	2,3

Nonlinear Refraction Data for Dye Solutions—*continued*

Dye	Solvent	Absorption coeff. $\alpha(\text{cm}^{-1})$	Method	Pulse length (ns)	Wave- length (nm)	$(10^{-20} \text{ m}^2/\text{V}^2)$	$\chi_{1111}^{(3)}$ $(10^{-12} \text{ cm}^3/\text{erg})$	Ref.
BP4B	Acetone	0.39	DFWM	20	532	89		5
BP4B	Ethanol	0.67	DFWM	20	532	151		5
BP4B	Glycerol	2.28	DFWM	20	532	130		5
BP4B	Methanol	0.74	DFWM	20	532	146		5
Chrysoidin ^a	Acetone	0.21	DFWM	20	532	83.1		5
Chrysoidin	Ethonal	0.67	DFWM	20	532	113		5
Chrysoidin	Methonal	0.66	DFWM	20	532	146		5
DQCI	Acetone	92	PS	6	590		8000	6
DQCI	Acetone	16.1	PS	6	590		1600	6
DQCI	Acetone	267	PS	6	590		20000	6
Malachite green	Acetone	27.6	PS	6	610		8800	6
Malachite green	Acetone	82.8	PS	6	610		4000	6
Malachite green	Acetone	175	PS	6	610		7000	6

^aLinear refractive index = 1.33.

Dye	Solvent	Dye conc. (10^{-4} M/l)	Method	Pulse length (ns)	Wave- length (nm)	Linear refract. index	$\chi_{1111}^{(3)}$ $(10^{-20} \text{ m}^2/\text{V}^2)$	Ref.
BDN	Toluene	*	DFWM	0.18	1064	1.5	91	2
CoTPP	Toluene	0.727	DFWM	0.08–0.2	532		10	2
H ₂ TPP	Toluene	3.86	DFWM	0.08–0.2	532		40	2
IR5	1,2-Dichloroethane	*	DFWM	0.18	1064	1.45	62	2
S501	1,2-Dichloroethane	*	DFWM	0.18	1064	1.45	59	2
Z _n TPP	Toluene	2.29	DFWM	0.08–0.2	532		20	2

*Dye concentration adjusted for 50% transmission in a 2-mm cell.

Dye	Solvent	Dye conc. (10^{-4} g/ml)	Method	Pulse length (ns)	Wave- length (nm)	Linear refract. index	$\chi_{1111}^{(3)}$ $(10^{-12} \text{ cm}^3/\text{erg})$	Ref.
MNTPM	THF	0.1–1.0	DFWM	17	532		14000	1
MNTPMP	THF	0.1–1.0	DFWM	17	532		12000	1
MOMT	THF	0.1–1.0	DFWM	17	532		8000	1
TBPP	THF	0.1–1.0	DFWM	17	532		3000	1
ZHDFT	THF	0.1–1.0	DFWM	17	532		2000	1
ZMTM	THF	0.1–1.0	DFWM	17	532		15000	1
ZMTMF	THF	0.1–1.0	DFWM	17	532		13000	1
ZMTP	THF	0.1–1.0	DFWM	17	532		3000	1
ZMTPDMAP	THF	0.1–1.0	DFWM	17	532		28000	1

Nonlinear Refraction Data for Liquids

Liquid	Method	Pulse length (ns)	Wave-length (nm)	Linear refract. index	$\chi_{1111}^{(3)}, \chi_{1212}^{(3)}$ (10 ⁻¹² cm ³ /erg)	$\chi_{1111}^{(3)}$ (10 ⁻¹² cm ³ /erg)	Ref.
4ABP	DFWM	0.040	1064		$<\chi^{(3)}> = 3$		9
α -Picoline	TRI	0.025	532		0.045	0.05	13
Benzene	OKE	0.03	1064, 459	1.52 ^a	0.057		14
Benzene	OKE	0.03	1064, 472	1.52 ^a	0.057		14
Benzene	OKE	0.03	1064, 496	1.51 ^a	0.068		14
Benzene	OKE	0.03	1064, 517	1.51 ^a	0.059		14
Benzene	OKE	0.03	1064, 590	1.50 ^a	0.070		14
Benzene	TRI	0.025	532	1.51	0.036	0.049	13
Benzene chloride	DFWM	0.033	1064		$\chi_{1212}^{(3)} = 0.11$		7
BTMSF	OL	10	1060	1.55		0.20	15
CCl ₄	TRI	0.025	532	1.45	0.008	0.009	16
CH ₃ COCH ₃	TRI	0.025	532		0.009	0.010	16
Chloroform	TRI	0.025	532	1.45	0.015	0.019	16
CS ₂	DFWM	0.033	1064		$\chi_{1212}^{(3)} = 0.32$		7
CS ₂	PST	130	10600	1.63		8.75	16
CS ₂	TRI	0.025	532	1.63	0.60	0.68	13
CS ₂	SFL	3	10600	1.63		0.83	17
Cyclohexane	RTI	0.025	532	1.43	0.007	0.009	13
DMF	DFWM	0.033	1064		$\chi_{1212}^{(3)} = 0.033$		7
DPA	DFWM	0.040	1064		$<\chi^{(3)}> = 3$		9
Molten ferrocene	OL	10	1060	1.55		0.17	15
Nitrobenzene	OKE	0.03	1064, 459	1.58 ^a	0.13		14
Nitrobenzene	OKE	0.03	1064, 472	1.58 ^a	0.168		14
Nitrobenzene	OKE	0.03	1064, 496	1.57 ^a	0.146		14
Nitrobenzene	OKE	0.03	1064, 517	1.56 ^a	0.132		14
Nitrobenzene	OKE	0.03	1064, 590	1.55 ^a	0.084		14
Nitrobenzene	OL	10	1060	1.56		0.20	15
Nitrobenzene	TRI	0.025	532	1.55	0.11	0.13	13
P(4ABP)	DFWM	0.040	1064		$<\chi^{(3)}> = 100$		9
P(DPA)	DFWM	0.040	1064		$<\chi^{(3)}> = 100$		9
PPV	DFWM	0.0004	602,580		400		18
Toluene	RTI	0.025	532	1.49	0.018	0.038	13

^aRefractive index of probe beam.

The tables above are from Garito, A. F. and Kuzyk, M G., Two-photon absorption, organic materials, *Handbook of Laser Science and Technology, Supplement 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 289.

References:

1. Rao, D. V. G. L. N., Aranda, F. J., Roach, J. F., and Remy, D. E., Third-order, nonlinear optical interactions of some benzoporphyrins, *Appl. Phys. Lett.* 58(12), 1241 (1991).
2. Maloney, C., Byrne, H., Dennis, W. M., and Blau, W., Picosecond optical phase conjugation using conjugated organic molecules, *Chem. Phys.* 21, 21 (1988).
3. Maloney, C., and Blau, W., Resonant third-order hyperpolarizabilities of large organic molecules, *J. Opt. Soc. Am. B* 4(6), 1035 (1987).
4. Winter, C. S., Hill, C. A. S., and Underhill, A. E., Near resonance optical nonlinearities in nickel dithiolene complexes, *Appl. Phys. Lett.* 58(14), 107 (1991).
5. Mailhot, S., Galarneau, P., Lessard, R. A., and Denariez-Roberge, M.-M., Degenerate four-wave mixing in organic azo dyes chrysoidin and benzopurpurin 4B, *Appl. Opt.* 27(16), 3418 (1988).
6. Marcano, A., and Aranguren, L., Absolute values of the nonlinear susceptibility of dye solutions measured by polarization spectroscopy, *J. Appl. Phys.* 62(8), 3100 (1987).
7. Nunzi, J. M., and Grec, D., Picosecond phase conjugation in polydiacetylene gels, *J. Appl. Phys.* 62(6), 2198 (1987).
8. Kanabara, H., Kobayashi, H., and Kubodera, K., Optical Kerr shutter performance of a solution of organic nonlinear optical materials, *IEEE Phot. Tech. Lett.* 1(6), 149 (1989).
9. Chandrasekhar, P., Thorn, J. R. G., and Hochstrasser, R. M., Third-order nonlinear-optical properties of poly(diphenyl amine) and poly(4-amino biphenyl), novel processible conducting polymers, *Appl. Phys. Lett.* 59(14), 1661 (1991).
10. Shirk, J. S., Lindle, J. R., Bartoli, F. J., Hoffman, C. A., Kafafi, Z. H., and Snow, A. W., Off-resonant third-order optical nonlinearities of metal-substituted phthalocyanines, *Appl. Phys. Lett.* 55(13), 1287 (1989).
11. Jenekhe, S. A., Lo, S. K., and Flom, S. R., Third-order nonlinear optical properties of a soluble conjugated polythiophene derivative, *Appl. Phys. Lett.* 54 (25), 2524 (1989).
12. Sakai, T., Kawabe, Y., Ikeda, H., and Kawasaki, K., Third-order nonlinear optical properties of retinal derivatives, *Appl. Phys. Lett.* 56(5), 411 (1990).
13. Xuan, N. P., Ferrier, J - L, Gazengel, J., and Rivoire, G., Picosecond measurements of the third order susceptibility tensor in liquids, *Opt. Commun.* 51(6), 433 (1984).
14. Kuzyk, M. G., Norwood, R. A., Wu, J. W., and Garito, A. F., Frequency dependence of the optical Kerr effect and third-order electronic nonlinear-optical processes of organic liquids, *J. Opt. Soc. Am. B* 6(2), 154 (1989).
15. Winter, C. S., Oliver, S. N., and Rush, J. D., n_2 measurements on various forms of ferrocene, *Opt. Commun.* 69(1), 45 (1988).
16. Mohebi, M., Aiello, P. F., Reali, G., Soileau, M. J., and Van Stryland, E. W., Self-focusing in CS₂ at 10.6 mm, *Opt. Lett.* 10(8), 396 (1985).
17. Golub, I., Beaudoin, Y., and Chin, S. L., Nonlinear refraction in CS₂ at 10.6 μm , *Opt. Lett.* 13 (6), 488 (1988).
18. Bhanu, Singh, P., Prasad, P. N., and Karasz, F. E., Third-order non-linear optical properties of oriented films of poly(*p*-phenylene vinylene) investigated by femtosecond degenerate four wave mixing, *Polymer* 29, 1949 (1988).

5.5.3 Kerr Constants

DC Kerr Constants of Pure Liquids

Liquid	DC Kerr constant B_0 (10^{-16} m/V 2)	Liquid	DC Kerr constant B_0 (10^{-16} m/V 2)
acetone, C ₃ H ₆ O	1814	cyclohexane, C ₆ H ₁₂	8.2
benzene, C ₆ H ₆	66	ethanol, C ₂ H ₆ O	85.5
carbon disulfide, CS ₂	358.9	hexane, C ₆ H ₁₄	5.0
carbon tetrachloride, CCl ₄	8.2	methanol, CH ₄ O	107.9
bronobenzene, C ₆ H ₅ Br	1012	nitrobenzene, C ₆ H ₅ NO ₂	28500
cyclohexane, C ₆ H ₁₂	8.2	toluene, C ₇ H ₈	83.3

Measurements made at a wavelength of 589.3 nm and 293 K.

Reference:

- Shen, Y. R., Electrostriction, optical Kerr effect and self-focusing of laser beams, *Phys. Lett.* 20, 378–380 (1966).

DC Kerr Response of Binary Liquids

Material A	Material B	Molar fraction A	Wave-length (nm)	Linear refract. index	Temp. (°C)	$n_{1111}^{(2)} - n_{1122}^{(2)}$ (10^{-20} m 2 /V 2)
Benzene	Chlorobenzene	0	632.8	1.524	25	9.15
Benzene	Chlorobenzene	0.3	632.8		25	6.21
Benzene	Chlorobenzene	0.6	632.8		25	3.28
Benzene	Chlorobenzene	1.0	632.8	1.501	25	0
Cyclohexane	Nitrobenzene	0	632.8	1.556	25	28.2
Cyclohexane	Nitrobenzene	0.2	632.8		25	16.4
Cyclohexane	Nitrobenzene	0.4	632.8		25	9.32
Cyclohexane	Nitrobenzene	0.8	632.8		25	1.41
Cyclohexane	Nitrobenzene	1.0	632.8	1.427	25	0
Nitromethane	Chlorobenzene	0	632.8	1.524	25	9.15
Nitromethane	Chlorobenzene	0.4	632.8		25	10.7
Nitromethane	Chlorobenzene	0.7	632.8		25	12.3
Nitromethane	Chlorobenzene	1.0	632.8	1.382	25	8.28
Pyridine	2,6-Lutidine	0	632.8	1.495	25	8.28
Pyridine	2,6-Lutidine	0.6	632.8		25	11.9
Pyridine	2,6-Lutidine	1.0	632.8	1.509	25	14.5

Reference:

- Piazza, R., Degiorgio, V., and Bellini, T., Kerr effect in binary liquids, *J. Opt. Soc. Am. B* 3, 1642 (1986).

DC Kerr Response of Binary Liquids

<u>Material</u>	Weight		<u>refractive Index</u>	<u>Temp.</u> (°C)	<u>$n_{1111}^{(2)} - n_{1222}^{(2)}$</u> $(10^{-20} \text{ m}^2/\text{V}^2)$
	<u>A</u>	<u>B</u>			
Lutidine	H ₂ O	0	632.8	1.33	23–32.8 24.0
Lutidine	H ₂ O	35	632.8		23 10.2
Lutidine	H ₂ O	35	632.8		32 21.9
Lutidine	H ₂ O	35	632.8		32.8 38.0
Lutidine	H ₂ O	100	632.8		32 8.76
Lutidine	H ₂ O	100	632.8		32.8 8.76
Lutidine	H ₂ O	100	632.8	1.495	23 8.76

Reference:

Piazza, R., Degiorgio, V., and Bellini, T., Kerr effect in binary liquids, *J. Opt. Soc. Am. B* 3, 1642 (1986).

The tables above are from Garito, A. F. and Kuzyk, M. G., Two-photon absorption, organic materials, *Handbook of Laser Science and Technology, Supplement 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 289.

Optical Kerr Constant

The laser-induced Kerr constant is given by $B_0 = (2\pi/n\lambda_p)(\chi^{(3)}_{1212} + \chi^{(3)}_{1221})$, where λ_p is the linearly polarized probe beam wavelength.

Optical Kerr Constants of Pure Liquids

<u>Liquid</u>	<u>Wavelength</u>		<u>Optical Kerr constant</u> <u>$B_0 (10^{-16} \text{ m/V}^2)$</u>
	<u>(nm)</u>	<u>(nm)</u>	
acetic acid	532		33.0
	694		22.9
	1064		21.5
acetone, C ₃ H ₆ O	694		8.2
benzene, C ₆ H ₆	532		79
	694		70
	1064		51
carbon disulfide, CS ₂	694		470
	1064		360
carbon tetrachloride, CCl ₄	694		8.9
	1064		3.3
chlorobenzene, C ₆ H ₅ Cl	1064		89.9
chloroform, CHCl ₃	694		23
	1064		18

Optical Kerr Constants of Pure Liquids—*continued*

Liquid	Wavelength (nm)	Optical Kerr constant B_0 (10^{-16} m/V ²)
cyclohexane, C ₆ H ₁₂	694	6.8
<i>m</i> -dichlorobenzene, C ₆ H ₄ Cl ₂	694	170
<i>o</i> -dichlorobenzene, C ₆ H ₄ Cl ₂	694	179
ethanol, C ₂ H ₆ O	694	5.22
	1064	5.1
heavy water, D ₂ O	1064	2.9
heptane, C ₇ H ₁₆	694	11.3
	1064	7.6
hexadecane, C ₁₆ H ₃₄	694	20.2
hexane, C ₆ H ₁₄	694	9.9
	1064	6.9
methanol, CH ₄ O	694	4.76
	1064	3.3
methylcyclohexane, C ₇ H ₁₄	694	7.7
nitrobenzene, C ₆ H ₅ NO ₂	694	420
	1064	260
tetrachloroethylene, C ₂ Cl ₄	694	148
toluene, C ₇ H ₈	694	120
	1064	99
water, H ₂ O	694	4.6
	1064	2
<i>o</i> -xylene, C ₈ H ₁₀	694	130
<i>m</i> -xylene, C ₈ H ₁₀	694	125
<i>po</i> -xylene, C ₈ H ₁₀	694	120

Measurements at room temperature.

Reference:

1. Harrison, N. J. and Jennings, B. R., Laser-induced Kerr constants for pure liquids, *J. Phys. Chem. Ref. Data* 21, 157–163 (1992).

5.5.4 Third-Order Nonlinear Optical Coefficients

Liquid	Nonlinear optical process	Coefficient $C_{jn} \times 10^{20} \text{ m}^2 \text{ V}^{-2}$	Wavelength (μm)
acetone, $\text{C}_3\text{H}_6\text{O}$	$(-\omega; \omega, \omega, -\omega)$	$C_{11} = 0.252 \pm 0.056$	0.6943
benzene, C_6H_6	$(-\omega; \omega, \omega, -\omega)$	$C_{11} = 0.518 \pm 0.07$	0.6943
		$C_{18} = 0.098$	0.5000
		$C_{18} = 0.0782$	0.6943
		$C_{18} = 0.091$	0.694
	$(-\omega_1; \omega_1, \omega_2, -\omega_2)$	$C_{18} = 0.028$	0.4880
	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 0.56$	0.694
		$C_{11} = 0.242 \pm 0.024$	0.5250
		$C_{11} = 0.00859 \pm 0.00037$	0.545
		$C_{18} = 0.252 \pm 0.00014$	0.545
	$(3\omega; \omega, \omega, \omega)$	$C_{11} = 0.0184 \pm 0.056$	1.89
	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.02215 \pm 15\%$	1.06
		$C_{11} = 0.02215 \pm 15\%$	1.318
bromobenzene, $\text{C}_6\text{H}_5\text{Br}$	$(-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2)$	$C_{11} = 0.084$	0.6943
		$C_{11} = 0.0196 \pm 15\%$	1.06
carbon disulfide, CS_2	$(-\omega; \omega, \omega, -\omega)$	$C_{18} = 0.476$	0.694
		$C_{18} = 0.560$	0.500
	$(-\omega_1; \omega_1, \omega_2, -\omega_2)$	$C_{18} = 0.266$	0.4880
	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.06233 \pm 15\%$	1.06
carbon tetrachloride, CCl_4	$(-\omega; \omega, \omega, -\omega)$	$C_{18} = 0.0168 \pm 30\%$	0.694
	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.0182 \pm 15\%$	1.06
chloroform, CHCl_3	$(-\omega; \omega, \omega, -\omega)$	$C_{18} = 0.07 \pm 30\%$	1.06
1,2-dichloroethane, $\text{C}_2\text{H}_4\text{Cl}_2$	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.042 \pm 15\%$	1.06
1,4-dioxane, $\text{C}_4\text{H}_8\text{O}_2$	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.01351 \pm 15\%$	1.06
ethanol, $\text{C}_2\text{H}_6\text{O}$	$(-\omega; \omega, \omega, -\omega)$	$C_{18} = 0.0315$	0.694
		$C_{11} = 0.196 \pm 0.042$	0.6943
glycerine (glycerol), $\text{C}_3\text{H}_8\text{O}_3$	$(-\omega; \omega, \omega, -\omega)$	$C_{11} = 0.196 \pm 0.07$	0.6943
heptane, C_7H_{16}	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.84 \pm 15\%$	1.06
hexane, C_6H_{14}	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.7105 \pm 15\%$	1.06
methanol, CH_4O	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.301 \pm 15\%$	1.06
methylbenzene, C_6H_8	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.056$	0.6943
nitrobenzene, $\text{C}_6\text{H}_5\text{NO}_2$	$(-\omega; \omega, \omega, -\omega)$	$C_{18} = 0.42$	0.500
		$C_{18} = 0.322$	0.6943
		$C_{11} = 1.148 \pm 0.140$	0.6943
	$(-\omega_1; \omega_1, \omega_2, -\omega_2)$	$C_{18} = 0.182$	0.4880
	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.585 \pm 15\%$	1.318
		$C_{11} = 0.360 \pm 15\%$	1.06
nitromethane, CH_3NO_2	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.042 \pm 0.093$	0.6943
toluene, C_7H_8	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.0238 \pm 15\%$	1.06
water, H_2O	$(-2\omega; \omega, \omega, 0)$	$C_{11} = 0.0616 \pm 15\%$	1.06

Data in the preceding table are from S. Singh, Nonlinear optical materials, *Handbook of Laser Science and Technology, Vol. III: Optical Materials, Part 1* (CRC Press, Boca Raton, FL, 1986), p. 54 ff. Data for additional liquids are included in this reference.

5.5.5 Stimulated Raman Scattering

Observed SRS Lineshifts ω of Liquids

Substance	ω (cm^{-1})	Ref.
bromoform	222	1
tetrachloroethylene	448	2
carbon tetrachloride ^a	460	3
ethyl iodide	497	4
hexafluorobenzene ^a	515	3
bromoform	539	1
chlorine	552	5
methylene bromide	580	3
trichloroethylene	640	1
carbon disulfide	655	6
ethylene bromide	660	7
chloroform	667	1
α -xylene	730	8
FC104 ^b	757	9
sulfur hexafluoride	775	10
α -dimethylphenethylamine	836	11
dioxane	836	1
morpholine ^a	841	3
thiophenol ^a	916	3
nitromethane ^a	927	3
deuterated benzene	944	12
potassium dihydrogen phosphate	980	13
cumene ^a	990	3
pyridine	991	12
1,3-dibromobenzene	992	2
benzene	992	12
aniline	997	14
styrene	998	15
<i>m</i> -toluidine ^a	999	3
acetophenone	999	16
bromobenzene	1000	14
chlorobenzene ^a	1001	3
<i>tert</i> -butylbenzene	1000	2
benzaldehyde ^a	1001	2
ethylbenzoate	1001	16
benzonitrile	1002	14
ethylbenzene	1002	8
toluene	1004	12

Observed SRS Lineshifts ω of Liquids—continued

Substance	ω (cm ⁻¹)	Ref.
fluorobenzene	1012	17
γ -picoline	1016	3
<i>m</i> -cresol ^a	1029	3
<i>m</i> -dichlorobenzene ^a	1034	3
1-fluoro-2-chlorobenzene ^d	1034	2
1-fluoro-2-chlorobenzene ^d	1034	2
iodo-benzene ^a	1070	3
benzoyl chloride ^a	1086	3
benzaldehyde ^a	1086	3
anisole ^a	1097	3
pyrrole ^a	1178	3
furan ^a	1180	3
nitrous oxide	1289	10
styrene	1315	15
nitrobenzene	1344	12
1-bromonaphthalene	1363	12
1-chloronaphthalene	1374	18
2-ethylnaphthalene	1382	2
<i>m</i> -nitrotoluene ^a	1389	3
carbon dioxide	1392	10
quinoline ^a	1427	3
homocyclohexane	1438	4
furan ^a	1522	3
methyl salicylate ^a	1612	3
cinnamaldehyde	1624	18
styrene	1631	15
3-methylbutadiene	1638	19
pentadiene	1655	19
isoprene	1792	11
1-hexyne	2116	2
dimethyl sulfoxide ^c	2128	20
α -dichlorobenzene ^a	2202	3
benzonitrile	2229	18
acetonitrile	2250	4
1,2-dimethylaniline	2292	3
nitrogen	2327	21
hydrobromic acid	2493	9
hydrochloric acid	2814	9
methylcyclohexane	2817	3
methanol	2831	1
<i>cis trans</i> , 1,3-dimethylcyclohexane	2844	2
tetrahydrofuran	2849	18
cyclohexane	2852	12
<i>cis</i> -1,2-dimethylcyclohexane	2853	2

Observed SRS Lineshifts ω of Liquids—continued

Substance	ω (cm ⁻¹)	Ref.
α -dimethylphenethylamine	2856	11
dioxane	2856	1
decahydronaphthalene	2860	9
cyclohexane	2863	1
cyclohexanone	2863	8
<i>cis, trans</i> -1,3-dimethylcyclohexane	2866	2
cyclohexane	2884	1
dichloromethane ^a	2902	3
dimethyl sulfoxide	2916	20
morpholine	2902	3
cargille 5610 ^f	2908	9
2,3-dimethyl-1,5-hexadiene	2910	2
limonene	2910	11
<i>o</i> -xylene	2913	8
1-hexyne	2916	2
<i>cis</i> -2-heptene	2916	2
2-octene	2918	2
acetonitrile	2920	9
mesitylene	2920	11
2-bromopropane	2920	2
acetone	2921	8
ethanol	2921	1
<i>cis</i> -1,2-dimethylcyclohexane	2921	2
carvone	2922	11
<i>cis, trans</i> -1,3-dimethylcyclohexane	2926	2
2-chloro-2-methylbutane	2927	2
dimethylformamide	2930	1
<i>m</i> -xylene	2933	8
1,2-diethyl tartrate	2933	11
<i>o</i> -xylene	2933	8
piperidine	2933	8
1,2-diethylbenzene	2934	2
1-bromopropane	2935	2
piperidine	2936	8
tetrahydrofuran	2939	18
decahydronaphthalene	2940	9
piperidine	2940	8
cyclohexanone	2945	8
2-nitropropane	2945	2
1,2 diethyl carbonate ^a	2955	3
1,2 dichloroethane ^a	2956	3
<i>trans</i> -dichloroethylene	2956	1
methyl fluoride	2960	10
1-bromopropane	2962	2

Observed SRS Lineshifts ω of Liquids—continued

Substance	ω (cm ⁻¹)	Ref.
2-chloro-2-methylbutane	2962	2
α -dimethylphenethylamine	2967	11
dioxane	2967	1
methyl chloride	2970	10
cyclohexanol ^a	2982	3
cyclopentane ^a	2982	3
cyclopentanol ^a	2982	3
bromocyclopentane ^a	2982	3
<i>o</i> -dichlorobenzene	2982	3
<i>p</i> -chlorotoluene	2982	3
<i>a</i> -picoline ^a	2982	3
<i>p</i> -xylene	2988	8
<i>o</i> -xylene	2992	8
dibutyl-phthalate ^a	2992	3
1, 1, 1-trichloroethane	3018	1
ethylene chlorohydrin ^a	3022	3
isophorone ^a	3022	3
nitrosodimethylamine ^a	3022	3
propylene glycol ^a	3022	3
cyclohexane ^a	3038	3
styrene	3056	15
pyridine	3058	2
benzene	3064	12
<i>tert</i> -butylbenzene	3065	2
1-fluoro-2-chlorobenzene	3082	2
turpentine ^a	3090	3
pseudocumene ^a	3093	3
acetic acid ^a	3162	3
acetonylacetone ^a	3162	3
methyl methacrylate ^a	3162	3
γ -picoline ^a	3182	3
aniline	3300	14
water ^a	3651	3

a Observed at low resolution

b Product of 3M Co., St. Paul, MN

c 1:1 mixture with tetrachloroethylene

d Very weak and diffuse

e Deuterated

f Product of Cargille Laboratories, Cedar Falls, NJ

Table from Milanovich, F. P., Stimulated Raman scattering, *Handbook of Laser Science and Technology, Vol. III: Optical Materials* (CRC Press, Boca Raton, FL, 1986), p. 283.

References:

1. Kern, S. and Feldman, B., *Stimulated Raman Emission*, Vol. 3, Massachusett Institute of Technology, Lincoln Laboratory, Bedford, MA. (1974), p. 18.
2. Barrett, J. J. and Tobin, M. C., Stimulated Raman emission frequencies in 21 organic liquids, *J. Opt. Soc. Am.* 56, 129 (1966).
3. Murtin, M. D. and Thomas, E. L., Infrared difference frequency generation, *IEEE J. Quantum Electron.* QE-2, 196 (1966).
4. El-Sayed, M. A., Johnson, F. M., and Duardo, J., A., Comparative study of the coherent Raman processes using the ruby and the second harmonic neodymium giant-pulsed lasers, *J. Chim. Phys.* 1, 227 (1967).
5. Kaiser, W. and Maier, M., Stimulated Rayleigh, Brillouin and Raman spectroscopy, in *Laser Handbook*, Vol. 2. Arrecchi, F. T. and Schultz-Dubois, E. O., Eds. (North-Holland, Amsterdam, 1972), p. 1078.
6. Giordmaine, J. A. and Howe, J. A., Intensity-induced optical absorption cross section in CS₂, *Phys. Rev. Lett.* 11, 207 (1963).
7. Prasada Rao, T. A. and Seetharaman, N., Amplification of stimulated Raman scattering by a dye. Ind., *J. Pure Appl. Phys.* 13, 207 (1975).
8. Geller, M., Bortfeld, D. P., and Sooy, W. R., New Woodbury-Raman laser materials, *Appl. Phys. Lett.* 3, 36 (1961).
9. Smith, W. L. and Milanovich, F. P., Lawrence Livermore National Laboratory. Livermore. CA, private communication (1973).
10. Maple, J. R. and Knudtson, J. T., Transient stimulated vibrational Raman scattering in small molecule liquids. *Chem. Phys. Lett.* 56, 241 (1978).
11. Wright, J. K., Carmichael, C. H. H., and Brown, B. J., Narrow linewidth output from d Q-switched, Nd³⁺/glass laser. *Phys. Lett.* 16, 264 (1965).
12. Eckhardt, G., Hellwarth, R. W., McClung, F. J., Shwarz, S. E., and Weiner, D., Stimulated Raman scattering from organic liquids, *Phys. Rev. Lett.* 9, 455 (1962).
13. Srivastava, M. K. and Crow, R. W., Raman susceptibility measurements and stimulated Raman effect in KDP, *Opt. Commun.* 8, 82 (1973).
14. Maker, P. D. and Terhune, R. W., Study of optical effects due to an induced polarization third order in the electric field strength, *Phys. Rev.* 137, A801 (1965).
15. Bortfeld, D. P., Geiller, M., and Eckhardt, G., Combination lines in the stimulated Raman spectrum of styrene. *J. Chem. Phys.* 40, 1770 (1964).
16. Orlovich, V. A., Measurement of the coefficient of stimulated Raman scattering in organic liquids with the aid of an amplifier with transverse pumping, *Zh. Prikl. Spektrosk.* 23, 224 (1975).
17. Calvieilo, J. A. and Heller, Z. H., Raman laser action in mixed liquids, *Appl. Phys. Lett.* 5, 112 (1964).
18. Eckhardt, C., Selection of Raman laser materials, *IEEE J. Quantum Electron..* QE-2, 1 (1966).
19. Subov, V. A., Sushchinskii, M. M., and Shuvalton, I. K., Investigation of the excitation threshold of induced Raman scattering, *J. Exp. Theor. Phys. U.S.S.R.* 47, 784 (1964).
20. Decker, C. D., High-efficiency stimulated Raman scattering/dye radiation source, *Appl. Phys. Lett.* 33, 323 (1978).
21. Stoicheff, B. P., Characteristics of stimulated Raman radiation generated by coherent light, *Phys. Lett.* 7, 186 (1963).

5.5.6 Stimulated Brillouin Scattering

Brillouin Gain Parameters for Selected Liquids

Material	Pump wave-length (nm)	Freq- uency shift (GHz)	$\Delta\nu$ (MHz)	τ_B (ns)	g_B (cm/GW)	n	Density (g/cm³)	Ref.
Acetone	1059	2.987	119 ± 5	1.34	15.8	1.355	0.791	1
	532	5.93	361	0.44	12.9	1.359 (Na _D)		2
	532	6.0	320	0.497	20			3
Benzene	1059	4.124	228	0.7	9.6	1.4837	0.879	1
	532	8.33	515	0.31	12.3	1.501 (Na _D)	0.874	2
Benzyl alcohol	532	9.38	2120	0.08	5.75	1.54 (Na-D)	1.045	2
Butyl acetate	532	6.23	575	0.28	9.13	1.394 (Na _D)	0.882	2
CS ₂	1060	3.761	50	3.2	68	1.595	1.262	1
	532	7.7	120	1.9	130			3
CCl ₄	1060	2.772	528	0.3	3.8	1.452	1.595	1
	532	5.72	890	0.18	8.77	1.4595	1.594	2
Chloroform	532	5.75	635	0.25	11.7	1.446 (Na _D)	1.492	2
Cyclohexane	532	7.19	1440	0.11	5.8	1.426 (Na _D)	0.779	2
<i>N,N</i> -Dimethyl formamide	532	7.93	615	0.26	7.8	1.431 (Na _D)	0.944	2
Dichloromethane	532	5.92	255	0.62	16.8	1.424	1.325	2
<i>o</i> -Dichlorobenzene	532	8.03	1340	0.12	4.7	1.551	1.306	2
Ethanol	532	5.91	546	0.29		1.36	0.785	2
Ethylene glycol	532	10.2	3630	0.04	0.85	1.431	1.113	2
Freon 113	532	3.72	81	0.18	5.5	1.3578	1.575	2
<i>n</i> -Hexane	532	5.64	580	0.27	8.8	1.379	0.67	2
Nitrobenzene	1060	4.255	396	0.4	7.2	1.5297	1.206	1
Methanol	532	5.47	325	0.49	10.6	1.329	.791	2
	530	5.6	210	0.334	13			3
Pyridine	532	8.92	746	0.21	14	1.51	0.978	2
Tin tetrachloride	1064	2.21 ± 0.02	182 ± 12	0.874	11.2 ± 0.5	1.36	2.226	4
	532	4.71	357	0.45				2
Titanium tetrachloride	1060	3.070	216	0.735	14.2	1.577	1.73	1
Toluene	532	7.72	1314	0.12	8.4	1.496	0.867	2
Trichloroethylene	532	5.94	765	0.21	12	1.4755	1.464	2
Water	1060	3.703	170	0.935	3.8	1.324	1	1
	532	7.4	607	0.26	2.94	1.333	1	2
Xylenes	532	7.74	1211	0.13	9.3	1.497	0.86	2

References:

1. Erohkin, A. I., Kovalev, V. I., and Faizullov, F. S., Determination of the parameters of a nonlinear response of liquids in an acoustic resonance region by the method of nondegenerate four wave interaction, *Sov. J. Quantum Electron.* 16, 872 (1986).
2. Dyer, M. J., and Bischel, W. K., unpublished data.
3. Narum, P., Skeldon, M. D., and Boyd, R. W., Effect of laser mode structure on stimulated Brillouin scattering, *IEEE J. Quantum Electron.* QE-22, 2161 (1986).
4. Amimoto, S. T., Gross, R. W. F., Garman-DuVall, L., Good, T. W., and Piranian, J. D., Stimulated Brillouin-scattering properties of SnCl₄, *Opt. Lett.* 16, 1382 (1991).

Brillouin Materials Used for Phase Conjugation

Liquids	Temp. (K)	Wave-length λ (nm)	Refract. index	Sound speed v_s (km/s)	Brillouin shift at λ (GHz)	Phonon lifetime τ_p (ns)	Line width $\Delta\nu_b$ (MHz)	Gain g (cm/GW)	Density ρ (g/cm ³)	Ref.
Acetic acid					5.05					1
	295	633			5.64		400			2
Acetone		694		1.40	4.61		235			3
		1064			3.1					4
		1064	1.36	1.19		4	40	18		5
		1064			2.97	1.8	90	12.9		6
		1064			5.93	0.44	361	12.9		7
		532			5.00			12.9		7
	295	633			5.05		260			2
	293	1064	1.355	1.168	2.987	2.67	119 ^a	15.8	0.791	8
		694					180	20		9
		694		1.19	4.600		175	18		11
Acetonitrile		633			5.52		300			2
BCl ₃		1064								6
Benzene		694		1.5			245	18		11
		632		1.50	7.10		340			3
		532			8.33	0.31	515	12.3		7
					7.03		520			2
					7.08					1
		1064	1.5	1.5		3		18		5
	293	1060	1.4837	1.473	4.124	1.40	228 ^a	9.6	0.879	8
	323	1060	1.4648	1.359	3.757	1.07	297			8

Benzene	694		6.470		289 ^a	18	9
Benzyl alcohol	532		9.38	0.08	2120	5.75	7
Butanol	633		5.63		720		2
Butyl acetate	532		6.23	0.28	575	9.13	7
C ₂ Cl ₃ F ₃	532		3.72	0.18	865–880	5.50	7
(Freon 113)	1064	1.36	0.728	1.86	0.72	220	5.5
Carbon disulfide, CS ₂	694		1.25		55	45	11
	694		1.142	5.85		80	1.263
	1064	1.62		3.8	7	23	1.263
	293	1060	1.593	1.250	3.76	6.4	5
	300	1060				4.9	8
		1064				6.7	4
		694				2.1	10
		633		6.45		140	2
	301	633		6.24		132	11
	162	633		9.05		396	11
Carbon tetra- chloride, CCl ₄	694		0.92	4.41		630	1.595
	694	1.46	1.05			430	3
		1.46	1.05		1.3		11
	1064		1.04?	2.9		122	6
	532			5.72	0.18	890	5
	633			4.82		1260	7
							2

Brillouin Materials Used for Phase Conjugation—*continued*

Liquids	Temp. (K)	Wave- length λ (nm)	Refract. index	Sound speed v_s (km/s)	Brillouin shift at λ (GHz)	Phonon lifetime τ_p (ns)	Line width $\Delta\nu_h$ (MHz)	Gain g (cm/GW)	Density ρ (g/cm ³)	Ref.
Carbon tetra- chloride, CCl ₄	293	1.452		1.012	2.772	0.60	528 ^a	3.8	1.595	8
		1060			4.390		650	6		12
								8		9
Chloroform	532				5.75	0.25	635	11.7		7
		633			4.88		840			2
Cyclohexane	532				7.19	0.11	1440	5.8		7
		1.43		1.35		1		7		5
		694			5.550		774 ^b	6.8		9
		694		1.35			670	6.8		11
Dichloromethane, CCl ₂ H ₂	532				5.92	0.62	255	16.8		7
					2.96	2.5	64	16.9		4
Ethanol	532				5.91	0.29	546			7
		633			5.04		600			2
		694			4.550		353 ^b	12 ^c		9
Ethylene glycol	532				10.2	0.04	3630	0.85		7
Germanium tetrachloride, GeCl ₄		1.46						12	1.87	6
Glycerol	298				2.8					11
		245			3.3		382			11

	166		3.7		42		11
Methanol	1064	1.33	1.12	3.7		13	5
	532			5.47	0.49	325	7
	633			4.68		260	2
	694			4.250		250 ^b	9
	694	1.33	1.118			200	13.2
<i>N,N</i> -Dimethyl formamide	532			7.93	0.26	615	7
<i>n</i> -Hexanes	532			5.64	0.27	580	8.80
	1064	1.37	1.11		3.5		7
	694					220	5
	694	1.37	1.113			212	9
	694					212	11
Nitrobenzene	694		1.56			900	4.5
	1064	1.56	1.56	0.8			11
	293	1060	1.530	4.255	0.80	396 ^a	4.5
	313	1060	1.521	4.057	0.77	416	8
<i>o</i> -Dichlorobenzene	532			8.03	0.12	1340	8.70
PCl ₃							8.6
Pyridine	532			8.92	0.21	746	7
	633			7.38			13
	633			7.36		780	2

Brillouin Materials Used for Phase Conjugation—*continued*

Liquids	Temp. (K)	Wave- length λ (nm)	Refract. index	Sound speed v_s (km/s)	Brillouin shift at λ (GHz)	Phonon lifetime τ_p (ns)	Line width $\Delta\nu_b$ (MHz)	Gain g (cm/GW)	Density ρ (g/cm ³)	Ref.
Silicon tetrachloride, SiCl ₄			1.41					10	1.48	
Tin tetrachloride, SnCl ₄	308	1064		0.830	2.21	1.7	182	11.2	11	14
		532			4.71	0.45	357			7
		1064			2.36	1.8	89			7
		1064								6
Titanium tetrachloride, TiCl ₄	293	1064	1.62	1.05	3.2	2	80	14	1.73	5
		532			4.71	0.45	357			7
		1064								15
		1064					2.0		20 ± 4	6
		1060	1.577	1.032	3.070	1.47	216 ^a	14.2	1.73	8
Toluene		694	1.38			480		13		11
		532			7.72	0.12	1314		8.4	7
		633			6.41	1000				2
		1064	1.5	1.4		1.5		10		5
Trichloroethylene		532			5.94	.21	765	12.00		7
Water, H ₂ O		1064	1.33	1.48	3.7					
		1064			3.7	1.1	152		2.94	7
		532			7.4	0.26	607		2.94	7
		633			6.23		440			2

	1064	1.33	1.49	3.4		4.8		5
293	1060	1.324		3.703	1.87 ^a	170 ^a	3.8	0.997
			1.482					8
	694	1.33	1.488			220	4.8	11
	694			5.69		317 ^b	4.8	9
Water, D ₂ O		1.33	1.38	3.46	3.4	47	3.1	1.1
Xylenes		532		7.74	0.13	1211	9.30	
26 Organic liquids	XeCl laser							17
30 Organic liquids		532						18

^aThese authors assume that lifetime = 1/(π × linewidth); ^bThis is the spontaneous scattering linewidth; these authors report different values for the spontaneous and stimulated scattering linewidth; ^cThis is a theoretically calculated, not an experimental, number; ^dDensity in amagats rather than pressure in atmospheres.

Table from Pepper, D. M., Minden, M. L., Bruesselbach, H. W. and Klein, M. B., Nonlinear optical phase conjugation materials, in *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 467.

References:

1. Cummins, H. Z., and Gammon, K. W., *J. Chem Phys.* 44, 2785 (1966).
2. Ratanaphruks, K., Grubbs, W. T., and MacPhail, R. A., CW stimulated Brillouin gain spectroscopy of liquids, *Chem. Phys. Lett.* 182, no. 3–4, 371–8 (2 Aug. 1991).
3. Laubereau, A., Engisch, W., and Kaiser, W., Hypersonic absorption of liquids determined from spontaneous and stimulated Brillouin scattering, *IEEE J. Quantum Electron.* QE-5, 410–415 (1969).
4. Chiao, R. Y., Brillouin scattering and coherent phonon generation, Ph.D. Diss. No. 0753, Massachusetts Institute of Technology, Cambridge, MA (1965).
5. Bespalov, V. I., and Pasmanik, G. A., *Nonlinear Optics and Adaptive Laser Systems* (Nauka, Moscow, U.S.S.R. (1985). Trans. by Translation Division, Foreign Technology Division, Wright Patterson Air Force Base, OH, document FTD-ID(RS)T-0889-86).
6. Bubis, E. L., Vargin, V. V., Konchalina, L. R., and Shilov, A. A., Study of low-absorption media for SBS in the near-IR spectral range, *Opt. Spektrosk. (Opt. Spectrosc.)* 65, 1281–1285 (759–9) (Dec. 1988).
7. Dyer, M. J., and Bischel, W. K., Stimulated Brillouin spectroscopy of liquids, Paper No. CTuN5, Conference on Lasers and Electro-Optics (CLEO), Anaheim, CA, May 10–15 (1992).
8. Erokhin, A. I., Kovalev, V. I., and Faizullov, F. S., Determination of the parameters of a nonlinear response of liquids in an acoustic resonance region by the method of nondegenerate four-wave interaction, *Kvantovaya Elektronika, Moskva (Sov. J. Quantum Electron.)* 13, no.7 (16, no.7), 1328–1335 (872–7) (July 1986).
9. Kaiser, W., and Maier, M., Stimulated Rayleigh, Brillouin and Raman spectroscopy, *Laser Handbook, Vol. 2*, Arecchi, F. T.. and Schulz-Dubois, E. O., Eds. (North-Holland Publishing, Amsterdam, 1972), p. 1115.
10. Pohl, D., and Kaiser, W., Time-resolved investigations of stimulated Brillouin scattering in transparent and absorbing media: determination of phonon lifetimes, *Phys. Rev. B (Solid State)* 1, 31–43 (1 Jan. 1970).
11. MacPhail, R. A., and Grubbs, W. T., Cw stimulated Brillouin gain spectroscopy of liquids, supercooled liquids, and glasses, Quantum Electronic Laser Science Conference (QELS), Anaheim, CA (May 10–15, 1992).
12. Volynkin, V. M., Gratsianov, K. V., Kolesnikov, A. N., Krushilin, Yu I., Lyubimov, V. V., Markosov, S. A., Pankov, V. G., Stepanov, A. I., and Shklyarik, S. V., Reflection by stimulated Brillouin scattering mirrors based on tetrachlorides of group IV elements, *Kvantovaya Elektronika, Moskva (Sov. J. Quantum Electron.)* 12, 2481–2 (1641–1642) (Dec. 1985).
13. Jain, V. K., and Whittenburg, S. L., Rayleigh-Brillouin light scattering studies of neat pyridine, *J. Phys. Chem.*, 92, 2023–2027 (7 April 1988).
14. Amimoto, S. T., Gross, R. W. F., Garman-DuVall, L., Good, T. W., and Piranian, J. D., Stimulated-Brillouin-scattering properties of SnCl₄, *Optics Lett.* 16, 1382–1384 (15 Sept. 1991).
15. Anikeev, I. Yu, Gordeev, A. A., Zubarev, I. G., Mironov, A. B., and Mikhailov, S. I., Gain and lifetime of acoustic phonons under conditions of stimulated Brillouin scattering in titanium tetrachloride, *Kvantovaya Elektronika, Moskva (Sov. J. Quantum Electron.)* 12, no.5 (15, no.5), 1081–3 (712–713) (May 1985).
16. Fleury, P. A., and Chiao, R. Y., *J. Acoust. Soc. Am.* 39, 751 (1966).
17. Eichler, H. J., Konig, R., Menzel, R., Patzold, H., and Schwartz, J., SBS reflection of broad band XeCl excimer laser radiation: comparison of suitable liquids, *J. Phys. D (Appl. Phys.)* 25, 1161–1168, 14 (Aug. 1992).
18. Azzeer, A. M., Masilamani, V., Salhi, M. S., and Al-Dwayyan, A., Phase conjugation by stimulated scattering from organic liquids, *Arab. J. Sci. Eng.* 17, 245–252 (April 1992).

5.6 Magnetooptic Properties

The following tables and figure are from Munin, E., Magnetooptic materials: organic and inorganic liquids, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, 1995), p. 403.

5.6.1 Verdet Constants of Inorganic Liquids

Verdet Constants V of Inorganic Liquids					
Liquid	$\lambda(\text{nm})$	T($^{\circ}\text{C}$)	n	V(rad/T·m)	Ref.
AsCl ₃	589		1.60	12.4	1
COCl ₂	589	3		3.93	1
D ₂ O	578	19.7		3.819	1
	589	19.7		3.656	1
H ₂ O	578	11.5		3.971	1
	589	10		3.811	1
N ₂	589	-195.5		1.21	2
NH ₃	578	-40	1.35	5.47	3
O ₂	589	-182.5		2.27	2
P ^a	589	33	2.07	38.7	1
PBr ₃	578	20	1.70	17.6	1
PCl ₃	578	26	1.511	8.78	1
P ₄ S	589	16		32.0	2
S ^a	589	114	1.93	23.5	1
SO ₂	589	-10	1.39	5.23	2
SbCl ₅	589	16		20.5	2
S ₂ Cl ₂	589	16		12.2	2
SiCl ₄	589	16		5.50	2
SnCl ₄	578	28	1.516	13.0	1
TiBr ₄	578	46		-15.4	5
TiCl ₄	578	17	1.612	-4.80	6

^aFused.

5.6.2 Verdet Constants of Organic Liquids

Verdet Constants V of Organic Liquids (from Ref. 7)				
Formula	Name	$\lambda(\text{nm})$	T($^{\circ}\text{C}$)	V (rad/T m)
CCl ₄	tetrachloromethane	589	25.1	4.65
CHCl ₃	trichloromethane	589	20.0	4.72
CH ₂ Br ₃	tribromomethane	589	17.9	9.10
CH ₂ O ₂	formic acid	589	20.8	3.04
CH ₂ Cl ₂	dichloromethane	589	11.9	4.65
CH ₂ Br ₂	dibromomethane	589	15.9	7.97
CH ₂ I ₂	diiodomethane	589	15.0	4.39
CH ₃ Cl	monochloromethane	589	23	3.99
CH ₃ Br	monobromomethane	589	1.5	5.93
CH ₃ I	monoiodomethane	589	19.5	9.74
CH ₄ O	methyl alcohol	589	18.7	2.79
CH ₃ O ₂ N	mononitromethane	589	9.9	2.40

Verdet Constants V of Organic Liquids (from Ref. 7)—continued

Formula	Name	λ (nm)	T(°C)	V (rad/T m)
C ₂ H ₃ Br	vinylbromide	589	7.8	6.11
C ₂ H ₄ O	ethyleneoxide (1,2-epoxiethane)	589	8.0	2.68
C ₂ H ₄ O	acetaldehyde (ethanal)	589	16.3	2.91
C ₂ H ₄ O ₂	acetic acid	589	21.0	3.04
C ₂ H ₄ O ₂	methylformate	589	16.5	2.79
C ₂ H ₄ Cl ₂	1,1-dichloroethane	589	14.4	4.39
C ₂ H ₄ Cl ₂	1,2-dichloroethane	589	14.4	4.80
C ₂ H ₄ Br ₂	1,2-dibromoethane	589	15.2	7.74
C ₂ H ₅ Cl	monochloroethane	589	5.0	3.96
C ₂ H ₅ Br	monobromoethane	589	19.7	5.29
C ₂ H ₅ I	monoiodoethane	589	18.1	8.58
C ₂ H ₆ O	ethyl alcohol	589	16.8	3.29
C ₂ H ₆ O ₂	glycol (1,2-ethanediol)	589	15.1	3.64
C ₂ H ₆ S	ethylmercaptan	578	16.0	5.38
C ₂ H ₂ O ₂ Cl ₂	dichloroacetic acid	589	13.5	4.42
C ₂ H ₃ O ₂ Cl	chloroacetic acid (cloroethanoic acid)	589	64.5	3.87
C ₂ H ₃ O ₂ Cl ₃	chloralhydrate	589	54.6	4.80
C ₂ H ₅ O ₂ N	mononitroethane	589	10.2	2.75
C ₃ H ₄ O	acrolein (propenal)	578	20.0	5.12
C ₃ H ₄ O ₃	pyruvic acid (2-oxopropanoic acid)	589	14.5	3.52
C ₃ H ₆ O	allyl alcohol	589	18.3	4.65
C ₃ H ₆ O	propyl alcohol (1-propanol)	589	13.6	3.17
C ₃ H ₆ O	acetone (2-propanone)	589	20	3.24
C ₃ H ₆ O ₂	propionic acid (propanoic acid)	589	20.3	3.20
C ₃ H ₆ O ₂	formic acid ethyl ester (ethylmethanoate)	589	18.8	3.05
C ₃ H ₆ O ₂	acetic acid methyl ester (methyl acetate)	589	20.0	3.00
C ₃ H ₇ Cl	propylchloride (1-chloropropane)	589	16.1	3.90
C ₃ H ₇ Cl	isopropylchloride (2-chloropropane)	589	17.2	3.90
C ₃ H ₇ Br	propylbromide (1-bromopropane)	589	19.2	5.21
C ₃ H ₇ Br	isopropylbromide (2-bromopropane)	589	17.1	5.15
C ₃ H ₇ I	propyl iodide (1-iodopropane)	589	18.1	7.82
C ₃ H ₇ I	isopropyl iodide (2-iodopropane)	589	26.3	7.65
C ₃ H ₈ O	<i>n</i> -propyl alcohol (1-propanol)	589	15.6	3.49
C ₃ H ₈ O	isopropyl alcohol (2-propanol)	589	20.0	3.58
C ₃ H ₈ O ₃	glycerine (1,2,3-propanetriol)	589	16.0	3.87
C ₃ H ₉ N	<i>n</i> -propylamine	589	9.6	3.87
C ₃ H ₅ O ₉ N ₃	nitroglycerine	589	13.5	2.62
C ₃ H ₇ O ₂ N	1-nitropropane	589	18.9	2.96
C ₄ H ₆	1,3-butadiene (erythrene)	589	15.0	6.28
C ₄ H ₈	1-butene (α-butylene)	589	15.0	4.04
C ₄ H ₈	<i>cis</i> -2-butene (β-butylene)	589	15.0	4.01
C ₄ H ₈	<i>trans</i> -2-butene	589	15.0	3.75
C ₄ H ₁₀	butane	589	15.0	3.17
C ₄ H ₁₀	isobutane (2-methylpropane)	589	15.0	3.23
C ₄ H ₄ O	furan (furfuran)	589	20.0	5.18
C ₄ H ₄ S	thiophene (thiofuran)	589	20.0	8.23
C ₄ H ₆ O ₃	acetic anhydride (ethanoic anhydride)	589	20.0	3.24

Verdet Constants V of Organic Liquids (from Ref. 7)—continued

Formula	Name	λ (nm)	T(°C)	V (rad/T m)
C ₄ H ₈ O ₂	<i>n</i> -butyric acid (butanoic acid)	589	18.8	3.35
C ₄ H ₈ O ₂	ethyl acetate (ethyl ethanoate)	589	20.0	3.14
C ₄ H ₈ O ₂	propionic acid methyl ester	589	20.0	3.11
C ₄ H ₁₀ O	ethyl ether (ethoxyethane)	589	20.0	3.17
C ₄ H ₁₀ O	<i>n</i> -butyl alcohol (1-butanol)	589	20.0	3.58
C ₄ H ₁₀ O	isobutyl alcohol (2-methyl-1-propanol)	589	17.7	3.69
C ₄ H ₁₀ O	<i>sec</i> -butyl alcohol (methylpropylcarbinol)	589	20.0	3.69
C ₅ H ₆	cyclopentadiene	589	15.0	5.88
C ₅ H ₈	1,3-pentadiene	589	15.0	6.05
C ₅ H ₈	isoprene (2-methyl-1,3-butadiene)	589	15.0	6.05
C ₅ H ₈	cyclopentene	589	15.0	4.42
C ₅ H ₁₀	1-pentene	589	15.0	4.04
C ₅ H ₁₀	isopentane (2-methyl-1-butane)	589	15.0	4.04
C ₅ H ₁₀	cyclopentane	589	20.0	3.58
C ₅ H ₁₂	pentane	589	15.0	3.35
C ₅ H ₁₂	isopentane (2-methylbutane)	589	15.0	3.40
C ₅ H ₄ O ₂	furfural (2-furancarbonal)	578	20.0	5.99
C ₅ H ₅ N	pyridine	589	11.9	7.50
C ₅ H ₁₀ O ₂	propionic acid ethyl ester	589	20.0	3.29
C ₅ H ₁₀ O ₂	acetic acid propylester	589	15.7	3.29
C ₅ H ₁₄ N ₂	cadaverine (1,5-pentanediamine)	589	14.7	4.45
C ₆ H ₆	benzene	589	15.0	8.73
C ₆ H ₁₂	cyclohexane	589	20.0	3.61
C ₆ H ₁₄	hexane	589	15.0	3.49
C ₆ H ₄ Cl ₂	1,4-dichlorobenzene (<i>p</i> -dichlorobenzene)	589	64.5	7.82
C ₆ H ₅ F	fluorobenzene (phenylfluoride)	589	19.0	7.30
C ₆ H ₅ Cl	chlorobenzene (phenylchloride)	589	15.0	8.49
C ₆ H ₅ Br	bromobenzene (phenylbromide)	589	15.0	9.48
C ₆ H ₅ I	iodobenzene (phenyl iodide)	589	15.0	11.8
C ₆ H ₆ O	phenol (hydroxybenzene)	589	39.0	9.34
C ₆ H ₇ N	aniline (aminobenzene)	589	15.0	12.2
C ₆ H ₁₁ Cl	chlorocyclohexane (cyclohexylchloride)	589	13.0	4.25
C ₆ H ₁₂ O ₃	paraldehyde (paraacetaldehyde)	589	17.3	3.46
C ₆ H ₁₄ O	2-hexanol (butylmethylcarbinol)	589	20.0	3.81
C ₆ H ₁₄ O	3-hexanol (ethylpropylcarbinol)	589	20.0	3.78
C ₆ H ₁₄ O	2-methyl-3-pentanol	589	20.0	3.84
C ₆ H ₄ O ₄ N ₂	1,3-dinitrobenzene (<i>m</i> -dinitrobenzene)	589	17.1	6.31
C ₆ H ₅ O ₂ N	nitrobenzene	589	15.0	6.31
C ₇ H ₈	toluene (methylbenzene)	589	15.0	7.88
C ₇ H ₁₄	1-heptene (alpha-heptylene)	589	18.0	4.16
C ₇ H ₁₆	heptane	589	15.0	3.58
C ₇ H ₅ N	benzonitrile (benzenecarbonitrile)	589	15.7	7.97
C ₇ H ₇ Cl	<i>o</i> -chlorotoluene (2-chloro-1-methylbenzene)	589	15.4	8.58
C ₇ H ₇ Cl	<i>p</i> -chlorotoluene (4-chloro-1-methylbenzene)	589	15.2	7.71
C ₇ H ₇ Br	<i>o</i> -bromotoluene (2-bromo-1-methylbenzene)	589	16.7	8.96
C ₇ H ₇ Br	<i>p</i> -bromotoluene (4-bromo-1-methylbenzene)	589	39.0	8.38
C ₇ H ₈ O	<i>o</i> -cresol (<i>o</i> -methylphenol)	589	16.0	8.93

Verdet Constants V of Organic Liquids (from Ref. 7)—continued

Formula	Name	λ (nm)	T(°C)	V (rad/T m)
C ₇ H ₈ O	<i>m</i> -cresol (<i>m</i> -methylphenol)	589	17.9	8.41
C ₇ H ₈ O	<i>p</i> -cresol (<i>p</i> -methylphenol)	589	17.0	8.46
C ₇ H ₉ N	<i>o</i> -toluidine (<i>o</i> -methylaniline)	589	17.3	11.0
C ₇ H ₉ N	<i>m</i> -toluidine (<i>m</i> -methylaniline)	589	15.0	10.4
C ₇ H ₉ N	<i>p</i> -toluidine (<i>p</i> -methylaniline)	589	50.0	9.80
C ₇ H ₁₄ O	enanthaldehyde (heptanal)	589	16.2	3.67
C ₇ H ₁₆ O	1-heptanol (<i>n</i> -heptylalcohol)	589	12.6	3.87
C ₇ H ₁₆ O	2-heptanol (amylmethylcarbinol)	589	20.0	3.84
C ₇ H ₁₆ O	3-heptanol (butylethylcarbinol)	589	20.0	3.99
C ₇ H ₇ O ₂ N	<i>o</i> -nitrotoluene	589	18.0	6.28
C ₇ H ₇ O ₂ N	<i>p</i> -nitrotoluene	589	54.3	5.73
C ₈ H ₁₀	ethylbenzene (phenylethane)	589	15.0	8.14
C ₈ H ₁₀	<i>o</i> -xilene (1,2-dimethylbenzene)	589	15.0	7.62
C ₈ H ₁₀	<i>m</i> -xilene (1,3-dimethylbenzene)	589	15.0	7.18
C ₈ H ₁₀	<i>p</i> -xilene (1,4-dimethylbenzene)	589	15.0	7.16
C ₈ H ₁₆	1-octene (<i>a</i> -octylene)	589	15.0	4.19
C ₈ H ₁₆	2-octene (<i>b</i> -octylene)	589	15.0	4.16
C ₈ H ₁₈	octane	589	15.0	3.67
C ₈ H ₁₈ O	1-octanol (<i>n</i> -octyl alcohol)	589	20.0	3.87
C ₈ H ₁₈ O	2-octanol (methylhexylcarbinol)	589	20.0	3.90
C ₈ H ₁₈ O	3-octanol (ethylamylcarbinol)	589	20.0	3.87
C ₉ H ₁₂	<i>o</i> -ethyltoluene (1-ethyl-2-ethylbenzene)	589	15.0	6.75
C ₉ H ₁₂	<i>m</i> -ethyltoluene (1-ethyl-3-ethylbenzene)	589	15.0	8.46
C ₉ H ₁₂	<i>p</i> -ethylbenzene (1-ethyl-4-ethylbenzene)	589	15.0	6.89
C ₉ H ₁₂	mesitylene (1-3-5-trimethylbenzene)	589	15.0	6.63
C ₉ H ₂₀	nonane	589	15.0	3.72
C ₁₀ H ₈	naphthalene	589	89.5	13.0
C ₁₀ H ₂₀	1-decene (<i>n</i> -decylene)	589	21.0	4.22
C ₁₀ H ₂₂	decane	589	15.0	3.78
C ₁₀ H ₇ Cl	1-chloronaphthalene (<i>α</i> -chloronaphthalene)	578	18.0	14.3
C ₁₀ H ₇ Br	1-bromonaphthalene (<i>α</i> -bromonaphthalene)	578	20.0	15.1
C ₁₀ H ₈ O	<i>b</i> -naphthol (2-hydroxinaphthalene)	578	13.6	14.0
C ₁₀ H ₉ N	1-naphthylamine (<i>α</i> -naphthylamine)	589	32.6	19.9
C ₁₀ H ₁₂ O ₂	isoeugenol (4-propenylguaiacol)	589	19.3	10.33
C ₁₀ H ₁₂ O ₂	eugenol (4-allylguaiacol)	589	15.4	8.38
C ₁₀ H ₁₂ O ₂	benzoic acid propylester (<i>n</i> -propylbenzoate)	589	15.4	6.40
C ₁₀ H ₁₂ O ₂	<i>o</i> -toluic acid ethyl ester	589	15.2	6.54
C ₁₀ H ₁₂ O ₂	<i>p</i> -toluic acid ethyl ester	589	15.0	6.34
C ₁₀ H ₁₂ O ₂	<i>α</i> -toluic acid ethyl ester (ethylphenylacetate)	589	14.0	6.54
C ₁₀ H ₁₂ O ₂	methylsalicylic acid ethylester	589	18.6	7.27
C ₁₀ H ₁₈ O	<i>α</i> -terpineol	589	16.0	4.54
C ₁₀ H ₁₈ O	Citronellal	589	14.5	4.39
C ₁₀ H ₁₈ O ₄	dipropylsuccinate	589	11.4	3.55
C ₁₀ H ₁₀ O ₆	tartaric acid dipropyl ester (propyltartrate)	589	15.4	3.61
C ₁₀ H ₂₀ O	menthol	589	45.2	4.07
C ₁₁ H ₂₄	undecane	589	20.5	3.81
C ₁₂ H ₂₆	dodecane	589	21.5	3.84

Verdet Constants V of Organic Liquids (from Ref. 7)—continued


Formula	Name	λ (nm)	T(°C)	V (rad/T m)
C ₁₄ H ₁₀	phenanthrene	578	100.0	17.0
C ₁₆ H ₃₄	hexadecane	589	15.0	3.93
C ₁₈ H ₁₄	1,2-diphenylbenzene	589	15.0	13.7
C ₁₈ H ₂₂	1,6-diphenylhexane	589	20.0	8.00

5.6.3 Dispersion of the Verdet Constants

Dispersion of the Verdet Constant V in the Near Ultraviolet and Visible

Formula	Name	V(λ)(rad/T·m), λ (nm)						
		347.1	457.9	488.0	514.5	580.0	632.8	694.3
CH ₃ NO ₂	nitromethane		4.07	3.58	3.26	2.60	2.15	1.67
CH ₄ O	methanol	8.46	4.68	4.16	3.69	3.00	2.40	1.88
C ₂ H ₄ O ₂	acetic acid	9.75	5.29	4.65	4.13	3.29	2.71	2.09
C ₂ H ₆ O	ethanol	10.5	5.61	4.95	4.45	3.49	2.90	2.30
C ₃ H ₆ O	acetone	10.5	5.64	4.95	4.45	3.46	2.84	2.79
H ₂ O	water	12.4	6.78	5.85	5.24	4.10	3.35	2.66
CCl ₄	carbon tetrachloride	15.4	8.03	7.04	6.31	4.95	4.04	3.23
C ₆ H ₅ NO ₂	nitrobenzene		10.7	9.60	8.41	6.66	5.41	4.33
C ₇ H ₈	toluene	31.4	14.3	12.2	10.7	8.09	6.60	5.24
C ₆ H ₆	benzene		16.0	13.6	12.1	9.13	7.39	5.93
CS ₂	carbon disulfide		22.2	19.2	16.8	12.9	10.4	8.26

Liquids are listed in increasing order of the Verdet constant.⁸



Dispersion of the Verdet constant for several liquids listed in the table above

Dispersion of the Verdet Constant V in the Near Infrared²

Formula	Name	$\frac{V\lambda}{\lambda} \text{ (rad/T}\cdot\text{m), } \lambda(\mu\text{m)}$				
		0.6	0.8	1.0	1.5	2.0
H ₂ O	water	3.67	2.04	1.28	(0.844 at 1.25 μm)	
SnCl ₄	tin tetrachloride	11.9	6.31	3.93	1.75	0.902
TiCl ₄	titanium tetrachloride	-3.81	-1.45	-0.756	-0.291	-0.145
CCl ₄	carbon tetrachloride	4.68	2.59	1.66	0.727	0.378
CS ₂	carbon disulfide	11.5	6.23	3.93	1.69	0.902
CHCl ₃	chloroform	4.51	2.50	1.63	0.698	0.378
CH ₃ I	methyl iodide	9.25	5.18	3.26	1.40	0.785
CH ₂ I ₂	methylene iodide	13.8	7.80	4.92	2.12	1.16
CH ₄ O	methyl alcohol	2.71	1.48	0.931	0.553	0.378
C ₂ H ₅ I	ethyl iodide	8.12	4.39	2.82	1.19	0.698
C ₂ H ₆ O	ethyl alcohol	3.23	1.75	1.11	0.553	0.291
C ₃ H ₆ O	acetone	3.00	1.77	1.16	0.495	0.262
C ₄ H ₁₀ O	ethyl ether	2.97	1.69	1.05	0.465	0.233
C ₄ H ₁₀ O	n-butyl alcohol	3.49	1.95	1.25	0.524	0.407
C ₆ H ₆	benzene	8.17	4.45	2.76	1.13	0.640
C ₆ H ₅ NO ₂	nitrobenzene	6.08	3.32	2.12	0.902	0.524
C ₇ H ₈	toluene	7.50	3.99	2.53	1.02	0.582
C ₇ H ₁₆	n-heptane	3.46	1.92	1.25	0.524	0.262
C ₈ H ₁₀	xilene	6.75	3.72	2.33	1.02	0.553
C ₁₀ H ₇ Br	α-bromonaphthalene	13.4	7.13	4.42	1.83	1.02

Temperature = 23°C.

References:

1. Mallemann, R. de, *Tables des constantes selectionnées, pouvoir rotatoire magnétique (effet Faraday)* (Hermann & Cie, Paris, 1951).
2. *International Critical Tables of Numerical Data, Physics, Chemistry and Technology* (McGraw Hill, New York, 1929).
3. Mallemann, R. de, and Gabiano, P., Pouvoir rotatoire magnétique de l'azote ammoniacal, *Comptes Rendus* 200, 823 (1935).
4. Mallemann, R. de, and Suhner, F., Rotativités du chlorure de silicium et du cyclohexane vaporisés, *Comptes Rendus* 227, 804 (1948).
5. Fritsch, P., Pouvoir rotatoire magnétique du tétrabromure de titane, *Comptes Rendus* 217, (1943).
6. Mallemann, R. de, and Suhner, F., Pouvoir rotatoire magnétique du chlorure titanique vaporisé, *Comptes Rendus* 227, 546 (1948).
7. *Handbook of Chemistry and Physics*, 72nd edition (CRC Press, Boca Raton, FL, 1991).
8. Villaverde, A. B., and Donatti, D. A., Verdet constant of liquids; measurements with a pulsed magnetic field, *J. Chem. Phys.* 71, 4021 (1979).

5.7 Commercial Optical Liquids

Cargille Refractive Index Liquids are examples of commercially available liquids having a wide range of known property values for optical applications. Specific refractive index and dispersion values are maintained by exacting quality control. These liquids are sold individually or in sets covering certain refractive index ranges at 25°C and 589.3 nm:

Series AAA	1.300–1.395
Series AA	1.400–1.458
Series A	1.460–1.640
Series B	1.642–1.700
Series M	1.705–1.800
Series H	1.81–2.00
Series EH	2.01–2.11
Series FH	2.12–2.21
Series GH	2.22–2.31

Other Cargille liquids are available with special properties of dispersion, transmittance, compatibility, fluorescence, stability, toxicity, etc. for special applications.

Whereas evaporation of a pure substance will not change the index of refraction, liquids that are mixtures of substances with different indices of refraction and different volatilities change refractive index through evaporation.

Typical optical liquids transmit well in the visible, begin to absorb in the near-UV and are characterized by a series of absorption bands from 800 to 1600 nm. Exceptions to this pattern are Cargille Laser Liquids Code 433 and Code 3421 which do not reach a UV cutoff until below 240 nm and which are highly transparent, without peaks and valleys in the IR out to 2500 nm.

The best optical liquids with refractive index above 1.810 are arsenic based, highly toxic, and corrosive (Cargille Refractive Index Liquids Series H, EH, FH, and GH).

Properties of representative Cargille optical immersion and laser liquids are given in the following three tables. For a discussion of the optical, physical, and chemical properties of liquids, see R. Sacher and W. Sacher, Optical liquids, *Handbook of Laser Science and Technology, Suppl. 2, Optical Materials* (CRC Press, Boca Raton, FL, 1995).

Properties of representative Cargille immersion liquids

Representative liquid	1	2	3	4	5	6	7	8	9	10	11	12
Formula code		<u>S1050</u>			<u>5040</u>				<u>40BN</u>		BNDN	
Refractive index range for code (n_D 25°C)		1.400–1.458			1.459–1.570				1.571–1.656		1.657–1.698	
Refractive index @25°C and percent transmittance through 1 cm at representative wavelengths (nm)	290 365 404.7 486.1	1.433 1.418 1.4127 F	1.461 1.444 1.4382 1.4054	1.499 82% 1.478 1.4637	— 0% 1.500 1.4819	— 0% 1.531 1.5086	— 0 % — 1.5625	— 0 % — 1.6036	— 0 % — 1.6437	— 0 % — 1.6832	— 0 % — 1.7174	— 0 % — 1.7408
Calibrated at n_D 25°C ±0.0005	<u>589.3</u> 656.3	D 1.4000 1.4250 1.4580 1.4750 1.5000 1.5350 1.5700 1.6000 1.6300 1.6560 1.6750 <u>1.6980</u>	<u>1.3977</u> C 1.4227 1.4557 1.4722 1.4966 1.5307 1.5648 1.5936 1.6224 1.6473 1.6657 1.6881	100% 100% 100% 100% 100% 100% 100% 100% 100% 100% 100% 100%	100% 100% 100% 100% 100% 100% 100% 100% 100% 100% 100% 100%	100% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99%	99% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99%	99% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99%	99% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99%	99% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99%	98% 96% 96% 96% 96% 96% 96% 96% 96% 96% 96% 96%	96% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99% 99%
Abbe v, $(n_D - 1)/(n_F - n_C)$	52	54	57	49	42	35	31	26	22	20	2019	
Temp. Coeff., dn_D/dt (°C)	-.000412	-.000402	-.000388	-.000393	-.000401	-.000411	-.000421	-.000438	-.000454	-.000468	-.000473	-.000479
Viscosity, cSt, @25°C	10	13	17	22	31	50	82	29	10	4	4 4	
Density g/cm³ @25°C	0.930	0.887	0.831	0.855	0.894	0.948	1.003	1.184	1.359	1.511	1.608	1.722
Thermal exp. cm³/cm³/°C	0.00100 0.0009	0.0008	0.0008	0.0008	0.0008	0.0007	0.0007	0.0006	0.0006	0.0006	0.0006	
Flash point, °C	>138				>138				>113			>93
Pour point, °C	<-7				<-7				<6			<6
Boiling point, °C	>200				>262				>279			>279
Toxicity (request MSDS)	Low				Low				Moderate			Moderate

Representative liquid (cont.)	1	2	3	4	5	6	7	8	9	10	11	12
Compatible (c) and incompatible (i)												
Acrylic	c			c			c		c		c	
Polycarbonate	na			c			i			na		
Polyethylene	c			c			c		c		c	
Polypropylene	c			c			c		c		c	
Polystyrene	c			i			i		i		i	
Latex rubber	i			i			i		i		i	
Neoprene rubber	c			i			i		i		i	
Silicone rubber	i			i (some)			c		c		c	
Aluminum	c			c			c		c		c	
Copper	c			c			i		i		i	
Steel	c			c			c		c		i	
Color stability in sun		Very high			Moderate				Low to moderate			Low
Best solvents		ethyl ether, naphtha, xylene, toluene, heptane, methylene chloride, turpentine						Acetone, ethyl ether, naphtha, xylene, methylene chloride, toluene, heptane, turpentine				

na = not available; MSDS=materials specification data sheet.

Table from Sacher, R. and Sacher, W., Optical Liquids, *Handbook of Laser Science and Technology, Supplement 2:Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 97.

Properties of representative special Cargille optical immersion liquids

Representative liquid	1	2	3	4	5	6	7	8	9	10	11	12			
Formula code	4550*	4501	50350*		1160		50BN*		5095		OHGL*	OHZB			
Refractive index range for code (n_D 25°C)	1.452–1.457	1.452–1.470	1.458–1.475		1.482–1.538		1.459–1.656		1.458–1.580		1.333–1.470	1.333–1.556			
Refractive index @25°C	290	1.489	–	1.518	–	–	–	–	–	–	1.503	–			
and percent transmittance through 1 cm at representative wavelengths (nm)	365	1	1.471	1.500	1.496	1.512	1.535	1.584	1.673	1.715	1.536	1.647	1.488	1.598	
			100%	53%	99%	90%	90%	90%	75%	71%	94%	85%	97%	78%	
			100%	96%	100%	95%	95%	95%	80%	76%	98%	95%	98%	91%	
			100%	100%	100%	99%	99%	99%	93%	92%	100%	100%	100%	97%	
Calibrated at n_D 25°C ± 0.0005	589.3	D	1.4520	1.4700	1.4750	1.4820	1.5000	1.5380	1.6000	1.6300	1.5000	1.5800	1.4700	1.5560	
			100%	100%	100%	100%	100%	100%	99%	99%	100%	100%	100%	99%	
			100%	100%	100%	100%	100%	100%	100%	100%	100%	100%	100%	100%	
			1064.8	1.444	1.460	1.467	1.471	1.487	1.522	1.577	1.604	1.487	1.558	1.461	1.539
				94%	95%	93%	97%	97%	97%	98%	99%	96%	98%	80%	93%
			1300	1.442	1.459	1.466	1.469	1.486	1.520	1.574	1.601	1.485	1.555	1.460	1.537
				88%	85%	87%	92%	93%	94%	94%	95%	92%	95%	58%	60%
			1550	1.442	1.458	1.465	1.468	1.485	1.519	1.573	1.599	1.484	1.554	–	–
				81%	84%	81%	87%	88%	90%	91%	93%	86%	90%	0%	0%
Abbe v, $(n_D - 1)/(n_F - n_C)$	57	43	58	42	38	32	24	22	37	25	58	33			
Temp. Coeff., dn_D/dt (°C)		-0.000394	-0.000488	-0.000360	-0.000348	-0.000349	-0.000350	-0.000446	-0.000458	-0.000398	-0.000416	-0.000377	-0.000330		
Viscosity, cSt @25°C		11	0.4	112	41	41	41	6	5	14	10	679	9		
Density, g/cm³ @25°C		0.816	0.840	0.867	0.969	1.016	1.115	1.322	1.426	0.881	0.981	1.254	2.498		
Thermal Exp., cm³/cm³/°C		0.00080.0010	0.0007	0.0007	0.0007	0.0006	0.0007	0.0007	0.0008	0.0007	0.0008	0.0006			
Flash point, °C		>135	>47	>138	>199			>113		>138		>165	None		
Pour point, °C		<2	<2	<-7	<-45			<6		<-7		<18	<1		
Boiling point, °C		>244	>178	>262	>370			>262		>262		>212	>212		
Toxicity (request MSDS)		None	Moderate	None		Low		Moderate	Moderate		Low	Moderate			

Representative liquid (cont.)	1	2	3	4	5	6	7	8	9	10	11	12
Compatible (c) and incompatible (i)												
Acrylic	c	na	c	c	c	c	c	c	c	c	c	c
Polycarbonate	c	na	c	c	i	c	c	c	c	c	na	
Polyethylene	c	na	c	c	c	c	c	c	c	c	c	c
Polypropylene	c	na	c	c	c	c	c	c	c	c	c	c
Polystyrene	c	na	c	i	i	i	i	i	i	c	c	
Latex rubber	i	na	i	c	i	i	i	c	c	c	c	c
Neoprene rubber	c	na	c	i	i	i	i	c	c	c	c	
Silicone rubber	i (some)	na	i (some)	c	c	c	i (some)	c	c	c	c	
Aluminum	c	na	c	c	c	c	c	c	i	i		
Copper	c	na	c	c	c	c	c	c	i	i		
Steel	c	na	c	c	c	c	c	c	i	i	c	
Color stability in sun	Very high	Moderate	Very high	High	Low to moderate	Moderate	na	Moderate				
Best solvents	Ethyl ether, naphtha, xylene,			Ethanol, acetone, ethyl, ether,			Ethyl ether, naphtha, xylene,			Water, ethanol	Water, ethanol	acetone
	methylene chloride			naphtha, xylene			methylene chloride					
	toluene,			methylene			toluene,					
	heptane, turpentine			chloride, toluene			heptane, turpentine					

*=very low fluorescence 356 nm excitation; na = not available; MSDS = materials specification data sheet.

Table from Sacher, R. and Sacher, W., Optical Liquids, in *Handbook of Laser Science and Technology, Supplement 2:Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 97.

Properties of representative Cargille laser liquids

Representative liquid	1	2	3	4	5	6	7	8	9	10	11	12	
Formula code	433		3421		S1056	5610		5610	1074	1057		5763	
Refractive index range for code (n_D 25°C)	1.295–1.319		1.320–1.400		1.398–1.459	1.460–1.535		1.460–1.535	1.535–1.557	1.558–1.578		1.579–1.630	
Refractive index @25°C and percent transmittance through 1cm at representative wavelengths (nm)	240 34% 365 100% 486.1 100% <u>589.3</u> 100%	1.31 11% 1.301 100% F 1.2970 <u>1.2950</u> 100%	1.33 22% 1.327 100% 1.4041 100% <u>1.3200</u> 100%	1.44 8% 1.414 100% 1.4055 100% <u>1.4000</u> 100%	1.45 0% 1.483 95% 1.4631 100% <u>1.4550</u> 100%	— 0% 1.507 95% 1.4840 100% <u>1.4750</u> 100%	290 42% 365 93% 404.7 h 96% 486.1 F 99%	1.579 34% 1.537 92% 1.5252 95% 1.5102 99%	1.633 0% 1.579 80% 1.5639 97% 1.5457 99%	— 0% 1.608 80% 1.5909 92% 1.5704 99%	— 0% 1.631 15% 1.6139 82% 1.5923 97%	— 0% 1.663 2% 1.6416 70% 1.6163 96%	
Calibrated at n_D 25°C ±0.0002	656.3 100% 1064.8 100% 1300 100% 1550 100% 2500 89%	C 1.2941 1.292 1.316 1.394 1.3977 100% 1.3190 100% 1.3983 100% 1.3977 100% 1.4518 100% 1.4713 100% <u>589.3 D</u> 1.5000 <u>1.5340</u> 1.5570 <u>1.5780</u> 1.6000 1.6300	1.2941 100% 1.292 100% 1.316 100% 1.394 100% 1.392 100% 1.444 96% 1.462 96% 656.3 C 100% 1.4960 100% 1.5295 100% 1.5518 100% 1.5724 100% 1.5937 100%										
Abbe v: (n_D – 1)/(n_F – n_C)	101 100	69	51	40	38	—	35	33	30	29	27	24	
Temp. Coeff., dn_D/dt (°C)	–0.000351	–0.000326	–0.000346	–0.000412	–0.000414	–0.000407		–0.000397	–0.000383	–0.000414	–0.000426	–0.000425	–0.000423
Viscosity, cSt @25°C	3	30	18	10	22	46		125	484	40	177	454	1734
Density, g/cm ³ @25°C	1.896	1.982	1.903	0.933	0.981	1.011		1.049	1.101	1.062	1.092	1.135	1.196
Thermal Exp., cm ³ /cm ³ /°C	0.00120.00010	0.0009	0.0010	0.0009	0.0008		0.0008	0.0007	0.0007	0.0007	0.0006	0.0006	
Flash point, °C	None	None		>121	>121		>121	>121	>121	>221	>243	>243	
Pour point, °C	<–20	<–20		<–70	<–22		<–22	<–22	<–20	<–6	<5		
Boiling point, °C	>174	>215		>149	>149		>149	>149	>288	>288	>476		
Toxicity (request MSDS)	Low	None		Low	None		None	None	None	None	Low		

Representative liquid (cont.)	1	2	3	4	5	6	7	8	9	10	11	12
Compatible (c) and incompatible (i)												
Acrylic	c	c	c	c	c	c	c	c	c	c	c	c
Polycarbonate	na	na	c	c	c	c	c	c	c	c	c	c
Polyethylene	c	c	c	c	c	c	c	c	c	c	c	c
Polypropylene	c	c	c	c	c	c	c	c	c	c	c	c
Polystyrene	c	c	c	c	c	c	c	c	c	c	c	c
Latex Rubber	c	c	c	c	c	c	c	c	c	c	c	c
Neoprene Rubber	c	c	c	c	c	c	c	c	c	c	c	c
Silicone Rubber	c	i (some)	i (some)	i (some)	i (some)	i (some)	c	c	c	c	c	i (some)
Aluminum	c	i	c	c	c	c	c	c	c	c	c	c
Copper	c	c	c	c	c	c	c	c	c	c	c	c
Steel	c	c	c	c	c	c	c	c	c	c	c	c
Color stability in sun	Very high	Very high	Very high	Very high	Very high	Very high	Very high	Very high	Very high	Very high	Very high	Low
Best solvents	Freon TF and other		Ethyl ether,		Acetone, ethyl, ether,			Acetone, ethyl, ether, xylene, methylene				
chloride,		chlorofluorocarbons; also remove with soap and water		naphtha, xylene, methylene Chloride	naphtha, xylene, methylene chloride				toluene, turpentine			

na = not available; MSDS=materials specification data sheet.

Table from Sacher, R. and Sacher, W., Optical Liquids, in *Handbook of Laser Science and Technology, Supplement 2:Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 97.

Section 6: Gases

6.1 Introduction

6.2 Physical Properties of Selected Gases

6.3 Index of Refraction

6.4 Nonlinear Optical Properties

6.5 Magnetooptic Properties

6.6 Atomic Resonance Filters

Section 6

GASES

6.1 Introduction

Gases included in this section:

Hydrogen, H ₂	<u>Noble gases</u>
Deuterium, D ₂	Helium, He
Nitrogen, N ₂	Neon, Ne
Oxygen, O ₂	Argon, Ar
Carbon monoxide, CO	Krypton, Kr
Carbon dioxide, CO ₂	Xenon, Xe
Nitrous oxide, N ₂ O	
Nitric oxide, NO	
Methane, CH ₄	
Ammonia, NH ₃	

Composition of Air

Molecular weights and assumed fractional-volume composition of sea-level dry air:

Gas species	Molecular weight (kg/kmol)	Fractional volume (percent)
N ₂	28.0134	0.78084
O ₂	31.9988	0.209476
Ar	39.948	0.00934
CO ₂	44.00995	0.000314
Ne	20.183	0.00001818
He	4.0026	0.00000524
Kr	83.80	0.00000114
Xe	131.30	0.000000087
CH ₄	16.04303	0.000002
H ₂	2.01594	0.0000005
N ₂ O	44.0129	0.0000005

From the "U.S. Standard Atmosphere, 1976," National Oceanic and Atmospheric Administration, National Aeronautics and Space Administration and the United States Air Force, 1976. The U.S. Standard Atmosphere, 1976, is an idealized, steady-state representation of the earth's atmosphere from the surface to 1000 km, as it is assumed to exist in a period of moderate solar activity. The air is assumed to be dry, and at heights sufficiently below 86 km, the atmosphere is assumed to be homogeneously mixed with a relative-volume composition leading to a mean molecular weight.

Mean Free Path of Gases				
Gas	Pressure 1 mm Hg (293 K)	Pressure 760 mm Hg (273 K)	Gas	Collision frequency (293 K)
Argon	4.73 x 10 ⁻⁵ m	6.30 x 10 ⁻⁸ m	Ammonia	9150 x 10 ⁶
Helium	13.32	17.4	Argon	4000
Hydrogen	8.81	11.1	Carbon monoxide	5100
Krypton	3.63	4.8	Carbon dioxide	6120
Neon	9.4	12.4	Helium	4540
Nitrogen	4.5	5.9	Hydrogen	10060
Oxygen	4.82	6.3	Nitrogen	5070
Xenon	2.62	3.5	Oxygen	4430

6.2 Physical Properties of Selected Gases

Values of all properties in this section are for atmospheric pressure, P = 101.325 kPa.

Physical Properties			
Gas	Specific gravity (kg/m ³)	Molecular mass	Mole fraction solubility* in H ₂ O (×10 ⁵)
<u>Noble gases</u>			
He	0.17846	4.0026	0.6997
Ne	0.90035	20.180	0.8152
Ar	1.7839	39.948	2.519
Kr	3.745	83.80	4.512
Xe	5.8971	131.29	7.890
<u>Other gases</u>			
H ₂	0.08988	2.01588	1.411
D ₂	—	4.0282	1.460
O ₂	1.42897	31.9988	2.293
CO	1.2504	28.0104	1.774
N ₂	1.2506	28.0134	1.183
CO ₂	1.97693	44.0098	6.1.5
CH ₄	0.5547	16.0428	2.552
NO	1.3402	30.0061	3.477
N ₂ O	1.977	44.0129	43.67
NH ₃	0.7710	17.031	—
air	1.205	28.966	—

* Mole fraction solubility is at 298 K.

Physical Properties—*continued*

Gas	Ionization potential (eV)	Permittivity ϵ	Polarizability 10^{-24} cm ³	Dipole moment μ/D	Dielectric strength*
<u>Noble gases</u>					
He	24.5874	1.0000650	—	0	0.15 ¹
Ne	21.5645	1.00013	0.3956	0	0.16, ² 0.25 ¹
Ar	15.7596	1.0005172	1.6411	0	0.18 ²
Kr	13.9996	1.00078	2.4844	0	—
Xe	12.1299	1.00126	4.044	0	—
<u>Other gases</u>					
H ₂	15.4259	1.0002538	0.8042	0	0.50 ^{1,2}
D ₂	15.46	—	0.7954	0	—
O ₂	12.07	1.0004947	1.5812	0	0.92 ²
N ₂	15.581	1.0005480	1.7403	0	1.00
CO	14.014	1.00262	1.95	0.110	1.02, ¹ 1.05 ²
CO ₂	13.723	1.000922	2.911	0	0.82, ² 0.88 ¹
CH ₄	12.71	1.00081	2.593	0	1.00, ¹ 1.13 ²
NO	9.264	1.00060	1.70	0.159	
N ₂ O	12.886	1.00104	3.03	0.161	1.24 ²
NH ₃	10.2	1.00622	2.81	—	—
air	—	1.0005364	—	—	0.97 ³
					3.0 kV/mm ⁴
					~0.5 V/mm ⁵
					1.4 kV/mm ⁶

Values for the permittivity (dielectric constant) and the average electric dipole polarization for ground state molecules are for 293 K.

Debye unit: 1 D = 3.33564 × 10⁻³⁰ C m.

* Relative to nitrogen. The dielectric strength (or breakdown voltage) of a material depends on the specimen thickness, the electrode shape, and the rate of the applied voltage increase. Values are given for standard conditions.

References:

- CRC Handbook of Chemistry and Physics*, 82nd edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001). Gas properties at other temperatures are also given in this reference.
1. Vijh, A. K., *IEEE Trans. EI-12*, 313 (1997).
 2. Brand, K. P., *IEEE Trans. EI-17*, 451 (1982).
 3. Shugg, W. T., *Handbook of Electrical and Electronic Insulating Materials* (Van Nostrand Reinhold, New York, 1986).
 4. *Encyclopedic Dictionary in Physics*, Vedensky, B. A. and Vul, B. M., Eds. (Moscow, 1986).
 5. Kubuki, M., Yoshimoto, R., Yoshizumi, K., Tsuru, S., and Hara, M., *IEEE Trans. DEI-1*, 305 (1994).
 6. Al-Arainy, A. A., Malik, N. H., and Cureshi, M. I., *IEEE Trans. EI-12*, 313 (1997).

Physical Properties—*continued*

Gas	Thermal conductivity $\kappa(\text{W/m K})$	Heat capacity at 288 K $C_p(\text{J/kg K})$	Viscosity at 300 K (μPa)
<i>Noble gases</i>			
He	0.1567*	5192	20.0
Ne	0.0498*	1030	32.1
Ar	0.0179*	519.2	22.9
Kr	0.0095*	247.0	25.6
Xe	0.0055*	158.3	23.2
<i>Other gases</i>			
H ₂	0.1869	14277	9.0
D ₂		7250	12.6
O ₂	0.0263	917	20.8
N ₂	0.0260	1043	17.9
CO	0.0250*	1031	17.8
CO ₂	0.0166	843.2	15.0
CH ₄	0.0341	2226	11.2
NO	0.0259	—	19.2
N ₂ O	0.0174	—	15.0
NH ₃	0.0244	2091	—
air	0.0262	1005	18.6

* Low pressure limiting value. In general values differ by less than 1% at atmosphere pressure.

Reference:

CRC Handbook of Chemistry and Physics, 75th edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 1994). Values of properties at other temperatures are also given in this reference.

Thermal Conductivity at Different Temperatures

Gas	Thermal Conductivity (mW/m K)						
	100 K	200 K	300 K	400 K	500 K	600 K	Ref.
<i>Noble gases</i>							
He*	75.5	119.3	156.7	190.6	222.3	252.4	1
Ne*	22.3	37.6	49.8	60.3	69.9	78.7	1
Ar*	6.2	12.4	17.9	22.6	26.8	30.6	1,2
Kr*	3.3	6.4	9.5	12.3	14.8	17.1	1
Xe*	2.0	3.6	5.5	7.3	8.9	10.4	1

Thermal Conductivity (mW/m K)—continued

Gas	100 K	200 K	300 K	400 K	500 K	600 K	Ref.
<i>Other gases</i>							
H ₂	68.6	131.7	186.9	230.4			3
O ₂	9.3	18.4	26.3	33.7	41.0	48.1	4
CO*			25.0	32.3	39.2	45.7	5
N ₂	9.8	18.7	26.0	32.3	38.3	44.0	6
CO ₂		9.6	16.8	25.1	33.5	41.6	7
CH ₄		22.5	34.1	49.1	66.5	84.1	8,9
NO		17.8	25.9	33.1	39.6	46.2	10
N ₂ O		9.8	17.4	26.0	34.1	41.8	10
air	9.4	18.4	26.2	33.3	39.7	45.7	11

* Low pressure limiting value. In general values differ by less than 1% at atmosphere pressure.

References:

1. Kestin, J. et al., Equilibrium and transport properties of the noble gases and their mixtures at low density, *J. Phys. Chem. Ref. Data* 13, 299 (1984).
2. Younglove, B. A. and Hanley, H. J. M., The viscosity and thermal conductivity of coefficients of gaseous and liquid argon, *J. Phys. Chem. Ref. Data* 15, 1323 (1986).
3. Assael, M. J., Mixafendi, S., and Wakeham, W. A., The viscosity of normal hydrogen in the limit of zero density, *J. Phys. Chem. Ref. Data* 15, 1315 (1986).
4. Younglove, B. A., Thermophysical properties of fluids. I. Argon, ethylene, parahydrogen, nitrogen, nitrogen trifluoride, and oxygen, *J. Phys. Chem. Ref. Data* 11, Suppl. 1 (1982).
5. Millat, J. and Wakeham, W. A., The thermal conductivity of nitrogen and carbon monoxide in the limit of zero density, *J. Phys. Chem. Ref. Data* 18, 565 (1989).
6. Stephen, K., Krauss, R., and Laesec, A., Viscosity and thermal conductivity of nitrogen for a wide range of fluid states, *J. Phys. Chem. Ref. Data* 16, 993 (1987).
7. Vescovic, V. et al., The transport properties of carbon dioxide, *J. Phys. Chem. Ref. Data* 19 (1990).
8. Younglove, B. A. and Ely, J. F., Thermophysical properties of fluids. II. Methane, ethane, propane, isobutane, and normal butane, *J. Phys. Chem. Ref. Data* 16, 577 (1987).
9. Friend, D. G., Ely, J. F., and Ingham, H., Thermophysical properties of methane, *J. Phys. Chem. Ref. Data* 18, 583 (1989).
10. Ho, C. Y., Ed., *Properties of Inorganic Fluids, CINDAS Data Series on Materials Properties*, Vol. V-1 (Hemisphere Publishing Corp., New York, 1988).
11. Kadoya, K., Matsunagz, N., and Nagashima, A., Viscosity and thermal conductivity of dry air in the gaseous phase, *J. Phys. Chem. Ref. Data* 14, 947 (1985).

Viscosity

Viscosity in micropascal seconds ($\mu\text{Pa s}$)							
Gas	100 K	200 K	300 K	400 K	500 K	600 K	Ref.
<u>Noble gases</u>							
He*	9.7	15.3	20.0	24.4	28.4	32.3	1
Ne*	14.4	24.3	32.1	38.9	45.0	50.8	1
Ar*	8.0	15.9	22.9	28.8	34.2	39.0	1,2
Kr*	8.8	17.1	25.6	33.1	39.8	45.9	1
Xe*	8.3	15.4	23.2	30.7	37.6	44.0	1
<u>Other gases</u>							
H ₂ *	4.2	6.8	9.0	10.9	12.7	14.4	3
D ₂ *	5.9	9.6	12.6	15.4	17.9	20.3	4
O ₂ *	7.5	14.6	20.8	26.1	30.8	35.1	5
CO	6.7	12.9	17.8	22.1	25.8	29.1	6
N ₂ *		12.9	17.9	22.2	26.1	29.6	5
CO ₂		10.0	15.0	19.7	24.0	28.0	7,8
CH ₄		7.7	11.2	14.3	17.0	19.4	8
NO		13.8	19.2	23.8	28.0	31.9	6
N ₂ O		10.0	15.0	19.4	23.6	27.4	6
air		13.3	18.6	23.1	27.1	30.8	9

* Low pressure limiting value. In general values differ by less than 1% at atmosphere pressure.

References:

1. Kestin, J. et al., Equilibrium and transport properties of the noble gases and their mixtures at low density, *J. Phys. Chem. Ref. Data* 13, 299 (1984).
2. Younglove, B. A. and Hanley, H. J. M., The viscosity and thermal conductivity of normal hydrogen in the limit of zero density, *J. Phys. Chem. Ref. Data* 15, 1323 (1986).
3. Assael, M. J., Mixafendi, S., and Wakeham, W. A., The viscosity of normal hydrogen in the limit of zero density, *J. Phys. Chem. Ref. Data* 15, 1315 (1986).
4. Assael, M. J., Mixafendi, S., and Wakeham, W. A., The viscosity of normal deuterium in the limit of zero density, *J. Phys. Chem. Ref. Data* 16, 189 (1987).
5. Cole, W. A. and Wakeham, W. A., The viscosity of nitrogen, oxygen, and their binary mixtures in the limit of zero density, *J. Phys. Chem. Ref. Data* 14, 209 (1985).
6. Ho, C. Y., Ed., *Properties of Inorganic Fluids, CINDAS Data Series on Materials Properties*, Vol. V-1 (Hemisphere Publishing Corp., New York, 1988).
7. Vescovic, V. et al., The transport properties of carbon dioxide, *J. Phys. Chem. Ref. Data* 19 (1990).
8. Trengove, R. D. and Wakeham, W. A., The viscosity of carbon dioxide, methane, and sulfur hexafluoride in the limit of zero density, *J. Phys. Chem. Ref. Data* 16, 175 (1987).
9. Kadoya, K., Matsunaga, N., and Nagashima, A., Viscosity and thermal conductivity of dry air in the gaseous phase, *J. Phys. Chem. Ref. Data* 14, 947 (1985).

6.3 Index of Refraction

Index of Refraction n of Helium, He

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
0.092		1.0000485	1
0.1000		1.0000453	1
0.1100		1.0000426	1
0.1200		1.0000407	1
0.1300		1.0000396	1
0.1400		1.0000389	1
0.1500		1.0000383	1
0.1600		1.0000378	1
0.1700		1.0000374	1
0.1800		1.0000373	1
0.1820		1.00003720	3
0.184949		1.00003718	3
0.194232		1.00003690	3
0.213923		1.00003634	3
0.228872		1.00003601	3
0.253728		1.00003549	3
	0.275278	1.00003573	3,4
	0.289360	1.00003562	3,4
	0.292541	1.00003559	3,4
	0.296728	1.00003557	3,4
	0.302150	1.00003553	3,4
	0.312566	1.00003547	3,4
	0.334148	1.00003536	3,4
	0.366328	1.00003523	3,4
	0.390641	1.00003516	3,4
	0.404656	1.00003512	3,4
	0.435835	1.00003505	3,4
	0.479992	1.00003498	5
	0.508582	1.00003494	5
	0.521007	1.00003493	3
0.546226	0.546074	1.00003490	3
0.577120	0.576959	1.00003486	3
0.579227	0.579065	1.00003486	3
0.644025	0.643847	1.00003481	3
	0.742511	1.00003477	5
	0.826452	1.00003474	5
	0.912296	1.00003472	5
	1.013979	1.00003470	5

Index of Refraction n of Helium, He—continued

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
	1.371857	1.00003466	5
	1.529596	1.00003465	5
	2.058128	1.00003464	5

References:

1. Huber, M. C. E. and Tondello, G., Refractive index of He in the region 920 AA, *J. Opt. Soc. Am.* 64, 390 (1974).
2. Abjean, R., Mehu, A., and Johannin-Gilles, A., *Comptes Rendus* 271, 835 (1970).
3. Leonard, P. J., *Atomic Data and Nuclear Data Tables* 14, 21 (1974).
4. Cuthbertson, C. and Cuthbertson, M., *Proc. Roy. Soc. A* 135, 40 (1932).
5. Mansfield, C. R. and Peck, E. R., Dispersion of helium, *J. Opt. Soc. Am.* 59, 199 (1969).

Dispersion formula [λ (μm) in vacuum at $T = 273$ K]	Range (μm)
$n = 1 + 0.01470091\lambda^2/423.98\lambda^2 - 1$	0.48–2.06

Reference: Mansfield, C. R. and Peck, E. R., Dispersion of helium, *J. Opt. Soc. Am.* 59, 199 (1969).

Index of Refraction n of Neon, Ne

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
0.1404		1.00007736	1
0.1525		1.00007520	1
0.1641		1.00007317	1
0.1702		1.00007280	1
0.180731		1.00007221	1
0.184949		1.00007190	1
0.194232		1.00007095	1
0.213923		1.00007017	1
0.228872		1.00006941	1
0.253728		1.00006872	1
	0.289360	1.00006860	2,3
	0.296728	1.00006850	2,3
	0.302150	1.00006843	2,3
	0.313183	1.00006831	2,3
	0.334148	1.00006812	2,3
	0.366328	1.00006788	2,3
	0.390641	1.00006773	2,3
	0.404656	1.00006766	2,3
	0.407781	1.00006765	2,3
	0.435835	1.00006753	2,3
	0.479992	1.00006739	2

Index of Refraction n of Neon, Ne—continued

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
	0.491604	1.00006736	2,3
	0.508582	1.00006731	2
	0.521007	1.00006729	2
0.546226	0.546074	1.00006724	2
0.577120	0.576959	1.00006718	2
0.579227	0.579065	1.00006718	2
0.644025	0.643847	1.00006711	2

References:

1. Bideau-Mehu, A., Guern, R., Abjean, Y., and Johannin-Gilles, A., Measurement of refractive indexes of He, Ar, Kr, and Xe in the 253.7–140.4 nm wavelength range. Dispersion relation and estimated oscillator strength of the resonance lines, *J. Quant. Spectrosc. Radiat. Transfer* 25, 395 (1981).
2. Leonard, P. J., *Atomic Data and Nuclear Data Tables* 14, 21 (1974).
3. Cuthbertson, C. and Cuthbertson, M., *Proc. Roy. Soc. A* 135, 40 (1932).

Dispersion formula [λ (μm) in vacuum at T = 273 K]	Range (μm)
$n = 1 + 0.012055[0.1063\lambda^2/(184.661\lambda^2 - 1) + 182.90\lambda^2/(376.840\lambda^2 - 1)]$	0.14–0.66

Reference: Bideau-Mehu, A., Guern, R. Abjean, Y., and Johannin-Gilles, A., Measurement of refractive indexes of He, Ar, Kr, and Xe in the 253.7–140.4 nm wavelength range. Dispersion relation and estimated oscillator strength of the resonance lines, *J. Quant. Spectrosc. Radiat. Transfer* 25, 395 (1981).

Index of Refraction n of Argon, Ar (vacuum ultraviolet)

$\lambda_{\text{vac}}(\mu\text{m})$	n (273 K)	Ref.	$\lambda_{\text{vac}}(\mu\text{m})$	n (273 K)	Ref.
0.1110	1.0008025	1	0.1700	1.0003451	1
0.1140	1.0006435	1	0.1702	1.0003446	2
0.1160	1.0005878	1	0.1805	1.0003352	1
0.1180	1.0005492	1	0.180731	1.0003352	2
0.1200	1.0005200	1	0.184949	1.0003315	2
0.1210	1.0005080	1	0.1850	1.0003318	1
0.1216	1.0005016	1	0.1900	1.0003281	1
0.1250	1.0004707	1	0.194232	1.0003256	2
0.1300	1.0004394	1	0.2000	1.0003220	1
0.1350	1.0004166	1	0.2100	1.0003169	1
0.1400	1.0003966	1	0.213923	1.0003150	2
0.1404	1.0003964	2	0.2200	1.0003127	1
0.1500	1.0003749	1	0.228872	1.0003102	2
0.1525	1.0003685	2	0.2300	1.0003091	1
0.1600	1.0003577	1	0.253728	1.0003029	2
0.1641	1.0003514	2			

**Index of Refraction Index n of Argon, Ar
(ultraviolet, visible, and near infrared)**

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
	0.230209	1.00030922	3
	0.234555	1.00030786	3
	0.237999	1.00030689	3
	0.244691	1.00030507	3
	0.246407	1.00030463	3
	0.257630	1.00030202	3
	0.267499	1.00030002	3
	0.275278	1.00029865	3
	0.275971	1.00029852	3
	0.289357	1.00029643	3
	0.292541	1.00029599	3
	0.334148	1.00029135	3
	0.380166	1.00028806	3
	0.410807	1.00028285	3
0.467947	0.467816	1.00028434	3,4
0.480126	0.479992	1.00028399	3
		1.00028398	3,4
	0.491604	1.00028368	3
0.508724	0.508582	1.00028325	3,4
		1.00028322	3
	0.521007	1.00028296	3
0.546226	0.546074	1.00028247	3
	0.567717	1.00028209	3
0.577120	0.576959	1.00028190	3
0.579227	0.579065	1.00028190	3
0.644025	0.643847	1.00028103	3
0.703435	0.703241	1.00028045	3,4
0.724716	0.724511	1.00028028	3,4
0.826679	0.826452	1.00027962	3,4
0.912547	0.912296	1.00027923	3,4
0.922703	0.922449	1.00027920	3,4
0.966043	0.965778	1.00027904	3,4
1.014257	1.013979	1.00027890	3,4
1.372233	1.371857	1.00027825	3,4
1.475650	1.475246	1.00027814	3,4
1.529354	1.528936	1.00027810	3,4
1.530015	1.529596	1.00027809	3,4
1.694521	1.694057	1.00027798	3,4
2.058691	2.058128	1.00027782	3,4

References:

1. Chashchina, G. I., Gladushchak, V. I., and Shreider, E. Ya., *Opt. Spektrosk.* 24, 1008-1010 (1968) English transl.: *Opt. Spectrosc. USSR* 24, 542 (1968).
2. Bideau-Mehu, A., Guern, R., Abjean, Y., and Johannin-Gilles, A., *J. Quant. Spectrosc. Radiat. Transfer* 25, 395 (1981).
3. Leonard, P. J., *Atomic Data and Nuclear Data Tables* 14, 21 (1974).
4. Peck, E. R. and Fisher, D. J., *J. Opt. Soc. Am.* 54, 1362 (1964).

Temperature variation of the index of refraction of argon at 293 K.

$$dn/dT (K^{-1}) = -0.897 \times 10^{-6} \text{ at } 546.1 \text{ nm}$$

$$dn/dT (K^{-1}) = -0.894 \times 10^{-6} \text{ at } 632.8 \text{ nm}$$

Dispersion formula [λ in vacuum (μm) at T = 273 K]	Range (μm)	Ref.
$n = 1 + 0.012055[0.2075\lambda^2/(91.012\lambda^2 - 1) + 0.0415\lambda^2/(87.892\lambda^2 - 1) + 4.3330\lambda^2/(214.02\lambda^2 - 1)]$	0.14–2.1	1
$n = 1 + [67.86711 + 30182.943\lambda^2/(144\lambda^2 - 1)] \times 10^{-6}$	0.47–2.06	2

References:

1. Bideau-Mehu, A., Guern, R., Abjean, Y., and Johannin-Gilles, A., Measurement of refractive indexes of He, Ar, Kr, and Xe in the 253.7–140.4 nm wavelength range. Dispersion relation and estimated oscillator strength of the resonance lines, *J. Quant. Spectrosc. Radiat. Transfer* 25, 395 (1981).
2. Peck, E. R. and Fisher, D. J., *J. Opt. Soc. Am.* 54, 1362–1364 (1964).

Index of Refraction n of Krypton, Kr

λ _{vac} (μm)	λ _{air} (μm)	n (273 K)	Ref.
0.1404		1.0007723	1
0.1525		1.0006548	1
0.1641		1.0005973	1
0.16846		1.0005829	2
0.16991		1.0005780	2
0.17015		1.0005773	2
0.1702		1.0005801	1
0.17044		1.0005767	2
0.17134		1.0005740	2
0.17224		1.0005718	2
0.18169		1.0005483	2
0.18365		1.0005442	2
0.1844		1.0005433	1
0.18455		1.0005425	2
0.18475		1.0005423	2
0.18507		1.0005416	2

Index of Refraction n of Krypton, Kr—continued

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
0.19013		1.0005326	2
0.19832		1.0005197	2
0.19889		1.0005191	2
	0.202551	1.00051493	3,4
0.20588		1.0005101	2
0.2062		1.0005108	1
0.21248		1.0005028	2
0.213923		1.0005023	1
	0.214438	1.00050126	3,4
	0.219463	1.00049664	3,4
0.22116		1.0004950	2
0.22174		1.0004946	2
	0.226502	1.00049089	3,4
0.228872		1.0004890	1
	0.230209	1.00048845	3,5
	0.232928	1.00048617	3,4
	0.234555	1.00048542	3,5
	0.237999	1.00048318	3,5
0.24359		1.0004791	2
	0.244691	1.00047910	3,5
	0.246407	1.00047815	3,5
0.25073		1.0004751	2
0.25151		1.0004747	2
0.25169		1.0004746	2
0.25200		1.0004745	2
0.25249		1.0004742	2
0.25293		1.0004740	2
	0.257309	1.00047221	3,4
	0.257630	1.00047236	3,5
0.26321		1.0004691	2
	0.267499	1.00046804	3,5
	0.274858	1.00046489	3,4
	0.275278	1.00046499	3,5
	0.275971	1.00046471	3,5
	0.283691	1.00046181	3,4
	0.285697	1.00046138	3,5
0.28824		1.0004601	2
	0.289360	1.00046017	3,5
	0.292541	1.00045924	3,5
	0.298063	1.00045739	3,4
	0.334148	1.00044933	3,5

Index of Refraction n of Krypton, Kr—continued

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
0.480126	0.340365	1.00044829	3,4
	0.380166	1.00044241	3,5
	0.410807	1.00043909	3,5
	0.441304	1.00043621	3,4
	0.479992	1.00043391	3,4
	0.491604	1.00043333	3,5
	0.508724	1.00043245	3,4
	0.546226	1.00043084	3
	0.567717	1.00043011	3,5
	0.607262	1.00042885	3,5
	0.612327	1.00042873	3,5
	0.623437	1.00042847	3,5

References:

1. Bideau-Mehu, A., Guern, R., Abjean, Y., and Johannin-Gilles, Measurement of refractive indexes of He, Ar, Kr, and Xe in the 253.7–140.4 nm wavelength range. Dispersion relation and estimated oscillator strength of the resonance lines, *J. Quant. Spectrosc. Radiat. Transfer* 25, 395 (1981).
2. Smith, P. L., Parkinson, W. H., and Huber, M. C. E., The refractive index of krypton for 168 nm to 288 nm, *Opt. Commun.* 14, 374 (1975).
3. Leonard, P. J., *Atomic Data and Nuclear Data Tables* 14, 21-37 (1974)..
4. Kronjager, W., *Z. Physik* 98, 17 (1936).
5. Koch, J., *Kungl. Fysiografiska Sällskapets i Lund Förfhandlingar* 19, 173 (1949).

Dispersion formula [λ (μm) in vacuum at T = 273 K]	Range (μm)
$n = 1 + 0.012055[0.2104\lambda^2/(65.4742\lambda^2 - 1) + 0.2270\lambda^2/(73.698\lambda^2 - 1) + 5.14975\lambda^2/(181.08\lambda^2 - 1)]$	0.15–0.62

Reference: See reference 1 above.

Index of Refraction n of Xenon, Xe

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
0.1483		1.005091	1
0.1495		1.003210	1
0.1525		1.0020686	1
0.1550		1.0018107	2
0.1600		1.0014614	2
0.1641		1.0013192	1
0.1650		1.0012978	2
0.1700		1.0011934	2
0.1702		1.0011867	1
0.1750		1.0011213	2
0.1800		1.0010678	2
0.180731		1.0010630	1

Index of Refraction n of Xenon, Xe—continued

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
0.184949		1.0010302	1
0.1850		1.0010226	2
0.1900		1.0009917	2
0.194232		1.0009713	1
0.1950		1.0009635	2
0.2000		1.0009398	2
0.2050		1.0009194	2
0.2100		1.0009018	2
0.213923		1.0008941	1
0.2150		1.0008862	2
0.2200		1.0008725	2
0.2250		1.0008603	2
0.228872		1.0008584	1
0.2300		1.0008494	2
	0.230209	1.00085519	3,4
	0.234555	1.00084664	3,4
	0.237999	1.00084025	3,4
	0.244691	1.00082907	3,4
	0.246407	1.00082640	3,4
0.253728		1.0008127	1
	0.257630	1.00081078	3,4
	0.267499	1.00079923	3,4
	0.275278	1.00079124	3,4
	0.275971	1.00079060	3,4
	0.285697	1.00078186	3,4
	0.289360	1.00077885	3,4
	0.292541	1.00077637	3,4
	0.334148	1.00075143	3,4
	0.380166	1.00073430	3,4
	0.410807	1.00072623	3,4
	0.491604	1.00071241	3,4
0.546226	0.546074	1.00070660	3
	0.567717	1.00070477	3,4
	0.607262	1.00070188	3,4
	0.612327	1.00070157	3,4
	0.623437	1.00070091	3,4

-
1. Bideau-Mehu, A., Guern, R., Abjean, Y., and Johannin-Gilles, A., *J. Quant. Spectrosc. Radiat. Transfer* 25, 395 (1981).
 2. Chashchina, G. I. and Shreider, E. Ya., *Opt. Spektrosk.* 27, 161 (1969) English transl.: *Opt. Spectrosc. USSR* 27, 79-80 (1969).
 3. Leonard, P. J., *Atomic Data and Nuclear Data Tables* 14, 21-37 (1974).
 4. Kronjager, W., *Z. Physik* 98, 17 (1936).

Dispersion formula [λ (μm) in vacuum at $T = 273$ K]	Range (μm)
$n = 1 + 0.012055[0.26783\lambda^2/(46.301\lambda^2 - 1) + 0.29481\lambda^2/(50.578\lambda^2 - 1) + 5.0333\lambda^2/(112.74\lambda^2 - 1)]$	0.15–0.62

Reference: Bideau-Mehu, A., Guern, R., Abjean, Y., and Johannin-Gilles, A., Measurement of refractive indexes of He, Ar, Kr, and Xe in the 253.7–140.4 nm wavelength range. Dispersion relation and estimated oscillator strength of the resonance lines, *J. Quant. Spectrosc. Radiat. Transfer* 25, 395 (1981).

Index of Refraction n of Hydrogen, H₂

$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)
0.230209	1.0001594	0.334148	1.0001461
0.237832	1.0001577	0.354308	1.0001450
0.244691	1.0001563	0.366328	1.0001443
0.246406	1.0001560	0.390641	1.0001432
0.253652	1.0001547	0.398400	1.0001430
0.257630	1.0001540	0.404656	1.0001427
0.267499	1.0001525	0.407781	1.0001426
0.275278	1.0001515	0.410807	1.0001426
0.275971	1.0001514	0.435835	1.0001418
0.285697	1.0001503	0.486133	1.0001406
0.289360	1.0001499	0.491604	1.0001405
0.292541	1.0001495	0.546074	1.0001397
0.296728	1.0001491	0.579065	1.0001393
0.312567	1.0001477	0.656279	1.0001387
0.313184	1.0001477	0.670784	1.0001385

Reference: Leonard, P. J., *Atomic Data and Nuclear Data Tables* 14, 21 (1974)

Index of Refraction n of Deuterium, D₂

$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)
0.230209	1.00015680	0.289357	1.00014756
0.234555	1.00015584	0.292541	1.00014725
0.237999	1.00015510	0.334148	1.00014395
0.244691	1.00015378	0.380166	1.00014160
0.246407	1.00015347	0.410807	1.00014048
0.257630	1.00015158	0.491604	1.00013850
0.267499	1.00015014	0.546074	1.00013766
0.275278	1.00014915	0.576959	1.00013731
0.275971	1.00014906	0.579065	1.00013727

Reference: Leonard, P. J., *Atomic Data and Nuclear Data Tables* 14, 21-37 (1974)

**Index of Refraction n of Nitrogen, N₂
(vacuum ultraviolet, ultraviolet, and visible)**

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
0.1641		1.0003748	1
0.1702		1.0003656	1
0.180731		1.0003552	2
0.184949		1.0003495	2
0.194232		1.0003435	2
0.213923		1.0003349	2
0.228872		1.0003299	2
	0.237832	1.0003261	3
	0.244691	1.0003241	3
	0.246406	1.0003236	3
	0.253652	1.0003218	3
0.253728		1.0003217	2
	0.257630	1.0003208	3
	0.267499	1.0003187	3
	0.275278	1.0003172	3
	0.275971	1.0003171	3
	0.285697	1.0003154	3
	0.289360	1.0003148	3
	0.292541	1.0003143	3
	0.296728	1.0003137	3
	0.334148	1.0003094	3
	0.354308	1.0003076	3
	0.390641	1.0003051	3
	0.398400	1.0003047	3
	0.407781	1.0003042	3
	0.410807	1.0003041	3
	0.491604	1.0003011	3
	0.546074	1.0002977	3
0.546226		1.0002911	4

References:

1. Bideau-Mehu, A., Guern, Y., Abjean, R., and Johannin-Gilles, A., Measurement of refractive indexes of gases in the vacuum ultraviolet and revised values for krypton, *Opt. Commun.* 16, 186 (1976).
2. Abjean, R., Mehu, A., and Johannin-Gilles, A., Interferometric measurement of the refractive indices of neon and helium in the ultraviolet, *Comptes Rendus* 271, 411-414 (1970).
3. Leonard, P. J., *Atomic Data and Nuclear Data Tables* 14, 21-37 (1974).
4. Peck, E. R. and Hanna, B. N., *J. Opt. Soc. Am.* 56, 1059-1063 (1966).

**Index of Refraction n of Nitrogen, N₂
(vacuum ultraviolet, ultraviolet, and visible)**

$\lambda_{\text{vac}}(\mu\text{m})$	$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Ref.
0.1641		1.0003748	1
0.1702		1.0003656	1
0.180731		1.0003552	2
0.184949		1.0003495	2
0.194232		1.0003435	2
0.213923		1.0003349	2
0.228872		1.0003299	2
	0.237832	1.0003261	3
	0.244691	1.0003241	3
	0.246406	1.0003236	3
	0.253652	1.0003218	3
0.253728		1.0003217	2
	0.257630	1.0003208	3
	0.267499	1.0003187	3
	0.275278	1.0003172	3
	0.275971	1.0003171	3
	0.285697	1.0003154	3
	0.289360	1.0003148	3
	0.292541	1.0003143	3
	0.296728	1.0003137	3
	0.334148	1.0003094	3
	0.354308	1.0003076	3
	0.390641	1.0003051	3
	0.398400	1.0003047	3
	0.407781	1.0003042	3
	0.410807	1.0003041	3
	0.491604	1.0003011	3
	0.546074	1.0002977	3
0.546226		1.0002911	4

References:

1. Bideau-Mehu, A., Guern, Y., Abjean, R., and Johannin-Gilles, A., Measurement of refractive indexes of gases in the vacuum ultraviolet and revised values for krypton, *Opt. Commun.* 16, 186 (1976).
2. Abjean, R., Mehu, A., and Johannin-Gilles, A., Interferometric measurement of the refractive indices of neon and helium in the ultraviolet, *Comptes Rendus* 271, 411 (1970).
3. Leonard, P. J., *Atomic Data and Nuclear Data Tables* 14, 21 (1974).
4. Peck, E. R. and Hanna, B. N., *J. Opt. Soc. Am.* 56, 1059 (1966).

**Index of Refraction n of Nitrogen, N₂
(visible and near infrared)**

$\lambda_{\text{vac}}(\mu\text{m})$	n (288 K)	$\lambda_{\text{vac}}(\mu\text{m})$	n (288 K)
0.467947	1.00028543	0.978719	1.00028000
0.480126	1.00028507	1.014257	1.00027989
0.508724	1.00028433	1.129050	1.00027961
0.546226	1.00028352	1.350788	1.00027926
0.703435	1.00028149	1.372233	1.00027923
0.724716	1.00028130	1.475650	1.00027912
0.826679	1.00028063	1.529354	1.00027907
0.912547	1.00028023	1.694521	1.00027896
0.922703	1.00028019	2.058691	1.00027879
0.966043	1.00028004		

Reference: Peck, E. R. and Hanna, B. N., *J. Opt. Soc. Am.* 56, 1059 (1966).

Temperature variation of index of refraction at 293 K:

$$dn/dT (\text{K}^{-1}) = -0.953 \times 10^{-6} \text{ at } 546.1 \text{ nm}$$

$$dn/dT (\text{K}^{-1}) = -0.949 \times 10^{-6} \text{ at } 632.8 \text{ nm}$$

Dispersion formula [λ (μm) in vacuum at T = 273 K]	Range (_m)
$n = 1 + [68.5520 + 32431.57\lambda^2/144\lambda^2 - 1] \times 10^{-6}$	0.47–2.06

Reference: Peck, E. R. and Hanna, B. N., *J. Opt. Soc. Am.* 56, 1059 (1966).

Index of Refraction n of Oxygen, O₂

$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)
0.275278	1.0003242
0.289360	1.0002936
0.302150	1.0002912
0.318770	1.0002879
0.388865	1.0002797
0.447148	1.0002763
0.471250	1.0002751
0.501568	1.0002740
0.587562	1.0002718
0.667815	1.0002708

Reference: Abjean, R., Mehu, A., and Johannin-Gilles, A., *Comptes Rendus* 271, 411 (1970).

Temperature variation of the index of refraction of oxygen at 293 K:

$$dn/dT (\text{K}^{-1}) = -0.864 \times 10^{-6} \text{ at } 546.1 \text{ nm}$$

$$dn/dT (\text{K}^{-1}) = -0.858 \times 10^{-6} \text{ at } 632.8 \text{ nm}$$

Index of Refraction n of Carbon Dioxide, CO₂

$\lambda_{\text{vac}}(\mu\text{m})$	n (273 K)	Ref.	$\lambda_{\text{vac}}(\mu\text{m})$	n (273 K)	Ref.
0.180731	1.0005513	1	0.410925	1.0004582	2
0.184949	1.0005441	1	0.480126	1.0004534	3
0.194232	1.0005333	1	0.491720	1.0004529	2
0.206230	1.0005207	1	0.508724	1.0004520	3
0.213923	1.0005142	1	0.546223	1.0004505	2
0.228872	1.0005034	1	0.724716	1.0004461	3
0.237910	1.0004973	2	0.744095	1.0004458	3
0.244764	1.0004937	2	0.826679	1.0004446	3
0.246482	1.0004929	2	0.877716	1.0004440	3
0.253728	1.0004895	1	0.893115	1.0004439	3
0.257708	1.0004878	2	0.912547	1.0004437	3
0.267577	1.0004840	2	0.922703	1.0004436	3
0.276058	1.0004811	2	0.966043	1.0004431	3
0.285780	1.0004781	2	1.014257	1.0004427	3
0.296813	1.0004752	2	1.296021	1.0004405	3
0.334242	1.0004674	2	1.372232	1.0004399	3
0.354469	1.0004644	2	1.475650	1.0004392	3
0.368104	1.0004625	2	1.529354	1.0004387	3
0.398507	1.0004593	2	1.694521	1.0004374	3

References:

1. Bideau-Mehu, A., Guern, Y., Abjean, R., and Johannin-Gilles, A., Interferometric determination of the refractive index of CO₂ in the ultraviolet region, Opt. Commun. 9, 432 (1973).
2. Leonard, P. J., Atomic Data and Nuclear Data Tables 14, 21 (1974).
3. Old, J. G., Gentili, K. L., and Peck, E. R., Dispersion of carbon dioxide, J. Opt. Soc. Am. 61, 89 (1971).

Temperature variation of the index of refraction of carbon dioxide at 293 K:

$$dn/dT (K^{-1}) = 1.432 \times 10^{-6} \text{ at } 546.1 \text{ nm}$$

$$dn/dT (K^{-1}) = 1.424 \times 10^{-6} \text{ at } 632.8 \text{ nm}$$

Dispersion formula [$\lambda (\mu\text{m})$ in vacuum at T = 273 K]	Range (μm)
$n = 1 + 0.012055[0.579925\lambda^2/(166.175\lambda^2 - 1) + 0.12005\lambda^2(79.609\lambda^2 - 1) + 0.0053334\lambda^2/(56.3064\lambda^2 - 1) + 0.0043244\lambda^2/(46.0196\lambda^2 - 1) + 0.0001218145\lambda^2/(0.0584738\lambda^2 - 1)]$	0.18–1.7

Reference: Bideau-Mehu, A., Guern, Y., Abjean, R., and Johannin-Gilles, A., Interferometric determination of the refractive index of CO₂ in the ultraviolet region, *Opt. Commun.* 9, 432 (1973).

Index of Refraction n of Methane, CH₄

$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Reference
0.5290	1.0004478	1
0.5718	1.0004454	1
0.5893	1.000444	2
0.5935	1.0004435	1
0.6375	1.0004411	1
0.6585	1.0004404	1

References:

1. *International Critical Tables of Numerical Data, Physics and Chemistry and Technology*, Vol. VII, Washburn, E. W., Ed., (McGraw-Hill, New York, 1930).
2. Kaye, G. W., and Laby, T. H., *Tables of Physical and Chemical Constants* (Longman Group, London, 1986).

Index of Refraction n of Ammonia, NH₃

$\lambda_{\text{air}}(\mu\text{m})$	n (273 K)	Reference
0.47999	1.0003830	1
0.50858	1.0003808	1
0.52091	1.0003800	1
0.54607	1.0003786	1
0.57695	1.0003771	1
0.57905	1.0003770	1
0.5893	1.000376	2
0.64385	1.0003746	1
0.67078	1.0003738	1

References:

1. *International Critical Tables of Numerical Data, Physics and Chemistry and Technology*, Vol. VII, Washburn, E. W., Ed., (McGraw-Hill, New York, 1930).
2. Kaye, G. W., and Laby, T. H., *Tables of Physical and Chemical Constants* (Longman Group, London, 1986).

Index of Refraction n of Air

$\lambda_{\text{air}} (\mu\text{m})$	n (288 K)	$\lambda_{\text{vac}} - \lambda_{\text{air}}$ (μm)	$\lambda_{\text{air}} (\mu\text{m})$	n (288 K)	$\lambda_{\text{vac}} - \lambda_{\text{air}}$ (μm)
0.200	1.0003256	0.0000651	0.560	1.0002769	0.0001551
0.210	1.0003188	0.0000670	0.570	1.0002768	0.0001578
0.220	1.0003132	0.0000689	0.580	1.0002766	0.0001604
0.230	1.0003086	0.0000710	0.590	1.0002765	0.0001631
0.240	1.0003047	0.0000731	0.600	1.0002763	0.0001658
0.250	1.0003014	0.0000754	0.610	1.0002762	0.0001685
0.260	1.0002986	0.0000776	0.620	1.0002761	0.0001712
0.270	1.0002962	0.0000800	0.630	1.0002760	0.0001739
0.280	1.0002941	0.0000824	0.640	1.0002759	0.0001766
0.290	1.0002923	0.0000848	0.650	1.0002758	0.0001792
0.300	1.0002907	0.0000872	0.660	1.0002757	0.0001819
0.310	1.0002893	0.0000897	0.670	1.0002756	0.0001846
0.320	1.0002880	0.0000922	0.680	1.0002755	0.0001873
0.330	1.0002869	0.0000947	0.690	1.0002754	0.0001900
0.340	1.0002859	0.0000972	0.700	1.0002753	0.0001927
0.350	1.0002850	0.0000998	0.710	1.0002752	0.0001954
0.360	1.0002842	0.0001023	0.720	1.0002751	0.0001981
0.370	1.0002835	0.0001049	0.730	1.0002751	0.0002008
0.380	1.0002829	0.0001075	0.740	1.0002750	0.0002035
0.390	1.0002823	0.0001101	0.750	1.0002749	0.0002062
0.400	1.0002817	0.0001127	0.760	1.0002749	0.0002089
0.410	1.0002812	0.0001153	0.770	1.0002748	0.0002116
0.420	1.0002808	0.0001179	0.780	1.0002748	0.0002143
0.430	1.0002803	0.0001205	0.790	1.0002747	0.0002170
0.440	1.0002799	0.0001232	0.800	1.0002746	0.0002197
0.450	1.0002796	0.0001258	0.810	1.0002746	0.0002224
0.460	1.0002792	0.0001284	0.825	1.0002745	0.0002265
0.470	1.0002789	0.0001311	0.850	1.0002744	0.0002332
0.480	1.0002786	0.0001338	0.875	1.0002743	0.0002400
0.490	1.0002784	0.0001364	0.900	1.0002742	0.0002468
0.500	1.0002781	0.0001391	0.925	1.0002741	0.0002536
0.510	1.0002779	0.0001417	0.950	1.0002740	0.0002604
0.520	1.0002777	0.0001444	0.975	1.0002740	0.0002671
0.530	1.0002775	0.0001471	1.000	1.0002739	0.0002739
0.540	1.0002773	0.0001497	1.050	1.0002738	0.0002875
0.550	1.0002771	0.0001524	1.100	1.0002737	0.0003011

Reference:

CRC Handbook of Chemistry and Physics, 75th edition, Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 1994).

6.4 Nonlinear Optical Properties

6.4.1 Nonlinear Refractive Index γ (300 K)

Gas	λ (nm)	γ (10^{-22} m ² /W)	Ref.
<u>Noble gases</u>			
He	694.3	0.014	1
Ne	694.3	0.006	2
Ar	248.4	0.29 ± 0.10	2
	694.3	0.25	1
<u>Other gases</u>			
H ₂	694.3	0.21	3
D ₂	694.3	0.21	1
O ₂	248.4	3.0 ± 0.3	2
	694.3	0.21	1
N ₂	248.4	0.76 ± 0.26	2
	694.3	0.21	1
CO ₂	248.4	0.32	1
	694.3	1.1	2
CH ₄	248.4	1.1 ± 0.4	2
	694.3	0.47	1

References:

1. Rado, W. G., *Appl. Phys. Lett.* 11, 123 (1967)
2. Shaw, M. J., Hooker, C. J., and Wilson, D. C., *Opt. Commun.* 103, 153 (1993).
3. Martin, W. E. and Winfield, R. J., *Appl. Opt.* 27, 577 (1988)

6.4.2 Two-Photon Absorption

Two-Photon Absorption Coefficients

Gas	Excitation duration (ns)	Applied two-photon energy (eV)	Two-photon cross-section 10^{-50} cm ⁴ s/phot. mol.	Ref.	Additional information
Anthracene	30	3.57	0.09	1	503 K, 1.7 Torr
Benzene	10	4.92	0.0126	2	30 Torr, Ar buffer
Benzene	10	8.43	0.0016	2	30 Torr, Ar buffer
Benzene	10	8.44	0.00075	2	30 Torr, Ar buffer
Benzene	10	8.53	0.00146	2	30 Torr, Ar buffer
Benzene	10	8.87	0.00001	2	30 Torr, Ar buffer
Perylene	30	3.57	1.2	1	583 K, 0.6 Torr
POPOP	30	3.57	0.05	1	603 K, 1.23 Torr

POPOP : 1,4-di[2-(5-phenyloxazolyl)] benzene.

References:

1. Blokhin, A. P., Povedalio, V. A., and Tolkachev, V. A., Polarization of two-photon excited fluorescence of vapors of complex organic molecules, *Opt. Spectrosc. (USSR)* 60, 37 (1986).
2. Zheng, B., Lin, M., Zhang, B., and Chen, W., Study of two-photon absorption cross section by multiphoton ionization spectroscopy, *Opt. Commun.* 73, 208 (1989).

6.4.3 Third-Order Nonlinear Optical Coefficients

Gas	Nonlinear optical process	Coefficient $C_{jn}^{mic} \times 10^{20} m^2 V^{-2}$	Wavelength (μm)
<u>Noble gases</u>			
Helium, He	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.00245$	0.6943
	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 0.00122$	0.6943
	($-2\omega; 0, \omega, \omega$)	$C_{22} = 0.0027$	0.6943
Neon, Ne	($-2\omega; 0, \omega, \omega$)	$C_{22} = 0.00735 \pm 0.00024$	0.6943
	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 0.00312 \pm 0.00053$	0.6943
Argon, Ar	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.0217 \pm 10\%$	0.6943
	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 0.0875$	0.308
	($-2\omega; 0, \omega, \omega$)	$C_{11} = 0.0441 \pm 0.007$	0.6943
		$C_{22} = 0.0833 \pm 0.0027$	0.6943
Krypton, Kr	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 0.13516 \pm 0.0262$	0.6943
	($-2\omega; 0, \omega, \omega$)	$C_{22} = 0.2037 \pm 0.0098$	0.6943
Xenon, Xe	($-2\omega; 0, \omega, \omega$)	$C_{11} = 0.3426 \pm 0.0655$	0.6943
		$C_{22} = 0.5635 \pm 0.0392$	0.6943
<u>Other gases</u>			
Carbon dioxide, CO ₂	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.028 \pm 10\%$	
	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 0.054 \pm 0.008$	0.6943
Carbon monoxide, CO	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.0252 \pm 10\%$	0.6943
	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 1.95$	9.33
Deuterium, D ₂	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.0182 \pm 10\%$	0.6943
Ethane, C ₂ H ₈	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.0868 \pm 10\%$	0.6943
Hydrogen, H ₂	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.0294 \pm 10\%$	0.6943
	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 0.028 \pm 0.0024$	0.6943
Methane, CH ₄	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{jn}^{mic} = 0.1925 \pm 0.0161$	0.6943
	($-2\omega; 0, \omega, \omega$)	$C_{jn}^{mic} = 0.1708 \pm 0.084$	0.6943
	($-\omega; 0, 0, +\omega$)	$C_{22} = 0.1806 \pm 0.013$	0.6943
	($-2\omega; \omega, \omega, 0$)	$C_{11} = 0.0413 \pm 10\%$	0.6943
Nitric oxide, NO	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.0588 \pm 10\%$	0.6943
Nitrogen, N ₂	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.0189 \pm 10\%$	0.6943
	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 0.03745 \pm 0.006$	0.6943
Oxygen, O ₂	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.0182 \pm 10\%$	0.6943
Sulfur hexafluoride, SF ₆	($-2\omega_1 + \omega_2; \omega_1, \omega_1, -\omega_2$)	$C_{11} = 0.035 \pm 10\%$	0.6943
	($-3\omega; \omega, \omega, -\omega$)	$C_{11} = 5862$	10.6

Data from a table of S. Singh, Nonlinear optical materials, *Handbook of Laser Science and Technology, Vol. III: Optical Materials, Part I* (CRC Press, Boca Raton, FL., 1986), p. 60 ff.

6.4.4 Stimulated Raman Scattering

Stimulated Raman Scattering Transitions in Gases

Substance	Raman frequency shift ν_0 (cm ⁻¹)	Ref.
barium vapor, ^a Ba	IR ^b	11
cesium vapor, ^a Cs	IR ^b	12,13
hydrogen fluoride, HF	FIR ^b	14
potassium vapor, ^a K	IR ^b	13,15
rubidium vapor, ^a Rb	IR ^b	16
para-hydrogen, <i>p</i> -H ₂	354	17,18
silane, SiH ₄	2186	5
germane, GeH ₄	2111	5
sulfur hexafluoride, SF ₆	775	5
carbon tetrafluoride, CF ₄	980	19
oxygen, O ₂	1552	24
nitrogen, N ₂	2331	20
potassium vapor, K	2721	21
methane, CH ₄	2916	22
deuterium, D ₂	2991	22
hydrogen deuteride, HD	3628	23
hydrogen, H ₂	4155	22

^a Stimulated electronic Raman scattering (SERS).

^b Generally tunable transitions in the infrared (IR) and far infrared (FIR).

The above table is from Milanovich, F. P., Stimulated Raman scattering, *Handbook of Laser Science and Technology, Vol. III: Optical Materials* (CRC Press, Boca Raton, FL, 1986), p. 283.

Raman Gain Parameters of Selected Gases at 298 K

Gas	Mode	ν_0 (cm ⁻¹)	$\Delta\nu_g$ (MHz) ^a	Ref.	gain (cm/GW)	ρ (amagat)	λ_I (nm)	Ref.
H ₂	Q(1)	4155	$\frac{309}{\rho} + 52.2\rho$	1	2.5 ± 0.4	20	532	2
					2.64 ± 0.2	60	532	3
					3.5 ± 0.3	20	477	2
					5.7	High density	350	4
					6.6 ± 0.8	20	308	2
	Q(0)		$\frac{257}{\rho} + 76.6\rho$	1	7.00	>20	248	5
	S(1)	587	119ρ	4	1.2	High density	350	4
p-H ₂ (81 K)	Q(0)	354	$\frac{76.6}{\rho} + 45.4\rho$	1				
(80 K)	S(1)				$0.096 \pm .009$		10P(20) ^b	6
					$0.102 \pm .014$		10R(20) ^b	6
					$0.111 \pm .012$		9P(20) ^b	6
					$0.123 \pm .014$		9R(20) ^b	6

Raman Gain Parameters of Selected Gases at 298 K—continued

Gas	Mode	ν_0 (cm $^{-1}$)	$\Delta\nu_g$ (MHz) ^a	Ref.	gain (cm/GW)	ρ (amagat)	λ_l (nm)	Ref.
D ₂	Q(2)	2987	$\frac{101}{\rho} + 120\rho$	7,8	0.45 ± 0.05	60 atm	532	3
			66ρ	4	1.9	High density	350	4
					0.47	High density	350	4
D ₂	S(2)	414	124ρ	4				4
HD	Q(1)	3628	693ρ	4				4
	S(1)	443	760ρ	4	0.23	High density	350	4
					0.098	High density	350	4
CH ₄	v ₁	2917	$8220 + 384\rho$	3	1.26	115	532	3
			9000 (1<ρ<10)	5	0.12ρ		248	5
					1.2			
					0.66			
N ₂	Q branch	2327	22.5 (ρ<10)	5	0.3ρ		248	5
	S(6)	60	0.00285 (D)	9	0.0063	>1 torr	400	9
			3570ρ	10	0.0036	>.01	566	10
	S(8)	76	0.00363 (D)	9	0.0073	>1 torr	400	9
			3570ρ	10	0.0046	>.01	565.5	10
	S(10)	92	0.00441 (D)	9	0.0072	>1 torr	400	9
			3570ρ	10	0.0048	>.01	565	10
	S(12)	108	0.00516 (D)	9	0.0061	>1 torr	400	9
			3570ρ	10	0.0043	>.01	564.5	10
O ₂	Q branch	1552	54	5	0.012ρ		248	5
SiH ₄	Q branch	2186	15 (est)	5	0.19ρ		248	5
GeH ₄	v ₁	2111	15 (est)	5	0.27ρ		248	5
CF ₄	v ₁	980	21 (est)	5	0.008ρ		248	5
SF ₆	v ₁	775	30 (est)	5	0.014ρ		248	5

^a ρ is measured in amagats

^b CO₂ laser lines.

(D) Döppler

The above table is from Reintjes, J. F., Stimulated Raman and Brillouin scattering, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 334.

Polarization Dependence of Relative Gain

	Pump polarization	Stokes polarization	Relative gain
Rotational scattering, linear molecules	linear	linear parallel	1.0
	linear	linear, perpendicular	0.75
	circular	circular, same sense	0.25
	circular	circular, opposite sense	1.5

References:

1. Bischel, W. K., and Dyer, M. J., Temperature dependence of the Raman linewidth and lineshift for the Q(1) and Q(0) transitions in normal and para H₂, *Phys Rev A* 33, 3113 (1986).
2. Bischel, W. K., and Dyer, M. J., Wavelength dependence of the absolute Raman gain coefficient for the Q(1) transition in H₂, *J. Opt. Soc. Am. B* 3, 677 (1986).
3. Ottusch, J. J., and Rockwell, D. A., Measurement of Raman gain coefficients of hydrogen, deuterium and methane, *IEEE J. Quantum Electron.* QE-24, 2076 (1988).
4. Bischel, W. K., Stimulated Raman gain processes in H₂, HD and D₂, unpublished.
5. Murray, J. R., Goldhar, J., Eimerl, D., and Szoke, A., Raman pulse compression of excimer lasers for application to laser fusion, *IEEE J. Quantum Electron.* QE-15, 342 (1979).
6. Corat, E. J., Airoldi, V. J. T., Scolari, S. L., and Ghizoni, C. C., Gain measurements in stimulated rotational Raman scattering in para hydrogen, *Opt. Lett.* 11, 368 (1986).
7. Russel, D. A., and Roh, W. B., High resolution CARS measurements of Raman linewidths of deuterium, *J. Mol. Spect.* 24, 240 (1987).
8. Smyth, K. C., Rosasco, G. J., and Hurst, W. S., Measurements and rate law analysis of D₂ Q-branch line broadening coefficients for collisions with D₂, He, Ar, H₂ and CH₄, *J. Chem. Phys.* 87, 1001 (1987).
9. Rokni, M., and Flusberg, A., Stimulated rotational Raman scattering in the atmosphere, *IEEE J. Quantum Electron.* QE-22, 1102 (1986).
10. Herring, G. C., Dyer, M. J., and Bischel, W. K., Temperature and wavelength dependence of the rotational Raman gain coefficient in N₂, *Opt. Lett.* 11, 348 (1986).
11. Carlsten, J. L. and Dunn, P. C., Stimulated stokes emission with a dye laser: intense tunable radiation in the infrared, *Opt. Commun.* 14, 8 (1975).
12. Cotter, D., Hanna, D. C., Kärkkäinen, P. A., and Wyatt, R., Stimulated electronic Raman scattering as a tunable infrared source, *Opt. Commun.* 15, 143 (1975).
13. Sorokin, P. P., Wynne, J. J., and Landkard, J. R., Tunable coherent IR source based upon four-wave parametric conversion in alkali metal vapors, *Appl. Phys. Lett.* 22, 342 (1973).
14. DeMartino, A., Frey, R., and Pradere, F., Tunable far infrared generation in hydrogen fluoride, *Opt. Commun.* 27, 262 (1978).
15. Cotter, D., Hanna, D. C., Kärkkäinen, P. A., and Wyatt, R., Stimulated electronic Raman scattering as a tunable infrared source, *Opt. Commun.* 15, 143 (1975).
16. May, P., Bernage, P., and Bocquet, H., Stimulated electronic Raman scattering in rubidium vapour, *Opt. Commun.* 29, 369 (1979).
17. Byer, R. L. and Trutna, W. R., 16-μm generation by CO₂-pumped rotational Raman scattering in H₂, *Opt. Lett.* 3, 144 (1978).
18. Rabinowitz, P., Stein, A., Brickman, R., and Kaldor, A., Efficient tunable H₂ Raman laser, *Appl. Phys. Lett.* 35, 739 (1979).
19. Pochon, E., Determination of the spontaneous Raman linewidth of CF₄ by measurements of stimulated Raman scattering in both transient and steady states, *Chem. Phys. Lett.* 77, 500 (1981).
20. Kinkaid, B. E. and Fontana, J. R., Raman cross-section determination by direction stimulated Raman gain measurements, *Appl. Phys. Lett.* 28, 12 (1975).
21. Roknl, M. and Yatslv, S., Resonance Raman effects in free atoms of potassium, *Phys. Lett.* 24, 277 (1967).
22. Minck, R. W., Terhune, R. W., and Rado, W. G., Laser-stimulated Raman effect and resonant four-photon interactions in gases H₂, D₂, and CH₄, *Appl. Phys. Lett.* 3, 181 (1963).
23. Komine, H., Northrop Corp., Palos Verdes, CA (private communication, F. P. Milanovich (1983)).
24. Geller, M., Bortfeld, D. P., and Sooy, W. R., New Woodbury-Raman laser materials, *Appl. Phys. Lett.* 11, 207 (1963).

6.4.5 Brillouin Phase Conjugation

Gases Used for Brillouin Phase Conjugation								Density ρ (g/cm ³)	Ref.
Gas	Wavelength λ (nm)	Refract. index n	Sound speed v_s (km/s)	Brillouin shift at λ (GHz)	Phonon lifetime τ_p (ns)	Line width $\Delta\nu_h$ (MHz)	Gain g (cm/GW)		
Argon, Ar	1064		0.34		3		4	50 ^a	1
Chlorotrifluoromethane, CClF_3 (Freon 13)									2
Dichlorodifluoromethane, CCl_2F_2 (Freon 12)	248	1.001	0.15	1.2		960	0.19	1	3 ^c
Hexafluoroethane, C_2F_6 (Freon 116)									2
Methane, CH_4	1064		0.46		3		8	150 ^a	1
	694				32		18	50	4
	694				22		40		4
	694				20		72	75	4
	694				20		100	105	5,6
Nitrogen, N_2	694				10		5 ^b	150 ^a	7
	1064		0.36		15	15	4	135	1
	694		0.39				30		4
Sulfur hexafluoride, SF_6	1064		0.14		20		6	20	1
	694				6		8	10	2
	694		0.113			14	35	22	3 ^c

Gases Used for Brillouin Phase Conjugation—continued

Gas	Wavelength λ (nm)	Refract. index n	Sound speed v_s (km/s)	Brillouin shift at λ (GHz)	Phonon lifetime τ_p (ns)	Line width $\Delta\nu_h$ (MHz)	Gain g (cm/GW)	Density ρ (g/cm ³)	Ref.
Xenon	1064		0.18		35		47	40 ^a	1
	694				6 ^d		10	20 ^a	2
	694				15		90	80 ^a	2
	694		0.149			11	44	39	4
	1315				65			50	8

^aDensity in amagats rather than pressure in atmospheres; ^bThis is the transient gain; the authors calculate steady-state gain as 30 cm/GW, and give a pressure dependence as well; ^cSome of the numbers in this row are theoretical calculations; the reference reports energy conversions; ^dDamzen et. al.² give the formula $t_B(\text{ns}) = 0.651L^2p$ (atm).

Table from Pepper, D. M., Minden, M. L., Bruesselbach, H. W., and Klein, M. B., Nonlinear optical phase conjugation materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 467.

References:

1. Bespalov, V. I., and Pasmanik, G. A., *Nonlinear Optics and Adaptive Laser Systems* (Nauka, Moscow, USSR, 1985). Trans. by Translation Division, Foreign Technology Division, Wright Patterson Air Force Base, OH, document FTD-ID(RS)T-0889-86.
2. Damzen, M. J., Hutchinson, M. H. R., and Schroeder, W. A., Direct measurement of the acoustic decay times of hypersonic waves generated by SBS, *IEEE J. Quantum Electron.* QE-23, 328 (March 1987).
3. Tomov, I. V., Fedosejevs, R., and McKen, D. C. D., Stimulated Brillouin scattering of KrF laser radiation in dichlorodifluoromethane, *IEEE J. Quantum Electron.* QE-21, 9 (January 1985).
4. Kovalev, V. I., Popovichev, V. I., Ragul'skii, V. V., and Faizullov, F. S., Gain and line width in stimulated Brillouin scattering in gases, *Kvantovaya Elektronika, Moskva* (Sov. J. Quantum Electron.), no.7 (2, no.1), 78–80 (69–71) (July–Aug. 1972).
5. Hammond Jr., C. M., and Wiggins, T. A., Rayleigh-Brillouin scattering from methane, *J. Chem. Phys.* 65, 2788 (1 Oct. 1976).
6. Cazabat, A. M., and Larour, J., Rayleigh-Brillouin scattering in compressed gases, *J. Phys.* 36, 1209 (Dec. 1975).
7. Hagenlocker, E. E., Minck, R. W., and Rado, W. G., Effects of phonon lifetime on stimulated optical scattering in gases, *Phys. Rev.* 154, 226 (1967).
8. Dolgopolov, Yu V., Komarevskii, V. A., Kormer, S. B., Kochemasov, G. G., Kulikov, S. M., Murugov, V. M., Nikolaev, V. D., and Sukharev, S. A., Experimental investigation of the feasibility of applying the wave front reversal phenomenon on induced Mandelstam-Brillouin scattering, *Z. Eksperiment. Teoret. Fiziki* (Sov. Phys.-JETP) 76, 908 (March 1979).

6.5 Magnetooptic Properties

Verdet Constant V (degrees/Tesla meter) of Gases at 273 K

	Wavelength (nm)							
	363.5	400	500	600	700	800	900	987.5
<u>Noble gases</u>								
He	0.0209	0.0168	0.0106	0.0074	0.0054	0.0041	0.0034	
Ne	0.0388	0.0326	0.0204	0.0137	0.0090	0.0064	0.0052	0.0047
Ar	0.4106	0.3297	0.2055	0.1403	0.1004	0.0768	0.0610	0.0516
Kr	0.8637	0.6820	0.4232	0.2855	0.2040	0.1531	0.1203	0.1004
Xe	2.1112	1.64492	1.0055	0.6684	0.4766	0.3567	0.2812	0.2354
<u>Other gases</u>								
H ₂	0.2882	0.2308	0.1425	0.0969	0.0690	0.0531	0.0422	0.0351
D ₂	0.2815	0.2221	0.1375	0.0943	0.0679	0.0522	0.0413	0.0344
O ₂	0.1948	0.1620	0.1144	0.0886	0.0725	0.0631	0.0568	0.0536
N ₂	0.2820	0.2268	0.1407	0.0968	0.0698	0.0527	0.0421	0.0359
CO ₂	0.4205	0.3391	0.2104	0.1445	0.1044	0.0789	0.0583	0.0536
CH ₄	0.7875	0.6246	0.3861	0.2618	0.1881	0.1433	0.1140	0.0953

References:

- Ingersoll, L. R. and Liebenberg, D. H., Faraday effect in gases and vapors. I, *J. Opt. Soc. Am.* 44, 566 (1954).
 Ingersoll, L. R. and Liebenberg, D. H., Faraday effect in gases and vapors. II, *J. Opt. Soc. Am.* 46, 538 (1956).

6.6 Atomic Resonance Filters

Atomic resonance filters (ARFs) are a class of filter devices that have very narrow bandwidth (~ 0.001 nm) and a wide field of view (180°). A cell containing atomic vapor (e.g., Rb, Cs, etc.) is placed between two narrow bandpass filters. The input filter has a peak transmission wavelength corresponding to a strong electron transition in the vapor species. Incoming light is then strongly absorbed, yielding an excited state population which decays, emitting photons of a second wavelength. The bandpass of the output filter corresponds to the emitted wavelength. Use of both ground state (passive operation) and excited state (laser-pumped operation) transitions have been reported for a variety of atomic vapors operating at a variety of wavelengths. A detailed review of the physics of ARFs is given by Gelbwachs.¹

Atomic Resonance Filters

Atomic species	Wavelength		Pump	
	Input	Output	source	Ref.
Na	1480 nm	489 nm	optical	2
	2340 nm	569 nm	optical	2
	3420 nm	616 nm	optical	2
K	$\sim 10.6 \mu\text{m}$	497 nm	optical	3
Rb	20,487–776 nm	420 nm	diode laser	1
	459 nm	894 nm	none	4

Atomic Resonance Filters—continued

Atomic species	Wavelength		Pump	Ref.
	Input	Output	source	
Cs ^a	456 nm	852 nm	none	4
	534 nm	404 nm	diode laser	5
Tl	535 nm	378 nm	photochemical	6
Mg	518 nm	384 nm	Nd:YAG	7
Ca ^a	423 nm	272 nm	diode laser	8

^a Not experimentally verified.

An alternative atomic resonance filter design is the Faraday anomalous dispersion optical filter (FADOF).^{2,3} An atomic vapor cell is placed in a magnetic field between crossed polarizers. The resonant Faraday effect causes polarization rotation at frequencies corresponding to atomic transitions. At other frequencies rotation is negligible. Thus, by proper adjustment of atomic vapor concentration, cell length, and magnetic field strength, ultranarrow-linewidth bandpass filters may be produced. FADOFs do not shift the output wavelength, and no response delay occurs. In principle, transmission is near unity at the center of the filter bandpass for linearly polarized incident light.

Atomic Faraday Filter Data

Atomic species	Operating wavelength (nm)	Peak transmission (%)	Bandwidth (GHz)	Rejection ratio	Ref.
K	766, 770	71	1.6		9
Rb	780	63	1.0	10^5	9
Cs	852	82	0.6	10^5	10

The above table is from Cook, L. M., Filter materials, *Handbook of Laser Science and Technology, Suppl. 2: Optical Materials* (CRC Press, Boca Raton, FL, 1995), p. 115 (with additions).

References:

1. Gelbwachs, J., Atomic resonance filters, *IEEE J. Quantum Electron.* 24, 1266 (1988).
2. Gelbwachs, J., Klein, C., and Wessel, J., Infrared detection by an atomic vapor quantum counter, *IEEE J. Quantum Electron.* QE-14, 77 (1978).
3. Gelbwachs, J., and Wessel, J., Atomic vapor quantum counter: narrow-band infrared upconverter, *IEEE Trans. Electron. Dev.* ED-27, 99 (1980).
4. Marling, J., Nilsen, J., West, L., and Wood, L., An ultrahigh Q isotropically sensitive optical filter employing atomic resonance transitions, *J. Appl. Phys.* 50, 610 (1979).
5. Shay, T., Ultrahigh-resolution, wide-field-of-view Cs optical filter for doubled Nd lasers, *Opt. Commun.* 77, 368 (1990).
6. Liu, C., Chantry, P., and Chen, C., A 535 nm active atomic line filter employing the thallium metastable state as the absorbing medium, *SPIE Proc.* 709, 132 (1986).
7. Chan, Y., Tabat, M., and Gelbwachs, J., Experimental demonstration of internal wavelength conversion in the magnesium atomic filter, *Opt. Lett.* 14, 722 (1989).
8. Gelbwachs, J., 422.7-nm atomic filter with superior solar background rejection, *Opt. Lett.* 15, 236 (1990).
9. Zhang, Y., Jia, X., Ma, Z., and Wang, Q., Potassium Faraday optical filter in line-center operation, *Opt. Commun.* 194, 147 (2001).
10. Dick, D., and Shay, T., Ultrahigh-noise rejection optical filter, *Opt. Lett.* 16, 867 (1991).
11. Menders, J., Benson, K., Bloom, S., Liu, C., and Korevaar, E., Ultranarrow line filtering using a Cs Faraday filter at 852 nm, *Opt. Lett.* 16, 846 (1991).

Appendices

- | | |
|--------------|--|
| Appendix I | Safe Handling of Optical Materials |
| Appendix II | Abbreviations, Acronyms, Initialisms, and
Mineralogical or Common Names of Optical
Materials |
| Appendix III | Abbreviations for Methods of Preparing Optical
Materials and Thin Films |
| Appendix IV | Fundamental Physical Constants |
| Appendix V | Units and Conversion Factors |

APPENDIX I

Safe Handling of Optical Materials

When using any optical material—solid, liquid, or gas—it is always advisable to consult the Material Safety Data Sheet (MSDS). These informative documents prepared by the manufacturer or importer of a hazardous substance describe the physical and chemical properties of the product, are helpful in understanding potential health and physical hazards, and describe how to respond effectively to exposure situations. They include information such as hazardous ingredients, physical data of the material, fire and explosion hazard data, health hazard data, reactivity data, spill or leak procedures, special protection information, and emergency and first aid procedures.

Hazards associated with optical materials depend on how the material is used. This is particularly important in the case of liquids where properties such as viscosity, toxicity, and system compatibility may need to be considered. Within the refractive index range of 1.45 to 1.55 there are so many possible liquids that one can easily choose one with low toxicity. Outside this range of indices the choices of liquid are fewer, thus some degree of toxicity may be unavoidable and the use of ventilation, fume hoods, protective gloves, eye protection, and other protective devices may be mandatory. When working with optical liquids, it is always a good idea to wear appropriate gloves and eye protection and to work where ventilation is sufficient.

The following tables present information about the suitability of various common glove materials for handling liquids and about the flammability of selected liquids.

Resistance to Liquids of Common Glove Materials

Liquid	Natural rubber	Neoprene	Nitrile	Vinyl
acetic acid, C ₂ H ₄ O ₂	excellent	excellent	excellent	excellent
acetone, C ₃ H ₆ O	good	good	good	fair
benzene, ^a C ₆ H ₆	poor	fair	good	fair
carbon disulfide, CS ₂	poor	poor	good	fair
carbon tetrachloride, ^a CCl ₄	poor	fair	good	fair
cyclohexane, C ₆ H ₁₂	fair	excellent	—	poor
diethyl ether, CH ₂ Cl ₂	fair	good	excellent	poor
dimethylsulfoxide, ^b C ₂ H ₆ OS	—	—	—	—
ethylene glycol, C ₂ H ₆ O ₂	good	good	excellent	excellent
glycerine (glycerol), C ₃ H ₈ O ₃	good	good	excellent	excellent
hexane, C ₆ H ₁₄	poor	excellent	—	poor
toluene, C ₇ H ₈	poor	fair	good	fair

^a Aromatic and halogenated hydrocarbons will attack all types of natural and synthetic glove materials.

^b No data are available on the resistance to methylsulfoxide of natural rubber, neoprene, nitrile rubber, or vinyl materials; the manufacturer recommends the use of butyl rubber gloves.

Flammability of Selected Liquids

Properties listed in the table below:

Boiling point: at a pressure of 101.325 kPa.

Flash point: minimum temperature at which the vapor pressure of the liquid is sufficient to form an ignitable mixture with air near the surface of the liquid.

Ignition temperature (also called autoignition temperature): minimum temperature required for self-sustained combustion in the absence of an external ignition source.

Both the flash point and the ignition temperature are not intrinsic properties but depend on the test conditions. Observed values may differ by several degrees and large uncertainties should be assumed.

Liquid	Flammability		
	Boiling point (°C)	Flash point (°C)	Ignition temperature (°C)
acetic acid, C ₂ H ₄ O ₂	117.9	39	463
acetone, C ₃ H ₆ O	56	-20	465
benzene, C ₆ H ₆	80.0	-11	498
carbon disulfide, CS ₂	46	-30	90
cyclohexane, C ₆ H ₁₂	80.7	-20	245
1,2-dichloroethane, C ₂ H ₄ Cl ₂	83.5	13	413
dicloromethane, CH ₂ Cl ₂	40	—	556
diethyl ether, C ₄ H ₁₀ O	34.5	-45	180
dimethylsulfoxide, C ₂ H ₆ OS	189	95	215
1,4-dioxane, C ₄ H ₈ O ₂	101.5	12	180
ethanol, C ₂ H ₆ O	78.2	13	363
ethylene glycol, C ₂ H ₆ O ₂	197.3	111	398
glycerine (glycerol), C ₃ H ₈ O ₃	290	199	370
heptane, C ₇ H ₁₆	98.5	—	204
hexane, C ₆ H ₁₄	68.7	-22	225
methanol, CH ₄ O	64.6	11	464
methylcyclohexane, C ₇ H ₁₄	100.9	—	250
nitrobenzene, C ₆ H ₅ NO ₂	210.8	88	482
toluene, C ₇ H ₈	110.6	4	480

Data for the above tables are from the *CRC Handbook of Chemistry and Physics*, 82nd ed., Lide, D. R., Ed. (CRC Press, Boca Raton, FL, 2001), p. 16–13 and 16–16. This reference contains extensive data on the flammability of many additional chemical substances.

References:

The internet site www.MSDS-Search.com provides links to all major online MSDS databases.

Other references to the handling and disposition of hazardous materials include:

Prudent Practices for Handling Hazardous Chemicals in Laboratories, National Academy Press, Washington, DC (1981).

Prudent Practices for Disposal of Chemicals from Laboratories, National Academy Press, Washington, DC (1981).

Fire Protection Guide to Hazardous Materials, 10th edition, National Fire Protection Association, Quincy, MA (1991).

Bretherick, L., *Handbook of Reactive Chemical Hazards*, 3rd edition, (Butterworths, London-Boston, 1985).

Urben, P. G., Ed., *Bretherick's Handbook of Reactive Chemical Hazards*, 5th edition (Butterworth-Heinemann, Oxford, 1995).

APPENDIX II

Abbreviations, Acronyms, Initialisms, and Mineralogical or Common Names of Optical Materials

α -quartz	silicon dioxide (crystal)	SiO_2
$\alpha\beta$ -YAG	alphabet YAG	$\text{Y}_3\text{Al}_5\text{O}_{12}:\text{Ho}^{3+},\text{Er}^{3+},\text{Tm}^{3+}$
AANP	2-adamantylamino-5-nitropyridine	
AB5	ammonium pentaborate	$\text{NH}_4\text{B}_5\text{O}_8 \cdot 4\text{H}_2\text{O}$
ABS	acrylonitrile, butadiene, styrene terpolymer	$[\text{CH}_2\text{CH}(\text{CN})]_x [\text{CH}_2\text{CHCHCH}_2]_y [\text{CH}_2\text{CH}(\text{C}_6\text{H}_5)]_z$
acrylic	polymethyl methacrylate	$[\text{CH}_2\text{C}(\text{CH}_3)(\text{COOCH}_3)]_n$
ADA	ammonium dihydrogen arsenate	$\text{NH}_4\text{H}_2\text{AsO}_4$
AD*A ^(a)	deuterated ammonium dihydrogen arsenate	$\text{NH}_4(\text{H,D})_2\text{AsO}_4$
ADC	allyl diglycol carbonate	$\text{O}(\text{CH}_2\text{CH}_2\text{OCOOCH}_2\text{CHCH}_2)_2$
ADP	ammonium dihydrogen phosphate	$\text{NH}_4\text{H}_2\text{PO}_4$
AD*P	deuterated ammonium dihydrogen phosphate	$\text{NH}_4(\text{H,D})_2\text{PO}_4$
AGS	silver gallium silicate	AgGaS_2
AGSe	silver gallium selenide	AgGaSe_2
AHC	alkali halide crystal	
alexandrite	Cr-doped chrysoberyl	$\text{BeAl}_2\text{O}_4:\text{Cr}$
ALON	aluminum oxynitride	$5\text{AlN}-9\text{Al}_2\text{O}_3$
altaite	lead selenide	PbSe
alumina	aluminum oxide	Al_2O_3
AMTIR	amorphous GeAsSe (glass)	GeAsSe
AN	acrylonitrile	$[\text{CH}_2\text{CH}(\text{CN})]_n$
anatase	titanium dioxide	TiO_2
andalusite	aluminum silicate	Al_2SiO_5
anglesite	lead sulfate	PbSO_4
AODCST	alkyl-oxydicyanostyrene	
apatite	calcium phosphate plus fluorine or chlorine	$\text{Ca}_5(\text{PO}_4)_3(\text{F},\text{OH},\text{Cl})$
APDA	8-(4'-acetylphenyl)-1,4-dioxa-8-azaspiro[4,5]decane	
APO	amorphous polyolefin	$[\text{CH}_2\text{CRR'}]_n$
aragonite	calcium carbonate	CaCO_3
ASN	strontium magnesium aluminate	$\text{SrMgAl}_{11}\text{O}_{19}$
ATCC	allythiourea cadmium chloride	
AZF	alumino-zirco-fluoride (glass)	variable compositions
β'' -alumina	beta double-prime alumina	$\text{Na}_{1+x}\text{Mg}_x\text{Al}_{11-x}\text{O}_{17}$
BANANAS	barium sodium niobate	$\text{Ba}_2\text{NaNb}_5\text{O}_{15}$

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—*continued***

barite	barium sulfate	BaSO ₄
BBB	beta barium borate	$\beta\text{-BaB}_2\text{O}_4$
BBcP	2,5-bis(benzylidene) cycloheptanone	
BBO	barium metaborate	BaB ₂ O ₄
BCBF	barium calcium fluoroborate	BaCaBO ₃ F
BCT	barium calcium titanate	Ba _{0.77} Ca _{0.23} TiO ₃
BEL	lanthanum beryllate	La ₂ Be ₂ O ₅
berlinite	aluminum phosphate	AlPO ₄
beryl	beryllium aluminum silicate	Be ₃ Al ₂ (SiO ₃) ₆
BFAP	barium fluoroapatite	Ba ₅ (PO ₄) ₃ F
BGO	bismuth germanate	Bi ₁₂ GeO ₂₀
BGO	bismuth germanium oxide	Bi ₄ Ge ₃ O ₁₂
BIBO	bismuth metaborate	BiB ₃ O ₆
BIG	bismuth substituted iron garnet	Bi _{3x} Y _{3(1-x)} Fe ₅ O ₁₂
BIGGSe	barium-indium-gallium-germanium selenide glass	variable compositions
BluB	barium lanthanum borate	Ba ₃ La(BO ₃) ₃
BMAG	barium magnesium germinate	Ba ₂ MgGe ₂ O ₇
BNB	m-bromonitrobenzene	Br(C ₆ H ₄ NO ₂)
BOV	barium vanadate	Ba ₅ (VO ₄) ₃
bromellite	beryllium oxide	BeO
bromyrite	silver bromide	AgBr
brookite	titanium dioxide	TiO ₂
BSG	borosilicate glass	variable compositions
BSKNN	barium strontium potassium sodium niobate	Ba _{2-x} Sr _x K _{1-y} Na _y Nb ₅ O ₁₅
BSO	bismuth silicate	Bi ₁₂ SiO ₂₀
BST	barium strontium titanate	Ba _{1-x} Sr _x TiO ₃
BSTN	barium strontium titanium niobate	Ba ₄ Sr ₂ Ti ₂ Nb ₈ O ₃₀
BT	barium titanate	BaTiO ₃
BTO	bismuth titanate	Bi ₁₂ TiO ₂₀
BYF	barium yttrium fluoride	BaY ₂ F ₈
BZMA	benzyl methacrylate	[CH ₂ C(CH ₃)(COOCH ₂ C ₆ H ₅)] _n
CAAP	calcium fluoroarsenite	Ca ₅ (AsO ₄) ₃ F
CAB	cellulose acetate butyrate	(C ₆ H ₇ O ₂)(C ₂ H ₃ O ₂) _x (C ₄ H ₇ O ₂) _y - (OH) _z
CaGB	calcium gadolinium borate	Ca ₃ Gd ₂ (BO ₃) ₄
calcite	calcium carbonate	CaCO ₃

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—*continued***

CALO	cerium aluminate	CeAlO_3
calomel	mercurous chloride	HgCl
CAMGAR	calcium magnesium garnet	$\text{CaY}_2\text{Mg}_2\text{Ge}_3\text{O}_{12}$
CAS	calcium aluminum silicate	$\text{Ca}_2\text{Al}_2\text{SiO}_7$
cassiterite	tin oxide	SnO_2
CAT	cadmium triallyd thiouracil	
CAZGAR	calcium zinc garnet	$\text{CaZn}_2\text{Y}_2\text{Ge}_3\text{O}_{12}$
CBN	cubic boron nitride	BN
CBO	cesium triborate	CsB_3O_5
CBS	carbon black suspension	C + liquid
CDA	cesium dihydrogen arsenate	CsH_2AsO_4
CD*A	deuterated cesium dihydrogen arsenate	$\text{Cs}(\text{H,D})_2\text{AsO}_4$
cerargyrite	silver chloride	AgCl
cerussite	lead carbonate	PbCO_3
CGA	cadmium germanium arsenate	CdGeAs_2
CGS	calcium gallium silicate	$\text{Ca}_2\text{Ga}_2\text{SiO}_7$
ChG	chalcogendie glass	variable compositions
chrysoberyl	beryllium aluminate	BeAl_2O_4
cinnabar	mercury sulfide	HgS
CIS	copper indium diselenide	CuInSe_2
CIGS	copper indium gallium diselenide	$\text{CuIn}_{1-x}\text{Ga}_x\text{Se}_2$
CLBO	cesium lithium triborate	$\text{CsLi}(\text{BO}_3)_3\text{O}$
CMP-M	2-cyano-3-(2-methyl phenyl)-propenoic acid methyl ester	
CMT	cadmium mercury telluride	$\text{Cd}_{1-x}\text{Hg}_x\text{Te}$
CNGG	calcium niobate gallium garnet	$\text{Ca}_3(\text{NbLiGa})_5\text{O}_{12}$
COANP	2-cyclo-octylamino-5-nitropyridine	
colquiriite	lithium calcium aluminum fluoride	LiCaAlF_6
corundum	aluminum oxide, alumina	Al_2O_3
cotunnite	lead chloride	PbCl_2
CPAP	calcium fluoroapatite	$\text{Ca}_5(\text{PO}_4)_3\text{F}$
CPF	calcium fluoroapatite	$\text{Ca}_5(\text{PO}_4)_3\text{F}$
CR 39	allyl diglycol carbonate	$[\text{O}(\text{CH}_2\text{CH}_2\text{OCOOCH}_2\text{CHCH}_2)_2]_n$
cristobalite	silica (allotropic form)	SiO_2
cryolite	sodium fluoroaluminate	Na_3AlF_6
CS-FAP	calcium-strontium fluoroapatite	$(\text{Ca},\text{Sr})_5(\text{PO}_4)_3\text{F}$
CTA	cesium titanyl arsenate	CsTiOAsO_4

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—continued**

CTH:YAG	chromium-thulium-holmium doped YAG	$\text{Y}_3\text{Al}_5\text{O}_{12}:\text{Cr,Tm,Ho}$
CTP	cesium titano phosphnate	CsTiOPO_4
cunyite	calcium germanate	Ca_2GeO_4
CVAP	calcium fluorovandate	$\text{Ca}_5(\text{VO}_4)_3\text{F}$
CWO	cadmium tungstate	CdWO_4
CYB	calcium yttrium borate	$\text{Ca}_3\text{Y}_2(\text{BO}_3)_4$
CYS	calcium yttrium silicate oxyapatite	$\text{CaY}_4(\text{SiO}_4)_3\text{O}$
CZ	cubic zirconia	ZrO_2
CZT	cadmium zinc telluride	$(\text{Cd,Zn})\text{Te}$
DAN	4-(<i>N,N</i> -dimethylamino)-3-nitroacetanilide	
DANS	4-di-methylamino-4'-nitrostilbene	
DAST	dimethylamino- <i>N</i> -methyl-4-stilbazolium-tosylate	
DBNMNA	2,6-dibromo- <i>N</i> -methyl-4-nitroailne	
DCANP	2-docosylamino-5-nitropyridine	
D-CDA	deuterated cesium dihydrogen arsenate	$\text{Cs}(\text{H,D})_2\text{AsO}_4$
DCM	4-dicyanomethylene-2-methyl-6-dimethylamino-4'-nitrostyrene	
DCMNA	2-docosyl-2-methyl-4-nitroaniline	
DEANS'	4-di-ethylamino-4'-nitrostilbene	
DEANST	4-(<i>N,N</i> -diethylamino)- <i>b</i> -nitrostyrene	
diamond	carbon	C
diopside	calcium magnesium silicate	$\text{CaMgSi}_2\text{O}_6$
D-KB5	deuterated potassium pentaborate	$\text{KB}_5\text{O}_8 \cdot 4\text{D}_2\text{O}$
D-KDA	deuterated potassium dihydrogen arsenate	$\text{K}(\text{H,D})_2\text{AsO}_4$
D-KDP	deuterated potassium dihydrogen phosphate	$\text{K}(\text{H,D})_2\text{PO}_4$
D-LAP	deuterated L-arginine phosphate	$[\text{C}_6\text{H}_{7+\text{x}}\text{D}_{8-\text{x}}\text{N}_4\text{O}_2]^+ \cdot \text{H}_2\text{PO}_4 \cdot \text{H}_2\text{O}$
DMC	7-dimethylamino-4-methylcoumarin	$\text{C}_{14}\text{H}_{17}\text{NO}_2$
DMNP	3,5-dimethyl-1-(4 nitrophenylpyrrole	
DMSM	trans-4'-dimethylamino- <i>N</i> -methyl-4-stilbazolium methyl sulfate	
dolomite	calcium magnesium carbonate	$\text{CaMg}(\text{CO}_3)_2$
D-RDA	deuterated rubidium dihydrogen arsenate	$\text{Rb}(\text{H,D})_2\text{AsO}_4$
DTGS	deuterated triglycine sulfate	$[\text{N}(\text{H,D})_2\text{CH}_2\text{COOH}]_3 \cdot \text{H}_2\text{SO}_4$
ECOB	erbium calcium oxyborate	$\text{ErCa}_4(\text{BO}_3)_3\text{O}$
EDDT	ethylene diamine dextrotartrate	$\text{C}_6\text{H}_{14}\text{N}_2\text{O}_6$
elpasolite	potassium sodium aluminum fluoride	K_2NaAlF_6

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—*continued***

emerald	Cr-doped beryl	$\text{Be}_3\text{Al}_2\text{Si}_6\text{O}_{18}:\text{Cr}$
eulytite	bismuth silicate	$\text{Bi}_4\text{Si}_3\text{O}_{12}$
EVA	ethylene-vinyl acetate	$[\text{CH}_2\text{CH}_2]_x-\text{[CH}_2\text{CH}(\text{OCOCH}_3)]_v$
EYAB	erbium yttrium aluminum borate	$\text{YAl}_3(\text{BO}_3)_4:\text{Er}$
FAG	fluoroaluminate glass	variable compositions
FAP	calcium fluoroapatite	$\text{Ca}_5(\text{PO}_4)_3\text{F}$
FEP	perfluorinated ethylene propylene	
fluorapatite	calcium phosphate fluoride	$\text{Ca}_5(\text{PO}_4)_3(\text{F},\text{Cl},\text{OH})$
fluorite	calcium fluoride	CaF_2
forsterite	magnesium silicate	Mg_2SiO_4
fused quartz	silicon dioxide (amorphous) ^(b)	SiO_2
fused silica	silicon dioxide (amorphous)	SiO_2
GAB	gadolinium aluminate borate	$\text{GdAl}_3(\text{BO}_3)_4$
gahnite	zinc aluminate	ZnAl_2O_4
galena	lead sulfide	PbS
garnet	complex family of mineral compositions	$\text{A}_3\text{B}_2\text{C}_3\text{O}_{12}$
GASH	quanidinium aluminate sulfate hexahydrate	$(\text{CN}_3\text{H}_6)\text{Al}(\text{SO}_4)_2 \cdot 6\text{H}_2\text{O}$
g-C	graphite	C
gelenite	calcium aluminium silicate	$\text{Ca}_2\text{Al}_2\text{SiO}_7$
GFG	gallium fluoride garnet	$\text{Na}_3\text{Ga}_2\text{Li}_3\text{F}_{12}$
GGG	gadolinium gallium garnet	$\text{Gd}_3\text{Ga}_5\text{O}_{12}$
GIGG	gadolinium indium gallium garnet	$\text{Gd}_3\text{In}_2\text{Ga}_3\text{O}_{12}$
GLF	gadolinium lithium tetrafluoride	GdLiF_4
GLS	generating luminescence stekla (Russian)	laser glass
GLS	gallium lanthanum sulfide (glass)	$\sim 70\text{GaS}-30\text{La}_2\text{O}_3$
GOS	gadolinium oxysulfide	$\text{Gd}_2\text{O}_2\text{S}$
greenockite	cadmium sulfide	CdS
grossularite	calcium aluminum silicate garnet	$\text{Ca}_3\text{Al}_2\text{Si}_3\text{O}_{12}$
GSAG	gadolinium scandium aluminum garnet	$\text{Gd}_3\text{Sc}_2\text{Al}_3\text{O}_{12}$
GSGG	gadolinium scandium gallium garnet	$\text{Gd}_3(\text{Sc},\text{Ga})_2\text{Ga}_3\text{O}_{12}$
GSO	gadolinium orthosilicate	Gd_2SiO_5
GVO	gadolimium vanadate	GdVO_4
GYAG	gadolinium-yttrium luminum garnet	$(\text{Gd},\text{Y})_3\text{Al}_5\text{O}_{12}$
halite	sodium chloride	NaCl
HAP	high-average-power (laser) glass	variable compositions
hematite	ferric oxide	Fe_2O_3
HMF	heavy metal fluoride (glass)	variable compositions

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—*continued***

HMO	heavy metal oxide (glass)	variable compositions
HPP glass	high-peak-power (laser) glass	variable compositions
hydroxy-	calcium phosphate hydroxide	$\text{Ca}_5(\text{PO}_4)_3\text{OH}$
apatite		
ilmenite	iron titanate	FeTiO_3
iodyrite	silver iodide	$\beta\text{-AgI}$
Irtran 1	magnesium fluoride (polycrystalline)	MgF_2
Irtran 2	zinc sulfide (polycrystalline)	ZnS
Irtran 3	calcium fluoride (polycrystalline)	CaF_2
Irtran 4	zinc selenide (polycrystalline)	ZnSe
Irtran 5	magnesium oxide (polycrystalline)	MgO
Irtran 6	cadmium tellurite (polycrystalline)	CdTe
ITO	indium tin oxide	$\sim 0.9\text{In}_2\text{O}_3 - 0.1\text{SnO}_2$
KABO	potassium aluminum borate	$\text{K}_2\text{Al}_2\text{B}_2\text{O}_7$
KAP	potassium acid phthalate	$\text{C}_8\text{H}_5\text{O}_4\text{K}$
KB5	potassium pentaborate	$\text{KB}_5\text{O}_8 \cdot 4\text{H}_2\text{O}$
KBBF	potassium beryllium borate fluoride	KBeBO_3F_2
KCND	potassium cerium nitrate dihydrate	$\text{K}_2\text{Ce}(\text{NO}_3)_5 \cdot \text{H}_2\text{O}$
KDA	potassium dihydrogen arsenate	KH_2AsO_4
KD*A ^(a)	deuterated potassium dihydrogen arsenate	$\text{K}(\text{H,D})_2\text{AsO}_4$
KDP	potassium dihydrogen phosphate	KH_2PO_4
KD*P ^(a)	deuterated potassium dihydrogen phosphate	$\text{K}(\text{H,D})_2\text{PO}_4$
KGW	potassium gadolinium tungstate	$\text{KGd}(\text{WO}_4)_2$
KLGF	potassium lithium gadolinium fluoride	KLiGdF_5
KLN	potassium lithium nitrate	$\text{K}_3\text{Li}_{2-x}\text{Nb}_{5+x}\text{O}_{15+2x}$
KLND	potassium lanthanum nitrate dihydrate	$\text{K}_2\text{La}(\text{NO}_3)_5 \cdot 2\text{H}_2\text{O}$
KLTN	potassium lithium tantalate niobate	$\text{K}_{1-y}\text{Li}_y\text{Ta}_{1-x}\text{Nb}_x\text{O}_3$
KLYF	potassium lithium yttrium fluoride	KLiYF_4
KN	potassium niobate	KNbO_3
KNB	potassium niobium borate	KNbB_2O_6
KNLF	potassium neodymium lithium fluoride	$\text{K}_5\text{NdLi}_2\text{F}_{10}$
KNSBN	potassium sodium strontium barium niobate	$(\text{K}_x\text{Na}_{1-x})_{0.4}(\text{Sr}_y\text{Ba}_{1-y})_{0.8}\text{Nb}_2\text{O}_6$
KRS-5	thallium bromoiodide	$\text{Tl}(\text{Br}_{1-x},\text{I}_x)$
KRS-6	thallium chlorobromide	$\text{Tl}(\text{Cl}_{1-x},\text{Br}_x)$
KRTA	potassium-rubidium titanyl arsenate	$(\text{K,Rb})\text{TiOAsO}_4$
KSAG	lutetium scandium aluminum garnet	$\text{Lu}_3\text{Cs}_2\text{Al}_5\text{O}_{12}$
KTA	potassium titanyl arsenate	KTiOAsO_4

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—*continued***

KTN	potassium tantalate niobate	$\text{KTa}_{1-x}\text{Nb}_x\text{O}_3$
KTP	potassium titanyl phosphate	KTiOPO_4
KTP-GTR	potassium titanyl phosphate-greytrack resistant	KTiOPO_4
kyanite	aluminum silicate	Al_2SiO_5
KYF	potassium yttrium fluoride	KYF_4
LABO	lanthanum metaborate	LaB_3O_6
LAP	L-arginine phosphate	$[\text{C}_6\text{H}_{15}\text{N}_4\text{O}_2]^+ \cdot \text{H}_2\text{PO}_4^- \cdot \text{H}_2\text{O}$
LB	Langmuir–Blodgett (film)	various compositions
LBG	lanthanum boron germanium oxide	LaBGeO_5
LBO	lithium triborate	LiB_3O_5
LC	liquid crystal	various compositions
Lexan	polycarbonate plastic	$[\text{OCOOC}_6\text{H}_4\text{C}(\text{CH}_3)_2\text{C}_6\text{H}_4]_n$
LFM	lithium formate monohydrate	$\text{LiHCO}_2 \cdot \text{H}_2\text{O}$
LGO	lithium germanate	Li_2GeO_5
LGS	lanthanum gallium silicate	$\text{La}_3\text{Ga}_5\text{SiO}_{14}$
LI	lithium iodate	LiIO_3
LiBAF	lithium barium aluminum fluoride	LiBaAlF_6
LiCAF	lithium calcium aluminum fluoride	LiCaAlF_6
LiChrom	lithium strontium chromium fluoride	LiSrCrF_6
LiSAF	lithium strontium aluminum fluoride	LiSrAlF_6
LiSGaF	lithium strontium gallium fluoride	LiSrGaF_6
litharge	lead oxide	PbO
LLF	Lutetium lithium fluoride	LuLiF_4
LLGG	lanthanum lutetium gallium garnet	$(\text{La},\text{Lu})_3(\text{Lu},\text{Ga})_2\text{Ga}_3\text{O}_{12}$
LMA	lanthanum magnesium hexaluminate	$\text{LaMgAl}_{11}\text{O}_{19}$
LN	lithium niobate	LiNbO_3
LNA	lanthanum neodymium hexaluminate	$\text{LaMgAl}_{11}\text{O}_{19}:\text{Nd}$
LNP	lithium neodymium tetraphosphate	$\text{LiNdP}_4\text{O}_{12}$
LNPP	lanthum neodymium pentaphosphate	$\text{La}_{1-x}\text{Nd}_x\text{P}_5\text{O}_{14}$
LOP	lutetium orthophosphate	LuPO_4
LSB	lanthanum scandium borate	$\text{LaSc}_3(\text{BO}_3)_4$
LSO	lutetium silicon oxide (orthosilicate)	Lu_2SiO_5
LT	lithium tantalate	LiTaO_3
LuAG	lutetium aluminum garnet	$\text{Lu}_3\text{Al}_5\text{O}_{12}$
Lucalox	alumina (polycrystalline)	Al_2O_3
magnesite	magnesium carbonate	MgCO_3

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—continued**

magnetite	iron oxide	Fe_3O_4
MAP	methyl-(2,4-dinitrophenyl)-aminopropanoate	$\text{C}_{10}\text{H}_{12}\text{N}_3\text{O}_6$
massicot	lead oxide	PbO
MBANP	2-(a-methyl benzylamino)-5-nitropyridine	
MBBF	alkali metal beryllium borate fluoride	$(\text{Na},\text{K})\text{BeBO}_3\text{F}_2$
MCT	mercury cadmium telluride	HgCdTe
MEH-PPV	poly(2-methoxy-5-(2'-ethyl-hexyloxy)-1,4-phenylene vinylene)	
Mg:LN	MgO-doped lithium niobate	$\text{Mg}:\text{LiNbO}_3$
Mg:SLN	MgO-doped stoichiometric lithium niobate	$\text{Mg}:\text{LiNbO}_3$
mica	potassium aluminosilicate	$\text{KAl}_3\text{Si}_3\text{O}_{10} \cdot (\text{OH})_2$
MMA	methylmethacrylate	$\text{CH}_2\text{C}(\text{CH}_3)(\text{COOCH}_3)$
MMONS	3-methyl-4-methoxy-4'-nitrostilbene	
MNA	2 methyl-4-nitro-aniline	$\text{CH}_3\text{NH}_2\text{NO}_2\text{C}_6\text{H}_4$
MND	4-methoxy-4'-nitro-diphenyl-diacylene-	
MNMA	2-methyl-4-nitro-N-methylaniline	
MNT	4-methyl-4'-nitrolan	
monazite	rare earth phosphate	(rare earth) PO_4
MPMMA	modified polymethylmethacrylate	
MSO	magnesium silicate	Mg_2SiO_4
MTTNPH	5-methylthio-thiophenecarboxaldehyde-4-nitrophenyl-hydrazone	
mullite	aluminum silicate	$\text{Al}_6\text{Si}_2\text{O}_{13}$
NAB	neodymium aluminum borate	$\text{NdAl}_3(\text{BO}_3)_4$
nantokite	copper chloride	CuCl
NAS	methyl methacrylate styrene copolymer	$[\text{CH}_2\text{C}(\text{CH}_3)(\text{COOCH}_3)]_x \cdot [\text{CH}_2\text{CH}(\text{C}_6\text{H}_5)]_y$
NBD-Cl	7-chloro-4'-nitrobenzo-2-oxa-1,3-diazole	
NdPP	neodymium pentaphosphate	$\text{NdP}_5\text{O}_{14}$
NGAB	neodymium gadolinium aluminum borate	$\text{Nd}_x\text{Gd}_{1-x}\text{Al}_3(\text{BO}_3)_4$
NMBA	4-nitro-4'-methyl-benzylidene aniline	
NPP	<i>N</i> -4-nitrophenyl-(L,S)-prolinol	
NPP	neodymium pentaphosphate	$\text{NdP}_5\text{O}_{14}$
NPPA	<i>N</i> -(4-nitro-2-pyridinyl)-phenylalaninol	
NYAB	neodymium yttrium aluminum borate	$\text{Nd}_x\text{Y}_{1-x}\text{Al}_3(\text{BO}_3)_4$
olivine	magnesium iron silicate	$(\text{Mg},\text{Fe})_2\text{SiO}_4$
ORMOSIL	organic modified silicate	SiO_2

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—continued**

orpiment	arsenic trisulfide	As_2S_3
PAMS	poly(alpha-methylstyrene)	
paratelluride	tellurium oxide	TeO_2
PBDG	poly(g-benzl-D-glutamate)	
PBLG	poly(g-benzl-L-glutamate)	
PBN	lead barium niobate	$\text{Pb}_{1-x}\text{Ba}_x\text{Nb}_2\text{O}_6$
PBSP	photonic band-gap structure	variable compositions
PBT	polybenzothiazole	$[\text{C}_6\text{H}_3\text{NSC}]_n$
PBZT	poly(p-phenylene benzo bis thiozole)	
PCS	plastic clad silica	
PDA	polydiacetylene	$[\text{C}(\text{R})\text{CCC}(\text{R})]_n$
PDBT	poly(3,4-dibutoxythiophene)	
PDHG	poly(di- <i>n</i> -hexylgermane)	
PDHS	poly(di- <i>n</i> -hexylsilane)	
PDLC	polymer dispersed liquid crystal	variable compositions
periclase	magnesium oxide	MgO
perovskite	calcium titanate	CaTiO_3
PET	pentaery-thritol	$[\text{OCH}_2\text{CH}_2\text{OOCC}_6\text{H}_4\text{CO}]_n$
PGO	lean germanium oxide	$\text{Pb}_5\text{Ge}_3\text{O}_{11}$
plattnerite	lead oxide	PbO
PLZT	lead lanthanum zirconium titanate	$\text{PbLa}(\text{Zr,Ti})\text{O}_3$
PMMA	polymethylmethacrylate	
PMPS	poly(methyl phenyl silane)	
PNP	2-(<i>N</i> -prolinol)-5-nitropyridine	
POF	plastic optical fiber	variable compositions
poly-	polydiacetylene poly-[5,7-dodecadiyn-2,12- diol-bis(<i>n</i> -butoxycarbonyl-methyl-urethane]	
4BCMU		
POM	3-methyl-4-nitropyridine-1-oxide	$\text{NO}_2 \cdot \text{CH}_3\text{NOC}_5\text{H}_4$
POMT	poly(3-octyloxy,4-methyl thiophene)	
PSC	porous silicon carbide	SiC
powellite	calcium molybdate	CaMoO_4
PPKTP	periodically poled potassium titanyl phosphate	KTiOPO_4
PPLN	periodically poled lithium niobate	LiNbO_3
PPLT	periodically poled lithium tantalate	LiTaO_3
PPNA	poly- <i>p</i> -nitroaniline	
PPRTA	periodically poled rubidium titanyl arsenate	RbTiOAsO_4
PPV	poly(<i>p</i> -phenylene vinylene)	

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—continued**

proustite	silver arsenic sulfide	Ag_3AsS_3
PrPP	praseodymium pentaphosphate	$\text{PrP}_5\text{O}_{14}$
PS	polystyrene	$[\text{CH}_2\text{CH}(\text{C}_6\text{H}_5)]_n$
PSG	porous silica glass	SiO_2
PSZ	partially stabilized zirconia	$\text{ZrO}_2 \cdot (\text{Mg,Ca,Y})$
PT	polythiophene	
PTB	lead tetraborate	PbB_4O_7
PTG	poly(3-hexylthiophene)	
PTOPT	poly-[3-(4-octylphenyl)]-2,2'-bithiophene	
PTS	poly-bis-(<i>p</i> -toluene sulfonate)-2,4-hexazine -1,6-diole	
PTV	poly(2,5-thienyl vinylene)	
PU	polyurethane	$[\text{OCONHRNHCOOR}']_n$
pucherite	bismuth vanadate	BiVO_4
PV	polyvinylxylene	$[\text{CH}_2\text{CH}(\text{CH}_2\text{C}_6\text{H}_4\text{CH}_3)]_n$
PVA	polyvinyl alcohol	
PVF ₂	polyvinylidene fluoride	
PVP	polyvinyl-pyrrolidimone	
pyrite	iron sulfide	FeS_2
PZT	lead zirconium titanate	$\text{Pb}(\text{Zr,Ti})\text{O}_3$
QC	quantum crystallite (quantum dot)	
quartz	silicon dioxide (crystal)	SiO_2
RAP	rubidium acid phthalate	$\text{C}_8\text{H}_5\text{O}_4\text{Rb}$
RB5	rubidium pentaborate	$\text{RbB}_5\text{O}_8 \cdot 4\text{H}_2\text{O}$
RbAP	rubidim acid phthalate	$\text{CO}_2\text{HC}_6\text{H}_4\text{CO}_2\text{Rb}$
RDA	rubidium dihydrogen arsenate	RbH_2ASO_4
RD*A	deuterated rubidium dihydrogen arsenate	$\text{Rb}(\text{H,D})_2\text{AsO}_4$
RDP	rubidium dihydrogen phosphate	RbH_2PO_4
RD*P	deuterated rubidium dihydrogen phosphate	$\text{Rb}(\text{H,D})_2\text{PO}_4$
RGB	rubidium gadolinium bromide	RbGd_2Br_7
rochelle salt	sodium potassium tartrate	$\text{NaKC}_4\text{H}_4\text{O}_6 \cdot 4\text{H}_2\text{O}$
rocksalt	sodium chloride	NaCl
RTA	rubidium titanyl arsenate	RbTiOAsO_4
RTP	rubidium titanyl phosphate	RbTiOPO_4
ruby	Cr-doped corundum (sapphire)	$\text{Al}_2\text{O}_3:\text{Cr}$
rutile	titanium dioxide	TiO_2
SAN	styrene acrylonitrile copolymer	$[\text{CH}_2\text{CH}(\text{C}_6\text{H}_5)]_x - [\text{CH}_2\text{CH}(\text{CN})]_v$

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—*continued***

sapphire	aluminum oxide	Al_2O_3
sapphire	aluminum oxide (gemstone)	$\text{Al}_2\text{O}_3:\text{Ti},\text{Fe}$
SBA	sodium- β " alumina	$\text{Na}_{1+x}\text{Mg}_x\text{Al}_{11-x}\text{O}_{17}$
SBBO	strontium beryllium borate	$\text{Sr}_2\text{Be}_2\text{B}_2\text{O}_7$
SBN	strontium barium niobate	$\text{Sr}_{1-x}\text{Ba}_x\text{Nb}_2\text{O}_6$
SCAB	scandium aluminum beryllate	ScAlBeO_4
scheelite	calcium tungstate	CaWO_4
SDG	semiconductor-doped glass	variable compositions
sellaité	magnesium fluoride	MgF_2
S–FAP	strontium fluoroapatite	$\text{Sr}_5(\text{PO}_4)_3\text{F}$
SGGM	strontium gadolinium gallium melilite	SrGdGaO_7
silica	silicon dioxide	SiO_2
SIMOX	separation by implanation of oxygen (silicon-on-insulator material)	
SLG	strontium lanthanum gallate	$\text{SrLaGa}_3\text{O}_7$
SMA	polystyrene co-maleic anhydride	$[\text{CH}_2\text{CH}(\text{C}_6\text{H}_5)\text{CH}(\text{COOCO})\text{CH}]_n$
SMMA	polystyrene co-methyl methacrylate	$[\text{CH}_2\text{C}(\text{CH}_3)(\text{COOCH}_3)]_{x-}$ $[\text{CH}_2\text{CH}(\text{C}_6\text{H}_5)]_y$
SNA	strontium aluminate	$\text{SrAl}_{12}\text{O}_{19}$
SOAP	calcium silico-oxyapatite	$\text{CaY}_4(\text{SiO}_4)_3\text{O}$
SOI	silicon-on-insulator (material)	
SOS	silicon (Si) epitaxial film on sapphire substrate	$\text{Si}/\text{Al}_2\text{O}_3$
SPAP	strontium fluoroapatite	$\text{Sr}_5(\text{PO}_4)_3\text{F}$
SPF	strontium fluoroapatite	$\text{Sr}_5(\text{PO}_4)_3\text{F}$
spodumene	lithium aluminum silicate	$\text{LiAlSi}_2\text{O}_6$
sphalerite	zinc sulfide (cubic)	ZnS
STRAP	strontium fluoroapatite	$\text{Sr}_5(\text{PO}_4)_3\text{F}$
sphalerite	zinc sulfide	ZnS
spinel	magnesium aluminate	MgAl_2O_4
spodumene	lithium aluminum silicate	$\text{LiAlSi}_2\text{O}_6$
SrYBO	strontium yttrium borate	$\text{Sr}_3\text{Y}(\text{BO}_3)_3$
styrene	polystyrene	
STZO	strontium titanate zironate	$\sim 0.8\text{SrTiO}_3 - 0.2\text{ZrO}_2$
S-VAP	strontium vanadium fluoroapatite	$\text{Sr}_5(\text{VO}_4)_3\text{F}$
sylvite	potassium chloride	KCl
SYS	strontium yttrium silicate oxyapatite	$\text{SrY}_4(\text{SiO}_4)_3\text{O}$
T-12	barium fluoride-calcium fluoride	$\text{BaF}_2\text{-CaF}_2$

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—*continued***

TAS	thallium arsenic selenide	Tl_3AsSe_3
TBPC	tetrakis (tert-butyl) phthalocyanine	
TCDMA	tricyclodecyl co-methacrylate	$[\text{CH}_2\text{C}(\text{CH}_3)(\text{COOC}_{10}\text{H}_{15})]_n$
TCO	transparent conductive oxide	e.g., ITO
TCNQ	7,7,8,8-tetracyanoquinodimethane	
TEOS	tetraethyl orthosilicate	$(\text{C}_2\text{H}_5\text{O})_4\text{Si}$
TeX	tellurium halide glass	variable composition
TGG	terbium gallium garnet	$\text{Tb}_3\text{Ga}_5\text{O}_{12}$
TGS	triglycine sulfate	$(\text{NH}_2\text{CH}_2\text{COOH})_3 \cdot \text{H}_2\text{SO}_4$
TGSe	triglycine selenate	
THAM-P	tris-hydroxymethylaminomethane-phosphate	
THAM-S	tris-hydroxymethylaminomethane-sulfate	
TiOPc	titanyl phthalocyanine	
Ti:S	Ti-doped corundum/alumina	$\text{Al}_2\text{O}_3:\text{Ti}$
Ti sapphire	Ti-doped corundum/alumina	$\text{Al}_2\text{O}_3:\text{Ti}$
TIAP	thallium acid phthalate	$\text{C}_8\text{H}_5\text{O}_4\text{Tl}$
TMOS	tetramethyloxysilane	$\text{Si}(\text{OCH}_3)_4$
TOC	transparent optical ceramic	various compositions
topaz	aluminum silicate fluoride hydroxide	$\text{Al}_2\text{SiO}_4(\text{F},\text{OH})_2$
tourmaline	sodium aluminum borosilicate	$\text{Na}_3\text{Al}_6\text{Si}_6\text{O}_{18}(\text{BO}_3)_2(\text{OH},\text{F})_4$
TPX	methyl pentene polymer	
tridymite	silicon dioxide	SiO_2
TSCCC	thiosemicarbazide cadmium chloride monohydrate	
tysonite	lanthanum trifluoride	LaF_3
urea	urea crystal	$\text{CH}_4\text{N}_2\text{O}$
VAC	vinyl acetate	$[\text{CH}_2\text{CH}(\text{OCOCH}_3)]_n$
VB	vinyl benzoate	
villiaumite	sodium fluoride	NaF
VOPc	vanadyl phthalocyanine	
VPAC	vinyl phenyl acetate	$[\text{CH}_2\text{CH}(\text{OCOC}_6\text{H}_5)]_n$
VTE LN	vapor-transport-equilibrated lithium niobate	LiNbO_3
weberite	sodium magnesium aluminum fluoride	NaMgAlF_7
willemite	zinc silicate	ZnSiO_4
wollastonite	calcium silicate	CaSiO_3
wulfenite	lead molybdate	PbMoO_4
wurtzite	zinc sulfide (hexagonal)	ZnS

**Abbreviations, Acronyms, Initialisms, and Mineralogical
or Common Names of Optical Materials—*continued***

xenotime	yttrium phosphate	YPO ₄
YAB	yttrium aluminum borate	YAl ₃ (BO ₃) ₄
YAG	yttrium aluminum garnet ^(c)	Y ₃ Al ₅ O ₁₂
YAlG	yttrium aluminum garnet	Y ₃ Al ₅ O ₁₂
valliaumite	sodium fluoride	NaF
yablonovite	photonic bandgap crystal	variant of the diamond structure
YAlO	yttrium orthoaluminate	YAlO ₃
YAP	yttrium aluminum perovskite	YAlO ₃
YAM	yttrium aluminum monoclinic	Y ₄ Al ₂ O ₉
YBF	yttrium barium fluoride	Y ₂ BaF ₈
YGG	yttrium gallium garnet	Y ₃ Ga ₅ O ₁₂
YGO	yttrium gadolinium oxide	(Y,Gd) ₂ O ₃
YGOB	yttrium gadolinium borate	CaY ₄ (BO ₃) ₃ O
YIG	yttrium iron garnet	Y ₃ Fe ₅ O ₁₂
YIGG	yttrium indium gallium gadolinium garnet	Y ₃ (In,Ga) ₂ Gd ₃ O ₁₂
YLF	yttrium lithium fluoride	YLiF ₄ (LiYF ₄)
YOP	yttrium orthophosphate	YPO ₄
YOS	yttrium orthosilicate	Y ₂ SiO ₅
YSAG	yttrium scandium aluminum garnet	Y ₃ Sc ₂ Al ₃ O ₁₂
YSB	yttrium scandium borate	YSc ₃ (BO ₃) ₄
YSGG	yttrium scandium gallium garnet	Y ₃ Sc ₂ Ga ₃ O ₁₂
YSO	yttrium silicon oxide (orthosilicate)	Y ₂ SiO ₅
YSZ	yttria stabilized zirconia	ZrO ₂ :Y ₂ O ₃
yttralox	yttrium oxide (polycrystalline)	Y ₂ O ₃
Zerodur	glass ceramic	SiO ₂ —Al ₂ O ₃ + . . .
zinc blende	zinc sulfide (cubic)	ZnS
zincite	zinc oxide	ZnO
ZTS	zinc tris(thiourea) sulfate	Zn[CS(NH ₂) ₂] ₃ SO ₄
zircon	zirconium silicate	ZrSiO ₄
zirconia	zirconium dioxide	ZrO ₂

(a) When crystals are grown in heavy water (D₂O) solution, hydrogen is replaced in part or totally by deuterium. Such crystals are designated by a prefix d- or D-, or by an asterisk, e.g., d-CDA and CD*A.

(b) Produced from natural quartz.

(c) Nd-doped YAG lasers are frequently simply called YAG lasers.

APPENDIX III

Abbreviations for Methods of Preparing Optical Materials and Thin Films

ACR	—	accelerated crucible rotation (flux growth)
ACRT	—	accelerated crucible rotation technique
ALE	—	atomic layer epitaxy
ALL MBE	—	atomic layer-by-layer molecular beam epitaxy
APCVD	—	accelerated plasma chemical vapor deposition
APD	—	accelerated plasma deposition
APE	—	annealed proton exchange
ARE	—	activated reactive evaporation
BARE	—	biased activated reactive evaporation
BE	—	bond and etch (waveguide structure)
Br	—	Bridgman (growth)
CAIBE	—	chemically-assisted ion beam epitaxy
CAMBE	—	chemically-assisted molecular beam epitaxy
CBE	—	chemical beam epitaxy
CLD	—	chemical liquid deposition
CVD	—	chemical vapor deposition
CVT	—	chemical vapor transport
Cz	—	Czochralski (growth)
DIBD	—	dual ion beam deposition
DIBS	—	dual ion beam sputtering
DMILC	—	double-metal-induced lateral crystallization
DWB	—	direct wafer bonding (waveguide structure)
ED	—	electrodeposition
EDFF	—	edge-defined film-fed (growth)
EFG	—	edge-defined film-fed growth
FHD	—	flame hydrolysis deposition
FIB	—	focused ion beam (sputtering)
FICZ	—	flat interface Czochralski (growth)
FZ	—	float zone
GD	—	glow discharge
GILD	—	gas immersion laser doping
GS-MBE	—	gas-source molecular beam epitaxy
HBr	—	horizontal Bridgman (growth)
HCD	—	hollow cathode discharge deposition
HEM	—	heat exchange method
HGF	—	horizontal gradient freeze
HIP	—	hot isostatic pressing
HPBr	—	high-pressure Bridgman (growth)
HPVB	—	high-pressure vertical Bridgman

**Abbreviations for Methods of Preparing
Optical Materials and Thin Films—*continued***

HTS	—	high temperature solution
HTSG	—	high temperature solution growth
HVPE	—	hydride vapor-phase epitaxy
IAD	—	ion assisted deposition
IAD	—	ion beam assisted deposition
IBD	—	ion beam deposition
IBE	—	ion beam etching
IBED	—	ion beam enhanced deposition
IBS	—	ion beam sputtering
ICB	—	ion cluster beam
ICBD	—	ionized cluster beam deposition
ISZ-THM	—	increasing solution zone travelling heater method
IVD	—	inside vapor deposition
IVDO	—	inside vapor deposition oxidation
JVD	—	jet vapor deposition
LAD	—	laser aerosol deposition
LAD	—	laser-assisted deposition
LB	—	Langmuir-Blodgett (film technique)
LBD	—	Langmuir-Blodgett deposition
LCVD	—	laser-induced chemical vapor deposition
LEC	—	liquid-encapsulated Czochralski (growth)
LECV	—	liquid-encapsulated chemical vapor deposition
LEVGF	—	liquid-encapsulated vertical gradient freeze
LHPG	—	laser heated pedestal growth
LPCVD	—	liquid-phase chemical vapor deposition
LPCVD	—	low-pressure chemical vapor deposition
LPE	—	liquid phase epitaxy
LP-MOVPE	—	low-pressure metal-organic vapor-phase epitaxy
LTE	—	local thermal equilibrium
LTGCz	—	low-thermal gradient Czochralski (growth)
LT-MBE	—	low-temperature molecular beam epitaxy
LVRIP	—	low-voltage reactive ion plating
MBD	—	molecular beam deposition
MBE	—	molecular beam epitaxy
MCVD	—	modified chemical vapor deposition
MIC	—	metal-induced crystallization
MILC	—	metal-induced lateral crystallization
MOCVD	—	metal-organic chemical vapor deposition
MOMBE	—	metal-organic molecular beam epitaxy
MOVD	—	modified vapor deposition
MOVPE	—	metal-organic vapor-phase epitaxy

**Abbreviations for Methods of Preparing
Optical Materials and Thin Films—*continued***

MPD	—	microwave plasma deposition
NSP	—	neutral solution processing
OMCVD	—	organometallic chemical vapor deposition
OMMBE	—	organometallic molecular beam epitaxy
OMVPE	—	organometallic vapor-phase epitaxy
OVD	—	outside vapor deposition
OVPO	—	outside vapor phase
PCVD	—	plasma chemical vapor deposition
PACVD	—	plasma-assisted chemical vapor deposition
PAE	—	plasma assisted epitaxy
PCVD	—	plasma chemical vapor deposition
PE	—	plasma etching
PECVD	—	plasma-enhanced chemical vapor deposition
PIBD	—	primary ion beam deposition
PICVD	—	plasma ionization chemical vapor deposition
PLD	—	physical liquid deposition
PLD	—	pulsed laser deposition
PVD	—	physical vapor deposition
PVT	—	physical vapor transport
RAP	—	reactive atmosphere processing
RE	—	reactive evaporation
RIBE	—	reactive ion beam etching
RICBD	—	reactive ionized cluster beam deposition
RIE	—	reactive ion etching
RS	—	reactive sputtering
SAM	—	self-assembled monolayer
SIBD	—	secondary ion beam deposition
SOL GEL	—	solution gelation (processing)
SPCVD	—	surface-plasma chemical vapor deposition
SPE	—	solid phase epitaxy
SPVT	—	seeded physical vapor transport
SSE	—	solid-state epitaxy
SSMOCVD	—	solid source metal-organic chemical vapor deposition
SSVG	—	self-selected vapor growth
St	—	Stockbarger (growth)
TGZM	—	temperature-gradient zone melting
THM	—	travelling heater method
TNFC	—	top nucleated floating crystal (growth)
TSFZ	—	travelling solvent float zone
TSM	—	travelling solvent method
TSSG	—	top-seeded solution growth

**Abbreviations for Methods of Preparing
Optical Materials and Thin Films—*continued***

UHV-CVD	—	ultra-high-vacuum chemical vapor deposition
VAD	—	vapor-phase axial deposition
VBr	—	vertical Bridgman (growth)
VD	—	vacuum deposition
VGD	—	vapor gel deposition
VGF	—	vertical gradient freeze
VLPC	—	very-low-pressure chemical
VD	—	vapor deposition
VLS	—	vapor-liquid-solid
VMS	—	vapor melt solid
VPE	—	vapor-phase epitaxy
VPG	—	vapor-phase growth
VPO	—	vapor-phase oxidation
VT	—	vapor transport
VTE	—	vapor transport equilibrated
ZM	—	zone melted
ZMR	—	zone melting recrystallization

APPENDIX IV

Fundamental Physical Constants

Quantity	Symbol	Value
speed of light in vacuum	c	299 792 458 m/s
permeability of vacuum, $4\pi \times 10^{-7}$	μ_0	$1.256 637 061 4 \times 10^{-6} \text{ N/A}^2$
permittivity of vacuum, $1/\mu_0 c^2$	ϵ_0	$8.854 187 817 \times 10^{-12} \text{ F/m}$
Planck constant	h	$6.626 075 5 \times 10^{-34} \text{ J s}$
elementary charge	e	$1.602 177 33 \times 10^{-19} \text{ C}$
magnetic flux quantum, $h/2e$	Φ_0	$2.067 834 61 \times 10^{-15} \text{ Wb}$
electron mass	m_e	$9.109 389 7 \times 10^{-31} \text{ kg}$
proton mass	m_p	$1.672 623 1 \times 10^{-27} \text{ kg}$
fine structure constant, $\mu_0 ce^2/2h$	α	$7.297 353 08 \times 10^{-3}$
inverse fine-structure constant	$1/\alpha$	137.035 989 5
Rydberg constant, $m_e c \alpha^2 / 2h$	R_y, R_∞	10 973 731.534 m ⁻¹
Bohr radius, $\alpha/4\pi R_\infty$	a_0	$0.529 177 249 \times 10^{-10} \text{ m}$
Hartree energy, $e^2/4\pi\epsilon_0 a_0 = 2R_\infty hc$ in eV, E_h/e	E_h	$4.359 748 2 \times 10^{-18} \text{ J}$ 27.211 396 1 eV
Compton wavelength, $h/m_e c$	λ_C	$2.426 310 58 \times 10^{-12} \text{ m}$
classical electron radius, $\alpha^2 a_0$	r_e	$2.817 940 92 \times 10^{-15} \text{ m}$
Bohr magneton, $eh/4\pi m_e$	μ_B	$9.274 015 4 \times 10^{-24} \text{ J/T}$
nuclear magneton, $eh/4\pi m_p$	μ_N	$5.050 786 6 \times 10^{-27} \text{ J/T}$
electron magnetic moment	μ_e	$9.284 770 1 \times 10^{-24} \text{ J/T}$
magnetic moment anomaly, $\mu_e/\mu_B - 1$	a_e	$1.159 653 193 \times 10^{-3}$
electron g factor, $2(1 + a_e)$	g_e	2.002 319 304 386
proton gyromagnetic ratio	γ_p	$2.675 221 28 \times 10^8 \text{ s}^{-1}\text{T}^{-1}$
Avogadro constant	N_A	$6.022 136 7 \times 10^{23} \text{ mol}^{-1}$
Boltzmann constant, R/N_A	k	$1.380 658 \times 10^{-23} \text{ J/K}$
Faraday constant, $N_A e$	F	96 485.309 C/mol
molar gas constant	R	8.314 510 J/mol K
Stefan-Boltzmann constant	s	$5.670 51 \times 10^{-8} \text{ W/m}^2 \text{ K}^4$

References:

- Cohen, E. R., and Taylor, B. N., The 1986 adjustment of the fundamental physical constants, *Rev. Mod. Phys.* 59, 1121 (1987).
 Taylor, B. N., and Cohen, E. R., Recommended values of the fundamental physical constants: a status report, *J. Res. Natl. Inst. Stand. Technol.* 95, 497 (1990).

For updated values see NIST Web site: physics.nist.gov/constants.

APPENDIX V

Units and Conversion Factors

Energy $E(\text{eV})$

Multiply $E(\text{eV})$ by 1.6022×10^{-19} to convert to $E(\text{J})$

Multiply $E(\text{eV})$ by 8065.5 to convert to $E(\text{cm}^{-1})$

$$\text{Photon energy (eV)} = 1.2398/\lambda_{\text{vacuum}}(\mu\text{m})$$

Linear absorption coefficient $\alpha(\text{cm}^{-1}) = (4\pi n \times 10^4/\lambda)k$, where n is the index of refraction of the material, the wavelength λ is in microns (μm), and k is the complex index of refraction.

Two-photon absorption coefficient $\beta(\text{m/W})$

$\beta(\text{m/W}) = (N/E)\sigma^2$, where N is the number density of molecules per cm^3 , E is the photon energy (J), σ^2 is the two-photon absorption cross section ($\text{cm}^4 \text{ s/molecule}$). Multiply $\beta(\text{m/W})$ by 10^{-9} to convert to the CGS system (cal/cm s/erg)

Nonlinear index of refraction $\gamma(\text{m}^2/\text{W})$

Multiply $\gamma(\text{m}^2/\text{W})$ by $2.386 \times 10^6 n$ to convert to the esu system, where n is the index of refraction of the material.

$$n_2[\text{cm}^3/\text{erg}] = 238.7n \gamma[\text{cm}^2/\text{W}]$$

Linear electrooptic coefficient $r(\text{m/V})$

Multiply $r(\text{m/V})$ by 2.9979×10^4 to convert to the CGS system (cm/statvolt)

Kerr constant $B(10^{-16}\text{m V}^2)$

Multiply $B(10^{-16}\text{m V}^2)$ by 8.988×10^6 to convert to the CGS system (cm/statvolt²)

Verdet constant $V(\text{rad/T m})$

Multiply $V(\text{rad/T m})$ by 3.438×10^{-3} to convert to the CGS system (min/Oe cm)

Temperature $T(\text{K})$

$$\text{Temperature } T(\text{ }^\circ\text{C}) = T(\text{K}) - 273.15$$

Specific heat capacity $c_p(\text{J/kg K})$

Multiply $c_p(\text{J/kg K})$ by 2.388×10^{-4} to convert to the CGS system (cal/g K)

Thermal conductivity $\kappa(\text{W/m K})$

Multiply $\kappa(\text{W/m K})$ by 2.388×10^{-3} to convert to the CGS system (cal/cm s K)

Hardness (Knoop or Vickers)

$$1 \text{ kgf/mm}^2 = 9.8066 \text{ N/mm}^2$$

Pressure, mechanical stress (Pa)

$$1 \text{ Pa} = 1 \text{ N/m}^2 = 1 \text{ kg/m s}^2$$

$$10^5 \text{ Pa} = 1 \text{ bar}$$

$$1 \text{ psi} = 6.9 \times 10^3 \text{ Pa}$$