

Open Die Shaped Forgings for Use in the Petroleum and Natural Gas Industry

API SPECIFICATION 20B
FIRST EDITION, APRIL 2013

ERRATA: DECEMBER 2013



AMERICAN PETROLEUM INSTITUTE

Special Notes

API publications necessarily address problems of a general nature. With respect to particular circumstances, local, state, and federal laws and regulations should be reviewed.

Neither API nor any of API's employees, subcontractors, consultants, committees, or other assignees make any warranty or representation, either express or implied, with respect to the accuracy, completeness, or usefulness of the information contained herein, or assume any liability or responsibility for any use, or the results of such use, of any information or process disclosed in this publication. Neither API nor any of API's employees, subcontractors, consultants, or other assignees represent that use of this publication would not infringe upon privately owned rights.

API publications may be used by anyone desiring to do so. Every effort has been made by the Institute to assure the accuracy and reliability of the data contained in them; however, the Institute makes no representation, warranty, or guarantee in connection with this publication and hereby expressly disclaims any liability or responsibility for loss or damage resulting from its use or for the violation of any authorities having jurisdiction with which this publication may conflict.

API publications are published to facilitate the broad availability of proven, sound engineering and operating practices. These publications are not intended to obviate the need for applying sound engineering judgment regarding when and where these publications should be utilized. The formulation and publication of API publications is not intended in any way to inhibit anyone from using any other practices.

Any manufacturer marking equipment or materials in conformance with the marking requirements of an API standard is solely responsible for complying with all the applicable requirements of that standard. API does not represent, warrant, or guarantee that such products do in fact conform to the applicable API standard.

All rights reserved. No part of this work may be reproduced, translated, stored in a retrieval system, or transmitted by any means, electronic, mechanical, photocopying, recording, or otherwise, without prior written permission from the publisher. Contact the Publisher, API Publishing Services, 1220 L Street, NW, Washington, DC 20005.

Copyright © 2013 American Petroleum Institute

Foreword

Nothing contained in any API publication is to be construed as granting any right, by implication or otherwise, for the manufacture, sale, or use of any method, apparatus, or product covered by letters patent. Neither should anything contained in the publication be construed as insuring anyone against liability for infringement of letters patent.

Shall: As used in a standard, “shall” denotes a minimum requirement in order to conform to the specification.

Should: As used in a standard, “should” denotes a recommendation or that which is advised but not required in order to conform to the specification.

This document was produced under API standardization procedures that ensure appropriate notification and participation in the developmental process and is designated as an API standard. Questions concerning the interpretation of the content of this publication or comments and questions concerning the procedures under which this publication was developed should be directed in writing to the Director of Standards, American Petroleum Institute, 1220 L Street, NW, Washington, DC 20005. Requests for permission to reproduce or translate all or any part of the material published herein should also be addressed to the director.

Generally, API standards are reviewed and revised, reaffirmed, or withdrawn at least every five years. A one-time extension of up to two years may be added to this review cycle. Status of the publication can be ascertained from the API Standards Department, telephone (202) 682-8000. A catalog of API publications and materials is published annually by API, 1220 L Street, NW, Washington, DC 20005.

Suggested revisions are invited and should be submitted to the Standards Department, API, 1220 L Street, NW, Washington, DC 20005, standards@api.org.

Contents

	Page
1 Scope	1
1.1 Purpose.	1
1.2 Applicability	1
1.3 Forging Specification Levels (FSL)	1
2 Normative References.	1
3 Terms and Definitions	2
3.1 Terms and Definitions	2
3.2 Acronyms and Abbreviations	4
4 Qualification	4
4.1 General	4
4.2 Qualification Forging	5
4.3 Qualification Forging Evaluation	5
4.4 Limits of Forging Qualifications	9
4.5 Records of Qualification	10
5 Production Forgings	11
5.1 Qualification of Procurement Sources for Starting Material	11
5.2 Material Specifications	12
5.3 Manufacturing Procedure Specification (MPS)	12
5.4 Process Control Variables	12
5.5 Forging Production	13
5.6 Inspection, Quality Control, Marking, and Documentation	13
5.7 Repair Welding	14
5.8 Traceability	14
5.9 Record Retention	14
5.10 Marking	15
5.11 Handling, Storage, and Shipping	15
Annex A (informative) API Monogram Program	16
Bibliography	20
Tables	
1 As-forged Weight Range Classes	5
2 Material Groups	6
3 ASTM E45 Method A Inclusion Rating Limits	8
4 Variables of Forging Qualification	9

Open Die Shaped Forgings for Use in the Petroleum and Natural Gas Industry

1 Scope

1.1 Purpose

This API standard specifies requirements for the qualification and production of open die shaped forgings for use in API service components in the petroleum and natural gas industries when referenced by an applicable equipment standard or otherwise specified as a requirement for compliance.

1.2 Applicability

This API standard is applicable to equipment used in the oil and natural gas industries where service conditions warrant the use of individually shaped open die forgings, including rolled rings. Examples include pressure containing or load bearing components. Forged bar, rolled bar, and forgings from which multiple parts are removed are beyond the scope of this specification.

1.3 Forging Specification Levels (FSL)

This API standard establishes requirements for four forging specification levels (FSL). These four FSL designations define different levels of forged product technical, quality and qualification requirements.

2 Normative References

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

API Specification 6A, Twentieth Edition, *Specification for Wellhead and Christmas Tree Equipment*

ASTM A370 ¹, *Standard Test Methods and Definitions for Mechanical Testing of Steel Products*

ASTM A388/A388M, *Standard Practice for Ultrasonic Examination of Steel Forgings*

ASTM A604, *Standard Practice for Macroetch Testing of Consumable Electrode Remelted Steel Bars and Billets*

ASTM E10, *Standard Test Method for Brinell Hardness Test of Metallic Materials*

ASTM E18, *Standard Test Method for Rockwell Hardness Test of Metallic Materials*

ASTM E45, *Standard Test Method for Determining the Inclusion Content of Steel*

ASTM E110, *Standard Test Method for Indentation Hardness of Metallic Materials by Portable Hardness Testers*

ASTM E112, *Standard Test Method for Determining Average Grain Size*

ASTM E165, *Standard Practice for Liquid Penetrant Examination for General Industry*

ASTM E381, *Standard Method of Macroetch Testing Steel Bars, Billets, Blooms and Forgings*

¹ ASTM International, 100 Barr Harbor Drive, West Conshohocken, Pennsylvania 19428, www.astm.org.

ASTM E428, *Standard Practice for Fabrication and Control of Metal, Other than Aluminum, Reference Blocks Used in Ultrasonic Testing*

ASTM E64, *Standard Test Method for Dynamic Tear Testing of Metallic Materials*

ASTM E709, *Standard Guide for Magnetic Particle Testing*

ANSI/NCSL Z540.3 ², *Requirements for the Calibration of Measuring and Test Equipment*

SAE AMS 2750 ³, *Pyrometry*

3 Terms and Definitions

For the purposes of this document, the following definitions apply.

3.1 Terms and Definitions

3.1.1

acceptance criteria

Defined limits placed on characteristics of materials, processes, products, or services.

3.1.2

as-forged

The condition of a forging as it leaves the forging operation without any subsequent operations.

3.1.3

bloom/billet

A semi-finished hot rolled, forged or extruded product, with a square, rectangular, or round cross section.

NOTE Bloom and billet can be used interchangeably.

3.1.4

calibration

Comparison and adjustment to a standard of known accuracy.

3.1.5

crop/cropping

Removal of the end(s) of ingot, billet, or bloom that may contain primary pipe or other defects.

3.1.6

grain flow

Fiber-like lines appearing on polished and etched sections of forgings caused by orientation of the constituents of the metal in the direction of working during forging.

3.1.7

heat

Material originating from a final melt, or for remelted alloys, the material originating from a single remelted ingot.

² NCSL International, 2995 Wilderness Place, Suite 107, Boulder, Colorado 80301-5404, www.ncsli.org.

³ Society of Automotive Engineers, 400 Commonwealth Drive, Warrendale, Pennsylvania 15096-0001, www.sae.org.

3.1.8**heat treatment**

Specified, timed sequence of controlled heating and cooling of materials for the purpose of changing physical or mechanical properties.

3.1.9**hot work ratio****(forging reduction ratio)**

A ratio measuring the change in the cross sectional area during each hot working operation.

EXAMPLE For other than upset forging, the hot work ratio for a single hot work operation can be calculated using the following relationship:

$$\text{hot work ratio} = \frac{A_i}{A_f} : 1$$

where

A_f is the final cross sectional area;

A_i is the initial cross sectional area.

For upset forging, the hot work ratio for a single hot work operation can be calculated using the following relationship:

$$\text{upset hot work ratio} = \frac{A_f}{A_i} : 1 \text{ or } \frac{h_i}{h_f} : 1$$

where

A_f is the final cross sectional area;

A_i is the initial cross sectional area;

h_f is the final forging height;

h_i is the initial material height.

The total hot work reduction ratio is defined as the product of the individual reduction ratios achieved at each step in the hot work operation from ingot cross section to the final hot work cross section. The ingot cross section shall be the cross section of the ingot obtained after casting or the final remelt step and any ingot grinding or surface preparation prior to the hot working. When the cross-section of the starting material or forged part varies, the cross-section resulting in the lowest calculated hot work ratio shall be used.

3.1.10**inclusions**

Particles of nonmetallic compounds of metals and impurity elements, such as oxides, sulfides, or silicates, that are present in ingots and are carried over in wrought products.

3.1.11**ingot**

A cast product intended for subsequent remelting or hot working by rolling, forging, or extrusion.

3.1.12**ladle refining**

Practices used on molten steel in the ladle that are used to adjust and refine the melt chemistry.

3.1.13**melt practice**

Type of process used to produce a heat of metal. Includes the use of equipment for melting and refining.

3.1.14**open die forging**

Process where the hot mechanical forming of metals between flat or shaped dies in which metal flow is not completely restricted.

NOTE 1 The open die forging process uses hammers and presses to shape individual metal parts, usually using repeated strokes and continuous manipulation. Multiple open die forging operations can be combined to produce the required shape.

NOTE 2 The metal used in open die forging may be reheated several times during the forging process before the final product is achieved.

3.1.15**prolongation**

An extension of metal added to a forging to permit removal and subsequent testing without destroying the forging. This extension is integrally made during the forging process and removed after final heat treatment.

3.1.16**rolled ring**

Circular open die forgings produced on a ring mill.

3.1.17**starting material**

The raw material used to produce a forging. Examples are billets, ingots, and blooms.

3.1.18**traceability**

The ability to verify the history, location or application of an item by means of documented recorded identification.

3.1.19**wrought structure**

A hot worked or forged structure that contains no cast dendritic elements.

3.2 Acronyms and Abbreviations

FSL	forging specification level
MPS	manufacturing procedure specification
NDE	nondestructive examination
QTC	qualification test coupon
UNS	unified numbering system

4 Qualification**4.1 General**

This standard gives the requirements for four forging specification levels (FSLs). The FSLs are numbered in increasing levels of severity from 1 to 4 in order to reflect increasing technical, quality and qualification criteria. The subparagraphs in Section 4 describe the conditions which, when met, allow the forging to receive the appropriate FSL classification level.

4.2 Qualification Forging

4.2.1 A qualification forging shall be produced, tested and evaluated by the forging supplier in order to establish qualification for a range of products listed in Table 1. Forgings shall be produced in accordance with a manufacturing procedure specification, as specified in 5.3. The material group of the qualification forging shall be in accordance with Table 2. Qualification forgings are to be in their completed forged form, with the addition of any specified rough machining and full heat treatment to establish the final mechanical properties required of the finished product. Qualification forgings shall be produced in accordance with the requirements of Section 4, Section 5, and the forging supplier's written specification that defines acceptance criteria.

4.2.2 A forging qualified to a specific FSL also qualifies lower FSLs (e.g. FSL-4 qualifies FSL-3, FSL-2, and FSL-1 forgings) within the limitations of Section 4.4.

4.2.3 Repair welding is prohibited on the qualification forging.

4.3 Qualification Forging Evaluation

4.3.1 Visual Examination

4.3.1.1 Visual inspection of the forging shall be performed in accordance with the forging supplier's procedures for cracks, laps, seams and other anomalies. Results shall be documented and the material shall be dispositioned.

4.3.1.2 Photographs of the qualification forging in the as forged condition shall be taken to document the configuration and general appearance.

4.3.2 Hardness Testing

Brinell and/or Rockwell hardness testing shall be performed on the surfaces of the qualification forging in accordance with ASTM E10, ASTM E110, or ASTM E18 to ensure the forging is within the specified limits. Results shall be documented.

4.3.3 Nondestructive Examination

4.3.3.1 Surface Examination

4.3.3.1.1 Sampling

All accessible surfaces of each qualification forging shall be examined by liquid-penetrant (PT) or magnetic-particle (MT) methods after final heat treatment and any machining operations. Forgings may have to be rough machined or ground in order to facilitate surface NDE.

Table 1—As-forged Weight Range Classes (weight in pounds)

	< 2500	≥ 2500 < 10,000	≥ 10,000
FSL-1	One qualification required		
FSL-2	One qualification required		One qualification required
FSL-3	One qualification required	One qualification required	One qualification required
FSL-4	Weight not applicable for FSL-4. Each forging shall be individually qualified.		

Table 2—Material Groups

Material Group	Description	Sub-Group	Typical Examples/Grades
1	Carbon, microalloyed steels	1A	Carbon steels (UNS G1xxxx)
		1B	Microalloyed (with small addition of V, Nb, Ti, Mo, Zr, or B) steels (ASTM A909, A921)
2	Low alloy steels	2A	Cr-Mo-low alloy steels (UNS G41xxx)
		2B	Ni-Cr-Mo medium carbon alloys (UNS G43xxx)
		2C	Cr-Ni-Mo low alloy steels (UNS G86xxx)
		2D	2 ¹ / ₄ Cr-1Mo steel (ASTM A182/A336 Grade F22/UNS K21590), / 9Cr-1Mo steel (ASTM A182 Grade F9/UNS K90941)
		2E	ASTM A707 Grades (modified)
3	Austenitic, martensitic, and martensitic precipitation-hardening stainless steels	3A	Austenitic UNS S31603, S30400
		3B	Martensitic 410 SS (UNS S41000), F6NM (UNS S41500, S42400)
		3C	Precipitation Hardening 17-4PH (UNS S17400), 15-5PH (UNS S15500)
4	Duplex and super duplex stainless steels	4A	Duplex UNS S31803, UNS S32205
		4B	Super Duplex UNS S31260, S32750, S32760, S39277
5	Nickel based alloys	5A	Solution Annealed UNS N06625, N08825
		5B	Precipitation Hardening UNS N07718, N07725, N09925, N09935, N09945

4.3.3.1.2 Test Method

All forgings shall be examined in accordance with procedures specified in ASTM E709 (MT) or ASTM E165 (PT). If any indications are believed to be non-relevant on the basis that they are not associated with a surface rupture (i.e. magnetic permeability variations, non-metallic stringers), they shall be examined by liquid penetrant surface NDE methods or removed and re-inspected, to confirm their non-relevancy.

4.3.3.1.3 Acceptance Criteria

The following acceptance criteria shall apply:

- a) no relevant indication with a major dimension equal to or greater than $\frac{3}{16}$ in. (5 mm);
- b) no more than 10 relevant indications in any continuous 6 in.² (40 cm²) area;
- c) four or more relevant indications in a line separated by less than $\frac{1}{16}$ in. (1.6 mm) (edge-to-edge) are unacceptable;

4.3.3.2 Volumetric Examination

4.3.3.2.1 Sampling

As far as practical, the entire volume of each qualification forging shall be ultrasonically examined after heat treatment for mechanical properties and prior to machining operations that limit effective interpretation of the results of the examination. For quench-and-tempered products, the volumetric inspection shall be performed after heat treatment for mechanical properties exclusive of stress-relief treatments or re-tempering to reduce hardness.

4.3.3.2.2 Test Method

All forgings shall be examined by the ultrasonic method in accordance with the flat-bottom-hole procedures specified in ASTM A388/388M, except that the immersion method may be used, and ASTM E428. Hollow forgings shall be examined using the angle beam method and acceptance criteria specified in ASTM A388/A388M.

The distance amplitude curve (DAC) shall be based on a $1/16$ in. (1.6 mm) flat-bottom hole for metal thicknesses through $1\frac{1}{2}$ in. (38 mm), on a $1/8$ in. (3.2 mm) flat-bottom hole for metal thicknesses from $1\frac{1}{2}$ in. (38 mm) through 6 in. (150 mm), and on a $1/4$ in. (6.4 mm) flat-bottom hole for metal thicknesses exceeding 6 in. (150 mm).

4.3.3.2.3 Acceptance Criteria

The following acceptance criteria apply:

- a) no single indication exceeding reference distance amplitude curve;
- b) no multiple indications exceeding 50 % of reference distance amplitude curve. Multiple indications are defined as two or more indications (each exceeding 50 % of the reference distance amplitude curve) within $1/2$ in. (13 mm) of each other in any direction.

4.3.4 Test Piece

4.3.4.1 Based on the size and complexity of the forging, the qualification forging shall be evaluated using at least one of the following test pieces:

- a) an integral prolongation, at a specified location;
- b) a sacrificial forging;
- c) a separately forged QTC representing the largest cross section is permitted for FSL 1 only.

4.3.4.2 When a prolongation is used, it shall remain integrally attached during all heat treatment operations except stress relief and any re-tempering or re-aging that may be required.

4.3.5 Mechanical Testing

4.3.5.1 Hardness testing shall be performed in accordance with ASTM E10, E110, or E18 on the cross section of the test piece, traversing the entire cross section in two perpendicular directions, with each traverse consisting of a minimum 5 points equally spaced across the cross section. Results shall be documented.

4.3.5.2 Tensile test specimens shall be removed from the test piece and tested in accordance with ASTM A370 at the following locations:

- a) at or near the surface of the forging but not deeper than $1\frac{1}{4}$ in. (31.75 mm);
- b) at $\frac{1}{4}T$ of the thickest cross section (T is defined as the thickest cross section of the forging in the as heat treated condition);
- c) at the location closest to $\frac{1}{2}T$ of the heaviest cross section of the forging in the final heat treated condition.

In all locations, as geometry permits, specimens shall be removed in the longitudinal and transverse direction to the grain flow.

4.3.5.3 Charpy (CVN) impact specimens shall be removed from the $\frac{1}{4}T$ and $\frac{1}{2}T$ areas and tested in accordance with ASTM A370 at a temperature specified by the material specification. In all locations, as long as the geometry permits, specimens shall be removed in the longitudinal and transverse direction to the grain flow. Results shall be documented.

4.3.6 Chemical Analysis

4.3.6.1 The forging supplier shall specify the nominal chemical composition, including composition tolerances, of the material used for the qualification forging.

4.3.6.2 Material composition shall be determined on a heat basis (or on a remelt-ingot basis for remelt-grade materials) in accordance with a nationally or internationally recognized standard.

4.3.7 Metallographic Examination—Applicable to FSL-3 and FSL-4 only

4.3.7.1 General

4.3.7.1.1 A metallographic sample shall be removed from 2 locations, surface and $\frac{1}{4}T$ of the heaviest cross section of the prolongation or sacrificial forging.

4.3.7.1.2 For Group 1 and Group 2 materials, steel cleanliness shall be determined in accordance with ASTM E45, Method A, and shall be within the limits shown in Table 3. The results shall be documented.

Table 3—ASTM E45 Method A Inclusion Rating Limits

Inclusion Type	Thin	Heavy
Type A sulfide	2	$1\frac{1}{2}$
Type B alumina	2	$1\frac{1}{2}$
Type C silicate	2	$1\frac{1}{2}$
Type D globular oxide	$1\frac{1}{2}$	$1\frac{1}{2}$

4.3.7.1.3 For Group 1 and Group 2 materials, grain size shall be determined in accordance with ASTM E112 at the $\frac{1}{4}T$ location. For carbon and low alloy steels the grain size shall be ASTM 5 or finer. For other materials the grain size shall be appropriate for the alloy. Photomicrographs of grain size shall be taken at 100X.

4.3.7.1.4 For Groups 3 and 5, the microstructure shall be evaluated by techniques appropriate to characterize the alloy.

4.3.7.1.5 For Group 4, the microstructure shall be evaluated by techniques appropriate to characterize the alloy. The micrographic examination shall include a sample taken from the qualification forging and its qualification test coupon at the same location as specimens taken for mechanical testing. The ferrite content shall be tested in accordance with ASTM E562. The ferrite content shall be in the range of 35 % to 65 % (volume fraction). Samples shall be electrolytically etched in either NaOH or KOH, and in such a manner as to provide maximum contrast for austenite and ferrite phase discrimination. A minimum of 15 fields and 16 points per field shall be used.

4.3.7.1.6 For Group 4, corrosion testing shall be performed in accordance with ASTM G48, method A. A sample shall be removed from the $\frac{1}{4}T$ envelope of the heaviest cross section of the prolongation or sacrificial forging. For Subgroup 4A, the test temp shall be $25^{\circ} \pm 1^{\circ}$ C. For Subgroup 4B, the test temp shall be $50^{\circ} \pm 1^{\circ}$ C. Test duration for both subgroups shall be 24 hours. Sides of the test specimens shall be ground to a 120 grit finish (or better) with the edges rounded. The test material shall show no evidence of pitting after 24 hours immersion in the test solution when examined with a low power magnification (20X) and the maximum weight loss shall be less than 1g/m^2 .

4.3.7.2 Macroetch

One full cross section sample shall be macroetched after sample is removed from the prolongation or sacrificial forging in accordance with ASTM A604 or ASTM E381, as applicable, to show the wrought structure. Acceptance criteria shall be in accordance with the forging supplier's written procedure.

4.3.8 Acceptance of the Qualification Forging

4.3.8.1 Results of the examinations specified in Section 4 shall comply with the acceptance criteria specified in the forging supplier's MPS.

4.3.8.2 Samples failing to meet the acceptance criteria shall be cause for re-evaluation of the processes and procedures used. A revision of the MPS and requalification is required.

4.4 Limits of Forging Qualifications

Forging qualification variables are shown below in Table 4.

Table 4—Variables of Forging Qualification

Variable	FSL1	FSL2	FSL3	FSL4
Change in material group (Table 2)	4.4.1	4.4.1	4.4.1	4.4.1
Change in forging practice that results in lower hot work ratio.		4.4.2.2	4.4.2.2	4.4.2.2
Change in melting/refining practice used for the starting material.		4.4.2.3	4.4.2.3	4.4.2.3
Change in as forged weight class (Table 1)		4.4.2.4	4.4.2.4	4.4.2.4
Change from press/hammer to ring rolling		4.4.2.5	4.4.2.5	4.4.2.5
Increase in the minimum specified strength level above qualified			4.4.3.2	4.4.3.2
Change in basic type of forge equipment			4.4.3.3	4.4.3.3
Change in immediate post-forge thermal process on forgings				4.4.3.4
Change in subgroup of materials in Groups 1, 2, 3, 4, 5 (Table 2)			4.4.3.5	4.4.3.5
Change in actual melt source used for starting material				4.4.4.2
Change in specific material grade within a material subgroup (Table 2)				4.4.4.3
NOTE This table provides a matrix of requirements and may not include all requirements and should be used as a reference only.				

4.4.1 FSL-1

A change in material group as shown in Table 2 from the forging that was previously qualified requires requalification of the forging.

4.4.2 FSL-2

4.4.2.1 Qualification requirements specified for FSL-1 are required for FSL-2.

4.4.2.2 A change to the forging practice resulting in a lower hot work ratio than that used to produce the qualification forging requires a requalification.

4.4.2.3 Any change in the melt practice used to qualify the forging requires a requalification.

4.4.2.4 A change in the as-forged weight range class as shown in Table 1 from the forging that was previously qualified requires requalification of the forging.

4.4.2.5 A change from press or hammer equipment to a ring rolling process.

4.4.3 FSL-3

4.4.3.1 Qualification requirements specified for FSL-1 and FSL-2 are required for FSL-3.

4.4.3.2 An increase in the minimum specified yield strength or minimum specified tensile strength in accordance with the applicable design standard above the values qualified for a given material subgroup requires a requalification.

4.4.3.3 A change in the basic type of forge equipment used (mechanical, press, hammer, ring roller, etc.) from the forging that was previously qualified requires requalification of the forging.

4.4.3.4 Any change of the subgroup in material groups 1, 2, 3, 4, and 5 from Table 2 requires a requalification.

4.4.4 FSL-4

4.4.4.1 Qualification requirements specified for FSL-1, FSL-2, and FSL-3 are required for FSL-4.

4.4.4.2 A change in the actual melt source used to supply the starting material from the forging that was previously qualified requires requalification of the forging.

4.4.4.3 A change in specific material grade within a subgroup requires requalification of the forging (Ex. 4130 and 4140 require separate qualifications).

4.4.4.4 A change in the immediate post-forge thermal process used from the forging that was previously qualified requires requalification of the forging.

4.5 Records of Qualification

The following records are required to document the qualification of the forging.

- a) Starting material, grade, UNS number, where applicable, heat number, material specification, supplier name, supplier mill, size, hot work ratio, cut weight, melt practice and ladle refinements, cleanliness, actual chemistry, minimum/maximum element tolerance, incoming material inspection/evaluation method, MPS revision level, and qualification number.

- b) Forging parameters: hot work temperature range, description of each forging operation including product configuration at start and finish of each operation, and hot work ratio for each step, forge equipment used.
- c) Post forging parameters: time, temperature, and media of cooling/bake-out, heat treatment specification and actual times and temperatures, cooling media, heat treatment equipment used.
- d) Test records: records of the examination, mechanical testing, and metallographic evaluations as described in Section 4.

5 Production Forgings

5.1 Qualification of Procurement Sources for Starting Material

5.1.1 Only melt source facilities that are approved by the forging supplier shall be used to supply starting material such as billet or ingot material. The forging supplier shall have a documented procedure, fully implemented, for qualifying starting material suppliers for each specific size and grade of starting material. The approval process shall be based on both a quality assurance and a technical evaluation. The approval process shall establish the methodology by which the starting material supplier will be evaluated on an ongoing basis to maintain their status as an approved supplier.

5.1.2 The maintenance of an acceptable quality program, such as an ISO registration, is not sufficient by itself to satisfy the requirements of 5.1.1. Documented evidence that a starting material supplier has a historical and ongoing technical capability of producing materials meeting this standard and who has proven, implemented procedures and capabilities in place to consistently produce acceptable product is a minimum requirement. Options for the technical approval of a starting material supplier include one or more of the following.

- a) Supplier experience over an extended period of time. Demonstration of acceptable experience shall include tests/inspections, quantity of material received, nonconformance analysis, etc.
- b) On-site technical audit at scheduled 3 year intervals. A new supplier shall be subject to an onsite technical audit, which includes the controls addressed in 5.1.3.

5.1.3 The forging supplier is responsible for ensuring that a starting material supplier has implemented controls addressing the following for each size and grade of starting material ordered:

- chemistry controls;
- hydrogen controls;
- melting practice controls;
- teeming practice and ingot mold controls;
- hot work practice controls (method of forging, amount of reduction, forging temperature, etc.);
- cooling rate and method controls;
- ingot/billet cropping controls;
- starting material inspection and acceptance criteria (cleanliness requirements, limitations on porosity or inclusions, grain size, secondary phases, microstructure, macrostructure, etc.) as applicable;
- material contamination controls (e.g. mercury, radioactivity).

5.2 Material Specifications

5.2.1 Starting material requirements shall be documented in the form of material specifications. Material specifications shall be developed by the forging supplier or the purchaser. Material specifications shall include as a minimum:

- material grade, including element chemistry ranges;
- melting practices and ladle refinements;
- acceptable forging reduction range, if applicable;
- acceptable cleanliness level range, as required by applicable FSL;
- acceptable inspection practices and criteria.

5.2.2 The forging supplier shall document acceptance of incoming starting material to the requirements of the material specification prior to use for production of forgings.

5.3 Manufacturing Procedure Specification (MPS)

The forging supplier shall prepare a manufacturing procedure specification (MPS) to include, as a minimum, the material specification and the general variables listed in 5.4.1 and the heat treat parameters listed in 5.4.2. As part of the MPS, the forging steps shall be shown detailing initial and final dimensions during forging for each step of the forging process. This will also include documentation of the heat or reheat temperature ranges required for each hot work reduction step in a drawing and written documents.

5.4 Process Control Variables

5.4.1 General Variables

The following are general process control variables for the production of qualified forgings:

- size of starting material, cut weight and tolerances;
- evaluation process used for incoming material and for determining cropped length of starting material;
- hydrogen flake-control method (bake-out, slow cool, etc.), if applicable;
- hot-working temperature range;
- overall hot work ratio from starting material;
- description of each forging operation, including general product configuration at the beginning and end of each different type of hot work or forging operation and hot-work ratio for each step;
- acceptable forging equipment for production;
- inspection requirements;
- NDE, if applicable.

5.4.2 Heat Treat Parameters

The following are heat treat parameters, as applicable:

- furnace loading diagram, orientation and spacing of production parts;
- heat treat times and temperatures for each processing cycle;
- forging configuration and dimensions at time of heat treatment;
- quenching medium and type of agitation (water/polymer, forced, horizontal; or vertical quench, ID/OD, etc.);
- quench medium start and finish temperature and transfer time to quench.

5.5 Forging Production

5.5.1 General

Forgings shall be produced by the open die or ring rolled forging process in accordance with the MPS specified in 5.3. The overall hot work ratio, as defined in 3.1.9, shall be sufficient to produce a wrought material structure throughout all sections of the forging. The overall hot-work ratio from starting stock to product shall be greater than or equal to that specified below for the applicable FSL.

- a) FSL-1: 3.0:1
- b) FSL-2: 3.0:1
- c) FSL-3 4.0:1
- d) FSL-4 4.0:1

5.5.2 Mechanical and Material Testing

The forging supplier shall perform mechanical or material testing of the production forgings as specified in the purchasing document.

5.6 Inspection, Quality Control, Marking, and Documentation

5.6.1 Calibrations Systems

Inspection, measuring, and testing equipment used for acceptance shall be identified, inspected, calibrated, and adjusted at specific intervals in accordance with ANSI/NCSL Z540.3 and this standard. Calibration standards shall be traceable to the applicable national or international standards agency and shall be no less stringent than the requirements included herein. Inspection, measuring, and testing equipment shall be used only within the calibrated range. Calibration intervals shall be established based on repeatability and degree of usage.

5.6.2 Furnace Calibration

5.6.2.1 Forging furnaces shall be calibrated in accordance with the forging suppliers written procedures.

5.6.2.2 Heat treatment furnaces shall be calibrated in accordance with recognized international standards such as API 6A, Annex M, or AMS 2750. Records of furnace calibration shall be maintained.

5.6.3 Visual Inspection

5.6.3.1 Visual inspection of the production forging shall be performed in accordance with the forging supplier's procedures for cracks, laps, seams and other anomalies.

5.6.3.2 Results shall be documented and the material shall be dispositioned.

5.6.3.3 Any discontinuities discovered shall be evaluated and the disposition documented.

5.6.4 Nondestructive Examination (NDE)

5.6.4.1 Production forgings shall be capable of meeting the NDE requirements of the applicable API product specification.

5.6.4.2 NDE shall be performed as specified in the purchasing documents.

5.6.5 Dimensional Inspection

Dimensional inspection shall be performed on forgings produced to this standard. Each forging shall be inspected. The purchaser shall specify dimensions to be inspected. Acceptance criteria for dimensions shall be as required by the purchaser's written specification.

5.7 Repair Welding

Repair welding is not permitted on forgings produced to this specification.

5.8 Traceability

5.8.1 Full traceability of forgings shall be maintained with respect to material heat, MPS with revision level and heat treatment loads.

5.8.2 Forging qualification records shall be traceable to the MPS with revision level.

5.8.3 Forgings produced to this specification shall be traceable to the applicable forging qualification record.

5.9 Record Retention

The forging supplier shall establish and maintain documented procedures to control all documents and data required by this standard. Records required by this standard shall be maintained for 10 years. Documents and data may be in any type of media (hard copy or electronic) and shall be:

- a) maintained to demonstrate conformance to specified requirements;
- b) legible;
- c) retained and readily retrievable;
- d) stored in an environment to prevent damage, deterioration, or loss;
- e) available and auditable by the user/purchaser.

5.10 Marking

5.10.1 Each forging shall be marked with the following:

- a) forging supplier's name or mark;
- b) part number;
- c) material grade;
- d) "API Spec 20B" and FSL;
- e) date of manufacture (month and year);
- f) heat and heat treat lot number;
- g) traceability number;
- h) material sub-group;
- i) weight range class;
- j) qualification record number;

5.10.2 Procurement drawings shall identify where stamping is appropriate. The above marking listed in 5.10.1 shall be applied using low-stress (dot, vibration, or rounded V) stamps. Conventional sharp V-stamping is acceptable in low-stress areas, such as the outside diameter of flanges, except as limited in the following.

- a) For material group 1 and 2, sharp V-stamping is not permitted in high stress areas unless subsequently stress-relieved at 1100 °F (590 °C) minimum.
- b) For material groups 3, 4, and 5, conventional sharp V-stamping in high-stress areas shall not be permitted unless agreed with the purchaser.

5.11 Handling, Storage, and Shipping

Forgings shall be packaged for storage or transit in accordance with the written specifications of the forging supplier.

Annex A **(informative)**

API Monogram Program

A.1 Scope

The API Monogram® is a registered certification mark owned by the American Petroleum Institute (API) and authorized for licensing by the API Board of Directors. Through the API Monogram Program, API licenses product manufacturers to apply the API Monogram to products which comply with product specifications and have been manufactured under a quality management system that meets the requirements of API Q1. API maintains a complete, searchable list of all Monogram licensees on the API Composite List website (www.api.org/compositelist).

The application of the API Monogram and license number on products constitutes a representation and warranty by the licensee to API and to purchasers of the products that, as of the date indicated, the products were manufactured under a quality management system conforming to the requirements of API Q1 and that the product conforms in every detail with the applicable standard(s) or product specification(s). API Monogram program licenses are issued only after an on-site audit has verified that an organization has implemented and continually maintained a quality management system that meets the requirements of API Q1 and that the resulting products satisfy the requirements of the applicable API product specification(s) and/or standard(s). Although any manufacturer may claim that its products meet API product requirements without monogramming them, only manufacturers with a license from API can apply the API Monogram to their products.

Together with the requirements of the API Monogram license agreement, this annex establishes the requirements for those organizations who wish to voluntarily obtain an API license to provide API monogrammed products that satisfy the requirements of the applicable API product specification(s) and/or standard(s) and API Monogram Program requirements.

For information on becoming an API Monogram Licensee, please contact API, Certification Programs, 1220 L Street, N. W., Washington, DC 20005 or call 202-682-8145 or by email at certification@api.org.

A.2 Normative References

In addition to the referenced standards listed earlier in this document, this annex references the following standard:

API Specification Q1, *Specification for Quality Management System Requirements for Manufacturing Organizations for the Petroleum and Natural Gas Industry*

For Licensees under the Monogram Program, the latest version of this document shall be used. The requirements identified therein are mandatory.

A.3 API Monogram Program: Licensee Responsibilities

A.3.1 Monogram Program Requirements

For all organizations desiring to acquire and maintain a license to use the API Monogram, conformance with the following shall be required at all times:

- a) the quality management system requirements of API Q1;
- b) the API Monogram Program requirements of API Q1, Annex A;
- c) the requirements contained in the API product specification(s) to which the organization is licensed;
- d) the requirements contained in the API Monogram Program License Agreement.

A.3.2 Control of the Application and Removal of the API Monogram

Each licensee shall control the application and removal of the API Monogram in accordance with the following.

- a) Products that do not conform to API specified requirements shall not bear the API Monogram.
- b) Each licensee shall develop and maintain an API Monogram marking procedure that documents the marking/monogramming requirements specified by this annex and any applicable API product specification(s) and/or standard(s). The marking procedure shall:
 - 1) define the authority responsible for application and removal of the API Monogram and license number;
 - 2) define the method(s) used to apply the Monogram and license number;
 - 3) identify the location on the product where the API Monogram and license number are to be applied;
 - 4) require the application of the date of manufacture of the product in conjunction with the use of the API Monogram and license number;
 - 5) require that the date of manufacture, at a minimum, be two digits representing the month and two digits representing the year (e.g. 05-12 for May 2012) unless otherwise stipulated in the applicable API product specification(s) or standard(s); and
 - 6) define the application of all other required API product specification(s) and/or standard(s) marking requirements.
- c) Only an API licensee shall apply the API Monogram and its designated license number to API monogramable products.
- d) The API Monogram and license number, when issued, are site-specific and subsequently the API Monogram shall only be applied at that site specific licensed facility location.
- e) The API Monogram may be applied at any time appropriate during the production process but shall be removed in accordance with the licensee's API Monogram marking procedure if the product is subsequently found to be out of conformance with any of the requirements of the applicable API product specification(s) and/or standard(s) and API Monogram Program.

For certain manufacturing processes or types of products, alternative API Monogram marking procedures may be acceptable. Requirements for alternative API Monogram marking are detailed in the, *API Monogram Program Alternative Marking of Products License Agreement*, available on the API Monogram Program website at <http://www.api.org/alternative-marking>.

A.3.3 Design and Design Documentation

Each licensee and/or applicant for licensing shall maintain current design documentation as identified in API Q1 for all of the applicable products that fall under the scope of each Monogram license. The design document information shall provide objective evidence that the product design meets the requirements of the applicable and most current API product specification(s) and/or standard(s). The design documentation shall be made available during API audits of the facility.

In specific instances, the exclusion of design activities is allowed under the Monogram Program, as detailed in Advisory # 6, available on API Monogram Program website at <http://www.api.org/advisories>.

A.3.4 Manufacturing Capability

The API Monogram Program is designed to identify facilities that have demonstrated the ability to manufacture equipment that conforms to API specifications and/or standards. API may refuse initial licensing or suspend current licensing based on a facility's level of manufacturing capability. If API determines that an additional review is warranted, API may perform additional audits (at the organization's expense) of any subcontractors to ensure their conformance with the requirements of the applicable API product specification(s) and/or standard(s).

A.3.5 Use of the API Monogram in Advertising

An API Monogram licensee shall not use the API Monogram and/or license number on letterheads, buildings or other structures, websites or in any advertising without an express statement of fact describing the scope of Licensee's authorization (license number and product specification). The Licensee should contact API for guidance on the use of the API Monogram other than on products.

A.4 Product Marking Requirements

A.4.1 General

These marking requirements shall apply only to those API Licensees wishing to mark applicable products in conjunction with the requirements of the API Monogram Program.

A.4.2 Product Specification Identification

Manufacturers shall mark products as specified by the applicable API specifications or standards. Marking shall include reference to the applicable API specification and/or standard. Unless otherwise specified, reference to the API specifications and/or standards shall be, as a minimum, "API [Document Number]" (e.g. API 6A, or API 600). Unless otherwise specified, when space allows, the marking may include use of "Spec" or "Std" as applicable (e.g. API Spec 6A or API Std 600).

A.4.3 Units

Products shall be marked with units as specified in the API specification and/or standard. If not specified, equipment shall be marked with U.S. customary (USC) units. Use of dual units [USC units and metric (SI) units] may be acceptable, if such units are allowed by the applicable product specification and/or standard.

A.4.4 Nameplates

Nameplates, when applicable, shall be made of a corrosion-resistant material unless otherwise specified by the API specification and/or standard. Nameplate shall be located as specified by the API specification and/or standard. If the location is not specified, then the licensee shall develop and maintain a procedure detailing the location to which the nameplate shall be applied. Nameplates may be attached at any time during the manufacturing process.

The API Monogram and license number shall be marked on the nameplate, in addition to the other product marking requirements specified by the applicable product specification and/or standard.

A.4.5 License Number

The API Monogram license number shall not be used unless it is marked in conjunction with the API Monogram. The license number shall be used in close proximity to the API Monogram.

A.5 API Monogram Program: Nonconformance Reporting

API solicits information on products that are found to be nonconforming with API specified requirements, as well as field failures (or malfunctions), which are judged to be caused by either specification and/or standard deficiencies or nonconformities against API specified requirements. Customers are requested to report to API all problems with API monogrammed products. A nonconformance may be reported using the API Nonconformance Reporting System available at <http://compositelist.api.org/ncr.aspx>.

Bibliography

- [1] ASTM A182, *Standard Specification for Forged or Rolled Alloy and Stainless Steel Pipe Flanges, Forged Fittings, and Valves and Parts for High Temperature Service*
- [2] ASTM A336, *Standard Specification for Alloy Steel Forgings for Pressure and High Temperature Parts*
- [3] ASTM A707, *Standard Specification for Forged Carbon and Alloy Steel Flanges for Low Temperature Service*
- [4] ASTM A909, *Standard Specification for Steel Forgings, Microalloy, for General Industrial Use*
- [5] ASTM A921, *Standard Specification for Steel Bars, Microalloy, Hot Wrought, Special Quality, for Subsequent Hot Forging*

EXPLORE SOME MORE

Check out more of API's certification and training programs, standards, statistics and publications.

API Monogram™ Licensing Program

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: certification@api.org
Web: www.api.org/monogram

API Quality Registrar (APIQR™)

- ISO 9001
- ISO/TS 29001
- ISO 14001
- OHSAS 18001
- API Spec Q1®
- API Spec Q2™
- API Quality*Plus*™
- Dual Registration

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: certification@api.org
Web: www.api.org/apiqr

API Training Provider Certification Program (API TPCP®)

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: tpcp@api.org
Web: www.api.org/tpcp

API Individual Certification Programs (ICP™)

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: icp@api.org
Web: www.api.org/icp

API Engine Oil Licensing and Certification System (EOLCS™)

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: eolcs@api.org
Web: www.api.org/eolcs

Motor Oil Matters™

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: motoroilmatters@api.org
Web: www.motoroilmatters.org

API Diesel Exhaust Fluid™ Certification Program

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: apidef@api.org
Web: www.apidef.org

API Perforator Design™ Registration Program

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: perfdesign@api.org
Web: www.api.org/perforators

API WorkSafe™

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: apiworksafe@api.org
Web: www.api.org/worksafe

API-U®

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: training@api.org
Web: www.api-u.org

API eMaintenance™

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: apiemaint@api.org
Web: www.apiemaintenance.com

API Standards

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Email: standards@api.org
Web: www.api.org/standards

API Data™

Sales: 877-562-5187
(Toll-free U.S. and Canada)
(+1) 202-682-8041
(Local and International)
Service: (+1) 202-682-8042
Email: data@api.org
Web: www.api.org/data

API Publications

Phone: 1-800-854-7179
(Toll-free U.S. and Canada)
(+1) 303-397-7956
(Local and International)
Fax: (+1) 303-397-2740
Web: www.api.org/pubs
global.ihs.com



1220 L Street, NW
Washington, DC 20005-4070
USA

202.682.8000

Additional copies are available through Techstreet

Phone Orders: 1-800-699-9277 (Toll-free in the U.S. and Canada)
734-780-8000 (Local and International)

Fax Orders: 734-780-2046

Online Orders: www.techstreet.com

Information about API Publications, Programs and Services
is available on the web at www.api.org

Product No. G20B01