



Standard Specification for Ferrosilicon¹

This standard is issued under the fixed designation A100; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers grades of ferrosilicon for steelmaking and foundry uses.

1.2 The values stated in inch-pound units are to be regarded as the standard. The metric equivalents of inch-pound units (SI units) given in parentheses may be approximate.

2. Referenced Documents

2.1 *ASTM Standards:*²

A1025 Specification for Ferroalloys and Other Alloying Materials, General Requirements

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

E360 Test Methods for Chemical Analysis of Silicon and Ferrosilicon (Withdrawn 2006)³

3. General Conditions of Delivery

3.1 Materials furnished to this specification shall conform to the requirements of Specification **A1025**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A1025** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A1025**, this specification shall prevail.

¹ This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.18** on Castings.

Current edition approved March 1, 2012. Published April 2012. Originally approved in 1925. Last previous edition approved in 2007 as A100 – 07. DOI: 10.1520/A0100-12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

4. Chemical Composition

4.1 The various grades shall conform to the requirements as to chemical composition prescribed in **Table 1**.

4.2 The manufacturer shall furnish an analysis of each shipment showing the silicon content and when required, such of the other elements specified in **Table 1**.

5. Size

5.1 The various grades are available in sizes as listed in **Table 2**.

5.2 The sizes listed in **Table 2** are typical as shipped from the manufacturer's plant. These alloys exhibit varying degrees of friability; therefore, some attrition may be expected in transit, storage, and handling. A quantitative test is not available for rating relative friability of ferroalloys. A code system has been developed, therefore, for this purpose, and a number rating for each product type is shown in the last column of **Table 2**. Definitions applicable to these code numbers are given in Specification **A1025**.

6. Chemical Analysis

6.1 Unless otherwise agreed upon, the chemical analysis of the material shall be made in accordance with Test Methods **E360**.

6.2 If alternative methods of analysis are used, Methods **E360** shall be used for referee.

6.3 Where a method is not given in Methods **E360** for the analysis for a particular element, the analysis shall be made in accordance with a procedure agreed upon between the manufacturer and the purchaser.

7. Keywords

7.1 ferroalloy; ferrosilicon

TABLE 1 Chemical Requirements

Element	Grade																
	C	CA	CB	C1	C2	D	DA	E	EA	E1	F	F1	F1A	G	GA	G1	G1A
	Composition, % ^{A,B}																
Silicon	74.0– 79.0	74.0– 79.0	74.0– 79.0	74.0– 79.0	74.0– 79.0	65.0– 70.0	65.0– 70.0	47.0– 51.0	47.0– 51.0	47.0– 51.0	20.0– 24.0	20.0– 24.0	20.0– 24.0	14.0– 17.0	14.0– 17.0	14.0– 17.0	14.0– 17.0
Carbon	0.10	0.10	0.10	0.10	0.10	0.10	0.10	.010	.010	0.10	0.50	0.50	0.50	0.70	0.70	0.70	0.70
Sulfur	0.025	0.025	0.025	0.025	0.025	0.025	0.025	0.025	0.025	0.025	0.025	0.025	0.025	0.025	0.025	0.025	0.025
Phosphorous	0.035	0.035	0.035	0.035	0.035	0.035	0.035	0.040	0.040	0.040	0.120	0.120	0.120	0.120	0.120	0.120	0.120
Aluminum	1.50	0.50	0.10	1.00– 1.50	1.00– 1.50	1.25	0.10	1.25	0.40	1.25	1.00	1.00	1.00	0.75	0.75	0.75	0.75
Manganese	0.40	0.40	0.40	0.40	0.40	0.50	0.50	0.75	0.75	0.75	1.00	1.00	1.00	1.25	—	1.25	—
Calcium ^C	—	—	—	0.50	1.50	—	—	—	—	—	—	—	—	—	—	—	—
Boron	—	—	—	—	—	—	—	—	—	0.04– 0.10	—	0.04– 0.10	0.04– 0.10	—	—	0.04– 0.10	0.04– 0.10

^A A single value indicates a maximum, except for calcium.

^B When shipped in 3000 lb containers, the average boron content of a container shall not vary from the average reported for the entire shipment by more than 0.010 %.

^C Minimum.



TABLE 2 Standard Sizes and Tolerances

Grades	Standard Sizes	Tolerances and Sieve Sizes Defined by ASTM Specification E11		Friability Rating ⁴
C,D,E	8-in. (203-mm) by 4-in. (102-mm)	90-lb (40.8-kg) lump, max	10 %, max, passing 4-in. (102-mm) sieve	
	8-in. (203-mm) by 2-in. (50.8-mm)	90-lb (40.8-kg) lump, max	10 %, max, passing 2-in. (50.8-mm) sieve	
	5-in. (127-mm) by 2-in. (50.8-mm)	10 %, max, retained on 5-in. (127-mm) sieve	10 %, max, passing 2-in. (50.8-mm) sieve	
	4-in. (102-mm) by ½-in. (12.7-mm)	10 %, max, retained on 4-in. (102-mm) sieve	10 %, max, passing ½-in. (12.7-mm) sieve	
	4-in. (102-mm) by down	10 %, max, retained on 4-in. (102-mm) sieve	12 %, max, passing ¼-in. (6.35-mm) sieve	
	3-in. (76.2-mm) by ½-in. (12.7-mm)	10 %, max, retained on 3-in. (76.2-mm) sieve	15 %, max, passing ½-in. (12.7-mm) sieve	
	3-in. (76.2-mm) by down	10 %, max, retained on 3-in. (76.2-mm) sieve	15 %, max, passing No. 8 (2.38-mm) sieve	
	2-in. (50.8-mm) by ½ in. (12.7-mm)	10 %, max, retained on 2-in. (50.8-mm) sieve	15 %, max, passing ½-in. (12.7-mm) sieve	
	2-in. (50.8-mm) by down	10 %, max, retained on 2-in. (50.8-mm) sieve	15 %, max, passing No. 8 (2.38-mm) sieve	
	1-in. (25.4-mm) by No. 8 (2.38-mm)	5 %, max, retained on 1-in. (25.4-mm) sieve	10 %, max, passing No. 8 (2.38-mm) sieve	
	1-in. (25.4-mm) by down	5 %, max, retained on 1-in. (25.4-mm) sieve	20 %, max, passing No. 8 (2.38-mm) sieve	
C,D,F	Lump or Pig	90-lb (40.8-kg) lump or pig, max		
C,D,E	½-in. (12.7-mm) by No. 8 (2.38-mm)	5 %, max, retained on ½-in. (12.7-mm) sieve	10 %, max, passing No. 8 (2.38-mm) sieve	
	¾-in. (9.51-mm) by No. 6 (3.36-mm)	5 %, max, retained on ¾-in. (9.51-mm) sieve	10 %, max, passing No. 6 (3.36-mm) sieve	
	¾-in. (9.51-mm) by No. 12 (1.68-mm)	5 %, max, retained on ¾-in. (9.51-mm) sieve	10 %, max, passing No. 14 (1.41-mm) sieve	
	¾-in. (9.51-mm) by down	5 %, max, retained on ¾-in. (9.51-mm) sieve	15 %, max, passing No. 70 (0.21-mm) sieve	
	¼-in. (6.35-mm) by down	5 %, max, retained on ¼-in. (6.35-mm) sieve		
	No. 8 (2.38-mm) by down	5 %, max, retained on No. 8 (2.38-mm) sieve		
	No. 28 (841-μm) by down	5 %, max, retained on No. 20 (841-μm) sieve		
G	pig	90-lb (40.8-kg) pig, max.		

⁴See Appendixes.

SUPPLEMENTARY REQUIREMENTS

The composition shall be further limited to the requirements of **Table S1.1**. Upon request of the purchaser, the manufacturer shall furnish an analysis of these elements on a schedule agreed between the manufacturer and purchaser.

TABLE S1.1 Supplementary Chemical Requirements

Element	Grade																		
	C	CA	CB	C1	C2	D	DA	E	Composition, % maximum				F	F1	F1A	G	GA	G1	G1A
									EA	E1	E1A								
Chromium 0.30	0.30	0.30	—	—	0.50	0.50	0.50	0.50	0.15	0.15	0.25	0.25	0.25	—	—	0.25	0.25	—	
Nickel	0.10	0.10	0.10	—	—	0.20	0.20	0.30	0.30	—	—	—	—	—	—	—	—	—	
Copper	0.10	0.10	0.10	—	—	0.20	0.20	0.30	0.30	—	—	—	—	—	—	—	—	—	
Titanium	0.20	0.20	0.20	—	—	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	0.20	—	—	0.20	0.20	

APPENDIX

(Nonmandatory Information)

X1. FRIABILITY RATINGS

X1.1 Proposed friability ratings are shown in **Table X1.1** as follows:

TABLE X1.1 Proposed Friability Ratings for Ferrosilicon

Product Grade	Proposed Friability Rating
C	4
D	4
E	5
F	4
G	2

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A100 – 04) that may impact the use of this standard.

(1) Revised Table 1 and footnotes to Table 1.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).