

# Standard Specification for Ferrovanadium<sup>1</sup>

This standard is issued under the fixed designation A102; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

#### 1. Scope

1.1 This specification covers one grade of ferrovanadium.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

#### 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

A1025 Specification for Ferroalloys and Other Alloying Materials, General Requirements

E365 Test Method for the Determination of Vanadium in Ferrovanadium and Vanadium Alloying Additives (Withdrawn 2005)<sup>3</sup>

#### 3. General Conditions for Delivery

3.1 Materials furnished to this specification shall conform to the requirements of Specification A1025, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A1025 constitutes nonconformance with this specification.

In case of conflict between the requirements of this specification and Specification A1025, this specification shall prevail.

3.2 Although ferrovanadium is ordered by total net weight, the customary basis of payment is per pound of contained vanadium.

#### 4. Chemical Composition

4.1 The material shall conform to the requirements as to chemical composition specified in Table 1.

4.2 The manufacturer shall furnish an analysis of each shipment showing the percentage of each element specified.

#### 5. Size

5.1 The grade is available in sizes as listed in Table 2.

Note 1—The sizes listed in Table 2 are typical as shipped from the manufacturer's plant. Ferrovanadium has a friability code number of "1". It is a tough material, susceptible to little, if any, breakage during shipment or handling.

#### 6. Chemical Analysis

6.1 The chemical analysis of the material shall be made in accordance with the procedure for ferrovanadium as described in Test Methods E365 or alternative methods which will yield equivalent results. For elements other than vanadium the chemical analysis shall be agreed upon by the purchaser and supplier.

6.2 If alternative methods of analysis are used, in case of discrepancy, Test Methods E365 shall be used for referee.

6.3 Where no method is given for the analysis for a particular element, the analysis shall be made in accordance with a procedure agreed upon by the manufacturer and the purchaser.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Oct. 1, 2014. Published October 2014. Originally approved in 1925. Last previous edition approved in 2009 as A102 – 04(2009). DOI: 10.1520/A0102-04R14.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

 $<sup>^{3}\,\</sup>text{The}$  last approved version of this historical standard is referenced on www.astm.org.

### A102 – 04 (2014)

#### TABLE 1 Chemical Requirements<sup>A</sup>

Element	Composition, %	
Vanadium, <sup>B</sup>	75-85	
Carbon, max	0.75	
Silicon, max	1.5	
Aluminum, max	2.0	
Sulfur, max	0.08	
Phosphorus, max	0.08	

<sup>A</sup>For the purposes of determining conformance with this specification, the reported analysis shall be rounded to the nearest unit in the last right-hand place of figures used in expressing the limiting value, in accordance with the rounding method of Practice A1025.

<sup>B</sup>For the purposes of determining the vanadium content of any shipment, vanadium shall be reported to the nearest 0.1 %, applying the same rounding procedure as prescribed in Footnote *A*.

TABLE 2 Sizing Requirements	
Size Requirements	
2 in. (50 mm) by down	
1 in. (25 mm) by down	
½ in. (12.5 mm) by down	
No. 8 (2.36 mm) by down	

#### SUPPLEMENTARY REQUIREMENTS

The composition shall be further limited to the requirements of Table S1.1 in addition to those in Table 1. An analysis of each lot is not required. The manufacturer shall supply, upon request, the results of an analysis for these elements on a cumulative basis over a period mutually agreed upon by the manufacturer and the purchaser.

Element	Maximum Limits Allowable, %
Chromium	0.50
Copper	0.15
Nickel	0.10
Lead	0.020
Tin	0.050
Zinc	0.020
Molybdenum	0.75
Titanium	0.15
Nitrogen	0.20

TABLE S1.1 Supplementary Chemical Requirements

## A102 – 04 (2014)

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/