

Designation: A1044/A1044M - 16a

# Standard Specification for Steel Stud Assemblies for Shear Reinforcement of Concrete<sup>1</sup>

This standard is issued under the fixed designation A1044/A1044M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification covers steel stud assemblies for shear reinforcement of concrete. Stud assemblies consist of either single-headed studs (Type 1) attached to a structural steel base rail by structural welding or stud welding, or double-headed studs (Type 2) mechanically crimped into a non-structural steel shape or attached to a steel plate by spot welding or tack welding. These stud assemblies are not intended for use as shear connectors in steel-concrete composite construction.

Note 1—The configuration of the studs for stud assemblies is much different than the configuration of the headed-type studs prescribed in Section 7, Figure 7.1 of AWS D1.1/D1.1M. Ratios of the cross-sectional areas of the head-to-shank of the AWS D1.1/D1.1M studs range from about 2.5 to 4. In contrast, this specification requires the area of the head of the studs for stud assemblies to be at least 10 times the area of the shank. Thus, the standard headed-type studs in Section 7, Figure 7.1 of AWS D1.1/D1.1M do not conform to the requirements of this specification for use as stud assemblies for shear reinforcement.

1.2 This specification is applicable for orders in either inch-pound units or in SI units.

1.3 The values stated either in inch-pound or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with this specification.

#### 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

A29/A29M Specification for General Requirements for Steel Bars, Carbon and Alloy, Hot-Wrought

A36/A36M Specification for Carbon Structural Steel

A370 Test Methods and Definitions for Mechanical Testing of Steel Products A615/A615M Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement

- A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement
- 2.2 AWS Standard:<sup>3</sup>
- AWS D1.1/D1.1M-2004 Structural Welding Code—Steel

2.3 U.S. Military Standards:<sup>4</sup>

MIL-STD-129 Marking for Shipment and Storage

MIL-STD-163 Steel Mill Products Preparation for Shipment and Storage

2.4 U.S. Federal Standard:<sup>4</sup>

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

## 3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *base rail, n*—the steel shape or plate that a group of headed studs is attached to by welding or other means.

3.1.1.1 *Discussion*—Stud assemblies comprised of singleheaded studs (Type 1) require a base rail; the base rail acts as a structural element to provide anchorage to the concrete. For stud assemblies in which double-headed studs (Type 2) are mechanically crimped into a steel shape, for example, into a steel channel, the base rail is not required to provide anchorage to the concrete; the purpose of the base rail is to hold the studs in the appropriate location, direction, and spacing until the concrete is cast. For stud assemblies in which double-headed studs (Type 2) are attached to a steel plate by spot welding or tack welding, the steel plate is not required to provide anchorage to the concrete; the purpose of the steel plate is to hold the studs in the appropriate location, direction, and spacing until the concrete is cast.

3.1.2 *headed stud*, *n*—a steel bar used in the reinforcement of concrete that has a head formed at one or both ends.

## 4. Ordering Information

4.1 It shall be the responsibility of the purchaser to specify all requirements that are necessary for material ordered to this

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved March 1, 2016. Published May 2016. Originally approved in 2005. Last previous edition approved in 2016 as A1044/A1044M - 16. DOI: 10.1520/A1044\_A1044M-16A.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> Available from American Welding Society (AWS), 8669 NW 36 Street, #130, Miami, FL 33166-6672, http://www.aws.org.

<sup>&</sup>lt;sup>4</sup> Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://dodssp.daps.dla.mil.

specification. Such requirements shall include but are not limited to the following:

4.1.1 Name of product: stud assemblies for shear reinforcement of concrete,

4.1.2 Quantity of studs by diameter,

4.1.3 Number of heads per stud,

4.1.4 Dimensions of base rail, if included,

4.1.5 Overall height of stud assembly,

4.1.6 Number of studs per each assembly and their spacing (see Note 2),

4.1.7 Requirements for inspection (11.1),

4.1.8 Packaging, and

4.1.9 ASTM designation and year of issue.

Note 2—In the case of ordering studs rather than assemblies, the length of the studs should be specified such that the appropriate height of the stud assembly is achieved.

#### 5. Materials and Manufacture

5.1 Headed Studs:

5.1.1 Type 1 single-headed studs and Type 2 double-headed studs shall be manufactured from steel conforming to Specification A29/A29M, Grades 1010 through 1020. The stud material and base rail material shall conform to the requirements for tensile properties prescribed in Table 1.

5.1.2 For Type 2 double-headed studs manufactured from deformed steel reinforcing bars, the deformed bars shall conform to Specification A615/A615M or Specification A706/A706M, Grade 60 [420].

5.2 Base Rails:

5.2.1 For stud assemblies in which the stude (Type 1) are welded to a base rail, the base rail material shall conform to 5.2.1.1, 5.2.1.2, or 5.2.1.3.

5.2.1.1 The base rail material, except for tensile properties, shall conform to Specification A36/A36M or equivalent. The base rail material shall conform to the requirements for tensile properties prescribed in Table 2.

5.2.1.2 Base rail material conforming to the minimum required tensile properties in Specification A36/A36M shall be permitted provided the base rail thickness is increased by a factor equal to the minimum yield strength specified in Table 2 divided by the minimum yield strength required by Specification A36/A36M.

5.2.1.3 Base rail material selected by the manufacturer shall be permitted subject to agreement with the purchaser. The manufacturer shall furnish documentation to the purchaser in the form of test reports that confirms the suitability of the selected base rail material for: (1) manufacturing stud assemblies; and (2) structural adequacy of the stud assemblies for the intended application.

5.2.2 For stud assemblies in which single-headed (Type 1) studs are attached to base rails by stud welding, the stud

TABLE 1 Tensile Requirements—Stud Material—Type 1 and Type 2 Studs

Tensile strength, min, psi [MPa]	65 000 [450]
Yield strength, min, psi [MPa]	51 000 [350]
Elongation in 2 in. [50 mm], min, %	20
Reduction of area, min, %	50

Tensile strength, min, psi [MPa]	65 000 [450]
Yield strength, min, psi [MPa]	44 000 [300]
Elongation in 8 in. [200 mm], min, %	20

<sup>A</sup> Type 1 studs welded to base rail.

welding shall conform to AWS D1.1/D1.1M, including the provisions for production control, and fabrication and verification requirements.

5.2.3 For stud assemblies in which double-headed studs (Type 2) are mechanically crimped into a steel shape, the steel shape shall be sufficiently stiff to hold the studs in the appropriate location, direction, and spacing.

5.2.4 For stud assemblies in which double-headed studs (Type 2) are attached to a steel plate by spot welding or tack welding, the steel plate shall be sufficiently stiff to hold the studs in the appropriate location, direction and spacing.

#### 5.3 Dimensions:

5.3.1 Minimum dimensions of Type 1 single-headed studs and plate base rails shall conform to Table 3.

5.3.2 Minimum dimensions of Type 2 double-headed studs shall conform to Table 4.

NOTE 3-The configurations of stud assemblies are shown in Fig. 1.

5.3.3 Headed studs with heads that have variable thickness shall be permitted, provided they meet the tensile requirements of this specification.

## 6. Tensile Tests

6.1 At periodic intervals, tensile tests of the headed stud with a single or double head formed at one or both ends of the shank or welded to the base rail shall be performed as specified in the quality assurance program of the manufacturer and agreed upon by the purchaser. Tensile tests on the studs shall be conducted by the assembly manufacturer, or an inspection agency, or the stud manufacturer.

6.2 Tensile testing shall be performed in accordance with the requirements described in Test Methods and Definitions A370. Tensile testing of headed studs shall be performed using a test fixture as described in Section 7.3.2 of AWS D1.1/D1.1M.

#### 7. Acceptance Criteria

7.1 In addition to meeting the strength requirements of 5.1 and 5.2, no observed partial or total fracture of the head, the stud weld, or the stud-to-base rail connection shall be permitted. The failure shall occur either in the stud material a minimum of one-half shank diameter from the head-to-shank or the stud-to-base rail connection, or by tearing a hole in the base rail. Failure of the head or stud-to-base rail connection within the attachment region shall be cause for rejection. The tensile force at which failure occurs shall exceed the minimum specified yield strength of the stud material.

#### 8. Number of Tests

8.1 A minimum of two tensile tests shall be conducted during a production shift or period. It shall be permissible to

# 🕼 A1044/A1044M – 16a

#### TABLE 3 Minimum Dimensions—Type 1 Single-Headed Studs and Base Rails

Stud Shank	Stud Head			Base	e Rail <sup>A</sup>
Diameter ( <i>d</i> ), in. [mm] <sup>B</sup>	Diameter ( <i>D</i> ), in. [mm] <sup>C</sup>	Thickness ( <i>t<sub>h</sub></i> ), in. [mm]	Radius at Connection of Stud Shank with Stud Head, in. [mm]	Width ( <i>b</i> ), in. [mm]	Thickness $(t_{\rho})$ , in. [mm]
0.375 [9.5] 0.500 [12.7] 0.625 [15.9] 0.750 [19.1]	1.19 [30.1] 1.58 [40.2] 1.98 [50.2] 2.37 [60.2]	0.21 [5.3] 0.28 [7.1] 0.35 [8.9] 0.42 [10.7]	0.25 [6.4] 0.25 [6.4] 0.25 [6.4] 0.375 [9.5]	1.00 [25.4] 1.25 [31.8] 1.75 [44.5] 2.00 [50.8]	<sup>3</sup> ∕16 [4.8] 1⁄4 [6.5] 5⁄16 [7.9] 3∕8 [9.5]

<sup>A</sup> Length of base rail specified by purchaser.

<sup>B</sup> Tolerance: -0.010 in. [-0.25 mm].

<sup>c</sup> Tolerance: -0.015 in. [-0.38 mm].

#### TABLE 4 Minimum Dimensions—Type 2 Double-Headed Studs

Stud	Shank	Stud Head		
Bar Designation No.	Diameter ( <i>d</i> ), in. [mm]	Niniume Cross-Sectional Area, <sup>a</sup> in. [mm]	Thickness ( <i>E</i> )	
3 [10] 4 [13] 5 [16] 6 [19] 8 [25]	0.375 [9.5] 0.500 [12.7] 0.625 [15.9] 0.750 [19.1] 1.000 [25.4]	1.10 [710] 2.00 [1290] 3.10 [1990] 4.40 [2840] 7.90 [5100]	Thickness required to meet minimum tensile strength and acceptance criteria	
Tolerances	Specification A615/A615M or A706/A706M	Specification A615/A615M or A706/A706M	+0.08 in./–0.12 in. [+2 mm/–3 mm]	

<sup>A</sup> Stud head may be any shape: round, square, or rectangular.



FIG. 1 Stud Assemblies: (a) Type 1 Single-Headed Studs Welded to a Base Rail; (b) Type 2 Double-Headed Studs Crimped into a Steel Channel; (c) Type 2 Double-Headed Studs Spot Welded or Tack Welded to a Steel Plate; (d) Detail of Type 1 Head; (e) Detail of Type 2 Head

test separate base rail material of the same thickness, chemical composition, and configuration of the base rails used in production. One test at the start and one test at the end of each 8-h production shift or less than 8-h production period, or at random intervals during the production period, shall be conducted.

8.2 In the event different heats of stud or base rail material within the same material specification are used to produce stud assemblies during a production run, a minimum of two tensile tests in accordance with Section 6 shall be conducted to verify the production method, product quality, and weldability of the heats of materials prior to continuing production.

8.3 Any identified procedural or performance deficiencies shall be corrected and testing repeated until the tensile test results meet the requirements of this specification.

## 9. Retests

9.1 If the tension test fails before meeting the specified minimum yield strength of the headed stud material in accordance with 5.1, but is within 2000 psi [14 MPa] of the required tensile strength, and if the fracture is not located within one-half shank diameter from the head-to-shank or stud-to-base rail connection, then a retest shall be allowed. Two specimens taken at random from the production lot shall be tested during a retest. Both assembled specimens shall pass the minimum yield strength requirements of 5.1 and 5.2 or the lot shall be rejected.

9.2 If any test specimen fails because of mechanical reasons such as failure of the testing equipment or from flaws caused by specimen preparation, shipment or other damage unrelated to fabrication or testing, it shall be discarded and another specimen from the same production lot substituted.

## 10. Finish

10.1 Finished studs shall be of uniform quality and condition, free of discontinuous laps, seams, fins, or other discontinuities that would adversely affect welding or structural strength of the studs. Radial cracks or bursts in the head(s) of the studs shall not be cause for rejection provided that the length of cracks or bursts do not exceed the value 0.25 times (head diameter – shank diameter), or using the notation in Fig. 1: 0.25 (D - d). Surface rust and mill scale shall not be cause for rejection provided they do not adversely affect welding or structural strength of the stud assembly.

Note 4—Heads of studs are subject to cracks or bursts, which are terms for the same thing. Cracks or bursts designate an abrupt interruption of the periphery of the stud head by radial separation of the metal.

## 11. Inspection

11.1 Inspection of the stud assemblies shall be agreed upon between the purchaser and the manufacturer as part of the purchase order or contract.

## 12. Rejection

12.1 The purchaser shall have the right to perform any of the inspections and tests as set forth in this specification as deemed necessary. Unless otherwise specified, any rejection based on tests made in accordance with this specification shall be reported to the manufacturer within five working days from the receipt of samples by the purchaser.

12.2 Material which does not meet the requirements of this specification subsequent to its acceptance at the manufacturer's facilities shall be subject to rejection, and the manufacturer shall be promptly notified.

## 13. Rehearing

13.1 Samples tested in accordance with this specification which represent rejected material shall be preserved for two weeks from the date rejection is reported to the manufacturer. In case of dissatisfaction with the results of the test, the manufacturer shall make claim for a rehearing within that time.

## 14. Certification and Test Reports

14.1 A manufacturer's product certificate shall accompany stud assemblies when they are shipped from the manufacturer's facilities to the purchaser. The certificate shall include a statement of compliance to this specification, copies of test reports required by 14.2 and 14.3, and a statement of compliance with AWS D1.1/D1.1M in the case of stud-welded rails.

14.2 A certified mill test report shall be furnished by the manufacturer containing, on a per heat basis, the chemical analysis of the stud material, as well as the base rail, if present.

14.3 A test report shall be required of the manufacturer for the production of stud assemblies as described in Section 6. A copy of the test report shall be provided to the purchaser upon request.

14.4 A Material Test Report, Certificate of Inspection, or similar document printed from or used in electronic form from an electronic data interchange (EDI) transmission shall be regarded as having the same validity as a counterpart printed in the certifier's facility. The content of the EDI transmitted document shall meet the requirements of the invoked ASTM standard(s) and conform to any existing EDI agreement between the purchaser and the manufacturer. Notwithstanding the absence of a signature, the organization submitting the EDI transmission is responsible for the content of the report.

Note 5—The industry definition as invoked here is: EDI is the computer-to-computer exchange of business information in a standard format such as ANSI ASC X12.

## 15. Packaging and Marking

15.1 Headed studs shall be packaged in suitable containers, clearly marked with the stud part number, description, heat number, and manufacturing code or production card number. Stud assemblies shall be shipped color coded with paint indicating the base rail type by width, thickness and length, and the number of headed studs and their diameter per rail type. The color coding used for each assembly, which shall be agreed upon in advance between the purchaser and manufacturer, shall be shown in the shipping documents.

15.2 Each manufacturer shall identify the symbols of its marking system for headed studs.

15.3 All headed studs produced under this specification shall be identified by a distinguishing set of marks legibly stamped onto the flat outer side of the head, away from the shank, to denote the manufacturer.

15.4 The finished stud assembly shall be marked to identify its manufacturer if different from the manufacturer of the headed studs.

15.5 For Government Procurement Only—When specified in the contract or order, and for direct procurement by or direct

## 🖽 A1044/A1044M – 16a

shipment to the U.S. government, material shall be preserved, packaged, and packed in accordance with the requirements of MIL-STD-163. The applicable levels shall be as specified in the contract. Marking for shipment of such material shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for military agencies.

#### 16. Keywords

16.1 base rail; concrete reinforcement; headed studs; shear reinforcement; steel; stud assemblies

## SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A1044/A1044M - 16) that may impact the use of this standard. (Approved March 1, 2016.)

(1) Revised 1.1, 2.1, 3.1.1.1, Section 5, 7.1, and 9.1.
(2) Revised title of Table 1, footnote of Table 2, title of Table 3, and added new Table 4.

(3) Revised image and caption of Fig. 1.

Committee A01 has identified the location of selected changes to this standard since the last issue (A1044/A1044M - 15) that may impact the use of this standard. (Approved Jan. 15, 2016.)

(1) Revised Sections 4 and 11.

Committee A01 has identified the location of selected changes to this standard since the last issue (A1044/A1044M - 05 (2010)) that may impact the use of this standard. (Approved March 1, 2015.)

(1) Revised Section 14.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/