

Standard Specification for Laser-Fused Stainless Steel Bars, Plates, and Shapes¹

This standard is issued under the fixed designation A1069/A1069M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers laser-fused stainless steel bars, plates, and shapes of structural quality for use in bolted or welded structural applications.

1.2 Shapes covered in this specification include those classified in Article 3.1.2 of Specification A6/A6M and those that are made from two or more shapes or plates.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

- A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling
- A240/A240M Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications
- A262 Practices for Detecting Susceptibility to Intergranular Attack in Austenitic Stainless Steels
- A276 Specification for Stainless Steel Bars and Shapes
- A370 Test Methods and Definitions for Mechanical Testing of Steel Products
- A479/A479M Specification for Stainless Steel Bars and Shapes for Use in Boilers and Other Pressure Vessels

- A484/A484M Specification for General Requirements for Stainless Steel Bars, Billets, and Forgings
- A673/A673M Specification for Sampling Procedure for Impact Testing of Structural Steel
- A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment
- A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products
- A923 Test Methods for Detecting Detrimental Intermetallic Phase in Duplex Austenitic/Ferritic Stainless Steels
- A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys
- E190 Test Method for Guided Bend Test for Ductility of Welds
- E208 Test Method for Conducting Drop-Weight Test to Determine Nil-Ductility Transition Temperature of Ferritic Steels
- E290 Test Methods for Bend Testing of Material for Ductility
- 2.2 ISO Standards:
- ISO 13919-1 Welding and Laser-beam Welded Jointsguidance on Quality Levels for Imperfections—Part 1: Steel
- ISO 15609-4 Specification and Qualification of Welding Procedures for Metallic Materials—Welding Procedure Specification
- ISO 15614-11 Specification and Qualification of Welding Procedures for Metallic Materials—Welding Procedure Test—Part 11: Electron and Laser Beam Welding

2.3 U.S. Military Standards:

MIL-STD-129 Marking for Shipment and Storage

2.4 Federal Standards:

Federal Standard No. 123 Marking for Shipment (Civil Agencies)

3. Terminology

3.1 Definitions:

3.1.1 Definitions of terms pertaining to this specification shall be those of Terminology A941, "Standard Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys."

3.2 Definitions of Terms Specific to This Standard:

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.17 on Flat-Rolled and Wrought Stainless Steel.

Current edition approved Sept. 1, 2016. Published September 2016. Originally approved in 2011. Last previous edition approved in 2011 as A1069/A1069M – 11. DOI: 10.1520/A1069_A1069M-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



3.2.1 *laser fusion*, n—a joining process that produces coalescence of material with the heat obtained from the application of a concentrated coherent light beam impinging on the surface of a weld joint.

3.2.2 *stainless steel starting materials, n*—stainless steels (in plate, sheet, strip, shape or bar form prior to joining by laser-fusion) that are then further processed into the final product.

4. Ordering Information

4.1 The purchaser has the responsibility to specify appropriate requirements that are necessary to adequately describe the product ordered under this specification. Such requirements to be considered include, but are not limited to, the following:

4.1.1 Name of structural product (plate, shape, bar, or sheet piling).

4.1.2 Shape designation and applicable dimensions including size, thickness, width, diameter, and length, if applicable.

4.1.3 Type of stainless steel or UNS designation as specified in Table 1 of Specification A240/A240M.

4.1.4 Quantity (weight or number of pieces).

4.1.5 ASTM specification designation and edition year if other than the latest edition.

4.1.6 Condition of fusion welded product, whether as welded, or subsequently stress-relieved, or heat treated.

4.1.7 Finish.

4.2 The purchaser has the option to specify additional requirements, including but not limited to the following:

4.2.1 Supplementary Requirements, if invoked.

4.2.2 Preparation for special delivery.

4.2.3 Special marking requirements.

4.2.4 Other special requirements.

Note 1—A typical ordering description is as follows: 5000 lb (2300 kg), Angle, $L4 \times 4 \times \frac{1}{2}$ in. (L100 × 100 × 13 mm), laser fused, 20 ft

(6 m) in length, Type 304L, ASTM Specification AXXXX dated ____

5. Materials and Manufacture

5.1 Condition:

5.1.1 Stainless steel starting materials shall be in accordance with the requirements of the following specifications.

5.1.1.1 For plates, sheet and strip, stainless steel starting materials shall be in conformance to Specification A240/A240M.

5.1.1.2 For bars and shapes, stainless steel starting materials shall be in conformance to Specification A276.

5.1.1.3 For bars and shapes for use in boilers and other pressure vessels, stainless steel starting materials shall be in conformance to Specification A479/A479M.

5.1.2 Bar and shape products shall be in the as-fused condition.

5.1.3 Fusion weld process shall comply with ISO 15614-11 and ISO 15609-4 standards.

5.1.4 The quality levels of welded joints shall be in accordance with ISO 13919-1 standard. If not otherwise specified, quality level B of ISO 13919-1 standard shall be met.

5.1.5 The tensile strength of the fusion weldment conducted on test specimens excised from the laser fused stainless steel plates, sheet, or strip, as shown in Fig. 1, shall meet or exceed the requirements of Table 2 of A240/A240M, A276, or A479/A479M when any of those materials are specified in the purchase order. Tensile testing and specimen dimensions shall be in accordance with Test Methods A370.

5.1.6 Bend tests in accordance with Article 14 of Test Methods A370 shall be conducted for evaluating the ductility of the fusion weldment. Test coupons shall be excised from the laser fused stainless steel plates in accordance with Fig. 1. The inside diameter for root bend test specimens shall meet the value(s) stipulated in the application specification, or the specific requirements of the purchase order. Root bend tests



FIG. 1 Butt-welded Test Pieces Are Laser-fusion Welded and Then Subsequently Machined Into Tensile Test Bars and Root-bend Test Specimens (Not to Scale)



shall be conducted, removing any flash or melt-through at the roots of the weld, and shall be in accordance with either Test Methods E190 or E290, depending on the thickness of the material and the purchaser's application. Lack of penetration or the presence of cracks, visible to persons with normal or corrected vision, shall be cause for rejection of the weldments.

6. Chemical Composition

6.1 The stainless steel shall conform to the requirements for chemical composition specified in Table 1 of Specifications A240/A240M, A276, or A479/A479M.

6.2 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods, Practices, and Terminology A751.

7. Mechanical Properties

7.1 The as-fused product or test specimens excised from the fused product shall conform to the mechanical test requirements specified in Table 2 of Specifications A240/A240M, A276, or A479/A479M when any of those materials are specified in the purchase order.

8. Dimensions, Mass, and Permissible Variations

8.1 The permitted variations in dimensions shall conform to the requirements of Section 9 of Specification A484/A484M.

9. Quality, Finish, and Appearance of Laser-fused Product

9.1 The product shall be of uniform quality consistent with good manufacturing and inspection practices. Imperfections in the product shall be of such a nature or degree for the type and quality ordered that they shall not adversely affect the forming, machining, or fabrication of finished parts.

10. Packaging, Marking, and Loading for Shipment

10.1 Packaging, marking, and loading for shipment shall be in accordance with Practices A700.

10.2 When specified in the contract or order and for direct procurement by or direct shipment to the U.S. Government, marking for shipment, in addition to requirements specified in the contract or order, shall be in accordance with MIL-STD-129 for military agencies and with Federal Standard No. 123 for civil agencies.

11. Keywords

11.1 joining; laser-fusion; laser-weld; plates; shapes; stain-less

SUPPLEMENTARY REQUIREMENTS

The following standardized supplementary requirements are for use when desired by the purchaser. Those that are considered suitable for use with each material specification are listed in the specification. Other tests may be performed by agreement between the supplier and the purchaser. These additional requirements shall apply only when specified in the order, in which event the specified tests shall be made by the manufacturer or processor before shipment of the material.

S1. Charpy V-notch Impact Test for Structural Shapes:

S1.1 Charpy V-notch impact tests shall be conducted in accordance with Specifications A673/A673M and Test Methods A370.

S1.2 The frequency of testing, the test temperature to be used, and the absorbed energy requirements shall be as specified on the order. Unless otherwise specified in the purchase order, the minimum average absorbed energy for each test shall be 20 ft × lbf [27 J] and the test temperature shall be 70° F [20°C].

S2. Drop-weight Test (for Material 0.625 in. [16 mm] and Over in Thickness):

S2.1 Drop-weight tests shall be made in accordance with Test Method E208. The specimens shall represent the material in the final condition of heat treatment. Agreement shall be reached between the purchaser and the manufacturer or processor as to the number of pieces to be tested and whether a maximum nil-ductility transition (NDT) temperature is mandatory or if the test results are for information only.

S3. Intergranular Corrosion Test:

S3.1 For shapes fabricated from austenitic stainless steels, tests for the presence of undesirable precipitate phases or susceptibility of the weld joint to intergranular corrosion shall be made by cutting and fabricating coupons obtained from the welded test pieces, and exposing them to one or more of the practice reagents described in Practices A262. The purchaser shall prescribe which particular practice(s) shall be followed in the purchase order.

S3.2 For shapes fabricated from duplex austenitic/ferritic stainless steels, tests for the presence of undesirable phases in the weld joint shall be made by cutting and fabricating coupons obtained from the welded test pieces, and testing them per the requirements of Test Methods A923. The purchaser shall prescribe which particular test method(s) shall be followed in the purchase order.

S3.3 The producer shall provide a report of the test results for certification and acceptance of the weld joints to the purchaser prior to shipment of the product.



ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/