



Standard Specification for Stainless and Heat-Resisting Chromium Steel Plate, Sheet, and Strip¹

This standard is issued under the fixed designation A176; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers stainless and heat-resisting chromium steel plate, sheet, and strip available in a wide variety of surface finishes.

1.2 The values stated in inch-pound units are to be regarded as the standard.

NOTE 1—Grades that were previously covered in both Specifications A176 and A240/A240M have been removed from this specification and may now be supplied and purchased in compliance with Specification A240/A240M. The chemical and mechanical property requirements of these grades were identical in Specifications A176 and A240/A240M at the time of removal from Specification A176.

2. Referenced Documents

2.1 ASTM Standards:²

A240/A240M Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A480/A480M Specification for General Requirements for Flat-Rolled Stainless and Heat-Resisting Steel Plate, Sheet, and Strip

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.17 on Flat-Rolled and Wrought Stainless Steel.

Current edition approved May 1, 2009. Published May 2009. Originally approved in 1935. Last previous edition approved in 2004 as A176 – 99 (2004). DOI: 10.1520/A0176-99R09.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 SAE Standard:³

J1086 Practice for Unified Numbering for Metals and Alloys (UNS)

3. Chemical Composition

3.1 The steel shall conform to the requirements as to chemical composition specified in Table 1, and shall conform to applicable requirements specified in Specification A480/A480M.

4. Mechanical Properties

4.1 The material shall conform to the mechanical properties specified in Table 2.

5. General Requirements

5.1 The following requirements for orders for material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A480/A480M.

- 5.1.1 Definitions,
- 5.1.2 General requirements for delivery,
- 5.1.3 Ordering information,
- 5.1.4 Process,
- 5.1.5 Special tests,
- 5.1.6 Heat treatment,
- 5.1.7 Dimensions and permissible variations,
- 5.1.8 Workmanship, finish, and appearance,
- 5.1.9 Number of tests/test methods,
- 5.1.10 Specimen preparation,
- 5.1.11 Retreatment,
- 5.1.12 Inspection,
- 5.1.13 Rejection and reheating,
- 5.1.14 Material test report, and
- 5.1.15 Certification.

³ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

TABLE 1 Chemical Requirements^A

UNS Designation ^B	Type	Composition, %								
		Carbon	Manganese	Phosphorus	Sulfur	Silicon	Chromium	Nickel	Nitrogen	Other Elements ^C
S40300	403	0.15	1.00	0.040	0.030	0.50	11.5–13.0	0.60
S42000	420	0.15 min	1.00	0.040	0.030	1.00	12.0–14.0	0.75	...	Mo 0.50 max
S42200	422	0.20–0.25	0.50–1.00	0.025	0.025	0.50	11.0–12.5	0.50–1.00	...	Mo 0.90–1.25 V 0.20–0.30 W 0.90–1.25
S43100	431	0.20	1.00	0.040	0.030	1.00	15.0–17.0	1.25–2.50
S44200	442	0.20	1.00	0.040	0.040	1.00	18.0–23.0	0.60
S44600	446	0.20	1.50	0.040	0.030	1.00	23.0–27.0	0.75	0.25	...

^A Maximum unless range or minimum is indicated.

^B New designation established in accordance with Practice E527 and SAE J1086.

^C The terms Columbium (Cb) and Niobium (Nb) both relate to the same element.

^D Carbon + nitrogen = 0.030 max.

TABLE 2 Mechanical Test Requirements

UNS Designation	Type	Tensile Strength, min		Yield Strength, min ^A		Elongation in 2 in. or 50 mm, min, %	Hardness, max ^B		Cold Bend, deg ^C
		ksi	MPa	ksi	MPa		Brinell	Rockwell B	
S40300	403	70	485	30	205	25.0 ^D	217	96	180
S42000	420	100 ^E	690	15.0	217	96	...
S42200	422	248	24 ^F	not required
S43100	431	285	29 ^F	not required
S44200	442	65	515	40	275	20.0	217	96	180
S44600	446	65	515	40	275	20.0	217	96	135

^A Yield strength shall be determined by the offset method at 0.2 % in accordance with Test Methods and Definitions A370. Unless otherwise specified (see 5.1.10), an alternative method of determining yield strength may be based on a total extension under load of 0.5 %.

^B Either Brinell or Rockwell B hardness is permissible.

^C Bend test not required for steels thicker than 1 in. (25.4 mm) unless specified by the purchaser.

^D Material 0.050 in. (1.27 mm) and under in thickness shall have a minimum elongation of 20.0 %.

^E Maximum. Type 420 is usually used in the heat-treated condition (quenched and tempered to a specified range of hardness or tensile strength).

^F Rockwell C scale.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).