Standard Specification for Low and Intermediate Tensile Strength Carbon Steel Plates¹

This standard is issued under the fixed designation A283/A283M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

- 1.1 This specification² covers two grades (C and D) of carbon steel plates of structural quality for general application.
- 1.2 When the steel is to be welded, a welding procedure suitable for the grade of steel and intended use or service is to be utilized. See Appendix X3 of Specification A6/A6M for information on weldability.
- 1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exactly equivalents; therefore, each system is to be used independently of the other, without combining values in any way.
- 1.4 For plate produced from coil and furnished without heat treatment or with stress relieving only, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification A6/A6M apply.
- 1.5 This specification contains notes or footnotes, or both, that provide explanatory material. Such notes and footnotes, excluding those in tables and figures, do not contain any mandatory requirements.

2. Referenced Documents

2.1 ASTM Standards:³

A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling

3. General Requirements for Delivery

- 3.1 Plates furnished under this specification shall con-form to the requirements of the current edition of Specification A6/A6M, for the specific date ordered, unless a conflict exists, in which case this specification shall prevail.
- 3.2 Coils are excluded from qualification to this specification until they are processed into finished plates. Plates produced from coil means plates that have been cut to individual lengths from a coil. The processor directly controls, or is responsible for, the operations involved in the processing of a coil into finished plates. Such operations include decoiling, leveling, cutting to length, testing, inspection, conditioning, heat treatment (if applicable), packaging, marking, loading for shipment, and certification.

Note 1—For plates produced from coil and furnished without heat treatment or with stress relieving only, two test results are to be reported for each qualifying coil. Additional requirements regarding plate produced from coil are described in Specification A6/A6M.

4. Process

- 4.1 The steel shall be made by one or more of the following processes: open-hearth, basic-oxygen, or electric-furnace.
 - 4.2 The steel shall be killed.

5. Chemical Requirements

- 5.1 The heat analysis shall conform to the requirements prescribed in Table 1.
- 5.2 The steel shall conform on product analysis to the requirements prescribed in Table 1, subject to the product analysis tolerances in Specification A6/A6M.

6. Mechanical Properties

- 6.1 Tensile Properties:
- 6.1.1 Material as represented by the test specimens shall conform to the requirements as to tensile properties prescribed in Table 2.

7. Keywords

7.1 carbon steel; plates; structural quality

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock and Ships.

Current edition approved Nov. 15, 2013. Published November 2013. Originally approved in 1946. Last previous edition approved in 2012 as A283/A283M – 12a. DOI: 10.1520/A0283_A0283M-13.

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-283/SA 283M in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Chemical Requirements

Elements	Heat Ar	Heat Analysis, %	
	Grade C	Grade D	
Carbon, max	0.24	0.27	
Manganese, max	0.90	0.90	
Phosphorus, max	0.030	0.030	
Sulfur, max	0.030	0.030	
Silicon			
Plates 1½ in. [40 mm] and under, max	0.40	0.40	
Plates over 1½ in. [40 mm]	0.15-0.40	0.15-0.40	
Copper, min % when copper is specified	0.20	0.20	

TABLE 2 Tensile Requirements^A

	Grade C	Grade D
Tensile strength, ksi [MPa]	55–75 [380–515]	60–80 [415–550]
Yield point, min, ksi [MPa]	30 [205]	33 [230]
Elongation in 8 in. [200 mm], min, % ^B	22	20
Elongation in 2 in. [50 mm], min, % ^B	25	23

^A See Specimen Orientation under the Tension Tests section of Specification A6/A6M.

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the order or contract. Standardized supplementary requirements for use at the option of the purchaser are listed in Specification A6/A6M. Those that are considered suitable for use with this specification are listed by title:

- S2. Product Analysis.
- S3. Simulated Post-Weld Heat Treatment of Mechanical Test Coupons.
 - S5. Charpy V-Notch Impact Test.

- S6. Drop Weight Test (for Material 0.625 in. [16 mm] and over in Thickness).
 - S8. Ultrasonic Examination.
 - S15. Reduction of Area.

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A283/A283M – 12a) that may impact the use of this standard. (Approved Nov. 15, 2013.)

(1) Modified phosphorus and sulfur limits in Table 1.

Committee A01 has identified the location of selected changes to this standard since the last issue (A283/A283M - 12) that may impact the use of this standard. (Approved Nov. 1, 2012.)

- (1) Added 4.2.
- (2) Option for killed steel removed from the Supplementary Requirements Section.

Committee A01 has identified the location of selected changes to this standard since the last issue (A283/A283M – 03 (2007)) that may impact the use of this standard. (Approved Aug. 1, 2012.)

- (1) Grades A and B removed from 1.1, Table 1 and Table 2. (3) Added Section 7.
- (2) Revised subject heading and numbering in Section 6.

^B For plates wider than 24 in. [600 mm], the elongation requirement is reduced two percentage points. See elongation requirement adjustments in the Tension Tests section of Specification A6/A6M.



ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).