

Standard Specification for Stress-Relieved Steel Wire for Prestressed Concrete¹

This standard is issued under the fixed designation A421/A421M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers two types of stress-relieved round high-carbon steel wire commonly used in prestressed concrete construction, as follows:

1.1.1 *Type BA* wire is used for applications in which cold-end deformation is used for anchoring purposes (Button Anchorage), and

1.1.2 *Type WA* wire is used for application in which the ends are anchored by wedges, and no cold-end deformation of the wire is involved (Wedge Anchorage).

1.2 A supplementary requirement (S1) is provided for use where low-relaxation wire and relaxation testing for that product is required by the purchaser. The supplementary requirement applies only when specified in the purchase order.

1.3 This specification is applicable for orders in either inch-pounds units (as Specification A421) or in SI units (as Specification A421M).

1.4 The values stated in either inch-pound or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:²

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

E328 Test Methods for Stress Relaxation for Materials and Structures

2.2 Military Standard:³

MIL-STD-129 Marking for Shipment and Storage

2.3 Federal Standard:³

Fed. Std. No. 123 Marking for Shipments (Civil Agencies)

3. Ordering Information

3.1 It shall be the responsibility of the purchaser to specify all requirements that are necessary for material ordered to this specification. Such requirements shall include, but are not limited to, the following:

- 3.1.1 Quantity lb [kg],
- 3.1.2 Nominal diameter,

3.1.3 Name of material (uncoated stress-relieved steel wire for prestressed concrete, Type BA or WA wire),

- 3.1.4 If outside inspection is required (10.1),
- 3.1.5 Packaging,
- 3.1.6 Supplementary Requirement S1 (if desired), and
- 3.1.7 ASTM designation and date of issue.

4. Manufacture

4.1 *Process*—The steel shall be made by any commercially accepted process.

4.2 *Internal Soundness*—A sufficient discard shall be made to ensure freedom from injurious piping and undue segregation.

4.3 *Wire*—The wire shall be cold-drawn to size and suitably stress-relieved after cold drawing by a continuous heat treatment to produce the prescribed mechanical properties.

5. Mechanical Property Requirements

5.1 *Tensile Strength*—The tensile strength of Type BA wire and Type WA wire shall conform to the requirements prescribed in Table 1, and shall be determined as prescribed in Test Methods and Definitions A370, including Annex A4.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Nov. 1, 2015. Published November 2015. Originally approved in 1958. Last previous edition approved in 2010 as A421/A421M – 10. DOI: 10.1520/A0421_A0421M-15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, http://dodssp.daps.dla.mil.

(5) A421/A421M – 15

TABLE 1 Tensile Strength Requirements

Nominal	Tensile Strength, min, psi [MPa]		
Diameter, in. [mm]	Туре ВА	Type WA	
0.192 [4.88]	А	250 000 [1725]	
0.196 [4.98]	240 000 [1655]	250 000 [1725]	
0.250 [6.35]	240 000 [1655]	240 000 [1655]	
0.276 [7.01]	235 000 [1620]	235 000 [1620]	

^A This size is not commonly furnished in Type BA wire.

5.2 Yield Strength:

5.2.1 The minimum yield strength for all wire, measured by the 1.0 % extension under load method, shall not be less than 85 % of the specified minimum tensile strength.

5.2.2 The extension under load shall be measured by an extension extension extension and larger than 0.0001 in./in. [0.0001 mm/mm] of gage length.

5.2.3 The initial load corresponding to the initial stress prescribed in Table 2 shall be applied to the specimen, at which time the extensometer is attached and adjusted to a reading of 0.001 in./in. [0.001 mm/mm] of gage length. The load shall then be increased until the extension extension of 1 %. The load for this extension shall be recorded. The stress corresponding to this load shall meet the requirements for stress at 1 % extension prescribed in Table 2.

5.3 *Elongation*—The total elongation under load of all wire shall not be less than 4.0 % when measured in a gage length of 10 in. [250 mm]. The elongation shall be determined by an extensometer which is placed on the test specimen after a load corresponding to the initial stress prescribed in Table 2 is applied. If the fracture takes place outside of the gage length and the elongation so measured meets the minimum requirements, no further testing shall be required. If the elongation is less than the minimum requirements, the test shall be considered an invalid test and a retest made.

6. Diameter and Permissible Variations

6.1 Wire meeting the requirements of this specification is normally ordered in the nominal diameters shown in Table 1.

6.2 The diameter of the wire shall not vary from the nominal diameter specified by more than ± 0.002 in. [± 0.05 mm].

6.3 The wire shall not be out-of-round by more than 0.002 in. [0.05 mm].

7. Workmanship and Finish

7.1 *Cast*—A wire sample having a chord length of 60 in. [1500 mm] shall have an offset at the center of the chord of not

TABLE 2 Yield Strength Requirements

		5 1		
Nominal Diameter,	Initial Stress,	Minimum S Extension	Minimum Stress at 1 % Extension, psi [MPa]	
in. [mm]	psi [ivira]	Type BA	Type WA	
0.192 [4.88]	29 000 [200]	Α	212 500 [1465]	
0.196 [4.98]	29 000 [200]	204 000 [1407]	212 500 [1465]	
0.250 [6.35]	29 000 [200]	204 000 [1407]	204 000 [1407]	
0.276 [7.01]	29 000 [200]	199 750 [1377]	199 750 [1377]	

^A This size is not commonly furnished in Type BA wire.

more than 3 in. [75 mm]. This is equivalent to a chord of an arc of a circle not less than 25 ft [7.6 m] in diameter.

7.2 *Type BA Wire*—Type BA wire shall be of suitable quality to permit cold forming of button heads for anchorage. Splitting shall not be considered a cause for rejection if the button anchorage is capable of developing the minimum required tensile strength of the wire.

7.3 The wire shall be free of kinks.

7.4 The wire shall be furnished in firmly tied coils having a minimum inside diameter of 48 in. [1200 mm]. Each coil shall be of one continuous length.

7.5 There shall be no welds or joints in the finished wire. Any welds or joints made during manufacture to enable continuity of operations shall be removed.

7.6 The wire shall not be oiled or greased. Slight rusting, provided it is not sufficient to cause pits visible to a person with normal or corrected vision, shall not be cause for rejection.

7.7 Temper colors which result from the stress-relieving operation are considered normal for the finished appearance of this wire.

8. Chemical Requirements

8.1 Variations in manufacturing processes and equipment among wire manufacturers necessitate the individual selection of an appropriate chemical composition at the discretion of the manufacturer.

8.2 Phosphorus and sulfur values shall not exceed the following:

Phosphorus	0.040 %
Sulfur	0.050 %

8.3 The purchaser shall have the right to make an analysis from finished wire representing each heat of steel. Samples for analysis shall be obtained by milling the wire in such a manner as to obtain a sample representative of the entire cross section. Prior to milling, the surface shall be cleaned to remove all foreign matter. All such individual determinations shall not vary from the limits shown in 8.2 by more than 0.008 %.

8.4 For referee purposes, Test Methods, Practices, and Terminology A751 shall be applied.

9. Sampling

9.1 Unless otherwise agreed upon between the manufacturer and the purchaser, one test specimen shall be taken from each 10 coils or less in a lot (Note 1) and tested to determine compliance with 5.1, 5.2, 5.3, 6, and 7.1.

Note 1—The term "lot" means all the coils of wire of the same nominal wire size contained in an individual shipping release or shipping order.

10. Inspection

10.1 The purchaser shall state at the time of order whether outside inspection is required. If outside inspection is required, the manufacturer shall afford the inspector representing the purchaser all reasonable facilities to satisfy the inspector that the material is being furnished in accordance with this specification. All tests and inspections shall be made at the place of manufacture prior to shipment, unless otherwise agreed upon at the time of purchase, and shall be so conducted without unnecessarily interfering with manufacturing operations.

11. Rejection

11.1 Unless otherwise specified, any rejection based on tests made in accordance with this specification shall be reported to the manufacturer within a reasonable length of time.

12. Certification

12.1 If outside inspection is not required, a manufacturer's certification that the material has been tested in accordance with and meets the requirements of this specification shall be the basis of acceptance of the material.

12.2 A Material Test Report, Certificate of Inspection, or similar document printed from or used in electronic form from an electronic data interchange (EDI) transmission shall be regarded as having the same validity as a counterpart printed in the certifier's facility. The content of the EDI transmitted document shall meet the requirements of the invoked ASTM standard(s) and conform to any existing EDI agreement be-

tween the purchaser and the manufacturer. Notwithstanding the absence of a signature, the organization submitting the EDI transmission is responsible for the content of the report.

Note 2—The industry definition as invoked here is: EDI is the computer-to-computer exchange of business information in a standard format such as ANSI ASC X12.

13. Packaging and Package Marking

13.1 The type of wire, size of the wire, ASTM designation A421 [A421M], heat number, and name of the manufacturer shall be marked on a tag securely attached to each coil of wire.

13.2 When specified in the purchase order or contract, and for direct procurement by or direct shipment to the U.S. Government, marking for shipment shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for military agencies.

14. Keywords

14.1 cold-drawn wire; low-relaxation wire; prestressed concrete; steel wire (tendon); stress-relieved wire

SUPPLEMENTARY REQUIREMENTS

S1. LOW-RELAXATION WIRE AND RELAXATION TESTING

The following supplementary requirement shall apply only when specified in the purchase order or contract.

S1.1 Scope

S1.1.1 This supplementary requirement delineates only those details which are peculiar to low-relaxation wire, and to the method of relaxation testing related to single wire tendons having properties generally as described in Specification A421/A421M.

S1.2 Test Method

S1.2.1 Low-relaxation wire shall be tested as prescribed in Test Methods E328.

S1.3 Relaxation Properties

S1.3.1 Low-relaxation wire shall meet the mechanical property requirements of this specification, with the added requirement that relaxation after 1000 h under the conditions of Section S1.5 shall not be more than 2.5 % when initially loaded to 70 % of specified minimum tensile strength or not more than 3.5 % when loaded to 80 % of specified minimum tensile strength of the wire.

S1.4 Yield Strength

S1.4.1 Yield strength of low-relaxation wire as described in 5.2 shall not be less than 90 % of the specified minimum tensile strength of the wire.

S1.5 Conditions of Relaxation Test

S1.5.1 If required, relaxation evidence shall be provided from the manufacturer's records of tests on similarly dimensioned wire of the same grade.

S1.5.2 The temperature of the test specimen shall be maintained at 68 \pm 3.5°F [20 \pm 2°C].

S1.5.3 The test specimen shall not be subjected to any loading prior to the relaxation test.

S1.5.4 The initial load shall be applied uniformly over a period of not less than 3 minutes and not more than 5 minutes, and the gage length shall be maintained constant; load relaxation readings shall commence 1 minute after application of the total load.

S1.5.5 Overstressing of the test specimen during the loading operation shall not be permitted.

S1.5.6 The duration of the test shall be 1000 h or a shorter period extrapolated to 1000 h which can be shown by records to provide similar relaxation values.

S1.5.7 The test gage length shall be at least 60 times the nominal diameter.



SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A421/A421M - 10) that may impact the use of this standard. (Approved Nov. 1, 2015.)

(1) Revised the specification's title.

(2) Revised 1.1, 1.4, 4.1, 12.2, 13.1, and 13.2.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/