



Designation: A473 – 17

## Standard Specification for Stainless Steel Forgings<sup>1</sup>

This standard is issued under the fixed designation A473; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This specification covers austenitic, austenitic-ferritic, ferritic, and martensitic stainless steel forgings for general use, and for low- or high-temperature service.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 Supplementary requirements from Specification A788/A788M may be specified when additional testing, inspection, or processing is required.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

A788/A788M Specification for Steel Forgings, General Requirements

A1058 Test Methods for Mechanical Testing of Steel Products—Metric

E8/E8M Test Methods for Tension Testing of Metallic Materials

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved May 1, 2017. Published May 2017. Originally approved in 1962. Last previous edition approved in 2016 as A473-16. DOI: 10.1520/A0473-17.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

### E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

### 3. Ordering Information

3.1 It is the responsibility of the purchaser to specify all requirements that are necessary for material ordered under this specification. Such requirements may include, but are not limited to, the following:

3.1.1 Quantity (weight or number of pieces),

3.1.2 Dimensions, including prints or sketches,

3.1.3 Name of material (stainless steel forgings),

3.1.4 Type or UNS designation (Table 1),

3.1.5 Condition (Table 2), and

3.1.6 ASTM designation and date of issue.

3.1.7 Test for magnetic permeability if specified by customer purchase order when ordering Types 207 and 205.

3.1.8 Special requirements.

3.2 If possible the intended end use of the item should be given on the purchase order especially when the item is ordered for a specific end use or uses.

NOTE 1—A typical ordering description is as follows: 5 stainless steel forgings, Type 410, Designation A, ASTM Specification A473 dated \_\_\_\_\_. End use: pump blocks for oil well equipment.

### 4. General Requirements

4.1 Material supplied to this specification shall conform to the requirements of Specification A788/A788M, which outlines additional ordering information, manufacturing requirements, testing and retesting methods and procedures, marking, certification, product analysis variations, and additional supplementary requirements.

4.2 If the requirements of this specification are in conflict with the requirements of Specification A788/A788M, the requirements of this specification shall prevail.

### 5. Manufacture

5.1 Material for forgings shall consist of ingots or blooms, billets, slabs, or bars, either forged or rolled from an ingot, and cut to the required length by a suitable process.

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Chemical Requirements<sup>A</sup>**

| UNS Designation <sup>B</sup>      | Type Number | Carbon, % | Manganese, % | Phosphorus, % | Sulfur, % | Silicon, % | Chromium, % | Nickel, % | Molybdenum, %     | Nitrogen, % | Other Elements, %                     |
|-----------------------------------|-------------|-----------|--------------|---------------|-----------|------------|-------------|-----------|-------------------|-------------|---------------------------------------|
| <b>Austenitic Grades</b>          |             |           |              |               |           |            |             |           |                   |             |                                       |
| S20100                            | 201         | 0.15      | 5.5–7.5      | 0.060         | 0.030     | 1.00       | 16.0–18.0   | 3.5–5.5   | ...               | 0.25        |                                       |
| S20200                            | 202         | 0.15      | 7.5–10.0     | 0.060         | 0.030     | 1.00       | 17.0–19.0   | 4.0–6.0   | ...               | 0.25        |                                       |
| S20500                            | 205         | 0.12–0.25 | 14.0–15.5    | 0.060         | 0.030     | 1.00       | 16.5–18.0   | 1.00–1.75 | ...               | 0.32–0.40   |                                       |
| S21900                            | XM-10       | 0.08      | 8.0–10.0     | 0.060         | 0.030     | 1.00       | 19.0–21.5   | 5.5–7.5   | ...               | 0.15–0.40   |                                       |
| S21904                            | XM-11       | 0.04      | 8.0–10.0     | 0.060         | 0.030     | 1.00       | 19.0–21.5   | 5.5–7.5   | ...               | 0.15–0.40   |                                       |
| S28200                            | ...         | 0.15      | 17.0–19.0    | 0.045         | 0.030     | 1.00       | 17.0–19.0   | ...       | 0.75–1.25         | 0.40–0.60   | Cu 0.75–1.25                          |
| S30200                            | 302         | 0.15      | 2.00         | 0.045         | 0.030     | 1.00       | 17.0–19.0   | 8.0–10.0  | ...               | 0.10        |                                       |
| S30215                            | 302B        | 0.15      | 2.00         | 0.045         | 0.030     | 2.00–3.00  | 17.0–19.0   | 8.0–10.0  | ...               | ...         |                                       |
| S30300                            | 303         | 0.15      | 2.00         | 0.20          | 0.15 min  | 1.00       | 17.0–19.0   | 8.0–10.0  | 0.60 <sup>C</sup> | ...         |                                       |
| S30323                            | 303 Se      | 0.15      | 2.00         | 0.20          | 0.06      | 1.00       | 17.0–19.0   | 8.0–10.0  | ...               | ...         | Se 0.15 min                           |
| S30400                            | 304         | 0.08      | 2.00         | 0.045         | 0.030     | 1.00       | 18.0–20.0   | 8.0–10.5  | ...               | 0.10        |                                       |
| S30403                            | 304L        | 0.030     | 2.00         | 0.045         | 0.030     | 1.00       | 18.0–20.0   | 8.0–12.0  | ...               | 0.10        |                                       |
| S30500                            | 305         | 0.12      | 2.00         | 0.045         | 0.030     | 1.00       | 17.0–19.0   | 10.5–13.0 | ...               | ...         |                                       |
| S30800                            | 308         | 0.08      | 2.00         | 0.045         | 0.030     | 1.00       | 19.0–21.0   | 10.0–12.0 | ...               | ...         |                                       |
| S30815                            | ...         | 0.10      | 0.80         | 0.040         | 0.030     | 1.40–2.00  | 20.0–22.0   | 10.0–12.0 | ...               | 0.14–0.20   | Ce 0.03–0.08                          |
| S30900                            | 309         | 0.20      | 2.00         | 0.045         | 0.030     | 1.00       | 22.0–24.0   | 12.0–15.0 | ...               | ...         |                                       |
| S30908                            | 309S        | 0.08      | 2.00         | 0.045         | 0.030     | 1.00       | 22.0–24.0   | 12.0–15.0 | ...               | ...         |                                       |
| S31000                            | 310         | 0.25      | 2.00         | 0.045         | 0.030     | 1.50       | 24.0–26.0   | 19.0–22.0 | ...               | ...         |                                       |
| S31008                            | 310S        | 0.08      | 2.00         | 0.045         | 0.030     | 1.50       | 24.0–26.0   | 19.0–22.0 | ...               | ...         |                                       |
| S31254                            | ...         | 0.020     | 1.00         | 0.030         | 0.010     | 0.80       | 19.5–20.5   | 17.5–18.5 | 6.0–6.5           | 0.18–0.25   | Cu 0.50–1.00                          |
| S31400                            | 314         | 0.25      | 2.00         | 0.045         | 0.030     | 1.50–3.00  | 23.0–26.0   | 19.0–22.0 | ...               | ...         |                                       |
| S31600                            | 316         | 0.08      | 2.00         | 0.045         | 0.030     | 1.00       | 16.0–18.0   | 10.0–14.0 | 2.00–3.00         | 0.10        |                                       |
| S31603                            | 316L        | 0.030     | 2.00         | 0.045         | 0.030     | 1.00       | 16.0–18.0   | 10.0–14.0 | 2.00–3.00         | 0.10        |                                       |
| S31700                            | 317         | 0.08      | 2.00         | 0.045         | 0.030     | 1.00       | 18.0–20.0   | 11.0–15.0 | 3.0–4.0           | 0.10        |                                       |
| S32100                            | 321         | 0.08      | 2.00         | 0.045         | 0.030     | 1.00       | 17.0–19.0   | 9.0–12.0  | ...               | ...         | Ti 5xC min                            |
| S34700                            | 347         | 0.08      | 2.00         | 0.045         | 0.030     | 1.00       | 17.0–19.0   | 9.0–13.0  | ...               | ...         | Cb+Ta 10xC, min                       |
| S34800                            | 348         | 0.08      | 2.00         | 0.045         | 0.030     | 1.00       | 17.0–19.0   | 9.0–13.0  | ...               | ...         | Cb+Ta 10xC, min<br>Ta 0.10<br>Co 0.20 |
| <b>Austenitic-Ferritic Grades</b> |             |           |              |               |           |            |             |           |                   |             |                                       |
| S32550 <sup>D</sup>               | ...         | 0.04      | 1.50         | 0.040         | 0.030     | 1.00       | 24.0–27.0   | 4.5–6.5   | 2.9–3.9           | 0.10–0.25   | Cu 1.50–2.50                          |
| S32760 <sup>D</sup>               | ...         | 0.030     | 1.00         | 0.030         | 0.010     | 1.00       | 24.0–26.0   | 6.0–8.0   | 3.0–4.0           | 0.20–0.30   | Cu 0.50–1.00<br>W 0.50–1.00           |
| S32950                            | ...         | 0.03      | 2.00         | 0.035         | 0.010     | 0.60       | 26.0–29.0   | 3.5–5.2   | 1.00–2.50         | 0.15–0.35   |                                       |
| <b>Ferritic Grades</b>            |             |           |              |               |           |            |             |           |                   |             |                                       |
| S40500                            | 405         | 0.08      | 1.00         | 0.040         | 0.030     | 1.00       | 11.5–14.5   | 0.60      | ...               | ...         | A1 0.10–0.30                          |
| S42900                            | 429         | 0.12      | 1.00         | 0.040         | 0.030     | 1.00       | 14.0–16.0   | 0.75      | ...               | ...         |                                       |
| S43000                            | 430         | 0.12      | 1.00         | 0.040         | 0.030     | 1.00       | 16.0–18.0   | 0.75      | ...               | ...         |                                       |
| S43020                            | 430F        | 0.12      | 1.25         | 0.06          | 0.15 min  | 1.00       | 16.0–18.0   | 0.75      | 0.60 <sup>C</sup> | ...         |                                       |
| S43023                            | 430F Se     | 0.12      | 1.25         | 0.06          | 0.06      | 1.00       | 16.0–18.0   | 0.75      | ...               | ...         | Se 0.15 min                           |
| S44600                            | 446         | 0.20      | 1.50         | 0.040         | 0.030     | 1.00       | 23.0–27.0   | 0.75      | ...               | 0.25        |                                       |
| <b>Martensitic Grades</b>         |             |           |              |               |           |            |             |           |                   |             |                                       |
| S40300                            | 403         | 0.15      | 1.00         | 0.040         | 0.030     | 0.50       | 11.5–13.0   | ...       | ...               | ...         |                                       |
| S41000                            | 410         | 0.15      | 1.00         | 0.040         | 0.030     | 1.00       | 11.5–13.5   | 0.75      | ...               | ...         |                                       |
| S41008                            | 410S        | 0.08      | 1.00         | 0.040         | 0.030     | 1.00       | 11.5–13.5   | 0.75      | ...               | ...         |                                       |
| S41400                            | 414         | 0.15      | 1.00         | 0.040         | 0.030     | 1.00       | 11.5–13.5   | 1.25–2.50 | ...               | ...         |                                       |
| S41425                            | ...         | 0.05      | 0.50–1.00    | 0.020         | 0.005     | 0.50       | 12.0–15.0   | 4.0–7.0   | 1.50–2.00         | 0.06–0.12   | Cu 0.30                               |
| S41500                            | E           | 0.05      | 0.5–1.0      | 0.030         | 0.030     | 0.60       | 11.5–14.0   | 3.5–5.5   | 0.40–0.80         | ...         |                                       |
| S41600                            | 416         | 0.15      | 1.25         | 0.06          | 0.15 min  | 1.00       | 12.0–14.0   | ...       | 0.60 <sup>C</sup> | ...         |                                       |
| S41623                            | 416 Se      | 0.15      | 1.25         | 0.06          | 0.06      | 1.00       | 12.0–14.0   | ...       | ...               | ...         | Se 0.15 min                           |
| S42000                            | 420         | Over 0.15 | 1.00         | 0.040         | 0.030     | 1.00       | 12.0–14.0   | ...       | ...               | ...         |                                       |
| S43100                            | 431         | 0.20      | 1.00         | 0.040         | 0.030     | 1.00       | 15.0–17.0   | 1.25–2.50 | ...               | ...         |                                       |
| S44002                            | 440A        | 0.60–0.75 | 1.00         | 0.040         | 0.030     | 1.00       | 16.0–18.0   | ...       | 0.75              | ...         |                                       |
| S44003                            | 440B        | 0.75–0.95 | 1.00         | 0.040         | 0.030     | 1.00       | 16.0–18.0   | ...       | 0.75              | ...         |                                       |
| S44004                            | 440C        | 0.95–1.20 | 1.00         | 0.040         | 0.030     | 1.00       | 16.0–18.0   | ...       | 0.75              | ...         |                                       |

<sup>A</sup> Maximum, unless range or minimum is indicated.

<sup>B</sup> New designation established in accordance with Practice E527 and SAE J 1086.

<sup>C</sup> At manufacturer's option; reported only when intentionally added.

<sup>D</sup> % Cr + 3.3 × % Mo + 16 × % N ≥ 40.

<sup>E</sup> Wrought version of CA6NM.

5.2 The material shall be forged by hammering, pressing, rolling, extruding, or upsetting. It shall be brought as nearly as possible to the finished shape and size by hot-working; and shall be processed, if practicable, so as to cause metal-flow

during the hot-working operation in the direction most favorable for resisting the stresses encountered in service as may be indicated to the manufacturer by the purchaser.

**TABLE 2 Mechanical Property Requirements**

| Type   | Condition                  | Yield Strength, min,<br>ksi (MPa) <sup>A</sup> | Tensile Strength, min,<br>ksi (MPa) | Elongation<br>in 2 in.<br>(50 mm) or<br>4D, min % | Reduction<br>of Area,<br>min, % | Brinell<br>Hardness<br>Number,<br>max |
|--|----------------------------|--|-------------------------------------|---|---------------------------------|---------------------------------------|
| <b>Austenitic Grades</b>   |                            |  |                                     |   |                                 |                                       |
| 201, 302, 302B, 303, 303SE, 305, 308, 309,<br>309S, 310, 310S, 314, 317, 321, 347, 348 | A                          | 30 (205)                                       | 75 (515)                            | 40  | 50                              | ...                                   |
| 202  | A                          | 45 (310)                                       | 90 (620)                            | 40  | 50                              | ...                                   |
| 205  | A                          | 50 (345)                                       | 90 (620)                            | 40  | 50                              | ...                                   |
| 304 and 316, Sections 5 in. (127 mm) and<br>Under                                      | A                          | 30 (205)                                       | 75 (515)                            | 40  | 50                              | ...                                   |
| 304 and 316, Sections Over 5 in. (127 mm)  | A                          | 30 (205)                                       | 70 (485)                            | 40  | 50                              | ...                                   |
| 304L and 316L  | A                          | 25 (170)                                       | 65 (450)                            | 40  | 50                              | ...                                   |
| XM-10 and XM-11  | A                          | 50 (345)                                       | 90 (620)                            | 45  | 60                              | ...                                   |
| S28200   | A                          | 60 (415)                                       | 110 (760)                           | 40  | 55                              | ...                                   |
| S30815   | A                          | 45 (310)                                       | 87 (600)                            | 40  | 50                              | ...                                   |
| S31254   | A                          | 44 (300)                                       | 95 (650)                            | 35  | 50                              | ...                                   |
| <b>Austenitic-Ferritic Grades</b>  |                            |  |                                     |   |                                 |                                       |
| S32550   | A                          | 80 (550)                                       | 109 (750)                           | 25.0  | ...                             | 290                                   |
| S32950   | A                          | 70 (480)                                       | 100 (690)                           | 15  | ...                             | 293                                   |
| S32760   | A                          | 80 (550)                                       | 109 (750)                           | 25  | ...                             | 290                                   |
| <b>Ferritic Grades</b>   |                            |  |                                     |   |                                 |                                       |
| 430F, 430FSE, 446  | A                          | 40 (275)                                       | 70 (485)                            | 20  | 45                              | 223                                   |
| 405  | A                          | 30 (205)                                       | 60 (415)                            | 20  | 45                              | 207                                   |
| 429  | A                          | 35 (240)                                       | 65 (450)                            | 23  | 45                              | 207                                   |
| 430  | A                          | 35 (240)                                       | 70 (485)                            | 20  | 45                              | 217                                   |
| <b>Martensitic Grades</b>  |                            |  |                                     |   |                                 |                                       |
| 403, 410, 416, 416SE   | A                          | 40 (275)                                       | 70 (485)                            | 20  | 45                              | 223                                   |
| 403, 410   | 1                          | 40 (275)                                       | 70 (485)                            | 20  | 45                              | 223                                   |
|  | 2                          | 85 (585)                                       | 110 (760)                           | 15  | 45                              | 269                                   |
|  | 3                          | 100 (690)                                      | 130 (895)                           | 12  | 35                              | 331                                   |
| 410S   | A                          | 35 (240)                                       | 65 (450)                            | 22  | 45                              | 217                                   |
| 414  | A                          | ...  | ...                                 | ...   | ...                             | 298                                   |
|  | T                          | 90 (620)                                       | 115 (795)                           | 15  | 45                              | 321                                   |
|  | H                          | 100 (690)                                      | 125 (860)                           | 15  | 45                              | 321                                   |
| S41425   | T                          | 95 (655)                                       | 120 (825)                           | 15  | 45                              | 321                                   |
| S41500   | normalized and<br>tempered | 90 (620)                                       | 115 (795)                           | 15  | 45                              | 295                                   |
| 420  | A                          | ...  | ...                                 | ...   | ...                             | 223                                   |
| 431  | A                          | ...  | ...                                 | ...   | ...                             | 277 <sup>B</sup>                      |
|  | T                          | 90 (620)                                       | 115 (795)                           | 15  | ...                             | 321                                   |
|  | H                          | 135 (930)                                      | 175 (1210)                          | 13  | ...                             | 440                                   |
| 440A, 440B, 440C   | A                          | ...  | ...                                 | ...   | ...                             | 269                                   |

<sup>A</sup> Yield strength shall be determined by the 0.2 % offset method in accordance with Test Methods and Definitions A370. An alternative method of determining yield strength may be used based on a total extension under load of 0.5 %.

<sup>B</sup> Type 431 forgings of designation A, when specified, shall be capable of meeting the above mechanical property requirements of designation T after oil quenching from 1800 to 1900 °F (980 to 1038 °C) and tempering at not less than 1100 °F (595 °C), or designation H when oil quenched from 1850 to 1950 °F (1010 to 1065 °C) and tempered at not more than 700 °F (370 °C).

5.3 When specified on the order, a sample forging may be sectioned and etched to show flow lines and the condition as regards internal imperfections. When so specified, the question of acceptable and unacceptable metal-flow shall be subject to agreement between the manufacturer and the purchaser prior to order entry.

5.4 When specified on the order, the manufacturer shall submit for approval of the purchaser a sketch showing the shape of the rough forging before machining, or before heat treating for mechanical properties.

5.5 The grain size shall be as fine as practicable and precautions shall be taken to minimize grain growth.

## 6. Heat Treatment

6.1 Except for S31254, the austenitic steels shall receive a solution heat treatment, consisting of heating the material to a minimum temperature of 1900 °F (1040 °C), followed by cooling rapidly in air or water.

6.2 S31254 shall receive a solution heat treatment, consisting of heating the material to a minimum temperature of 2100 °F (1150 °C) followed by cooling rapidly in air or water.

6.3 When specified, Types 347, 348, and 321 shall receive a stabilization heat treatment in addition to the solution heat treatment specified in 6.1, which shall consist of holding the forgings at 1550 to 1750 °F (845 to 955 °C) for 1 h for each inch of section thickness with a minimum holding time of 2 h, followed by air-cooling or water quenching. The stabilization heat treatment is not usually specified, unless these steels are intended for severely corrosive environments in the temperature range from 800 to 1600 °F (425 to 870 °C). When specified, the stabilization heat treatment shall be the final heat treatment and may be performed before machining.

6.4 S32950 shall receive an annealing treatment, consisting of heating the material to a temperature of 1825 °F (995 °C) to 1875 °F (1025 °C) for an appropriate time followed by water quenching or rapid cooling by other means.

6.5 S32760 shall receive an annealing treatment consisting of heating the material to a minimum temperature of 2010 °F (1100 °C), followed by water quenching or rapid cooling by other means.

6.6 The ferritic grades shall be properly annealed:

6.7 Except for S41425 and S41500, the martensitic grades shall be annealed, or hardened and tempered as specified. Liquid quenching shall be permitted only by agreement with the purchaser.

6.8 For S41425, heat to 1700 °F (925 °C) minimum and hold for 1 h at temperature minimum. Air cool to below 90 °F (32 °C) and temper at 1100 °F (595 °C) minimum for 1 h/in. of cross-sectional thickness minimum.

6.9 For S41500 heat to 1750 °F (955 °C) minimum, air cool to 200 °F (95 °C) or lower prior to any optional intermediate temper and prior to the final temper. The final temper shall be between 1050 °F (565 °C) and 1150 °F (620 °C).

6.10 Types 420, 440A, 440B, and 440C should be used by the purchaser in the hardened and tempered condition. In response to heat treatment, these materials shall be capable of meeting the minimum hardness requirements as specified in **Table 3**.

6.11 Types 403 and 410 tempered material shall be normalized, or shall be liquid quenched from 1700 °F (925 °C), minimum, followed by being held at the tempering temperature for at least 1 h/in. (25.4 mm) of cross section in accordance with **6.11.1**, **6.11.2** or **6.11.3**.

6.11.1 *Condition 1*—1250 °F (675 °C) minimum, 1400 °F (760 °C) maximum.

6.11.2 *Condition 2*—1100 °F (595 °C) minimum, 1400 °F (760 °C) maximum.

6.11.3 *Condition 3*—1050 °F (565 °C) minimum, 1400 °F (760 °C) maximum.

6.12 Type S32550 shall receive an annealing treatment consisting of heating the material to a minimum temperature of 1940 °F (1060 °C), followed by water quenching of rapid cooling by other means.

## 7. Chemical Composition

7.1 The steel shall conform to the requirements for chemical composition specified in **Table 1**.

7.2 Methods and practices relating to chemical analysis required by this specification shall be in accordance with Test Methods, Practices, and Terminology **A751**.

## 8. Mechanical Properties Requirements

8.1 The material shall conform to the room temperature mechanical requirements specified in **Table 2**.

8.2 Instead of tension tests, hardness requirements, in accordance with **Table 2**, may be specified by the purchaser for the ferritic and the martensitic steels.

8.3 The martensitic grades shall be capable of meeting the hardness requirements, after heat treating, as specified in **Table 3**.

## 9. Magnetic Permeability

9.1 When required by the purchase order, the magnetic permeability of Types 201 and 205 in the annealed condition shall not exceed 1.2 as tested by a Severn-type indicator.

## 10. Prolongations for Tests

10.1 Subject to Sections **11** and **12**, the forgings shall be produced with prolongations for testing, unless otherwise specified. The producer may elect to submit an extra forging to represent each test lot instead of prolongations, or the test specimens can be taken from the forgings themselves.

## 11. Number of Tests

11.1 For all classes of forgings weighing from 5000 to 7000 lb (2270 to 3180 kg) each, at least one tension test shall be made from each forging. Also, one magnetic permeability test must be made when specified on the customer order.

11.2 For all classes of forgings weighing more than 7000 lb each, one tension test shall be made from each end of each forging. In the case of ring forgings, the tension test specimen shall be removed from each of two locations on the periphery, approximately 180° apart, or insofar as practicable from opposite ends of the forging. Also, one magnetic permeability test must be made when specified on the customer order.

11.3 For forgings weighing less than 5000 lb each, one tension test shall be made from each size classification for each heat in each heat-treating charge. When the heat-treating cycles are the same and the furnaces (either batch or continuous type) are controlled within  $\pm 25$  °F ( $\pm 14$  °C) and equipped with recording pyrometers so that complete records of heat treatment are available, then only one tension test from each heat of each size classification is required. Also, one magnetic permeability test must be made when specified on the customer order.

## 12. Test Specimens

12.1 Tension test specimens shall be taken from the test prolongations or from the forgings as provided in Section **10**.

12.2 Depending upon the method of forging, test specimens shall be procured as follows, unless otherwise specified:

**TABLE 3 Response to Heat Treatment**

| Type <sup>A</sup> | UNS    | Heat Treatment <sup>B</sup><br>Temperature<br>°F (°C) | Quenchant | Hardness<br>HRC, min |
|-------------------|--------|---|-----------|----------------------|
| 403               | S40300 | 1750 (955)  | Air       | 35                   |
| 410               | S41000 | 1750 (955)  | Air       | 35                   |
| 410S              | S41008 | 1750 (955)  | Oil       | 25 max               |
| 414               | S41400 | 1750 (955)  | Oil       | 42                   |
| 416               | S41600 | 1750 (955)  | Air       | 35                   |
| 416 Se            | S41623 | 1750 (955)  | Air       | 35                   |
| 420               | S42000 | 1825 (955)  | Air       | 50                   |
| 431               | S43100 | 1875 (1020)   | Oil       | 40                   |
| 440A              | S44002 | 1875 (1020)   | Air       | 55                   |
| 440B              | S44003 | 1875 (1020)   | Oil       | 56                   |
| 440C              | S44004 | 1875 (1020)   | Air       | 58                   |

<sup>A</sup> Samples for testing shall be in the form of a section not exceeding  $\frac{3}{8}$  in. (9.50 mm) in thickness.

<sup>B</sup> Temperature tolerance is  $\pm 25$  °F (14 °C).

12.2.1 The axis of the specimen shall be located at any point midway between the center and the surface of solid forgings; at any point midway between the inner and outer surfaces of the wall of bored forgings; and shall be parallel to the direction of greatest metal flow.

12.2.2 The axis of the specimen shall be tangential to the forging on the periphery; that is, at right angles to both the radius and the axis of the forging.

12.3 The tension test specimens shall be machined to the form and dimensions for standard round tension test specimens with 2-in. or 50-mm gauge length shown in Fig. 5 of Test Methods and Definitions **A370** or Test Methods **E8/E8M** Fig. 8 for forgings ordered to SI units. On small forgings where it is not practicable to use such specimens, the substitution of

specimens conforming to the small-size specimens of Fig. 6 of Test Methods and Definitions **A370** is permitted or for forgings ordered to SI units, refer to Section 10.2 of Test Methods **A1058**.

### **13. Retreatment**

13.1 If any specimen selected to represent any lot as described in Section **12** fails to meet any of the test requirements, the material represented by such specimens may be retreated and resubmitted for test.

### **14. Keywords**

14.1 austenitic-ferritic duplex stainless steel; austenitic stainless steel; ferritic stainless steel; martensitic stainless steel; stainless steel forgings

## **SUMMARY OF CHANGES**

Committee A01 has identified the location of selected changes to this standard since the last issue (A473 – 16) that may impact the use of this standard. (Approved May 1, 2017.)

(1) Revised **Table 2** to add tensile property value requirements for Types 403 and 410 in Conditions 1, 2, and 3.

Committee A01 has identified the location of selected changes to this standard since the last issue (A473 – 15) that may impact the use of this standard. (Approved May 1, 2016.)

(1) Revised **Table 2** to correct the yield and tensile strength value requirements for S41425.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*