



Standard Specification for Ferrochrome-Silicon¹

This standard is issued under the fixed designation A482/A482M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers several grades of ferrochrome-silicon.

1.2 *Units*—The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.2.1 This specification is expressed in both inch-pound units and in SI units; however, unless the purchase order or contract specifies the applicable M specification designation (SI units), the inch-pound units shall apply.

1.2.2 Within the text, the SI units are shown in brackets.

2. Referenced Documents

2.1 *ASTM Standards*:²

A1025 Specification for Ferrous Alloys and Other Alloying Materials, General Requirements

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

E364 Test Methods for Chemical Analysis of Ferrochrome-Silicon (Withdrawn 2006)³

3. General Conditions for Delivery

3.1 Materials furnished to this specification shall conform to the requirements of Specification A1025, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification A1025 constitutes nonconformance with this specification.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.18 on Castings.

Current edition approved Sept. 1, 2016. Published September 2016. Originally approved in 1963. Last previous edition approved in 2011 as A482/A482M – 11. DOI: 10.1520/A0482_A0482M-11R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

In case of conflict between the requirements of this specification and Specification A1025, this specification shall prevail.

4. Chemical Composition

4.1 The various grades shall conform to the requirements as to chemical composition specified in Tables 1 and 2.

4.2 The manufacturer shall furnish an analysis of each shipment showing the percentage of each element specified in Table 1.

4.3 The values shown in Table 2 are expected maximums. Upon request of the purchaser, the manufacturer shall furnish an analysis for any of these elements on a cumulative basis over a period mutually agreed upon between the manufacturer and the purchaser.

5. Size

5.1 The various grades are available in sizes as listed in Table 3.

5.2 The sizes listed in Table 3 are typical as shipped from the manufacturer's plant. These alloys exhibit varying degrees of friability; therefore, some attrition may be expected in transit, storage, and handling. A quantitative test is not available for rating relative friability of ferroalloys. A code system has been developed, therefore, for this purpose, and a number rating each product type is shown in the last column of Table 3. Definitions applicable to these code numbers are given in Specification A1025.

6. Chemical Analysis

6.1 The chemical analysis of the material shall be made in accordance with the procedure for the ferroalloys as described in Test Methods E364, or alternative methods, agreed upon by the purchaser and supplier, that will yield equivalent results.

6.2 If alternative methods of analysis are used, in case of discrepancy, Test Methods E364 shall be used for reference.

6.3 Where a method is not given in Test Methods E364 for the analysis of a particular element, the analysis shall be made in accordance with a procedure agreed upon between the manufacturer and the purchaser.

7. Keywords

7.1 ferrochrome; ferrochrome silicon

*A Summary of Changes section appears at the end of this standard

TABLE 1 Chemical Requirements

Element	Composition, %	
	Grade A	Grade B
Chromium	34.0–38.0	38.0–42.0
Carbon, max	0.060	0.050
Silicon	38.0–42.0	41.0–45.0
Sulfur, max	0.030	0.030
Phosphorus, max	0.030	0.030

TABLE 2 Supplementary Chemical Requirements

Element	Composition, max, percent Ferrochrome-Silicon (Grades A and B)
Nitrogen	0.050
Manganese	0.75
Nickel	0.50
Vanadium	0.50
Copper	0.050
Molybdenum	0.050
Columbium	0.050
Tantalum	0.050
Cobalt	0.10
Aluminum	0.50
Titanium	0.50
Zirconium	0.050
Arsenic	0.005
Lead	0.005
Tin	0.005
Zinc	0.005
Boron	0.005
Antimony	0.005
Silver	0.005
Bismuth	0.005


TABLE 3 Standard Sizes and Tolerances

Product	Standard Sizes	Tolerances ^A	
Ferrochrome-Silicon	75 lb [35 kg] by down	Maximum lump weight - 90 lb [40 kg]. The maximum allowed proportion of lump weight >75 lb [35 kg] is 10%	
	75 lb [35 kg] by 1 in. [25 mm]	Maximum lump weight - 90 lb [40 kg]	Maximum allowed weight passing 1-in. [25 mm] sieve is 10% of the total weight
	75 lb [35 kg] by 2 in. [50 mm]	Maximum lump weight - 90 lb [40 kg]	Maximum allowed weight passing 2-in. [50 mm] sieve is 10% of the total weight
	40 lb [18 kg] by down	Maximum lump weight - 50 lb [23 kg]	
	25 lb [10 kg] by down	Maximum lump weight - 30 lb [14 kg]	
	4 in. [100 mm] by down	10% Maximum weight retained on 4-in. [100 mm] sieve is 10% of the total weight	
	3 in. [75 mm] by down	Maximum weight retained on 3 in. [75 mm] sieve is 10% of the total weight	
	3 by 1/2 in. [75 by 15 mm]	Maximum weight retained on 3-in. [75 mm] sieve is 10% of the total weight	Maximum allowed weight passing 1/2 in. [15 mm] sieve is 10% of the total weight
	2 in. [50 mm] by down	Maximum weight retained on 2-in. [50 mm] sieve is 10% of the total weight	
	2 by 1/4 in. [50 by 5 mm]	Maximum weight retained on 2-in. [50 mm] sieve is 10% of the total weight	Maximum allowed weight passing 1/4 in. [5 mm] sieve is 10% of the total weight
	3/4 in. [20 mm] by down	Maximum weight retained on 3/4 in. [20 mm] sieve is 10% of the total weight	

^A Specifications of sieve sizes used to define tolerances herein are as listed in Specification E11.

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A482 – 05 (2010)) that may impact the use of this standard. (Approved May 1, 2011.)

(1) Added section 1.2, revised Table 3.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/