



# Standard Specification for Drawing Alloy Steel, Sheet and Strip, Hot-Rolled and Cold-Rolled<sup>1</sup>

This standard is issued under the fixed designation A507; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification covers hot-rolled and cold-rolled drawing alloy-steel sheet and strip. Material of this quality is produced principally for applications involving severe cold plastic deformation such as deep drawn or severely formed parts. This steel is produced by a closely controlled steel-making practice designed to assure internal soundness, relative uniformity of chemical composition, and freedom from injurious imperfections.

1.2 The material covered by this specification may be furnished in several conditions, heat treatments, surface finishes, and edges, as specified herein, in coils or cut lengths.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

A505 Specification for Steel, Sheet and Strip, Alloy, Hot-Rolled and Cold-Rolled, General Requirements for  
A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *capable of*—as used in this specification, means that tests need not be performed. However, if application by the purchaser establishes that the material does not meet the requirements, the material shall be subject to rejection.

3.1.2 *drawing alloy steel*—alloy-steel sheet and strip intended for applications involving severe cold plastic deformation such as deep drawn or severely formed parts.

3.1.3 *standard steels*—steel chemical compositions defined as “standard” by the Society of Automotive Engineers (SAE). See Table 1.

3.1.4 *steels other than standard*—steel chemical compositions other than those defined as “standard,” and furnished to the composition limits shown in Table 2.

## 4. General Requirements and Ordering Information

4.1 Material supplied to this specification shall conform to Specification A505, which includes the general requirements and establishes the rules for the ordering information that should be complied with when purchasing material to this specification.

4.2 In addition to the Ordering Information required by Specification A505, the following shall also be included:

4.2.1 Mechanical properties, if required (show properties desired, which must be consistent with the grade and heat treatment),

4.2.2 Surface finish, if other than that normally furnished (see Section 10), and

4.2.3 Application, or end use (identification of the part to be made).

## 5. Manufacture

5.1 *Rolling*—The material shall be furnished either hot-rolled or cold-rolled, as specified on the order.

5.2 *Heat Treatment*—Unless otherwise specified on the order, the material shall be furnished spheroidize-annealed. (See Terminology A941 for heat treatment terms.)

5.2.1 If the material is to be heat treated by other than the producer, the order shall so state. The material may be ordered in the as-rolled condition, in such cases.

## 6. Chemical Requirements

6.1 The heat (cast) analysis shall conform to the requirements for the grade specified on the order.

6.1.1 Standard steels listed in Table 1 are those commonly produced for drawing alloy-steel sheet and strip.

6.1.2 Nonstandard steel grades may be specified, using the ranges and limits shown in Table 2.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.19 on Steel Sheet and Strip.

Current edition approved May 1, 2016. Published May 2016. Originally approved in 1964. Last previous edition approved in 2012 as A507 – 12. DOI: 10.1520/A0507-16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

**TABLE 1 Standard Steels Commonly Produced for Drawing Alloy-Steel Sheet and Strip**

Steel Designation No.	Chemical Composition Ranges and Limits, % (Heat Analysis) <sup>A</sup>								
	C	Mn	P	S	Si <sup>B</sup>	Ni	Cr	Mo	V
E3310 <sup>C</sup>	0.08–0.13	0.45–0.60	0.025	0.025	0.15–0.35	3.25–3.75	1.40–1.75	...	...
4012 <sup>C</sup>	0.09–0.14	0.75–1.00	0.025	0.025	0.15–0.35	...	...	0.15–0.25	...
4118	0.18–0.23	0.70–0.90	0.025	0.025	0.15–0.35	...	0.40–0.60	0.08–0.15	...
4130	0.28–0.33	0.40–0.60	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4135	0.33–0.38	0.70–0.90	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4137	0.35–0.40	0.70–0.90	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4140	0.38–0.43	0.75–1.00	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4142	0.40–0.45	0.75–1.00	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4145	0.43–0.48	0.75–1.00	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4147 <sup>C</sup>	0.45–0.50	0.75–1.00	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4150	0.48–0.53	0.75–1.00	0.025	0.025	0.15–0.35	...	0.80–1.10	0.15–0.25	...
4320	0.17–0.22	0.45–0.65	0.025	0.025	0.15–0.35	1.65–2.00	0.40–0.60	0.20–0.30	...
4340	0.38–0.43	0.60–0.80	0.025	0.025	0.15–0.35	1.65–2.00	0.70–0.90	0.20–0.30	...
E4340	0.38–0.43	0.65–0.85	0.025	0.025	0.15–0.35	1.65–2.00	0.70–0.90	0.20–0.30	...
4520 <sup>C</sup>	0.18–0.23	0.45–0.65	0.025	0.025	0.15–0.35	...	...	0.45–0.60	...
4615	0.13–0.18	0.45–0.65	0.025	0.025	0.15–0.35	1.65–2.00	...	0.20–0.30	...
4620	0.17–0.22	0.45–0.65	0.025	0.025	0.15–0.35	1.65–2.00	...	0.20–0.30	...
4718	0.16–0.21	0.70–0.90	0.025	0.025	0.15–0.35	0.90–1.20	0.35–0.55	0.30–0.40	...
4815	0.13–0.18	0.40–0.60	0.025	0.025	0.15–0.35	3.25–3.75	...	0.20–0.30	...
4820	0.18–0.23	0.50–0.70	0.025	0.025	0.15–0.35	3.25–3.75	...	0.20–0.30	...
5015	0.12–0.17	0.30–0.50	0.025	0.025	0.15–0.35	...	0.30–0.50	...	...
5046	0.43–0.50	0.75–1.00	0.025	0.025	0.15–0.35	...	0.20–0.35	...	...
5115	0.13–0.18	0.70–0.90	0.025	0.025	0.15–0.35	...	0.70–0.90	...	...
5120	0.17–0.22	0.70–0.90	0.025	0.025	0.15–0.35	...	0.70–0.90	...	...
5130	0.28–0.33	0.70–0.90	0.025	0.025	0.15–0.35	...	0.80–1.10	...	...
5132	0.30–0.35	0.60–0.80	0.025	0.025	0.15–0.35	...	0.75–1.00	...	...
5140	0.38–0.43	0.70–0.90	0.025	0.025	0.15–0.35	...	0.70–0.90	...	...
5150	0.48–0.53	0.79–0.90	0.025	0.025	0.15–0.35	...	0.70–0.90	...	...
5160	0.56–0.64	0.75–1.00	0.025	0.025	0.15–0.35	...	0.70–0.90	...	...
E51100 <sup>C</sup>	0.95–1.10	0.25–0.45	0.025	0.025	0.15–0.35	...	0.90–1.15	...	...
E52100	0.98–1.10	0.25–0.45	0.025	0.025	0.15–0.35	...	1.30–1.60	...	...
6150	0.48–0.53	0.70–0.90	0.025	0.025	0.15–0.35	...	0.80–1.10	...	0.15 min
6158 <sup>C</sup>	0.55–0.62	0.70–1.10	0.025	0.015	0.15–0.35	...	0.90–1.20	...	0.10–0.20
8615	0.13–0.18	0.70–0.90	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8617	0.15–0.20	0.70–0.90	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8620	0.18–0.23	0.70–0.90	0.035	0.035	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8630	0.28–0.33	0.70–0.90	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8640	0.38–0.43	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8642 <sup>C</sup>	0.40–0.45	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8645	0.43–0.48	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8650 <sup>C</sup>	0.48–0.53	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8655	0.51–0.59	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8660	0.55–0.65	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25	...
8720	0.18–0.23	0.70–0.90	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.20–0.30	...
8735 <sup>C</sup>	0.33–0.38	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.20–0.30	...
8740 <sup>C</sup>	0.38–0.43	0.75–1.00	0.025	0.025	0.15–0.35	0.40–0.70	0.40–0.60	0.20–0.30	...
9260	0.56–0.64	0.75–1.00	0.025	0.025	1.80–2.20	...	...	...	...
9262 <sup>C</sup>	0.55–0.65	0.75–1.00	0.025	0.025	1.80–2.20	...	0.25–0.40	...	...
E9310 <sup>C</sup>	0.08–0.13	0.45–0.65	0.025	0.025	0.20–0.35	3.00–3.50	1.00–1.40	0.08–0.15	...

<sup>A</sup> The chemical ranges and limits shown are subject to product analysis tolerances. See Specification A505.

<sup>B</sup> Other silicon limits can be substituted on agreement between the purchaser and producer.

<sup>C</sup> Not an S.A.E. Steel Designation.

## 7. Metallurgical Structure

### 7.1 Microstructure:

7.1.1 *Requirements*—At least 75 % of the carbide microstructure shall be of the globular type.

7.1.2 *Number of Tests*—The number of tests shall be in accordance with the producer's standard quality control procedures. A specific number of tests is not required, but the material shall be produced by manufacturing practices established to assure compliance with the specified requirements. The material shall be subjected to mill tests and inspection procedures to assure such compliance. For government procurement, mill tests and inspection procedures utilized to

show conformance to the microstructure requirements shall be made available on request.

## 8. Mechanical Requirements

### 8.1 Tension and Hardness Tests:

8.1.1 *Requirements*—When tension tests or hardness tests, or both are specified on the order, the test results shall conform to the requirements specified on the order. Yield strength, tensile strength, and elongation requirements may be specified. The tensile properties will vary depending on the chemical composition, condition, and heat treatment. Producers are frequently consulted as to grade, resultant mechanical

**TABLE 2 Heat (Cast) Analysis Ranges for Other Than Standard Steel Alloy Sheet and Strip**

Element	When Maximum of Specified Element Is, %	Range or Limit, %
Carbon	To 0.55 incl	0.05
	Over 0.55 to 0.70 incl	0.08
	Over 0.70 to 0.80 incl	0.10
	Over 0.80 to 0.95 incl	0.12
	Over 0.95 to 1.35 incl	0.13
Manganese	To 0.60 incl	0.20
	Over 0.60 to 0.90 incl	0.20
	Over 0.90 to 1.05 incl	0.25
	Over 1.05 to 1.90 incl	0.30
	Over 1.90 to 2.10 incl	0.40
Phosphorus	...	0.025 max
Sulfur	...	0.025 max
Silicon	To 0.15 incl	0.08
	Over 0.15 to 0.20 incl	0.10
	Over 0.20 to 0.40 incl	0.15
	Over 0.40 to 0.60 incl	0.20
	Over 0.60 to 1.00 incl	0.30
	Over 1.00 to 2.20 incl	0.40
Copper	To 0.60 incl	0.20
	Over 0.60 to 1.50 incl	0.30
	Over 1.50 to 2.00 incl	0.35
Nickel	To 0.50 incl	0.20
	Over 0.50 to 1.50 incl	0.30
	Over 1.50 to 2.00 incl	0.35
	Over 2.00 to 3.00 incl	0.40
	Over 3.00 to 5.30 incl	0.50
	Over 5.30 to 10.00 incl	1.00
Chromium	To 0.40 incl	0.15
	Over 0.40 to 0.90 incl	0.20
	Over 0.90 to 1.05 incl	0.25
	Over 1.05 to 1.60 incl	0.30
	Over 1.60 to 1.75 incl	0.35
	Over 1.75 to 2.10 incl	0.40
	Over 2.10 to 3.99 incl	0.50
Molybdenum	To 0.10 incl	0.05
	Over 0.10 to 0.20 incl	0.07
	Over 0.20 to 0.50 incl	0.10
	Over 0.50 to 0.80 incl	0.15
	Over 0.80 to 1.15 incl	0.20
Vanadium	To 0.25 incl	0.05
	Over 0.25 to 0.50 incl	0.10

properties, recommended heat treatment, and other information needed to establish the property parameters to meet end use requirements. Rockwell hardness requirements may be specified, providing the requirements are compatible with the tension test requirements.

8.1.2 *Number of Tests*—Two tension tests and two hardness tests, when specified, shall be taken at random from each heat (cast) and heat treatment lot.

## 9. Other Tests and Requirements

### 9.1 End Use Suitability:

9.1.1 When steel is to be furnished in the spheroidize-annealed condition, the user and producer shall review any part(s) to be produced to reach adequate agreement on capability to produce said parts.

9.1.2 Material in the spheroidize-annealed condition generally work hardens and may require stress-relief-annealing between drawing operations.

## 10. Workmanship, Finish, and Appearance

### 10.1 Surface Finish:

10.1.1 *Hot-Rolled*—Unless otherwise specified, hot-rolled material shall be furnished descaled and oiled. When required, the material may be specified to be furnished not oiled.

10.1.2 *Cold-Rolled*—Unless otherwise specified, cold-rolled material shall be furnished with a commercial dull matte finish and shall be oiled. When required, the material may be specified to be furnished not oiled.

### 10.2 Edges:

10.2.1 *Hot-Rolled*—Unless otherwise specified, hot-rolled material shall be furnished with Mill Edge. The material may be specified to have other types of edges, in accordance with Specification **A505**.

10.2.2 *Cold-Rolled*—Unless otherwise specified, cold-rolled sheet shall be furnished with Cut Edge and cold-rolled strip shall be furnished with No. 3 Edge. The material may be specified to have other types of edges, in accordance with Specification **A505**.

## 11. Keywords

11.1 alloy steel with improved formability; cold-rolled alloy steel; deep drawn alloy steel; drawing alloy steel sheet; drawing alloy steel strip; forming alloy steel; hot-rolled alloy steel; special soundness alloy steel



**SUMMARY OF CHANGES**

Committee **A01** has identified the location of selected changes to this standard since the last issue (A507 – 12) that may impact the use of this standard. (Approved May 1, 2016.)

(1) Revised Si limits in **Table 1**.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*