



Standard Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel, and Alloy Steel¹

This standard is issued under the fixed designation A510/A510M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope*

1.1 This specification covers general requirements for carbon and alloy steel wire rods and uncoated coarse round wire in coils or straightened and cut lengths.

1.2 In case of conflict, the requirements in the purchase order, on the drawing, in the individual specification, and in this general specification shall prevail in the sequence named.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 ASTM Standards:²

A5 Specification for High-Carbon Steel Joint Bars; Replaced by A 3 (Withdrawn 1979)³

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A510M Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel (Metric) (Withdrawn 2011)³

A700 Practices for Packaging, Marking, and Loading Methods for Steel Products for Shipment

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

A941 Terminology Relating to Steel, Stainless Steel, Related Alloys, and Ferroalloys

A1040 Guide for Specifying Harmonized Standard Grade Compositions for Wrought Carbon, Low-Alloy, and Alloy Steels

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E30 Test Methods for Chemical Analysis of Steel, Cast Iron, Open-Hearth Iron, and Wrought Iron (Withdrawn 1995)³

E112 Test Methods for Determining Average Grain Size

E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 SAE Standard:⁴

J 1086 Numbering Metals and Alloy

2.3 AIAG Standard:⁵

AIAGB-5 02.00 Primary Metals Identification Tag Application Standard

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *coarse round wire*—from 0.035 to 0.999 in. [0.90 to 25 mm] in diameter, inclusive, wire that is produced from hot-rolled wire rods or hot-rolled coiled bars by one or more cold reductions primarily for the purpose of obtaining a desired size with dimensional accuracy, surface finish, and mechanical properties. By varying the amount of cold reduction and other wire mill practices, including thermal treatment, a wide diversity of mechanical properties and finishes are made available.

3.1.1.1 *Discussion*—Coarse round wire is designated by Steel Wire Gauge numbers, common fractions, or decimal parts of an inch, or metric equivalents. The Steel Wire Gauge system (US) is shown in **Table 1** (English Units) and **Table 1(M)** (SI Units). Since the many gauge systems in use may cause confusion, the purchaser is encouraged to specify wire diameters in inches, decimal parts, or metric equivalents.

3.1.2 *straightened and cut wire*—wire that is produced from coils of wire by means of special machinery which straightens the wire and cuts it to a specified length.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.03 on Steel Rod and Wire.

Current edition approved April 1, 2013. Published April 2013. Originally approved in 1964. Last previous edition approved in 2011 as A510 – 11. DOI: 10.1520/A0510_A0510M-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Society of Automotive Engineers (SAE), 400 Commonwealth Dr., Warrendale, PA 15096-0001, <http://www.sae.org>.

⁵ Available from Automotive Industry Action Group (AIAG), 26200 Lahser Rd., Suite 200, Southfield, MI 48033, <http://www.aiag.org>.

*A Summary of Changes section appears at the end of this standard

**TABLE 1 Steel Wire Gauge^A (English Units)**

Gauge No.	Decimal Equivalent, in.	Gauge No.	Decimal Equivalent, in.
7/0	0.490	9	0.148*
6/0	0.462*	9½	0.142
5/0	0.430*	10	0.135
4/0	0.394*	10½	0.128
3/0	0.362*	11	0.120*
2/0	0.331	11½	0.113
1/0	0.306	12	0.106*
1	0.283	12½	0.099
1½	0.272	13	0.092*
2	0.262*	13½	0.086
2½	0.253	14	0.080
3	0.244*	14½	0.076
3½	0.234	15	0.072
4	0.225*	15½	0.067
4½	0.216	16	0.062*
5	0.207	16½	0.058
5½	0.200	17	0.054
6	0.192	17½	0.051
6½	0.184	18	0.048*
7	0.177	18½	0.044
7½	0.170	19	0.041
8	0.162	19½	0.038
8½	0.155	20	0.035*

^A The steel wire gauge outlined in this table has been taken from the original Washburn and Moen Gauge chart. In 20 gauge and coarser, sizes originally quoted to 4 decimal equivalent places have been rounded to 3 decimal places in accordance with rounding procedures of Practice E29. All rounded U.S. customary values are indicated by an asterisk.

TABLE 1 (M) Steel Wire Gauge^A (SI Units, mm)

0.90	6.0
1.00	6.5
1.10	7.0
1.20	7.5
1.30	8.0
1.40	8.5
1.60	9.0
1.80	9.5
2.0	10.0
2.1	11.0
2.2	12.0
2.4	13.0
2.5	14.0
2.6	15.0
2.8	16.0
3.0	17.0
3.2	18.0
3.5	19.0
3.8	20.0
4.0	21.0
4.2	22.0
4.5	23.0
4.8	24.0
5.0	25.0
5.5	

3.1.2.1 *Discussion*—The straightening operation may alter the mechanical properties of the wire, especially the tensile strength. The straightening operation may also induce changes in the diameter of the wire. The extent of the changes in the properties of the wire after cold straightening depends upon the kind of wire and also on the normal variations in the adjustments of the straightening equipment. It is therefore not possible to forecast the properties of straightened and cut wire and each kind of wire needs individual consideration. In most cases, the end use of straightened and cut wire is not seriously influenced by these changes.

3.1.3 *wire rods*—rods that are hot rolled from billets to an approximate round cross section into coils of one continuous length. Rods are not comparable to hot-rolled bars in accuracy of cross section or surface finish and as a semifinished product are intended primarily for the manufacture of wire.

3.1.3.1 *Discussion*—Rod sizes from 7/32 to 47/64 in. [5.5 to 18.6 mm] in diameter, inclusive, are designated by fractions or decimal parts of an inch or metric equivalents as shown in Table 2 (English Units) and Table 2(M) (SI Units).

4. Ordering Information

4.1 Orders for hot-rolled wire rods under this specification should include the following information:

- 4.1.1 Quantity (lbs [kg or Mg]),
- 4.1.2 Name of material (wire rods),
- 4.1.3 Diameter (Table 2),
- 4.1.4 Chemical composition grade no. (Guide A1040),
- 4.1.5 Packaging,
- 4.1.6 ASTM designation and date of issue, and
- 4.1.7 Special requirements, if any.

NOTE 1—A typical ordering description is as follows: 100 000 lb Wire Rods, 7/32 in., Grade 1010 in approximately 1000 lb Coils to 50 000 kg

TABLE 2 Sizes of Wire Rods^A (English Units)

Inch Fraction	Decimal Equivalent, in.	Inch Fraction	Decimal Equivalent, in.
7/32	0.219	31/64	0.484
15/64	0.234	1/2	0.500
1/4	0.250	33/64	0.516
17/64	0.266	17/32	0.531
9/32	0.281	35/64	0.547
19/64	0.297	9/16	0.562
5/16	0.312	37/64	0.578
21/64	0.328	19/32	0.594
11/32	0.344	39/64	0.609
23/64	0.359	5/8	0.625
3/8	0.375	41/64	0.641
25/64	0.391	21/32	0.656
13/32	0.406	43/64	0.672
27/64	0.422	11/16	0.688
7/16	0.438	45/64	0.703
29/64	0.453	23/32	0.719
15/32	0.469	47/64	0.734

^A Rounded off to 3 decimal places in decimal equivalents in accordance with procedures outlined in Practice E29.

TABLE 2 (M) Sizes of Wire Rods (SI Units, mm)

5.5	12.5
6	13
6.5	13.5
7	14
7.5	14.5
8	15
8.5	15.5
9	16
9.5	16.5
10	17
10.5	17.5
11	18
11.5	18.5
12	19

steel wire rods, 5.5 mm, Grade G10100 in approximately 600 kg for metric orders to ASTM A510 dated _____.

4.2 Orders for coarse round wire under this specification should include the following information:

- 4.2.1 Quantity (lbs or pieces [kg or pieces]),
- 4.2.2 Name of material (uncoated carbon steel wire or alloy steel wire),
- 4.2.3 Diameter (see 3.1.1),
- 4.2.4 Length (straightened and cut only),
- 4.2.5 Chemical composition (Guide A1040),
- 4.2.6 Packaging,
- 4.2.7 ASTM designation and date of issue, and
- 4.2.8 Special requirements, if any.

NOTE 2—A typical ordering description is as follows: 40 000 lb Uncoated Carbon or Alloy Steel Wire, 0.148 in. (9 ga.) diameter, Grade 1008 in 500 lb Coils on Tubular Carriers to ASTM A150/A150M-XX, or 2500 Pieces, Carbon or Alloy Steel Wire, 0.375 in. diameter, Straightened and Cut 29½ in., Grade 1015, in 25 Piece Bundles on Pallets to ASTM A150/A150M-XX.

For metric, a typical ordering description is as follows: 15 000 kg uncoated carbon or alloy steel wire 3.8 mm diameter, Grade G10080 in 1000 Kg coils on tubular carriers to ASTM A150/A150M-XX, or 2500 pieces carbon or alloy steel wire, 9.5 mm diameter, straightened and cut, 0.76 m, Grade G10500, in 25-piece bundles on pallets to ASTM A150/A150M-XX.

5. Manufacture

5.1 The steel shall be made by any commercially accepted steel making process. The steel may be either ingot cast or strand cast.

6. Chemical Composition

6.1 The chemical composition for steel under this specification shall conform to the requirements set forth in the purchase order. Chemical compositions are specified by ranges or limits for carbon and other elements. The grades commonly specified for carbon and alloy steel wire rods and coarse round wire are designated in Guide A1040.

6.1.1 For wire rods intended for direct-drawn wire, it is common practice to specify a range of tensile strength. If chemistry ranges are also specified, due consideration should be taken to ensure that the producer can achieve the required strengths within the allowable carbon range. The Mn, P, and S limits for carbon steel wire rods are normally specified according to Guide A1040.

6.2 *Boron Additions to Control Strain Ageing Behavior*—Intentional additions of boron to low carbon steels for the purpose of controlling strain ageing behavior during wire drawing is permissible only with the agreement of the purchaser. In such cases, the boron content shall be reported in either a material test report or certification.

6.2.1 For steels that do not have intentional boron additions for hardenability or for control of strain ageing behavior, the boron content will not normally exceed 0.0008 %.

6.3 *Cast or Heat Analysis (Formerly Ladle Analysis)*—An analysis of each cast or heat shall be made by the producer to determine the percentage of the elements specified. The analysis shall be made from a test sample, preferably taken during the pouring of the cast or heat. The chemical composition thus

determined shall be reported, if required, to the purchaser, or his representative. Reporting of significant figures and rounding shall be in accordance with Test Methods, Practices, and Terminology A751.

6.4 *Product Analysis (Formerly Check Analysis)*—A product analysis may be made by the purchaser. The analysis is not used for a duplicate analysis to confirm a previous result. The purpose of the product analysis is to verify that the chemical composition is within specified limits for each element, including applicable permissible variations in product analysis. The results of analyses taken from different pieces of a heat may differ within permissible limits from each other and from the heat or cast analysis. Table 3 shows the permissible variations for product analysis of carbon steel. Table 4 shows the permissible variations for product analysis of alloy steel. The results of the product analysis obtained, except lead, shall not vary both above and below the permissible limits.

6.4.1 Rimmed or capped steels are characterized by a lack of uniformity in their chemical composition, especially for the elements carbon, phosphorus, and sulfur, and for this reason product analysis is not technologically appropriate for these elements unless misapplication is clearly indicated.

6.4.2 Because of the degree to which phosphorus and sulfur segregate, product analysis for these elements is not technologically appropriate for rephosphorized or resulfurized steels, or both, unless misapplication is clearly indicated.

6.4.3 The location at which chips for product analysis are obtained from the sample is important because of segregation. For rods and wire, chips are taken by milling or machining the full cross section of the sample.

6.4.3.1 Steel subjected to certain thermal treatment operations by the purchaser may not give chemical analysis results that properly represent its original composition. Therefore,

TABLE 3 Permissible Variations for Product Analysis of Carbon Steel

Element	Limit, or Max of Specified Range, %	Over Max Limit, %	Under Min Limit, %
Carbon	0.25 and under over 0.25 to 0.55, incl over 0.55	0.02 0.03 0.04	0.02 0.03 0.04
Manganese	0.90 and under over 0.90 to 1.65, incl	0.03 0.06	0.03 0.06
Phosphorus	to 0.040, incl	0.008	...
Sulfur	to 0.060, incl	0.008	...
Silicon	0.35 and under over 0.35 to 0.60, incl	0.02 0.05	0.02 0.05
Copper ^A	under minimum only	...	0.02
Lead ^B	0.15 to 0.35, incl	0.03	0.03

^A Product analysis permissible variations for copper apply only when the amount of copper is specified or required. Copper bearing steels typically specify 0.20 % min copper.

^B Product analysis permissible variations for lead apply only when the amount of lead is specified or required. A range from 0.15 to 0.35 % lead is normally specified for leaded steels.

**TABLE 4 Product or Verification Analysis Tolerances—Alloy Steels**

Element	Limit or Maximum of Specified Range, %	Tolerance Over Maximum Limit or Under Minimum Limit, %
Carbon	To 0.30, incl	0.01
	Over 0.30 to 0.75, incl	0.02
	Over 0.75	0.03
Manganese	To 0.90, incl	0.03
	Over 0.90 to 2.10, incl	0.04
Phosphorus	Over max only	0.005
Sulfur	To 0.060, incl ^A	0.005
Silicon	To 0.40, incl	0.02
	Over 0.40 to 2.20, incl	0.05
Nickel	To 1.00, incl	0.03
	Over 1.00 to 2.00, incl	0.05
	Over 2.00 to 5.30, incl	0.07
	Over 5.30 to 10.00, incl	0.10
Chromium	To 0.90, incl	0.03
	Over 0.90 to 2.10, incl	0.05
	Over 2.10 to 3.99, incl	0.10
Molybdenum	To 0.20, incl	0.01
	Over 0.20 to 0.40, incl	0.02
	Over 0.40 to 1.15, incl	0.03
Vanadium	To 0.01, incl	0.01
	Over 0.10 to 0.25, incl	0.02
	Over 0.25 to 0.50, incl	0.03
	Min value specified, check under min limit	0.01
Tungsten	To 1.00, incl	0.04
	Over 1.00 to 4.00, incl	0.08
Aluminum	Up to 0.10, incl	0.03
	Over 0.10 to 0.20, incl	0.04
	Over 0.20 to 0.30, incl	0.05
	Over 0.30 to 0.80, incl	0.07
	Over 0.80 to 1.80, incl	0.10
Lead	0.15 to 0.35, incl	0.03 ^B
Copper	To 1.00, incl	0.03
	Over 1.00 to 2.00, incl	0.05

^A Sulfur over 0.060 % is not subject to check, product, or verification analysis.

^B Tolerance is over and under.

purchasers should analyze chips taken from the steel in the condition in which it is received from the producer.

6.4.3.2 When samples are returned to the producer for product analysis, the samples should consist of pieces of the full cross section.

6.4.4 For referee purposes, Test Methods E30 shall be used.

7. Metallurgical Structure

7.1 Grain size, when specified, shall be determined in accordance with the requirements of Test Methods E112.

7.2 Wire rods of the steel grades listed in Table 3, when supplied in the “as-rolled” condition, shall not contain injurious microconstituents such as untempered martensite.

8. Mechanical Requirements

8.1 The properties enumerated in individual specifications shall be determined in accordance with Test Methods and Definitions A370.

8.2 Because of the great variety in the kinds of wire and the extensive diversity of end uses, a number of formal mechanical test procedures have been developed. These tests are used as control tests by producers during the intermediate stages of wire processing, as well as for final testing of the finished product, and apply particularly to specification wire and wires for specified end uses. A number of these tests are further described in Supplement IV, Round Wire Products, of Test Methods and Definitions A370.

8.3 Since the general utility of rods and wire requires continuity of length, in the case of rods, tests are commonly made on samples taken from the ends of coils after removing enough rings to clear any non-uniformity in the controlled cooling process, if applicable. In the case of wire, tests are commonly made on samples taken from the ends of coils, thereby not impairing the usefulness of the whole coil.

9. Dimensions, Mass, and Permissible Variations

9.1 The diameter and out-of-roundness of the wire rod shall not vary from that specified by more than that prescribed in Table 5 (English Units) and Table 5(M) (SI Units).

9.2 The diameter and out-of-roundness of the coarse round wire and straightened and cut wire shall not vary from that specified by more than that prescribed in Table 6 (English Units) and Table 6(M) (SI Units).

9.3 The length of straightened and cut wire shall not vary from that specified by more than that prescribed in Table 7 (English Units) and Table 7(M) (SI Units).

TABLE 5 Permissible Variations in Diameter for Wire Rod in Coils (English Units)

NOTE 1—For purposes of determining conformance with this specification, all specified limits are absolute as defined in Practice E29.

Diameter of Rod		Permissible Variation, Plus and Minus, in.	Permissible Out-of-Round, in.
Fractions	Decimal		
7/32 to 47/64 in., incl	0.219 to 0.734 in., incl	0.016	0.025

TABLE 5 (M) Permissible Variations in Diameter for Wire Rod in Coils (SI Units)

NOTE 1—For purposes of determining conformance with this specification, all specified limits are absolute as defined in Practice E29.

Diameter of Rod [mm]		Permissible Variation, Plus and Minus, [mm]	Permissible Out-of-Round, [mm]
5.5 to 19		0.40	0.60

TABLE 6 Permissible Variations in Diameter for Uncoated Coarse Round Wire (English Units)

NOTE 1— For purposes of determining conformance with this specification, all specified limits are absolute as defined in Practice E29.

In Coils		
Diameter of Wire, in.	Permissible Variations, Plus and Minus, in.	Permissible Out-Of-Round, in.
0.035 to under 0.076	0.001	0.001
0.076 to under 0.500	0.002	0.002
0.500 and over	0.003	0.003

Straightened and Cut		
Diameter of Wire, in.	Permissible Variations, Plus and Minus, in.	Permissible Out-Of-Round, in.
0.035 to under 0.076	0.001	0.001
0.076 to 0.148, incl	0.002	0.002
Over 0.148 to under 0.500	0.003	0.003
0.500 and over	0.004	0.004

TABLE 6 (M) Permissible Variations in Diameter for Uncoated Coarse Round Wire (SI Units)

NOTE 1— For purposes of determining conformance with this specification, all specified limits are absolute as defined in Practice E29.

In Coils		
Diameter of Wire, [mm]	Permissible Variations, Plus and Minus, [mm]	Permissible Out-Of-Round, [mm]
0.90 to under 1.90	0.03	0.03
1.90 to under 12.5	0.05	0.05
12.5 and over	0.08	0.08

Straightened and Cut		
Diameter of Wire, [mm]	Permissible Variations, Plus and Minus, [mm]	Permissible Out-Of-Round, [mm]
0.90 to under 1.90	0.03	0.03
1.90 to under 3.80	0.05	0.05
3.80 to under 12.5	0.08	0.08
12.5 and over	0.10	0.10

9.4 The burrs formed in cutting straightened and cut wire shall not exceed the diameter specified by more than that prescribed in Table 8 (English Units) and Table 8(M) (SI Units).

10. Workmanship, Finish, and Appearance

10.1 The wire rod shall be free of detrimental surface imperfections, tangles, and sharp kinks.

10.1.1 Two or more rod coils may be welded together to produce a larger coil. The weld zone may not be as sound as the original material. The mechanical properties existing in the weld metal may differ from those in the unaffected base metal. The weld may exceed the standard dimensional permissible variations on the minus side and must be within the permissible variations on the plus side.

10.2 The wire as received shall be smooth and substantially free from rust, shall not be kinked or improperly cast. No

TABLE 7 Permissible Variations in Length for Straightened and Cut Wire (English Units)

NOTE 1—For purposes of determining conformance with this specification, all specified limits are absolute as defined in Practice E29.

Cut Length, ft	Permissible Variations, Plus and Minus, in.
Under 3	1/16
3 to 12, incl	3/32
Over 12	1/8

TABLE 7 (M) Permissible Variations in Length for Straightened and Cut Wire (SI Units)

NOTE 1—For purposes of determining conformance with this specification, all specified limits are absolute as defined in Practice E29.

Cut Length, [m]	Permissible Variations, Plus and Minus, [mm]
Under 1.0	1.6
1.0 to 4.0	2.4
Over 4.0	3.0

TABLE 8 Permissible Variations for Burrs for Straightened and Cut Wire (English Version)

NOTE 1—For purposes of determining conformance with this specification, all specified limits are absolute as defined in Practice E29.

Diameter of Wire, in.	Permissible Variation over Measured Diameter, in.
Up to 0.125, incl	0.004
Over 0.125 to 0.250, incl	0.006
Over 0.250 to 0.500, incl	0.008
Over 0.500	0.010

TABLE 8 (M) Permissible Variations for Burrs for Straightened and Cut Wire (SI Units)

NOTE 1—For purposes of determining conformance with this specification, all specified limits are absolute as defined in Practice E29.

Diameter of Wire, [mm]	Permissible Variation over Measured Diameter, [mm]
Up to 3.0, incl	0.10
Over 3.0 to 6.5, incl	0.15
Over 6.5 to 12.5, incl	0.20
Over 12.5	0.25

detrimental die marks or scratches may be present. Each coil shall be one continuous length of wire. Welds made during cold drawing are permitted.

10.3 The straightened and cut wire shall be substantially straight and not be kinked or show excessive spiral marking.

11. Number of Tests and Retests

11.1 The difficulties in obtaining truly representative samples of wire rod and coarse round wire without destroying the usefulness of the coil of wire account for the generally accepted practice of allowing retests for mechanical tests and surface examination. Two additional test pieces are cut from each end of the coil from which the original sample was taken. A portion of the coil may be discarded prior to cutting the

sample for retest. If any of the retests fails to comply with the requirements, the coil of wire may be rejected. Before final rejection, however, it is frequently advisable to base final decision on an actual trial of the material to determine whether or not it will be suitable for the intended use.

12. Inspection

12.1 The manufacturer shall afford the purchaser's inspector all reasonable facilities necessary to satisfy him that the material is being produced and furnished in accordance with this specification. Mill inspection by the purchaser shall not interfere unnecessarily with the manufacturer's operations. All tests and inspections shall be made at the place of manufacture, unless otherwise agreed.

13. Rejection and Rehearing

13.1 Any rejection based on tests made in accordance with this specification shall be reported to the producer within a reasonable length of time. The material must be adequately protected and correctly identified in order that the producer may make a proper investigation.

14. Certification

14.1 When specified in the purchase order or contract, a producer's or supplier's certification shall be furnished to the purchaser that the material was manufactured, sampled, tested, and inspected in accordance with this specification and has been found to meet the requirements. When specified in the purchase order or contract, a report of the test results shall be furnished.

14.2 The certification shall include the specification number, year date of issue, and revision letter, if any.

14.3 A material test report, certificate of inspection, or similar document printed from or used in electronic form from an electronic data interchange (EDI) transmission shall be regarded as having the same validity as a counterpart printed in the certifier's facility. The content of the EDI transmitted document shall meet the requirements of the invoked ASTM standard(s) and conform to any existing EDI agreement between the purchaser and the manufacturer. Notwithstanding the absence of a signature, the organization submitting the EDI transmission is responsible for the content of the report.

NOTE 3—The industry definition as invoked here is: EDI is the computer-to-computer exchange of business information in a standard format such as ANSI ASC X12.

15. Packaging and Package Marking

15.1 A tag shall be securely attached to each coil or bundle and shall be marked with the size, ASTM specification number, heat or cast number, grade number, and name or mark of the manufacturer.

15.2 When specified in the purchase order, packaging, marking, and loading for shipments shall be in accordance with those procedures recommended by Practices **A700**.

15.3 *Bar Coding*—In addition to the previously-stated identification requirements, bar coding is acceptable as a supplementary identification method. Bar coding should be consistent with AIAG B-5 02.00, Primary Metals Identification Tag Application. The bar code may be applied to a substantially affixed tag.

16. Keywords

16.1 alloy steel; carbon; carbon steel; coarse round wire; general; grain size; straightened and cut; weld; wire; wire rods

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A510 – 11) that may impact the use of this standard. (Approved April 1, 2013.)

- (1) Revised Section **5.1**.
- (2) Revised Section **11.1**.

- (3) Added new Section **14.3**.
- (4) Added **Table 4**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).