

Standard Specification for Structural Carbon Steel Plates of Improved Toughness¹

This standard is issued under the fixed designation A573/A573M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers structural quality carbonmanganese-silicon steel plates in three tensile strength ranges intended primarily for service at atmospheric temperatures where improved notch toughness is important.

1.2 Plates covered by this specification are limited to a maximum thickness of 1.5 in. [40 mm].

1.3 If the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized. See Appendix X3 of Specification A6/A6M for information on weldability.

1.4 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system is to be used independently of the other without combining values in any way.

2. Referenced Documents

2.1 ASTM Standards:²

A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling

3. General Requirements for Delivery

3.1 Plates furnished under this specification shall conform to the requirements of the current edition of Specification A6/A6M, unless a conflict exists in which case this specification shall prevail.

4. Materials and Manufacture

4.1 The steel shall be made to fine grain practice.

5. Chemical Composition

5.1 The heat analysis shall conform to the requirements given in Table 1.

5.2 The product analysis shall conform to the requirements given in Table 1 subject to the product analysis tolerances in Specification A6/A6M.

6. Tension Test

6.1 The plates, as represented by the tension test specimens, shall conform to the tensile requirements given in Table 2.

7. Keywords

7.1 carbon steel; plates; structural steel; toughness; welded construction

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock and Ships.

Current edition approved Nov. 15, 2013. Published November 2013. Originally approved in 1966. Last previous edition approved in 2009 as A573/A573M - 05 (2009). DOI: 10.1520/A0573_A0573M-13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

🕼 A573/A573M – 13

TABLE 1 Chemical Requirements (Heat Analysis)

	Composition, %		
	Grade 58 [400]	Grade 65 [450]	Grade 70 [485]
Carbon, max:			
1/2 in. [13 mm] and under	0.23	0.24	0.27
Over 1/2 in. [13 mm] to 11/2 in.,	0.23	0.26	0.28
[40 mm], incl			
Manganese ^A	0.60-0.90	0.85–1.20	0.85-1.20
Phosphorus, max	0.030	0.030	0.030
Sulfur, max	0.030	0.030	0.030
Silicon	0.10-0.35	0.15–0.40	0.15-0.40

^A For each reduction of 0.01 percentage point below the specified maximum for carbon, an increase of 0.06 percentage points above the specified maximum for manganese is permitted, up to a maximum of 1.50 % for Grades 58 and 65; and up to a maximum of 1.60 % for Grade 70.

	TABLE 2 Tensile Requirements ^A			
	Grade 58	Grade 65	Grade 70	
	[400]	[450]	[485]	
Tensile strength, ksi	58–71	65–77	70–90	
[MPa]	[400–490]	[450–530]	[485–620]	
Yield point, min, ksi	32	35	42	
[MPa]	[220]	[240]	[290]	
Elongation in 8 in. [200 mm] min ^{B,C} , %	21	20	18	
Elongation in 2 in. [50	24	23	21	

mm], min^{*B,C*} , %

^A See the Orientation subsection in the Tension Tests section of Specification A6/A6M.

^B Elongation need not be determined for floor plate.

^c For plates wider than 24 in. [600 mm], the elongation requirement is reduced two percentage points. See the Elongation Requirement Adjustments subsection in the Tension Tests section of Specification A6/A6M.

SUPPLEMENTARY REQUIREMENTS

Standardized supplementary requirements for use at the option of the purchaser are listed in Specification A6/A6M. Supplementary requirements shall not apply unless specified in the purchase order or contract.

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A573/A573M - 05 (2009)) that may impact the use of this standard. (Approved Nov. 15, 2013.)

(1) Modified phosphorus and sulfur limits in Table 1.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).