



Standard Specification for Deformed and Plain Carbon-Steel Bars for Concrete Reinforcement¹

This standard is issued under the fixed designation A615/A615M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers deformed and plain carbon-steel bars in cut lengths and coils for concrete reinforcement. Steel bars containing alloy additions, such as with the Association for Iron and Steel Technology and the Society of Automotive Engineers series of alloy steels, are permitted if the resulting product meets all the other requirements of this specification. The standard sizes and dimensions of deformed bars and their number designations are given in [Table 1](#).

1.2 Bars are of five minimum yield strength levels: namely, 40 000 psi [280 MPa], 60 000 psi [420 MPa], 75 000 psi [520 MPa], 80 000 psi [550 MPa], and 100 000 psi [690 MPa], designated as Grade 40 [280], Grade 60 [420], Grade 75 [520], Grade 80 [550], and Grade 100 [690], respectively.

NOTE 1—Grade 100 [690] reinforcing bars were introduced in this specification in 2015. In contrast to the lower grades, which have ratios of specified tensile strength to specified yield strength that range from 1.31 to 1.5, Grade 100 [690] reinforcing bars have a ratio of specified tensile strength to specified yield strength of 1.15. Designers should be aware that there will, therefore, be a lower margin of safety and reduced warning of failure following yielding when Grade 100 [690] bars are used in structural members where strength is governed by the tensile strength of the reinforcement, primarily in beams and slabs. If this is of concern, the purchaser has the option of specifying a minimum ratio of tensile strength to actual yield strength. Consensus design codes and specifications such as “Building Code Requirements for Structural Concrete (ACI 318)” may not recognize Grade 100 [690] reinforcing bars; therefore the 125 % of specified yield strength requirements in tension and compression are not applicable. Mechanical and welded splices should meet a minimum specified tensile strength of 115 000 psi [790 MPa].

NOTE 2—Designers need to be aware that design standards do not recognize the use of the No. 20 [64] bar, the largest bar included in this specification. Structural members reinforced with No. 20 [64] bars may require approval of the building official or other appropriate authority and require special detailing to ensure adequate performance at service and factored loads.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Jan. 15, 2016. Published March 2016. Originally approved in 1968. Last previous edition approved in 2015 as A615/A615M – 15a^{ε1}. DOI: 10.1520/A0615_A0615M-16.

1.3 Plain bars, in sizes up to and including 2½ in. [63.5 mm] in diameter in coils or cut lengths, when ordered shall be furnished under this specification in Grade 40 [280], Grade 60 [420], Grade 75 [520], Grade 80 [550], and Grade 100 [690]. For ductility properties (elongation and bending), test provisions of the nearest smaller nominal diameter deformed bar size shall apply. Requirements providing for deformations and marking shall not be applicable.

NOTE 3—Welding of the material in this specification should be approached with caution since no specific provisions have been included to enhance its weldability. When this steel is to be welded, a welding procedure suitable for the chemical composition and intended use or service should be used. The use of the latest edition of AWS D1.4/D1.4M is recommended. The AWS D1.4/D1.4M Welding Code describes the proper selection of the filler metals and preheat/interpass temperatures, as well as performance and procedure qualification requirements.

1.4 Requirements for alternate bar sizes are presented in [Annex A1](#). The requirements in [Annex A1](#) only apply when specified by the purchaser (see [4.2.5](#)).

1.5 The text of this specification references notes and footnotes which provide explanatory material. These notes and footnotes (excluding those in tables) shall not be considered as requirements of the specification.

1.6 This specification is applicable for orders in either inch-pound units (as Specification A615) or in SI units (as Specification A615M).

1.7 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the specification.

1.8 *This specification does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this specification to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

*A Summary of Changes section appears at the end of this standard

TABLE 1 Deformed Bar Designation Numbers, Nominal Weights [Masses], Nominal Dimensions, and Deformation Requirements

Bar Designation No.	Nominal Weight, lb/ft [Nominal Mass, kg/m]	Nominal Dimensions ^A			Deformation Requirements, in. [mm]		
		Diameter, in. [mm]	Cross-Sectional Area, in. ² [mm ²]	Perimeter, in. [mm]	Maximum Average Spacing	Minimum Average Height	Maximum Gap (Chord of 12.5 % of Nominal Perimeter)
3 [10]	0.376 [0.560]	0.375 [9.5]	0.11 [71]	1.178 [29.9]	0.262 [6.7]	0.015 [0.38]	0.143 [3.6]
4 [13]	0.668 [0.994]	0.500 [12.7]	0.20 [129]	1.571 [39.9]	0.350 [8.9]	0.020 [0.51]	0.191 [4.9]
5 [16]	1.043 [1.552]	0.625 [15.9]	0.31 [199]	1.963 [49.9]	0.437 [11.1]	0.028 [0.71]	0.239 [6.1]
6 [19]	1.502 [2.235]	0.750 [19.1]	0.44 [284]	2.356 [59.8]	0.525 [13.3]	0.038 [0.97]	0.286 [7.3]
7 [22]	2.044 [3.042]	0.875 [22.2]	0.60 [387]	2.749 [69.8]	0.612 [15.5]	0.044 [1.12]	0.334 [8.5]
8 [25]	2.670 [3.973]	1.000 [25.4]	0.79 [510]	3.142 [79.8]	0.700 [17.8]	0.050 [1.27]	0.383 [9.7]
9 [29]	3.400 [5.060]	1.128 [28.7]	1.00 [645]	3.544 [90.0]	0.790 [20.1]	0.056 [1.42]	0.431 [10.9]
10 [32]	4.303 [6.404]	1.270 [32.3]	1.27 [819]	3.990 [101.3]	0.889 [22.6]	0.064 [1.63]	0.487 [12.4]
11 [36]	5.313 [7.907]	1.410 [35.8]	1.56 [1006]	4.430 [112.5]	0.987 [25.1]	0.071 [1.80]	0.540 [13.7]
14 [43]	7.65 [11.38]	1.693 [43.0]	2.25 [1452]	5.32 [135.1]	1.185 [30.1]	0.085 [2.16]	0.648 [16.5]
18 [57]	13.60 [20.24]	2.257 [57.3]	4.00 [2581]	7.09 [180.1]	1.58 [40.1]	0.102 [2.59]	0.864 [21.9]
20 [64] ^B	16.69 [24.84]	2.500 [63.5]	4.91 [3167]	7.85 [199.5]	1.75 [44.5]	0.113 [2.86]	0.957 [24.3]

^A The nominal dimensions of a deformed bar are equivalent to those of a plain round bar having the same weight [mass] per foot [metre] as the deformed bar.

^B Refer to **Note 2**.

2. Referenced Documents

2.1 ASTM Standards:²

A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling
A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A510/A510M Specification for General Requirements for Wire Rods and Coarse Round Wire, Carbon Steel, and Alloy Steel

A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment

A706/A706M Specification for Deformed and Plain Low-Alloy Steel Bars for Concrete Reinforcement

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

E29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications

E290 Test Methods for Bend Testing of Material for Ductility

2.2 ACI Standard:³

ACI 318 Building Code Requirements for Structural Concrete

2.3 AWS Standard:⁴

AWS D1.4/D1.4M Structural Welding Code—Reinforcing Steel

2.4 U.S. Military Standard:⁵

MIL-STD-129 Marking for Shipment and Storage

2.5 U.S. Federal Standard:⁵

Fed. Std. No. 123 Marking for Shipment (Civil Agencies)

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Concrete Institute (ACI), P.O. Box 9094, Farmington Hills, MI 48333-9094, <http://www.concrete.org>.

⁴ Available from American Welding Society (AWS), 8669 NW 36 Street, #130, Miami, FL 33166-6672, <http://www.aws.org>.

⁵ Available from Standardization Documents Order Desk, DODSSP, Bldg. 4, Section D, 700 Robbins Ave., Philadelphia, PA 19111-5098, <http://www.dodssp.daps.mil>.

3. Terminology

3.1 Definitions of Terms Specific to This Specification:

3.1.1 *deformations, n*—transverse protrusions on a deformed bar.

3.1.2 *deformed bar, n*—steel bar with protrusions; a bar that is intended for use as reinforcement in reinforced concrete construction.

3.1.2.1 *Discussion*—The surface of the bar is provided with protrusions that inhibit longitudinal movement of the bar relative to the concrete surrounding the bar in such construction. The protrusions conform to the provisions of this specification.

3.1.3 *plain bar, n*—steel bar without protrusions.

3.1.4 *rib, n*—longitudinal protrusion on a deformed bar.

4. Ordering Information

4.1 Orders for carbon-steel bars for concrete reinforcement under this specification shall contain the following information:

4.1.1 Quantity (weight) [mass],

4.1.2 Deformed or plain,

4.1.3 Bar designation number (size) of deformed bars, or nominal diameter (size) of plain bars

4.1.4 Cut lengths or coils,

4.1.5 Grade, and

4.1.6 ASTM designation and year of issue.

4.2 The purchaser shall have the option to specify additional requirements, including but not limited to, the following:

4.2.1 Require bars in each bundle to be supplied from a single heat (19.1),

4.2.2 Requirements for inspection (17.1),

4.2.3 Special package marking requirements (20.2),

4.2.4 Other special requirements, if any, and

4.2.5 Optional requirements of **Annex A1**.

5. Material and Manufacture

5.1 The bars shall be rolled from properly identified heats of mold-cast or strand-cast steel. The steel shall be made by any commercially accepted process.



6. Chemical Composition

6.1 The chemical analysis of each heat of steel shall be determined in accordance with Test Methods, Practices, and Terminology [A751](#). The manufacturer shall make the analysis on test samples taken preferably during the pouring of the heat. The percentages of carbon, manganese, phosphorus, and sulfur shall be determined. The phosphorus content thus determined shall not exceed 0.06 %.

6.2 A product check, for phosphorus, made by the purchaser shall not exceed that specified in [6.1](#) by more than 25 %.

7. Requirements for Deformations

7.1 Deformations shall be spaced along the bar at substantially uniform distances. The deformations on opposite sides of the bar shall be similar in size, shape, and pattern.

7.2 The deformations shall be placed with respect to the axis of the bar so that the included angle is not less than 45°. Where the line of deformations forms an included angle with the axis of the bar from 45 to 70° inclusive, the deformations shall alternately reverse in direction on each side, or those on one side shall be reversed in direction from those on the opposite side. Where the line of deformations is over 70°, a reversal in direction shall not be required.

7.3 The average spacing or distance between deformations on each side of the bar shall not exceed seven tenths of the nominal diameter of the bar.

7.4 The overall length of deformations shall be such that the gap (measured as a chord) between the ends of the deformations shall not exceed 12.5 % of the nominal perimeter of the bar. Where the ends terminate in a rib, the width of the rib shall be considered as the gap between these ends. The summation of the gaps shall not exceed 25 % of the nominal perimeter of the bar. The nominal perimeter of the bar shall be 3.1416 times the nominal diameter.

7.5 The spacing, height, and gap of deformations shall conform to the requirements prescribed in [Table 1](#).

8. Measurements of Deformations

8.1 The average spacing of deformations shall be determined by measuring the length of a minimum of ten spaces and dividing that length by the number of spaces included in the measurement. The measurement shall begin from a point on a deformation at the beginning of the first space to a correspond-

ing point on a deformation after the last included space. Spacing measurements shall not be made over a bar area containing bar marking symbols involving letters or numbers.

8.2 The average height of deformations shall be determined from measurements made on not less than two typical deformations. Determinations shall be based on three measurements per deformation, one at the center of the overall length and the other two at the quarter points of the overall length.

8.3 Insufficient height, insufficient circumferential coverage, or excessive spacing of deformations shall not constitute cause for rejection unless it has been clearly established by determinations on each lot ([Note 4](#)) tested that typical deformation height, gap, or spacing do not conform to the minimum requirements prescribed in [Section 7](#). No rejection shall be made on the basis of measurements if fewer than ten adjacent deformations on each side of the bar are measured.

NOTE 4—As used within the intent of [8.3](#), the term “lot” shall mean all the bars of one bar size and pattern of deformations contained in an individual shipping release or shipping order.

9. Tensile Requirements

9.1 The material, as represented by the test specimens, shall conform to the requirements for tensile properties prescribed in [Table 2](#).

9.2 The yield point or yield strength shall be determined by one of the following methods:

9.2.1 The yield point shall be determined by the drop or halt of the gauge of the tensile testing machine, where the steel tested has a sharp-knead or well-defined yield point.

9.2.2 Where the steel tested does not have a well-defined yield point, the yield strength shall be determined by the offset method (0.2 % offset), as described in Test Methods and Definitions [A370](#).

9.3 When material is furnished in coils, the test specimen shall be taken from the coil and straightened prior to placing it in the jaws of the tensile testing machine. (See [Note 5](#).)

NOTE 5—Straighten the test specimen to avoid formation of local sharp bends and to minimize cold work. Insufficient straightening prior to attaching the extensometer can result in lower-than-actual yield strength readings.

9.3.1 Test specimens taken from post-fabricated material shall not be used to determine conformance to this specification. (See [Note 6](#).)

TABLE 2 Tensile Requirements

	Grade 40 [280] ^A	Grade 60 [420]	Grade 75 [520]	Grade 80 [550]	Grade 100 [690]
Tensile strength, min, psi [MPa]	60 000 [420]	90 000 [620]	100 000 [690]	105 000 [725]	115 000 [790]
Yield strength, min, psi [MPa]	40 000 [280]	60 000 [420]	75 000 [520]	80 000 [550]	100 000 [690]
Elongation in 8 in. [200 mm], min, %					
Bar Designation No.					
3 [10]	11	9	7	7	7
4, 5 [13, 16]	12	9	7	7	7
6 [19]	12	9	7	7	7
7, 8 [22, 25]	...	8	7	7	7
9, 10, 11 [29, 32, 36]	...	7	6	6	6
14, 18, 20 [43, 57, 64]	...	7	6	6	6

^A Grade 40 [280] bars are furnished only in sizes 3 through 6 [10 through 19].



TABLE 3 Bend Test Requirements

Bar Designation No.	Pin Diameter for Bend Tests ^A				
	Grade 40 [280]	Grade 60 [420]	Grade 75 [520]	Grade 80 [550]	Grade 100 [690]
3, 4, 5 [10, 13, 16]	3½ <i>d</i> ^B	3½ <i>d</i>	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>
6 [19]	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>
7, 8 [22, 25]	...	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>
9, 10, 11 [29, 32, 36]	...	7 <i>d</i>	7 <i>d</i>	7 <i>d</i>	7 <i>d</i>
14, 18 [43, 57] (90°)	...	9 <i>d</i>	9 <i>d</i>	9 <i>d</i>	9 <i>d</i>
20 [64] (90°)	...	10 <i>d</i>	10 <i>d</i>	10 <i>d</i>	...

^A Test bends 180° unless noted otherwise.

^B *d* = nominal diameter of specimen.

NOTE 6—Multiple bending distortion from mechanical straightening and fabricating machines can lead to excessive cold work, resulting in higher yield strengths, lower elongation values, and a loss of deformation height.

9.4 The percentage of elongation shall be as prescribed in Table 2.

10. Bending Requirements

10.1 The bend-test specimen shall withstand being bent around a pin without cracking on the outside radius of the bent portion. The requirements for degree of bending and sizes of pins are prescribed in Table 3. When material is furnished in coils, the test specimen shall be straightened prior to placing it in the bend tester.

10.2 The bend test shall be made on specimens of sufficient length to ensure free bending and with apparatus that provides:

10.2.1 Continuous and uniform application of force throughout the duration of the bending operation.

10.2.2 Unrestricted movement of the specimen at points of contact with the apparatus and bending around a pin free to rotate.

10.2.3 Close wrapping of the specimen around the pin during the bending operation.

10.3 It shall be permissible to use other methods of bend testing as described in Test Methods E290, such as placing a specimen across two round bearings free to rotate and applying the bending force with a fixed rounded-tip mandrel conforming to the specified bend radius, allowing the bar to pass through with sufficient clearance. When failures occur under other methods of bend testing, retests shall be permitted under the bend-test method prescribed in 10.2.

11. Permissible Variation in Weight [Mass]

11.1 Deformed reinforcing bars shall be evaluated on the basis of nominal weight [mass]. The weight [mass] determined using the measured weight [mass] of the test specimen and rounding in accordance with Practice E29, shall be at least 94 % of the applicable weight [mass] per unit length prescribed in Table 1. In no case shall overweight [excess mass] of any deformed bar be the cause for rejection.

11.2 Weight [mass] variation for plain bars shall be computed on the basis of permissible variation in diameter. For plain bars smaller than ⅜ in. [9.5 mm] in diameter, use Specification A510/A510M. For larger plain bars up to and including 2½ in. [63.5 mm] in diameter, use Specification A6/A6M.

12. Finish

12.1 The bars shall be free of detrimental surface imperfections.

12.2 Rust, seams, surface irregularities, or mill scale shall not be cause for rejection, provided the weight [mass], nominal dimensions, cross-sectional area, and tensile properties of a hand wire brushed test specimen are not less than the requirements of this specification.

12.3 Surface imperfections or flaws other than those specified in 12.2 shall be considered detrimental when specimens containing such imperfections fail to conform to either tensile or bending requirements. Examples include, but are not limited to, laps, seams, scabs, slivers, cooling or casting cracks, and mill or guide marks.

NOTE 7—Deformed reinforcing bars intended for epoxy coating applications should have surfaces with a minimum of sharp edges to achieve proper coverage. Particular attention should be given to bar marks and deformations where coating difficulties are prone to occur.

NOTE 8—Deformed reinforcing bars destined to be mechanically-spliced or butt-spliced by welding may require a certain degree of roundness in order for the splices to adequately achieve strength requirements.

13. Number of Tests

13.1 One tension test and one bend test shall be made of each bar size rolled from each heat.

13.2 One set of dimensional property tests including bar weight [mass] and spacing, height, and gap of deformations shall be made of each bar size rolled from each heat.

14. Retests

14.1 If the results of an original tension test specimen fail to meet the specified minimum requirements and are within 2000 psi [14 MPa] of the required tensile strength, within 1000 psi [7 MPa] of the required yield strength, or within two percentage units of the required elongation, a retest shall be permitted on two random specimens for each original tension test specimen failure from the lot. Both retest specimens shall meet the requirements of this specification.

14.2 If a bend test fails for reasons other than mechanical reasons or flaws in the specimen as described in 14.4.2 and 14.4.3, a retest shall be permitted on two random specimens from the same lot. Both retest specimens shall meet the requirements of this specification. The retest shall be performed on test specimens that are at air temperature but not less than 60°F [16°C].

14.3 If a weight [mass] test fails for reasons other than flaws in the specimen as described in 14.4.3, a retest shall be permitted on two random specimens from the same lot. Both retest specimens shall meet the requirements of this specification.

14.4 If the original test or any of the random retests fails because of any reasons listed in 14.4.1, 14.4.2, or 14.4.3, the test shall be considered an invalid test:

14.4.1 The elongation property of any tension test specimen is less than that specified, and any part of the fracture is outside the middle half of the gage length, as indicated by scribe marks on the specimen before testing;

NOTE 9—Marking specimens with multiple scribe or punch marks can reduce the occurrence of fracture outside or near these marks and the need for declaring the test invalid.

14.4.2 Mechanical reasons such as failure of testing equipment or improper specimen preparation; and

14.4.3 Flaws are detected in a test specimen, either before or during the performance of the test.

14.5 The original results from 14.4.1, 14.4.2, or 14.4.3 shall be discarded and the test shall be repeated on a new specimen from the same lot.

15. Test Specimens

15.1 All mechanical tests shall be conducted in accordance with Test Methods and Definitions A370. In case of any conflict between the requirements in this specification and the requirements of Test Methods and Definitions A370, the requirements in this specification shall prevail.

15.2 Tension test specimens shall be the full section of the bar as rolled. Unit stress determinations for yield and tensile strength shall be based on the nominal bar area.

15.2.1 Tension test specimens shall be long enough to provide for an 8-in. [200-mm] gage length, a distance of at least two bar diameters between each gage mark and the grips.

NOTE 10—It is recommended that sufficient additional length of the test specimen be provided to fill the grips completely, leaving some excess length protruding beyond each grip. The grips should be shimmed so that no more than ½ in. [13 mm] of a grip protrudes from the head of the tensile testing machine.

15.2.2 *Gage Marks*—The 8-in. [200-mm] gage length shall be marked on the specimen using a preset 8-in. [200-mm] punch or, alternately, may be punch marked every 2 in. [50 mm] along the 8-in. [200-mm] gage length, on one of the longitudinal ribs, if present, or in the clear spaces between transverse deformations. Punch marks shall not be placed on a transverse deformation.

NOTE 11—Light punch marks are desirable because deep marks severely indent the bar and may affect the results.

15.3 Bend test specimens shall be the full section of the bar as rolled.

16. Test Reports

16.1 The following information shall be reported on a per heat basis. Report additional items as requested or desired.

16.1.1 Chemical analysis including the percentages of carbon, manganese, phosphorus, and sulfur.

16.1.2 Tensile properties.

16.1.3 Bend test results.

16.2 A Material Test Report, Certificate of Inspection, or similar document printed from or used in electronic form from an electronic data interchange (EDI) transmission shall be regarded as having the same validity as a counterpart printed in the certifier's facility. The content of the EDI transmitted document shall meet the requirements of the invoked ASTM standard(s) and conform to any EDI agreement between the purchaser and the manufacturer. Notwithstanding the absence of a signature, the organization submitting the EDI transmission is responsible for the content of the report.

NOTE 12—The industry definition invoked here is: EDI is the computer to computer exchange of business information in a standard format such as ANSI ASC X12.

17. Inspection

17.1 Inspection of the carbon-steel reinforcing bars shall be agreed upon between the purchaser and the manufacturer as part of the purchase order or contract.

18. Rejection and Rehearing

18.1 Any rejection based on testing undertaken by the purchaser shall be promptly reported to the manufacturer.

18.2 Samples tested that represent rejected material shall be preserved for two weeks from the date rejection is reported to the manufacturer. In case of dissatisfaction with the results of the tests, the manufacturer shall have the right to make claim for a rehearing within that time.

19. Marking

19.1 When loaded for mill shipment, bars shall be properly separated and tagged with the manufacturer's heat or test identification number. Unless otherwise specified, it shall be permissible for the manufacturer to make a full-size bundle at the end of a heat by adding bars from a consecutively rolled heat of the same nominal chemical composition. The manufacturer shall identify a bundle consisting of bars from two heats with the identification number of the first heat rolled or identify both heats. The manufacturer shall maintain records of the heats contained in each bundle.

NOTE 13—It is recommended that the manufacturer provide mill certificates from both heats in bundle.

19.2 Each manufacturer shall identify the symbols of their marking system.

19.3 All bars produced to this specification, except plain bars which shall be tagged for grade, shall be identified by a distinguishing set of marks legibly rolled onto the surface of one side of the bar to denote in the following order:

19.3.1 *Point of Origin*—Letter or symbol established as the manufacturer's mill designation.

19.3.2 *Size Designation*—Arabic number corresponding to bar designation number of Table 1.

19.3.3 *Type of Steel*—Letter S indicating that the bar was produced to this specification, or for Grades 60 [420] and 80



[550] bars only, letters *S* and *W* indicating that the bar was produced to meet both this specification and Specification **A706/A706M**.

19.3.4 Minimum Yield Strength Designation—For Grade 60 [420] bars, either the number 60 [4] or a single continuous longitudinal line through at least five deformation spaces offset from the center of the bar side. For Grade 75 [520] bars, either the number 75 [5] or two continuous longitudinal lines through at least five deformation spaces offset each direction from the center of the bar. For Grade 80 [550] bars, either the number 80 [6] or three continuous longitudinal lines through at least five deformation spaces. For Grade 100 [690] bars, either the number 100 [7] or four continuous lines through at least five deformation spaces, or the letter *C*. No marking designation is required for Grade 40 [280] bars.

19.3.5 It shall be permissible to substitute: a metric size bar of Grade 280 for the corresponding inch-pound size bar of Grade 40, a metric size bar of Grade 420 for the corresponding inch-pound size bar of Grade 60, a metric size bar of Grade 520

for the corresponding inch-pound size bar of Grade 75, a metric size bar of Grade 550 for the corresponding inch-pound size bar of Grade 80, and a metric size bar of Grade 690 for the corresponding inch-pound size bar of Grade 100.

20. Packaging and Package Marking

20.1 Packaging, marking, and loading for shipment shall be in accordance with Practices **A700**.

20.2 When specified in the purchase order or contract, and for direct procurement by or direct shipment to the U.S. Government, marking for shipment, in addition to requirements specified in the purchase order or contract, shall be in accordance with MIL-STD-129 for military agencies and with Fed. Std. No. 123 for civil agencies.

21. Keywords

21.1 concrete reinforcement; deformations (protrusions); steel bars

ANNEX

(Mandatory Information)

A1. ALTERNATE BAR SIZES

A1.1 The following requirements shall apply only when specified in the purchase order or contract. When specified, the following **Table A1.1**, **Table A1.2**, and **Table A1.3** replace **Table 1**, **Table 2**, and **Table 3**, respectively.

TABLE A1.1 Deformed Bar Designations, Nominal Weights [Masses], Nominal Dimensions, and Deformation Requirements

Bar Designation No. ^A	Nominal Weight, lb/ft ^B [Nominal Mass, kg/m] ^C	Nominal Dimensions ^D			Deformation Requirements, in. [mm]		
		Diameter, in. [mm]	Cross-Sectional Area in. ² [mm ²]	Perimeter, in. [mm]	Maximum Average Spacing	Minimum Average Height	Maximum Gap (Chord of 12.5 % of Nominal Perimeter)
10	0.414 [0.617]	0.394 [10.0]	0.12 [79]	1.237 [31.4]	0.276 [7.0]	0.016 [0.40]	0.151 [3.8]
12	0.597 [0.888]	0.472 [12.0]	0.18 [113]	1.484 [37.7]	0.331 [8.4]	0.019 [0.48]	0.181 [4.6]
16	1.061 [1.578]	0.630 [16.0]	0.31 [201]	1.979 [50.3]	0.441 [11.2]	0.028 [0.72]	0.241 [6.1]
20	0.657 [2.466]	0.787 [20.0]	0.49 [314]	2.474 [62.8]	0.551 [14.0]	0.039 [1.00]	0.301 [7.7]
25	2.589 [3.853]	0.984 [25.0]	0.76 [491]	3.092 [78.5]	0.689 [17.5]	0.049 [1.25]	0.377 [9.6]
28	3.248 [4.834]	1.102 [28.0]	0.95 [616]	3.463 [88.0]	0.772 [19.6]	0.055 [1.40]	0.422 [10.7]
32	4.242 [6.313]	1.260 [32.0]	1.25 [804]	3.958 [100.5]	0.882 [22.4]	0.063 [1.60]	0.482 [12.2]
36	5.369 [7.990]	1.417 [36.0]	1.58 [1018]	4.453 [113.1]	0.992 [25.2]	0.071 [1.80]	0.542 [13.8]
40	6.629 [9.865]	1.575 [40.0]	1.95 [1257]	4.947 [125.7]	1.102 [28.0]	0.79 [2.00]	0.603 [15.3]
50	10.36 [15.41]	1.969 [50.0]	3.04 [1963]	6.184 [157.1]	1.378 [35.0]	0.098 [2.50]	0.753 [19.1]
60	14.91 [22.20]	2.362 [60.0]	4.38 [2827]	7.421 [188.5]	1.654 [42.0]	0.106 [2.70]	0.904 [23.0]

^A The bar designations are based on the number of millimetres of the nominal diameter of the bar.

^B The assumed weight of a cubic foot of steel is 490 lb/ft³ in accordance with Specification **A6/A6M**.

^C The assumed mass of a cubic metre of steel is 7850 kg/m³ in accordance with Specification **A6/A6M**.

^D The nominal dimensions of a deformed bar are equivalent to those of a plain round bar having the same weight [mass] per foot [metre] as the deformed bar.



TABLE A1.2 Tensile Requirements

	Grade 40 [280] ^A	Grade 60 [420]	Grade 75 [520]	Grade 80 [550]	Grade 100 [690]
Tensile strength, min, psi [MPa]	60 000 [420]	90 000 [620]	100 000 [690]	105 000 [725]	115 000 [790]
Yield strength, min, psi [MPa]	40 000 [280]	60 000 [420]	75 000 [520]	80 000 [550]	100 000 [690]
Elongation in 8 in. [200 mm], min, %					
Bar Designation No.					
10	11	9	7	7	7
12, 16	12	9	7	7	7
20	12	9	7	7	7
25	...	8	7	7	7
28, 32, 36	...	7	6	6	6
40, 50, 60	...	7	6	6	6

^A Only bar sizes 10 through 20 are covered by this specification for Grade 40 [280].

TABLE A1.3 Bend Test Requirements

Bar Designation No.	Pin Diameter for Bend Tests ^A				
	Grade 40 [280]	Grade 60 [420]	Grade 75 [520]	Grade 80 [550]	Grade 100 [690]
10, 12, 16	3½ <i>d</i> ^B	3½ <i>d</i>	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>
20	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>
25	...	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>	5 <i>d</i>
28, 32, 36	...	7 <i>d</i>	7 <i>d</i>	7 <i>d</i>	7 <i>d</i>
40, 50, 60 (90°)	...	9 <i>d</i>	9 <i>d</i>	9 <i>d</i>	9 <i>d</i>

^A Test bends 180° unless noted otherwise.

^B *d* = nominal diameter of specimen.

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A615/A615M – 15a^{e1}) that may impact the use of this standard. (Approved Jan. 15, 2016.)

(1) Revised Sections 4 and 17.

Committee A01 has identified the location of selected changes to this standard since the last issue (A615/A615M – 15) that may impact the use of this standard. (Approved July 1, 2015.)

(1) Added 4.2.1 and revised 19.1.

(2) Revised Section 15.

Committee A01 has identified the location of selected changes to this standard since the last issue (A615/A615M – 14) that may impact the use of this standard. (Approved April 1, 2015.)

(1) Revised 3.1.2.1.

(2) Revised 16.1 and Section 4 to require the manufacture to furnish test results.

(3) Revised 2.1 and 10.3.

(4) Added Grade 100 [690], which required revision of 1.2, 1.3, 19.3.4, and 19.3.5, in addition of new Note 1, and revision of Table 2, Table 3, Table A1.2, and Table A1.3.

(5) Added bar size No. 20 [64], which required revision of Table 1, Table 2, and Table 3, and addition of new Note 2.



ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>