



## Standard Specification for Nickel Oxide Sinter<sup>1</sup>

This standard is issued under the fixed designation A636; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers one grade of nickel oxide sinter, designated as 75 used for alloying in iron and steel melting.

### 2. Referenced Documents

2.1 *ASTM Standards*:<sup>2</sup>

**A1025** Specification for Ferrous Alloys and Other Alloying Materials, General Requirements

### 3. General Conditions for Delivery

3.1 Materials furnished to this specification shall conform to the requirements of Specification **A1025**, including any supplementary requirements that are indicated in the purchase order. Failure to comply with the general requirements of Specification **A1025** constitutes nonconformance with this specification. In case of conflict between the requirements of this specification and Specification **A1025**, this specification shall prevail.

### 4. Chemical Requirements

4.1 The chemical requirements are shown in **Table 1**.

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.18** on Castings.

Current edition approved April 1, 2013. Published April 2013. Originally approved in 1970. Last previous edition approved in 2008 as A636 - 08. DOI: 10.1520/A0636-08R13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

### 5. Sampling for Chemical Analysis

5.1 The material shall be sampled in accordance with procedures outlined below:

5.1.1 The sample shall be taken by cutting across the entire stream at regular intervals during the time of movement of the mass being sampled. The quantity to be taken at each interval and the number of such intervals shall be so proportioned that the total quantity taken shall amount to not less than 0.40 % of the total material being sampled.

#### 5.2 Treatment of Sample:

5.2.1 In the case of nickel oxide sinter 75, the sample representing each shipment or lot shall be reduced in amount using a riffle splitter or other suitable mechanical splitter to 1000 g. This 1000-g sample shall be placed in an oven at 250°F (121°C) for ½ h to remove any traces of moisture, and then pulverized to pass an 80-mesh screen using appropriate equipment to avoid sample contamination. Approximately 250 g of this pulverized material shall be split out for copper and sulfur assays, using a riffle splitter or other suitable mechanical splitter. The unused portion of individual shipment (or lot) samples whose copper and sulphur assays are within specification shall be combined by weight into two, three, or four lot composites. Approximately 250 g of the composited material shall be split out, using a riffle splitter or other suitable mechanical splitter and analyzed for nickel. This nickel analysis shall apply to each shipment (or lot) comprising the composite.

### 6. Keywords

6.1 nickel; nickel oxide; sinter

**TABLE 1 Chemical Requirements**

Element	Composition, %
	Grade 75
Nickel, min	75.00
Cobalt, max	1.30
Copper, max	0.90
Iron, max	0.50
Sulfur, max	0.02

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the ASTM website ([www.astm.org/COPYRIGHT/](http://www.astm.org/COPYRIGHT/)).