



Standard Specification for Precipitation–Strengthened Low-Carbon Nickel-Copper- Chromium-Molybdenum-Columbium Alloy Structural Steel Plates¹

This standard is issued under the fixed designation A710/A710M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers low-carbon precipitation–strengthened nickel - copper - chromium - molybdenum - columbium alloy steel plates for general applications. The alloys in this specification are strengthened by precipitation in various temperature ranges. Precipitation strengthening can occur upon air cooling after hot rolling, during normalizing, and by another heat treatment. These grades are not intended for use in applications above 900°F [540°C].

1.2 Two grades, each with three classes, are provided as follows:

Grade and Class	Condition
Grade A, Class 1	as-rolled and precipitation heat treated
Grade A, Class 2	normalized and precipitation heat treated
Grade A, Class 3	quenched and precipitation heat treated
Grade B, Class 1	as-rolled
Grade B, Class 2	normalized
Grade B, Class 3	normalized and precipitation heat treated

1.3 Grade A provides minimum yield strength levels ranging from 50 to 85 ksi [345 to 585 MPa], depending on thickness and condition.

1.4 Grade A, Class 1, plates are limited to a maximum thickness of ¾ in. [20 mm]. The maximum thickness of Grade A, Classes 2 and 3, is limited only by the capacity of the composition to meet the specified mechanical property requirements; however, current practice normally limits the maximum thickness to 8 in. [200 mm].

1.5 Mandatory notch toughness requirements are specified for Grade A, Class 1.

1.6 Grade B provides minimum yield strength levels ranging from 70 to 75 ksi [480 to 515 MPa], depending on thickness and condition.

1.7 Grade B plates are limited to a maximum thickness of 2 in. [50 mm].

1.8 Mandatory notch toughness requirements are specified for the three classes of Grade B.

1.9 When the steel is to be welded, it is presupposed that a welding procedure suitable for the grade of steel and intended use or service will be utilized. See Appendix X3 of Specification **A6/A6M** for information on weldability.

1.10 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification.

2. Referenced Documents

2.1 ASTM Standards:²

A6/A6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling
A673/A673M Specification for Sampling Procedure for Impact Testing of Structural Steel

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *precipitation heat treatment*—a sub-critical temperature thermal treatment performed to cause precipitation of submicroscopical constituents, etc., so as to result in enhancement of some desirable property.

3.1.2 *precipitation strengthening*—the precipitation of sub-microscopic and/or microscopic constituents of an alloy at various temperatures, which results in the alteration of certain properties.

¹ This specification is under the jurisdiction of ASTM Committee **A01** on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee **A01.02** on Structural Steel for Bridges, Buildings, Rolling Stock and Ships.

Current edition approved May 15, 2013. Published June 2013. Originally approved in 1974. Last previous edition approved in 2007 as A710/A710M – 02 (2007). DOI: 10.1520/A0710_A0710M-02R13.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

***A Summary of Changes section appears at the end of this standard**

3.1.3 *soak*—to hold at temperature after the material has attained the temperature throughout.

4. General Requirements for Delivery

4.1 Material furnished under this specification shall conform to the requirements of the current edition of Specification **A6/A6M**, for the ordered material, unless a conflict exists in which case this specification shall prevail.

5. Materials and Manufacture

5.1 The steel shall be made to fine grain practice.

6. Heat Treatment

6.1 Grade A, Class 1 material shall be precipitation heat treated in the temperature range from 1000 to 1300°F [540 to 705°C] for a time to be determined by the material manufacturer.

6.2 Grade A, Class 2 material shall be normalized at a temperature in the range from 1600 to 1700°F [870 to 925°C] and then precipitation heat treated at a temperature in the range from 1000 to 1300°F [540 to 705°C] for a time to be determined by the material manufacturer.

6.3 Grade A, Class 3 material shall be quenched in water or oil from a temperature in the range from 1600 to 1700°F [870 to 925°C] and then precipitation heat treated at a temperature in the range from 1000 to 1300°F [540 to 705°C] for a time to be determined by the material manufacturer.

6.4 Grade B, Class 1 shall be hot-rolled.

6.5 Grade B, Class 2 shall be normalized after hot rolling by reheating to 1600 to 1700°F [870 to 925°C], and then cooled in still air.

6.6 Grade B, Class 3, shall be normalized at 1600 to 1700°F [870 to 925°C], and then precipitation heat treated at 1000 to 1300°F [540 to 705°C] for a time to be determined by the material manufacturer. One hour at a specified temperature is generally considered as a maximum.

6.7 If the purchaser elects to perform the thermal (heat) treatment, the material shall be accepted on the basis of mill tests from test coupons heat treated in accordance with the purchase order requirements. If the test coupon heat treatment requirements are not indicated on the purchase order, the

manufacturer shall heat treat the test coupons under conditions he considers appropriate. The manufacturer shall inform the purchaser of the procedure followed in thermally treating the test coupons at the mill.

7. Chemical Composition

7.1 The heat analysis shall conform to the requirements as to chemical composition prescribed in **Table 1**.

7.2 The steel shall conform on product analysis to the requirements prescribed in **Table 1**, subject to the product analysis tolerance in Specification **A6/A6M** for alloy steels.

8. Tension Test

8.1 The material, as represented by the test specimens, shall conform to the requirements specified in **Table 2**.

8.2 *Number of Tests*—One tension test shall be taken from a corner of each plate as heat treated for each class of material. For plates $\frac{3}{8}$ in. [10 mm] and under in thickness, a tension test shall be made from a corner of each of two plates per lot. A lot shall consist of plates from the same heat and thickness, same prior condition and scheduled heat treatment, and shall not exceed 15 tons [13.6 Mg] in weight. Plates wider than 24 in. [610 mm] shall be tested in the transverse direction and are subject to the modifications for elongation contained in footnote ^D of **Table 2**.

9. Notch Toughness Requirements

9.1 *Notch Toughness Tests—Grade A, Class 1:*

9.1.1 Notch toughness tests shall be made in accordance with Test Frequency H of Specification **A673/A673M**. Upon agreement, transverse tests may be specified instead of the longitudinal tests specified in Specification **A673/A673M** (plates only).

9.1.2 The test results shall meet a minimum average value of 20 ft·lbf [27 J] at –50°F [–45°C] for longitudinal specimens. For transverse specimens, the test results shall meet a minimum average value of 15 ft·lbf [20 J] at –50°F [–45°C]. By agreement, a test temperature lower than –50°F [–45°C] may be used.

9.2 *Notch Toughness Tests—Grade B:*

9.3 Notch toughness tests shall be made in accordance with Test Frequency H of Specification **A673/A673M**.

TABLE 1 Chemical Requirements

Element	Composition, %	
	Grade A	Grade B
Carbon	0.07 max	0.03–0.09
Manganese	0.40–0.70	0.45–1.30
Phosphorus, max	0.025	0.025
Sulfur, max	0.025	0.025
Silicon	0.40 max	0.30–0.50
Nickel	0.70–1.00	0.80–1.00
Chromium	0.60–0.90	0.30 max
Molybdenum	0.15–0.25	0.25 max
Copper	1.00–1.30	1.25–1.50
Columbium	0.02 min	0.02–0.06
Titanium	...	0.01–0.03

NOTE: Where an ellipsis (...) appears in the table, there is no requirement.

TABLE 2 Tensile Requirements^A

	Grade A Class 1	Grade A Class 2	Grade A Class 3	Grade B Class 1	Grade B Class 2	Grade B Class 3
Yield strength,^B min, ksi [MPa]						
¼ in. [6.5 mm] and under	85 [585]	65 [450]	80 [550]	70 [485]	70 [485]	70 [515]
Over ¼ in. to ⅝ in. [6.5 to 8 mm], incl	85 [585]	65 [450]	80 [550]	70 [485]	70 [485]	70 [515]
Over ⅝ in. to ¾ in. [8 to 10 mm], incl	80 [550]	65 [450]	80 [550]	70 [485]	70 [485]	70 [515]
Over ¾ in. to 1 in. [10 to 12.5 mm], incl	80 [550]	65 [450]	80 [550]	70 [485]	70 [485]	70 [515]
Over 1 in. to 1¼ in. [12.5 to 20 mm], incl	80 [550]	65 [450]	80 [550]	70 [485]	70 [485]	70 [515]
Over 1¼ in. to 2 in. [20 to 25 mm], incl	...	65 [450]	80 [550]	70 [485]	70 [485]	70 [485]
Over 2 in. to 4 in. [25 to 30 mm], incl	...	60 [415]	80 [550]	...	70 [485]	70 [485]
Over 4 in. to 6 in. [30 to 50 mm], incl	...	60 [415]	75 [515]	...	70 [485]	70 [485]
Over 6 in. to 10 in. [50 to 100 mm], incl	...	55 [380]	65 [450]
Over 10 in. [100 mm]	...	50 [345]	60 [415]
Tensile strength, min, ksi [MPa]						
¼ in. [6.5 mm] and under	90 [620]	72 [495]	85 [585]	80 [550]	80 [550]	80 [585]
Over ¼ in. to ⅝ in. [6.5 to 8 mm], incl	90 [620]	72 [495]	85 [585]	80 [550]	80 [550]	80 [585]
Over ⅝ in. to ¾ in. [8 to 10 mm], incl	90 [620]	72 [495]	85 [585]	80 [550]	80 [550]	80 [585]
Over ¾ in. to 1 in. [10 to 12.5 mm], incl	90 [620]	72 [495]	85 [585]	80 [550]	80 [550]	80 [585]
Over 1 in. to 1¼ in. [12.5 to 20 mm], incl	90 [620]	72 [495]	85 [585]	80 [550]	80 [550]	80 [585]
Over 1¼ in. to 2 in. [20 to 25 mm], incl	...	72 [495]	85 [585]	80 [550]	80 [550]	80 [550]
Over 2 in. to 4 in. [25 to 30 mm], incl	...	72 [495]	85 [585]	...	80 [550]	80 [550]
Over 4 in. to 6 in. [30 to 50 mm], incl	...	72 [495]	85 [585]	...	80 [550]	80 [550]
Over 6 in. to 10 in. [50 to 100 mm], incl	...	65 [450]	75 [515]
Over 10 in. [100 mm]	...	60 [415]	70 [485]
Elongation in 2 in. or 50 mm, min, % ^{CD}	20	20	20	20	20	20

NOTE: Where ellipses (...) appear in the table, there is no requirement.

^A For plates wider than 24 in. [600 mm], the test specimen is taken in the transverse direction. See Specification **A6/A6M**, Tension Tests requirements.

^B 0.2 % offset or 0.5 % extension-under-load.

^C For thickness of ¾ in. [20 mm] and under, measured on 1½ in. [40 mm] wide full thickness rectangular specimen as shown in Fig. 4 of Test Methods and Definitions A370. The elongation is measured in a 2-in. [50-mm] gage length which includes the fracture and which shows the greatest elongation.

^D For plates wider than 24 in. [600 mm], the elongation requirement is reduced two percentage points.

9.4 The test results for Grade B, Class 1, and Grade B, Class 3, shall have a minimum average notch toughness of 35 ft-lbf [47 J] at -10°F [-23°C] in the longitudinal direction of the plate. For Grade B, Class 2, test results shall have a minimum average notch toughness of 20 ft-lbf [27 J] at -50°F [-45°C] in the longitudinal direction of the plate.

10. Retreatment

10.1 Thermally treated material that fails to meet the mechanical property requirements may be reheat-treated. All required tests shall be repeated when material is resubmitted for inspection.

11. Keywords

11.1 alloy; carbon; chromium; columbium; copper; general applications; low carbon; manganese; molybdenum; nickel; plates; precipitation heat treatment; precipitation strengthening; steel; structural steel

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the purchase order or contract. Standardized supplementary requirements for use at the option of the purchaser are listed in Specification **A6/A6M**. In addition, the following supplementary requirement is also suitable for use with this specification:

S94. Notch Toughness—Grade A, Classes 2 and 3

S94.1 Notch toughness tests on longitudinal specimens shall be made in accordance with Test Frequency H of Specification **A673/A673M**.

S94.2 *Grade A, Class 2*—The test results shall meet a minimum average value of 50 ft-lbf [69 J] at -50°F [-45°C].

S94.3 *Grade A, Class 3*—The test results shall meet a minimum average value of 50 ft-lbf [69 J] at -80°F [-60°C].

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).