

Standard Specification for Pressure Vessel Plates, Heat-Treated, Carbon-Manganese-Silicon Steel, for Moderate and Lower Temperature Service¹

This standard is issued under the fixed designation A738/A738M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification² covers heat-treated carbonmanganese-silicon steel plates intended for use in welded pressure vessels at moderate and lower temperature service.

1.2 Material under this specification is available in four strength levels, 75 ksi [515 MPa], 85 ksi [585 MPa], 80 ksi [550 MPa], and 90 ksi [620 MPa] minimum ultimate tensile strengths.

1.3 The maximum thickness of plates for Grades A, B, and C is limited only by the capacity of the chemical composition and heat treatment to meet the specified mechanical property requirements; however, current practice normally limits the maximum thickness of plates furnished under this specification to 6 in. [150 mm] for Grade A, 4 in. [100 mm] for Grade B, and 6 in. [150 mm] for Grade C. The maximum permitted nominal thickness is 1.5 in. [40 mm] for Grade D and 2 in. [50 mm] for Grade E.

1.4 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

2. Referenced Documents

2.1 *ASTM Standards:*³ A20/A20M Specification for General Requirements for Steel Plates for Pressure Vessels

3. General Requirements and Ordering Information

3.1 Material supplied to this material specification shall conform to Specification A20/A20M. These requirements outline the testing and retesting methods and procedures, permitted variations in dimensions, and mass, quality and repair of defects, marking, loading, and ordering information.

3.2 In addition to the basic requirements of this specification, certain supplementary requirements are available when additional control, testing, or examination is required to meet end use requirements. The purchaser is referred to the listed supplementary requirements in this specification and to the detailed requirements in Specification A20/A20M.

3.3 If the requirements of this specification are in conflict with the requirements of Specification A20/A20M, the requirements of this specification shall prevail.

4. Manufacture

4.1 *Steelmaking Practice*—The steel shall be killed and shall conform to the fine austenitic grain size requirement of Specification A20/A20M.

5. Heat Treatment

5.1 Grade A plates 2.5 in. [65 mm] and under in thickness shall be supplied in the normalized condition or in the quenched and tempered condition at the option of the manufacturer.

5.2 Grade A plates over 2.5 in. [65 mm] in thickness and Grade B, Grade C, Grade D, and Grade E plates in all thicknesses shall be quenched-and-tempered.

5.3 When plates are tempered, the minimum tempering temperature shall be 1100° F [595°C].

6. Chemical Requirements

6.1 The steel shall conform to the chemical requirements shown in Table 1 unless otherwise modified in accordance with Supplementary Requirement S 17, Vacuum Carbon-Deoxidized Steel in Specification A20/A20M.

7. Mechanical Requirements

7.1 *Tension Test Requirements*—The plates as represented by the tension test specimens shall conform to the requirements of Table 2.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.11 on Steel Plates for Boilers and Pressure Vessels.

Current edition approved Nov. 1, 2012. Published January 2013. Originally approved in 1976. Last previous edition approved in 2012 as A738/A738M – 12. DOI: $10.1520/A0738_A0738M$ -12A.

 $^{^2}$ For ASME Boiler and Pressure Vessel Code applications see related Specification SA-738/SA-738M in Section II of that Code.

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959. United States

A738/A738M – 12a

TABLE 1 Chemical Requirements

Flowent	Composition, %						
Element	Grade A	Grade B	Grade C	Grade D	Grade E		
Carbon, max ^A	0.24	0.20	0.20	0.10	0.12 ^B		
Manganese:							
Heat analysis	4.50	0.00 4.50	1 50		1 10 1 00 ^B		
1.5 In. [40 mm] and under	1.50 max	0.90-1.50	1.50 max	1.00-1.60	1.10-1.60		
Over 1.5 to 2.0 In.	1.50 max	0.90-1.50	1.50 max	0	1.10-1.60		
$[40\ 10\ 50\ 1111]$	1 E0 may	0.00 1.50	1 E0 mov	С	С		
[50 to 65 mm] incl	1.50 max	0.90-1.50	1.50 max				
Over 2.5 in. [65 mm]	1.60 max	0.90-1.60	1.60 max	С	С		
Product analysis							
1.5 in. [40 mm] and under	1.62 max	0.84-1.62	1.62 max	0.92-1.72	1.02–1.72 ^B		
Over 1.5 to 2.0 in.	1.62 max	0.84-1.62	1.62 max	C	1.02–1.72 ^B		
[40 to 50 mm], incl				0	C		
Over 2.0 to 2.5 in.	1.62 max	0.84–1.62	1.62 max	C	C		
[50 to 65 mm], Incl Over 2.5 in [65 mm]	1 70 mov	0 94 1 72	1 70 max	С	С		
	1.72 max	0.04-1.72	1.72 max				
Phosphorus, max ^A	0.025	0.025	0.025	0.015	0.015		
Sulfur, max ^A	0.025	0.025	0.025	0.006	0.006		
Silicon:							
Heat analysis	0.15-0.50	0.15-0.55	0.15-0.50	0.15-0.50	0.15-0.50		
Product analysis	0.13-0.55	0.13-0.60	0.13-0.55	0.13-0.55	0.13–0.55		
0							
Copper, max:	0.05	0.05	0.05	0.05	0.05		
Product analysis	0.35	0.35	0.35	0.35	0.35		
	0.50	0.50	0.00	0.00	0.00		
Nickel, max:							
Heat analysis	0.50	0.60	0.50	0.60	0.70		
Product analysis	0.53	0.63	0.53	0.63	0.73		
Ohmanni una anna							
Chromium, max:	0.05	0.00	0.05	0.05	0.00		
Product analysis	0.25	0.30	0.25	0.25	0.30		
	0.23	0.04	0.23	0.23	0.04		
Molybdenum, max:							
Heat analysis							
1.5 in. [40 mm] and under	0.08	0.20	0.08	0.30	0.35		
Over 1.5 in. [40 mm]	0.08	0.30	0.08	C	C		
Product analysis							
1.5 in [40 mm] and under	0.09	0.21	0.09	0 33	0.38		
Over 1.5 in [40 mm]	0.09	0.33	0.09	C.00	C		
Vanadium, max:	0.00	0.00	0100				
Heat analysis	0.07 ^D	0.07	0.05	0.08	0.09		
Product analysis	0.08 ^D	0.08	0.05	0.09	0.10		
- · · · ·							
Columbium, max:	0.040	0.04	F	0.05	0.05		
Product analysis	0.04 ⁻ 0.05 ^D	0.04	E	0.05	0.05		
	0.05	0.00		0.00	0.00		
Columbium plus Vanadium,							
max:							
Heat analysis	0.08 ^D	0.08	E	0.11	0.12		
Product analysis	0.10 ^D	0.10	E	0.12	0.13		
Titanium max ^A				F	G		
Boron, max ^A			•••	0.0007	0.0007		
Aluminum, min ^A				0.020 total or	0.020 total or		
				0.015 acid	0.015 acid		
				soluble ^F	soluble ^G		

^A Applies to both heat and product analyses.

^B For each reduction of 0.01 percentage point below the specified maximum for carbon, an increase of 0.06 percentage point above the specified maximum for manganese is permitted, up to a maximum of 1.85 % by heat analysis, and 1.99 % by product analysis. $^{\it C}$ Not applicable.

^D Vanadium and columbium may be added only by agreement between the manufacturer and the purchaser.

^E For Grade C, columbium is an unspecified element.

^F By agreement between the manufacturer and the purchaser, the steel may be produced with titanium, in which case the minimum aluminum content shall not apply. If this option is exercised, the titanium content, by heat analysis, shall be 0.006 % to 0.03 %, and the titanium content for the heat and product analyses shall be reported on the test report.

^G By agreement between the manufacturer and the purchaser, the steel may be produced with titanium, in which case the minimum aluminum content shall not apply. If this option is exercised, the titanium content, by heat analysis, shall be 0.006 % to 0.03 % inclusive and the titanium content for the heat and product analyses shall be reported on the test report.

∰ A738/A738M – 12a

TABLE 2 Tensile Requirements

NOTE 1-t =plate nominal thickness.

	Grade A	Grade B	Grade C	Grade D	Grade E
Tensile strength, ksi [MPa]					
1.5 in. [40 mm] and under	75–95 [515–655]	85–102 [585–705]	80–100 [550–690]	85–105 [585–724]	90–110 [620–760]
Over 1.5 to 2.0 in. [40 to 50 mm], incl	75–95 [515–655]	85–102 [585–705]	80–100 [550–690]	А	90–110 [620–760]
Over 2.0 to 2.5 in. [50 to 65 mm]	75–95 [515–655]	85–102 [585–705]	80–100 [550–690]	А	А
Over 2.5 to 4 in. [65 to 100 mm], incl	75–95 [515–655]	85–102 [585–705]	75–95 [515–655]	А	А
Over 4 in. [100 mm]	75–95 [515–655]	85–102 [585–705]	70–90 [485–620]	А	А
Yield strength, min, ksi [MPa]					
1.5 in. [40 mm] and under	45 [310]	60 [415]	60 [415]	70 [485]	75 [515]
Over 1.5 to 2.0 in. [40 to 50 mm], incl	45 [310]	60 [415]	60 [415]	А	75 [515]
Over 2.0 to 2.5 in. [50 to 65 mm], incl	45 [310]	60 [415]	60 [415]	A	А
Over 2.5 to 4 in. [65 to 100 mm], incl	45 [310]	60 [415]	55 [380]	А	А
Over 4 in. [100 mm]	45 [310]	60 [415]	46 [315]	А	А
Elongation in 2 in. [50 mm], min, % ^B					
1.5 in. [40 mm] and under	20	20	22	20	20
Over 1.5 to 4 in. [40 to 100 mm], incl	20	20	22	A	А
Over 4 in. [100 mm]	20	20	20	А	А

A Not applicable.

^B See Specification A20/A20M for elongation requirement adjustments.

7.1.1 For nominal plate thicknesses of $\frac{3}{4}$ in. [20 mm] and under, the 1.5-in. [40-mm] wide rectangular specimen may be used for the tension test and the elongation may be determined in a 2-in. [50-mm] gage length that includes the fracture and shows the greatest elongation.

8. Keywords

8.1 pressure-containing parts; pressure vessel steel; steel plates; steel plates for pressure vessel applications

SUPPLEMENTARY REQUIREMENTS

Supplementary requirements shall not apply unless specified in the purchase order. A list of standardized supplementary requirements for use at the option of the purchaser is included in Specification A20/A20M. Several of those considered suitable for use with this specification are listed by title. Other tests may be performed by agreement between the supplier and the purchaser:

S1. Vacuum Treatment

S2. Product Analysis.

S3. Simulated Post-Weld Heat Treatment of Mechanical Test Coupons.

S4. Additional Tension Test.

S5. Charpy V-Notch Impact Test.

S6. Drop Weight Test (for Material 0.625 in. [16 mm] and Over in Thickness).

S9. Magnetic Particle Examination.

S12. Ultrasonic Examination in accordance with Specification A578/A578M.

S20. Maximum Carbon Equivalent for Weldability



APPENDIX

(Nonmandatory Information)

X1. CHARPY V-NOTCH IMPACT TEST

X1.1 The energy values below are shown only for information as to the guarantees that are generally available. Mandatory conformance to any of the values listed is a matter of agreement between the purchaser and the manufacturer. X1.1.1 *Longitudinal*—20 ft·lbf [27 J] at -50°F [-45°C]. X1.1.2 *Transverse*—20 ft·lbf [27 J] at -20°F [-30°C].

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this standard since the last issue (A738/A738M – 12) that may impact the use of this standard. (Approved Nov. 1, 2012.)

(1) 1.3 and 5.1 were revised.

(2) Table 1 and Table 2 were revised.

Committee A01 has identified the location of selected changes to this standard since the last issue (A738/A738M - 07) that may impact the use of this standard. (Approved May 1, 2012.)

(1) Table 1 was revised.

(2) Section 3 was editorially revised.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or a 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).