

Standard Specification for Metallic-Coated Steel Wire Rope and Fittings for Highway Guardrail¹

This standard is issued under the fixed designation A741; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers ³/₄ and 1-in. (19 and 25-mm) metallic-coated steel wire rope and fittings for use in the construction of highway guardrail.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

2. Referenced Documents

- 2.1 ASTM Standards:²
- A90/A90M Test Method for Weight [Mass] of Coating on Iron and Steel Articles with Zinc or Zinc-Alloy Coatings
- A123/A123M Specification for Zinc (Hot-Dip Galvanized) Coatings on Iron and Steel Products
- A153/A153M Specification for Zinc Coating (Hot-Dip) on Iron and Steel Hardware
- A370 Test Methods and Definitions for Mechanical Testing of Steel Products
- A902 Terminology Relating to Metallic Coated Steel Products

B6 Specification for Zinc

B750 Specification for GALFAN

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology A902.

4. Ordering Information

4.1 Orders for wire rope guardrail material purchased to this specification shall include the following:

4.1.1 Diameter of wire rope,

4.1.2 Type of wire rope construction,

4.1.3 Class and Type of Metallic coating—Z for zinc (see Table 1), M for Zinc-5 % Aluminum-Mischmetal Alloy (see Table 2),

4.1.4 Quantity of wire rope and length per reel, and

4.1.5 ASTM designation and year of issue.

Note 1—A typical ordering description is as follows: $\frac{3}{4}$ -in. (19-mm) diameter, Metallic-Coated Wire Rope for Guardrail, Type 1 Construction, Class ZA Coating, 80 000 lineal ft (24 300 m) on forty 2000-ft (608-m) reels, ASTM A741–.

5. Material

5.1 *Base Metal*—The base metal shall be steel made by any process and shall be of such quality that the finished wire rope and the individual metallic-coated wires shall have the properties as prescribed in this specification.

5.2 Zinc—The slab zinc or Zinc-5 % Aluminum-Mischmetal Alloy when used for the coating shall be any grade of zinc conforming to Specification B6 for Zinc coatings or Specification B750 for Zinc-5 % Aluminum-Mischmetal Alloy coatings.

5.3 *Coating Bath Analysis*—The bath metal used in continuous hot-dip Zn-5 Al-MM alloy-coated wire shall meet the chemical composition limits specified in Specification B750.

6. Mechanical Requirements

6.1 *Breaking Strength*—The metallic-coated steel wire rope shall conform to the mechanical properties in Table 3 when tested in accordance with Test Methods and Definitions A370 and employing a suitable gripping device as covered in Supplement VII of Test Methods and Definitions A370.

6.2 *Construction*—The metallic-coated wire rope and individual wires shall conform to the dimension and construction requirements of Table 3.

6.3 *Ductility of Steel*—The individual metallic-coated wires shall be capable of being wrapped two turns in a close helix at a rate not exceeding 15 turns per minute around a cylindrical steel mandrel equal to three times the nominal diameter of the wire under test without cracking or breaking of the wire.

6.4 Weight of Zinc Coating or Zinc-5 % Aluminum-Mischmetal Alloy—The class of metallic coating weight shall

¹ This specification is under the jurisdiction of ASTM Committee A05 on Metallic-Coated Iron and Steel Productsand is the direct responsibility of Subcommittee A05.12 on Wire Specifications.

Current edition approved Nov. 1, 2016. Published November 2011. Originally approved in 1976. Last previous edition approved in 2011 as A741 – 11^{ϵ_1} . DOI: 10.1520/A0741-11R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

🕼 A741 – 11 (2016)

TABLE 1 Minimum Weight of Coating for Zinc

		Weight of Zinc Coating, min						
Nominal Diame	eter of Coaled Wire	oz/ft ² of Uncoated Wire Surface g/m ² of Uncoated V			f Uncoated Wire	Vire Surface		
in.	mm	Class A Coating	Class B Coating	Class C Coating	Class A Coating	Class B Coating	Class C Coating	
0.040 to 0.061. incl	1.02 to 1.55. incl	0.40	0.80	1.20	122	244	366	
0.062 to 0.079, incl	1.58 to 2.01, incl	0.50	1.00	1.50	152	305	458	
0.080 to 0.092, incl	2.03 to 2.34, incl	0.60	1.20	1.80	183	366	549	
0.093 to 0.103, incl	2.36 to 2.62, incl	0.70	1.40	2.10	214	427	640	
0.104 to 0.119, incl	2.64 to 3.02, incl	0.80	1.60	2.40	244	488	732	
0.120 to 0.142, incl	3.05 to 3.61, incl	0.85	1.70	2.55	259	518	778	

TABLE 2 Minimum Weight of Coating for Zinc-5 % Aluminum-Mischmetal Alloy

Nominal Diameter of Coated Wire		Weight of Zinc-5 % Aluminum-Mischmetal Alloy Coating, min						
		oz/ft ² o	oz/ft ² of Uncoated Wire Surface g/m ² of Uncoated Wire Surf			Surface		
in.	mm	Class A Coating	Class B Coating	Class 1 Coating	Class A Coating	Class B Coating	Class 1 Coating	
0.040 to 0.061, incl	1.02 to 1.55, incl	0.40	0.80	0.20	122	244	61	
0.062 to 0.079, incl	1.58 to 2.01, incl	0.50	1.00	0.25	152	305	76	
0.080 to 0.092, incl	2.03 to 2.34, incl	0.60	1.20	0.30	183	366	92	
0.093 to 0.103, incl	2.36 to 2.62, incl	0.70	1.40	0.30	214	427	92	
0.104 to 0.119, incl	2.64 to 3.02, incl	0.80	1.60	0.40	244	488	122	
0.120 to 0.142, incl	3.05 to 3.61, incl	0.85†	1.70	0.40	259	518	122	

†Class A Coating Weight (oz/ft²) in the 0.120 to 0.142, incl range was editorially corrected.

TABLE 3 Guard Cable Requirements

Туре	Diameter, min, in. (mm)	Construction (No. of Strands × No. of Wires per Strand)	Breaking Strength, min, Ibf (kN)	Length of Lay of Strand, max, in. (mm)	Length of Lay of Wires in Strand, max, in. (mm)	Diameter of Coated Wires in Strand, in. (mm)
I	³ ⁄4 (19)	3 by 7	25 000 (110)	7.5 (190)	4.5 (114)	0.117 to 0.124 (2.97 to 3.15)
11	3⁄4 (19)	6 by 19 ^A IWRC ^B	42 800 (190)	Ċ	Ċ	variable
ll(a)	3⁄4 (19)	6 by 19 ^A wire strand core	42 800 (190)	С	С	variable
111	1 (25)	7 by 7	45 000 (200)	10 (254)	4.5 (114)	0.105 to 0.116 (2.67 to 2.84)

^A6 by 19 classification may have from 15 to 26 wires per strand.

^BIWRC = independent wire rope core.

^CLength of lay as specified by the manufacturer.

be specified by the purchaser. The weight of the metallic coating on the individual wires for the specified class and appropriate wire size shall not be less than that specified in Table 1 or Table 2 when tested in accordance with the stripping test of Test Method A90/A90M.

6.5 Adherence of Coating—The individual metallic-coated wires shall be capable of being wrapped two turns in a close helix at a rate not exceeding 15 turns per minute around a cylindrical steel mandrel equal to three times the nominal diameter of the wire under test without the coating cracking or flaking to such an extent that any zinc or Zinc-5 % Aluminum-Mischmetal Alloy can be removed by rubbing with bare fingers. Loosening or detachment during the adherence test of superficial small particles of zinc or Zinc-5 % Aluminum-Mischmetal Alloy formed by mechanical polishing of the surface of metallic-coated wire shall not be considered cause for rejection.

6.6 *Appearance*—The individual wires shall be cylindrical in form, of uniform quality, and free of imperfections not consistent with good commercial practice. The coating shall be continuous and reasonably uniform.

7. Wire Rope

7.1 The wire rope shall be right regular lay, preformed, and of the type of construction shown in Table 3. A right lay is defined as a clockwise twist away from the observer. The type of construction shall be specified by the purchaser.

8. Joints and Splices

8.1 *Individual Wires*—The distance between joints in any two individual wires in a strand shall be not less than 18 in. (460 mm). Joints in individual wires shall be either butt-welded or brazed-lap type. Joints made by butt welding shall have all flash removed. When the brazed-lap type of joint is used, the

A741 – 11 (2016)

length of the lap shall be not less than three times the diameter of the wire and the overlapping faces shall be smooth, clean, properly fluxed, and completely covered by the brazing metal. All joints shall be recoated after welding so that the joints shall have protection from corrosion equivalent to the metalliccoated wire itself.

8.2 *Strand or Rope*—Strand or rope splices may only be made when authorized in writing by the purchaser.

9. Sampling and Testing

9.1 One wire rope test specimen shall be taken from each lot. A lot shall consist of not more than 20 tons (18 metric tons) of wire rope of one size and type delivered at one time.

9.2 The test specimen shall be of a length to perform conveniently all tests prescribed in this specification.

9.3 A minimum of four wire test specimens shall be cut from each size of main wires in the rope, selected at random for testing for compliance with 6.2, 6.3, 6.4, and 6.5.

9.4 If an individual wire or the rope fails to meet any requirements of this specification, that reel shall be rejected and two additional tests shall be made on samples of wire rope from two different reels in the lot. If failure occurs in either of these tests, the lot of wire rope shall be rejected. The lot may be resubmitted for inspection after testing every reel for the characteristic in which the specimen failed and sorting out the defective reels.

10. Inspection

10.1 All tests and inspection shall be made at the place of manufacture unless otherwise specified and shall be so con-

ducted as not to interfere unnecessarily with the operation of the works. The manufacturer shall afford the inspector representing the purchaser all reasonable facilities to satisfy him that the material being furnished is in accordance with this specification. When specified, inspection may be waived and certified copies of test reports furnished. The purchaser reserves the right to test individual wires for compliance to 6.2, 6.3, 6.4, and 6.5, and the metallic-coated wire rope after fabrication.

11. Packaging

11.1 Current standard practice is to ship the wire rope on wooden reels. Each reel shall have the length, nominal diameter, type of strand construction, weight of rope, and name or trademark of the manufacturer plainly and indelibly marked on a strong tag, firmly attached, or this information shall be painted on the reel. The wooden reel shall be mountable so that it will revolve and the rope will run off by pulling straight ahead.

12. Fittings

12.1 The fittings shall be of the design called for in the plans and shall have the properties necessary to develop the strength of the wire rope.

12.2 Fittings as shown in the plans shall have a uniform coating of zinc conforming to Specifications A123/A123M or A153/A153M, whichever applies.

13. Keywords

13.1 galvanized wire; steel wire; wire; metallic-coated carbon steel wire

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/