

# Standard Specification for Steel, Sheet, Carbon, Ultra High Strength Cold Rolled<sup>1</sup>

This standard is issued under the fixed designation A980/A980M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

# 1. Scope

1.1 This specification covers a cold rolled ultra high strength carbon steel sheet in coils or cut lengths. The product is available in four strength levels. The steel's strength is obtained by water quenching from an austenitic temperature resulting in a martensitic microstructure. This product is intended for miscellaneous applications where ultra high strength, weight saving, and good weldability are important.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

# 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

A568/A568M Specification for Steel, Sheet, Carbon, Structural, and High-Strength, Low-Alloy, Hot-Rolled and Cold-Rolled, General Requirements for

# 3. Ordering Information

3.1 It is the purchaser's responsibility to specify in the purchase order all ordering information necessary to purchase the needed material. Examples of such information include, but are not limited to:

3.1.1 ASTM specification number and year of issue,

3.1.2 Name of material (cold rolled ultra high strength steel sheet),

3.1.3 Grade (see Table 1),

3.1.4 Specify oiled or not oiled as required,

3.1.5 Dimensions (thickness, width and whether cut lengths or coils),

3.1.6 Coil size (must include inside diameter, outside diameter, and maximum mass),

3.1.7 Quantity,

3.1.8 Application (show part identification and description),

3.1.9 Special Requirements (if required), and

3.1.10 Cast or heat analysis report (request if required).

# 4. Materials and Manufacture

4.1 *Melting Practice*—This sheet shall be produced from aluminum killed steel.

4.2 *Annealing*—The material shall be continuous annealed to austenitic temperatures and water quenched.

# 5. General Requirements

5.1 Materials furnished under this specification shall conform to the applicable requirements of the current edition of Specification A568/A568M unless otherwise provided herein.

# 6. Chemical Composition

6.1 The cast or heat analysis shall conform to the requirements prescribed in Table 1 and Table 2.

6.1.1 Each of the elements listed in Table 2 shall be included in the report of the cast or heat analysis. Where the amount of copper nickel, chromium or molybdenum is less than 0.02 %, the analysis may be reported as <0.02 %. When the amount of vanadium or columbium is less than 0.008 %, the analysis may be reported as <0.008 %.

# 7. Mechanical Properties

7.1 Tension Tests:

7.1.1 *Requirements*—Materials as represented by the test specimen shall conform to the tensile requirements specified in Table 3.

7.1.2 *Number of Tests*—Two tests shall be made from each heat or from each lot of 50 tons [45 000 kg]. When the amount of finished material from a heat or lot is less than 50 tons [45 000 kg], one test shall be made. When material rolled from one heat differs by 0.050 in. [1.27 mm] or more in thickness, one tension test shall be made from the thickest and thinnest material regardless of the weight represented.

7.1.3 Location and Orientation:

7.1.3.1 Tension test specimens shall be taken at a point immediately adjacent to the material to be qualified.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of SubcommitteeA01.19 on Steel Sheet and Strip.

Current edition approved Nov. 1, 2011. Published November 2011. Originally approved in 1997. Last previous edition approved in 2003 as A980–97(2010). DOI: 10.1520/A0980\_A0980M-11.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

# (5) A980/A980M – 11

#### **TABLE 1** Chemical Requirements

Composition - Weight % Heat Analysis

Element	Grade			
	130 [900]	160 [1100]	190 [1300]	220 [1500]
Carbon, max	0.10	0.15	0.23	0.28
Manganese, max	0.60	0.60	0.60	0.60
Phosphorus, max	0.030	0.030	0.030	0.030
Sulfur, max	0.035	0.035	0.035	0.035
Aluminum, min	0.01	0.01	0.01	0.01

#### **TABLE 2 Limits on Unspecified Elements**

Element <sup>A</sup>	Composition Weight % Heat Analysis
Copper	
When specified, min	.20
When not specified, max	.20
Nickel, max	0.20
Chromium, max	0.15
Molybdenum, max	0.06
Vanadium, max	0.008
Columbium, max	0.008

<sup>A</sup> Minimum copper added

#### **TABLE 3 Mechanical Requirements**

	Tensile Strength	
Grade	Min, ksi [MPa]	
130 [900]	130 [900]	
160 [1100]	160 [1100]	
190 [1300]	190 [1300]	
220 [1500]	220 [1500]	

7.1.3.2 Tension test samples shall be taken from the full thickness of the sheet as rolled.

7.1.3.3 Tension test specimens shall be taken from a location approximately halfway between the center of the sheet and the edge of the material as-rolled.

# 7.1.4 Retests:

7.1.4.1 A retest shall be permitted if the results of an original tension specimen are within 2 ksi [15 MPa] of the required tensile strength.

7.1.4.2 A retest shall consist of one random specimen from the same heat or lot as the original specimen.

7.1.4.3 If the results of the retest specimen meet the specified requirements, the cast or test lot shall be accepted.

# 8. Finish and Appearance

8.1 *Surface Finish*—The sheet shall have a matte surface texture.

#### 8.2 Oiling:

8.2.1 Unless otherwise specified, the sheet shall be oiled.

8.2.2 When required, the sheet may be specified to be not oiled (dry).

8.3 *Edges*—The sheet shall have cut edges.

# 9. Certification and Reports

9.1 When required by the purchase order, the producer shall furnish the test results of the cast or heat analysis or the mechanical properties, or both. The report shall include the purchase order number, ASTM designation number and year issue, and cast or lot number correlating the test data with the material represented.

# 10. Keywords

10.1 carbon steel sheet; cold rolled steel sheet; steel sheet; ultra high-strength

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or a 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).