

Designation: A981/A981M - 11 (Reapproved 2016)

Standard Test Method for Evaluating Bond Strength for 0.600-in. [15.24-mm] Diameter Steel Prestressing Strand, Grade 270 [1860], Uncoated, Used in Prestressed Ground Anchors¹

This standard is issued under the fixed designation A981/A981M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method describes procedures to establish the relative bond strength of 0.600-in. [15.24-mm] diameter, Grade 270 [1860] steel prestressing strand in cement grout as used in prestressed ground anchors for the purpose of evaluating the effects of manufacturing practices on bond strength.

1.2 The bond strength values obtained are not intended to be used to design the bond length of ground anchors that depend on field conditions.

1.3 This test method is not intended to be used as a bond test for prestressed concrete applications.

1.4 The values stated in either inch-pound or SI units are to be regarded as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

- A416/A416M Specification for Low-Relaxation, Seven-Wire Steel Strand for Prestressed Concrete
- C150 Specification for Portland Cement
- C511 Specification for Mixing Rooms, Moist Cabinets, Moist Rooms, and Water Storage Tanks Used in the

Testing of Hydraulic Cements and Concretes C1019 Test Method for Sampling and Testing Grout E4 Practices for Force Verification of Testing Machines

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *bond strength*—maximum measured load in a pull test on a 0.600-in. [15.24-mm] diameter steel prestressing strand embedded in cement grout.

3.1.2 *bonded length*—the length of the test strand that is in contact with the cement grout.

4. Apparatus

4.1 *Equipment*—A suitable tensile testing machine or load frame shall be used. The loading system shall be calibrated in accordance with Practices E4. The test system shall have sufficient capacity to prevent yielding of its various components and shall ensure that the applied tensile load remains parallel to the axis of the steel prestressing strand during testing.

4.2 Strand Displacement Measurements—Displacements of the free end of the steel prestressing strand shall be measured with respect to the loaded surface of the test specimen using suitable measurement devices. Dial gages having the smallest division of not more than 0.001 in. [25 μ m] or linear variable differential transformers (LVDTs) with equal or superior accuracy are examples of satisfactory devices.

5. Strand Bond Test Specimen

5.1 *Steel Prestressing Strand*—Strand shall be 0.600-in. [15.24-mm] diameter, Grade 270 [1860] and comply with Specification A416/A416M and shall be cut from standard production coils prior to packaging. The surface of the test samples shall not be wiped or cleaned in order to preserve their original condition. Minimum recommended sample length is 30 in. [750 mm].

5.2 *Test Specimen Fabrication*—The test specimen shall consist of the steel prestressing strand embedded in cement grout and centered inside a steel pipe, 5-in. [125-mm] O.D. with a 0.125-in. [3-mm] thick wall, 18-in. [450-mm] long with

¹ This test method is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.05 on Steel Reinforcement.

Current edition approved Sept. 1, 2016. Published September 2016. Originally approved in 1997. Last previous edition approved in 2011 as A981 – 11. DOI: 10.1520/A0981_A098M-11R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



a 6 by 6 by 0.25 in. [150 by 150 by 6 mm] base plate welded to one end of the steel pipe, or otherwise attached with a leakproof connection. Other mold designs, including reusable molds, shall be permitted, provided that the dimensions and confinement in regard to circumferential stress provided for the grout body are the same. A 0.625-in. [16-mm] diameter hole shall be provided in the base plate to allow the strand to pass through. A 2-in. [50-mm] long debonding tube (Note 1) shall be positioned on the strand above the base plate and the strand shall protrude at least 2 ± 0.5 in. [50 \pm 10 mm] from the top of the grouted steel tube. A typical test specimen is illustrated in Fig. 1.

Note 1—Polyethylene, Styrofoam,³ or similar material are commonly used for this purpose.

5.3 *Test Specimen Preparation*—The untensioned strand sample shall be installed and centered inside the steel pipe as



³ Styrofoam is a registered trademark of The Dow Chemical Company.

FIG. 1 Untensioned Strand Specimen

shown in Fig. 1. A sealing agent shall be applied around the hole in the base plate to prevent leakage of grout from the sample during casting.

5.3.1 The grout shall be made solely from fresh portland cement conforming to Specification C150, Type I with a water/cement ratio of 0.45, by weight. Water shall be potable. The cement shall be added to the water. Mixing of the grout shall continue until the grout is free of lumps and undispersed cement. The grout then shall be poured into the steel tube to completely fill it. Six 2 by 2 by 2 in. [50 by 50 by 50 mm] test cubes shall be cast at the same time from the same batch of grout.

5.4 Test Specimen Conditioning—The test specimen including the grout test cubes, shall be cured according to Specification C511 at a 74 \pm 3°F [23 \pm 1.7°C] temperature and minimum 95 % relative humidity until the grout strength, as determined according to Test Method C1019 on at least two 2 by 2 by 2 in. [50 by 50 by 50 mm] test cubes, has reached a compressive strength of 3500 to 4000 psi [24 to 28 MPa] The seal around the hole in the base plate may be removed once the grout has set.

5.5 The loss in height of the cured test cylinder because of grout bleed or drainage of water, or both, through the interstices of the seven-wire strand shall not be more than 0.5 in. [13 mm]. Test cylinders with a height loss of more than 0.5 in. [13 mm] shall be discarded and new test cylinders prepared using a more thorough mixing of the grout or sealing the interstices of the seven-wire strand, or both, within the 2-in. [50-mm] wide tape bond-breaker zone shown in Fig. 1. However, tests performed successfully on test cylinders shorter than the allowed minimum length, shall be deemed acceptable.

6. Pull Test

6.1 *Pull Test Setup*—With the test specimen supported with its base plate on the table of the testing machine or load frame, the free strand protruding from the base plate shall be gripped by the jaws of the testing machine or load frame with a minimum of 12 in. [300 mm] of free strand in between the base plate and the jaws.

6.1.1 A dial gage or other suitable measuring device shall be positioned to measure the longitudinal displacement at the unloaded end of the test specimen. A suitable test setup is shown in Fig. 2.

6.2 *Pull Test Procedure*—Testing shall not commence until the grout has reached a compressive strength of 3500 psi [24 MPa] but before reaching a strength of 4000 psi [28 MPa].

6.2.1 The pull force shall be applied to the test specimen at a rate of 0.1 in. [2.5 mm] per minute, with a tolerance of ± 25 %, until the displacement at the unloaded end of the strand sample reaches 0.01 in. [0.25 mm] at which point the force shall be recorded.

Note 2—Although not required, it is advisable to use a continuous load/displacement recording device. The shape of the load/displacement curve may provide valuable insight on the bond behavior of the strand sample.

45 A981/A981M – 11 (2016)



7. Report

7.1 Report the following information:

7.1.1 Date of test and report.

7.1.2 Identification of the steel prestressing strand:

7.1.2.1 0.600-in. [15.24-mm] diameter, Grade 270 [1860] strand;

7.1.2.2 Manufacturer of strand;

7.1.2.3 Date of strand manufacture;

7.1.2.4 Reel, reelless pack, or lot number.

7.1.3 Any presence of corrosion on the strand tested shall be reported.

7.1.4 Description of any deviations from the fabrication of the strand bond test specimen and testing procedures specified.

7.1.5 Description of the grout used, including mix design, compressive strength at a time of test (average of a minimum of two cubes), and

7.1.6 Individual load value (bond strength), in pounds [N], for each test specimen at a displacement of 0.01 in. [0.25 mm].

8. Precision and Bias

8.1 No statement is made on the precision or bias of this test method since the test results indicate only whether there is conformance to given criteria and since no generally accepted method for determining precision and bias of this test method is currently available. General guidelines provided herein for the specimens, instrumentation and procedures make the results intractable to calculation of meaningful values by statistical analysis for precision and bias at this time.

9. Keywords

9.1 bond strength test; prestressed ground anchors; steel prestressing strand

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/