



Designation: B888/B888M – 17

Standard Specification for Copper Alloy Strip for Use in Manufacture of Electrical Connectors or Spring Contacts¹

This standard is issued under the fixed designation B888/B888M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification establishes the requirements for copper alloy strip for use in the manufacture of electrical connectors or spring contacts produced from one of the following Copper Alloy UNS Nos.²: C14530, C15100, C15500, C17000, C17200, C17410, C17450, C17460, C17500, C17510, C19002, C19010, C19015, C19025, C19210, C19400, C19500, C19700, C23000, C26000, C40810, C40850, C40860, C42200, C42500, C42520, C42600, C50580, C50780, C51000, C51080, C51100, C51180, C51980, C52100, C52180, C52480, C63800, C64725, C65400, C68800, C70250, C70260, C70265, C70310, C70350, C75200, and C76200.

1.2 The requirements for the other copper alloys such as copper-nickel-tin spinodal, UNS C72650, C72700, and C72900, shall be as prescribed in the current edition of Specification B740.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of Committee B05 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.01 on Plate, Sheet, and Strip.

Current edition approved April 1, 2017. Published April 2017. Originally approved in 1998. Last previous edition approved in 2013 as B888/B888M-13. DOI: 10.1520/B0888_B0888M-17.

² The UNS system for copper and copper alloys (see Practice E527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “c” and a suffix “00.” The suffix can be used to accommodate composition variations of the base alloy.

2. Referenced Documents

2.1 ASTM Standards:³

- B193 Test Method for Resistivity of Electrical Conductor Materials
- B248 Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar
- B248M Specification for General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)
- B601 Classification for Temper Designations for Copper and Copper Alloys—Wrought and Cast
- B740 Specification for Copper-Nickel-Tin Spinodal Alloy Strip
- B820 Test Method for Bend Test for Determining the Formability of Copper and Copper Alloy Strip
- B846 Terminology for Copper and Copper Alloys
- E8/E8M Test Methods for Tension Testing of Metallic Materials
- E54 Test Methods for Chemical Analysis of Special Brasses and Bronzes (Withdrawn 2002)⁴
- E62 Test Methods for Chemical Analysis of Copper and Copper Alloys (Photometric Methods) (Withdrawn 2010)⁴
- E75 Test Methods for Chemical Analysis of Copper-Nickel and Copper-Nickel-Zinc Alloys (Withdrawn 2010)⁴
- E478 Test Methods for Chemical Analysis of Copper Alloys
- E527 Practice for Numbering Metals and Alloys in the Unified Numbering System (UNS)

2.2 ISO Standards:⁵

- ISO 4744 Copper and Copper Alloys—Determination of Chromium Content—Flame Atomic Absorption Spectrometric Method

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard’s Document Summary page on the ASTM website.

⁴ The last approved version of this historical standard is referenced on www.astm.org.

⁵ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

*A Summary of Changes section appears at the end of this standard



ISO 7602 Copper and Copper Alloys—Determination of Tellurium Content

3. Terminology

3.1 *Definitions*—For definition of terms used in this specification, refer to Terminology B846.

4. General Requirements

4.1 For product furnished under this specification in English units, the following sections of Specification B248 must constitute a part of this specification. For product furnished under this specification in the SI units, the following sections of Specification B248M must constitute a part of this specification.

- 4.1.1 Terminology,
- 4.1.2 Materials and Manufacture,
- 4.1.3 Dimensions, Weights, and Permissible Variations,
- 4.1.4 Workmanship, Finish, and Appearance,
- 4.1.5 Sampling,
- 4.1.6 Number of Tests and Retests,
- 4.1.7 Specimen Preparation,
- 4.1.8 Test Methods,
- 4.1.9 Significance of Numerical Limits,
- 4.1.10 Certification,
- 4.1.11 Test Reports, and
- 4.1.12 Packaging and Package Marking.

4.2 In the event of a conflict between this specification and Specification B248 or B248M, the requirements of this specification shall take precedence.

5. Classification

5.1 Product produced to this specification is classified as strip material to be used for spring contact or electrical and electronic connector applications only.

6. Ordering Information

6.1 Contract or purchase orders for product under this specification should include the following information:

- 6.1.1 ASTM designation and year of issue,
- 6.1.2 UNS alloy designation,
- 6.1.3 Dimensions, for example, thickness, width,
- 6.1.4 Quantity, and
- 6.1.5 Temper (Section 8).

6.2 The following options are available under this specification and shall be specified in the contract or purchase order when required:

6.2.1 Type of edge: slit, sheared, sawed, square corners, rounded corners, rounded edges, or full-rounded edges (Section 11),

6.2.2 Width and straightness tolerances, slit-metal tolerances, square-sheared metal tolerances, sawed metal tolerances, straightened or edge-rolled metal tolerances (Section 11),

6.2.3 Identification marking (Section 22),

6.2.4 Certification (Section 20),

6.2.5 Mill test report (Section 21), and

6.2.6 How packaged: coil wound in traverse or pancake style (Section 22).

6.2.6.1 Number of strip lengths per coil,

6.2.6.2 Size and weight of each coil, and

6.2.7 The electrical resistivity or any other physical and electrical properties (See Table X1.1).

7. Materials and Manufacture

7.1 *Material*—The material of manufacture shall be a cast bar, slab, cake, billet, or other form of the composition given in Table 1 for the specified alloy, suitable for processing into the product prescribed in this specification.

7.2 *Manufacture*—The product shall be produced by either hot- or cold-working operation. It shall be finished, unless otherwise specified, by such hot working, cold working, annealing, or heat treatment as may be necessary to meet the properties specified in Table 2.

7.3 *Edges*—The edges shall be slit or rolled edges as specified by the buyer. Slit edges shall be furnished unless otherwise specified or agreed upon between the purchaser and supplier or manufacturer.

8. Chemical Composition

8.1 The materials shall conform to the chemical compositional requirements in Table 1 for the corresponding Copper Alloy UNS Number designation specified in the ordering information.

8.2 These composition limits do not preclude the presence of other elements. Limits for unnamed elements may be established and analysis required by agreement between manufacturer or supplier and purchaser when required.

8.3 Copper, when given as the remainder, is determined as the difference between the sum of results for all elements determined and 100 %.

8.4 Zinc, when given as the remainder, is determined as the difference between the sum of results for all elements determined and 100 %.

8.4.1 For those copper alloys in which zinc is given as the remainder, copper may be determined by difference; however, when so determined, the result shall conform to the limits prescribed in Table 1.

8.5 When a chemical analysis is performed as specified in the ordering information, for the Copper Alloy UNS No. in



TABLE 1 Chemical Requirements

Elements Composition, %

Copper Alloy UNS No.	Copper	Aluminum	Beryllium	Cobalt	Iron	Lead	Magnesium	Manganese	Nickel	Phosphorus	Tin	Zinc	Chromium	Zirconium	Silicon	Silver	Tellurium	Other
C14530	99.90 ^A min	0.001–0.010	0.003–0.023	0.003–0.023 ^B	...
C15100 ^C	99.80 ^D min	0.05–0.15
C15500	99.75 ^D min	0.08–0.13	0.040–0.080	0.027–0.10
C17000 ^E	remainder ^D	0.20 max	1.60–1.85 min	0.20 ^F min	0.20 max
C17200 ^F	remainder ^D	0.20 max	1.80–2.00 min	0.20 ^F min	0.20 max
C17410 ^F	remainder ^D	0.20 max	0.15–0.50 min	0.35–0.6	0.20 max	0.20 max
C17450 ^F	remainder ^D	0.20 max	0.15–0.50 min	...	0.20 max	0.50–1.0	...	0.25 max	0.50 % max	0.20 max
C17460 ^F	remainder ^D	0.20 max	0.15–0.50 min	...	0.20 max	1.0–1.4	...	0.25 max	0.50 % max	0.20 max
C17500 ^F	remainder ^D	0.20 max	0.4–0.7 min	2.4–2.7	0.10 max	0.20 max
C17510 ^F	remainder ^D	0.20 max	0.2–0.6 min	0.3 max	0.10 max	1.4–2.2	0.20 max
C19002 ^F	remainder ^D	0.10 max	0.05	0.01	...	1.4–1.7 ^G	0.05	0.02–0.30	0.04–0.35	...	0.005–0.05	0.20–0.35	0.02–0.50
C19010 ^F	remainder ^D	0.8–1.8	0.01–0.05	0.15–0.35
C19015 ^H	remainder ^D	0.02–0.15	0.50–2.4	0.02–0.20	0.10–0.40
C19025 ^I	remainder ^D	0.10 max	0.8–1.2	0.03–0.07	0.7–1.1	0.20 max
C19210 ^H	remainder	0.05–0.15	0.025–0.04
C19400 ^H	97.0 min	2.1–2.6 max	0.03 max	0.015–0.15	...	0.05–0.20
C19500 ^H	96.0 min	0.02 max	...	0.30–1.3	1.0–2.0 max	0.02 max	0.01–0.35	0.10–1.0	0.20 max
C19700 ^H	remainder	0.05 max	0.30–1.2	0.05 max	0.01–0.20	0.05 max	0.05 max	0.10–0.40	0.20 max	0.20 max
C23000 ^H	84.0–86.0	0.05 max	0.05 max	remainder
C26000 ^I	68.5–71.5	0.05 max	0.07 max	remainder
C40810 ^I	94.5–96.5	0.08–0.12 max	0.05 max	0.11–0.20	0.028–0.04	1.8–2.2	remainder
C40850 ^I	94.5–96.5	0.05–0.20 max	0.05 max	0.05–0.20	0.01–0.20	2.6–4.0	remainder



TABLE 1 Continued

		Elements Composition, %																
Copper Alloy UNS No.	Copper	Alum-inum	Beryll-ium	Cobalt	Iron	Lead	Magnes-ium	Man-ganese	Nickel	Phos-phorus	Tin	Zinc	Chro-mium	Zirc-onium	Silicon	Silver	Tellur-ium	Other
C40860 ^F	94.0-96.0	0.01-0.05	0.05 max	0.05-0.20	0.02-0.04	1.7-2.3	remainder
C42200 ^F	86.0-89.0	0.05 max	0.05 max	0.35 max	0.8-1.4	remainder
C42500 ^F	87.0-90.0	0.05 max	0.05 max	0.35 max	1.5-3.0	remainder
C42520 ^F	88.0-91.0	0.05-0.20	0.05 max	0.05-0.20	0.01-0.20	1.5-3.0	remainder
C42600 ^F	87.0-90.0 ^D	0.05-0.20	0.05 max	0.05-0.20 ^G	0.01-0.20	2.5-4.0	remainder
C50580 ^F	remainder	0.05-0.20	0.05 max	0.05-0.20	0.01-0.35	1.0-1.7	0.30 max
C50780 ^F	remainder	0.05-0.20	0.05 max	0.05-0.20	0.01-0.35	1.7-2.3	0.30 max
C51000 ^F	remainder	0.10 max	0.05 max	0.03-0.35	4.2-5.8	0.30 max
C51080 ^F	remainder	0.05-0.20	0.05 max	0.05-0.20	0.01-0.35	5.8	0.30 max
C51100 ^F	remainder	0.10 max	0.05 max	0.03-0.35	3.5-4.9	0.30 max
C51180 ^F	remainder	0.05-0.20	0.05 max	0.05-0.20	0.01-0.35	3.5-4.9	0.30 max
C51980 ^F	remainder	0.05-0.20	0.05 max	0.05-0.20	0.01-0.35	5.5-7.0	0.30 max
C52100 ^F	remainder	0.10 max	0.05 max	0.03-0.35	7.0-9.0	0.20 max
C52180 ^F	remainder	0.05-0.20	0.05 max	0.05-0.20	0.01-0.35	7.0-9.0	0.30 max
C52480 ^F	remainder	0.05-0.20	0.05 max	0.05-0.20	0.01-0.35	9.0-11.0	0.30 max
C63800 ^F	remainder ^D	2.5-3.1	...	0.25-0.55	0.20 max	0.05 max	...	0.10 max	0.20 max	0.8 max	1.5-2.1
C64725 ^F	95.0 min ^D	0.25 max	0.01	0.20	...	1.3-2.7 ^G	...	0.20-0.8	0.50-1.5	0.09	...	0.20-0.8	0.01 Calcium
C65400 ^F	remainder ^D	0.05 max	1.2-1.9	0.50 max	0.01-0.12	...	2.7-3.4
C68600 ^F	remainder ^D	3.0-3.8 ^J	...	0.25-0.55	0.20 max	0.05 max	21.3-24.1 ^J
C70250 ^F	remainder ^D	0.20 max	0.05 max	0.05-0.30	0.10 max	2.2-4.2 ^G	1.0 max	0.25-1.2
C70260 ^F	remainder ^D	1.0-3.0 ^G	0.01 max	0.7
C70265 ^F	remainder ^D	0.05 max	1.0-3.0 ^G	0.01 max	0.05-0.8	0.30 max	0.20-0.7
C70310 ^F	remainder ^D	0.10	0.05	0.01	...	1.0-4.0 ^G	0.05	1.0	2.0	...	0.005-0.05	0.08-0.50
C70350 ^F	remainder ^D	1.0-2.0	0.20 max	0.05 max	0.04 max	0.20 max	1.0-2.5	1.0 max	0.50-1.2
C75200 ^F	63.0-66.5 ^D	0.25 max	0.05 max	...	0.50 max	16.5-19.5 ^G	remainder



TABLE 1 Continued

Elements Composition, %																		
Copper Alloy UNS No.	Copper	Aluminum	Beryllium	Cobalt	Iron	Lead	Magnesium	Manganese	Nickel	Phosphorus	Tin	Zinc	Chromium	Zirconium	Silicon	Silver	Tellurium	Other
C76200 ^F	57.0-61.0 ^D	0.25 max	0.09 max	...	0.50 max	11.0-13.5 ^G	remainder

^A Includes silver + tin + tellurium + selenium.
^B Tellurium or selenium, or both.
^C Copper + the sum of the named elements shall be 99.9 % min.
^D Copper value includes silver.
^E Copper + the sum of the named elements shall be 99.5 % min.
^F Nickel + cobalt, 0.20 % min; nickel + iron + cobalt, 0.6 % max.
^G Includes cobalt.
^H Copper + the sum of the named elements shall be 99.8 % min.
^I Copper + the sum of the named elements shall be 99.7 % min.
^J Aluminum + zinc = 25.1-27.1.

**TABLE 2 Mechanical Requirements**

Temper Designation		Tensile Strength, ksi		Tensile Strength, MPa		Yield Strength (0.2 % Offset), ksi	Yield Strength (0.2 % Offset), MPa	Elongation, %
Standard	Former	min	max	min	max	min	min	min
Copper Alloy UNS NO. C14530								
H01	¼ hard	35	45	240	310	26	180	7
H02	½ hard	40	50	275	345	33	230	5
H03	¾ hard	44	54	305	370	39	270	3
H04	hard	47	57	325	395	43	295	2
H06	extra hard	50	60	345	415	47	325	1
H08	spring	54	64	370	440	51	350	1
H10	extra spring	58	...	400	...	56	385	...
Copper Alloy UNS NO. C15100								
O61	annealed	37	42	255	290	9	60	35
H01	¼ hard	40	45	275	310	26	180	11
H02	½ hard	43	51	295	350	35	240	4
H03	¾ hard	47	56	325	385	45	310	2
H04	hard	53	62	365	425	51	350	2
H06	extra hard	59	65	405	450	57	395	1
H08	spring	64	71	440	490	62	425	1
Copper Alloy UNS NO. C15500								
O61	annealed	34	43	235	295	15	105	30
H02	½ hard	45	55	310	380	38	260	13
H04	hard	56	64	385	440	50	345	6
H06	extra hard	63	72	435	495	56	385	5
H08	spring	65	73	450	505	60	415	4
H10	extra spring	68	75	470	515	63	435	3
Copper Alloy UNS NO. C17000								
TB00	A	60	78	410	540	30	210	35
TD01	¼ H	75	88	520	610	60	415	15
TD02	½ H	85	100	590	690	75	520	9
TD04	H	100	130	690	900	90	620	2
TF00	AT	150	180	1030	1240	130	900	3
TH01	¼ HT	160	190	1100	1310	135	930	2.5
TH02	½ HT	170	200	1170	1380	145	1000	1
TH04	HT	180	210	1240	1450	155	1070	1
AM	TM00	100	110	690	760	70	480	18
¼ HM	TM01	110	120	760	830	80	550	15
½ HM	TM02	120	135	830	930	95	660	12
HM	TM04	135	150	930	1030	110	760	9
SHM	TM05	150	160	1030	1100	125	860	9
XHM	TM06	155	175	1070	1210	135	930	3
Copper Alloy UNS NO. C17200								
TB00	A	60	78	410	540	30	210	35
TD01	¼ H	75	88	520	610	60	415	20
TD02	½ H	85	100	590	690	75	520	12
TD04	H	100	130	690	900	90	620	2
TF00	AT	165	195	1140	1340	140	970	4
TH01	¼ HT	175	205	1210	1410	150	1030	3
TH02	½ HT	185	215	1280	1480	160	1100	2
TH04	HT	190	220	1310	1520	165	1140	1
AM	TM00	100	110	690	760	70	480	16
¼ HM	TM01	110	120	760	830	80	550	15
½ HM	TM02	120	135	830	930	95	660	12
HM	TM04	135	150	930	1030	110	760	9
SHM	TM05	150	160	1030	1100	125	860	9
XHM	TM06	155	175	1070	1210	135	930	4
XHMS	TM08	175	190	1210	1310	150	1030	3
Copper Alloy UNS NO. C17410								
TH02	½ HT	95	115	665	790	80	550	10
TH04	HT	110	130	760	895	100	690	7
Copper Alloy UNS NO. C17450								
TH02	½ HT	95	115	655	790	80	550	12
Copper Alloy UNS NO. C17460								
TH03	¾ HT	115	135	790	930	95	655	11
TH04	HT	120	140	825	965	105	720	10
Copper Alloy UNS NO. C17500								
TB00	A	35	55	240	380	25	170	20
TD04	H	70	85	480	585	55	380	3
TF00	AT	100	120	690	830	80	550	10
TH04	HT	110	130	760	900	95	655	8
HTR		120	150	830	1030	110	760	1
HTC		75	85	512	590	50	340	8
Copper Alloy UNS NO. C17510								
TB00	A	35	55	240	380	25	170	20
TD04	H	70	85	480	585	55	380	2

TABLE 2 *Continued*

Temper Designation		Tensile Strength, ksi		Tensile Strength, MPa		Yield Strength (0.2 % Offset), ksi	Yield Strength (0.2 % Offset), MPa	Elongation, %
Standard	Former	min	max	min	max	min	min	min
TF00	AT	100	120	690	830	80	550	10
TH04	HT	110	140	760	965	95	655	8
Copper Alloy UNS No. C19002								
TM04	HM	72	87	495	600	65	450	10
TM06	XHM	84	94	580	650	78	540	7
TM08	XHMS	89	101	615	695	82	565	5
TM05	SHM	84	94	580	650	75	515	8
Copper Alloy UNS NO. C19010								
TM03	¾ HM	67	77	460	520	50	340	12
TM04	HM	71	81	490	560	60	410	10
TM06	XHM	75	86	520	590	64	440	8
TM08	SHM	84	...	580	...	74	510	6
H01	¼ hard	52	64	360	430	40	275	8
H02	½ hard	60	70	410	470	54	370	7
H03	¾ hard	67	77	460	520	62	410	5
H04	hard	71	81	490	560	66	435	4
H06	extra hard	75	86	520	590	72	460	3
H08	spring	84	95	580	655	78	520	2
H10	extra spring	95	...	655	...	85	585	1
Copper Alloy UNS NO. C19015								
H020	½ Hard	53	64	365	440	38	260	7
H040	Hard	60	71	415	490	54	370	5
H060	Extra hard	66	75	455	515	64	440	2
TM02	½ HM	70	81	485	485	55	380	10
TM04	HM	64	86	440	595	64	440	8
Copper Alloy UNS NO. C19025								
HR01	¼ hard	49	68	340	470	42	290	15
HR02	½ hard	63	76	435	525	58	400	9
HR04	hard	72	83	495	570	68	470	5
HR06	extra hard	78	89	540	615	74	510	4
HR08	spring	84	95	580	655	81	560	...
HR10	extra spring	91	106	625	730	88	605	...
Copper Alloy UNS NO. 19210								
O61	annealed	27	42	190	290	16	110	30
H01	¼ hard	43	53	300	365	20	135	20
H02	½ hard	47	60	325	410	44	310	5
H03	¾ hard	52	62	355	425	50	345	4
H04	full hard	56	66	385	455	54	355	3
H06	extra hard	60	70	410	480	58	400	2
H08	spring hard	64	74	440	510	62	425	1
H10	extra spring	66	...	455	...	64	440	1
Copper Alloy UNS NO. C19400								
O61	annealed	40	63	275	435	16	110	10
H02	½ hard	53	63	365	435	36	250	6
H04	full hard	60	70	415	485	53	365	3
H06	extra hard	67	73	460	505	64	440	2
H08	spring hard	70	76	485	525	67	460	2
H10	extra spring	73	80	505	550	70	485	1
Copper Alloy UNS NO. C19500								
O61	annealed	50	60	345	415	21	145	22
H01	¼ hard	60	72	415	495	45	310	5
H02	½ hard	68	78	470	540	66	455	3
H03	¾ hard	75	85	515	585	72	495	2
H04	full hard	82	90	565	620	79	545	2
H08	spring	88	97	605	670	85	585	1
Copper Alloy UNS NO. C19700								
O61	annealed	43	53	295	365	16	110	20
H02	½ hard	53	63	365	435	36	250	6
H04	full hard	60	70	415	485	53	365	2
H06	extra hard	67	73	460	505	64	440	2
H08	spring hard	70	76	485	525	67	460	2
H10	extra spring	73	80	505	550	70	485	1
Copper Alloy UNS NO. C23000								
O61	annealed	39	47	270	325	8	55	43
H01	¼ hard	44	54	305	370	23	160	15
H02	½ hard	51	61	350	420	43	295	8
H03	¾ hard	57	67	395	460	51	350	4
H04	hard	63	72	435	495	57	395	4
H06	extra hard	72	80	495	550	65	450	3
H08	spring	78	86	540	595	69	475	3
H10	extra spring	82	90	565	620	73	505	2
Copper Alloy UNS NO. C26000								

**TABLE 2** *Continued*

Temper Designation		Tensile Strength, ksi		Tensile Strength, MPa		Yield Strength (0.2 % Offset), ksi	Yield Strength (0.2 % Offset), MPa	Elongation, %
Standard	Former	min	max	min	max	min	min	min
O61	annealed	45	61	310	420	10	70	40
H01	¼ hard	49	59	340	405	21	145	34
H02	½ hard	57	67	395	460	42	290	19
H03	¾ hard	64	74	440	510	55	380	8
H04	hard	71	81	490	560	67	460	6
H06	extra hard	83	92	570	635	79	545	2
H08	spring	91	100	625	690	82	565	1
H10	extra spring	95	104	655	715	86	595	1
Copper Alloy UNS NO. C40810								
H02	½ hard	57	73	395	505	41	285	20
H04	hard	75	87	515	600	68	470	8
H06	extra hard	88	97	605	670	84	580	6
H08	spring	92	100	635	690	88	605	4
Copper Alloy UNS NO. C40850								
H02	½ hard	57	73	395	505	41	285	20
H04	hard	75	87	515	600	68	470	8
H06	extra hard	88	97	605	670	84	580	6
H08	spring	92	104	635	715	90	620	4
Copper Alloy UNS NO. C40860								
H02	½ hard	56	72	385	495	40	275	20
H04	hard	73	86	505	595	66	455	8
H06	extra hard	86	96	595	660	84	580	6
H08	spring	90	103	620	710	88	605	4
Copper Alloy UNS NO. C42200								
O61	annealed	41	49	285	340	12	85	43
H01	¼ hard	47	57	325	395	21	145	17
H02	½ hard	54	65	370	450	48	330	6
H03	¾ hard	60	72	415	495	58	400	4
H04	hard	67	79	460	545	67	460	3
H06	extra hard	75	85	515	585	72	495	2
H08	spring	82	92	565	635	77	530	2
H10	extra spring	88	...	605	...	82	565	1
Copper Alloy UNS NO. C42500								
O61	annealed	41	47	285	325	13	90	47
H01	¼ hard	49	59	340	405	20	140	24
H02	½ hard	57	69	395	475	51	350	13
H03	¾ hard	62	74	425	510	58	400	10
H04	hard	70	82	485	565	66	455	6
H06	extra hard	76	88	525	605	73	505	5
H08	spring	84	94	580	650	81	560	3
H10	extra spring	92	...	635	...	87	600	...
Copper Alloy UNS NO. C42520								
H02	½ hard	67	82	460	565	60	415	20
H04	hard	80	95	550	655	75	515	8
H06	extra hard	90	105	620	725	85	585	6
H08	spring	95	110	655	760	90	620	4
H10	extra spring	100	115	690	795	95	655	3
Copper Alloy UNS NO. C42600								
H02	½ hard	72	87	495	600	65	450	12
H04	hard	85	100	585	690	80	550	8
H06	extra hard	97	112	670	770	92	635	6
H08	spring	108	123	745	850	103	710	3
H10	extra spring	114	128	785	885	110	760	1
Copper Alloy UNS NO. C50580								
H02	½ hard	56	71	385	490	51	350	15
H04	hard	69	84	475	580	66	455	8
H06	extra hard	74	89	510	615	71	490	6
H08	spring	79	94	545	650	77	530	5
Copper Alloy UNS NO. C50780								
H02	½ hard	58	74	400	510	43	295	15
H04	hard	75	88	515	605	65	450	8
H06	extra hard	83	97	570	670	76	525	5
H08	spring	86	100	595	690	81	560	3
Copper Alloy UNS NO. C51000								
O61	annealed	46	56	315	385	19	130	48
H01	¼ hard	49	61	340	420	22	150	32
H02	½ hard	58	73	400	505	47	325	10
H03	¾ hard	68	79	470	545	61	420	10
H04	hard	76	91	525	625	74	510	9
H06	extra hard	88	103	605	710	85	585	2
H08	spring	95	110	655	760	92	635	1
H10	extra spring	100	114	690	785	98	675	1

TABLE 2 *Continued*

Temper Designation		Tensile Strength, ksi		Tensile Strength, MPa		Yield Strength (0.2 % Offset), ksi	Yield Strength (0.2 % Offset), MPa	Elongation, %
Standard	Former	min	max	min	max	min	min	min
Copper Alloy UNS NO. C51080								
H02	½ hard	87	102	600	705	83	670	8
H04	hard	100	115	690	795	96	660	6
H06	extra hard	105	120	725	825	101	695	4
H08	spring	110	125	760	860	107	740	1
Copper Alloy UNS NO. C51100								
O61	annealed	46	54	315	370	16	110	45
H01	¼ hard	46	58	315	400	20	140	25
H02	½ hard	55	70	380	485	42	290	12
H03	¾ hard	67	82	460	565	64	440	6
H04	hard	72	87	495	600	70	485	2
H06	extra hard	84	99	580	685	81	560	1
H08	spring	91	105	625	725	88	605	1
H10	extra spring	96	109	660	750	92	635	1
Copper Alloy UNS NO. C51180								
H02	½ hard	83	98	570	675	78	540	15
H04	hard	97	112	670	770	93	640	8
H06	extra hard	102	117	705	805	98	675	5
H08	spring	105	120	725	825	103	710	2
Copper Alloy UNS NO. C51980								
H02	½ hard	90	105	620	725	86	595	18
H04	hard	103	118	710	815	99	685	10
H06	extra hard	109	124	750	855	105	725	6
H08	spring	115	130	795	895	112	770	2
Copper Alloy UNS NO. C52100								
O61	annealed	56	65	385	450	23	160	60
H01	¼ hard	63	75	435	515	35	240	40
H02	½ hard	69	84	475	580	51	350	25
H03	¾ hard	80	92	550	635	70	485	18
H04	hard	85	100	585	690	78	540	12
H06	extra hard	97	112	670	770	92	635	10
H08	spring	105	119	725	820	100	690	3
H10	extra spring	110	122	760	840	105	725	2
Copper Alloy UNS NO. C52180								
H02	½ hard	95	110	655	760	90	620	20
H04	hard	107	122	740	840	105	725	10
H06	extra hard	112	128	770	885	108	745	6
H08	spring	120	140	825	965	118	815	2
H10	extra spring	125	145	860	1000	120	825	2
Copper Alloy UNS NO. C52480								
H02	½ hard	102	118	705	815	96	660	15
H04	hard	114	128	785	885	112	770	6
H06	extra hard	120	136	825	940	118	815	4
H08	spring	130	150	895	1035	127	875	2
H10	extra spring	136	156	940	1075	135	930	1
Copper Alloy UNS NO. C63800								
O61	annealed	77	87	530	600	45	310	27
H01	¼ hard	90	102	620	705	75	515	12
H02	½ hard	100	112	690	770	87	600	7
H03	¾ hard	105	117	725	805	93	640	5
H04	hard	114	126	785	870	102	705	3
H06	extra hard	118	130	815	895	106	730	2
H08	spring	123	134	850	925	111	765	2
H10	extra spring	130	119	820	...
Copper Alloy UNS NO. C64725								
TM02	½ HM	85	105	585	725	70	480	7
TM04	HM	95	120	655	825	85	585	5
TM06	XHM	100	120	690	825	95	655	3
TM08	XHMS	105	125	725	860	100	690	1
Copper Alloy UNS NO. C65400								
H01	¼ hard	75	90	515	620	45	310	21
H02	½ hard	86	101	595	695	66	455	11
H03	¾ hard	97	112	670	770	82	565	6
H04	hard	108	120	745	825	94	650	3
H06	extra hard	116	126	800	870	102	705	2
H08	spring	124	133	855	915	112	770	2
H10	extra spring	131	140	905	965	118	815	1
Copper Alloy UNS NO. C68800								
O61	annealed	77	87	530	600	44	305	30
H01	¼ hard	87	101	600	695	63	435	10
H02	½ hard	97	112	670	770	82	565	3
H04	hard	106	120	730	825	95	655	2

TABLE 2 *Continued*

Temper Designation		Tensile Strength, ksi		Tensile Strength, MPa		Yield Strength (0.2 % Offset), ksi	Yield Strength (0.2 % Offset), MPa	Elongation, %
Standard	Former	min	max	min	max	min	min	min
H06	extra hard	113	127	780	875	102	705	2
H08	spring	123	133	850	915	111	765	1
H10	extra spring	130	...	895	...	117	805	1
Copper Alloy UNS NO. C70250								
TM00	AM	90	110	620	760	65	450	10
TM02	½ HM	95	120	655	825	83	585	7
TM03	¾ HM	100	125	690	860	95	655	5
Copper Alloy UNS NO. C70260 and UNS NO. C70265								
TM00	AM	80	100	550	690	65	450	10
TM01	¼ HM	90	105	620	720	75	515	6
TM02	½ HM	90	110	620	760	85	585	4
TM03	¾ HM	105	120	720	825	95	655	2
TM04	HM	110	125	760	860	100	685	1
Copper Alloy UNS NO. C70310								
TM02	½ HM	95	108	655	745	85	585	10
TM04	HM	100	117	690	805	95	655	6
TM08	XHMS	110	...	760	...	105	725	4
Copper Alloy UNS NO. C70350								
TM02	½ HM	100	120	690	830	98	675	5
TM04	HM	112	130	770	900	109	750	4
TM06	XHM	122	140	840	970	117	810	1
TM08	XHMS	133	157	920	1080	127	880	1
TM10	SHMS	142	165	980	1140	136	940	...
Copper Alloy UNS NO. C75200								
O61	annealed	53	63	365	435	18	125	29
H01	¼ hard	58	72	400	495	26	180	14
H02	½ hard	66	80	455	550	48	330	6
H03	¾ hard	74	86	510	595	69	475	4
H04	hard	78	91	540	625	75	515	3
H06	extra hard	86	98	595	675	85	585	3
H08	spring	90	101	620	695	88	605	1
H10	extra spring	96	...	660	...	95	655	1
Copper Alloy UNS NO. C76200								
O61	annealed	57	75	395	515	21	145	32
H01	¼ hard	65	81	450	560	36	250	20
H02	½ hard	75	91	515	625	58	400	6
H03	¾ hard	83	98	570	675	73	505	4
H04	hard	90	105	620	725	82	565	3
H06	extra hard	101	114	695	785	93	640	1
H08	spring	109	122	750	840	101	695	1
H10	extra spring	114	...	785	...	102	705	1

Table 1, copper plus the sum of the named elements shall be as specified in the appropriate table footnote.

9. Temper

9.1 Tempers, as defined in Classification **B601**, available under this specification are as follows:

Temper Designation ⁴	
Standard	Former
O61	annealed
H01	¼ hard
H02	½ hard
H03	¾ hard
H04	hard
H06	extra hard
H08	spring
H10	extra spring
TM00	AM
TM01	¼ HM
TM02	½ HM
TM03	¾ HM
TM04	HM
TM05	SHM
TM06	XHM
TM08	XHMS
TM10	SHMS

⁴ All tempers are subject to product limitations, and the manufacturer should be consulted.

9.2 *Rolled (H) Material*—The standard tempers of rolled products are as designated in **Table 2** with the prefix “H.” Former designations and the standard designations as defined in Classification **B601** are shown.

9.3 *Mill Hardened (TM) Material*—The standard tempers of mill hardened products are as designated in **Table 2** with the prefix “TM.” Former designations and the standard designations as defined in Classification **B601** are shown.

NOTE 1—The properties for product in special or nonstandard tempers are subject to negotiation between the manufacturer and the purchaser.

10. Mechanical Property Requirements

10.1 Product ordered to this specification shall conform to the requirements prescribed in **Table 2** for the alloy and temper specified in the contract or purchase order.

10.1.1 The ultimate tensile strength, 0.2 % offset minimum yield strength, and the minimum elongation properties shall be the basis for acceptance or rejection when tested in accordance with Test Methods **E8/E8M**.

10.1.1.1 Product ordered to this specification in inch-pound units shall be tested in accordance with Test Methods **E8/E8M** and shall conform to tensile strength, 0.2 % offset minimum yield strength, and minimum elongation requirements prescribed in ksi units in **Table 2**.

10.1.1.2 Product ordered to this specification in SI units shall be tested in accordance with Test Methods **E8/E8M** and shall conform to tensile strength, 0.2 % offset minimum yield strength, and minimum elongation requirements prescribed in MPa units in **Table 2**.

11. Dimensions, Mass, and Permissible Variations

11.1 The dimensions and tolerances for product under this specification shall be as prescribed in Specification **B248** or **B248M**, with particular reference to Section 5 and the following tables of those specifications:

11.1.1 *Thickness*—See Paragraph 5.2 and Table 1.

11.1.2 *Width*:

11.1.2.1 *Slit Metal and Slit Metal with Rolled Edges*—See Paragraph 5.3 and Table 4.

11.1.2.2 *Square Sheared Metal*—See Paragraph 5.3 and Table 5.

11.1.2.3 *Sawed Metal*—See Paragraph 5.3 and Table 6.

11.1.3 *Length*:

11.1.3.1 *Specific and Stock Lengths with and without Ends*—See Paragraph 5.4 and Table 7.

11.1.3.2 *Schedule of Lengths (Specific and Stock) with Ends*—See Paragraph 5.4 and Table 8.

11.1.3.3 *Length Tolerances for Squared Sheared Metal*—See Paragraph 5.4 and Table 9.

11.1.3.4 *Length Tolerances for Sawed Metal*—See Paragraph 5.4 and Table 10.

11.1.4 *Straightness*:

11.1.4.1 *Slit Metal or Slit Metal Either Straightened or Edge Rolled*—See Paragraph 5.5 and Table 11.

11.1.4.2 *Square Sheared Metal*—See Paragraph 5.5 and Table 12.

11.1.4.3 *Sawed Metal*—See Paragraph 5.5 and Table 13.

12. Workmanship, Finish, and Appearance

12.1 The product shall be free of defects, well cleaned, and free of dirt. A superficial film of residual light lubricant is normally present and is acceptable unless otherwise specified. The surface finish and appearance of the material shall be as prescribed in Specification **B248** unless otherwise specified.

13. Sampling

13.1 The lot size, portion size, and selection of sample pieces shall be as prescribed in the sampling section of Specification **B248** or **B248M**.

14. Specimen Preparation

14.1 The specimen preparation procedure to be used for the products covered by this specification shall be as prescribed in the specimen preparation section of Specification **B248** or **B248M**.

15. Test Methods

15.1 Test methods used for quality control or production control, or both, for determining conformance to product property requirements are discretionary.

15.1.1 Test methods used to obtain data for the preparation of certification or test report shall be made available to the purchaser on request.

15.2 *Chemical Analysis*—In case of disagreement, the test method to be followed for a specific element and range or maximum concentration shall be as indicated in **Table 3** for alloys listed in **Table 1**.

15.2.1 The determination of calcium, magnesium and zirconium, for which no recognized test method is known to be published, shall be subject to agreement between the manufacturer or supplier and the purchaser.

15.3 *Tensile Strength*—The tensile strength must be determined in accordance with Test Methods **E8/E8M**.

15.4 *Yield Strength*—The yield strength shall be determined in accordance with Test Methods **E8/E8M**.

15.5 *Elongation*—The elongation shall be determined in accordance with Test Methods **E8/E8M**.

16. Number of Tests and Retests

16.1 The number of tests and retests procedure to be used for the products covered by this specification shall be as prescribed in the Number of Tests and Retests section of Specification **B248** or **B248M**.

17. Significance of Numerical Limits

17.1 For significance of numerical limits, refer to Specification **B248** or **B248M**.

18. Inspection

18.1 The manufacturer or supplier shall inspect and make tests necessary to verify that the product furnished conforms to the requirements specified for the product.

19. Rejection and Rehearing

19.1 *Rejection*:

TABLE 3 Chemical Test Methods

Element	Range or max %	Test Method
Aluminum (Al)	0.0-12.0	E54
	2.0-12.0	E478
Chromium (Cr)	0.003-2.0	ISO 4744
Cobalt (Co)	0.5	E75
Copper (Cu)	50-99.99	E478
Iron (Fe)	0.003-1.25	E478
Lead (Pb)	0.002-15.0	E478 Atomic Absorption
Magnesium (Mg)	0.01-2.0	...
Manganese (Mn)	6.0	E62
Nickel (Ni)	50.0	E478
Phosphorus (P)	1.2	E62
Silicon (Si)	5.0	E54
Silver (Ag)	0.01-0.12	E478
Tellurium (Te)	0.003-0.05	ISO 7602 Part I E/F (ISO/TC26 N692)
Tin (Sn)	0.01-1.0	E478 Photometric
	0.5-20.0	E478 Titrimetric
Zinc (Zn)	2-40	E478 Titrimetric
Zirconium (Zr)	0.01-0.30	...

19.1.1 Product that fails to conform to the requirements of the product specification may be rejected.

19.1.2 The rejection shall be reported to the manufacturer or the supplier, promptly and in writing.

19.1.3 In case of disagreement or dissatisfaction with the results of the test upon which rejection was based, the manufacturer or supplier may make claim for a rehearing.

19.2 *Rehearing*—As a result of product rejection, the manufacturer or supplier may make claim for retest to be conducted by the manufacturer or supplier and the purchaser. Samples of the rejected product shall be taken in accordance with the product specification and tested by both parties as directed in the product specification, or alternatively, upon agreement by both parties, an independent laboratory may be selected for the tests using the test methods prescribed in the specification.

20. Certification

20.1 When specified in the purchase order or contract, the purchaser shall be furnished certification that samples representing each lot have been either tested or inspected as directed in this specification and requirements have been met. When specified in the purchase order or contract, a report of the test results shall be furnished.

21. Mill Test Report

21.1 When specified in the purchase order or contract, the manufacturer or supplier shall furnish to the purchaser a manufacturer's test report showing the results of the required tests.

22. Packaging and Package Marking

22.1 *Packaging*—The material shall be separated by size, composition, and temper and prepared for shipment in such

manner as to ensure acceptance by common carrier for transportation and afford protection from normal hazards of transportation.

22.2 *Package Marking*—Each shipping unit shall be legibly marked with the purchase order number, specification number, alloy designation, temper, gross and net weight, and name of supplier.

22.3 Product shall be supplied in coils wound in traverse or pancake style as specified in the purchase order or contract.

22.3.1 Product supplied in coils wound in pancake style shall be with or without interleaf paper as required by the purchaser.

23. Keywords

23.1 coefficient of thermal expansion; density; electrical conductivity; electrical connectors; electrical resistivity; elongation; modulus of elasticity; spring contacts; thermal conductivity; yield strength; UNS No. C14530; UNS No. C15100; UNS No. C15500; UNS No. C17000; UNS No. C17200; UNS No. C17410; UNS No. C17450; UNS No. C17460; UNS No. C17500; UNS No. C17510; UNS No. C19002; UNS No. C19010; UNS No. C19015; UNS No. C19025; UNS No. C19210; UNS No. C19400; UNS No. C19500; UNS No. C19700; UNS No. C23000; UNS No. C26000; UNS No. C40810; UNS No. C40850; UNS No. C40860; UNS No. C42200; UNS No. C42500; UNS No. C42520; UNS No. C42600; UNS No. C50580; UNS No. C50780; UNS No. C51000; UNS No. C51080; UNS No. C51100; UNS No. C51180; UNS No. C51980; UNS No. C52100; UNS No. C52180; UNS No. C52480; UNS No. C63800; UNS No. C64725; UNS No. C65400; UNS No. C68800; UNS No. C70250; UNS No. C70260; UNS No. C70265; UNS No. C70310; UNS No. C70350; UNS No. C72650; UNS No. C72700; UNS No. C72900; UNS No. C75200; UNS No. C76200

APPENDIX

(Nonmandatory Information)

X1. PREFERRED PHYSICAL AND ELECTRICAL PROPERTIES

X1.1 *Physical Properties:*

X1.1.1 Unless specified in the purchase order or contract, the modulus of elasticity, density, electrical conductivity, thermal conductivity, coefficient of thermal expansion, and the electrical resistivity data in **Table X1.1** do not constitute a part of this specification. They will indicate to the purchaser the mechanical and physical properties that may be expected.

X1.1.2 Formability property of material usually determines if a spring material is capable of forming to a given radius. Bend test per Test Method **B820** will provide useful information as to the formability or the ability of copper alloy spring material to resist cracking when formed. This test method may

be used in selecting a spring material that will safely form to the geometry of a given part.

X1.2 *Electrical Properties:*

X1.2.1 The value of 0.15328 $\Omega \cdot \text{g}/\text{m}^2$ at 20°C (68°F) is the international standard for the resistivity of annealed copper equal to 100 % conductivity. The term means that a wire 1 m in length and weighing 1g would have a resistance of 0.15328 Ω . This is equivalent to a resistivity value of 875.20 $\Omega \cdot \text{lb}/\text{mile}^2$, which signifies the resistance of a wire 1 mile in length weighing 1 lb. The electrical resistivity (weight) values in **Table X1.1** are calculated from the corresponding electrical conductivity per Test Method **B193** as follows:



TABLE X1.1 Preferred Physical Properties

Copper Alloy UNS No.	Density		Modulus of Elasticity		Electrical Conductivity	Electrical Resistivity ζ (max) ^A		Thermal Conductivity		Coefficient of Thermal Expansion	
	lbs/in. ³ at 68 °F	g/cm ³ at 20 °C	10 ⁶ psi	GPa	% IACS (min) at 68 °F (20 °C)	Ω -lb/mile ² at 68 °F	Ω -g/m ² at 20 °C	BTU/ft-h °F at 68 °F	W/m-k at 20 °C	in./in./°F × 10 ⁻⁶ from 68–572 °F	m/m °C × 10 ⁻⁶ from 20–300 °C
C14530	0.323	8.94	17	115	94	931.06	0.163 06	210	363	9.8	17.6
C15100	0.323	8.94	17	115	95	921.26	0.161 35	208	360	9.8	17.6
C15500	0.322	8.91	17	115	86	1 017.67	0.178 23	200	346	9.9	17.8
C17000	0.304	8.41	19	131	22 ^B	3 978.18	0.696 73	60	103.8	9.7	17.4
C17200	0.302	8.36	19	131	22 ^B	3 978.18	0.696 73	60	103.8	9.7	17.4
C17410	0.318	8.81	20	137.9	45 ^C	1 944.89	0.340 62	135	233.7	9.8	17.6
C17450	0.318	8.81	20	137.9	45 ^C	1 944.89	0.340 62	128	222	9.8	17.6
C17460	0.318	8.81	20	137.9	50 ^C	1 733.07	0.303 52	128	222	9.8	17.6
C17500	0.319	8.83	20	137.9	45 ^C	1 944.89	0.340 62	120	207.7	9.8	17.6
C17510	0.319	8.83	20	137.9	45 ^C	1 944.89	0.340 62	140	242.3	9.8	17.6
C19002	0.322	8.9	19	130	45	1 944.89	0.340 62	148	256	9.25	16.8
C19010	0.322	8.91	19	130	60	1 458.67	0.255 47	150	260	9.8	17.6
C19015	0.322	8.91	19	130	80	1 094.00	0.191 60	149	258	9.3	16.9
C19025	0.322	8.91	17	115	40	2 188.00	0.383 20	93	161	9.4	16.9
C19210	0.322	8.91	17	115	80	1 094.00	0.191 60	185	320	9.8	17.6
C19400	0.322	8.91	17	115	60	1 458.67	0.255 47	150	260	9.8	17.6
C19500	0.322	8.91	17	115	50	1 750.40	0.306 56	115	199	9.4	16.9
C19700	0.319	8.83	17	115	80	1 094.00	0.191 60	185	320	9.6	17.3
C23000	0.316	8.75	17	115	37	2 365.41	0.414 27	92	159	10.4	18.7
C26000	0.308	8.53	16	110	28	3 125.71	0.547 43	70	121	11.1	20.0
C40810	0.320	8.86	17	115	33	2 652.12	0.464 48	82	142	10.1	18.2
C40850	0.320	8.86	17	115	30	2 917.33	0.510 93	75	130	10.1	18.2
C40860	0.320	8.86	17	115	32	2 735.00	0.479 00	80	138	10.1	18.2
C42200	0.318	8.80	16	110	31	2 823.23	0.494 45	75	130	10.2	18.4
C42500	0.317	8.77	16	110	28	3 125.71	0.547 43	69	119	10.2	18.4
C42520	0.318	8.80	16	110	30	2 917.33	0.510 93	75	130	10.2	18.4
C42600	0.318	8.80	17	115	25	3 500.80	0.613 12	63	113	10.2	18.4
C50580	0.321	8.89	17	115	41	2 134.63	0.372 85	103	178	9.9	17.8
C50780	0.320	8.86	17	115	35	2 500.57	0.437 94	87	151	9.9	17.8
C51000	0.320	8.86	16	110	15	5 834.67	1.021 87	40	69	9.9	17.8
C51080	0.320	8.86	16	110	15	5 834.67	1.021 87	40	69	9.9	17.8
C51100	0.320	8.86	16	110	20	4 376.00	0.766 40	48	83	9.9	17.8
C51180	0.321	8.89	16	110	20	4 376.00	0.766 40	52	90	9.9	17.8
C51980	0.319	8.83	16	110	14	6 251.42	1.094 87	38	66	10.0	18.0
C52100	0.318	8.80	16	110	13	6 732.31	1.179 08	36	62	10.1	18.2
C52180	0.318	8.80	16	110	13	6 732.31	1.179 08	36	62	10.1	18.2
C52480	0.317	8.77	16	110	11	7 683.63	1.393 45	29	50	10.2	18.4
C63800	0.299	8.28	17	115	10	8 752.00	1.532 80	22	38	9.5	17.1
C64725	0.320	8.87	19	130	48	1 823.33	0.319 33	110	194	9.5	17.0
C65400	0.309	8.55	17	115	7	12 502.86	2.189 71	21	36	9.7	17.5
C68800	0.296	8.19	17	115	18	4 862.22	0.851 56	47	81	10.1	18.2
C70250	0.318	8.80	19	130	40	2 188.00	0.383 20	98	170	9.8	17.6
C70260	0.320	8.86	19	130	40	2 188.00	0.383 20	90	156	10.0	18.0
C70310	0.319	8.85	19	130	38	2 303.15	0.403 36	91	157	9.4	17.1
C70265	0.320	8.86	19	130	35	2 500.57	0.437 94	87	151	10.0	18.0
C75200	0.316	8.75	18	125	6	14 586.67	2.554 67	19	33	9.0	16.2
C76200	0.310	8.58	18	125	9	9 724.44	1.703 11	24	42	9.0	16.2

^A The weight resistivity values in the table are calculated from the corresponding electrical conductivity per Test Method B193 as follows:

$R = 1/N(15.328)$, where R = wt. resistivity at 20 °C in ohms · grams per square metre (Ω -g/m²) and N = electrical conductivity in % IACS.

^B 15 % minimum before age hardening, 17 % minimum after mill hardening, and 22 % minimum after age hardened.

^C Mill hardened.

$$R = 1/N (15.328) \Omega \cdot \text{g}/\text{m}^2 = 1/N (875.20) \Omega \cdot \text{lb}/\text{mile}^2 \quad (\text{X1.1})$$

where:

R = wt. resistivity at 20°C in Ohms · grams per square metre
or wt. resistivity at 68°F in Ohms · pounds per square
mile and

N = electrical conductivity in % IACS.

X1.3 Metric Equivalent:

X1.3.1 The SI unit for strength properties now shown is in accordance with the International Systems of Units (SI). The

derived SI unit for force is the Newton (N), which is defined as that force which when applied to a body having a mass of 1 kg gives it an acceleration of 1 m/s² ($N = \text{kg} \times \text{m}/\text{s}^2$). The derived SI unit for pressure or stress is the Newton per square meter (N/m²), which has been named the Pascal (Pa) by the General Conference on Weights and Measures. Since 1 ksi = 6894.757 Pa, the metric equivalents are expressed as megapascal (MPa), which is the same as MN/m² and N/mm².

SUMMARY OF CHANGES

Committee B05 has identified the location of selected changes to this standard since the last issue (B888/B888M-13) that may impact the use of this standard. (Approved April 1, 2017.)

(1) Corrected Be range for alloy C17000.

(2) Added alloy C70350.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>