

Designation: C1014 – 17

# Standard Specification for Spray-Applied Mineral Fiber Thermal and Sound Absorbing Insulation<sup>1</sup>

This standard is issued under the fixed designation C1014; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification covers the composition and the physical properties of spray-applied mineral fiber thermal and sound absorbing insulation.

1.2 These mineral fibers shall be pneumatically conveyed to a spray nozzle where they are mixed with water. These mineral fibers shall have a binder either pre-mixed with the fibers or added at the spray nozzle with the water.

1.3 The spray-applied mineral fiber insulation is intended for use in building constructions at ambient conditions.

1.4 This is a material specification only and is not intended to cover methods of application that are supplied by the manufacturer.

1.5 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.6 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

## 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

- C168 Terminology Relating to Thermal Insulation
- C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus
- C390 Practice for Sampling and Acceptance of Thermal Insulation Lots

- C423 Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method
- C518 Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- C665 Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing
- C1104/C1104M Test Method for Determining the Water Vapor Sorption of Unfaced Mineral Fiber Insulation
- C1114 Test Method for Steady-State Thermal Transmission Properties by Means of the Thin-Heater Apparatus
- C1149 Specification for Self-Supported Spray Applied Cellulosic Thermal Insulation
- C1304 Test Method for Assessing the Odor Emission of Thermal Insulation Materials
- C1338 Test Method for Determining Fungi Resistance of Insulation Materials and Facings
- C1368 Test Method for Determination of Slow Crack Growth Parameters of Advanced Ceramics by Constant Stress-Rate Strength Testing at Ambient Temperature
- E84 Test Method for Surface Burning Characteristics of Building Materials
- E605 Test Methods for Thickness and Density of Sprayed Fire-Resistive Material (SFRM) Applied to Structural Members
- E736 Test Method for Cohesion/Adhesion of Sprayed Fire-Resistive Materials Applied to Structural Members
- E759 Test Method for Effect of Deflection on Sprayed Fire-Resistive Material Applied to Structural Members
- E795 Practices for Mounting Test Specimens During Sound Absorption Tests
- E859 Test Method for Air Erosion of Sprayed Fire-Resistive Materials (SFRMs) Applied to Structural Members

## 3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, see Terminology C168.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *constant mass*—the mass of a sample at equilibrium conditions of 75  $\pm$  5°F (23  $\pm$  5°C) and 50  $\pm$  5% relative humidity that shall not deviate more than 0.5% over a 24-h period.

 $<sup>^{1}\,\</sup>text{This}$  specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.23 on Blanket and Loose Fill Insulation.

Current edition approved March 1, 2017. Published March 2017. Originally approved in 1984. Last previous edition approved in 2013 as C1014 – 08 (2013). DOI: 10.1520/C1014-17.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

3.2.2 *cured*—the state or condition of the finished product after the liquid vehicle has been evaporated to a constant mass.

## 4. Materials and Manufacture

4.1 *Composition*—The basic material shall be fibers made form mineral substances such as rock, slag or glass processed from the molten state into a fibrous form. If necessary, add organic or inorganic substances to the fibers or to the binder, or to both, to enhance properties such as flame retardancy, processing, and adhesive/cohesive properties.

## 5. Physical Properties

5.1 For spray-applied mineral fiber insulation, the properties of density, thermal resistance, and sound absorption will vary with the manufacturer. These values shall be as stated by the manufacturer before sale and shall be tested in accordance with 9.1, 9.3, and 9.10, respectively.

5.1.1 *Test Specimens*—Three specimens shall be tested, unless otherwise agreed upon between purchaser and supplier. These are to be obtained from one representative package of insulation.

5.2 Adhesive/Cohesive (Bond Strength)—All selfsupporting applications of the insulation shall have a minimum adhesive/cohesive strength of five times the weight of the material under the testing plate when tested in accordance with 9.2.

5.3 Substrate Deflection—The insulation shall not spall, crack, or delaminate when the substrate is deflected an equivalent of  $\frac{1}{120}$  th the span when tested in accordance with 9.4.

5.4 Water Vapor Sorption—The insulation shall gain not more than 5 % moisture by weight when tested in accordance with 9.5.

5.5 *Surface Burning Characteristics*—The insulation shall have a maximum flame spread index of 25 and a maximum smoke developed of 50 when tested in accordance with 9.6.

5.6 *Smoldering Combustion*—The insulation shall have a weight loss not greater than 5 %, nor shall there be a flaming ignition when tested in accordance with 9.7.

5.7 *Fungi Resistance*—When tested in accordance with 9.8 the insulation shall have growth no greater than that observed on the white birch tongue depressor comparative material.

5.8 *Corrosion*—The spray-applied mineral fiber shall show no greater corrosion than the comparative plate in contact with the sterile cotton for the particular metal substrate to which classification is desired, when tested in accordance with 9.9.

5.9 *Odor Emission*—A detectable odor of a strong objectionable nature recorded by more than two of the five panel members shall constitute rejection of the material when tested in accordance with 9.11.

5.10 *Air Erosion*—Report the results of the air erosion test described in 9.12.

# 6. Workmanship, Finish, and Appearance

6.1 The spray-applied mineral fiber insulation shall be free of all extraneous foreign material such as metal and paper, which would adversely affect the performance of the insulation. 6.2 The thickness and the appearance of the insulation shall be as agreed upon between the purchaser and the supplier. Surface alterations shall be done only in accordance with the manufacturer's instructions.

## 7. Sampling

7.1 Sampling of the insulation shall be in accordance with Practice C390. Specific provision for sampling shall be agreed upon between the purchaser and the supplier.

#### 8. Specimen Preparation

8.1 All specimens of spray-applied mineral fiber insulation shall be prepared using the manufacturer's recommended spray apparatus and spray techniques. All specimens shall be cured to constant mass before testing. All specimens shall be tested at the maximum design thickness or the applied thickness unless otherwise specified by the specific test method in Section 9.

## 9. Test Methods

9.1 *Density and Thickness*—Density and thickness of each sample tested in accordance with this specification shall be determined in accordance with Test Methods E605.

9.2 Adhesive/Cohesive Strength—The adhesive/cohesive strength of the spray-applied mineral fiber insulation shall be determined in accordance with Test Method E736.

9.3 *Thermal Resistance*—The thermal resistance of the spray-applied mineral fiber insulation shall be determined in accordance with Test Methods C177, C518, C1114, or C1368. The mean temperature shall be 75°F (23°C) and the minimum temperature difference shall be a minimum of 40°F (4°C). Since this product is normally used for walls, the R-value shall be determined at a minimum of 3.5 in. (8.9 cm).

9.3.1 When Test Methods C177, C518, or C1114 are used, the surface irregularities shall be trimmed to provide uniform thickness and surface for good plate contact.

9.4 *Substrate Deflection*—Effects of substrate deflection of the insulation shall be determined in accordance with Test Method E759.

9.5 *Water Vapor Sorption*—Water vapor sorption of the spray-applied mineral fiber insulation shall be determined in accordance with Test Method C1104/C1104M.

9.6 *Surface Burning Characteristics*—The surface burning characteristics shall be determined in accordance with Test Method E84.

9.7 *Smoldering Combustion*—The smoldering combustion shall be determined in accordance with Specification C1149.

9.8 *Fungi Resistance*—The fungi resistance of the insulation shall be determined in accordance with Test Method C1338.

9.9 *Corrosion*—The corrosion of a particular metal substrate by spray-applied mineral fiber shall be determined in accordance with Specification C665.

9.10 *Sound Absorption*—Sound absorption of the insulation shall be determined in accordance with Test Method C423 and material shall be tested at applied thickness on applicable mountings in accordance with Practices E795. The test results

shall be reported as the absorption coefficients at the six test frequencies, and the single number ratings shall be the noise reduction coefficient (NRC). Report thickness, density, and area of test specimen.

9.11 *Odor Emission*—Determine the odor emission in accordance with Test Method C1304.

9.12 *Air Erosion*—Air erosion characteristics shall be determined in accordance with Test Method E859 for material used in exposed applications, such as a plenum. This testing shall not be required for materials which partially or completely fill enclosed or covered spaces such as wall cavities.

## 10. Packaging and Package Marking

10.1 Material shall be delivered to the site in the approved manufacturer's original and unopened packing, bearing labels showing the type of material, brand name, labels as required, and the manufacturer's name and address.

## 11. Delivery and Storage

11.1 Material shall be stored under cover in a dry and clean location. Delivered materials that have been exposed to water before use or are otherwise not suitable for insulation shall be removed from the job site and replaced with acceptable materials.

## 12. Installation

12.1 Sprayed thermal insulation material shall be applied in strict conformance with the manufacturer's written instructions, and in conformance with all applicable codes.

12.2 Material shall be applied within the temperature limitation in accordance with manufacturer's written instructions.

#### 13. Keywords

13.1 mineral fiber insulation; sound absorbing; sprayapplied; thermal

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/