



Standard Test Method for Determination of Wood Fiber in Asbestos Cement¹

This standard is issued under the fixed designation C1096/C1096M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

^{ε1} NOTE—Units information was editorially corrected in January 2012.

1. Scope

1.1 This test method covers the determination of the cellulose content of asbestos-cement products. Refer to **Note 1** and **Note 2**.

1.2 Before this test method can be used for the determination of other organic substances in asbestos-cement, it must be ascertained that accurate results can be obtained by correlation trials with known concentrations of the organic substances in question present in samples of asbestos-cement.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 **Warning**—Breathing of asbestos dust is hazardous. Asbestos and asbestos products present demonstrated health risks for users and for those with whom they come into contact. In addition to other precautions, when working with asbestos-cement products, minimize the dust that results. For information on the safe use of chrysotile asbestos, refer to “Safe Use of Chrysotile Asbestos: A Manual on Preventive and Control Measures.”²

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. See 1.4 for a specific safety warning.*

¹ This test method is under the jurisdiction of ASTM Committee C17 on Fiber-Reinforced Cement Products and is the direct responsibility of Subcommittee C17.03 on Asbestos - Cement Sheet Products and Accessories.

Current edition approved Nov. 1, 2011. Published January 2012. Originally approved in 1988. Last previous edition approved in 2007 as C1096 – 07. DOI: 10.1520/C1096_C1096M-07R11E01.

² Available from The Asbestos Institute, http://www.chrysotile.com/en/sr_use/manual.htm.

2. Referenced Documents

2.1 ASTM Standards:³

C114 Test Methods for Chemical Analysis of Hydraulic Cement

D1193 Specification for Reagent Water

E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

2.2 ACS Standard:

Reagent Chemicals, American Chemical Society Specifications⁴

3. Significance and Use

3.1 The determination of wood fiber in asbestos-cement products is necessary because such fibers may be added when multi-wall paper bags containing the asbestos are included in the batch formulations, or cellulose may be added as a processing aid during the manufacture of the products.

3.2 Although moderate concentrations of wood fiber usually have a negligible effect on product durability and performance, higher concentrations can have deleterious effects on products exposed to moisture and thermal shocks.

4. Interferences

4.1 The presence of organic compounds such as surface-active processing aids and water-repellent substances that would produce CO₂ during the digestion steps of the procedure would probably affect results. Refer to **Note 1**.

4.2 The presence of organic pigments and organic polymeric fibers other than cellulose could also interfere and impair accuracy (**Note 2**).

³ For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

⁴ Available from American Chemical Society, 1155 16th St., NW, Washington, DC.

5. Apparatus

5.1 *Sieve, a 149 μm (No. 100), sieve conforming to Specification E11.*

5.2 *Drying oven, ventilated, capable of maintaining 100 to 105°C [212 to 220°F].*

5.3 Apparatus for determination of total carbon by direct combustion. The several types of commercially available apparatus are generally suitable. A typical combustion train may include the following sequence of components:

- 5.3.1 Source of oxygen under pressure,
- 5.3.2 Pressure reducing valve,
- 5.3.3 Rubber tubing,
- 5.3.4 Scrubber for removing traces of carbon dioxide and moisture in the oxygen,
- 5.3.5 Manometer,
- 5.3.6 Combustion tube,
- 5.3.7 Electric furnace,
- 5.3.8 Filter packed with absorbent cotton for the removal of solid particles,
- 5.3.9 U-tube containing anhydrous $\text{Mg}(\text{ClO}_4)_2$,
- 5.3.10 Absorbing bulb containing 20 to 30 mesh inert base impregnated with NaOH absorbing the CC , and
- 5.3.11 Bottle containing H_2SO_4 (sp. gr 1.84) to protect the discharge end.

6. Reagents

6.1 Type III Reagent water conforming to Specification D1193.

6.2 *Hydrochloric Acid*—Dilute one part of concentrated hydrochloric acid (HCl , sp gr 1.19 conforming to the ACS specifications) with 17 parts of reagent water.

6.3 *Chromic Acid*—For each digestion dissolve 30 g of chromium trioxide crystals conforming to the ACS specifications (see 2.2) with 60 cm^3 of reagent water.

7. Hazards

7.1 **Warning**—see 1.4.

8. Sampling, Test Specimens, and Test Units

8.1 For each replicate analysis desired take sufficient sample to yield two specimens each with a mass of 0.15 g per unit percentage of wood fiber expected in the product under analysis. If no estimate of the wood fiber concentration is available take a 3-g sample. If the inorganic carbonate content is known to yield 1 % CO_2 or more when digested, a 1-g sample will suffice.

8.2 Grind the sample to entirely pass the 149 μm (No. 100) sieve (see 1.4).

8.3 Dry the sample to constant weight in the oven at 100 to 105°C [212 to 220°F] and cool to room temperature in a desiccator.

8.4 Weigh out two specimens to the nearest 0.001 g.

9. Procedure

9.1 Transfer one specimen to the digestion flask of the apparatus and connect this to the carbon dioxide absorption system.

9.2 Determine the mass of the carbon dioxide absorption tube.

9.3 Pour the chromic acid into the addition funnel.

9.4 Apply vacuum to the absorption system and introduce the chromic acid slowly.

9.5 When the acid is completely added, rinse the chromic acid from the funnel with small amounts of reagent water.

9.6 Slowly heat the digestion flask to boiling and maintain boiling for 30 min.

9.7 Obtain the total mass of carbon dioxide evolved by reweighing the carbon dioxide absorption tube and subtracting the initial mass determined in 9.2.

9.8 Determine the evolved carbon dioxide of inorganic origin (present as carbonates) by repeating steps 9.1 – 9.7 using the hydrochloric acid with the second specimen.

NOTE 1—Asbestos-cement products may include surface-active processing aids and water-repellent substances that would produce carbon dioxide during the chromic acid digestion step of this test method. Such substances are usually soluble in chloroform. In case of dispute, the chloroform-soluble organic substance shall be determined as described in Sections 69 to 72 of Test Methods C114. A 40.0-g sample of the pulverized, oven-dried material shall be used for this correction procedure. Water-repellent substances contain a higher percentage of carbon than cellulose. To correct for this, 1.8 times the percentage of chloroform-soluble organic substance, so determined, shall be subtracted from the calculated percentage of wood fiber.

NOTE 2—This test method does not provide a correction for organic pigments or polymeric fibers that decompose during chromic acid digestion and which could produce carbon dioxide and thereby interfere with the results obtained by this test method.

10. Calculation

10.1 Calculate the carbon dioxide evolved from wood as the difference between the total carbon dioxide evolved as obtained in 9.7, and the carbon dioxide evolved from inorganic carbonates as obtained in 9.8.

10.2 Calculate the carbon that corresponds to the carbon dioxide evolved from wood as obtained in 10.1 by multiplying by the ratio of carbon to carbon dioxide = 12/44.

10.3 Calculate the concentration of wood on the as-received basis by dividing the percentage carbon evolved as obtained in 10.2 by the percent carbon in the wood. If that value is not known, assume the nominal value of 45.1 % carbon.

10.4 Calculate the concentration of wood present in the dry furnish (solid ingredients of the asbestos-cement) by dividing the concentration of the wood on the as-received basis as obtained in 10.3 by

$$(100 - A - B) \% \quad (1)$$

where:

A = Percent CO_2 originating from the hydration reaction (carbonation) of the cement and calculated from the results obtained with a blank sample prepared similarly and containing no wood. Alternatively, use the arbitrary value of 5.6 %.

B = Percent CO_2 of inorganic origin obtained in 9.8.

10.5 Sample Calculation:

10.5.1 For the case where the following analytical results were obtained:

10.5.1.1 $W_a = 2.0602$ g mass of specimen digested in the chromic acid.

10.5.1.2 $W_1 = 249.0113$ g mass of absorption tube before chromic acid digestion.

10.5.1.3 $W_2 = 249.3499$ g mass of absorption tube after chromic acid digestion.

10.5.1.4 $W_b = 1.9398$ g mass of specimen digested in the hydrochloric acid.

10.5.1.5 $W_3 = 249.0236$ g mass of absorption tube before hydrochloric acid digestion.

10.5.1.6 $W_4 = 249.0643$ g mass of absorption tube after hydrochloric acid digestion.

10.5.1.7 Carbon content of wood assumed to be 45.1 %.

10.5.1.8 Carbon dioxide originating from hydration of cement; 5.6 % assumed. Total carbon dioxide evolved $W_2 - W_1 = 249.3499 \text{ g} - 249.0113 \text{ g} = 0.3386 \text{ g}$ ($W_2 - W_1$)/ $W_a = 0.3386/2.0602 = 0.165 = 16.5 \%$ CO_2 .

10.5.2 The carbon dioxide evolved from wood is:

10.5.2.1 Carbon dioxide evolved from inorganic carbonates = $W_a - W_3 = 249.0643 \text{ g} - 249.0236 \text{ g} = 0.0407 \text{ g}$ ($W_4 - W_3$)/ $W_b = 0.0407/1.9398 = 0.021 = 2.1 \%$ CO_2 .

10.5.2.2 Net value of carbon dioxide evolved from wood = $16.5 - 2.1 = 14.4 \%$ CO_2 .

10.5.2.3 Carbon dioxide evolved from the inorganic carbonates (from 10.5.1.5 and 10.5.1.6)

= $249.0643 - 249.0236 = 0.0407 \text{ g}$.

10.5.2.4 Percentage carbon dioxide evolved from inorganic carbonates (from 10.5.1.4) = $0.0407 \times 100/1.9398 = 2.1 \%$.

10.5.2.5 Carbon dioxide evolved from wood

= $16.5 - 2.1 = 14.4 \%$.

10.5.3 The carbon that corresponds to the carbon dioxide evolved from wood (from 10.5.2.5)

= $14.4 \% \times 12/44 = 3.9 \%$.

10.5.4 The concentration of wood on the as-received basis (from 10.5.1.7 and 10.5.3) = $3.9 \% \times 100/45.1 = 8.7 \%$ (where 45.1 denotes C_{std} nominal).

10.5.5 The concentration of wood present in the dry furnish (from 10.5.4) = $8.7/(100 - A - B) \%$,

where:

A = 5.6 % (from 10.5.1.8), and

B = 2.1 % (from 10.5.2.4).

Therefore, the nominal concentration of wood present in the dry furnish = $8.7 \times 100/(100 - 5.6 - 2.1) \% = 9.5 \%$.

11. Precision and Bias

11.1 *Precision*—The intra-laboratory single apparatus, operator and specimen repeatability of the percent of wood fiber in the dry furnish determined is as follows:

Mean, % = 9.6 %,
Standard Deviation, % = 0.082 %,
Relative standard deviation, % = 0.85 %.

11.2 *Bias*—Results obtained average 4.2 % lower than the true value of the wood fiber concentration in the dry furnish.

12. Keywords

12.1 asbestos; asbestos-cement; cellulose; cellulose fiber content; determination; wood; wood fiber content

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/