

# Standard Specification for Nuclear-Grade Hafnium Oxide Powder<sup>1</sup>

This standard is issued under the fixed designation C1098; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification defines the physical and chemical requirements for hafnium oxide powder intended for fabrication into shapes for use in a nuclear reactor core.

1.2 The material described herein shall be particulate in nature.

1.3 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

#### 2. Referenced Documents

- 2.1 ASTM Standards:<sup>2</sup>
- C117 Test Method for Materials Finer than 75-µm (No. 200) Sieve in Mineral Aggregates by Washing
- C371 Test Method for Wire-Cloth Sieve Analysis of Nonplastic Ceramic Powders
- C859 Terminology Relating to Nuclear Materials
- E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves
- E105 Practice for Probability Sampling of Materials
- 2.2 ANSI/ASME Standard:
- NQA-1 ASME Quality Assurance Program Requirements for Nuclear Facility Applications<sup>3</sup>
- 2.3 U.S. Government Standard:
- Code of Federal Regulations, Title 10, Part 50, Energy (10 CFR 50), Domestic Licensing of Production and Utilization Facilities<sup>4</sup>

#### 3. Terminology

3.1 Terms shall be defined in accordance with Terminology C859 except for the following:

3.2 buyer-the organization issuing the purchase order.

3.3 *hafnium oxide powder*—hafnium oxide that contains no hard aggregates larger than 20 mesh (840  $\mu$ m).

3.4 *phase transformation*—the rearrangement of the atomic ordering of a crystalline lattice as material is cycled through a critical transformation or inversion temperature; the change from one crystalline phase to another may be accompanied by a volume change that could lead to cracks or defects in products fabricated from such materials.<sup>5,6</sup>

3.5 *powder lot*—a specified quantity of hafnium oxide powder (with stabilizing additive, if applicable) blended together such that samples taken in accordance with the procedures of Section 8 can be considered as representative of the entire quantity.

3.6 seller-the hafnium oxide powder processor.

3.7 *stabilizing additive*—material which, when added in sufficient concentration to the subject material exhibiting the phase transformation, produces a stabilized crystalline phase that does not undergo a transformation at any temperature within the expected fabrication or usage regime of the manufactured product; the potentially deleterious volume change is therefore avoided.

## 4. Ordering Information

4.1 The buyer shall specify the following information on the order:

4.1.1 Quantity (weight of delivered product).

4.1.2 Nominal particle size, particle size range, and applicable tolerances. Test Method C371 and Test Method C117 and Specification E11 may be applied for particles larger than 37  $\mu$ m. For particle sizes less than 37  $\mu$ m, the particle size distribution will be determined using a method agreed upon between the buyer and the seller.

4.1.3 *Stabilizing Additive*—The amount and types of stabilizing additives (if any, including limits).

4.1.4 Lot size.

<sup>&</sup>lt;sup>1</sup>This specification is under the jurisdiction of ASTM Committee C26 on Nuclear Fuel Cycle and is the direct responsibility of Subcommittee C26.03 on Neutron Absorber Materials Specifications.

Current edition approved Jan. 1, 2015. Published January 2015. Originally approved in 1988. Last previous edition approved in 2008 as C1098 – 08. DOI: 10.1520/C1098-08R15.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

<sup>&</sup>lt;sup>3</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

<sup>&</sup>lt;sup>4</sup> Available from U.S. Government Printing Office Superintendent of Documents, 732 N. Capitol St., NW, Mail Stop: SDE, Washington, DC 20401, http:// www.access.gpo.gov.

<sup>&</sup>lt;sup>5</sup> Curtis, C. E., Doney, L. M., and Johnson, J. R., "Some Properties of Hafnium Oxide, Hafnium Silicate, Calcium Hafnate, and Hafnium Carbide," *Journal of American Ceramic Society*, Vol 37, 1954, pp. 458–465.

<sup>&</sup>lt;sup>6</sup> Brown, L. M., and Mazdiyasni, K. S., "Characterization of Alkoxy-Derived Yttria-Stabilized Hafnia," *Journal of American Ceramic Society*, Vol 53, 1970, pp. 590–594.

4.1.5 Sampling requirements.

## 5. Chemical Composition

5.1 A stabilizing additive may be utilized with the hafnium oxide. The recommended stabilizing additive is yttrium oxide  $(Y_2O_3)$ . The typical concentration range is 7 to 10 weight %  $Y_2O_3$  in the finished product. References to other stabilizing additives (such as calcium oxide (CaO) and magnesium oxide (MgO)) may be found in the literature and may be used if agreed upon between the buyer and the seller. However, it is cautioned that the buyer should be aware of potential destabilization during thermal cycling when MgO or CaO is used.

5.2 Use analytical chemistry methods as agreed upon between the buyer and the seller.

5.3 *Impurity Concentration*—The impurity concentration, excluding zirconia and the stabilizing additives, shall not exceed 0.5 weight %. Individual element limits are specified in Table 1. The buyer may, in addition, specify the limits for elements not listed in Table 1.

5.4 The zirconium concentration shall not exceed 4.5 weight % on the basis of Zr/(Zr + Hf).

## 6. Physical Requirements

6.1 The nominal particle size, particle size range, and applicable tolerances shall be specified on the purchase order.

## 7. Cleanliness

7.1 The powder shall be handled in a manner to avoid contamination by foreign matter such as dust, cleaning agents and organics, and materials such as plastics and paper used in packaging. Cleaning solutions, if used, shall be free of halides and nonvolatile additives and shall be removed from the powder prior to sampling and packaging.

## 8. Sampling

8.1 Sampling plans to meet acceptance criteria and inspection and measurement procedures that describe the method of compliance with this specification shall be approved by the buyer. The degree of sampling where not specified in this specification varies with the application and for this reason should be specified on the purchase order. Practice E105 is referenced as a guide.

TABLE 1 Impur	ity Concentration	Limits
---------------	-------------------	--------

Element	Maximum Concentration Limit, (μg/g Powder)
В	400
Gd	200
Gd + Sm + Eu + Dy	500
Со	100
Si	2000
F	30
F + Cl + Br + I	100
Th	400

8.2 Sufficient samples shall be taken, as needed, for quality verification tests, acceptance tests, referee tests and archive samples.

8.3 Archive samples shall be retained and disposed of in accordance with the buyer's instructions.

## 9. Inspection and Certification

9.1 The seller shall inspect the material covered by this specification and shall furnish the buyer with certificates of tests showing the results of testing and inspection performed on each powder lot.

9.2 The seller shall certify that each powder lot is in compliance with the provisions of this specification.

#### 10. Rejection and Rehearing

10.1 Unless the buyer and seller agree otherwise, rejection and acceptance shall be on a lot basis.

10.2 Powder lots that fail to conform to the requirements of the specification may be rejected by the buyer. The seller may petition the buyer to waive selected requirements for identified out-of-specification lots. Decision to grant such waiver belongs to the buyer. The seller may also apply any remedy to bring rejected lots into specification providing the seller can demonstrate to the buyer that such remedy does not impair the function or preclude the certification of the rejected material.

10.3 In the event of disagreement over the results of analysis, samples shall be submitted to a mutually selected referee for resolution.

## 11. Packaging, and Package Marking

11.1 The powder shall be packaged in sealed containers for shipment from the seller to the buyer. The seller will be responsible for using a shipping container that assures cleanliness, minimizes moisture pickup, provides adequate protection against damage during transportation, and ensures reasonable ease of unpackaging.

11.2 Each container shall be clearly marked with the following:

11.2.1 Hafnium oxide powder plus stabilizing additive, if applicable,

11.2.2 Purchase order number,

11.2.3 Purchase order specification,

11.2.4 Gross, net, and tare weight,

11.2.5 Lot number, and


11.2.6 Name of seller.

## 12. Quality Assurance

12.1 Quality assurance requirements shall be specified in the purchase order. Code of Federal Regulations Title 10, Part 50, Appendix B and ASME NQA-1 are referenced as guides.

## 13. Keywords

13.1 CaO; hafnium oxide; MgO; powder; stabilizing additive;  $Y_2O_3$ 



ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/