



# Standard Specification for Glass Mat Gypsum Substrate for Use as Sheathing<sup>1</sup>

This standard is issued under the fixed designation C1177/C1177M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification covers glass mat gypsum substrate, which is designed to be used as an exterior substrate for a weather barrier.

1.2 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.3 The text of this standard references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of the standard.

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**C11 Terminology Relating to Gypsum and Related Building Materials and Systems**

**C22 Specification for Gypsum**

**C473 Test Methods for Physical Testing of Gypsum Panel Products**

**C645 Specification for Nonstructural Steel Framing Members**

**C1264 Specification for Sampling, Inspection, Rejection, Certification, Packaging, Marking, Shipping, Handling, and Storage of Gypsum Panel Products**

**E119 Test Methods for Fire Tests of Building Construction and Materials**

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.01 on Specifications and Test Methods for Gypsum Products.

Current edition approved Oct. 1, 2013. Published October 2013. Originally approved in 1991. Last previous edition approved in 2008 as C1177/C1177M–08. DOI: 10.1520/C1177\_C1177M-13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## 3. Terminology

3.1 Definitions shall be in accordance with Terminology **C11**.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *glass mat, n*—a mat of glass fibers with or without a binder.

3.2.2 *edge, n*—the bound edge as manufactured.

3.2.3 *weather barrier, n*—a material that prevents the passage of rain, sleet and snow.

## 4. Materials and Manufacture

4.1 *Glass Mat Gypsum Substrate* shall consist of a noncombustible water-resistant core, essentially gypsum complying with Specification **C22**, surfaced with glass mat partially, or completely embedded in the core.

4.2 *Glass Mat Gypsum Substrate, type X (special fire-resistant)* designates glass mat gypsum substrate complying with this specification that provide not less than 1-h fire resistance rating for substrate  $\frac{5}{8}$  in. [15.9 mm] thick or  $\frac{3}{4}$ -h fire resistance rating for substrate  $\frac{1}{2}$  in. [12.7 mm] thick, applied parallel with and on each side of load bearing 2 by 4 wood studs spaced 16 in. [406 mm] on center with 6d coated nails, 1  $\frac{7}{8}$  in. [48 mm] long, 0.0915 in. [2.3 mm] diameter shank,  $\frac{1}{4}$  in. [6.4 mm] diameter heads, spaced 7 in. [178 mm] on center with glass mat gypsum substrate joints staggered 16 in. [406 mm] on each side of the partition and tested in accordance with Test Methods **E119**.

NOTE 1—Consult manufacturers for independent test data on assembly details and fire resistance ratings for other types of construction. See fire test reports or listings from recognized fire testing laboratories for assembly particulars, materials, and ratings.

## 5. Physical Properties

5.1 Specimens shall be taken from the samples obtained in accordance with Specification **C1264**.

5.2 Specimens shall be tested in accordance with Methods **C473**.

5.2.1 *Flexural Strength*—The specimens shall be tested face up and face down. The average breaking load shall not be less than the following:



## Method B

Thickness, in. [mm]	Load, lbf [N] Bearing edges perpendicular to the substrate edge	Load, lbf [N] Bearing edges parallel to the substrate edge
¼ [6.4]	50 [222]	40 [178]
⅞ [11.1]	88 [394]	70 [314]
½ [12.7]	100 [445]	80 [356]
⅝ [15.9]	140 [623]	100 [445]

5.2.2 *Humidified Deflection*—Specimens shall have an average deflection of not more than the following:

Thickness, in. [mm]	Humidified deflection, eighths of an in. [mm]
¼ [6.4]	not required
⅞ [11.1]	3 [9]
½ [12.7]	2 [6]
⅝ [15.9]	1 [3]

5.2.3 *Core, End and Edge Hardness*—Specimens shall have an average hardness of not less than 15 lbf [67 N] when tested in accordance with Method B:

5.2.4 *Nail Pull Resistance*—Specimens shall have an average nail pull resistance of not less than the following when tested in accordance with Method B:

Thickness, in. [mm]	Nail pull resistance, lbf [N]
¼ [6.4]	40 [178]
⅞ [11.1]	70 [314]
½ [12.7]	80 [356]
⅝ [15.9]	90 [400]

5.2.5 *Water Resistance*—The three specimens selected shall have an average water absorption of not more than 10 weight % after a 2-h immersion.

## 6. Dimensions and Tolerances

6.1 Specimens shall be taken from the samples obtained in accordance with Specification C1264.

6.2 *Thickness, width, length and end squareness* shall be determined in accordance with Test Methods C473.

6.2.1 *Thickness*—The nominal thickness shall be ¼, ⅞, ½, or ⅝ in. [6.4, 11.1, 12.7 or 15.9 mm], with tolerances in the nominal thickness of ± ⅓ in. [± 0.8 mm], and with local variations of ± ⅓ in. [± 1.6 mm] from the nominal thickness.

6.2.2 *Width*—The nominal width shall be up to 48 in. [1220 mm], with tolerance of ⅛ in. [3 mm] under the specified width.

6.2.3 *Length*—The tolerance in length shall be ± ¼ in. [± 6 mm]

6.2.4 *End Squareness*—Corners shall be square with a tolerance of ± ⅛ in. [± 3 mm] in the full width of the substrate.

6.3 *Edges and Ends*—The edges and ends shall be straight and either square, beveled, featured, tapered, or featured and tapered.

## 7. Finish and Appearance

7.1 Glass mat gypsum substrate shall be free of any cracks and imperfections that would render it unfit for its designed use.

## 8. Sampling, Inspection, Rejection, Certification, Packaging, Marking, Shipping, Handling, and Storage

8.1 Shall be in accordance with Specification C1264.

## 9. Keywords

9.1 core; exterior substrate; fire-resistant classification; flexural strength; glass mat; glass mat gypsum substrate; gypsum; hardness; humidified deflection; nail pull resistance; noncombustible; sheathing; substrate; type X; water resistance; weather barrier

## APPENDIX

### (Nonmandatory Information)

This Appendix gives general information and also suggestions for inclusions to be made elsewhere by the specifier. They are not part of this specification.

The definitions of type X as given in 4.2 and the alternate definition given in this appendix, are intended only as a test to define glass mat gypsum substrate for use as sheathing as meeting the requirements of type X. These tests do not indicate a preferred application nor do they limit the use of the product in other fire related assemblies.

All gypsum panel products for which type X is defined, except gypsum lath and gypsum shaftliner board, use the same test for type X products, therefore the type X designation indicates a consistent level of fire resistance.

### X1. ALTERNATE DEFINITION FOR TYPE X

X1.1 Glass mat gypsum substrate, type X (special fire-resistant) designates glass mat gypsum substrate providing a greater fire resistance than regular glass mat gypsum substrate of the same thickness. Type X (special fire-resistant) glass mat gypsum substrate, when tested in accordance with Test Methods E119, shall provide the following minimum fire resistance ratings for the assemblies described:

X1.1.1 One hour for a ⅝ in. [15.9 mm] thickness applied to a partition in a single layer application on each side of 3⅝ in. [92 mm] deep non-loadbearing galvanized steel studs complying with Specification C645 spaced 24 in. [610 mm] on center. The ⅝ in. [15.9 mm] thick glass mat gypsum substrate 48 in. [1220 mm] wide shall be attached using 1 in. [25 mm] long drywall screws spaced 8 in. [203 mm] on center along the



edges and ends, and 12 in. [305 mm] along intermediate studs. All joints shall be oriented parallel to and located over studs and staggered on opposite sides of the assembly; and

X1.1.2 Two hours for a ½ in. [12.7 mm] thickness applied to a partition in a double layer application on each side of 2½ in. [64 mm] deep non-loadbearing galvanized steel studs complying with Specification **C645** spaced 24 in. [610 mm] on center. The base layer 48 in. [1220 mm] wide shall be attached using 1 in. [25 mm] long drywall screws spaced 12 in. [305

mm] on center along substrate edges, ends and along intermediate studs. Joints shall be oriented parallel to and located over studs and staggered on opposite sides of the assembly. The face layer 48 in. [1220 mm] wide shall be attached using 1⅝ in. [41 mm] long drywall screws spaced 12 in. [305 mm] along substrate edges, ends and along intermediate studs. Joints shall be oriented parallel to and located over studs, offset 24 in. [610 mm] from the base layer joints, and staggered on opposite sides of the assembly.

## **SUMMARY OF CHANGES**

Committee C11 has identified the location of selected changes to this specification since the last issue, C1177/C1177M – 08, that may impact the use of this specification. (Approved Oct. 1, 2013)

(1) Revised **2.1** and **4.1**.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*