

Designation: C1305/C1305M - 16

Standard Test Method for Crack Bridging Ability of Liquid-Applied Waterproofing Membrane¹

This standard is issued under the fixed designation C1305/C1305M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers a laboratory procedure for determining the ability of a waterproofing membrane to bridge a crack in the substrate.

1.2 There are no ISO standards similar or equivalent to this ASTM standard.

1.3 The values stated in either SI units or inch-pound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

C33/C33M Specification for Concrete Aggregates

C150/C150M Specification for Portland Cement

C717 Terminology of Building Seals and Sealants

C1375 Guide for Substrates Used in Testing Building Seals and Sealants

3. Terminology

3.1 *Definitions*—Refer to Terminology C717 for definitions of technical terms used in this test method.

4. Summary of Test Method

4.1 This test method consists of casting five specimens of membrane on mortar substrates containing a preexisting crack

and allowing them to age 14 days at standard conditions followed by seven days in an air-circulating oven at 70°C [158°F], placing them in a test machine, and subjecting the assembly to ten cycles of movement.

5. Significance and Use

5.1 This test method is used to indicate a waterproofing membrane's ability to maintain its integrity while bridging a preexisting crack in the substrate at low ambient temperatures, when the membrane is least likely to be flexible.

6. Comparison to Other Standards

6.1 The committee with jurisdiction over this standard is not aware of any comparable standards published by other organizations.

7. Apparatus and Materials

7.1 Automatic Extension and Compression Machine, with cold box capable of maintaining $-26 \pm 1^{\circ}C$ [-15 $\pm 2^{\circ}F$].

7.2 Circulating Hot-Air Oven.

7.3 *Portland Cement*, high early strength conforming to Specification C150/C150M, Type III.

7.4 *Fine Aggregate*, conforming to Specification C33/C33M.

7.5 Aluminum Angles, 75 by 50 by 25 mm [3 by 2 by 1 in.], if needed.

7.6 *Epoxy Cement*, or gun-grade construction mastic, if needed.

7.7 Masking Tape.

7.8 *Molds*, six, 50 by 25 by 25 mm [2 by 1 by 1 in.] inside dimensions, or 75 by 88 by 25 mm [0.5 by 1.5 by 1 in.] notches in either side, as shown in Fig. 1, for casting mortar blocks.

8. Preparation of Substrates

8.1 Prepare mortar blocks in sizes required for testing in accordance with the requirements in Guide C1375.

¹ This test method is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.22 on Waterproofing and Dampproofing Systems.

Current edition approved Nov. 1, 2016. Published November 2016. Originally approved in 1995. Last previous edition approved in 2008 as C1305 – 08. DOI: 10.1520/C1305_C1305M-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

(5) C1305/C1305M – 16



FIG. 1 Test Assembly Options

8.2 If required to fit the test assembly into the jaws of the testing machine, aluminum angles may be adhered to the sides of the substrates after the membrane has been applied.³

8.3 Other substrates may be used and shall be prepared to provide a clean, level test surface. Prepare glass and aluminum substrates in accordance with the requirements in Guide C1375. Other preparation requirements shall be as agreed upon between the supplier and the specifier.

9. Conditioning/Mixing

9.1 Store all materials to be tested at standard conditions of $23 \pm 2^{\circ}$ C [73.4 \pm 3.6°F] and 50 \pm 5 % relative humidity for at least 24 h before any test specimens are prepared.

9.2 Follow the manufacturer's instructions for mixing and preparing membrane materials for testing. Thoroughly stir one component samples before using. Mix two component compounds in the ratio, and as recommended by the manufacturer.

10. Procedure

10.1 Five assemblies shall be tested.

10.2 To prepare the test assembly, set two blocks as indicated in Fig. 1, with sides touching, in a sand bed. Level the test surface (top) and bind the blocks together using masking tape. Spread the test compound to produce a uniform dry film thickness of 1.50 ± 0.10 mm [0.060 ± 0.005 in.] over the top area bisected by the joint between the blocks. The membrane may be applied in multiple coats, if recommended by the manufacturer.

³ A general purpose, gun-grade construction mastic or a structural epoxy cement has been found suitable for this purpose.



10.3 Cure the test assembly 14 days at room temperature followed by seven days in a circulating hot-air oven at $70 \pm 2^{\circ}$ C [158 \pm 3.6°F]. Allow the test specimen to cool to room temperature for at least 1 h. Cut a strip of membrane 6 mm [¹/₄ in.] away from the edge, across the joint on both sides. This will eliminate edge effects (see Fig. 1). If needed, aluminum angles may be adhered to the sides of the assembly after the room temperature curing period (see Fig. 1, Option A).

10.4 Remove the tape from the blocks and place them in the testing machine, preconditioned to -26° C [-15° F] for at least 24 h. Maintaining this temperature, subject the assembly to ten cycles of movement, each cycle consisting of pulling the blocks apart at the rate of 3.2 mm [$\frac{1}{8}$ in.]/h until the space between them is 3.2 mm and then closing the space at the same rate.

10.5 Upon completion of the ten cycles, extend the membrane to 3.2 mm while still in the machine and examine the membrane for cracking, splitting, pinholes, or any other condition in the area of the joint in the substrates.

11. Report

11.1 Report the following information:

11.1.1 The number of specimens which show no failure, as described in 10.5, in ten cycles, and

11.1.2 All observable physical changes in the membrane.

12. Precision and Bias

12.1 The precision and bias calculations for this test method are based on the results of three laboratories testing three materials.

12.2 Since this is a pass-fail test, the interlaboratory testing was conducted only to ascertain agreement between laboratories. The test results showed 100 % agreement between the three laboratories, indicating that this test method is valid.

13. Keywords

13.1 crack bridging; membrane; waterproofing

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/