

Standard Test Method for Determination of Total Neutralizing Capability and Dissolved Calcium and Magnesium Oxide in Lime for Flue Gas Desulfurization (FGD)¹

This standard is issued under the fixed designation C1318; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers analysis of magnesian, dolomitic and high-calcium limes for total neutralizing capability and dissolved major oxides. Dissolved calcium and magnesium are the major species that neutralize acid under the conditions of the test.

1.2 The test conditions are chosen to measure the acidneutralizing capacity of both calcium hydroxide and magnesium hydroxide contained in slaked lime. By controlling the neutralization pH at 6, magnesium hydroxide and magnesium oxide are titrated in addition to calcium hydroxide fraction.

1.3 This test method also determines the fraction of Mg ions present in the lime that will dissolve under lime flue gas desulfurization (FGD) conditions. Because the Mg^{2+} ion alters FGD performance, it is important to know its concentration.

1.4 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

C25 Test Methods for Chemical Analysis of Limestone, Quicklime, and Hydrated Lime

C51 Terminology Relating to Lime and Limestone (as used by the Industry)

C110 Test Methods for Physical Testing of Quicklime, Hydrated Lime, and Limestone

- C1301 Test Method for Major and Trace Elements in Limestone and Lime by Inductively Coupled Plasma-Atomic Emission Spectroscopy (ICP) and Atomic Absorption (AA)
- E11 Specification for Woven Wire Test Sieve Cloth and Test Sieves

3. Terminology

3.1 *Definitions*—Unless otherwise specified, for definitions of terms used in these test methods refer to Terminology C51.

4. Summary of Test Method

4.1 Lime is slaked by boiling and is reacted with acid at a pH and residence time similar to those found in full-scale FGD reaction tanks.

4.2 A sample of lime is titrated with 1N hydrochloric acid, maintaining a pH of 6 for 30 min. After 30 min, the acid consumption is recorded. The total neutralizing capacity is calculated from the acid consumption and reported as % CaO. Dissolved magnesium is determined by spectrometry or by EDTA titration and reported as percent dissolved Magnesium Oxide (as MgO).

5. Significance and Use

5.1 There are existing lime-based flue gas desulfurization units in operation that require a method to measure the oxides available for sulfur dioxide absorption. Dissolved magnesium oxide varies among limes depending on the limestone sources and calcination conditions.

6. Interferences

6.1 Any substance reacting with acid under the conditions of the test will contribute to the total oxide and dissolved oxide values.

6.2 Magnesium in forms other than MgO, which dissolve under test conditions, may affect the dissolved MgO and total oxide values.

¹ This test method is under the jurisdiction of ASTM Committee C07 on Lime and Limestone and is the direct responsibility of Subcommittee C07.05 on Chemical Tests.

Current edition approved Dec. 1, 2015. Published January 2016. Originally approved in 1995. Last previous edition approved in 2015 as C1318 – 15. DOI: 10.1520/C1318-15A.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

7. Apparatus

7.1 *Digital Readout pH Meter*, with combination electrode readable to 0.01 pH units, or an autotitrator with an automatic temperature compensator capable of titrating to a preset endpoint (Note 1).

Note 1-Use of an automatic titrator is recommended.

7.2 Stirrers and Stir Bars.

7.3 Inductively Coupled Plasma Spectrometer or Atomic Absorption Spectrometer, if not using EDTA titration.

7.4 *Filtering Funnel*, Type AE glass fiber paper, volumetric flasks (size as needed), 500 mL volumetric flasks, and various Class A pipettes.

8. Reagents

8.1 *1.0 Normal Hydrochloric Acid*, standardized using procedures in the section on Available Lime Index in Test Methods C25.

8.2 Deionized or Distilled Water, CO₂ free.

8.3 *Calcium and Magnesium Standard Solutions*, commercially available or use the procedures in the section on Calcium and Magnesium Oxide (Alternative EDTA Titration Method) in Test Methods C25.

8.4 *EDTA Standard Solution* (0.4 %), standardized according to the procedure in the section on Calcium and Magnesium Oxide (Alternative EDTA Titration Method) in Test Methods C25.

8.5 1:1 Hydrochloric Acid, a solution prepared by diluting concentrated Hydrochloric Acid by addition to an approximately equal volume of distilled or deionized water.

9. Sample Preparation

9.1 The sampling and grinding of any lime sample shall be carried out as rapidly as possible, so that the absorption of moisture and carbon dioxide is held to a minimum.

9.2 The sample as received at the laboratory shall be thoroughly mixed and a representative sample with minimum weight of 100 g shall be taken and pulverized to pass a 300 μ m (No. 50) sieve for analysis. Conduct the sieve analysis in accordance with Test Methods C110.

9.3 The prepared sample shall be stored in a tightly capped container.

10. Procedure

10.1 Slaking of Lime Sample:

10.1.1 Weigh rapidly 1.402 g of the finely pulverized sample and brush carefully into a 250 mL Erlenmeyer flask containing about 50 mL of CO_2 free deionized or distilled water and immediately stopper the flask.

10.1.2 Remove the stopper. Swirl the flask, place on a hot plate, and boil actively 1 min for complete slaking. Remove from the hot plate, stopper the flask loosely, and place in a cold-water bath to cool to room temperature.

10.2 Titration of Sample:

10.2.1 Set the pH electrode, burette tip, and temperature sensing device in place, while maintaining agitation.

10.2.2 Begin the titration by adding standard 1.0 normal hydrochloric acid solution. Titrate to and maintain a pH of 6.0 within 0.4 pH units for 30 min (Note 2). Time begins from initial addition of acid.

Note 2—When doing a manual titration, the increment of acid addition may require the use of partial drops (suspend a small amount of titrant on the buret tip and wash into the titration flask with CO_2 free deionized or distilled water) to avoid exceeding the 0.4 unit limit of pH 6.

10.2.3 Record the amount of acid consumed after 30 min.

10.2.4 Filter the solution, rinse the flask thoroughly with $\rm CO_2$ free deionized or distilled water, and pass the rinse through the filter.

10.2.5 Carefully transfer the combined filtrate and a rinse to an appropriately sized volumetric flask, add approximately 10 mL of 1:1 hydrochloric acid, and dilute to volume with distilled or deionized water. This is the "Initial Volume."

10.3 Determination of Dissolved Oxides:

10.3.1 Spectroscopy:

10.3.1.1 Pipet an aliquot of the diluted solution from the volumetric flask to make the required dilutions to a "Final Volume" and determine the dissolved magnesium in accordance with Test Method C1301.

10.3.1.2 Calculate the dissolved magnesium as % MgO according to 11.2.

10.3.2 EDTA Titration:

10.3.2.1 From the diluted solution prepared in 10.2.5, pipette 20 mL of sample into a 500 mL Erlenmeyer flask and dilute with CO_2 free deionized or distilled water to an approximate volume of 100 mL.

10.3.2.2 Determine the total dissolved calcium according to the procedure for Calcium Oxide in the section on Calcium and Magnesium Oxide (Alternative EDTA Titration Method) in Test Methods C25. Record mL of EDTA standard solution required for titration.

10.3.2.3 Repeat 10.3.2 and determine the total dissolved oxides according to the procedure for Magnesium Oxide in the section on Calcium and Magnesium Oxide (Alternative EDTA Titration Method) in Test Methods C25. Record mL of EDTA standard solution required for this titration.

11. Calculation of Results

11.1 Percent Total Neutralizing Capability (TNC):

% TNC (as CaO) =
$$\frac{A \times B \times C_{-1}}{W}$$
 (1)

where:

A = mL HCl used in 10.2.3,

B = normality HCl,

$$C_1$$
 = chemical factor = 2.804 (mequi of CaO/10), and

W =sample weight, g.

11.2 Spectroscopy:

11.2.1 Dilution Factor:

$$Dilution factor = \frac{"Final Volume" (see 10.3.1.1)}{Pipetted volume of aliquot for final dilution}$$
(2)

11.2.2 Percent Dissolved Magnesium:

% Dissolved Mg²⁺(as MgO) = $(A \times B \times C_2 \times D)/(W \times 10,000)$ (3)

where:

 $A = \text{concentration of magnesium from instrument ppm} Mg^{2+},$

B =dilution factor,

- C_2 = chemical factor = 1.658 (MgO/Mg²⁺),
- D = "Initial Volume," volume, mL, and

W = sample weight, g.

11.3 EDTA Titration:

11.3.1 Aliquot Factor:

(4)

11.3.2 Percent Dissolved Calcium:

% Dissolved Ca²⁺(as CaO) =
$$\frac{A \times B \times C_3 \times D}{W \times 10}$$
 (5)

where:

A = mL of EDTA standard solution used,

B = aliquot factor,

 C_3 = chemical factor = 1.399 (CaO/Ca²⁺),

D = EDTA titer, mg Ca²⁺/mL EDTA standard solution, and

W =sample weight, g.

11.3.3 Percent Total Dissolved Oxides (TDO):

% TDO (as CaO) =
$$\frac{A \times B \times C_3 \times D}{W \times 10}$$
 (6)

where:

A = mL of EDTA standard solution used,

B = aliquot factor,

 C_3 = chemical factor = 1.399 (CaO/Ca²⁺),

D = EDTA titer, mg Ca²⁺/mL EDTA standard solution, and

W = sample weight, g.

11.3.4 Percent Dissolved Magnesium:

% Dissolved Mg²⁺(as MgO) =
$$(A - B) \times C_4$$
 (7)

where:

A = % total dissolved oxides,

B = % dissolved calcium as CaO, and

 C_4 = chemical factor = 0.7188 (MgO/CaO).

12. Precision and Bias

12.1 The precision and bias of this test method have not been determined.

12.2 When sufficient data has been obtained and analyzed, a statement of precision will be provided.

12.3 The user is cautioned to verify by the use of reference materials, if available, that the bias of the test method is adequate for the contemplated use.

13. Keywords

13.1 dissolved calcium; dissolved magnesium; flue gas desulfurization (FGD); lime; pH determination; total neutralizing capability

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/