

Designation: C1325 – 17a

## Standard Specification for Non-Asbestos Fiber-Mat Reinforced Cementitious Backer Units<sup>1</sup>

This standard is issued under the fixed designation C1325; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification covers non-asbestos fiber-mat reinforced cementitious backer units manufactured to be dimensionally stable and suitable as either an unfinished substrate (see Note 1) or as a substrate for decoration such as natural stone or tile on walls, floors, or decks in wet and dry areas. It is also suitable to be used as a substrate in the Application of Class PB Exterior Insulation Finish Systems (Practice C1397), the Application of Direct-Applied Finish Systems (Practice C1516), and the Application of Exterior Insulation Finish Systems Class PI (Practice C1535).

Note 1—When used as an unfinished substrate, consult the manufacturer's written installation literature for proper application details.

1.2 This specification is not applicable to asbestos-cement flat sheets (Specification C220); non-asbestos fiber cement flat sheets for exterior applications such as claddings, facades, curtain walls, and soffits (Specification C1186); gypsum backing board, coreboard, and shaftliner (Specification C1396/C1396M); water-resistant gypsum backing board (Specification C1396/C1396M); glass mat gypsum backing board (Specification C1178/C1178M); particle boards (Definitions D1554); and discrete non-asbestos fiber cement interior substrate sheets (Specification C1288).

1.3 Units—The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

#### 2. Referenced Documents

- 2.1 ASTM Standards:<sup>2</sup>
- C220 Specification for Flat Asbestos-Cement Sheets
- C473 Test Methods for Physical Testing of Gypsum Panel Products
- C666/C666M Test Method for Resistance of Concrete to Rapid Freezing and Thawing
- C947 Test Method for Flexural Properties of Thin-Section Glass-Fiber-Reinforced Concrete (Using Simple Beam With Third-Point Loading)
- C1154 Terminology for Non-Asbestos Fiber-Reinforced Cement Products
- C1178/C1178M Specification for Coated Glass Mat Water-Resistant Gypsum Backing Panel
- C1185 Test Methods for Sampling and Testing Non-Asbestos Fiber-Cement Flat Sheet, Roofing and Siding Shingles, and Clapboards
- C1186 Specification for Flat Fiber-Cement Sheets
- C1288 Specification for Discrete Non-Asbestos Fiber-Cement Interior Substrate Sheets
- C1396/C1396M Specification for Gypsum Board
- C1397 Practice for Application of Class PB Exterior Insulation and Finish Systems (EIFS) and EIFS with Drainage
- C1516 Practice for Application of Direct-Applied Exterior Finish Systems
- C1535 Practice for Application of Exterior Insulation and Finish Systems Class PI
- D1037 Test Methods for Evaluating Properties of Wood-Base Fiber and Particle Panel Materials
- D1554 Terminology Relating to Wood-Base Fiber and Particle Panel Materials
- D2394 Test Methods for Simulated Service Testing of Wood and Wood-Base Finish Flooring
- E84 Test Method for Surface Burning Characteristics of Building Materials
- G21 Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee C17 on Fiber-Reinforced Cement Productsand is the direct responsibility of Subcommittee C17.01 on Non-Asbestos Fiber-Mat Reinforced Products.

Current edition approved June 1, 2017. Published July 2017. Originally approved in 1996. Last previous edition approved in 2017 as C1325 - 17. DOI: 10.1520/C1325-17A.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

G22 Practice for Determining Resistance of Plastics to Bacteria (Withdrawn 2002)<sup>3</sup>

- 2.2 ANSI Standards:<sup>4</sup>
- A118.1 American National Standard Specification for Dry-Set Cement Mortar
- A118.4 American National Standard Specification for Modified Dry-Set Cement Mortar
- A136.1 Standard for Organic Adhesives for Installation of Ceramic Tile

## 3. Terminology

3.1 Definitions—Refer to Terminology C1154.

#### 4. Classification

4.1 Flat sheets covered by this specification are divided into two types, according to their intended application.

4.1.1 Type A—Sheets are intended for exterior applications as a substrate for other cladding materials, or as an unfinished substrate for decoration such as natural stone, tile, or coatings. Type A products are also suitable for interior use.

4.1.2 Type B-Sheets are intended for covered exterior applications such as soffit areas, or for interior dry or wet area applications as a desired unfinished substrate or an unfinished substrate for decoration such as natural stone or tile, where substrate dimensional stability is required.

NOTE 2-Flat sheets may be supplied coated or uncoated.

#### 5. Composition and Manufacture

5.1 Composition—This specification is applicable to nonasbestos fiber-mat reinforced cementitious backer units consisting essentially of an inorganic hydraulic binder or a calcium silicate binder formed by the chemical reaction of a siliceous material and a calcareous material, reinforced by fiber-mat made of organic fibers, inorganic non-asbestos fibers, or both.

NOTE 3-Process aids, fillers, pigments, and other fibers that are compatible with the fiber-mat cement may be added.

5.2 Manufacture—These products are formed either with or without pressure and cured, either under natural or accelerated conditions, to meet the property requirements of this specification.

#### 6. Mechanical and Physical Properties

6.1 Mechanical and physical properties shall be determined on an uncoated product wherever practical. Where the products are supplied coated, this material shall also be tested with the results identified as applying to coated material.

6.2 Sampling-Obtain five samples of the particular cement substrate sheet to be tested from a commercial lot of not less than 50 000 ft<sup>2</sup> to conduct the tests described in this specification.

6.3 Mechanical Properties:

6.3.1 Flexural Strength-When tested in accordance with Test Method C947, flexural strength shall be not less than 750 psi (5170 kPa).

6.3.2 Sheets shall be tested and specified in both the wet and equilibrium conditions and shall meet the minimum wet and minimum equilibrium flexural strength requirements.

NOTE 4-When sampled from continuous production, these tests may be conducted on dry, equilibrium, or saturated specimens, provided a relationship can be established between this testing and the specified values.

#### 6.4 Physical Properties:

6.4.1 Density-Nominal values and tolerances for density shall be stated by the manufacturer for each of the products. When tested in accordance with the test method specified in Test Methods C1185, the value for the density shall comply with the value stated by the manufacturer.

6.4.2 Modulus of Elasticity-Values for the modulus of elasticity shall be stated by the manufacturer for each of the products. When tested in accordance with Test Method C947, the value for modulus of elasticity shall comply with the value stated by the manufacturer. Calculate the modulus of elasticity for each sample specimen by the following equation:

$$E = 5(P_2 - P_1) \times L^{-3}/27bd^3(y_2 - y_1)$$
(1)

where:

Ε	=	modulus of elasticity, psi (MPa),
$P_2$ and $P_1$	=	loads, lb (N), taken from two points within the
		linear section of the plot,

= deflections, in. (mm) corresponding to the loads  $y_2$  and  $y_1$ selected,

= width of specimen, in. (mm), b

d = thickness of specimen, in. (mm), and

L = span, in. (mm).

## 7. Dimensions and Tolerances

7.1 Method of Measurement—The method of measurement for 7.1.1 - 7.1.5 shall be in accordance with Test Methods C473.

7.1.1 Nominal Length and Width-Fiber-mat reinforced cementitious backer units are typically supplied in nominal lengths of 48 in. (1219 mm) to 96 in. (2438 mm) and nominal widths of 32 in. (810 mm) to 48 in. (1219 mm). Lengths and widths other than stated above are not prohibited from being supplied.

7.1.2 Nominal Thickness-Fiber-mat reinforced cementitious backer units are typically supplied in nominal thicknesses of 1/4 in. (6 mm) to 5/8 in. (16 mm). Thicknesses other than stated above are not prohibited from being supplied.

7.1.3 Length and Width Tolerance—The tolerance from the nominal value shall be  $\pm \frac{1}{8}$  in. (3 mm).

7.1.4 Thickness Tolerance-The maximum difference between extreme values of the thickness measurement within a sheet shall not exceed 0.03 in. (0.8 mm). Thickness variation from sheet to sheet shall not exceed 0.03 in. (0.8 mm).

7.1.5 Squareness Tolerance-The length of the diagonals shall not vary by more than 1/32 in./ft (2.6 mm/m) of the length of the sheets. Opposite sides of the sheet shall not vary in length by more than  $\frac{1}{32}$  in./ft (2.6 mm/m).

<sup>&</sup>lt;sup>3</sup> The last approved version of this historical standard is referenced on www.astm.org.

<sup>&</sup>lt;sup>4</sup> Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036, http://www.ansi.org.

7.2 *Edge Straightness Tolerance*—The sheet edges shall be straight within  $\frac{1}{32}$  in./ft (2.6 mm/m) of length or width when tested in accordance with Test Methods C1185.

#### 8. Workmanship

8.1 *Workmanship*—Sheets shall be free of defects that will impair erection, use, or serviceability.

## 9. Inspection and Acceptance

9.1 Inspection of material, if required, shall be at the point of shipment. The inspector representing the purchaser shall have authorized access to the carriers being loaded for shipment to the purchaser. The purchaser shall be afforded all reasonable and available facilities at the point of shipment for sampling and inspection of the material, which shall be conducted so as not to interfere unnecessarily with the loading of the carriers.

9.2 Third party certification, either continuous or at regular intervals, shall be recognized as an alternative to lot inspection.

9.3 Failure to conform to any one of the requirements of this specification shall constitute grounds for nonacceptance.

#### **10. Product Marking**

10.1 *Identification*—Product marking shall include trademark, type of product (A or B), or other means of

identification that ensures that the manufacturer and product type can be identified. The method of marking shall be stated in the manufacturer's catalog.

## 11. Packaging and Storage

11.1 *Commercial Packaging*—Flat sheets shall be packaged so as to prevent damage during shipment.

11.2 *Storage*—Flat sheets shall be stacked on supports that will keep the sheets level and flat. The sheets shall be stacked with the edges square and flush and covered to provide protection from the weather until used.

#### 12. Keywords

12.1 acceptance; air cured; appearance; density; edge straightness; finish; flexural strength; glass mat cement sheet; inspection; interior wet area application; length and width tolerance; mechanical properties; minimum equilibrium strength; minimum wet strength; moisture content; moisture movement; nominal length; nominal thickness; nominal width; non-asbestos fiber-mat; packaging; physical properties; pressure cured; sampling; shipping; squareness tolerance; storage; supplementary requirements; supplementary tests; surface burning characteristics; thickness requirements; thickness tolerance; third party certification; tolerance; type tests; warm water resistance; workmanship

#### SUPPLEMENTARY REQUIREMENTS

#### S1. Supplementary Tests

S1.1 Supplementary tests for fiber-mat reinforced cementitious backer units shall consist of once only supplementary test, with the manufacturer's statement of results provided upon customer's request. Fundamental changes in formulation or methods of manufacture, or both, shall require the subsequent retesting of the supplementary tests.

S1.2 Supplementary tests shall be determined on uncoated product wherever practical. Where fiber-mat reinforced cementitious backer units are supplied coated, this material shall also be tested with the results identified as applying to coated material.

S1.3 The following supplementary tests shall be required:

Moisture Content Moisture Movement Warm Water Resistance Surface Burning Characteristics Shear Bond Strength (Dry-Set Portland Cement Mortar) Shear Bond Strength (Latex-Portland Cement Mortar) Shear Bond Strength (Organic Adhesive Type 1) Nail-Head Pull-Through (roofing nail) Modulus of Elasticity Mold Resistance Compression Indentation Falling Ball Impact Bacteria Resistance Freeze Thaw Resistance S1.3.1 *Moisture Content*—State the percentage of moisture content of the fiber-mat reinforced cementitious backer units when conditioned at 50  $\pm$  5% relative humidity and a temperature of 73  $\pm$  4°F (23  $\pm$  2°C) in accordance with Test Method C1185.

S1.3.2 *Moisture Movement*—The linear variation with change in moisture content shall be stated as the percentage change in length based on a relative humidity change from 30 % to 90 % in accordance with Test Method D1037. The linear variation with change shall be less than or equal to 0.07 %. For the purpose of this test, obtain 5 samples of the particular cement substrate sheet to be tested from a commercial lot of not less than 50 000 ft<sup>2</sup>.

S1.3.3 *Warm Water Resistance*—The specimens, when tested in accordance with Test Method C1185, shall not show visible cracks or structural alteration such as to affect their performance in use. The average flexural strength of the specimens soaked in warm water shall be not less than 70 % of the 750 psi flexural strength requirement from 6.3.1, that is, the average warm water flexural strength shall be not less than 525 psi.

S1.3.4 *Surface Burning Characteristics*—When utilized as a finished substrate without decoration, fiber-mat reinforced cementitious backer units shall have a reported flame spread

index of 10 or less and a smoke developed index of not more than 5 when tested in accordance with Test Method E84. Tests shall be conducted on samples that have been cured for 28 days in a controlled atmosphere of  $73 \pm 4^{\circ}F$  ( $23 \pm 2^{\circ}C$ ) and  $50 \pm 5\%$  relative humidity.

S1.3.5 Shear Bond Strength (Dry-Set Cement Mortar)— Fiber-mat reinforced cementitious backer units tested in accordance with Section 7.1.3 of ANSI A118.1 (fiber-mat reinforced cementitious backer units to fiber-mat reinforced cementitious backer units) shall demonstrate a shear bond strength greater than 50 psi (345 kPa) for samples cured and tested in a saturated condition at 7 days.

S1.3.6 Shear Bond Strength (Modified Dry-Set Cement Mortar)—Fiber-mat reinforced cementitious backer units tested in accordance with Section 7.1.3 of ANSI A118.4 (fiber-mat reinforced cementitious backer units) shall demonstrate a shear bond strength greater than 50 psi (345 kPa) for samples cured and tested in a saturated condition at 7 days.

S1.3.7 Shear Bond Strength (Organic Adhesives Type 1)— Fiber-mat reinforced cementitious backer units tested in accordance with Section 6.2.3.2 of ANSI A136.1 (fiber-mat reinforced cementitious backer units to fiber-mat reinforced cementitious backer units) shall demonstrate a shear bond strength greater than 50 psi (345 kPa) for samples cured and tested in a saturated condition at 7 days.

S1.3.8 Nail-Head Pull Through—Fiber-mat reinforced cementitious backer units of  $\frac{1}{2}$  in. (13 mm) thickness shall have a minimum saturated nail-head pull through resistance of 90 lb (400 N), when tested in accordance with Test Method D1037 utilizing a roofing nail with a 0.375 in. (10 mm) diameter head and a shank diameter of 0.121 in. (3 mm). A pilot-hole having a maximum diameter of 0.121 in. is pre-drilled at the center of cement board specimen. The roofing nail is then driven through the pilot-hole into the specimen.

S1.3.9 *Mold Resistance*—When tested in accordance with Practice G21, samples shall show an observed growth rating of 0.

S1.3.10 *Compression Indentation*—When tested in accordance with Test Method D2394, the average true deformation of cement board at an applied compressive stress of 1250 psi (8620 kPa) must not exceed 0.5 in. (1.3 mm).

S1.3.10.1 Load is applied at the center of a cement board specimen using a steel disc 1 in. in diameter (the circumference of the disc is rounded to a radius of 0.05 in.). Specimen is loaded to a maximum load of 982 lb (4368 N), corresponding to a compressive stress of 1250 psi (8620 kPa), and the specimen apparent load-versus-deformation plot is recorded. Testing machine cross-head displacement is recorded as the apparent deformation of the cement board specimen due to loading.

S1.3.10.2 The specimen true load-versus-deformation plot is derived using the specimen recorded apparent load-versusdeformation plot. This is done by eliminating the specimen extraneous deformations that result from settling of the machine fixtures or from settling of the specimen due to presence of a bow or surface texture. The specimen extraneous deformations are typically manifested in the initial part of the load-versus-deformation plot in the form of a non-linear region that precedes a linear plot. The extraneous deformations are eliminated by drawing a tangent on the aforementioned linear plot to intersect the x-axis (that is, the deformation measurement axis) on the x-y plot. The intersection point of the tangent and x-axis marks the initial specimen deformation (that is, zero specimen deformation). The true load-versus-deformation graph is plotted after making corrections for the extraneous deformations as described above. The true deformation of the specimen at an applied compressive stress of 1250 psi (8620 kPa) is then calculated from the plot.

S1.3.11 *Falling Ball Impact*—When tested in accordance with Test Method D1037, samples shall show no damage to top or bottom surfaces at a 12 in. (305 mm) drop.

S1.3.11.1 Failure is characterized by presence of any one or more of the following damage mechanisms: (1) mesh rupture (top or bottom surface); (2) complete mesh delamination from the cement board core (top or bottom surface); or (3) breakage, crumbling, and falling-off of cementitious core material sandwiched between the top and bottom mesh reinforcement. Minor responses such as specimen indentation at the ball impact location, microcracking of the cementitious core, and spalling of mesh reinforcement cement cover are not considered as damage or causes of failure.

S1.3.12 *Bacteria Resistance*—When tested in accordance with Practice G22, samples shall show an observed growth rating of 0.

S1.3.13 *Freeze Thaw Resistance*—When tested in accordance with Test Method C666/C666M (Procedure B) samples shall show no disintegration at 50 cycles for Type A and 25 cycles for Type B.

S1.3.13.1 The term disintegration in S1.3.13 is characterized by one or more of the following: (1) complete delamination of top and/or bottom mesh reinforcement from the core (loss of composite action); (2) fracture of top and/or bottom mesh reinforcement (loss of composite action); (3) cementitious core developing significant macrocracking and/or crumbling (loss of composite action); (4) cementitious core dissolving in water. Minor responses such as development of hairline cracks in the cementitious core and localized chipping and spalling of mesh reinforcement cement cover are not considered as damage or causes of failure.

# C1325 – 17a

## SUMMARY OF CHANGES

Committee C17 has identified the location of selected changes to this standard since the last issue (C1325 - 17) that may impact the use of this standard. (June 1, 2017)

(1) Revised S1.3.5, S1.3.6, and S1.3.7.

Committee C17 has identified the location of selected changes to this standard since the last issue (C1325 - 14) that may impact the use of this standard. (November 1, 2016)

(1) Revised Section 7.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/