



# Standard Practice for Sampling Materials for Shotcrete<sup>1</sup>

This standard is issued under the fixed designation C1385/C1385M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice covers procedures for obtaining representative samples of materials to be shotcreted. The practice covers sampling from stationary and truck mixers, volumetric and continuous mixing equipment, and bag and bulk delivery.

1.2 The values stated in either inch-pound or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with this practice.

1.3 *This standard does not purport to address the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

**C125 Terminology Relating to Concrete and Concrete Aggregates**

## 3. Terminology

3.1 For definitions of terms used in this standard, refer to Terminology **C125**.

## 4. Significance and Use

4.1 This practice is used to obtain representative samples of materials delivered to the shotcrete machine. These samples are used to perform tests to determine compliance with the specifications under which the material is furnished.

## 5. Procedure

5.1 Composite samples are required by this practice, unless specifically made exempt by procedures governing the tests to be performed, such as tests to determine uniformity of consistency and mixer efficiency. Procedures used to select the specific test batches are not described in this practice, but it is recommended that random sampling be used to determine overall specification compliance.

5.2 The size of an individual sample shall be a minimum of 12 kg [25 lb], the size of the composite sample shall be a minimum of 35 kg [75 lb]. The composite sample shall be large enough to perform the required tests.

5.3 Sampling shall be performed as the shotcrete material is delivered to the shotcrete machine. The procedures used in sampling shall include the use of every precaution that will assist in obtaining samples that are truly representative of the nature and condition of the material sampled as follows:

5.3.1 *Sampling Dry Process Shotcrete Materials*—Sample the material by collecting two or more portions taken at regularly spaced intervals during discharge of the middle of the batch or two or more random portions from the discharge of continuous mixers. Combine the portions into one sample for testing purposes. Do not obtain portions of the composite sample from the first 15 % or the last 15 % of the discharge.

5.3.2 *Sampling Wet Process Shotcrete Material*—Sample as described in 5.3.1 within the following limits.

5.3.2.1 The elapsed time between obtaining the first and last portions of the composite sample shall be as short as possible but in no instance shall exceed 15 min.

5.3.2.2 Start test for slump or air content, or both, within 5 min after obtaining last portion of the composite.

5.3.3 *Alternative Procedure for Truck and Stationary Mixers*—The mixer shall be stopped and material portions removed by any suitable means at approximately equal distances from the front and back of the drum. Composite the portions into one sample for testing. Do not obtain portions from the very front and back of the drum. Sample wet process shotcrete material within the time limits described in 5.3.2.1 and 5.3.2.2.

5.3.4 *Sampling Bagged Prepackaged Material*—Randomly select a single package, or more if required to perform the specified tests, from a lot. A lot is the quantity normally placed

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.46 on Shotcrete.

Current edition approved June 15, 2010. Published July 2010. Originally approved in 1998. Last previous edition approved in 2004 as C1385–98(2004) <sup>$\epsilon$ 1</sup>. DOI: 10.1520/C1385\_C1385M-10.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



on a pallet. In general, this quantity will weigh from 2000 to 4000 lbs [900 to 1300 kg].

**5.3.5 Sampling Bulk Prepackaged Material**—Sample the material at the point of delivery to the shotcrete machine by collecting three or more portions at regular intervals during discharge of the container or transportation unit. Obtain por-

tions from the first, middle, and last third of the unit. Do not sample the first 15 % or last 15 % of the discharge. Combine portions for testing.

## **6. Keywords**

6.1 dry process; sampling; shotcrete; wet process

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the ASTM website ([www.astm.org/COPYRIGHT/](http://www.astm.org/COPYRIGHT/)).*