



Standard Guide for Selecting Jacketing Materials for Thermal Insulation¹

This standard is issued under the fixed designation C1423; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This guide covers criteria for selecting thermal insulation jacketing materials and is not intended for use as a performance or product specification.

1.2 This guide applies to jacketing materials applied over thermal insulation for piping, ducts, and equipment.

1.3 This guide includes jacketing materials used over thermal insulation whether the insulation is in the form of pipe, board, or blanket, or field applied materials that are self-supporting, including insulating cements.

1.4 This guide does not include covers or other retaining walls that contain loose fill, other nonsupporting insulation materials, or conduits or containers for buried insulation systems.

1.5 This guide does not include mastics and coatings and their reinforcements.

1.6 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.7 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- A240/A240M Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications
- A366/A366M Specification for Commercial Steel (CS)

¹ This guide is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is direct responsibility of Subcommittee C16.40 on Insulation Systems.

Current edition approved March 1, 2016. Published March 2016. Originally approved in 1998. Last previous edition approved in 2015 as C1423 – 15a. DOI: 10.1520/C1423-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

Sheet, Carbon, (0.15 Maximum Percent) Cold-Rolled (Withdrawn 2000)³

A1008/A1008M Specification for Steel, Sheet, Cold-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, Solution Hardened, and Bake Hardenable

B209 Specification for Aluminum and Aluminum-Alloy Sheet and Plate

C165 Test Method for Measuring Compressive Properties of Thermal Insulations

C168 Terminology Relating to Thermal Insulation

C488 Test Method for Conducting Exterior Exposure Tests of Finishes for Thermal Insulation

C835 Test Method for Total Hemispherical Emittance of Surfaces up to 1400°C

C921 Practice for Determining the Properties of Jacketing Materials for Thermal Insulation

C1057 Practice for Determination of Skin Contact Temperature from Heated Surfaces Using a Mathematical Model and Thermesthesiometer

C1136 Specification for Flexible, Low Permeance Vapor Retarders for Thermal Insulation

C1258 Test Method for Elevated Temperature and Humidity Resistance of Vapor Retarders for Insulation

C1263 Test Method for Thermal Integrity of Flexible Water Vapor Retarders

C1338 Test Method for Determining Fungi Resistance of Insulation Materials and Facings

C1371 Test Method for Determination of Emittance of Materials Near Room Temperature Using Portable Emis-someters

C1729 Specification for Aluminum Jacketing for Insulation

C1767 Specification for Stainless Steel Jacketing for Insulation

C1775 Specification for Laminate Protective Jacket and Tape for Use over Thermal Insulation for Outdoor Applications

C1785 Test Method for Concentration of Pinhole Detections in Moisture Barriers on Metal Jacketing

D774/D774M Test Method for Bursting Strength of Paper (Withdrawn 2010)³

³ The last approved version of this historical standard is referenced on www.astm.org.

- D828** Test Method for Tensile Properties of Paper and Paperboard Using Constant-Rate-of-Elongation Apparatus (Withdrawn 2009)³
- D882** Test Method for Tensile Properties of Thin Plastic Sheeting
- D1000** Test Methods for Pressure-Sensitive Adhesive-Coated Tapes Used for Electrical and Electronic Applications
- D1204** Test Method for Linear Dimensional Changes of Nonrigid Thermoplastic Sheeting or Film at Elevated Temperature
- D3330/D3330M** Test Method for Peel Adhesion of Pressure-Sensitive Tape
- D3363** Test Method for Film Hardness by Pencil Test
- D3759/D3759M** Test Method for Breaking Strength and Elongation of Pressure-Sensitive Tape
- E84** Test Method for Surface Burning Characteristics of Building Materials
- E96/E96M** Test Methods for Water Vapor Transmission of Materials
- E119** Test Methods for Fire Tests of Building Construction and Materials
- E596** Test Method for Laboratory Measurement of Noise Reduction of Sound-Isolating Enclosures
- F1249** Test Method for Water Vapor Transmission Rate Through Plastic Film and Sheeting Using a Modulated Infrared Sensor
- G154** Practice for Operating Fluorescent Ultraviolet (UV) Lamp Apparatus for Exposure of Nonmetallic Materials
- 2.2 *TAPPI Standards*:⁴
- T461** Flame Resistance of Treated Paper and Paperboard
- 2.3 *ANSI Standards*:
- H35.2.H35.2(M)** Dimensional Tolerances for Aluminum Mill Products

3. Terminology

3.1 *Definitions*—Terminology **C168** apply to the terms used in this practice. The following terms are also used in this standard.

3.1.1 *abuse resistance*—ability of a material to be exposed for prolonged periods of time to normal physical abuse without significant deformation or punctures.

3.1.2 *ambient temperature*—the dry bulb temperature of surrounding air when shielded from any sources of incident radiation.

3.1.3 *cleanability*—ability of a material to be washed or otherwise cleaned to maintain its appearance.

3.1.4 *corrosion resistance*—ability of a material to be exposed for prolonged periods of time to a corrosive environment without significant onset of corrosion and the consequential loss of mechanical properties.

3.1.5 *fire resistance*—ability of a material, product, or assembly to withstand fire or give protection from it for a period of time.

3.1.6 *fungal growth resistance*—ability of a material to be exposed continuously to damp conditions without the growth of mildew or mold.

3.1.7 *temperature resistance*—ability of a material to perform its intended function after being subjected to high and low temperatures which the material might be expected to encounter during normal use.

3.1.8 *weather resistance*—ability of a material to be exposed for prolonged periods of time to the outdoors without significant loss of mechanical properties.

4. Significance and Use

4.1 This standard is intended to be used by engineers and designers as a guide to assist them in selecting appropriate thermal insulation jacketing materials. As a guide, it can be used to identify performance characteristics that might be necessary for a particular insulation jacketing system. This guide is not a specification and therefore should not be used as such. It might, however, be useful in writing a specification. Specification **C921** can also be used to determine properties of jacketing materials for thermal insulation.

5. Materials and Manufacture

5.1 Jacketing materials may be composed of a single material or a lamination of several components. The material may be in the form of rolls or sheets or preformed to fit the surface to which they are to be applied. The materials may be applied in the field or may be a factory-applied composite with the insulation.

5.2 *Metallic*:

5.2.1 Metallic jacketing materials are those whose primary material (usually the component of greatest thickness) is metal, such as, aluminum, coated steel, and stainless steel. The metal may be smooth, corrugated, or embossed. The dimensions of corrugations (pitch and depth) may be specified by the purchaser for interchangeability, constant rigidity, and control of sizes. The inner surface of metallic jacketing materials may be coated or covered with a moisture resistant film to retard possible galvanic and/or chemical corrosion of the jacketing.

5.2.1.1 Aluminum jacketing should be manufactured in compliance with Specification **C1729** which incorporates by reference the chemical composition and physical properties of Specification **B209**. Where ambient conditions are particularly corrosive or when a higher surface emissivity is desired, the outer surface of the aluminum may be coated with paint or plastic film.

5.2.1.2 Coated steel jacketing materials can be manufactured in compliance with several Specifications including **A366/A366M** and **A1008/A1008M** using alloys 1010, 1015, or 1020 steel. The outer surface is typically protected by aluminizing, galvanizing, or coating with another type of corrosion resistant metal alloy. Metal thicknesses generally available are from 0.010 to 0.019 in. (0.25 to 0.46 mm).

5.2.1.3 Stainless steel jacketing should be manufactured in compliance with Specification **C1767** which incorporates by reference the chemical composition and physical properties of Specification **A240/A240M**.

⁴ Available from Technical Association of the Pulp and Paper Industry (TAPPI), 15 Technology Parkway South, Norcross, GA 30092, <http://www.tappi.org>.

5.3 *Nonmetallic and Laminated Jacketing:*

5.3.1 Laminated jacketing materials are typically manufactured from combinations of plastic films, plastic composites, metallic foils, reinforcing fabrics, papers, or felts selected to obtain the required performance characteristics. Laminated jacketing for outdoor applications should be manufactured in compliance with Specification **C1775**.

5.3.1.1 One common type of laminated jacketing is flexible low permeance vapor retarders, which should be manufactured in compliance with Specification **C1136**.

5.3.2 Textile or cloth jacketing materials are woven or knitted of textile yarns. Commonly available forms are 4, 6, or 8 oz/yd² (0.14, 0.20, or 0.27 kg/m²) cotton canvas, various weaves of glass fiber yarns, presized glass cloth, knit, or woven plastic fibers.

5.3.3 Plastic jacketing materials are manufactured in various forms and types. Thicknesses generally available are from 0.003 to 0.035 in. (0.08 to 0.89 mm). Various materials can be used such as poly-vital chloride (PVC), CPVS, fiberglass reinforced plastic (FRP), and others.

5.3.4 Saturated felt or cloth jacketing materials are manufactured from various base felts or cloths that have been impregnated with bitumen or resinous materials. Examples: Glass fiber, polyester fiber, polyolefin fiber. This definition does not include tar paper, asphalt paper, or other paperboard materials or other products, such as rag felt, that are made out of waste and they do not represent a continuous and resistant base for a jacketing.

5.3.5 Rubber containing membranes are manufactured from combinations of layers of various rubber containing materials such as butyl rubber or rubberized bitumen with layers of other materials such as plastic films, metallic foils, reinforcing fabrics, or a combination thereof.

5.4 *Classifications used in jacketing specifications*—Each of the various ASTM specifications for jacketing contains a different classification system appropriate for that material. While each individual ASTM specification should be consulted for the details, the general outlines for each of these systems are shown below.

5.4.1 Specification **C1136** Flexible Low Permeance Vapor Retarders,

5.4.1.1 Classified into seven Types based on physical properties and structural requirements,

5.4.2 Specification **C1729** Aluminum Jacketing for Insulation,

5.4.2.1 Classified into four Types based on outer surface treatment and emittance,

5.4.2.2 Classified into six Grades based on aluminum alloy and temper,

5.4.2.3 Classified into four Classes based on type of moisture retarder,

5.4.3 Specification **C1767** Stainless Steel Jacketing for Insulation:

5.4.3.1 Classified into one Type based on outer surface treatment and emittance,

5.4.3.2 Classified into two Grades based on stainless steel alloy and temper, and

5.4.3.3 Classified into three Classes based on type of moisture retarder.

5.4.4 Specification **C1775** Laminate Protective Jacket and Tape for Use over Thermal Insulation for Outdoor Applications:

5.4.4.1 Classified into three Types based on several strength properties and peel adhesion, and

5.4.4.2 Classified into three Grades based on emittance.

6. Physical and Chemical Performance Considerations

6.1 This section includes a number of performance issues that should be considered when using this guide to select a jacketing material for thermal insulation. Some may not be applicable to the particular application. However, to be certain none are overlooked, the user should consider all materials initially and then eliminate those that are not applicable.

6.2 *Abuse Resistance*—Consideration should be given to the ability of a jacketing material to withstand a variety of physical conditions in excess of required functional design criteria. Prior to selection, consideration should be given to the expected intensity and types of abuse as well as the length of time the jacketing material is expected to withstand a given level of abuse.

6.2.1 *Abuse May Include the Following Factors:*

6.2.1.1 *Foot traffic*—Will people or equipment be applying loads directly on the jacketing material such as when piping is used like a ladder?

6.2.1.2 *Impact Resistance*—Is the jacketing material located where there is a probability of it being routinely struck by falling tools or other objects or being hit by traffic moving by?

6.2.1.3 *System Maintenance*—Does the system that the jacketing material is on require maintenance at regular intervals that would require the removal and reinstallation of the jacketing material?

6.2.1.4 *Puncture Resistance*—Is the jacketing material easily punctured? See **9.2.2**.

6.3 *Weather Resistance*—Consideration should be given to the ability of a jacketing system to be exposed outdoors without a significant loss of properties. Factors to consider in selection of the jacketing materials, that comprise the jacketing system, are the following.

6.3.1 Possible effects of precipitation, including rain, snow, sleet, hail, frost, and dew as appropriate for the use area.

6.3.2 Possible effect of ultra violet radiation from sunlight.

6.3.3 Maximum wind velocity.

6.3.4 Possibility of abrasion caused by blowing sand or salt.

6.3.5 Possible effect of high humidity or fog.

6.4 *Water Vapor Transmission (Vapor Retarding Capability)*—Consideration should be given to the ability of a jacketing material to inhibit transport of water vapor through it. Some factors to consider are the following:

6.4.1 Water vapor tends to travel from areas of high vapor pressure to areas of low vapor pressure. See **9.2.1**.

6.4.2 Water in insulation tends to reduce its efficiency. Therefore, if the system constantly runs above ambient it may be appropriate that the jacketing material or system will allow water vapor transmission. If the system constantly runs below

ambient then the jacketing material and system should retard the ingress of water vapor.

6.4.3 If a jacketing system is being used as a water vapor transmission retarder, particular care must be paid to the jacketing material's system of attachment so that any screw holes or other penetrations are vapor sealed. Vapor sealing of jacketing and butt joints must be thorough. In general, any penetrations or areas of discontinuity of the jacketing material must be vapor sealed to retard intrusion of ambient moisture vapor.

6.5 *External Corrosion Resistance*—Consideration should be given to whether corrosive chemicals might be present around the insulation jacketing system. Many types of corrosive atmospheres or corrosive chemical spills can corrode certain jacketing materials compromising insulation system performance.

6.6 *Internal Corrosion Resistance*—There are several types of internal corrosion. One is an electrical reaction that results from electrolysis between the metallic surface to be insulated and the inner metallic surface of the jacketing. The second is a chemical reaction between two dissimilar metals. With the insulation otherwise in direct contact with the jacketing and the presence of internal moisture in the insulation, consideration should be given to provide a suitable protective barrier on the jacket's interior surface to retard such corrosion. A third is a chemical reaction, that takes place in the presence of water that has condensed from moisture in the air, between a metal jacket and chemicals leached out of the insulation. See 9.2.13.

6.7 *Fungal Resistance*—Consideration should be given to the ability of a material to be exposed continuously to damp conditions without the growth of mildew or mold. See 9.2.6.

6.8 *Reusability*—Consideration should be given to the ease with which the jacketing material may be removed and reinstalled in its original condition.

6.9 *Aesthetics*—Consideration should be given to the general outward appearance of the jacketing material such that it harmonizes with the other facilities in the area or the environment.

6.10 *Color Identification*—Consideration should be given to the color of the jacketing materials for the purpose of identifying the fluid content, the temperature, or both, of each system being insulated.

6.11 *Surface Emittance*—Consideration should be given to the outer surface emittance, of the system being insulated, for the purpose of lowering surface temperatures for personnel protection. See Section 9.2.10.

6.12 *Surface Burning Characteristics*—For selection of the jacketing, consideration should be given to the surface burning characteristics as determined by Flame Spread/Smoke Developed Indices in accordance with Test Method E84 on the exterior jacket surface or, where required by code, the insulation system including the jacketing material. The purposes are generally to determine a comparative surface burning behavior of the jacket or insulation system or to meet codes or regulatory requirements that maintain specific, not to exceed, index requirements, or a combination thereof. See 9.2.4.

6.13 *Temperature Resistance*—Consideration should be given to the mechanical properties of the jacketing materials after exposure, for extended periods of time, to the expected in-service maximum and minimum temperature. See 9.2.9 and 9.2.13.

6.14 *Fire Resistance*—Consideration should be given to the ability of the jacketing materials or building elements that include the jacketing materials to resist the passage of flame, heat, or smoke when exposed to a time-temperature curve, for example, the standard curve contained in Test Method E119 while maintaining certain mechanical properties. Consideration might also be given to the strength to hold the insulation system in place during and/or after the fire test. See 9.2.17.

6.15 *Mechanical Strength*—Consideration should be given to the mechanical strength of the jacketing materials, in particular to its need to contain the weight of the insulation materials and to withstand seismic acceleration.

6.16 *Cleanability*—Consideration should be given to the ease with which the jacketing materials can be cleaned. See 9.2.11.

6.17 *Thermal Properties*—Consideration should be given to the thermal properties of the jacketing materials and their effect on skin contact temperature for the purpose of personnel protection. See 9.2.14. An example of this is the lower burn potential of cloth jacketing compared to metal jacketing.

6.18 *Thermal Expansion/Contraction Characteristics and Dimensional Stability*—Consideration should be given to the thermal expansion/contraction characteristics of the jacketing materials and their impact on the overall system dimensional stability. See 9.2.7 and 9.2.15.

6.19 *Acoustical Properties*—Consideration should be given to the requirements for sound reduction across the thermal insulation system. The acoustical properties of the insulation jacketing material, such as the Noise Reduction Coefficient, may need to be considered in its selection. See Test Method E596.

6.20 *Insulation Compressive Resistance*—Consideration should be given to the compressive resistance of the insulation (referred to as rigidity in some jacketing standards) under the jacketing and how this might influence the jacket thickness necessary. To prevent physical damage to the jacketing, in some cases, a greater jacket thickness may be necessary when applied over a lower compressive resistance insulation. See 9.2.18.

7. Typical Sizes and Forms

7.1 Jacketing materials are typically available for field or factory application in rolls, sheets, or preformed pressed pieces that are used on elbows and fittings. Jacketing standard dimensions vary based on the applicable ASTM material specification, if any, and with the thickness and shape of the jacketing. Consult the specific ASTM jacketing specification for the details on available dimensions.

7.2 Flexible low permeance vapor retarders (Specification C1136) are typically available in rolls with widths from 24 to

72 in. (0.61 to 1.83 m) and lengths from 150 to 3000 ft (46 to 914 m). The most commonly used width is 35.5 in. (0.90 m).

7.3 Metallic jacketing materials are available in either rolls or sheets. Roll widths are typically 3 or 4 ft (0.9 or 1.2m) and lengths typically 100 ft (30 m). Sheets intended for use on pipe insulation will typically have a width of 3 or 4 ft (0.9 or 1.2m) and a length equal to the insulation circumference plus a suitable overlap. See the applicable ASTM metal jacketing specification for more details on overlaps. Sheets intended for use on equipment or vessels will have widths that vary from 27.5 to 48 in. (0.70 to 1.22 m) depending on several factors including whether the sheet is flat, has deep corrugations, or has a box rib pattern. Sheets for equipment and vessels typically have a length that is 6 to 12 ft (1.8 to 3.7 m).

7.4 Laminate jacketing (Specification **C1775**) are typically available in rolls that are 75 or 150 ft (22.9 or 45.7 m) long and in either 23 or 35.5 in. (484 or 902 mm) width.

7.5 For jacketing materials for which an ASTM specification does not exist and where thickness, length, and width tolerances are required, they should be as agreed upon by the manufacturer and the purchaser.

7.6 Thickness of jacketing varies greatly, especially amongst the different kinds of materials, but even within any given material. For example, aluminum jacketing thickness can range, in accordance with Specification **C1729**, from 0.016 in. (0.4 mm) to 0.040 in. (1.0 mm). See the applicable ASTM jacketing specification, where it exists, for specifically required jacketing thickness. Where an ASTM specification does not exist, the thickness of jacketing should be agreed upon by the manufacturer and the purchaser. In general, as the curvature of the jacketing decreases, such as would occur on a cylindrical pipe or tank as the diameter of the object being insulated increased, the thickness of the jacketing required increases to achieve the same resistance to physical abuse and damage.

8. Workmanship and Finish

8.1 Consideration should be given to requiring that the product be free of laminate separations, holes, tears, cuts, or creases, and/or stains and discoloration, and that it show no visual defects that will reduce serviceability.

8.2 Acceptance of visual defects should be agreed upon by the manufacturer and purchaser.

9. Test and Evaluation Methods

9.1 Where ASTM specifications exist for a type of jacketing such as Specification **C1729** for aluminum jacketing, refer to that specification for the details on the required physical properties, test methods to be used, and any sampling requirements. The following subsections contain the properties that are specified and the test methods to be used in the various ASTM jacketing specifications.

9.1.1 Specification **C1136** Flexible Low Permeance Vapor Retarders:

9.1.1.1 Water vapor permeance in accordance with Test Method **E96/E96M**, Procedure A (desiccant method),

9.1.1.2 Surface burning characteristics in accordance with Test Method **E84**,

9.1.1.3 Tensile strength in machine and cross directions in accordance with Test Method **D882**,

9.1.1.4 Dimensional change in accordance with Test Method **D1204**,

9.1.1.5 Fungi growth resistance in accordance with Test Method **C1338**,

9.1.1.6 Thermal integrity in accordance with Test Method **C1263**,

9.1.1.7 *Bursting Strength*—Test Method given in **D774/D774M**,

9.1.1.8 Permanence of flame retardancy in accordance with Test Method TAPPI T461 for paper containing materials, and

9.1.1.9 Elevated temperature and humidity resistance in accordance with Test Method **C1258**.

9.1.2 Specification **C1729** Aluminum Jacketing for Insulation:

9.1.2.1 Thickness in accordance with Test Method ANSI H35.2/H35.2(M),

9.1.2.2 Surface burning characteristics in accordance with Test Method **E84**,

9.1.2.3 Total hemispherical emittance in accordance with Test Method **C1371** or **C835**,

9.1.2.4 Moisture barrier pinholes in accordance with Test Method **C1785**,

9.1.2.5 Moisture barrier water vapor transmission rate in accordance with Test Method **F1249**, and

9.1.2.6 Pencil hardness of painted surfaces in accordance with Test Method **D3363**.

9.1.3 Specification **C1767** Stainless Steel Jacketing for Insulation:

9.1.3.1 Thickness in accordance with Test Method ANSI H35.2/H35.2(M),

9.1.3.2 Surface burning characteristics in accordance with Test Method **E84**,

9.1.3.3 Total hemispherical emittance in accordance with Test Method **C1371** or **C835**,

9.1.3.4 Moisture barrier pinholes in accordance with Test Method **C1785**, and

9.1.3.5 Moisture barrier water vapor transmission rate in accordance with Test Method **F1249**.

9.1.4 Specification **C1775** Laminate Protective Jacket and Tape for Use over Thermal Insulation for Outdoor Applications:

9.1.4.1 Water vapor permeance in accordance with Test Method **E96/E96M**, Procedure B (water method) or **F1249**,

9.1.4.2 Puncture resistance in accordance with Test Method **D1000**,

9.1.4.3 *Bursting Strength*—Test Method given in **D774/D774M**,

9.1.4.4 Tensile strength in accordance with Test Method **D882** or **D3759/D3759M**,

9.1.4.5 Peel adhesion in accordance with Test Method **D3330/D3330M**, Method A,

9.1.4.6 Low and high temperature exposure in accordance with Test Method **C1263**,

9.1.4.7 Dimensional change in accordance with Test Method **D1204**,

9.1.4.8 Weather resistance in accordance with Practice **G154**, Cycle 1, 1000 hours exposure,

9.1.4.9 Water resistance,

9.1.4.10 Fungi growth resistance in accordance with Test Method **C1338**, and

9.1.4.11 Total hemispherical emittance in accordance with Test Method **C1371**.

9.2 Where no ASTM specification exists for a type of jacketing the properties enumerated in this guide can be determined using any method appropriate for the selected material but the following methods are recommended. Actual performance values can be selected by the user.

9.2.1 *Water Vapor Transmission*—Test Method **E96/E96M** and Test Method **F1249**.

9.2.2 *Bursting Strength*—Test Method given in **D774/D774M**.

9.2.3 *Tensile Strength*—Test Methods **D828** for paper products or Test Methods **D882** for plastic film properties.

9.2.4 *Surface Burning Characteristics*—Test Method **E84**. Obtain characteristics for the jacket, the insulation system including the jacket, or both.

9.2.5 *Leachability Resistance of Fire Retardant Additives (applicable to paper-containing products only)*—Test Method given in **C1136**.

9.2.6 *Fungal Resistance*—Test Method given in **C1338**.

9.2.7 *Dimensional Stability*—Test Method given in **C1136**, Section 10.4.

9.2.8 *Low-Temperature Resistance*—Test Method given in **C1263**.

9.2.9 *High-Temperature Resistance*—Test Method given in **C1263**.

9.2.10 *Total Hemispherical Emittance*—Test Method **C835** or Test Method **C1371**.

9.2.11 *Cleanability*—Test Method **C488** (for exposure) and then clean using a procedure agreed upon by the buyer and seller. Record any differences between a retained control and the exposed/cleaned samples.

9.2.12 *Flame Resistance of Treated Paper and Paperboard*—Test in accordance with TAPPI T461.

9.2.13 *Elevated Temperature and Humidity Resistance of Vapor Retarders for Insulation*—Test in accordance with Test Method **C1258**.

9.2.14 *Calculation of Skin contact Temperature*—Evaluate in accordance with Standard Practice **C1057**.

9.2.15 *Thermal Expansion/Contraction Characteristics*—for plastic materials, test in accordance with Test Method **D1204**.

9.2.16 *Material Compatibility*—There is no ASTM standard for evaluating this property for insulation jacketing materials.

9.2.17 *Fire Resistance*—test in accordance with Method **E119**.

9.2.18 *Compressive Resistance*—Test in accordance with Test Method **C165**.

10. Keywords

10.1 jacketing materials; metallic jacketing; nonmetallic jacketing; protective jacketing; self-supporting; thermal insulation; vapor retarder

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/