

Standard Test Method for Determining the Moisture Content of Organic and Inorganic Insulation Materials by Weight¹

This standard is issued under the fixed designation C1616; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method will determine the moisture content, as a percentage of the dry weight of organic and inorganic insulation materials.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

- C168 Terminology Relating to Thermal Insulation
- C302 Test Method for Density and Dimensions of Preformed Pipe-Covering-Type Thermal Insulation
- C303 Test Method for Dimensions and Density of Preformed Block and Board–Type Thermal Insulation
- C390 Practice for Sampling and Acceptance of Thermal Insulation Lots

3. Terminology

3.1 *Definitions*—For definitions used in this specification, see Terminology C168.

3.2 Symbols:

M = moisture content weight, percent

 W_I = initial specimen weight, lb (g)

 W_{MF} = moisture-free specimen weight (g) M, lb

4. Summary of Test Method

4.1 This test method is based upon weighing specimens of the insulation material and then drying the specimens by heating them in an oven to remove any moisture. Then the moisture content is determined using the calculation procedure in 9.1.

5. Significance and Use

5.1 Some insulation materials contain moisture, which will affect the thermal and other physical properties of the insulation.

6. Apparatus

6.1 Air-circulating Oven.

6.2 Scale (accurate to within 0.0011 lb (0.5 g).

7. Sampling and Test Specimen Preparation

7.1 *Test Specimen*—The test specimen shall be of a size that can be conveniently tested in a drying oven but not less than 72 cubic inches in volume such as 6 by 6 by 2 in. thick (150 by 150 by 51 mm).

8. Procedure

8.1 Four test specimens shall be tested. Cut or prepare the four specimens to meet the size requirements of 7.1.

8.2 Measure and record the specimens weight (W_l) immediately after the specimens are prepared to size. The specimens shall be weighed to the nearest 0.0011 lb (0.5 g).

8.3 Place the specimens in an air-circulating oven at a temperature specified in the material specification or at a temperature no higher than $230 \pm 10^{\circ}$ F ($110 \pm 6^{\circ}$ C) for a minimum of 2 h. Cool the specimens to room temperature in a desiccator and measure their weight. Repeat the process until successive weights agree to within 0.2 % of the specimen weight obtained in the latest weighing. Record these weights as moisture free weight (W_{MF}).

Note 1—When testing an insulation that contains multiple ingredients and one or more ingredients will dehydrate between the material specification upper temperature limit or above, the oven temperature can be lowered. The oven temperature will be adjusted based on the chemical the dehydrates at the lowest temperature.

¹ This test method is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.33 on Insulation Finishes and Moisture.

Current edition approved Sept. 1, 2012. Published November 2012. Originally approved in 2005. Last previous edition approved in 2007 as C1616–07. DOI: 10.1520/C1616-07R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

9. Calculation

9.1 Calculate the moisture content as follows:

$$M = 100 \left[\frac{\left(W_I - W_{MF} \right)}{W_{MF}} \right] \tag{1}$$

9.2 The value reported shall be the numerical average of the calculated moisture content of the four specimens rounded to the nearest 0.1 percent.

10. Report

10.1 Report the following information:

10.1.1 Complete sample identification including trade name, manufacturer, lot number and date of production, when known,

10.1.2 Date and time of test initiation,

10.1.3 Date and time of all weight determinations along with the weights,

10.1.4 Actual temperature used to dry the sample,

10.1.5 Time to reach steady dry weight, and

10.1.6 Report the results of all the specimens tested for each sample and the numerical average calculated in 9.2.

11. Precision and Bias

11.1 Precision and bias have not yet been determined but are being investigated. A precision and bias statement will be included when the proper data have been obtained and analyzed.

12. Keywords

12.1 inorganic insulation; insulation; moisture content; organic insulation; water; weight

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).