



# Standard Practice for Instrumental Transmittance Measurement of Color for Flat Glass, Coated and Uncoated<sup>1</sup>

This standard is issued under the fixed designation C1649; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This practice provides guidelines for the instrumental transmittance measurement of the color of coated and uncoated transparent glass. See Terminology [E284](#).

1.2 The practice specifically excludes fluorescent and iridescent samples.

1.3 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

2.1 *ASTM Standards:*<sup>2</sup>

[D2244](#) Practice for Calculation of Color Tolerances and Color Differences from Instrumentally Measured Color Coordinates

[E284](#) Terminology of Appearance

[E179](#) Guide for Selection of Geometric Conditions for Measurement of Reflection and Transmission Properties of Materials

[E308](#) Practice for Computing the Colors of Objects by Using the CIE System

[E1164](#) Practice for Obtaining Spectrometric Data for Object-Color Evaluation

[E1348](#) Test Method for Transmittance and Color by Spectrophotometry Using Hemispherical Geometry

<sup>1</sup> This practice is under the jurisdiction of ASTM Committee [C14](#) on Glass and Glass Products and is the direct responsibility of Subcommittee [C14.11](#) on Optical Properties.

Current edition approved May 1, 2014. Published May 2014. Originally approved in 2008. Last previous edition approved in 2008 as C1649 – 08. DOI: 10.1520/C1649-14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

2.2 *CIE Standard:*<sup>3</sup>

[CIE 15:2004](#) Colorimetry

## 3. Summary of Practice

3.1 The color of transparent glass is measured in the total transmittance mode on a CIE-conforming diffuse instrument. (See Guide [E179](#) and Test Method [E1348](#).) The glass color is expressed in CIE tristimulus values based on spectral transmittance measurements over the full CIE spectral range of 350 – 780 nm with a maximum 10-nm band pass. (See CIE 15:2004 and Practice [E308](#).) For color measurement, use of a truncated spectral range of 400 – 700 nm is acceptable. (See CIE 15:2004.) Further information on the UV absorbing characteristics of the glass or glass coating, or both, may be determined by examining the spectral data in the 350 – 400 nm range. If the instrument allows spectral measurement above 700 nm, useful information on the IR transmittance characteristics of the glass or glass coating may also be determined. If coatings are present, they are assumed to reflect and partially transmit light.

## 4. Significance and Use

4.1 Color measurement quantifies the transmitted color for glass. The user defines an acceptable range of color appropriate for the end use. A typical quality concern for transmittance color measurement of glass products is verification of lot-to-lot color consistency for end-user acceptance.

4.2 If the transmitted color of a glass product is consistent from lot-to-lot and within agreed supplier-buyer acceptance criteria, the product's color is expected to be consistent and acceptable for end-use.

## 5. Apparatus

5.1 For color measurements, a CIE-conforming diffuse sphere instrument capable of making transmission measurements in the total transmittance mode is required.

5.2 In addition, a device for mounting the glass sample flush at the transmission port is required.

<sup>3</sup> Available from CIE, Commission Internationale de L'Eclairage, Wien, Austria, [www.cie.co.at](http://www.cie.co.at).

5.3 The instrument and associated color quality software/firmware shall be capable of converting measured spectral transmittance data to CIE  $L^*$ ,  $a^*$ ,  $b^*$ ; Hunter  $L$ ,  $a$ ,  $b$ ; or  $Y$ ,  $x$ ,  $y$  values calculated for CIE illuminant D65 and the CIE 1964 10 degree standard observer. (See Practice E1164.) Any of those mappings will serve as a full numerical color descriptor. (See Practice E308.) CIE  $Y$  transmittance can also serve as an over-all indicator of transmission. For other illuminant/observer combinations, see Practice E308 for guidance in use. For effective communication of color values between sites, color measurements must be expressed in the same color scale, illuminant, and standard observer.

5.4 The expression of a color difference in terms of rectangular, polar, or elliptical color differences shall serve to quantify the difference between target product color and lot color. See Practice D2244.

## 6. Materials

6.1 Samples are uncoated or partially reflective coated transparent glass with defined substrate, coating compositions, and thicknesses.

## 7. Hazards

7.1 Consult Material Safety Data Sheets, and local regulations for all materials used in this practice.

## 8. Color Instrument Calibration and Set up Procedure

8.1 Prepare instrument for operation by following the instrument manufacturer's instructions.

8.2 Use instrument standardization to set the color instrument to the assigned values for the transmission standards supplied by the manufacturer or other suitable reference material.

8.3 To verify consistency over time in the performance of the color instrument, read and record color values of an instrument diagnostic standard (such as a color standard or didymium filter) at regular intervals. Care should be taken to visually inspect these standards for any significant visual abrasion and replace it if warranted.

8.4 As the stability characteristics of coated and un-coated glass are generally good, the user may, at their option, read and record color values for a coated glass sample to document consistency in the measurement method over time. Care should be taken to visually inspect the coated glass sample for any significant visual abrasion and replace it if warranted.

## 9. Measurement Method

9.1 Place the glass sample at the transmittance measurement port.

9.2 At a minimum, scan the sample over the range of wavelengths required for measurement. Two scans with a 90° rotation of the samples are preferable. If practical and possible, scan at least one other area of the sample as well.

9.3 *Correction for reflection loss of uncoated glass (optional):*

9.3.1 Because of historical practices, some industries apply a correction for reflection loss to the transmittance and others do not. As a result, specifications based on transmitted color measurements of glass may differ from industry segment to industry segment. Typically, the architectural glass industry does not use the correction, but the container glass industry does. The user of this document is advised to ascertain industry segment practices before deciding to apply or not apply the reflection correction.

9.3.2 When required by the respective glass industry, the correction is (See Appendix X1.):

$$T_{corrected} = k_T T_{measured} \quad (1)$$

Where:

$$k_T = \left[ \frac{2n_{air}n_{glass}}{(n_{air}^2 + n_{glass}^2)} \right]$$

## 10. Report

10.1 Report the following information:

10.1.1 Sample identification,

10.1.2 Color scale, illuminant, standard observer, instrument geometry and transmittance mode,

10.1.3 Sample preparation and presentation conditions, including number and pattern of readings averaged, and

10.1.4 Average color or color difference values, or both, relative to a product standard color to nearest hundredth of a unit.

NOTE 1—Sample preparation includes items of glass description such as the type and form (single layer versus multi-layer IG; laminated, pattern and thickness), as well as the surface preparation technique (cleaning method prior to measurement, polishing).

NOTE 2—Sample presentation includes any side or positional information; the area of view measured in each reading; the number of readings averaged and if readings were taken in a specific pattern.

10.1.5 The CIE  $Y$  value may also be reported to nearest hundredths of a unit, as an instrumental measurement of the overall transmittance of the transparent glass.

## 11. Keywords

11.1 coatings; color; glass; transmittance

## APPENDIX

### X1. REFLECTION LOSS CALCULATIONS

X1.1 Reflection loss,  $R$  at the sample surface is determined by the refractive indices:

$$R' = \left( \frac{n_{air} - n_{glass}}{n_{air} + n_{glass}} \right)^2 \quad (X1.1)$$

X1.2 Expressed as a correction factor for transmission:

$$k'_T = \frac{4n_{air}n_{glass}}{(n_{air} + n_{glass})^2} = 1 - R' \quad (X1.2)$$

X1.3 Because the glass sample has two reflecting surfaces, total reflection loss is:

$$R = \frac{2R'}{1 + R'} \quad (X1.3)$$

X1.4 As a result, the correction factor for transmission becomes:

$$k_T = \frac{2n_{air}n_{glass}}{n_{air}^2 + n_{air}^2} = 1 - R \quad (X1.4)$$

X1.5 Approximate refractive indices (relative to air) for some commercial glasses:<sup>4</sup>

|   |      |
|---|------|
| Containers and windows (soda-lime silica) | 1.52 |
| Laboratory ware (borosilicate)            | 1.47 |
| Other borosilicate                        | 1.48 |
| Fiber glass (E-glass)                     | 1.55 |
| High lead                                 | 1.54 |
| Fused silica                              | 1.45 |

---

<sup>4</sup> Handbook of Glass Properties, Bansal and Doremus, Editors, Chapters 1 and 2, Academic Press, 1986.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*