# Standard Specification for Unreinforced Autoclaved Aerated Concrete (AAC) Masonry Units<sup>1</sup>

This standard is issued under the fixed designation C1691; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

# 1. Scope\*

- 1.1 This specification covers solid, unreinforced masonry units manufactured from autoclaved aerated concrete (AAC), a cementitious product. This specification addresses dimensional tolerances, maximum limits for drying shrinkage, and shipping and handling.
- 1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.
- 1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

#### 2. Referenced Documents

2.1 ASTM Standards:<sup>2</sup>

C1232 Terminology of Masonry

C1693 Specification for Autoclaved Aerated Concrete (AAC)

## 3. Terminology

3.1 *Definitions*—Terms defined in Terminology C1232 shall apply in this specification.

### 4. Classification

4.1 AAC masonry units manufactured in accordance with this specification shall be classified according to their strength class.

#### 5. Materials and Manufacture

5.1 AAC masonry units manufactured in accordance with this specification shall be composed entirely of AAC material conforming to Specification C1693.

## 6. Physical Requirements

- 6.1 Compressive Strength—The compressive strength of the units shall be determined according to Specification C1693 and shall conform to the requirements of Specification C1693 for the strength class in which the units are classified.
- 6.2 Dry Bulk Density—The dry bulk density shall be determined according to Specification C1693 and shall conform to the requirements of Specification C1693 for the strength class in which the units are classified.
- 6.3 Drying Shrinkage—The drying shrinkage shall be determined in accordance with Specification C1693 and shall conform to the requirements of Specification C1693 for the strength class in which the units are specified.

#### 7. Dimensions and Permissible Variations

- 7.1 The specified dimensions of the units shall be established by the AAC unit manufacturer.
- 7.2 No overall unit dimension (width, height, or length) shall differ by more than ½ in. (3 mm) from the corresponding specified dimension

## 8. Visual Inspection

8.1 All units shall be sound and free of defects that would interfere with the proper placing of the unit or impair the strength or permanence of the construction. Minor imperfections incidental to the usual methods of manufacture, or resulting from customary methods of handling in shipment and delivery, shall not be deemed grounds for rejection.

## 9. Sampling and Testing

9.1 The purchaser or the authorized representative shall be accorded proper facilities to inspect and sample the units at the place of manufacture from the lots ready for delivery.

## 10. Rejection and Rehearing

10.1 If the shipment fails to conform to the specific requirements, the manufacturer shall be permitted to sort it, and new

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee C15 on Manufactured Masonry Units and is the direct responsibility of Subcommittee C15.10 on Autoclaved Aerated Concrete Masonry Units.

Current edition approved Dec. 1, 2011. Published December 2011. Originally approved in 2009. Last previous edition approved in 2009 as C1391 – 09. DOI: 10.1520/C1691-11.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



specimens shall be selected by the purchaser from the retained lot and tested. If the second set of specimens fails to conform to the test requirements, the entire lot shall be rejected.

Note 1—Unless otherwise specified in the purchase order, the cost of tests is typically borne as follows: If the results of the tests show that the units do not conform to the requirements of this specification, the cost is typically borne by the seller. If the results of the tests show that the units do conform to the requirements of this specification, the cost is typically borne by the purchaser.

## 11. Keywords

11.1 autoclaved aerated concrete (AAC); compressive strength; density; masonry units; shrinkage

#### SUMMARY OF CHANGES

Committee C15 has identified the location of selected changes to this standard since the last issue (C1691 – 09) that may impact the use of this standard. (Approved Dec. 1, 2011.)

(1) Deleted redundant definition of autoclaved aerated concrete from Section 3.

(2) Corrected typo ("manufacturer") in 10.1.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).