

Standard Test Methods for Non Metallic Plaster Bases (Lath) Used with Portland Cement Based Plaster in Vertical Wall Applications¹

This standard is issued under the fixed designation C1764; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 These test methods evaluate the performance of vertical wall applications of non metallic plaster bases used with Portland Cement Based Plaster under a variety of test exposures.

1.2 Units—The values stated in either SI units or inchpound units are to be regarded separately as standard. The values stated in each system may not be exact equivalents; therefore, each system shall be used independently of the other. Combining values from the two systems may result in nonconformance with the standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

- C926 Specification for Application of Portland Cement-Based Plaster
- E330 Test Method for Structural Performance of Exterior Windows, Doors, Skylights and Curtain Walls by Uniform Static Air Pressure Difference

E631 Terminology of Building Constructions

- E2098 Test Method for Determining Tensile Breaking Strength of Glass Fiber Reinforcing Mesh for Use in Class PB Exterior Insulation and Finish Systems (EIFS), after Exposure to a Sodium Hydroxide Solution
- 2.2 ICC-ES Acceptance Criteria:
- AC 191 Acceptance Criteria for Metal Plaster Bases (Lath)

3. Terminology

3.1 *Definitions*—For definitions of terms used in these test methods, refer to Terminology E631.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *non metallic, plaster base (lath)*—material used as a base for Portland Cement Based Plaster that is flat or self furred.

4. Significance and Use

4.1 General:

4.1.1 Non metallic reinforced Portland Cement Based Plaster are vertically applied exterior wall claddings that may be subject to variety of conditions over the claddings service life. The series of tests described in this standard evaluates performance under a variety of test conditions and exposures. Any given project may not be subject to all of the test conditions described herein and all of the test methods may not evaluate all exposures for a given project.

4.2 Transverse Load:

4.2.1 This test determines the ultimate wind load resistance of the wall assembly including influence of the framing, sheathing, and means of attachment.

4.3 Vertical Load:

4.3.1 The weight and attachment mechanism of Portland Cement Based Plaster results in a vertical load transfer to the plaster base. This test method determines the ultimate vertical load capacity of the cladding assembly based on taking the specimen to failure.

4.4 Embedment:

4.4.1 Plaster bases serve as a key, reinforcement and attachment mechanism for Portland Cement Based Plaster. The thickness, profile, and material properties of the plaster bases must be such that it is adequately embedded in the Portland Cement Based Plaster. This can be accomplished through use of a self furred non metallic plaster base or other means such as furring strips. This test procedure determines the effectiveness of the furring mechanism to ensure that the minimum embedment is obtained.

4.5 Fastener Pull Through Resistance:

¹ These test methods are under the jurisdiction of ASTM Committee C11 on Gypsum and Related Building Materials and Systems and is the direct responsibility of Subcommittee C11.02 on Specifications and Test Methods for Accessories and Related Products.

Current edition approved Sept. 1, 2016. Published September 2016. Originally approved in 2012. Last previous edition approved in 2012 as C1764 – 12. DOI: 10.1520/C1764-12R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

(1764 – 12 (2016)

4.5.1 The non metallic lath is secured to the building frame or substrate with fasteners. This test evaluates the fastener attachment effectiveness.

4.6 Alkali Resistance (Glass Fiber Lath Only): 4.6.1 Per E2098.

5. Sampling, Test Specimens, and Test Units

5.1 The number, size and configuration of the test specimens shall be as per each test procedure with the exception of Transverse Load tests which shall incorporate wood or steel framing as determined by the user. Samples shall be representative of standard products and construction methods.

6. Test Specimens

6.1 Transverse Load:

6.1.1 Construct three test specimens. Test specimen size shall be minimum 4 ft (1.2 m) by 8 ft (2.4 m) and constructed representative of end use conditions. Framing members shall be wood or steel as determined by the user. C926 Portland

Cement Based Plaster shall be mixed and applied in the configuration of the test specimen.

6.2 Vertical Load:

6.2.1 Construct three test frames measuring 12 inch (305 mm) by 20 inch (508 mm) using nominal 2 inch (50 mm) by 4 inch (100 mm) wood lumber with specific gravity of 0.42. The test frame shall have one intermediate stud with top and bottom plates and sheathed one side with 1/2 inch (13 mm) thick gypsum sheathing. Attach studs to plates using 2 16d $(3\frac{1}{2})$ inch (89 mm) length) nails and sheathing to framing using 6d (2 inch length) common nails or equal fastened 8 inches (200 mm) on center. A test panel shall be prepared measuring 6 inches (152 mm) high by 16 inches (406 mm) wide and consisting of a water-resistive barrier (provided to prevent adhesion of the test panel to the test frame); non metallic plaster base, which is attached through the water-resistive barrier to the intermediate framing member with one fastener; and apply Portland Cement Based Plaster per C926. The samples shall be cured a minimum of 28 days. Refer to Fig. 1



FIG. 1 Test Assembly

for an illustration of the test assembly.

6.3 *Embedment*:

6.3.1 Construct one test frame using nominal 2 inch (50 mm) by 4 inch (100 mm) wood lumber with specific gravity of 0.42 unless specified otherwise by the manufacturer. The test frame shall be 48 inches (1.2 m) wide and high studs spaced 16 inches (406 mm) on center, wood plates top and bottom and sheathed with minimum $\frac{1}{2}$ inch (13 mm) thick wood based sheathing. Two layers of a water resistive barrier shall be attached to the sheathing using staples 12 inches (305 mm) on center around the panel perimeter. A plaster stop or grounds shall be fastened around the panel perimeter. Apply the non metallic lath to the sample with one horizontal lap and fastened to the stud per the manufacturers recommendations. Apply the scratch and brown Portland Cement Based Plaster per C926.

6.4 Fastener Pull Through Resistance:

6.4.1 Construct five test frames using nominal 2 inch (50 mm) by 4 inch (100 mm) wood framing with specific gravity of 0.42 and any other types of framing as specified by the non metallic lath manufacturer. The test frame shall be 12 inches (305 mm) wide and sufficient height to permit placement of three or more lath fasteners. One stud centered in the panel and sheathed one side with $\frac{1}{2}$ inch (13 mm) thick gypsum sheathing. Two layers of a water resistive barrier shall be attached to the sheathing using staples 12 inches (305 mm) on center around the panel perimeter. A plaster stop or grounds shall be fastened around the panel perimeter. Apply the lath to the sample with one horizontal lap and fastened to the stud per the manufacturers recommendations. Apply the Portland Cement Based Plaster per C926. Allow the stucco to cure and remove the sheathing that exists between the wood framing.

6.5 Alkali Resistance (Glass Fiber Lath Only):

6.5.1 Ten specimens in the warp and ten specimens in the weft directions should be cut from the roll glass fiber lath and labeled as control specimens. Ten specimens in the warp and ten specimens in the weft directions should be cut from the roll glass fiber lath and labeled as conditioned specimens. All specimens were 2 (50 mm) inch wide by 12 (305 mm) inch long.

7. Apparatus

7.1 The description of apparatus in this section is general in nature consequently any set up capable of performing the test is acceptable.

7.2 Transverse Load:

7.2.1 The apparatus shall be capable of subjecting specimen uniformly to test conditions described in Test Method E330 Procedure A.

7.3 Vertical Load:

7.3.1 Universal testing machine with capabilities to accommodate section 9.2.1.

7.4 Fastener Pull Through Resistance:

7.4.1 Universal testing machine with capabilities to accommodate section 9.4.1.

7.5 Alkali Resistance (Glass Fiber Lath Only):

7.5.1 The apparatus shall be capable of subjecting specimen uniformly to test conditions described in Test Method E2098.

8. Conditioning

8.1 Transverse Load:

8.1.1 Cure test specimens 28 days under ambient conditions prior to testing.

8.2 Vertical Load:

8.2.1 Cure test specimens 28 days under ambient conditions prior to testing.

8.3 Embedment:

8.3.1 Cure test specimens 28 days under ambient conditions prior to testing.

8.4 Fastener Pull Through Resistance:

8.4.1 Cure test specimens 28 days under ambient conditions prior to testing.

8.5 Alkali Resistance (Glass Fiber Lath Only):

8.5.1 In accordance with Test Method E2098.

9. Procedure

9.1 Transverse Load:

9.1.1 In accordance with Test Method E330 Procedure A. Terminate test when specified pressure can not be maintained due to failure of the test specimen.

9.2 Vertical Load:

9.2.1 Apply vertical, downward load uniformly across entire width of specimen, at a rate of one inch/minute until failure using a universal testing machine. Record deflection, results and failure mechanism.

9.3 Embedment:

9.3.1 Cut the test panel diagonally from the intersection of the top stud to the intersection of the bottom stud such that the cross section of the Portland Cement Plaster is visible. Measure each strand with respect to its embedment in the Portland Cement Plaster. Make all from the back plane of the non metallic lath to the back plane of the plaster.

9.4 Fastener Pull Through:

9.4.1 Place center stud in a rigid jig to assure each fastener will receive equivalent loads. Apply load in tension by pulling the center stud away from the plaster surface uniformly using a universal testing machine, at a rate of two inches/minute until failure. Record results and failure mechanism.

9.5 Alkali Resistance (Glass Fiber Lath Only):

9.5.1 In accordance with Test Method E2098.

10. Report

10.1 Reports shall include the following information:

10.1.1 Name, address and telephone number of the laboratory.

10.1.2 Date of test, date of report, and test report identification number.

10.1.3 Reference to the test standard including any deviations.

10.1.4 Description and identification of the non metallic lath sample including manufacturer, type and thickness of the

C1764 – 12 (2016)

stucco, construction details, dimensions, framing, sheathing, application instruction and other pertinent information needed to describe the specimens.

10.1.5 Specifics required by the standard including ambient conditions, photographs, illustrations, and calculations.

10.1.6 Test reports shall be signed and include observations, failure mode, as well as conclusions.

11. Precision and Bias

11.1 Neither the precision nor bias of the test methods in this standard have been determined.

12. Keywords

12.1 lath; non metallic plaster base; portland cement based plaster

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/