



# Standard Specification for Finishing Hydrated Lime<sup>1</sup>

This standard is issued under the fixed designation C206; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

## 1. Scope\*

1.1 This specification covers two types of finishing hydrated lime that are suitable for use in the scratch, brown, and finish coats of plaster, for stucco, for mortar, and as an addition to portland-cement concrete. The two types of lime sold under this specification shall be designated as follows:

1.1.1 *Type N*—Normal hydrated lime for finishing purposes, and

1.1.2 *Type S*—Special hydrated lime for finishing purposes.

NOTE 1—Type N, normal finishing hydrated lime, is differentiated from Type S, special finishing hydrated lime, in that no limitation on the amount of unhydrated oxides is specified for Type N hydrate, and the plasticity requirement for Type N hydrate shall be determined after soaking for 16 to 24 h.

NOTE 2—For lime putty, refer to Specification C1489.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

C25 Test Methods for Chemical Analysis of Limestone, Quicklime, and Hydrated Lime

C50 Practice for Sampling, Sample Preparation, Packaging, and Marking of Lime and Limestone Products

C51 Terminology Relating to Lime and Limestone (as used by the Industry)

C110 Test Methods for Physical Testing of Quicklime, Hydrated Lime, and Limestone

C842 Specification for Application of Interior Gypsum Plaster

C1271 Test Method for X-ray Spectrometric Analysis of

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C07 on Lime and Limestone and is the direct responsibility of Subcommittee C07.02 on Specifications and Guidelines.

Current edition approved Dec. 1, 2014. Published December 2014. Originally approved in 1946. Replaces C6 – 49 (1974). Last previous edition approved in 2009 as C206 – 03 (2009). DOI: 10.1520/C0206-14.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

## Lime and Limestone

C1301 Test Method for Major and Trace Elements in Limestone and Lime by Inductively Coupled Plasma-Atomic Emission Spectroscopy (ICP) and Atomic Absorption (AA)

C1489 Specification for Lime Putty for Structural Purposes

## 3. Terminology

3.1 *Definitions*—For definitions of terms relating to hydrated lime, refer to Terminology C51.

## 4. Chemical Composition

4.1 Hydrated lime for finishing purposes shall conform to the following requirements as to chemical composition:

	Type N 95	Type S 95
Calcium and magnesium oxides (LOI-free basis), min, %		
Carbon dioxide (as-received basis), max, %		
If sample is taken at the place of manufacture	5	5
If sample is taken at any other place	7	7
Unhydrated oxides (as-received basis), max, %	...	8

## 5. Residue

5.1 The percentage residue of finishing hydrated lime shall conform to the following requirements:

Residue retained on 600-μm (No. 30) sieve, max, %	0.5
Residue retained on 75-μm (No. 200) sieve, max, %	15

## 6. Popping and Pitting

6.1 Finishing hydrated lime shall show no pops or pits when tested in accordance with the method prescribed in 10.1.2.

## 7. Plasticity

7.1 The putty made from Type N, normal finishing hydrated lime, shall have a plasticity figure of not less than 200 when soaked for a period of not less than 16 h nor more than 24 h.

7.2 The putty made from Type S, special finishing hydrated lime, shall have a plasticity figure of not less than 200 when tested commencing within 30 min after mixing with water.

## 8. Application of Interior Gypsum Plaster

8.1 For recommended application procedures refer to Specification C842.

\*A Summary of Changes section appears at the end of this standard

**9. Sampling, Inspection, and so forth**

9.1 The sampling, inspection, rejection, retesting, packing, and marking shall be conducted in accordance with Methods **C50**.

**10. Test Methods**

10.1 The properties enumerated in this specification shall be determined in accordance with the following methods:

10.1.1 *Chemical Analysis*—Test Methods **C25** or, for total calcium and magnesium oxides, Test Methods **C1271** or **C1301**.

10.1.2 *Physical Tests*—Test Methods **C110**.

**11. Package Marking**

11.1 Type N hydrated lime, in bags, conforming to this specification, shall be soaked for a minimum of 16 h prior to use.

**12. Keywords**

12.1 finishing lime; masonry; plaster; plasticity; popping and pitting; residue; Type N; Type S; unhydrated oxides

**SUMMARY OF CHANGES**

Committee **C07.02** has identified the location of selected changes to this standard since the last issue (C206 – 03 (2009)) that may impact the use of this standard. (Approved Dec. 1, 2014.)

(1) Added Test Methods **C1271** and **C1301** to Section 2.

(2) Revised **4.1**, **5.1**, and **10.1.1**.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or [service@astm.org](mailto:service@astm.org) (e-mail); or through the ASTM website ([www.astm.org](http://www.astm.org)). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>*