



Standard Specification for Clay Flue Liners and Chimney Pots¹

This standard is issued under the fixed designation C315; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This specification establishes the criteria for acceptance, prior to installation, of clay flue liners and chimney pots used for conveying hot gases in masonry chimneys.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 For installation of clay flue liners, see Practice C1283.

2. Referenced Documents

2.1 *ASTM Standards*:²

C67 Test Methods for Sampling and Testing Brick and Structural Clay Tile

C301 Test Methods for Vitrified Clay Pipe

C896 Terminology Relating to Clay Products

C1283 Practice for Installing Clay Flue Lining

3. Terminology

3.1 *Definitions*:

3.1.1 Clay, fire clay, shale, and surface clay are as defined in Terminology C896.

3.1.2 *chimney pot*—a pipe used at the top of the chimney to increase draft and carry off smoke.

4. Classification

4.1 *Types*—Flue liners acceptable under this specification shall be designated as rectangular nonmodular, rectangular modular, round or oval.

5. Materials and Manufacture

5.1 Flue liners and chimney pots shall be manufactured from fire clay, shale, surface clay, or a combination of these

materials that when formed and fired to suitable temperatures, shall yield a product that is strong, durable, serviceable, and conforms to this specification.

6. Physical and Chemical Requirements

6.1 *Absorption*:

6.1.1 The absorption of clay flue liners and chimney pots shall not exceed 8.0 % when tested in accordance with Test Methods C301.

6.1.2 *Test Specimens*—Five dry test specimens shall be obtained from the five flue liners or chimney pots to be tested and shall measure as closely as possible to 4 by 4 in. (100 by 100 mm) per side. All rough edges shall be ground off and loose particles removed.

6.1.3 If any of the test specimens fail to meet the requirements, the manufacturer shall be allowed to retest on two additional specimens for each one that failed. The flues and pots will be acceptable if all the subsequent specimens for retest meet the requirements.

6.2 *Acid Resistance*:

6.2.1 This is a test used to determine the resistance of clay flue liners and chimney pots to the action of acids encountered in chimneys. This test shall be performed only when specified.

6.2.2 The flue liner and chimney pots shall be acceptable if the acid soluble material does not exceed 0.25 % when tested in accordance with Test Methods C301.

6.2.3 *Test Specimens*—Select one test specimen from each size of flue liner or chimney pot. The specimens shall measure about 2 by 2 in. (51 by 51 mm) per side and weigh not more than 200 g. They shall be sound pieces with all edges freshly broken, free of cracks or shattered edges, and shall be thoroughly cleaned.

6.3 *Freeze-Thaw Cycle Test*:

6.3.1 When flue liners or chimney pots are tested in accordance with Test Methods C67, Section 9 on structural clay tile, there shall be no breakage and the percentage of weight loss shall not exceed 0.5 %.

6.3.2 *Test Specimens*—Five dry test specimens shall be obtained from the five flue liners or chimney pots to be tested and shall measure as closely as possible to 4 by 4 in. (100 by 100 mm) per side. All rough edges shall be ground off and loose particles removed.

¹ This specification is under the jurisdiction of ASTM Committee C04 on Vitrified Clay Pipe and is the direct responsibility of Subcommittee C04.20 on Methods of Test and Specifications.

Current edition approved Nov. 1, 2016. Published November 2016. Originally approved in 1953. Last previous edition approved in 2011 as C315 – 07(2011). DOI: 10.1520/C0315-07R16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.



7. Sizes and Dimensions

7.1 Flue liners shall be specified and furnished in the dimensions prescribed in **Tables 1-4**. When other sizes are required, flue liners that meet the requirements of Sections 5 and 6 shall be cut and installed in the chimney.

7.2 Variations in dimensions in **Tables 1-4** shall not exceed $\pm 1/2$ in. (± 13 mm) for outside dimensions. Permissible wall thickness variation is $\pm 1/8$ in. (± 3 mm) for all flue liners, except that there shall be no limit for plus variation in round flue liners. Variations in dimensions of round flue lining shall not exceed those shown in **Table 3**. The maximum difference in the diagonal dimensions of rectangular modular flue liners shall not exceed $1/2$ in. (13 mm) for sizes up to and including 12 by 12 in. (305 by 305 mm) and $3/4$ in. (19 mm) for larger sizes.

7.3 Dimensions in **Tables 1-4** are not to be used to determine the effective area of the flue liner. Consult manufacturer or use actual measurements to determine effective areas of the liners for sizing purposes.

7.4 Flue liners are available in various lengths. The variation in length shall not exceed $\pm 1/4$ in./ft (± 21 mm/m). The maximum difference in length of the opposite sides of flue liners shall not exceed $1/4$ in./ft (21 mm/m) of length.

8. Workmanship, Finish, and Appearance

8.1 Flue liners and chimney pots shall be well burned and substantially free of laminations.

8.2 Blisters shall not exceed 3 in. (76 mm) in diameter, and blisters or pimples shall not project more than $1/8$ in. (3 mm) above the surface, in sizes up to and including $17\frac{3}{4}$ by $17\frac{3}{4}$ in. (450 by 450 mm). For larger sizes, blisters shall not exceed 4 in. (100 mm) in diameter nor project more than $1/2$ in. (13 mm) above the surface.

8.3 Chips shall not exceed 2 in. (51 mm) in length, 2 in. (51 mm) in width, and a depth of more than one half the wall thickness.

9. Inspection

9.1 Inspection of the material shall be agreed upon by the purchaser and supplier as part of the purchase contract and shall be performed by a competent inspector employed by the purchaser. Inspection shall be made at the factory or promptly

TABLE 2 Rectangular Modular Clay Flue Liners—Standard Dimensions

Outside Dimensions, in. (mm)	Nominal Wall Thickness, in. (mm)	Outside Corner Radius, max., in. (mm)
3½ by 7½ (90 by 190)	⅝ (16)	1 (25)
3½ by 11½ (90 by 290)	⅝ (16)	1 (25)
7½ by 7½ (190 by 190)	⅝ (16)	2 (51)
7½ by 11½ (190 by 290)	¾ (19)	2 (51)
11½ by 11½ (290 by 290)	⅞ (22)	3 (76)
11½ by 15½ (290 by 395)	1 (25)	3 (76)
15½ by 15½ (395 by 395)	1⅛ (29)	4 (100)
15½ by 19½ (395 by 495)	1¼ (32)	4 (100)
19½ by 19½ (495 by 495)	1⅝ (35)	5 (130)
19½ by 23½ (495 by 595)	1½ (38)	5 (130)
23½ by 23½ (595 by 595)	1⅝ (41)	6 (150)

TABLE 3 Round Clay Flue Liners—Standard Dimensions

Nominal Inside Diameter, in. (mm)	Permissible Variation in Inside Diameter, \pm in. \pm (mm)	Nominal Wall Thickness, in. (mm)
6 (150)	¼ (6)	⅝ (16)
7 (180)	¼ (6)	¾ (19)
8 (205)	¼ (6)	¾ (19)
10 (255)	⅝ (8)	⅞ (22)
10¾ (275)	⅝ (10)	1 (25)
12 (305)	⅝ (10)	1 (25)
15 (380)	⅝ (10)	1⅛ (29)
18 (455)	⅞ (11)	1¼ (32)
21 (535)	⅞ (11)	1⅝ (41)
24 (610)	½ (13)	1⅝ (41)
27 (685)	⅞ (14)	2 (51)
30 (760)	⅝ (16)	2⅛ (54)
33 (840)	1⅛ (17)	2¼ (57)
36 (915)	1¼ (32)	2½ (64)

TABLE 4 Oval Clay Flue Liners—Standard Dimensions

Outside Dimensions, in. (mm)	Nominal Wall Thickness, in. (mm)	Nominal Outside Corner Radius, in. (mm)
8½ by 12¾ (215 by 325)	¾ (19)	4¼ (110)
8½ by 16¾ (215 by 425)	1 (25)	4¼ (110)
10 by 17¾ (255 by 450)	1 (25)	5 (130)
12¾ by 16¾ (325 by 425)	1 (25)	6⅝ (160)
12¾ by 21 (325 by 535)	1⅛ (29)	6⅝ (160)
16¾ by 16¾ (425 by 425)	1 (25)	6⅝ (160)
16¾ by 21 (425 by 535)	1⅜ (30)	6⅝ (160)
21 by 21 (535 by 535)	1¼ (32)	6⅝ (160)

at the point of delivery. All flue liners and chimney pots accepted shall be plainly marked by the inspector. Rejected flue liners and chimney pots shall not be defaced but shall be replaced by the manufacturer or seller, without additional cost, with flue liners and chimney pots that meet the requirements of this specification.

10. Product Marking

10.1 Flue liners and chimney pots furnished under this specification shall be marked on the material with the name, brand, or trademark of the manufacturer and ASTM C315. Such marking may be indented into the surface of the material during manufacturing.

11. Keywords

11.1 chimney; chimney pot; clay; flue; flue liners; masonry; venting; vitrified

TABLE 1 Rectangular Nonmodular Clay Flue Liners—Standard Dimensions

Outside Dimensions, in. (mm)	Nominal Wall Thickness, in. (mm)	Outside Corner Radius Max., in. (mm)
4½ by 8½ (115 by 215)	⅝ (16)	1 (25)
4½ by 13 (115 by 330)	¾ (19)	1 (25)
8½ by 8½ (215 by 215)	¾ (19)	2 (51)
8½ by 13 (215 by 330)	⅞ (22)	2 (51)
8½ by 17¾ (215 by 450)	1 (25)	2 (51)
13 by 13 (330 by 330)	⅞ (22)	3 (76)
13 by 17¾ (330 by 450)	1 (25)	4 (100)
17¾ by 17¾ (450 by 450)	1¼ (32)	4 (100)
20 by 20 (510 by 510)	1⅝ (35)	5 (130)
20 by 24 (510 by 610)	1½ (38)	5 (130)
24 by 24 (610 by 610)	1⅝ (41)	6 (150)

SUPPLEMENTARY REQUIREMENTS

These requirements apply only to Federal/Military procurement, not domestic sales or transfers.

S1. Government/Military Procurement

S1.1 Responsibility for Inspection—Unless otherwise specified in the contract or purchase order, the producer is responsible for the performance of all inspection and test requirements specified herein. The producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless the purchaser disapproves. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to ensure that material conforms to prescribed requirements.

NOTE S1.1—In U.S. Federal contracts, the contractor is responsible for inspection.

S2. Packaging and Marking for U.S. Government Procurement:

S2.1 Packaging—Unless otherwise specified in the contract, the materials shall be packaged in accordance with the supplier's standard practice in a manner ensuring arrival at destination in satisfactory condition and which will be acceptable to the carrier at lowest rates. Containers and packing shall comply with Uniform Freight Classification rules or National Motor Freight Classification rules.

S2.2 Marking—Marking for shipment shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for military agencies.

NOTE S2.1—The inclusion of U.S. Government procurement requirements should not be construed as an indication that the U.S. Government uses or endorses the products described in this document.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>