



Standard Practice for Use of Chemically Setting Chemical-Resistant Silicate and Silica Mortars¹

This standard is issued under the fixed designation C397; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice provides information for the proper storage, mixing, and use of chemically setting silicate and silica mortars for bonding chemical-resistant brick or tile in order to obtain the optimum chemical resistance and physical strength of the mortar.

1.2 This practice does not apply to the air-setting type of silicate and silica chemical-resistant mortars.

1.3 Chemical-resistant brick or tile conforming to Specifications C279, C410, or C980 are considered satisfactory for use with these mortars.

NOTE 1—For specifications for mortars covered by this practice, see Specification C466.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

C267 Test Methods for Chemical Resistance of Mortars, Grouts, and Monolithic Surfacing and Polymer Concretes
C279 Specification for Chemical-Resistant Masonry Units
C410 Specification for Industrial Floor Brick
C414 Test Method for Working, Setting, and Service Strength Setting Times of Chemically Setting Chemical-

Resistant Silicate and Silica Mortars

C466 Specification for Chemically Setting Silicate and Silica Chemical-Resistant Mortars

C904 Terminology Relating to Chemical-Resistant Nonmetallic Materials

C980 Specification for Industrial Chimney Lining Brick

3. Terminology

3.1 For definitions of terms used in this practice, see Terminology C904.

4. Shipment and Storage

4.1 The powder shall be protected from water during shipment and storage. Powder that has become wet shall be discarded.

4.2 The liquid binder shall be protected from freezing during shipment and storage. In the event that any containers of liquid have ruptured, they shall be discarded.

4.3 In the event that silica sols freeze, they must be discarded. In the event that silicates freeze, they may be restored by warming and thorough stirring until a uniform solution results. Consult the manufacturer for recommendations.

5. Installation Conditions

5.1 Silicate and silica mortars shall be applied when the powder, binder or water, brick or tile, substrate and ambient air temperatures are all between 50°F (10°C) and 90°F (32°C). For temperatures outside this range, consult the manufacturer for recommendations.

5.2 The brick or tile and substrate shall be clean and dry during installation.

6. Mixing and Application

6.1 Use the proportions of powder to binder or potable water recommended by the manufacturer. Weigh the powder and binder or potable water into separate containers according to the recommended ratio. Liquid and powder levels may then be marked so that future measurements may be made by volume.

6.1.1 The optimum properties may vary due to temperature. The mortar should be sufficiently stiff for the brick or tile to

¹ This practice is under the jurisdiction of ASTM Committee C03 on Chemical-Resistant Nonmetallic Materials and is the direct responsibility of Subcommittee C03.02 on Monolithics, Grouts and Polymer Concretes.

Current edition approved Aug. 1, 2012. Published September 2012. Originally approved in 1957. Last previous edition approved in 2005 as C397-00 (2005). DOI: 10.1520/C0397-00R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

retain its position without slipping or sliding or without sagging out of the joint.

6.2 Using a clean mortar pan or other suitable container, add approximately three fourths of the powder to the liquid and mix with hoe, trowel, or power mixer until all of the powder has been wetted. Add the remainder of the powder to the mix and continue mixing to a proper mortar consistency.

6.3 Mix only as much mortar as can be used during its working time. Since the working time depends on the temperature, the batch size shall be determined on the job site if data are not available from the manufacturer.

6.4 Mortar that has begun to set shall not be altered by adding binder or water. Remove mortar that has begun to set from the mortar pan, and discard it before preparing fresh batches.

6.5 No additives, such as portland cement shall be added to the mortar. Silica sand or other materials shall not be added unless recommended by the manufacturer, and then only in a quantity and quality specified by the manufacturer.

6.6 Apply the mortar to the brick or tile in a manner consistent with good workmanship. Butter the surface to fully cover, leaving a slight mound of mortar in the center of the brick face. Strike the mounded mortar toward each edge to ensure full contact. Tap the brick or tile firmly into position so that the joints are of the width recommended by the design engineer or the manufacturer and mortar is extruded from all joints. Strike extruded mortar off the faces of the brick or tile with a trowel. Chemical-resistant brickwork joints should be as narrow as good workmanship and uniformity of the brick or tile will permit (preferably less than $\frac{1}{8}$ in. (3 mm)).

7. Acid Washing

7.1 If acid washing is recommended by the manufacturer, it shall be carried out in accordance with his directions.

8. Curing

8.1 The time interval between the bonding of the brick or tile and the time the structure can be put into service shall be that recommended by the manufacturer. Test Method C414 is recommended for use in the determination of time to put into service.

8.2 The installation shall be protected from moisture in all forms, and mechanical damage, for the period of time recommended by the manufacturer.

9. Chemical Resistance

9.1 Sodium and potassium silicate, and silica mortars are resistant to most acids (except those containing fluorine).

9.1.1 Exposure of silicate and silica mortars to water, boiling water, or neutral salt solutions may be detrimental. Consult the manufacturer for recommendations.

9.1.2 Silicate and silica mortars are generally not resistant to alkalis.

9.2 Under certain conditions crystal formation can occur in silicate mortars. If the crystals are growth salts, they can damage the joints.

9.3 Chemical resistance to specific chemical media may be determined in accordance with Test Method C267.

9.4 Consult the manufacturer regarding service conditions and selection of either sodium or potassium silicate, or silica mortars.

10. Temperature Resistance

10.1 Consult the manufacturer regarding the temperature resistance of a specific mortar.

11. Keywords

11.1 chemical-resistant; masonry units; mortars; silica; silicate

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).