



# Standard Specification for Compression Joints for Vitrified Clay Pipe and Fittings<sup>1</sup>

This standard is issued under the fixed designation C425; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

## 1. Scope

1.1 This specification covers materials and test requirements for compression joints for vitrified clay pipe and fittings. See Specification C700 for pipe specifications. The test requirements are applicable to pipe joint assemblies prior to field installation of pipe.

NOTE 1—Install pipe in accordance with Practice C12.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 The following precautionary caveat pertains only to the Test Requirements portion, Section 7, of this standard. *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:<sup>2</sup>

- A167 Specification for Stainless and Heat-Resisting Chromium-Nickel Steel Plate, Sheet, and Strip
- A240/A240M Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications
- C12 Practice for Installing Vitrified Clay Pipe Lines
- C700 Specification for Vitrified Clay Pipe, Extra Strength, Standard Strength, and Perforated
- C896 Terminology Relating to Clay Products
- D395 Test Methods for Rubber Property—Compression Set
- D412 Test Methods for Vulcanized Rubber and Thermoplastic

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C04 on Vitrified Clay Pipe and is the direct responsibility of Subcommittee C04.20 on Methods of Test and Specifications.

Current edition approved Dec. 1, 2013. Published December 2013. Originally approved in 1958. Last previous edition approved in 2009 as C425 – 04(2009). DOI: 10.1520/C0425-04R13.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

tic Elastomers—Tension

- D471 Test Method for Rubber Property—Effect of Liquids
- D518 Test Method for Rubber Deterioration—Surface Cracking (Withdrawn 2007)<sup>3</sup>
- D543 Practices for Evaluating the Resistance of Plastics to Chemical Reagents
- D573 Test Method for Rubber—Deterioration in an Air Oven
- D583 Methods of Test for Water Resistance of Textile Fabrics (Withdrawn 1971)<sup>3</sup>
- D1149 Test Methods for Rubber Deterioration—Cracking in an Ozone Controlled Environment
- D1566 Terminology Relating to Rubber
- D2240 Test Method for Rubber Property—Durometer Hardness

## 3. Terminology

3.1 *Definitions*—Terms relating to plastics and rubber shall be as defined in Terminologies D583 and D1566, respectively.

3.2 Terminology C896 can be used for clarification of terminology in this specification.

## 4. Principles of Joint Design

4.1 Sealing elements shall be compressed between bearing surfaces to assure watertight integrity as required in Section 7.

4.2 Sealing elements shall either be bonded to bearing surfaces or be independent elements.

## 5. Materials and Manufacture

5.1 Rubber ring-sealing elements shall conform to the requirements of Table 1.

5.2 Rubber for other than ring-sealing elements shall conform to the requirements of Table 2.

5.3 Plastic components shall conform to the requirements of Table 3.

5.4 Metallic components shall be of corrosion-resistant metal conforming to Specifications A167 and A240/A240M.

<sup>3</sup> The last approved version of this historical standard is referenced on [www.astm.org](http://www.astm.org).

**TABLE 1 Tests for Rubber—Ring-Sealing Elements**

NOTE 1—Except for the water absorption test (Test Method **D471**), the tests shall be run on specimens cut from rubber test slabs representative of the finished product.

Test	Test Requirement	ASTM Standard
Chemical resistance: 1N sulfuric acid 1N hydrochloric acid	no weight loss no weight loss	<b>D543</b> (48 h at 23 ± 2°C)
Tensile strength	1500 psi (10.4 MPa) min; 500 % min elongation at break	<b>D412</b>
Hardness	Shore A durometer 35 min to 50 max	<b>D2240</b>
Compression set	16 % max of original deflection	<b>D395</b> , Method B (22 h at 70 ± 2°C)
Water absorption	5 % max	<b>D471</b> —Immerse a 2-in. (51-mm) long section cut from a rubber-sealing element in distilled water for 7 days at 70 ± 2°C
Ozone resistance	no visible cracking under 2× specimen magnification using <b>D518</b> , Procedure B, stretched 20 % and exposed to ozone concentrations of 0.5 ppm for 24 h at 40 ± 1°C	<b>D1149</b>
Accelerated oven aging	80 % min of original tensile strength 75 % min of original elongation	<b>D573</b> (7 days at 70 ± 2°C)

**TABLE 2 Tests for Rubber—Other than Ring-Sealing Elements**

NOTE 1—Except for the water absorption test (Test Method **D471**), the tests shall be run on specimens cut from rubber test slabs representative of the finished product.

Test	Test Requirements	ASTM Standard
Chemical resistance: 1N sulfuric acid 1N hydrochloric acid	no weight loss no weight loss	<b>D543</b> (48 h at 23 ± 2°C)
Tensile strength	1000 psi (6.9 MPa) min; 250 % min elongation at break	<b>D412</b>
Hardness	Shore A durometer 55 min to 70 max	<b>D2240</b>
Compression set	20 % max of original deflection	<b>D395</b> , Method B (22 h at 70 ± 2°C)
Water absorption	5 % max	<b>D471</b> —Immerse a 2-in. (51-mm) long section cut from a rubber coupling in distilled water for 7 days at 70 ± 2°C
Ozone resistance	no visible cracking under 2× specimen magnification, using <b>D518</b> , Procedure B, stretched 20 % and exposed to ozone concentrations of 0.5 ppm for 24 h at 40 ± 1°C	<b>D1149</b>
Accelerated oven aging	85 % min of original tensile strength 85 % min of original elongation	<b>D573</b> (7 days at 70 ± 2°C)

**TABLE 3 Tests for Plastic Materials**

Test	Test Requirements	ASTM Standard
Chemical resistance:		<b>D543</b> (48 h at 23 ± 2°C)
1 N sulfuric acid	no weight loss	
1 N hydrochloric acid	no weight loss	

5.5 If any of the test specimens fail to meet the chemical resistance requirements, the manufacturer will be allowed a retest of two additional specimens, representative of the original material tested, for each one that failed. The jointing material will be acceptable if all retest specimens meet the test requirements.

5.6 Joints complying with this standard are suitable for most domestic and commercial applications. However, attention is called to the fact that industrial effluents vary in content, concentration, duration of discharge and temperature; and specific evaluations of joint performance in such environments are necessary. In those instances, consult the manufacturer.

## 6. Joint Specimen Preparation

6.1 When required, assembled joints representative of the pipe and joints to be used, shall be selected from the supplier's stock by the purchaser or his representative.

6.2 Specimens selected for the test shall be up to 0.25 % of the number of joints to be furnished. No fewer than two assembled joints shall be tested for each diameter of pipe furnished.

6.3 Test specimens shall not be taken from damaged joints or pipe.

## 7. Test Requirements for Joints

7.1 Joints shall meet the requirements of **7.1.1** and **7.1.2** or **7.1.1** and **7.1.3**, when subjected to an internal 10-ft (3.1-m) head of water pressure (4.3 psi (30 kPa)), for a total test period of 1 h. The recommended temperature of the water, pipe, and atmosphere is 60 to 75°F (16 to 24°C).

7.1.1 Joints shall not leak when tested in the straight position and when deflected to amounts shown in **Table 4**. The ends of the test line shall only be restrained the amount that is necessary to prevent longitudinal movement. The deflection shall be determined by measuring the distance the free end of one pipe moves away from the center line in any direction while the other pipe remains fixed.

7.1.2 Assembled joints shall not leak when subjected to shear. The shear load shall be a force of 150 lbf/in. (26 kN/m) of nominal diameter uniformly applied over an arc of not less

**TABLE 4 Deflection**

Nominal Diameter, in. (mm)	Deflection of Pipe, in./linear ft (mm/linear m)
3 to 12 (76 to 305), incl	$\frac{1}{2}$ (42)
15 to 24 (380 to 610), incl	$\frac{3}{8}$ (31)
27 to 36 (685 to 915), incl	$\frac{1}{4}$ (21)
39 and 42 (990 and 1065)	$\frac{3}{16}$ (16)
48 (1220)	$\frac{1}{8}$ (10)

than 120° (2.1 rad) along a longitudinal distance of not more than 12 in. (305 mm) at the spigot end of one pipe. The load is applied immediately adjacent to the assembled joint with the

other pipe adequately secured and supported on blocks placed immediately adjacent to the joint.

7.1.3 Joints shall not leak when the jointed ends are displaced relative to one another in any direction perpendicular to the pipe axis a distance of 0.04 in./in. (0.04 mm/mm) of pipe diameter.

## 8. Keywords

8.1 bell; chemical resistance; clay pipe; compression joints; corrosion resistance; couplings; deflection; joints; sealing elements; shear; testing

## SUPPLEMENTARY REQUIREMENTS

These requirements apply only to Federal/Military procurement, not domestic sales or transfers.

### S1. Government/Military Procurement

S1.1 *Responsibility for Inspection*—Unless otherwise specified in the contract or purchase order, the producer is responsible for the performance of all inspection and test requirements specified herein. The producer may use his own or any other suitable facilities for the performance of the inspection and test requirements specified herein, unless the purchaser disapproves. The purchaser shall have the right to perform any of the inspections and tests set forth in this specification where such inspections are deemed necessary to ensure that material conforms to prescribed requirements.

NOTE S1.1—In U.S. Federal contracts, the contractor is responsible for inspection.

### S2. Packaging and Marking for U.S. Government Procurement:

S2.1 *Packaging*—Unless otherwise specified in the contract, the materials shall be packaged in accordance with the supplier's standard practice in a manner ensuring arrival at destination in satisfactory condition and which will be acceptable to the carrier at lowest rates. Containers and packing shall comply with Uniform Freight Classification rules or National Motor Freight Classification rules.

S2.2 *Marking*—Marking for shipment shall be in accordance with Fed. Std. No. 123 for civil agencies and MIL-STD-129 for military agencies.

NOTE S2.1—The inclusion of U.S. Government procurement requirements should not be construed as an indication that the U.S. Government uses or endorses the products described in this document.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).*