



## Standard Specification for Grout for Masonry<sup>1</sup>

This standard is issued under the fixed designation C476; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the U.S. Department of Defense.*

### 1. Scope\*

1.1 This specification covers two types of grout, fine and coarse grout, for use in the construction of masonry structures. Each type (fine and coarse) is further classified as conventional grout (requiring mechanical consolidation by puddling or vibration when placed) and self-consolidating grout (not requiring mechanical consolidation when placed). Conventional grout is specified by (1) proportions or (2) strength requirements. Self-consolidating grout is specified by strength requirements.

1.2 The text of this specification references notes and footnotes that provide explanatory material. These notes and footnotes (excluding those in tables and figures) shall not be considered as requirements of this specification.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

### 2. Referenced Documents

#### 2.1 ASTM Standards:<sup>2</sup>

C5 Specification for Quicklime for Structural Purposes  
C143/C143M Test Method for Slump of Hydraulic-Cement Concrete  
C150/C150M Specification for Portland Cement  
C207 Specification for Hydrated Lime for Masonry Purposes  
C260/C260M Specification for Air-Entraining Admixtures for Concrete  
C404 Specification for Aggregates for Masonry Grout  
C494/C494M Specification for Chemical Admixtures for Concrete

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee C12 on Mortars and Grouts for Unit Masonry and is the direct responsibility of Subcommittee C12.05 on Grout & Grout Admixtures for Masonry.

Current edition approved July 15, 2016. Published July 2016. Originally approved in 1961. Last previous edition approved in 2010 as C476 – 10. DOI: 10.1520/C0476-16.

<sup>2</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

C595/C595M Specification for Blended Hydraulic Cements  
C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete  
C989/C989M Specification for Slag Cement for Use in Concrete and Mortars  
C1019 Test Method for Sampling and Testing Grout  
C1157/C1157M Performance Specification for Hydraulic Cement  
C1611/C1611M Test Method for Slump Flow of Self-Consolidating Concrete

### 3. Materials

3.1 Materials used as ingredients in grout shall conform to the requirements specified in 3.1.1 – 3.1.8.

3.1.1 *Cementitious Materials*—Cementitious materials shall conform to one of the following specifications:

3.1.1.1 *Portland Cement*—Type I, IA, II, IIA, III, and IIIA of Specification C150/C150M.

3.1.1.2 *Blended Cements*—Type IS, IS(MS), IS-A, IS-A(MS), IP, or IP-A of Specification C595/C595M or types GU, HE, MS, or HS of Specification C1157/C1157M.

3.1.1.3 *Quicklime*—Specification C5.

3.1.1.4 *Hydrated Lime*—Type S of Specification C207.

3.1.1.5 *Coal Fly Ash or Raw Calcined Natural Pozzolan*—Specification C618. Addition rates shall be in an amount governed by the portland-pozzolan cement category of Specification C595/C595M. The grout produced with blends of portland cement and fly ash or raw calcined natural pozzolan shall have the compressive strength specified (4.2.1.2 or 4.2.2.1).

3.1.1.6 *Granulated Blast Furnace Slag*—Specification C989/C989M. Addition rates shall be as governed by the portland blast furnace slag cement category of Specification C595/C595M. Grouts produced with blends of portland cement and granulated blast furnace slag shall have the compressive strength specified (4.2.1.2 or 4.2.2.1).

3.1.2 *Air-Entraining Admixtures*—Air-entraining admixtures shall conform to Specification C260/C260M.

3.1.3 *Aggregates*—Aggregates shall conform to Specification C404.

3.1.4 *Water*—Water shall be clean and potable.

3.1.5 *Admixtures*—Integral waterproofing compounds, accelerators, or other admixtures not mentioned definitely in

\*A Summary of Changes section appears at the end of this standard

**TABLE 1 Conventional Grout Proportions by Volume**

Type	Parts by Volume of Portland Cement or Blended Cement	Parts by Volume of Hydrated Lime or Lime Putty	Aggregate, Measured in a Damp, Loose Condition	
			Fine	Coarse
Fine grout	1	0–1/10	2 1/4 –3 times the sum of the volumes of the cementitious materials	...
Coarse grout	1	0–1/10	2 1/4 –3 times the sum of the volumes of the cementitious materials	1–2 times the sum of the volumes of the cementitious materials

the specification shall not be used in grout for use in reinforced masonry without approval from the purchaser.

3.1.5.1 *Admixtures for Ready-Mixed Grout Transported to the Job Site*—Retarding admixtures conforming to Specification C494/C494M, Type B or D, for producing ready-mixed grout transported to the job site and meeting 4.2.1.2 are permitted.

3.1.5.2 *Admixtures for Self-consolidating Grout*—High-range water-reducing admixtures conforming to Specification C494/C494M, Type F or G, and viscosity-modifying admixtures conforming to Specification C494/C494M, Type S, for producing self-consolidating grout are permitted.

NOTE 1—Polycarboxylate-based high-range water-reducing admixtures are best suited to achieve the water reduction and slump flow values required for self-consolidating grout. While viscosity-modifying admixtures are acceptable for producing self-consolidating grout, there currently are no ASTM specifications specifically for these admixtures. The C494/C494M requirements for Type S (specific performance) admixture provide a means of determining that the viscosity-modifying admixture will not have adverse effects on fresh, hardened and durability properties of the grout. Admixture suppliers should be consulted to ensure that the particular high-range water-reducing admixture and viscosity-modifying admixture being used are suitable for production of self-consolidating grout.

3.1.6 *Pumping Aids*—Pumping aids are permitted to be used in cases where the brand, quality, and quantity are approved by the specifier, or are specifically stipulated in the contract documents.

3.1.7 *Antifreeze Compounds*—No antifreeze liquids, salts, or other substances shall be used in grout to lower the freezing point.

3.1.8 *Storage of Materials*—Cementitious materials and aggregates shall be stored in such a manner as to prevent deterioration or intrusion of foreign material or moisture. Any material that has become unsuitable for good construction shall not be used.

NOTE 2—If the grout is to be used to bond masonry units to reinforcing bars, the use of air-entraining materials or air-entraining admixtures is not recommended.

## 4. Grout Type and Proportions

4.1 *Type*—Grout type shall be specified as fine or coarse.

4.1.1 Fine grout shall be manufactured with fine aggregates.

4.1.2 Coarse grout shall be manufactured with a combination of coarse and fine aggregates.

NOTE 3—Building code provisions and grout space dimensions should be reviewed when selecting grout type or types.

4.2 *Proportions of Ingredients*—Proportions shall be determined as follows:

4.2.1 *Conventional Grout*—Proportions shall be determined by one of the following methods:

4.2.1.1 Requirements of Table 1.

4.2.1.2 *Specified Compressive Strength*—Proportions established by 28-day compressive strength tests in accordance with Test Method C1019 that equal or exceed the specified compressive strength. The grout shall be mixed to a slump of 8 to 11 in. (200 to 280 mm) as determined by Test Method C143/C143M and shall have a minimum compressive strength of 2000 psi (14 MPa) at 28 days.

4.2.2 *Self-consolidating Grout*—Proportions shall be determined by the following method:

4.2.2.1 *Specified Compressive Strength*—Proportions established by 28-day compressive strength tests in accordance with Test Method C1019 that equal or exceed the specified compressive strength. The grout shall be mixed to a slump flow of 24 to 30 in. (610 to 760 mm) as determined by Test Method C1611/C1611M and shall have a Visual Stability Index (VSI) of not greater than 1 as determined by Appendix X1 of Test Method C1611/C1611M. The grout shall have a minimum compressive strength of 2000 psi (14 MPa) at 28 days.

NOTE 4—The value for  $T_{50}$  as described in Appendix X1.1 and Note X1.1 of Test Method C1611/C1611M is a property of self-consolidating concrete and can be used as an indicator of batch-to-batch quality, consistency and performance in-situ of self-consolidating grout. While there is no consensus as to the appropriate  $T_{50}$  for all self-consolidating grouts, average values from 1.5 to 4 sec, with variations of  $\pm 0.5$  sec from the average value, determined for the particular self-consolidating grout, typically provide proper viscosity and indicate batch-to-batch consistency.

NOTE 5—Building code provisions should be reviewed when selecting the specified compressive strength of grout.

## 5. Measurement and Production

5.1 *Measurement of Materials*—Measure materials for grout such that the required proportions of the grout materials are controlled and accurately measured.

NOTE 6—When converting volume proportions to batch weights, use the following material bulk densities:

Material	Weight, lb/ft <sup>3</sup> (kg/m <sup>3</sup> )
Portland cement	94 (1505)
Blended cement	Obtain from bag or supplier
Other cementitious materials	Obtain from bag or supplier
Hydrated lime	40 (640)
Lime putty <sup>A</sup>	80 (1280)
Sand, damp and loose	80 (1280) of dry sand
Coarse aggregate	Refer to C404 to determine weight per cubic foot.

<sup>A</sup>All quicklime should be slaked in accordance with the manufacturer's directions. All quicklime putty, except pulverized quicklime putty, should be sieved through a No. 20 (850- $\mu$ m) sieve and allowed to cool until it has reached a temperature of 80°F (26.7°C). Quicklime putty should weigh at least 80 lb/ft<sup>3</sup> (281 kg/m<sup>3</sup>). Putty that weighs less than this may be used in the proportion specifications if the required quantity of extra putty is added to meet the minimum weight requirements.

5.2 *Production Methods*—Grout shall be produced using one of the following procedures:

5.2.1 *Grout Materials Mixed with Water at the Job Site:*

5.2.1.1 *Conventional Grout:*

(1) Individual cementitious materials and aggregates stored at the job site shall be mixed in a mechanical mixer for a minimum of 5 min with sufficient water to achieve the desired consistency.

(2) Individual ingredients transported to the job site in suitable compartments shall be mixed with water at the job site using continuous volumetric proportioning equipment to achieve the desired consistency. Mix with an auger of appropriate length to provide adequate mixing.

(3) Factory pre-blended grout materials delivered to the job site shall be mixed in a mechanical batch mixer for a minimum of 5 min or in a continuous mixer following mixer manufacturer's recommendation with sufficient water to achieve the desired consistency.

NOTE 7—Conventional grout may be hand-mixed on small jobs with written approval of the mixing procedure by the specifier.

5.2.1.2 *Self-consolidating Grout:*

(1) Individual ingredients transported to the job site as part of a self-consolidating grout manufacturer's system, shall be mixed at the job-site with water, per the manufacturer's recommendations, using continuous volumetric proportioning equipment to achieve the desired consistency. Mix with an auger of appropriate length to provide adequate mixing.

(2) Factory preblended grout materials delivered to the job site shall be mixed in a mechanical mixer with sufficient water, per the self-consolidating grout manufacturer's recommendation, to achieve the desired consistency.

(3) Job site proportioning and mixing of individual materials that are not part of a self-consolidating grout manufacturer's system shall not be permitted.

5.2.2 *Ready-Mixed Grout Transported to the Job Site:*

5.2.2.1 *Conventional Grout*—Grout shall arrive at the job site in a ready-mixed condition. Slump shall be adjusted as necessary, and grout shall be re-mixed at mixing speed for at least 1 min before discharging to achieve the desired consistency.

5.2.2.2 *Self-consolidating Grout*—Grout shall arrive at the job-site in a ready-mixed condition. The addition of water at the job site is permitted in accordance with the self-consolidating grout manufacturer's recommendations.

## 6. Keywords

6.1 aggregates; cement; compressive strength; grout; masonry; portland cement; proportions ; self-consolidating grout

## SUMMARY OF CHANGES

Committee C12 has identified the location of selected changes to this standard since the last issue (C476 – 10) that may impact the use of this standard. (July 15, 2016)

(1) Added 3.1.5.1 to permit Type B and D admixtures.

(2) Modified 3.1.6 to clarify approval of pumping aids.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*