



Standard Test Method for Facial Dimensions and Thickness of Flat, Rectangular Ceramic Wall and Floor Tile¹

This standard is issued under the fixed designation C499; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This test method covers the determination of the facial dimensions and thickness of flat, rectangular ceramic wall and floor tile. This test method covers tile as defined in Terminology C242.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

C242 Terminology of Ceramic Whitewares and Related Products

3. Terminology

3.1 *Definitions of Terms Specific to This Standard:*

3.1.1 *major facial dimension*—the overall length or width of the tile, including the lugs on opposite sides.

3.1.2 *major thickness*—the thickness of tile, including any maximum protuberances or ridges on the back.

3.1.3 *minor facial dimension*—the length or width of the tile exclusive of the lugs.

3.1.4 *minor thickness*—the thickness of tile that does not include maximum protuberances or ridges.

¹ This test method is under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.06 on Ceramic Tile.

Current edition approved Dec. 1, 2014. Published December 2014. Originally approved in 1962. Last previous edition approved in 2009 as C499 – 09. DOI: 10.1520/C0499-09R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

4. Significance and Use

4.1 This test method provides a means of determining whether a lot of tile meets specifications of variations in size and thickness. In specifications, the nominal size always refers to the minor facial dimension and the nominal thickness of a tile always refers to the major thickness.

5. Apparatus

5.1 A suitable measuring device such as a micrometer or dial indicator, reading in 0.001-in. (0.025-mm) divisions and accurate to ± 0.001 in. (± 0.025 mm), shall be used. If a dial indicator is used, suitable jigs for holding the tile and the indicator shall be provided.

6. Test Specimens

6.1 At least ten tile specimens shall be selected at random from the lot to be tested. The same specimens may be used for the determination of facial dimensions and thickness. Brush the specimens to remove all adhering particles of clay or sand.

7. Procedure

7.1 *Major Facial Dimension*—Measure the length of the tile to the nearest 0.001 in. (0.025 mm) across two pairs of opposite lugs. Follow the same procedure for measuring the width of the tile. For tile whose lugs are not arranged opposite each other, it may be necessary to use a jig to obtain the major facial dimensions. For square tile, average all four measurements and call the result the average major dimension. For oblong tile, average the two length measurements and call the result the average major length of the tile; average the two width measurements and call the result the average major width of the tile.

7.2 *Minor Facial Dimension*—Measure the length of the tile exclusive of the lugs to the nearest 0.001 in. (0.025 mm) in two places. Follow the same procedure for measuring the width exclusive of the lugs. Points of measurement shall be at least 0.25 in. (6.4 mm) and not more than 0.50 in. (12.7 mm) from the corners of the tile. For tile with tapered sides, a jig is required to determine the minor facial dimension of such tile. For square tile, average all four measurements and call the

result the average minor dimension. For oblong tile, average the two length measurements and call the result the average minor length; average the two width measurements and call the result the average minor width.

7.3 Major Thickness—Measure the major thickness to the nearest 0.001 in. (0.025 mm) at each of the four corners of the tile including any protuberances or ridges on the back of the tile. Points of measurement shall be at least 0.25 in. (6.4 mm) and not more than 0.75 in. (19.0 mm) in from the edge of the tile. Average the four readings and call the result the average major thickness.

7.4 Minor Thickness—Measure the minor thickness to the nearest 0.001 in. (0.025 mm) near each of the four corners of the tile not including any protuberances or ridges on the back of the tile. Points of measurements shall be at least 0.25 in. (6.4 mm) and not more than 0.75 in. (19.0 mm) in from the edge of the tile. Average the four readings and call the result the average minor thickness.

8. Report

8.1 The report shall give the type and number of tile tested and shall show for each specimen the following information:

8.1.1 Average, maximum, and minimum values of the major length,

8.1.2 Average, maximum, and minimum values of the major width,

8.1.3 Average, maximum, and minimum values of the minor length,

8.1.4 Average, maximum, and minimum values of the minor width,

8.1.5 Average, maximum, and minimum values of the major thickness, and

8.1.6 Average, maximum, and minimum values of the minor thickness.

NOTE 1—For square tile, 8.1.2 and 8.1.3 shall be omitted. For tile without lugs, major and minor facial dimensions are identical. The major and minor thickness of tile without any protuberances or ridges on the back is identical.

9. Precision and Bias

9.1 *Precision*—The precision of the average dimensions reported is ± 0.002 in. (0.05 mm).

9.2 *Bias*—Bias depends almost entirely on the accuracy of the measuring devices and care taken to set up the equipment. No interlaboratory data are available with which to estimate bias.

10. Keywords

10.1 ceramic tile; facial dimension; major dimension; minor dimension; thickness dimension

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; <http://www.copyright.com/>