

Standard Specification for Chemical-Resistant Resin Grouts for Brick or Tile¹

This standard is issued under the fixed designation C658; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers the requirements for chemicalresistant resin grouts for filling joints of chemical-resistant brick or tile units. For use of these materials, see Practice C723. (For mortars, see Specification C395.)

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

Note 1—Resin grouts and mortars are differentiated as follows: Resin grouts are applied to the joints, generally ¹/₄ in. (6 mm) wide, after the brick or tile are set in place and the setting bed has hardened (grouting or tilesetter's method). Resin mortars are trowelled onto the brick or tile in sufficient quantity to achieve a ¹/₈-in. (3-mm) thick joint after the brick or tile are laid in place (buttering or bricklayer's method).

2. Referenced Documents

2.1 ASTM Standards:²

- C307 Test Method for Tensile Strength of Chemical-Resistant Mortar, Grouts, and Monolithic Surfacings
- C308 Test Methods for Working, Initial Setting, and Service Strength Setting Times of Chemical-Resistant Resin Mortars
- C395 Specification for Chemical-Resistant Resin Mortars
- C413 Test Method for Absorption of Chemical-Resistant Mortars, Grouts, Monolithic Surfacings, and Polymer Concretes
- C531 Test Method for Linear Shrinkage and Coefficient of Thermal Expansion of Chemical-Resistant Mortars, Grouts, Monolithic Surfacings, and Polymer Concretes
- C579 Test Methods for Compressive Strength of Chemical-Resistant Mortars, Grouts, Monolithic Surfacings, and Polymer Concretes

C723 Practice for Chemical-Resistant Resin Grouts for Brick or Tile

C904 Terminology Relating to Chemical-Resistant Nonmetallic Materials

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, see Terminology C904.

4. Types of Resins, Fillers, and Setting Agents

4.1 The liquid resins may be furan, epoxy, vinyl ester, or others capable of forming chemical-resistant grout when mixed with a suitable setting agent and filler.

4.2 The fillers may be silica, carbon, or other chemical resistant materials. Fillers may be supplied as a separate component or can be combined as a premix with the liquid resin and/or setting agent.

4.3 The setting agents may include amines, polyamides, peroxides, acids, or other reactants. Setting agents may be supplied as a separate component to be incorporated into the resin and filler at the time of mixing or may be supplied as a constituent of the filler.

5. General Requirements

5.1 When these components are mixed at 65 to 85° F (18 to 29° C) they form a uniform and flowable grout. The mixed grout shall be of a viscosity such that it will readily flow to the full depth of the open joint.

5.2 The filler shall have properly graded particles, not exceeding $\frac{1}{32}$ in. (1 mm), that will permit the filling of a minimum joint width of $\frac{3}{16}$ in. (5 mm).

5.3 The service limitations of the grout shall be defined by the manufacturer.

6. Physical Requirements

6.1 Chemical-resistant resin tile grouts prepared from these materials shall conform to the physical requirements prescribed in Table 1.

7. Test Methods

7.1 Determine the properties enumerated in this specification in accordance with the following methods:

¹ This specification is under the jurisdiction of ASTM Committee C03 on Chemical-Resistant Nonmetallic Materialsand is the direct responsibility of Subcommittee C03.02 on Monolithics, Grouts and Polymer Concretes.

Current edition approved Aug. 1, 2012. Published September 2012. Originally approved in 1970. Last previous edition approved in 2008 as C658 – 98 (2008). DOI: 10.1520/C0658-98R12.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

(112) C658 – 98 (2012)

TABLE 1 Physical Requirements at $73 \pm 4^{\circ}F(23 \pm 2^{\circ}C)$

	Furan Resin Grout	Epoxy Resin Grout	Vinyl Ester Resin Grout
Initial setting time, max, h	10	16	10
Service strength setting time, max, days	7	7	7
Compressive strength, 7 days, min, psi (MPa)	4000 (28)	7500 (52)	7500 (52)
Tensile strength, 7 days, min, psi (MPa)	600 (4)	1200 (8)	1300 (9)
Water absorption, max,%	0.5	0.5	0.4
Linear Shrinkage, 7 days, max,%	1.0	0.4	1.0

7.1.1 Setting Time— Test Method C308.

7.1.2 Compressive Strength—Test Method C579.

7.1.3 Tensile Strength— Test Method C307.

7.1.4 Water Absorption— Test Method C413.

7.1.5 Linear Shrinkage— Test Method C531.

8. Rejection

8.1 The grout may be rejected if it fails to meet any of the requirements of this specification.

9. Packaging and Package Marking

9.1 Each component shall be packaged to prevent deterioration in storage and shall be labeled in such a manner to indicate clearly the other components with which it is to be used.

9.2 The supplier, at his discretion and responsibility, may indicate on the package that the product contained therein meets the requirements of this specification.

10. Keywords

10.1 brick; chemical-resistant; grout; tile

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).