



Standard Test Method for Bubbling of One-Part, Elastomeric, Solvent-Release Type Sealants¹

This standard is issued under the fixed designation C712; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers determination of the degree of bubble formation or surface blistering in one-part, elastomeric solvent-release type sealants when exposed to elevated temperatures.

1.2 The subcommittee with jurisdiction is not aware of any similar ISO standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards:*²

C717 Terminology of Building Seals and Sealants

C719 Test Method for Adhesion and Cohesion of Elastomeric Joint Sealants Under Cyclic Movement (Hockman Cycle)

3. Terminology

3.1 *Definitions*—Refer to Terminology C717 for definitions of the following terms used in this test method: compound, elastomer, elastomeric, sealant, solvent-release sealant, substrate, and standard conditions.

4. Significance and Use

4.1 The type and amount of solvent used in these sealants can sometimes give rise to surface bubbling and blistering problems. The substrate used, whether porous or nonporous, will also have an effect. Although blistering is often caused by misapplication, this test method is useful in differentiating

between a sealant that develops an acceptably smooth surface and one that may have blistering tendencies.

5. Apparatus

5.1 *Plates*, thin aluminum, approximately 3 in. (76 mm) wide by 5 in. (127 mm) long by 0.012 in. (0.30 mm) thick.

5.2 *Blocks*, prepare cement mortar, as described in Terminology C719 to the following size: approximately 2 in. (51 mm) wide by 4 in. (102 mm) long by 1 in. (25 mm) thick.

NOTE 1—Other substrates such as brick, cast stone, marble, stainless steel, etc., may be specified either in place of the standard materials specified in 5.1 and 5.2 or in addition to them.

5.3 *Frame*, flat, rectangular, of 1/8-in. (3.2-mm) steel or brass, with an opening of 1 in. by 3 3/4 in. (25 mm by 95 mm) and outside dimensions of approximately 2 in. by 4 3/4 in. (51 mm by 121 mm).

5.4 *Spatula*, steel, with knife edge.

5.5 *Oven*, forced-draft type, having a temperature controlled at $122 \pm 3.6^\circ\text{F}$ ($50 \pm 2^\circ\text{C}$).

6. Test Specimen

6.1 Take the test specimen from a previously unopened container as received from the sealant manufacturer.

7. Procedure

7.1 Prepare three test specimens on each substrate as follows: Center the frame on the test substrate and carefully fill it with compound, avoiding air pockets. Strike off the surface of the compound flush with the frame, to a uniform thickness of 1/8 in. (3.2 mm). With the spatula, cut all around the outside edge of the compound and lift the frame straight up and off.

7.2 Condition the specimens for 48 h at standard conditions.

7.3 Place the specimens in the oven at $122 \pm 3.6^\circ\text{F}$ ($50 \pm 2^\circ\text{C}$) for 72 h.

7.4 After heat exposure, allow the specimens to cool at $73.4 \pm 3.6^\circ\text{F}$ ($23 \pm 2^\circ\text{C}$) for 1 h.

7.5 Examine each specimen for surface gas bubbles and blisters.

¹ This test method is under the jurisdiction of ASTM Committee C24 on Building Seals and Sealants and is the direct responsibility of Subcommittee C24.20 on General Test Methods.

Current edition approved Dec. 1, 2014. Published December 2014. Originally approved in 1972. Last previous edition approved in 2009 as C712 – 03 (2009). DOI: 10.1520/C0712-14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 Precision and Bias Data

Material	Average	Estimated Standard Deviation Within Laboratory	Estimated Standard Deviation Between Laboratories	Repeatability Interval	Reproducibility
G1	0.000	0.000	0.000	0.000	0.000
G2	0.064	0.209	0.212	0.590	0.600
G3	0.011	0.028	0.020	0.079	0.078

8. Report

8.1 For each substrate, report the total surface area covered by the bubbles or blisters, estimated to the nearest 0.1 in.² (65 mm²). The area of bubble formation may be estimated by superimposing on the specimen a glass or clear plate ruled into ½-in. (13-mm) squares.

9. Precision and Bias³

9.1 The precision and bias calculations for this test method are based on the results of four laboratories testing three materials using five specimens per test. The results are given in **Table 1**.

³ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:C24-1021.

9.1.1 At 95 % confidence level a variation of as much as 0.59 in.² can be expected within a laboratory and 0.60 in.² between laboratories. This is based on three materials being tested by four laboratories.

10. Keywords

10.1 bubbling; elastomeric; solvent-release sealant

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/