This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.



# Standard Specification for Mineral Wool Roof Insulation Board<sup>1</sup>

This standard is issued under the fixed designation C726; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\varepsilon$ ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

## 1. Scope

1.1 This specification covers the composition and physical properties of mineral wool insulation board used above structural roof decks in building construction. The mineral wool roof insulation acts as a base for systems such as single-ply, polymer-modified bitumen and built-up roof. This specification also covers mineral wool insulation boards that incorporate a fibrous high density upper layer on the top surface

1.2 It is possible that the use of thermal insulation materials covered by this specification will be regulated by building codes or other agencies that address fire performance, or both. The fire performance of the material needs to be addressed through standard fire test methods established by the appropriate governing documents.

1.3 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.4 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of the regulatory limitations prior to use.

1.5 This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.

#### 2. Referenced Documents

2.1 The following standards, of the issue in effect on the date of material purchase, form a part of this specification to the extent specified herein:

- 2.2 ASTM Standards:<sup>2</sup>
- C165 Test Method for Measuring Compressive Properties of Thermal Insulations
- C168 Terminology Relating to Thermal Insulation
- C177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus
- C203 Test Methods for Breaking Load and Flexural Properties of Block-Type Thermal Insulation
- C209 Test Methods for Cellulosic Fiber Insulating Board
- C303 Test Method for Dimensions and Density of Preformed Block and Board–Type Thermal Insulation
- C390 Practice for Sampling and Acceptance of Thermal Insulation Lots
- C518 Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- C665 Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured Housing
- C1363 Test Method for Thermal Performance of Building Materials and Envelope Assemblies by Means of a Hot Box Apparatus
- C1763 Test Method for Water Absorption by Immersion of Thermal Insulation Materials
- D312 Specification for Asphalt Used in Roofing
- D482 Test Method for Ash from Petroleum Products
- D450 Specification for Coal-Tar Pitch Used in Roofing, Dampproofing, and Waterproofing

<sup>&</sup>lt;sup>1</sup>This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.20 on Homogeneous Inorganic Thermal Insulations.

Current edition approved March 1, 2017. Published April 2017. Originally approved in 1972. Last previous edition approved in 2012 as C726 – 12. DOI: 10.1520/C0726-17.

<sup>&</sup>lt;sup>2</sup> For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

- D2126 Test Method for Response of Rigid Cellular Plastics to Thermal and Humid Aging
- E84 Test Method for Surface Burning Characteristics of Building Materials
- E2058 Test Methods for Measurement of Material Flammability Using a Fire Propagation Apparatus (FPA)
- 2.3 Other Referenced Documents:
- CAN/ULC-S102 Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies<sup>3</sup>
- EN 12430 :1998/A1 Thermal Insulating Product for Building Applications – Determination of Behaviour Under Point Load<sup>4</sup>
- FM 4470 Approval Standard for Single-Ply, Polymer-Modified Bitumen Sheet, Built-Up Roof (BUR) and Liquid Applied Roof Assemblies for use in Class 1 and Noncombustible Roof Deck Constructions<sup>5</sup>
- ISO 1716 :2002, Reaction-to-Fire Tests for Building Products – Determination of the Heat of Combustion<sup>6</sup>

#### 3. Terminology

3.1 *Definitions:* Terms used in this specification are defined in Terminology C168.

3.1.1 *noncombustible core*—a fibrous roof insulation product conforming to the ash content, visible flaming and heat of combustion requirements 12.11.

## 4. Classification

4.1 The thermal insulation shall be of the following types, classes and grades;

4.1.1 *Type I*—Roof insulation board comprised of a monolithic fibrous material having a fibrous high density upper surface layer and a lower density fibrous bottom layer.

4.1.1.1 *Class 1*—Minimum upper surface layer actual density of 11.2 lb/ft<sup>3</sup> (180 kg/m<sup>3</sup>) and a minimum lower layer actual density of 7.5 lb/ft<sup>3</sup> (120 kg/m<sup>3</sup>).

4.1.1.2 *Class* 2—Upper surface layer and lower surface layer density less than Class 1.

(1) Grade A – Minimum point load of 146 lbf (650 N).

(2) Grade B – Point load < 146 lbf (650 N).

4.1.2 *Type II*—Roof insulation board of singular density.

4.1.2.1 *Class 1*—Minimum actual density of 9 lb/ft<sup>3</sup> (144 kg/m<sup>3</sup>).

4.1.2.2 Class 2-Actual density less than Class 1.

## 5. Ordering Information

5.1 Orders for material purchased under this specification shall include:

5.1.1 Designation of this specification,

5.1.2 Product name,

5.1.3 Board dimensions,

5.1.4 Quantity of material, and

5.1.5 Special packaging or marking, (14.1 and 14.2) if required.

#### 6. Materials and Manufacture

6.1 Mineral wool roof insulation board shall consist of mineral wool with an organic resin or other suitable binder.

6.2 For built-up roofing or polymer modified bitumen systems the board shall be faced during manufacture on one surface with a cover adequate for the application of Specification D312 asphalt or Specification D450 coal-tar pitch.

6.3 For single ply membrane systems the board shall be permitted to be faced or unfaced. For mechanically fastened single ply membrane systems the board shall be permitted to be faced or unfaced. For adhered single ply membrane systems the board shall be permitted to be faced during manufacture on one surface with a cover adequate for the application of the adhesive used to secure the single ply membrane.

#### 7. Physical Properties

7.1 The average thermal resistance, R, of specimens sampled in accordance with Practice C390 shall be as specified by the manufacturer.

7.2 Nominal thickness required to obtain the specified resistance or conductance shall be as stated by the manufacturer.

7.3 Roof insulation boards shall have the limiting property values shown in Table 1.

#### 8. Dimensions and Tolerances

8.1 The dimensions shall be as agreed upon between the purchaser and manufacturer. Tolerances shall be as follows:

	Tolerance, in. (mm)
Long dimension	±1⁄4 (6)
Short dimension	±1⁄4 (6)
Thickness	±1⁄8 (3)

The long and short dimension tolerances in this section are for individual boards. The tolerance for long and short dimension averages for at least 20 boards shall be  $\pm \frac{1}{16}$  in. (2 mm).

8.2 Board squareness shall be within required tolerance if the two diagonal measurements of the board differ by no more than  $\frac{1}{4}$  in. (6 mm).

8.3 Board flatness shall be within required tolerance if, when board is placed concave side up, the average distance between a flat supporting surface and the bottom board surface at the corners does not exceed  $\frac{5}{16}$  in. (8 mm) over a temperature range from 20 to  $140^{\circ}$ F (-7 to  $60^{\circ}$ C). Maximum distance at an individual corner shall not exceed  $\frac{1}{2}$  in. (13 mm).

 $8.4\,$  The thermal resistance of any single specimen shall not be more than 10 % below the value specified by the manufacturer.

8.5 Mass per unit area of any board,  $lb/ft^2$  (kg/m<sup>2</sup>) shall be within 10 % of the value specified by the manufacturer. Average mass per unit area of at least 20 boards shall be within 5 % of the value specified by the manufacturer.

<sup>&</sup>lt;sup>3</sup> Available from Underwriters Laboratories (UL), 2600 N.W. Lake Rd., Camas, WA 98607-8542, http://www.ul.com.

<sup>&</sup>lt;sup>4</sup> Available from European Committee for Standardization (CEN), Avenue Marnix 17, B-1000, Brussels, Belgium, http://www.cen.eu.

<sup>&</sup>lt;sup>5</sup> FM Approvals, 1151 Boston-Providence Turnpike, P.O. Box 9102, Norwood, MA 02062.

<sup>&</sup>lt;sup>6</sup> Available from International Organization for Standardization (ISO), 1, ch. de la Voie-Creuse, CP 56, CH-1211 Geneva 20, Switzerland, http://www.iso.org.

TABLE 1 Physical Properties			
Property	Requirement		
Type I: Class 1–Minimum Upper Density, Ib/ft <sup>3</sup> (kg/m <sup>3</sup> ) Minimum Lower Density, Ib/ft <sup>3</sup> (kg/m <sup>3</sup> ) Class 2–Upper Density, Ib/ft <sup>3</sup> (kg/m <sup>3</sup> ) Lower Density, Ib/ft <sup>3</sup> (kg/m <sup>3</sup> )	11.2 (180) 7.5 (120) <11.2 (180) <7.5 (120)		
Class 1 Minimum Density, lb/ft <sup>3</sup> (kg/m3) Class 2 Density, lb/ft <sup>3</sup> (kg/m <sup>3</sup> )	9.0 (144) <9.0 (144)		
Compressive resistance: at 25 % deformation, min, psi (kPa) at 10 % deformation min, psi (kPa) Tensile strength perpendicular to board surface, min,	12 (83) 7 (48) 450 (22)		
Breaking load, min, lbf (N): Type 1 Type 2	60 (266) 30 (133)		
Water absorption, max, volume %	5 <sup>A</sup>		
Dimensional Stability: % Linear Change, Thickness, Max $+200 \pm 4^{\circ}F (93 \pm 2^{\circ}C)$ $-40 \pm 6^{\circ}F (-40\pm 3^{\circ}C)$ $+158 \pm 4^{\circ}F (70 \pm 2^{\circ}C)$ % Linear Change, Length and Width, Max $+200 \pm 4^{\circ}F (93\pm 2^{\circ}C)$ $-40 \pm 6^{\circ}F (-40 \pm 3^{\circ}C)$ $+158 \pm 4^{\circ}E (70 \pm 2^{\circ}C)$	বা বা বা বা		
Point Load at 5mm compression, min, N: Type I	650		
Noncombustible Core Ash content (%) Visible Flaming Heat of Combustion, max, BTU/lb (kJ/g)	≥90 None 860 (2.0)		
Corrosiveness Surface Burning Characteristics	Shall meet requirements of Specification C665 for Steel Flame Spread ≤25 Smoke ≤ 50		

<sup>A</sup> There shall be no delamination during the water absorption test.

#### 9. Workmanship, Finish, and Appearance

9.1 Insulation boards shall not have visible defects that will adversely affect service qualities.

## 10. Sampling

10.1 Sampling for qualification tests, if required, shall be in accordance with Practice C390. Qualification tests will be conducted on the physical requirements in 7.1 and Table 1.

10.2 Sampling for inspection tests, if required, shall be in accordance with Practice C390. Inspection requirements are dimensions (Section 8) plus any other properties as agreed upon between the purchaser and manufacturer.

#### **11. Specimen Preparation**

11.1 Specimens for all tests shall include any factoryapplied cover. Take care that the cover is not partially detached in the process of cutting specimens. 11.2 Unless otherwise specified, condition samples prior to cutting specimens for at least 12 h at  $73 \pm 2^{\circ}F$  (24 ± 1°C), 50 ± 5 % relative humidity before testing.

11.3 Unless otherwise stated testing of Type I product shall be done with the higher density surface layer facing up.

## 12. Test Methods

12.1 *Thermal Resistance*—Test Method C177, C518, or Test Method C1363 at a mean temperature of  $75 \pm 2^{\circ}F(24 \pm 1^{\circ}C)$  and  $40^{\circ}F(22^{\circ}C)$  minimum temperature gradient across the thickness of the test specimen or at a mean temperature agreed upon between the purchaser and manufacturer. Some typical additional mean temperatures of interest are  $25^{\circ}F(-4^{\circ}C)$  and  $110^{\circ}F(43^{\circ}C)$ .

12.2 Compressive Resistance—Test Method C165, Procedure A. Crosshead speed shall be  $0.1 \pm 0.01$  in.  $(2.5 \pm 0.25$  mm) for each 1 in. (25.4 mm) of specimen thickness. A total of four (4) specimens shall be tested with one (1) specimen from each of four (4) different boards. The average of the results shall not be less than those defined in Table 1 and any individual specimen shall not be less than 90 % of the minimum in Table 1.

12.3 Tensile Strength Perpendicular to the Board Surface— Test Methods C209, see Test Conditions and Tensile Strength Perpendicular to Surface, except that the specimens shall be 6 by 6 in. (150 by 150 mm). A total of four (4) specimens shall be tested with one (1) specimen from each of four (4) different boards. The average of the results shall not be less than those defined in Table 1 and any individual specimen shall not be less than 90 % of the minimum in Table 1.

12.4 *Breaking Load*—Test Methods C203, Method I, Procedure D. Specimen width shall be 6 in. (152 mm) and support span shall be 10 in. (254 mm). A total of four (4) specimens shall be tested with one (1) specimen from each of four (4) different boards. The average of the results shall not be less than those defined in Table 1 and any individual specimen shall not be less than 90 % of the minimum in Table 1.

12.5 *Water Absorption*—Test Method C1763, Method B. When material is thicker than 1.0 in., split the material to give a specimen thickness of  $1.00 \pm 0.03$  in. For Type 1 product, test at 1 inch or the minimum manufactured thickness as slicing would not provide a representative specimen. The test specimen shall include the faced side of the material if applicable. Immerse the specimen with the faced surface down. A total of four (4) specimens shall be tested with one (1) specimen from each of four (4) different boards.

12.6 Surface Burning Characteristics of Building Materials—Test with the bottom surface exposed to the test flame. Test in accordance with Test Method E84. For Canada, test in accordance with Test Method CAN/ULC-S102. When the referenced Canadian document in this specification is referred to in applicable Canadian building codes, the editions, referenced by those building codes, shall govern.

12.7 *Dimensions*—Test Methods C209, see Test Conditions, Thickness, and Size of Finished Board.

12.8 *Point Load*—Test in accordance with EN 12430:1998/ A1. A total of four (4) specimens shall be tested with one (1) specimen from each of four (4) different boards. The average of the results shall not be less than those defined in Table 1 and any individual specimen shall not be less than 90 % of the minimum in Table 1.

12.9 *Dimensional Stability*—Test Method D2126 except that each specimen shall be 12 by 12 in. (300 by 300 mm) by the full thickness. A total of four (4) specimens shall be tested with one (1) specimen from each of four (4) different boards.

12.9.1 The standard environmental conditions shall be as follows:

	Temperature	Relative Humidity, %RH	Exposure Time, Days
°F	°C		-
$+200 \pm 4$	(93 ± 2)	Ambient	7
-40 ± 6	$(-40 \pm 3)$	Ambient	7
$+158 \pm 4$	(70 ± 2)	97 ± 3 %	7

12.10 *Density*—Test for actual density in accordance with Test Method C303.

12.10.1 To test the upper and lower surface layer densities of Type 1 product, the layers are separated using slicing procedures such as a band saw. Report the thickness used for this determination. For testing purposes the upper layer thickness is  $\frac{1}{2}$  inch (12.7 mm) for Type I products.

## 12.11 Noncombustible Core—See Note 1.

12.11.1 When tested in accordance with Test Method D482, the samples shall have a minimum content of 90 % ash. When a single test produces a result of less than 90 %, two (2) additional tests shall be permitted to be conducted. The results of all three (3) tests shall be averaged. When averaged, the result shall not be less than 90 % ash. See Note 1.

12.11.2 When tested in accordance with Test Methods E2058, visible flaming of the insulation core shall not occur during the entire test. The test shall be terminated at 15 min if the mass loss from the sample has ceased or if visible vapors (if present) have ceased to be generated, or both. If, at 15 min,

the sample still exhibits mass loss or visible vapors, or both, the test shall continue until the mass loss or visible vapors cease, or both. See Note 1.

12.11.3 When tested in accordance with ISO 1716, the insulation core shall have a maximum heat of combustion of 860 BTU/lb (2.0 kJ/g). When a single test produces greater than 860 BTU/lb (2.0 kJ/g), two (2) additional tests shall be permitted to be conducted. The results of all three (3) tests shall be averaged. When averaged, the result shall be less than 860 BTU/lb (2.0 kJ/g). See Note 1.

Note 1-Methodology and requirements conforming to FM 4470, Section 4.9, NCC (Noncombustible Core) Rated Roof Insulation,

12.12 *Corrosiveness*—Test in accordance with Specification C665 for corrosiveness to steel. The product shall conform to the requirements within Specification C665 for steel.

#### 13. Rejection

13.1 Failure to conform to the requirements in this specification shall constitute cause for rejection. In case of rejection, the manufacturer shall have the right to reinspect the rejected shipment and resubmit the lot after removal of that portion not conforming to requirements.

## 14. Packaging and Marking

14.1 *Packaging*—Unless otherwise specified, the insulation shall be supplied in the manufacturer's standard commercial packages.

14.2 *Marking*—Unless otherwise specified, each package shall be marked with the material name, manufacturer's name or trademark, board dimensions, number of pieces, coverage area of the material in the package, and thermal resistance or conductance.

14.2.1 Products that incorporate a fibrous high density upper layer on the top surface as in Type I shall be marked in order to identify the top layer for installation purposes.

## 15. Keywords

15.1 board; insulation; mineral wool; roof

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/