



Standard Specification for Mineral Fiber Loose-Fill Thermal Insulation¹

This standard is issued under the fixed designation C764; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification covers the composition and physical properties of nodulated mineral fiber thermal insulation for use in attics or enclosed spaces in housing and other framed buildings.

1.2 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- [B152/B152M](#) Specification for Copper Sheet, Strip, Plate, and Rolled Bar
- [C168](#) Terminology Relating to Thermal Insulation
- [C177](#) Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Guarded-Hot-Plate Apparatus
- [C390](#) Practice for Sampling and Acceptance of Thermal Insulation Lots
- [C518](#) Test Method for Steady-State Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus
- [C687](#) Practice for Determination of Thermal Resistance of Loose-Fill Building Insulation
- [C870](#) Practice for Conditioning of Thermal Insulating Materials
- [C1104/C1104M](#) Test Method for Determining the Water

- [Vapor Sorption of Unfaced Mineral Fiber Insulation](#)
- [C1304](#) Test Method for Assessing the Odor Emission of Thermal Insulation Materials
- [C1338](#) Test Method for Determining Fungi Resistance of Insulation Materials and Facings
- [C1363](#) Test Method for Thermal Performance of Building Materials and Envelope Assemblies by Means of a Hot Box Apparatus
- [C1374](#) Test Method for Determination of Installed Thickness of Pneumatically Applied Loose-Fill Building Insulation
- [C1574](#) Guide for Determining Blown Density of Pneumatically Applied Loose-Fill Mineral Fiber Thermal Insulation
- [C1630](#) Guide for Development of Coverage Charts for Loose-Fill Thermal Building Insulations
- [E136](#) Test Method for Behavior of Materials in a Vertical Tube Furnace at 750°C
- [E970](#) Test Method for Critical Radiant Flux of Exposed Attic Floor Insulation Using a Radiant Heat Energy Source
- [G1](#) Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens

3. Terminology

3.1 *Definitions*—For definitions of terms used in this specification, refer to Terminology [C168](#).

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *settled density*—The mass per unit volume of a loose-fill insulation after which time or forces, or both, have exerted their effect upon thickness.

3.2.1.1 *Discussion*—The settled density is determined using long term aging studies in attics.

4. Classification

4.1 The nodulated mineral fiber thermal insulation shall be of the following types and classes:

4.1.1 *Type I*—Pneumatic application.

4.1.2 *Type II*—Poured application.

5. Ordering Information

5.1 Both types of nodulated mineral fiber thermal insulation are intended for use as thermal insulation in open spaces, such as attics and enclosed spaces, such as walls, in housing and

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.23 on Blanket and Loose Fill Insulation.

Current edition approved Sept. 1, 2011. Published September 2011.. Originally approved 1973. Last previous edition approved in 2007 as C764 – 07. DOI: 10.1520/C0764-11.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

buildings at ambient temperatures. Type I is used for pneumatic application (blown or conveyed by an air stream through a hose and discharged over the area to be insulated). Type II is used for application by pouring in place.

6. Materials and Manufacture

6.1 *Basic Material*—The basic material shall be fibers made from mineral substances such as rock, slag, or glass processed from the molten state into an incombustible fibrous form.

6.2 *Manufacture*—The fibers shall be mechanically processed into nodules, and are permitted to be treated to provide improved processing and handling characteristics suitable for installation by pouring or pneumatic applications.

7. Physical Properties

7.1 *Thermal Characteristics*—The standard thermal resistance values normally recommended for open application are expressed in °F·h·ft²/Btu (K·m²/W). Typical values are shown in Table 1. *R* values others than those listed in Table 1 shall be as agreed upon between the supplier and the purchaser. The thermal resistance *R* for the average of any (four) randomly selected samples shall not be more than 5 % below the mutually agreed upon *R* value when tested in accordance with 12.2, nor shall any single specimen be more than 10 % below the mutually agreed upon *R* value.

7.2 *Critical Radiant Flux*—Mineral fiber loose fill when tested in accordance with 12.3 shall have a critical radiant flux-flame propagation resistance ≥0.12 W/cm² (.11 Btu/ft² · s).

7.3 *Combustion Characteristics*—Mineral fiber loose fill when tested in accordance with 12.4 shall not have a recorded temperature rise of more than 54°F (30°C); shall have no flaming after the first 30 s; and, if the specimen weight loss exceeds 50 % during the test, the recorded temperature of the specimen during the test shall not rise above the furnace air

temperature at the beginning of the test, and there shall be no flaming of the specimen.

7.4 *Water Vapor Sorption*—The water vapor sorption of the insulation shall not be more than 5 % by weight when tested in accordance with 12.5.

7.5 *Odor Emission*—A detectable odor of a strong objectionable nature recorded by more than two of the five panel members shall constitute rejection of the material when tested in accordance with 12.6.

7.6 *Corrosiveness*—When tested in accordance with 12.7, the metal plates that are in contact with the insulation shall show no corrosion greater than the comparative plates that are in contact with sterile cotton that has been tested in the same manner.

7.7 *Fungi Resistance*—When tested in accordance with 12.8, the insulation shall have growth no greater than that observed on the white birch tongue depressor comparative material.

8. Other Requirements

8.1 *Qualification Requirements*—The following requirements are generally emphasized for purposes of initial material product requirements:

- 8.1.1 Thermal resistance,
- 8.1.2 Critical radiant flux,
- 8.1.3 Combustion characteristics,
- 8.1.4 Water vapor sorption,
- 8.1.5 Odor emission,
- 8.1.6 Corrosiveness, and
- 8.1.7 Fungi Resistance.

8.2 *Inspection Requirements*—The following requirements are generally emphasized for purposes of acceptance sampling of lots of qualified thermal insulation:

TABLE 1 Coverage Chart

NOTE 1—Chart is occasionally given in metric units.

<i>R</i> Value at 75°F Mean Temperature	Maximum Net Coverage		Minimum Thickness		Minimum Weight per ft ²
To obtain an insulation resistance (<i>R</i>) of:	Minimum bags per 1000 ft ² of net area (bags/MSF)	Maximum ft ² coverage per bag (ft ²)	Installed insulation to be not less than: (in.)	Settled thickness not to be less than: (in.)	The weight per ft ² of installed insulation to be not less than: (lbs/ft ²)
$\frac{h \cdot ft^2 \cdot ^\circ F}{Btu}$					
Attic:					
11					
13					
15					
19					
22					
26					
30					
33					
38					
44					
49					
60					
Sidewalls ^A : <i>R</i> —					

^A Optional information for products intended for sidewall application.

- 8.2.1 Minimum bag weight, and
- 8.2.2 Workmanship.

9. Workmanship

9.1 Mineral fiber nodulated insulation shall be free of foreign materials and shall be clean and dry. The insulation shall not have visible defects that will adversely affect the service quality.

10. Significance and Use

10.1 This specification covers products that are used in buildings. While products that comply with this specification are used in various constructions, they are adaptable primarily, but not exclusively, to wood frame constructions.

11. Sampling and Conditioning

11.1 Sampling of the insulation shall be in accordance with Practice C390. Specific provisions for sampling shall be agreed upon between the purchaser and supplier.

11.2 Condition the test samples in accordance with Practice C870.

12. Test Methods

12.1 *Blown Density*—Determine the blown density in accordance with Guide C1574.

12.2 *Thermal Resistance*—Using samples prepared in accordance with 12.1 and adjusted to the settled density, the thermal conductivity or thermal conductance shall be determined in accordance with Test Method C518, Test Method C177, or derived from measurements made by Test Method C1363. The mean temperature shall be 75°F (23.9°C) and the temperature difference shall be a minimum of 40°F (22°C). The thermal resistance shall then be calculated from the thermal conductance values using Practice C687. See Note 1.

NOTE 1—The thermal resistance is a function of mean temperature. As an option, determine the thermal resistance at additional mean temperatures as agreed upon by the purchaser and the manufacturer.

12.3 *Critical Radiant Flux*—The critical radiant flux of the insulation shall be determined in accordance with Test Method E970.

12.4 *Behavior of Materials in a Vertical Tube Furnace at 1382°F (750°C)*—The behavior of mineral fiber loose-fill insulation in a vertical tube furnace at 1382°F (750°C) shall be determined in accordance with Test Method E136.

12.5 *Water Vapor Sorption*—The water vapor sorption of the test specimen shall be determined in accordance with Test Method C1104/C1104M.

12.6 *Odor Emission*—Determine the odor emission in accordance with Test Method C1304.

12.7 Corrosiveness:

12.7.1 *Scope*—This test method provides a qualitative measure of the corrosiveness of mineral fiber insulation by comparison to a control.

12.7.2 Summary of Test Method:

12.7.2.1 Individually sandwich five each of specially cleaned steel, copper, and aluminum test plates between pieces

of insulation. Hold the insulation uniformly against each side of the test plate with wire screens and rubber bands.

12.7.2.2 Sandwich an equal number of cleaned metal test plates between pieces of washed sterile cotton in an identical manner.

12.7.2.3 Vertically suspend the samples in a humidity test chamber at $95 \pm 3\%$ relative humidity and temperature of $120 \pm 3^\circ\text{F}$ ($49 \pm 2^\circ\text{C}$) for time periods determined by the type of metal being tested. Steel is tested for 96 ± 2 h. Copper and aluminum are tested for 720 ± 5 h.

12.7.2.4 After the appropriate test period, compare the test plates exposed to the insulation to the control plates exposed to sterile cotton for severity of corrosion. The insulation is considered to have passed this test if the corrosion attributed to the insulation is not significantly worse than that of the washed sterile cotton controls. The criterion for acceptance is predetermined through the use of non-parametric statistics and a 90 % confidence level ($\alpha = 0.10$).

12.7.3 Significance and Use:

12.7.3.1 The fiber composition and the type of binder used in the manufacture of mineral fiber insulation sometimes create a potential for corrosion on certain metals in the presence of liquid water or water vapor.

12.7.3.2 This test method is used to determine the relative corrosion potential of mineral fiber insulation on specific metals under high humidity conditions.

12.7.4 Materials:

12.7.4.1 *Metal Test Plates*, with dimensions of 1 by $4 \pm \frac{1}{4}$ in. (25 by 100 mm). Steel plates shall be 0.02 ± 0.005 in. (0.5 mm) thick, bright No. 2 finish, cold-rolled low-carbon strip steel, quarter hard, temper No. 3. The aluminum plates shall be 0.025 ± 0.005 in. (0.6 mm) thick, type 3003-0. Copper plates shall be 0.032 ± 0.005 in. (0.8 mm) thick, in accordance with Specification B152/B152M type ETP, No. 110 soft copper.

12.7.4.2 *Woven Wire Screen*, $1\frac{1}{2} \pm \frac{1}{4}$ by $4\frac{1}{2} \pm \frac{1}{4}$ in. (114 by 38 mm), made of Type 304 stainless steel, 0.063 ± 0.005 in. (1.60 mm) wire, $\frac{7}{16} \pm \frac{1}{16}$ in. (11 mm) open-square grid.

12.7.4.3 *Rubber Bands*, No. 12.

12.7.4.4 *Humidity Test Chamber* clean, well maintained, and capable of controlling temperature at $120 \pm 3^\circ\text{F}$ ($49 \pm 2^\circ\text{C}$) and humidity at $95 \pm 3\%$ relative humidity.

12.7.4.5 *Cheesecloth or Cotton Gauze*, cut into 6 by 10-in. (152 by 254-mm) pieces.

12.7.4.6 *Sample Preparation Fixture*, having a rectangular compartment or well with interior dimensions of $4\frac{1}{2}$ by $1\frac{1}{2}$ by $1\frac{1}{2}$ in. (114 by 38 by 38 mm) with one $4\frac{1}{2}$ by $1\frac{1}{2}$ in. (114 by 38 mm) opening.

12.7.5 *Test Specimen*—A test specimen shall consist of a layer of loose-fill insulation held in place on each side of the metal test plate by a cheesecloth wrap. The loose-fill insulation is compressed uniformly against each side of the metal test plate using woven wire screening and a No. 12 rubber band at each end so that there is approximately a $4\frac{1}{2}$ by $1\frac{1}{2}$ by $\frac{1}{2}$ -in. (114- by 38- by 13-mm) thick layer of insulation on each side of the metal test plate.

12.7.6 Test Method:

12.7.6.1 Clean the metal test plates until the surface is free of water breaks. Clean the steel test plates first by 5 min of

vapor degreasing (using 1-1-1 trichlorethane or chloroprene). After degreasing, wipe residue from both sides of the coupons using paper laboratory wipes. Then immerse for 15 min in a hot caustic solution (15 % KOH by volume), rinse thoroughly in distilled water, and immediately dry using paper laboratory wipes. Degrease the copper plates in the same manner and then further clean in a hot acidic solution (10 % nitric acid by volume) for 15 min. Rinse the copper plates and dry immediately using paper laboratory wipes. Clean the aluminum plates with a 5 % solution all-purpose laboratory detergent and water, then rinse in distilled water and dry with laboratory wipes. Care shall be taken to avoid excessive handling of the surfaces of the metal plates. They shall not be touched after the final cleaning step. Plastic surgical gloves or their equivalent are recommended for handling of plates. Also clean the wire screens before use in the same manner as the aluminum plates (that is, wash in detergent, rinse in distilled water, and dry).

12.7.6.2 Build up the five test specimens as follows: place one woven wire screen in the compartment bottom, center and drop the cheesecloth over the compartment. Place a quantity of loose-fill insulation into the compartment and tamp the insulation to form a uniform pack $4\frac{1}{2}$ by $1\frac{1}{2}$ by $\frac{1}{2}$ in. (114 by 38 by 13 mm) thick. Place a metal test plate over the insulation, adding more insulation over the metal test plate and tamp to achieve a uniform top layer $4\frac{1}{2}$ by $1\frac{1}{2}$ by $\frac{1}{2}$ in. (114 by 38 by 13 mm) thick. Fold the cheesecloth around this configuration. Place a woven wire screen on top of the assembly and secure the assembly at each end with a No. 12 rubber band.

12.7.6.3 Make five test specimens, each one consisting of one piece of metal placed between two pieces of insulation. Compress this assembly between two pieces of woven wire screen and secured near each end with a No. 12 rubber band. The compressed thickness of this assembly shall measure $1 \pm \frac{1}{8}$ in. (25 ± 3 mm).

12.7.6.4 Assemble five control specimens, each consisting of one piece of metal placed between two $1\frac{1}{2}$ by $4\frac{1}{2}$ by $\frac{1}{2}$ in. (38 by 114 by 13 mm) pieces of sterile cotton. Identify the outer surface of the cotton as rolled. After cleaning, the sterile cotton surface shall be the surface placed against the metal coupons in the same manner as the insulation specimen. The sterile cotton shall have previously been solvent extracted in reagent grade acetone³ for 48 h, and then vacuum dried at low heat. Compress these specimens and secure in exactly the manner described in 12.7.6.2.

12.7.6.5 Suspend the five test specimens and five control specimens vertically in an atmosphere free of contaminants, having a relative humidity of 95 ± 3 %, and a temperature of $120 \pm 3^\circ\text{F}$ ($49 \pm 2^\circ\text{C}$) for the specified test period (96 ± 2 h for steel, 720 ± 5 h for copper and aluminum). The humidity chamber shall remain closed for the entire test period. If the chamber must be opened, care shall be taken to ensure that no condensation is within the chamber. At the conclusion of the

test period, remove the specimens from the chamber, disassemble, and mark to distinguish individual plates.

12.7.6.6 Closely examine the surfaces of each of the test and control plates for the following characteristics:

(1) *Steel*—The presence and relative severity of red rust and pitting. Surface blush shall not be weighed strongly.

(2) *Aluminum*—The presence and relative severity of pitting, scaling, or other evidence of attack. The generation of oxide is a protective mechanism of aluminum and shall be disregarded. Remove the oxide by scrubbing with a non-abrasive rubber implement under running water or immersion in a 70 % solution of nitric acid.

(3) *Copper*—Presence and relative severity of scaling, pitting, deposits, or encrustation, severe discolorations, or general uniform attack. Surface blush and slight discolorations shall be ignored and removed by scrubbing with a non-abrasive rubber implement under running water or immersing into a 10 % solution of sulfuric acid.

NOTE 2—Additional guidance for evaluating the plates can be found in Practice G1.

12.7.7 Interpretation of Results:

12.7.7.1 Because of the subjectivity inherent in the judging of these plates, nonparametric statistical methods are employed to identify those materials which are conclusively more corrosive than sterile cotton.

12.7.7.2 The ten metal plates (five test, five control), shall be examined by at least four judges with experience in corrosion evaluation. Each judge shall independently rank all ten plates in order from least severe corrosion to most severe corrosion. The judges shall receive no indication as to which plates are control and which are test specimens. The judges' rankings shall be based on their own best estimate of the severity of the corrosion visible on each plate.

12.7.7.3 Upon completion of the judges' ratings, the arithmetic sum of all of the rankings for each plate shall be calculated. These sums shall then be ranked from 1 (lowest total) to 10 (highest total) with any ties being assigned the arithmetic mean of the rankings involved (for example, two plates tied for third = $(3 + 4)/2 = 3.5$; three plates tied for fourth = $(4 + 5 + 6)/3 = 5$). The new rankings thus established shall then be totaled for the control plates only; if this sum is less than 21, then the control plates are judged to be significantly better than the test plates and the insulation tested is considered to have *failed* the test. Any sum of the rankings for the five control plates greater than or equal to 21 indicates that there is no statistical difference between the control and test plates and the insulation *passes*.

12.7.8 *Precision and Bias*—Assuming that there is no bias involved in the judges' rankings, this test method will identify those materials which are significantly worse than sterile cotton with a statistical confidence of $\alpha = 0.10$. This means that a material which is judged to be more corrosive to a metal than sterile cotton has at most a 10 % chance of being incorrectly failed. This test method can make no estimate of the probability that an insulation which is more corrosive than sterile cotton will not be identified as such.

12.8 *Fungi Resistance*—Determine fungi resistance in accordance with Test Method C1338.

³ Reagent Chemicals, American Chemical Society Specifications, American Chemical Society, Washington, DC. For Suggestions on the testing of reagents not listed by the American Chemical Society, see *Annual Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

12.9 *Installed Thickness*—Determine the installed thickness in accordance with Test Method **C1374**.

13. Inspection

13.1 Inspection of the insulation shall be made as agreed upon by the purchaser and the manufacturer as part of the purchase contract.

14. Packaging and Package Marking

14.1 *Packaging*—Unless otherwise specified, the insulation shall be packaged in the manufacturer's standard commercial containers.

14.2 *Package Marking*—Markings shall be clear and legible. Unless otherwise specified, each container shall be marked as follows:

14.2.1 Name of manufacturer,

14.2.2 Type of insulation,

14.2.3 Net weight of insulation per bag,

14.2.4 The manufacturer recommends that the insulation be installed at these minimum thicknesses, maximum coverages, to provide the levels of insulation thermal resistance (*R*-value) shown. The specific blowing machine type and machine settings used to determine the initial installed thicknesses shall be stated on the bag.

14.2.5 *Coverage Chart*—The chart, **Table 1**, for thermal and coverage values shall be based on product settled density, determined by one of the procedures in Guide **C1630**, except for the initial installed thickness which is determined by using Test Method **C1374**.

14.2.6 *Certification*—The certification shall state the following:

14.2.6.1 This insulation has been installed in conformance with the above recommendations to provide a value of *R*-_____ using _____ bags of this insulation to cover _____ square feet of area,

14.2.7 Place for the signature of the builder, company name and date,

14.2.8 Place for the signature of the applicator, company name and date.

NOTE 3—A separate attic card containing the same information will satisfy the requirements of **14.2.5**, **14.2.6**, **14.2.7**, and **14.2.8**.

14.2.9 Where material is intended for both blowing or pouring application, the bag shall have a separate coverage chart for each type of application.

15. Keywords

15.1 loose-fill; mineral fiber; thermal insulation

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the ASTM website (www.astm.org/COPYRIGHT/).