



Standard Test Method for Methylene Blue Index of Clay¹

This standard is issued under the fixed designation C837; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the measurement of the adsorption of methylene blue dye by a clay, which is calculated as a methylene blue index for a clay.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:²

C324 Test Method for Free Moisture in Ceramic Whiteware Clays

3. Significance and Use

3.1 Tests run on many clays generally indicate that a straight-line relationship exists between the methylene blue index (MBI) and such fundamental clay properties as cation exchange capacity, dry bond strength, and casting rate. Where the colloidal portion of the clay is kaolinite, there is also a direct correlation with specific surface (as determined by nitrogen adsorption). Where the colloidal portion contains significant amounts of illite or montmorillonite, the same close correlation does not exist. The MBI better correlates with the ceramic-forming properties than does the specific surface.

3.2 That portion of a clay lying within the colloidal range (generally defined as the 0.5- to 0.001- μ m range), determines the strictly colloidal properties of the clay and, together with the amount and type of organic material associated with the

clay and the 2- to 0.2- μ m fraction, largely determines the properties of the clay when used in ceramic-forming processes. While the specific surface of a clay is a function of the particle size and morphology and a relationship exists between dye adsorption and specific surface, the MBI should not be considered to be a particle size analysis since the value obtained is dominated by the character of only the very fine end of the particle size distribution. This procedure describes the determination of the dye adsorption (in this case, methylene blue) of a clay.

4. Apparatus

4.1 *Balance*, accurate to 0.01 g.

4.2 *Mixer*.

4.3 *pH Meter or pH Paper*.

4.4 *Beaker*, 600 mL.

4.5 *Buret*, 25 mL.

4.6 *Medicine Dropper or Glass Stirring Rod*.

4.7 *Filter Paper*. Baroid No. 987.

5. Reagents

5.1 *Purity of Reagents*—Reagent grade chemicals shall be used in all tests. Unless otherwise indicated, it is intended that all reagents shall conform to the specifications of the Committee on Analytical Reagents of the American Chemical Society, where such specifications are available.³ Other grades may be used, provided it is first ascertained that the reagent is of sufficiently high purity to permit its use without lessening the accuracy of the determination.

5.2 *Purity of Water*—Unless otherwise indicated, references to water shall be understood to mean distilled water or water of equal purity.

5.3 *Methylene Blue Solution (1 mL = 0.01 meq)*³—Store in darkness.

¹ This test method is under the jurisdiction of ASTM Committee C21 on Ceramic Whitewares and Related Products and is the direct responsibility of Subcommittee C21.04 on Raw Materials.

Current edition approved Dec. 1, 2014. Published December 2014. Originally approved in 1976. Last previous edition approved in 2009 as C837 – 09. DOI: 10.1520/C0837-09R14.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ *Reagent Chemicals, American Chemical Society Specifications*, American Chemical Society, Washington, DC. For suggestions on the testing of reagents not listed by the American Chemical Society, see *Analar Standards for Laboratory Chemicals*, BDH Ltd., Poole, Dorset, U.K., and the *United States Pharmacopeia and National Formulary*, U.S. Pharmacopeial Convention, Inc. (USPC), Rockville, MD.

5.4 Sulfuric Acid (0.1N).

6. Procedure

6.1 Weigh out 2.00 g of clay that has been dried in accordance with the procedure in Test Method **C324** and place in the 600-mL beaker. If the clay cannot be tested immediately after drying, it should be stored in a desiccator.

6.2 Add 300 mL of distilled water to the beaker and stir with the mixer until the clay is uniformly dispersed.

6.3 Determine the pH of the slurry and add sufficient sulfuric acid to bring the pH within the range from 2.5 to 3.8. Continue stirring while the pH is being adjusted and continue stirring for 10 to 15 min after the last addition of acid.

6.4 Again test the slurry for pH, adding additional acid if necessary to restore the pH to the 2.5 to 3.8 range.

6.5 With the slurry still under the mixer, fill the buret with the methylene blue solution, add 5 ml of the solution to the slurry, and stir for 1 to 2 min.

6.6 Remove a drop of the slurry, using the dropper or the glass stirring rod, and place on the edge of the filter paper.

6.7 Observe the appearance of the drop on the filter paper. The end point is indicated by the formation of a light blue halo around the drop. Continue adding the methylene blue solution to the slurry in 1.0-mL increments with 1 to 2 min of stirring after each addition, then testing, until the end point is reached. For ball clays with relatively high methylene blue indexes, testing may start after two or even three 5-mL additions have been made to save time. Allow 1 to 2 min of stirring after each 5-mL increment.

6.8 After the end point is reached, continue stirring for 2 min and retest.

NOTE 1—Greater precision can be obtained by using larger samples with only minor influence on the value obtained.

7. Calculation

7.1 Calculate the methylene blue index as follows:

$$\text{MBI} = \frac{E \times V}{W} \times 100$$

where:

MBI = methylene blue index for the clay in meq/100 g clay,
E = milliequivalents of methylene blue per millilitre (see **5.3**),
V = millilitres of methylene blue solution required for the titration, and
W = grams of dry material.

7.2 The calculations may be facilitated by using a multiplication factor where the specimen size is 2.00 g and the methylene blue titrating solution is 0.01N:

$$\begin{aligned} \text{MBI} &= \frac{0.01 \times V}{2} \times 100 \\ &= 0.5 V \end{aligned}$$

7.3 Record the methylene blue index for the clay.

8. Precision and Bias

8.1 The precision of this test method is the calculated methylene blue index (MBI) ± 0.25 meq/100 g clay. The MBI value cannot be directly related to any single, simply measured, characteristic of the clay; thus the bias of this test method cannot be specified.

9. Keywords

9.1 bond strength; casting rate; cation exchange capacity; clay; colloidal range; MBI

SUMMARY OF CHANGES

Committee C21 has identified the location of selected changes to this standard since the last issue (C837–99 (2003)) that may impact the use of this standard.

(1) Addition of **1.2**, describing the use of units in this test method, with renumbering of the subsequent sections of the Scope.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/