This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.



Standard Practice for Petrographic Examination of Hardened Concrete¹

Section

This standard is issued under the fixed designation C856; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This practice outlines procedures for the petrographic examination of samples of hardened concrete. The samples examined may be taken from concrete constructions, they may be concrete products or portions thereof, or they may be concrete or mortar specimens that have been exposed in natural environments, or to simulated service conditions, or subjected to laboratory tests. The phrase "concrete constructions" is intended to include all sorts of objects, units, or structures that have been built of hydraulic cement concrete.

Note 1—A photographic chart of materials, phenomena, and reaction products discussed in Sections 8 - 13 and Tables 1-6 are available as Adjunct C856 (ADJCO856).

1.2 The petrographic procedures outlined herein are applicable to the examination of samples of all types of hardened hydraulic-cement mixtures, including concrete, mortar, grout, plaster, stucco, terrazzo, and the like. In this practice, the material for examination is designated as "concrete," even though the commentary may be applicable to the other mixtures, unless the reference is specifically to media other than concrete.

1.3 The purposes of and procedures for petrographic examination of hardened concrete are given in the following sections:

Qualifications of Petrographers and Use of Technicians	4
Purposes of Examination	5
Apparatus	6
Selection and Use of Apparatus	7
Samples	8
Examination of Samples	9
Specimen Preparation	10
Visual and Stereomicroscope Examination	11
Polarizing Microscope Examination	12
Paste Features	13
Report	14

1.4 The values stated in inch-pound units are to be regarded as the standard. The SI units in parentheses are provided for information purposes only. 1.5 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use. A specific hazard statement is given in 6.2.10.1.

2. Referenced Documents

- 2.1 ASTM Standards:²
- C125 Terminology Relating to Concrete and Concrete Aggregates
- C215 Test Method for Fundamental Transverse, Longitudinal, and Torsional Resonant Frequencies of Concrete Specimens
- C227 Test Method for Potential Alkali Reactivity of Cement-Aggregate Combinations (Mortar-Bar Method)
- C342 Test Method for Potential Volume Change of Cement-Aggregate Combinations (Withdrawn 2001)³
- C441 Test Method for Effectiveness of Pozzolans or Ground Blast-Furnace Slag in Preventing Excessive Expansion of Concrete Due to the Alkali-Silica Reaction
- C452 Test Method for Potential Expansion of Portland-Cement Mortars Exposed to Sulfate
- C457 Test Method for Microscopical Determination of Parameters of the Air-Void System in Hardened Concrete
- C496/C496M Test Method for Splitting Tensile Strength of Cylindrical Concrete Specimens
- C597 Test Method for Pulse Velocity Through Concrete
- C803/C803M Test Method for Penetration Resistance of Hardened Concrete
- C805 Test Method for Rebound Number of Hardened Concrete
- C823 Practice for Examination and Sampling of Hardened Concrete in Constructions
- C1012 Test Method for Length Change of Hydraulic-Cement Mortars Exposed to a Sulfate Solution
- C1260 Test Method for Potential Alkali Reactivity of Aggregates (Mortar-Bar Method)

*A Summary of Changes section appears at the end of this standard

¹ This practice is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.65 on Petrography.

Current edition approved Jan. 1, 2017. Published March 2017. Originally approved in 1977. Last previous edition approved in 2014 as C856 – 14. DOI: 10.1520/C0856-17.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

 $^{^{3}\,\}mathrm{The}$ last approved version of this historical standard is referenced on www.astm.org.

(III) C856 – 17

TABLE 1 Visual Examination of Concrete (1)⁵

Coarse Aggregate	+ Fine Aggreg	ate	+ Matrix	+ Air	+ Embedded Items
Composition: Maximum dimension, ^A in. or mm. in the range> $d>$					
Туре:	Туре:		color, by comparison with National Research Council <i>Rock Color</i> <i>Chart</i> (1963)	more than 3 % of total,	Type, size, location; kinds of metal; other items
1 Gravel 2 Crushed stone 3 Mixed 1 and 2 4 Other (name) 5 Mixed 1 + /or 2 + /or 4 If Type 1, 2, or 4, homogeneous or heterogeneous Lithologic types Coarse aggregate more than 20, 30, 40, or 50 % of total	1 Natural sand 2 Manufactured sand 3 Mixed 4 Other (name) 5 Mixed 1 + /or 2 + /c If Type 1, 2, or 4, homogeneous or heterogeneous	or 4	color distribution: 1 mottled 2 even 3 gradational changes	predominantly in spherical voids? less than 3 % of total, abundant nonspherical voids? color differences between voids and mortar? voids empty, filled, lined, or partly filled	
Fabric: Shape Distribution Packing Grading (even, uneven,	distribution particle shape grading preferred orientation	as per- ceptible	distribution	shape distribution grading (as perceptible) parallelism of long axes of	voids below horizontal or low-angle reinforcement
excess, or deficiency of size or sizes) Parallelism of flat sides or long axes of exposed sections, normal to direction of placement + /or parallel to formed and finished surfaces ^B				irregular voids or sheets of voids: with each other; with flat sides or long axes of coarse aggregate	
Condition: Does it ring when hit lightly with a Through or around coarse aggrega Surface deposits? If air drv. are the	hammer or give a dull flat s ate? With cores or sawed sp ere unusually wet or drv lool	ound? Can ecimens, c king areas	you break it with your fingers? did the aggregate tear in drilling ? Rims on aggregate?	? Cracks? How distributed? g or sawing? Crack fillings?	clean or corroded? Are cracks associated with embedded items?

^A A substantial portion of the coarse aggregate has maximum dimensions in the range shown as measured on sawed or broken surfaces.

^B Sections sawed or drilled close to and parallel to formed surfaces appear to show local turbulence as a result of spading or rodding close to the form. Sections sawed in the plane of bedding (normal to the direction of placement) are likely to have inconspicuous orientation. Sections broken normal to placement in conventionally placed concrete with normal bond tend to have aggregate knobs abundant on the bottom of the upper piece as cast and sockets abundant on the top of the lower piece as cast.

E3 Guide for Preparation of Metallographic Specimens E883 Guide for Reflected–Light Photomicrography 2.2 *ASTM Adjuncts:* Adjunct C856 (ADJCO856) A chart of 27 photos⁴

3. Terminology

3.1 *Definitions:* For definitions of terms used in this practice, refer to Terminology C125.

4. Qualifications of Petrographers and Use of Technicians

4.1 All petrographic examinations of hardened concrete described in this practice shall be performed by or under the technical direction of a full time supervising petrographer with at least 5 years experience in petrographic examinations of concrete and concrete-making materials. The supervising concrete petrographer shall have college level courses that include petrography, mineralogy, and optical mineralogy, or 5 years of

documented equivalent experience, and experience in their application to evaluations of concrete-making materials and concrete products in which they are used and in cementitiousbased materials. A resume of the professional background and qualifications of all concrete petrographers shall be available.

4.2 A concrete petrographer shall be knowledgeable about the following: concrete-making materials; processes of batching, mixing, handling, placing, and finishing of hydrauliccement concrete; the composition and microstructure of cementitious paste; the interaction of constituents of concrete; and the effects of exposure of such concrete to a wide variety of conditions of service.

4.3 Sample preparation shall be performed by concrete petrographers or trained technicians pursuant to instructions from and under the guidance of a qualified concrete petrographer. Aspects of the petrographic examination, such as the measurement of sample dimensions, photography of asreceived samples, staining of sample surfaces, that do not require the education and skills outlined in 4.1, shall be

⁴ Available from ASTM International Headquarters. Order Adjunct No. ADJC0856. Original adjunct produced in 1995.



TABLE 2 Outline for Examination of Concrete with a Stereomicroscope (1)

NOTE 1—*Condition*—When it is examined at 6 to 10× under good light, the freshly broken surface of a concrete in good physical condition that still retains most of its natural moisture content has a luster that in mineralogical terms is subtranslucent glimmering vitreous.^A Thin edges of splinters of the paste transmit light; reflections appear to come from many minute points on the surface, and the quality of luster is like that from broken glass but less intense. Concrete in less good physical condition is more opaque on a freshly broken surface, and the luster is dull, subvitreous going toward chalky. A properly cured laboratory specimen from a concrete mixture of normal proportions cured 28 days that has shown normal compressive or flexural strength and that is broken with a hammer and examined on a new break within a week of the time that it finished curing should provide an example of concrete in good physical condition.

Under the same conditions of examination, when there is reasonable assurance that the concrete does not contain white portland cement or slag cement, the color of the matrix of concrete in good physical condition is definitely gray or definitely tan, except adjoining old cracks or original surfaces.

Coarse Aggregate	Fine Aggregate	Matrix	Voids
Coarse Aggregate Lithologic types and mineralogy as percep- tible Surface texture Within the piece: Grain shape Grain size extreme range observed, mm Median within range _ to _ mm Textureless (too fine to resolve) Uniform or variable within the piece From piece to piece: Intergranular bond Porosity and absorption ^B If concrete breaks through aggregate, through how much of what kind? If boundary voids, along what kind of aggregate? All? All of one kind? More	Fine Aggregate Lithologic types and miner- alogy as perceptible Shape Surface texture Grading Distribution	Matrix Color Fracture around or through aggregate Contact of matrix with aggregate: close, no opening visible on sawed or broken surface; aggregate not dislodged with fingers or probe; boundary openings frequent, common, rare Width Empty Filled Cracks present, absent, result of spec- imen preparation, preceding spec- imen preparation Supplementary Cementitious Materials ^C Contamination	Grading Proportion of spherical to nonspherical Nonspherical, ellipsoidal, irregular, disk- shaped Color change from interior surface to matrix Interior surface luster like rest of ma- trix, dull, shining Linings in voids absent, rare, common, in most, complete, partial, colorless, colored, silky tufts, hexagonal tab- lets, gel, other Underside voids or sheets of voids un- common, small, common, abundant
than 50 % of one kind? Several kinds?		Bleeding	

^A Dana, E. S., Textbook of Mineralogy, revised by W. E. Ford, John Wiley & Sons, New York, N. Y., 4th ed., 1932, pp. 273–274.

 $^{\scriptscriptstyle B}$ Pore visible to the naked eye, or at \times _, or sucks in water that is dropped on it.

^C Dark solid spheres or hollow-centered spheres of glass, or of magnetite, or some of glass and some of magnetite, recognizable at magnification of × 9 on sawed or broken surfaces. Other mineral admixtures with characteristic particles visible at low magnification are recognizable. Ground surface of concrete containing portland blast-furnace slag cement are unusually white near-free surfaces but retain greenish or blue-greenish patches, and slag particles can be seen with the stereomicroscope or polarizing microscope.

performed by concrete petrographers or by trained technicians pursuant to instructions and under the guidance of a qualified concrete petrographer. The analysis and interpretation of the features that are relevant to the investigation and evaluation of the performance of the materials represented by the sample shall be made solely by concrete petrographers with qualifications consistent with those outlined in 4.1.

4.4 A concrete petrographer shall be prepared to provide an oral statement, written report, or both that includes a description of the observations and examinations made during the petrographic examinations, and interpretation of the findings insofar as they relate to the concerns of the person or agency for whom the examination was performed. Supplementary information provided to the petrographer on the concrete and concrete materials, conditions of service, or other features of the concrete construction may be helpful in interpreting the data obtained during the petrographic examinations.

4.5 This practice may form the basis for establishing arrangements between a purchaser of the consulting service and the consulting petrographer. In such cases, the purchaser of the consulting service and the consulting petrographer should together determine the kind, extent, and objectives of the examinations and analyses to be made, and may record their agreement in writing. The agreement may stipulate specific determinations to be made, observations to be reported, funds to be obligated, or a combination of these and other conditions.

5. Purposes of Examination

5.1 Examples of purposes for which petrographic examination of concrete is used are given in 5.2 - 5.5. The probable usefulness of petrographic examination in specific instances may be determined by discussion with an experienced petrographer of the objectives of the investigation proposed or underway.

5.2 Concrete from Constructions:

5.2.1 Determination in detail of the condition of concrete in a construction.

5.2.2 Determination of the causes of inferior quality, distress, or deterioration of concrete in a construction.

5.2.3 Determination of the probable future performance of the concrete.

5.2.4 Determination whether the concrete in a construction was or was not as specified. In this case, other tests may be required in conjunction with petrographic examination.

5.2.5 Description of the cementitious matrix, including qualitative determination of the kind of hydraulic binder used, degree of hydration, degree of carbonation if present, evidence of unsoundness of the cement, presence of supplementary cementitious materials, the nature of the hydration products, adequacy of curing, and unusually high water–cement ratio of the paste.

5.2.6 Determination whether alkali–silica or alkali–carbonate reactions, or cement–aggregate reactions, or reactions



TABLE 3 Effects of Fire on Characteristics of Concrete

Characteristic	Causes and E	Effects	Ways of Investigation
Surface hardness	Dehydration to 100°C removes free water; dehydration is essentially complete at 540°C; calcium hydroxide goes to CaO at 450–500°C. Paste expands with thermal coefficient effect and then shrinks, cracks, decrepitates, and becomes soft (2).		Beneath the softened concrete, which can be tested in accordance with Test Method C805, the concrete is probably normal if it has not undergone color change. Establish by coring for compressive tests, by wear tests (CRD-C 52) (2), and by scratching with a knife.
Cracking	Perpendicular to the face and internal, where heating or cooling caused excess tensile stresses. In some new concrete, resembles large-scale shrinkage cracking; may penetrate up to 100 mm but may heal autogenously (2).		Examination of the surface, ultrasonic tests, coring, petrographic examination (2).
<i>Color change</i> —When concrete has not spalled, observe depth of pink color to estimate the fire exposure.	Concrete made with sedimentary or aggregates shows permanent colo Color normal to 230°C; goes from 590°C; from 590 to 900°C color of then to buff (2). For temperatures temperature distribution is little affic carbonate rather than siliceous ag low quartz inverts to high with 0.88 volume, producing popouts. Spalli expose one fourth of the bar at 79 decomposed hydration products a crazing about 290°C; deeper craci	metamorphic or change on heating. pink to red from 290 to hanges to gray and up to about 500°C ected by using gregate (3). At 573°C 5 % increase in ng over steel to 10°C; white powdered t 900°C. Surface king about 540°C	Color change is the factor most useful to the investigator; permits recognizing how deeply a temperature of about 300°C occurred (3).
Aggregate behavior—Aggregate behavior affects strength, modulus, spalling, cracking, surface hardness, and residual thermal strains (2).	Aggregates differ in thermal diffusivit coefficient of expansion. Heat tran from concrete made with highly sil sandstone, traprock, limestone, lig (2)	y, conductivity, smission decreases liceous aggregate, htweight aggregates	Changes on heating are often accompanied by volume change (2).
Spalling	Occurs subparallel to free face; follo saucer-like pieces especially at co	wed by breaking off	
Note: Compressive strength and elastic modulus. For concrete at least 1-year old, strength will increase after cooling	Reduction in strength of concrete containing siliceous gravel after heating, then cooling and testing: Heated to Temperature		Determinations by compressive tests and static modulus of cores; Test Method C805 for qualitative determination; Test Method C597(2).
from 300°C if design strength was	° C	Reduction, %	
attained (3).	180	25	
	370	50	
	570	80	
	Reduction in Modulus		
	Temperature,° C	Reduction, %	
	200	25	
	430	50	
	/0/	70	

between contaminants and the matrix have taken place, and their effects upon the concrete.

5.2.7 Determination whether the concrete has been subjected to and affected by sulfate attack, or other chemical attack, or early freezing, or to other harmful effects of freezing and thawing.

5.2.8 Part of a survey of the safety of a structure for a present or proposed use.

5.2.9 Determination whether concrete subjected to fire is essentially undamaged or moderately or seriously damaged.

5.2.10 Investigation of the performance of the coarse or fine aggregate in the structure, or determination of the composition of the aggregate for comparison with aggregate from approved or specified sources.

5.2.11 Determination of the factors that caused a given concrete to serve satisfactorily in the environment in which it was exposed.

5.2.12 Determination of the presence and nature of surface treatments, such as dry shake applications on concrete floors.

5.3 Test Specimens from Actual or Simulated Service— Concrete or mortar specimens that have been subjected to actual or simulated service conditions may be examined for most of the purposes listed under Concrete from Constructions.

5.4 Concrete Products:

5.4.1 Petrographic examination can be used in investigation of concrete products of any kind, including masonry units, precast structural units, piling, pipe, and building modules. The products or samples of those submitted for examination may be either from current production, from elements in service in constructions, or from elements that have been subjected to tests or to actual or simulated service conditions.

5.4.2 Determination of features like those listed under concrete from constructions.

5.4.3 Determination of effects of manufacturing processes and variables such as procedures for mixing, molding, demolding, consolidation, curing, and handling.

5.4.4 Determination of effects of use of different concretemaking materials, forming and molding procedures, types and amounts of reinforcement, embedded hardware, etc.

5.5 *Laboratory Specimens*—The purposes of petrographic examination of laboratory specimens of concrete, mortar, or cement paste are, in general, to investigate the effects of the test on the test piece or on one or more of its constituents, to provide examples of the effects of a process, and to provide the petrographer with visual evidence of examples of reactions in

C856 – 17

TABLE 4 Outline for Examination of Concrete in Thin Sections

Mineralogy, texture, fabric, variable or homogeneous. Normal cement paste consists in plane transmited only residual cement grains are those that were largest, which may be composed of several constituents or bed all the orbite (substituted boundaries in aggregate. Normal cement paste consists in plane transmited but devises or deficiency of sand sizes is to boundaries in aggregate. Normal cement paste consists in plane transmited but devises or deficiency of sand sizes is to boundaries in aggregate. Normal cement paste consists in plane transmited but devises or trushed stone; nature constituents or bed is left or bettle (substituted but net paste constituents) the paste constituents or bed all in the orbite (substituted but net paste constituents). Normal cement paste consists in plane transmited but or frageregate index of refractions or but but the orbite (substituted but net paste constituents or bed is net paste but net paste is black or very dark motified gray with scattered anhedral appringence of allie in disorted quashiexaponal in high refractive index and place transmited brown reactions or the coarse apgregate is a carbonate rock or rocks, are there from calcium hydroxide along the doninitic portion while he paste along the doninitic portion while he paste loading the innextone portion is normal. See other comments in Column 3. Normal cement paste is black or very dark motified gray with scattered anhedral apgregate is a carbonate rock or rocks, are thare in the correct of the paste along the doninitic portion while he paste along the column hydroxide along the doninitic portion is normal. See other comments in Column 3. Alkal - salica reaction - Does the aggregate contain in acroad gagregate, previous of the bay witch or the torocare bay witch in the ordion form is orbite or the hydraton in bisch or the coarrete or any of the pastite and or	Coarse and Fine Aggregate	Relict Cement Grains and Hydration Products	Characteristics of Cement Paste
homogeneous. Grading: excess or deficiency of sand sizes is to be judged after examination of a series of thin sections. Grading: excess or deficiency of sand sizes is to particulated is agregate. Classification of coarse and fine aggregate. Classification of coarse and fine aggregate acrushed some nature or manufactured fine aggregate. Bond with matrix: peripheral cracks inside the borders of agregate agregate, internal cracks. General microfractures if one can establish that they existed before thin-sectioning. <i>Alkai - catchonset reactions</i> —If the coarse aggregate is a carbonate rock rocks, at the aggregate is a carbonate rock rocks. The beast profine is bordy or of the granitic grani	Mineralogy, texture, fabric, variable or	In concrete over 2 years old and normally cured, the	Normal cement paste consists in plane transmitted
Grading: excess or deficiency of sand sizes is to be judged after examination of a series of thim sections. Grain size and nature of internal boundaries in aggregate. Casification of coarse and fine aggregate. Casification of coarse borders of aggregate grains; internal cracks General microinclatures of ne case is hisdle the borders of aggregate grains; internal cracks. General microinclatures of ne can establish that they existed before thin-sectioning. <i>Alkali- cachonale</i> reactions—the bocase trans to partial tims depleted in calcium typdroxide Party doomlit crocks that have reacted sometimes are bordered with paste fre- form calcium hydratites and pleochrosim masked by the cocho of the grain. Traclaturin alluminate is usually not recognized in this section because the cubit form is isotropic ettingile or toreadise the related constructs. So construct, the no- struct the particle are a large as the maximum size of trans allow the distruct (chert, novaculite, acid volcancy lass, cristobalite, tradic areachon—Does the aggregate contain particles of types known to be reactive (chert, novaculite, acid volcancy lass, cristobalite, tradic areachon and issection because the but are best discriminated by X-ray different metamorphoed subgraywacke, argilite, phylite, or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate been gelatinized or that appear to be tensile and to natify cristile area alory evidence of alkali - silica reaction (4).	homogeneous.	only residual cement grains are those that were	light of pale tan matter varying somewhat in
judged after examination of a series of thin sections. <i>Circuit</i> of internal boundaries in aggregate. Classification of coras- and fine aggregate or crushed stone; natural or manufactured fine aggregate and the core of the largest relict grains may be truly unhydrated and retain the low (dark gray) birefringence of alite in distorted quashexagonal sections and the visible birefringence to first-order yellow of the largest relict grains may be truly unhydrated and retain the low (dark gray) birefringence of alite in distorted quashexagonal sections and the visible birefringence to first-order yellow of the largest relict grains may be truly aggregate is a carbonat erock or cocks, are there first order yellow of the largest relict grains that approte the adopted in calcium typdroxide? Partly dolomit in cocks that have reacted sometimes are bordered with paste free from calcium hydroxide allong the dolomitic portion is mornal. See other comments in <i>Alkali - silica reaction</i> —Des the aggregate is constanted aluminum sultate hydrate or other tetracalcium aluminum sultate hydrate or other tetracalcium aluminum hydrate or visite in voids in older concrete form is isocropic ettringite or tetracalcium aluminum wither hydrate or other tetracalcium aluminum sultate hydrate or other tetracalcium aluminum sultate hydrate or other tetracalcium aluminum sultate hydrate or other tetracalcium aluminum wither and the calificences aggregate, the calcium hydroxide is socrete of lower water-cement ratio. higher conserts for allein descrete field grains, about 100 µm. In concrete of lower water-cement ratio, higher conserts for allengest in concrete with source. Conserts for allengest in concrete with aggregate is achonate reacks inside the periphery of autor. Conserts of alumined retire and the calificences to alumined retire and the calificences of aggregate, water with abore. Conserts for allengest in concrete with aggregate is and no narrow from the conter towake, here periphery of alumined retire and the calificence with aggreg	Grading; excess or deficiency of sand sizes is to be	largest, which may be composed of several	index of refraction and containing relict
sections. Grain size and nature of internal boundaries in aggregate. Casilication of two layers of gel having different indexes of refraction, or by a layer of calcium hydrated and retain the low (dark gray) bornor two layers of gel having different indexes of refraction, or by a layer of calcium hydrated cement grains ranging down to having a gergate can establish that the source can establish that have existed before thin-sectioning. Alkali - adiaconte ranking the calcium hydrated and retain the low (dark gray) bir distored quasily the lamellar twins in roundad grains of belien. Interstitial aluminoferrite appears the case of ordexed with paste free down to red dark in distored quasily in the source of alkali - silica reaction—Does the aggregate contain particles of types known to be reactive (chert, novaculite, acid volcancy glass, cristobalite, roix gargegate) for a lawinic drains rand the divers and the source of alkali - silica reaction (4).	judged after examination of a series of thin	constituents or be of alite or belite (substituted	unhydrated cement grains. In concrete sectioned
by one or two layers of gel having different Natural mineral aggregate. Classification of coarse and fine aggregate or roushed stone; natural or manufactured fine aggregate. Bond with matrix: peripheral cracks inside the bodres of aggregate grains: internal cracks. General microfractures if one can establish that they existed before thin-sectioning. <i>Alkali - carbonate reactions—If</i> the coarse aggregate is a carbonate rocks, are there firms or partial mis depleted in calcium hydroxide? Partly dolomitic rocks that have reacted sometimes are boroted on the calcium hydroxide and piechnism masked by the color of the grain. Tricalcium atuminate is portion while the paste landon history of the coarcete form calcium hydroxide and piechnism to subteal the paste particles of types known to be reactive (char). Tridymite, opal botte glass)? If quartize, metamorphosed subgraywack, argilite, phylife, or any of those listed in the sentence above, aggregate? Has the aggregate been gelatinized or any of those listed in the sentence above, area to real coarse for dolomitic portion while the pastel along for dolomitic portion shills the pastel and dolomitic portion while the pastel and the landers with or without other anions. <i>Alkali - silica reaction</i> -Does the aggregate the sentence above, reaction between cement at alio, align). Cracks that appear to be tensile and diagn). Cracks that appear to be tensile and the particle are also or widence of alkali - silica reaction (4).	sections. Grain size and nature of internal	C_3S and C_2S). The latter two may be bordered	at early age or not adequately cured, the paste
and fine aggregate. Indexes of refraction, or by a layer of calcium or manufactured fine aggregate or crushed store; natural or manufactured fine aggregate. Bond with matrix peripheral cracks inside the borders of aggregate grains; internal cracks. General microfractures if one can establish that they existed before thin-sectioning. <i>Alkal - carbonate reactions—II</i> the coarse aggregate is a carbonate rock that have reacted sometimes are bordered with paste free trims or partial rims depleted in calcium hydroxide? Partly dolomitic rocks that have reacted sometimes are bordered with paste free trims or partial rims depleted in calcium hydroxide. The large area to undex or rocks, are there there reacted sometimes are bordered with paste free trims color of the grain. Tricacium alluminate is usually not recognized in thin section because any in the hydrates early in the hydrates contain <i>Column 3.</i> <i>Alkal - silica reaction—Does</i> the aggregate contain <i>Malkal - silica reaction—Does</i> the aggregate contain metamorphosed subgraywacke, argilite, phyline, or any of those listed in the sentence above; that has pulled off during sectioning leaving only a peripheral hull bonded to the morary. (This last phenomenon allos occurs in concrete with air-cooled sale aggregate been gelations there internal cracks inside the periphery of the cancer of alkali - silica reaction (4). Cernent paste in advised be are estimated by X-ray diffraction- concrete or alkali - silica reaction (4). Cernent paste in concrete with air-cooled sale aggregate are as a page are as a converted. How and the particle are also evidence of alkali - silica reaction (4).	boundaries in aggregate. Classification of coarse	by one or two layers of gel having different	contains unhydrated cement grains ranging down
Natural mineral aggregate or crushed stone; natural or manufactured fine aggregate. The largest relict grains may be truly converting the state of the sections and the visible birefingence to first-order yellow of the lamellar twins in rounded rarea to reduce the heat of thydration. With aggregate is a carbonate reactions—If the coarse aggregate is a carbonate rock or rocks, are there inthe or partial rims depleted in calcium hydroxide? Parity dolomitic rock or rocks, are there from calcium hydroxide along the intestone portion while the paste along the limestone portion is normal. See other comments in Column 3. <i>Alkali - silica reaction</i> —Dees the aggregate contain particles of types known to be reactive (chert, novaculite, acid volcanic glass, cristobalite, tridymite, opale been gelinterized to the mortar? (This so that it has pulled off during sectioning leaving only a peripheral hall bonded to the mortar? (This so that it has pulled off during sectioning leaving only a peripheral hall bonded to the mortar? (This so that it has pulled off during sectioning leaving only a peripheral hall bonded to the mortar? (This so that it has pulled off during sectioning leaving only a peripheral hall bonded to the mortar? (This so that it has pulled off during sectioning leaving only a peripheral hall bonded to the mortar? (This so that it has pulled off during sectioning leaving only a peripheral hall bonded to the mortar? (This so that it has pulled off during sectioning leaving only a peripheral hall bonded to the mortar? (This so that it has pulled off during sectioning leaving only a peripheral hall bonded to the mortar? (This so that it has pulled off during sectioning leaving only a peripheral hall bonded to the mortar? (This so that it has pulled off during sectioning leaving only a peripheral hall bonded to the mortar? (This so meand here) so that it has pulled off during sectioning leaving only a peripheral hall bonded to the particle are also evidence of alkali - silica r	and fine aggregate.	indexes of refraction, or by a layer of calcium	to a few micrometres in maximum size with an
or manufactured fine aggregate. Bond with matrix: peripheral cracks inside the borders of aggregate grains; internal cracks. General microfractures if one can establish that they existed before thin-sectioning. <i>Rikali - cationate reactions—II the coarse aggregate is a carbonate rock or rocks, are there trims or partial tims depleted in calcium thydroxide? Partly dolomitic rocks that have reacted sometimes are bordered with paste free from calcium hydroxide and the visible brown and having a high refractive index and pleochroism masked by the other of the garanes of ealoum Alkali - silica reaction—Ones the aggregate contain particles of types known to be reactive (chert, novaculite, ead volcanic glass; ristobalite, tridymite, opal, bottle glass)? If quarzite, metamorphosed subgraywacke, arglilite, phylite, roary of these issed in the sentence above, ear there internal cracks inside the periphery of the aggregate to be lensile the particles are also evidence of alkali - silica reaction (4).</i>	Natural mineral aggregate or crushed stone; natural	hydroxide. The largest relict grains may be truly	upper limit as large as 100 µm in maximum
Bond with matrix; peripheral cracks inside the borders of alter in distorted quashexagonal sciences and the visible birefiningence to alter in distorted quashexagonal sciences and the visible birefiningence to alter in distorted quashexagonal sciences and the visible birefiningence to alter in distorted quashexagonal sciences and the visible birefiningence to alter in distorted quashexagonal sciences and the visible birefiningence to alter in distorted quashexagonal sciences and the visible birefiningence to alter in distorted quashexagonal sciences and the visible birefiningence to alter in distorted quashexagonal sciences and the visible birefiningence to alter in distorted quashexagonal sciences and the visible birefiningence to alter th	or manufactured fine aggregate.	unhydrated and retain the low (dark gray)	diameter if the cement was ground in open-circuit
borders of aggregate grains; internal cracks. General microfractures if one can establish that they existed before thin-sectioning. <i>Alkali - calconate rock or rocks, are there ims or partial irms depleted in calcium hydroxide? Partly dolomitic rocks that have reacted sometimes are bordered with paste free portion is normal. See other comments in <i>Column 3.</i> <i>Alkali - silica reaction – Does the aggregate contain particles of types known to be reactive (chert, novaculite, acid volcanic (gass, cristobalite, tridymite, opal, bottle glass?) If quartzite, metamorphosed subgraywacke, argilite, phylite, or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate been gelatinized so that it has pulled off during sectioning leaving only a peripheral hull bonder to the marri? (This har polae disa gagregate, where it indicates reaction between cement and slag.). Cracks that appear to be lensile and to narrow from the conter toward the border of the particle are also evidence of alkali - silica reaction (4). Sections a subject as a subject and the source with agregate? Has the aggregate been gelation at -cooled also gagregate been gelation. These may be visible in match cements from on the part obse thensile and to narrow from the conter toward the border of the particle are also evidence of alkali - silica reaction (4). Sections a subject as a subject and the solid so that it has pulled off during sectioning leaving source. Sections a subject as a subject and the solid source. Sections a subject as a subject and the solid source. Section between cement and slag.) Cracks that appear to be lensile and to narrow from the conter toward the border of the particle are also evidence of alkali - silica reaction (4). Sections and the solid source and the solid as addition and the solid source. Section between cement and slag.) Cracks that appear to be lensile and to narrow from the conter toward the border of the par</i></i>	Bond with matrix; peripheral cracks inside the	birefringence of alite in distorted quasihexagonal	mills or was deliberately ground to low surface
General microtractures if one can establish that they existed before thin-sectioning. <i>Alkali - carbonate reactions</i> —If the coarse aggregate is a carbonate cock or rocks, are there rims or partial rims depleted in calcium hydroxide? Partly dolomitic rocks that have reacted sometimes are bordered with pasts free portion is normal. See other comments in portion while the pasts along the imestone portion is normal. See other comments in particles of types known to be reactive (chert, novacuite, acid volcanic glass, cristobalite, tridymite, opal, bottle glass?) If quartzite, metanorphosed subgraywacka, argillite, phylite, or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate contain in a should be possible to match cements from of aggregate? Has the aggregate leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with agregate? Has the aggregate are also evidence of alkali - silica reaction [4].	borders of aggregate grains; internal cracks.	sections and the visible birefringence to	area to reduce the heat of hydration. With
they existed before thin-sectioning. <i>Alkali - actionate reactions</i> —If the coarse aggregate is a carbonate rock or rocks, are they hydroxide? Partly dolomitic rocks that have reacted sometimes are bordered with paste free from calcium hydroxide along the dolomitic portion is normal. See other comments in <i>Column 3.</i> <i>Alkali - silica reaction</i> —Does the aggregate contain particles of types known to be reactive (chert, novaculite, acid volcanic glass, cristobalite, tridymite, opal, bottle glass)? If quartite, there internal cracks inside the periphery of the aggregate? Has the aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).	General microfractures if one can establish that	first-order yellow of the lamellar twins in rounded	crossed polars, normal paste is black or very
Arkair - carbonate reactions—in the coarse inggregate is a carbonate rock or rocks, are there rims or partial rims depleted in calcium hydroxide along the linestone portion hylife the paste along the linestone portion is normal. See other comments in Column 3. <i>Alkali - silica reaction</i> —Does the aggregate contain particles of types known to be reactive (chert, novaculite, acid volcanic glass, cristobalite, tridymite, opal, bottle glass)? If quartzite, metamorphosed subgraywacke, arglilite, phylite, or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate been et indicates reaction between cement and slag). Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).	they existed before thin-sectioning.	grains of belite. Interstitial aluminoterrite appears	dark mottled gray with scattered anhedral
aggregate is a carbonate rook or locks, are three ims or partial ims depleted in calcium hydroxide? Party dolomitic rocks that have reacted sometimes are bordered with paste free from calcium hydroxide along the dolomitic portion is normal. See other comments in <i>Column 3. Miali - silica reaction</i> —Does the aggregate contain <i>particles of types</i> known to be reactive (chert, novaculite, acid volcanic glass, cristobalite, tridymite, opal, bottie glass)? If quartzite, metamorphosed subgraywacke, argillite, phylite, or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate bene gelatinized so that it has pulled of during sectioning leaving only a peripheral hull bonded to the mortar? (This iar-cooled slag aggregate, where it indicates reaction between cement and slag). Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).	Alkali - carbonate reactions—It the coarse	as prismatic grains ranging in color from brown to	polikilitic crystals or small segregations of calcium
In the original many depleted in calcium hydroxide reaction because in hydroxide? Partly dolomitic rocks that have reacted sometimes are bordered with paste free rom calcium hydroxide along the dolomitic portion while the paste along the domitic portion is normal. See other comments in Column 3. <i>Alkai - silica reaction</i> —Does the aggregate to the aggregate to the service that the best discriminated by X-ray diffraction. These may be visible in voids in older concrete that it has pulled off during sectioning leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4) .	aggregate is a carbonate rock or rocks, are there	greenish brown to reddish brown and having a	nydroxide and scattered relict grains of cement.
In your preacted sometimes are bordered with paste free from calcium hydroxide along the dolomitic portion while the paste along the limestone portion is normal. See other comments in <i>Column</i> 3. <i>Alkali - silica reaction</i> —Does the aggregate contain <i>particles</i> of types known to be reactive (chert, novaculite, acid volcanic glass, 0 ristobalite, ritdymite, opal, bottle glass)? If quartite, meta-totime hydrates with aluminum hydrates with or without other enaions. These may be visible in voids in older concrete but are best discriminated by X-ray diffraction. These may be visible in voids in older concrete but are best discriminated by X-ray diffraction. These may be visible in voids in older concrete but are best discriminated by X-ray diffraction. These may be visible to match cements from one source. Source. Source different colors of aluminoferrite and the calcium silicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).	hudrovide? Barthy delemitic rocks that have	the color of the grain. Tricoloium eluminate in	alliconcrete of high water-cement fatto and
The existing the second	reacted sometimes are bordered with paste free	usually not recognized in this section because the	siliceous aggregate, the calcium hydroxide
 a class in while the paste along the limestone portion is normal. See other comments in Column 3. Alkali - silica reaction—Does the aggregate contain particles of types known to be reactive (chert, novaculite, acid volcanic) glass, cristobalite, tridymite, opal, bottle glass)? If quartzite, metamorphosed subgraywacke, argillite, phyllite, or any of those listed in the sentence above, are plearen to particles of alkali - silica reaction (4). each vin the hydrate or other tetracalcium aluminum sulfate hydrates with or without other anions. These may be visible in voids in older concrete but are best discriminated by X-ray diffraction. Cements from different sources have different colors of aluminoferrite and the calcium silicates have pale green or yellow or white shades. It should be possible to match cements from one source. Cement paste in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). Cement paste in concrete with air-cooled slag aggregate, where it indicates reaction (4). Cement paste in concrete with air-cooled slag aggregate, where it indicates reaction (4). Cement paste in concrete with air-silica reaction (4). Cement paste in concrete that has been subjected to prolonged acid leaching is low in calcium hydroxide is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO₃ content of the correct by it may accompany submicroscopic ettringite in the paste bill at the paste bill and the	from calcium hydroxide along the dolomitic	cubic form is isotropic or because it hydrates	residual cement grains about 100u m. In
before the exterior of the particles and the indicates reaction (4). The series of the particles and the periphere of the particles and the periphere of the particles and the periphere of the p	nortion while the paste along the limestone	early in the hydration history of the concrete	concrete of lower water-cement ratio higher
Column 3. Alkal - silica reaction—Does the aggregate contain particles of types known to be reactive (chet, novaculite, acid volcanic glass, cristobalite, tridymite, opal, bottle glass)? If quartzite, metamorphosed subgraywacke, argliller, phylice, or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate been gelatinized so that it has pulled off during sectioning leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in correte with air-cooled slag aggregate, where it indicates reaction between cement and snag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).	portion is normal. See other comments in	forming submicroscopic ettringite or tetracalcium	cement content, and either siliceous or carbonate
Alkali - silica reaction—Does the aggregate contain particles of types known to be reactive (chert, novaculite, acid volcanic glass, cristobalite, tridymite, opal, bottle glass)? If quartzite, metamorphosed subgraywacke, argilite, phyllite, or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate been gelatinized so that it has pulled off during sectioning leaving only a peripheral hull bonded to the montar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).	Column 3.	aluminum sulfate hydrate or other tetracalcium	aggregate, the maximum size of calcium
particles of types known to be reactive (chert, novaculite, acid volcanic glass, cristobalite, tridymite, opal, bottle glass)? If quartzite, metamorphosed subgraywacke, argilite, phylite, or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate been gelatinicated so that it has pulled off during sectioning leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).	Alkali - silica reaction-Does the aggregate contain	aluminum hydrates with or without other anions.	hydroxide crystals is considerably smaller.
novaculite, acid volcanic glass, cristobalite, tridymite, opal, bottle glass)? If quartzite, metamorphosed subgraywacke, argillite, phyllite, or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate been gelatinized so that it has pulled off during sectioning leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). but are best discriminated by X-ray diffraction. Cements from one source. but are best discriminated by X-ray diffraction. Cements from one source. but are best discriminated by X-ray diffraction. Coolers of aluminoferrite and the calcium silicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). but are best discriminated by X-ray diffraction. Cements from one source.	particles of types known to be reactive (chert,	These may be visible in voids in older concrete	Regardless of water-cement ratio and type of
tridymite, opal, bottle glass)? If quartzite, metamorphosed subgraywacke, argillite, phyllite, or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate been gelatinized so that it has pulled off during sectioning leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). Cements from different sources have different colors of aluminofernite and the calcium silicates neation between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). Cement setter is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO ₃ content of the concrete although it may accompany submicroscopic ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste thas damaged concrete although it may	novaculite, acid volcanic glass, cristobalite,	but are best discriminated by X-ray diffraction.	aggregate, calcium hydroxide crystals occupy
metamorphosed subgraywacke, argillite, phyllite, or any of those listed in the sentence above, are aggregate? Has the aggregate been gelatinized so that it has pulled off during sectioning leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). Carlos that is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO ₃ content of the concrete is greater than would be supplied by the original sulfate content of the content of the concrete is greater than would be supplied by the original sulfate content of the content of the concrete is greater than would be supplied by the original sulfate content of the content of the concrete is greater than would be supplied by the original sulfate content of the comment of the concrete is greater than would be supplied by the original sulfate content of the comment of the concrete is any solitant to the the comment of the concrete is a terry submicroscopic ettringite in the paste	tridymite, opal, bottle glass)? If quartzite,	Cements from different sources have different	space tangential to the undersides of aggregate
or any of those listed in the sentence above, are there internal cracks inside the periphery of the aggregate? Has the aggregate been gelatinized so that it has pulled off during sectioning leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).	metamorphosed subgraywacke, argillite, phyllite,	colors of aluminoferrite and the calcium silicates	particles. Where all the aggregate is carbonate
there internal cracks inside the periphery of the aggregate? Has the aggregate been gelatinized so that it has pulled off during sectioning leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).	or any of those listed in the sentence above, are	have pale green or yellow or white shades. It	rock the maximum size of calcium hydroxide is
aggregate? Has the aggregate been gelatinized source. so that it has pulled off during sectioning leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). Source is a concrete with appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). Source is a concrete with appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). Source is a concrete with appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). Source is greater that the SO ₃ content of the concrete is greater than would be supplied by the original sulfate attack it must be established chemically that the SO ₃ content of the concrete although it may accompany submicroscopic ettringite in the paste that has damaged concrete although it may accompany submicroscopic ettringite in the paste that has damaged the operate the submicroscopic ettringite in the paste that has damaged the operate the submicroscopic ettringite in the paste that has damaged the operate the operate the submicroscopic ettringite in the paste that has damaged the operate the submicroscopic ettringite in the paste that has damaged the operate t	there internal cracks inside the periphery of the	should be possible to match cements from one	smaller than in comparable concrete with
so that it has pulled off during sectioning leaving only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). Cement paste in concrete that has been subjected to prolonged acid leaching is low in calcium hydroxide which is present as recrystallized virtually anhedral grains precipitated near the exterior surfaces. In concrete over 2 or 3 years old made with Type I, II, or III cement, some ettringite is to be expected as rosettes in air voids. This is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO ₃ content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste that has damaged the concrete	aggregate? Has the aggregate been gelatinized	source.	siliceous aggregate. (Calcium hydroxide is
only a peripheral hull bonded to the mortar? (This last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).Cement paste in concrete that has been subjected to prolonged acid leaching is low in calcium hydroxide which is present as recrystallized virtually anhedral grains precipitated near the exterior surfaces.In concrete over 2 or 3 years old made with Type I, II, or III cement, some ettringite is to be expected as rosettes in air voids. This is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO3 content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste that be demaged the concrete although it may accompany submicroscopic ettringite in the paste that be demaged the concrete although it may accompany submicroscopic ettringite in the paste	so that it has pulled off during sectioning leaving		probably epitaxial on calcite.)
last phenomenon also occurs in concrete with air-cooled slag aggregate, where it indicatesto prolonged acid leaching is low in calcium hydroxide which is present as recrystallized virtually anhedral grains precipitated near the exterior surfaces.reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4).In concrete over 2 or 3 years old made with Type I, II, or III cement, some ettringite is to be expected as rosettes in air voids. This is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO3 content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste that has damaged the concrete	only a peripheral hull bonded to the mortar? (This		Cement paste in concrete that has been subjected
air-cooled slag aggregate, where it indicates reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). In concrete over 2 or 3 years old made with Type I, II, or III cement, some ettringite is to be expected as rosettes in air voids. This is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO ₃ content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste that bace damaged the comparts	last phenomenon also occurs in concrete with		to prolonged acid leaching is low in calcium
reaction between cement and slag.) Cracks that appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). In concrete over 2 or 3 years old made with Type I, II, or III cement, some ettringite is to be expected as rosettes in air voids. This is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO ₃ content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste that bace domaged the comparts	air-cooled slag aggregate, where it indicates		hydroxide which is present as recrystallized
appear to be tensile and to narrow from the center toward the border of the particle are also evidence of alkali - silica reaction (4). In concrete over 2 or 3 years old made with Type I, II, or III cement, some ettringite is to be expected as rosettes in air voids. This is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO ₃ content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste that base damaged the concrete sufface attack to the paste that base damaged the concrete sufface attack is the paste that base damaged the concrete sufface attack is the paste that base damaged the concrete sufface attack is the paste that base damaged the concrete sufface attack is the paste that base damaged the concrete sufface attack is the paste that base damaged the concrete sufface attack is the paste that base damaged the concrete sufface attack is the paste that base damaged the concrete to the paste that base damaged the concrete paste that base damaged the concrete the paste that bas	reaction between cement and slag.) Cracks that		virtually anhedral grains precipitated near the
center toward the border of the particle are also evidence of alkali - silica reaction (4). In concrete over 2 or 3 years old made with Type I, II, or III cement, some ettringite is to be expected as rosettes in air voids. This is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO ₃ content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste that bace damaged the concrete.	appear to be tensile and to narrow from the		exterior surfaces.
evidence of alkali - silica reaction (4). II, or III cement, some ettringite is to be expected as rosettes in air voids. This is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO ₃ content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste that has damaged the concrete.	center toward the border of the particle are also		In concrete over 2 or 3 years old made with Type I,
as rosettes in air voids. This is a normal phenomenon; to demonstrate sulfate attack it must be established chemically that the SO ₃ content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste that has damaged the concrete.	evidence of alkali - silica reaction (4).		II, or III cement, some ettringite is to be expected
must be established chemically that the SO ₃ content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste			as rosettes in air voids. This is a normal
content of the concrete is greater than would be supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste that has damaged the concrete			prieriomenon, to demonstrate suitate attack it
supplied by the original sulfate content of the cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste			must be established chemically that the SO_3
cement. Ettringite in voids is not ettringite that has damaged concrete although it may accompany submicroscopic ettringite in the paste			supplied by the original sulfate content of the
has damaged concrete although it may accompany submicroscopic ettringite in the paste			complete by the original surface content of the
accompany submicroscopic ettringite in the paste			has damaged concrete although it may
that has damaged the constants			accompany submicroscopic ettringite in the paste
mai nas namanen me compete			that has damaged the concrete

paste or mortar or concrete of known materials, proportions, age, and history. Specific purposes include:

5.5.1 To establish whether alkali–silica reaction has taken place, what aggregate constituents were affected, what evidence of the reaction exists, and what were the effects of the reaction on the concrete.

5.5.2 To establish whether one or more alkali–carbonate reactions have taken place, which aggregate constituents were affected and what evidence of the reaction or reactions exists, and the effects of the reaction on the concrete properties.

5.5.3 To establish whether any other cement– aggregate reaction has taken place. In addition to alkali–silica and alkali–carbonate reactions, these include hydration of anhydrous sulfates, rehydration of zeolites, wetting of clays and reactions involving solubility, oxidation, sulfates, and sulfides (see Refs (1-17)).⁵

5.5.4 To establish whether an aggregate used in a test has been contaminated by a reactive constituent when in fact the aggregate was not reactive.

5.5.5 To establish the effects of a freezing and thawing test or other physical or mechanical exposure of concrete on the aggregate and the matrix.

5.5.6 To establish the extent of reaction, the nature of reaction products, and effects of reaction produced in exposure to a chemically aggressive environment such as in Test Method C452 or Test Method C1012.

5.5.7 To determine the characteristics of moist-cured concrete that has not been subjected to chemical attack or cement–aggregate reaction or freezing and thawing.

5.5.8 By comparison with appropriate laboratory specimens, a petrographer may be able to substantiate the existence of a particular reaction in concrete or determine that the reaction cannot be detected.

⁵ The boldface numbers in parentheses refer to a list of references at the end of this standard.

(E) C856 – 17

TABLE 5 Characteristics of Concrete Observed Using Microscopes

	Type of Microscope		
Characteristic	Stereomicroscope	Petrographic	Metallographic
Aggregate:			
Shape	Х	Х	Х
Grading	Х		
Distribution	Х		
Texture	Х	Х	Х
Composition	Х	Х	
Rock types	Х	Х	
Alteration	Х	Х	
degree	х	Х	
products	Х	Х	
Coatings	Х	Х	
Rims	Х	х	Х
Internal cracking	х	х	
Contamination	х	х	
Concrete:			
Air-entrained or not	х	х	х
Air voids			
shape	х	х	Х
size	х	х	Х
distribution	х		
Bleeding	x		
Segregation	X		
Aggregate-paste bond	x	×	×
Fractures	x	x	x
Embedded items			
size	x		
shane	X		
location	X		
type	X		
Alteration			
degree and type	×	x	X
reaction products	X	~	X
location	X	x	X
identification	XA	x	X
Nature and condition of surface treatments	Ŷ	×	
Pacto	X	~	
Color	X	¥	
Hardness	X	~	 Y
Porosity	×		×
Carbonation	X	×	X
Besidual cament	X	~	
distribution		¥	X
particle size		~	×
paritice size		~ ~	×
appundance		~ ~	×
Cumposition	 VB	~ ~	×
	~	~ ~	×
SIZE		~ ~	~ ~
abullualite	A V	~ ~	
identification	A VC	~ ~	X V
Compounds in nyarated cement	λŬ	Ā	X
	V	×	V
SIZE	X V	Ā	X
	Х	X	X
Identification		X	X ²

^A Secondary ettringite can sometimes be recognized by crystal habit and silky luster.

^B Fly ash can be detected by color and shape when dark spheres are present. In concrete that has not oxidized the presence of slag may be inferred from the green or blue color of the paste.

^C Ettringite and calcium hydroxide in voids may be recognized by their crystal habits.

^D Magnesium oxide and calcium oxide should be identifiable in polished section.

6. Apparatus

6.1 The apparatus and supplies employed in making petrographic examinations of hardened concrete depend on the procedures required. The following list includes the equipment generally used. Equipment required for field sampling is not listed. Any other useful equipment may be added.

6.2 For Specimen Preparation:

6.2.1 *Diamond Saw*—Slabbing saw with an automatic feed and blade large enough to make at least a 7-in. (175-mm) cut in one pass.

6.2.2 Cutting Lubricant, for diamond saw.

C856 – 17

TABLE 6 Secondary Deposits in Concrete^A

Compound and Mineral Equivalent	Indexes of	Refraction	Form and Occurrence
Calcium carbonate (CaCO ₃); calcite	0 =	= 1.658	Fine-grained, white or gray masses or coatings in the
	= 3	= 1.486	cement paste, in voids, along fractures, or on exposed surfaces; very common
Calcium carbonate (CaCO ₃); aragonite	α =	= 1.530	Minute, white prisms or needles in voids or fractures in
	β =	= 1.680	concrete; rare
	γ =	= 1.685	
Calcium carbonate (CaCO ₃); vaterite	0 =	= 1.544–1.550	Spherulitic, form-birefringent, white encrustations on
	E =	= 1.640–1.650	moist-stored laboratory specimens (vaterite A); also identified in sound concrete from structures by X-ray diffraction (α -vaterite); common (5)
6-calcium aluminate trisulfate-32 hydrate {Ca6[Al(OH)6]2·	ω =	= 1.464–1.469 ^{<i>B</i>}	Fine, white fibers or needles or spherulitic growths in
24H ₂ O}(SO ₄) ₃ ·2H ₂ O (6) ; ettringite	3	= 1.458–1.462	voids, in the cement paste, or in fractures; very common (1, 5)
Tetracalcium aluminate monosulfate-12-hydrate (3CaO-	ω =	= 1.504	White to colorless, minute, hexagonal plates in voids and
$AI_2O_3 \cdot CaSO_4 \cdot 12H_2O)$	3	= 1.49	fractures; very rare (5)
Tetracalcium aluminate-13-hydrate (Ca ₄ Al ₂ (OH) ₁₄ ·6H ₂ O)	ω =	= 1.53	Micalike, colorless, pseudohexagonal, twinned crystals in
	3	= 1.52	voids; very rare (7)
Hydrous sodium carbonate (Na ₂ O·CO ₂ ·H ₂ O);	α =	= 1.420	Minute inclusions in alkalic silica gel; rare (5)
thermonatrite	β =	= 1.506	
	γ =	= 1.524	
Hydrated aluminum sulfate (2Al ₂ O ₃ ·SO ₃ ·15H ₂ O);	α =	= 1.463 ± 0.003	Occurring in cavities in intensely altered concrete; very
paraluminite	β =	= 1.471	rare (7)
	γ =	= 1.471	
Calcium sulfate dihydrate (CaSO ₄ ·2H ₂ O); gypsum	α =	= 1.521	White to colorless crystals in voids, in the cement paste,
	β =	= 1.523	or along the surfaces of aggregate particles in concrete
	γ =	= 1.530	or mortar affected by sulfate or seawater attack; unusual
Calcium hydroxide (Ca(OH) ₂); portlandite	ω =	= 1.574	White to colorless, hexagonal plates or tablets in the
	= 3	= 1.547	cement paste, in voids, along fractures; ubiquitous in concrete
Magnesium hydroxide (Mg(OH) ₂); brucite	ω =	= 1.559	White to yellow, fine-grained encrustations and fillings in
	3	= 1.580	concrete attacked by magnesian solutions or seawater; unusual (8, 9)
Hydrous silica (SiO ₂ · n H ₂ O); opal	η =	= 1.43	White to colorless, finely divided, amorphous; resulting from intense leaching
	varie	es with water content	or carbonation of cement paste; unusual in recognizable proportions
Alkalic silica gel (Na ₂ O·K ₂ O·CaO·SiO ₂)	η =	= 1.46–1.53	White, yellowish, or colorless; viscous, fluid, waxy, rubbery, hard; in voids, fractures, exudations, aggregate; common (10, 11)
Hydrated iron oxides (Fe ₂ O ₃ .nH ₂ O); Limonite	opad	que or nearly so	Brown stain in fractures and on surfaces; common
Thaumasite { $Ca_6[Si(OH)_6]_2 \cdot 24H_2O$ }(SO_4) ₂ (CO_3) ₂ (6)	ω =	= 1.504	Prismatic, hexagonal; capable of growing in continuity with
	= 3	= 1.468± 0.002 ^B	ettringite; in sewer pipe subject to sulfate attack, in grout, in some pavement (12)
Syngenite (K ₂ Ca(SO ₄) ₂)·H ₂ O	α =	= 1.501 (13)	Found in cavities and zones peripheral to slate particles, in
	β =	= 1.51	fibrous form (14)
	γ =	= 1.51	
Hydrotalcite Mg _{3/4} Al _{1/4} (OH) ₂ (CO ₃) _{1/8} (H ₂ O) _{1/2} (6)	ω =	= 1.510 ± 0.003	Foliated platy to fibrous masses (15, 6)
	= 3	= 1.495± 0.003	

^A The literature and private reports include data on many unidentified secondary compounds in concrete; these are not included in the tabulation. Indexes of refraction of common mineralogic types are taken from standard works on mineralogy.

^B Higher and lower indexes of refraction have been recorded for naturally occurring ettringite (13) and thaumasite (12), but it is not known that the naturally occurring minerals and compounds found in hydrated cement are of the same composition.

6.2.3 *Horizontal Lap Wheel or Wheels*, steel, cast iron, or other metal lap, preferably at least 16 in. (400 mm) in diameter, large enough to grind at least a 4 by 6-in. (100 by 152-mm) area.

6.2.4 *Free Abrasive Machine*, using abrasive grit in lubricant, with sample holders rotating on a rotating table. This type of grinding machine greatly increases the speed of preparation of finely ground surfaces.

6.2.5 *Polishing Wheel*, at least 8 in. (200 mm) in diameter and preferably two-speed, or a vibratory polisher.

6.2.6 *Hot Plate or Oven*, thermostatically controlled, to permit drying and impregnating specimens with resin or wax for preparing thin sections, ground surfaces, and polished sections.

6.2.7 Prospector's Pick or Bricklayer's Hammer, or both.

6.2.8 *Abrasives*—Silicon carbide grits, No. 100 (150- μ m), No. 220 (63- μ m), No. 320 (31- μ m), No. 600 (16- μ m), No. 800 (12- μ m); optical finishing powders, such as M-303, M-204, M-309; polishing powders as needed.

6.2.9 *Plate-glass Squares*, 12 to 18-in. (300 to 450-mm) on an edge and at least $\frac{3}{8}$ in. (10 mm) thick for hand-finishing specimens.

6.2.10 *Suitable Medium or Media*, for impregnating concrete and mounting thin sections plus appropriate solvent. Canada balsam, Lakeside 70 cement, and flexibilized epoxy formulations have been used.

6.2.10.1 **Warning**—Flexibilized epoxies form strong bonds but have higher indexes of refraction than Canada balsam or Lakeside 70 and are toxic. Do not allow to touch the skin; plastic gloves shall be worn, and the work shall be done under a hood so as not to breathe the fumes.

6.2.11 *Microscope Slides*—Clear, noncorrosive, glass approximately 24 mm wide and at least 45 mm long. Thickness may need to be specified to fit some thin section machines.

6.2.12 *Cover Glasses*, noncorrosive and preferably No. 1 (0.18-mm) thickness.

6.3 For Specimen Examination:

6.3.1 *Stereomicroscope*, providing magnifications in the range from $7 \times$ to $70 \times$ or more.

6.3.2 *Dollies*—Small, wheeled dollies with flat tops and with tops curved to hold a section of core assist in manipulating concrete specimens under the stereomicroscope.

6.3.3 *Petrographic Microscope or Polarizing Microscope*, for examinations in transmitted light, with mechanical stage; low-, medium-, and high-power objectives such as 3.5×, 10×, and 20 to 25×; 43 to 50× with numerical aperture 0.85 or more; assorted eyepieces having appropriate corrections and magnifications for use with each of the objectives; micrometer eyepiece; condenser adjustable to match numerical aperture of objective with highest numerical aperture to be used; full-wave and quarter-wave compensators, quartz wedge, and other accessories.

6.3.4 *Metallographic Microscope*, with vertical illuminator, mechanical stage, metallographic objectives of low, medium, and high magnification, and appropriate eyepieces to provide a range of magnifications from about $25 \times$ to $500 \times$. Reflected polarized light should be available and appropriate compensators provided. Some polarizing microscopes can be equipped with accessories for metallographic examination, if the tube can be raised or the stage lowered to give adequate clearance for the vertical illuminator and the thicker specimens usually employed.

6.3.5 *Eyepiece Micrometer*—Eyepiece micrometers calibrated using a stage micrometer are useful for measuring particles of aggregate, cement grains, calcium hydroxide and other crystals, and crack widths.

6.3.6 Stage Micrometer, to calibrate eyepiece micrometers.

6.3.7 *Microscope Lamps*—Many modern polarizing microscopes have built-in illuminators which are convenient and satisfactory if, with the condenser, they can be adjusted to fill the back lens of the objective of highest numerical aperture with light. If the microscope requires a separate illuminator, tungsten ribbon-filament bulbs in suitable adjustable housings are satisfactory. Many kinds of illuminators are available for stereomicroscopes; some can be mounted on the microscope, some stand on their own bases; choice is a question of adequacy of illumination for the tasks intended. Focusable illuminators are preferred.

6.3.8 *Needleholders and Points*—In addition to pin vises and needles from laboratory supply houses, a No. 10 sewing needle mounted in a handle or a selection of insect pins from size 00 to size 4 are useful for prying out reaction products.

6.3.9 *Bottles with Droppers*, for acid, water, and other reagents applied during examination.

6.3.10 *Assorted Forceps*, preferably stainless steel, including fine-pointed watchmaker's forceps.

6.3.11 Lens Paper.

6.3.12 *Refractometer, and Immersion Media,* covering the range of refractive indexes from 1.410 to at least 1.785, in steps not larger than 0.005. Stable immersion media, calibrated at a known temperature and of known thermal coefficient, are preferable and should be used in a temperature-controlled room. A thermometer graduated in tenths of a degree Celsius should be used to measure air temperature near the microscope stage so that thermal corrections of refractive index can be made if needed.

7. Selection and Use of Apparatus

7.1 Laboratories should be equipped to provide photographs, photomacrographs, and photomicrographs to illustrate significant features of the concrete. While ordinary microscope lamps are sometimes satisfactory for photomicrography in transmitted and reflected light, lamps providing intense point or field sources, such as tungsten ribbon-filament bulbs, or zirconium or carbon arcs, are highly desirable. For much useful guidance regarding photomicrography, especially using reflected light, see Guide E883.

7.2 The minimum equipment for petrographic examination of concrete where both specimen preparation and examination are completed within the laboratory consists of a selection of apparatus and supplies for specimen preparation, a stereomicroscope preferably on a large stand so that 6-in. (152-mm) diameter cores can be conveniently examined, a polarizing microscope and accessories, lamps for each microscope, and stable calibrated immersion media of known thermal coefficient. Specimens for petrographic examination may be obtained by sending samples to individuals or firms that offer custom services in preparing thin or polished sections and finely ground surfaces. It is more convenient to prepare specimens in house, and their prompt availability overrides their probably greater cost.

7.3 X-ray diffraction, X-ray emission, differential thermal analysis, thermogravimetric analysis, analytical chemistry, infrared spectroscopy, scanning electron microscopy, energy or wavelength dispersive analysis, and other techniques may be very useful in obtaining quick and definite answers to relevant questions where microscopy will not do so. Some undesirable constituents of concrete, some hydration products of cement, and some reaction products useful in defining the effects of different exposures, and many contaminating materials may not be identified unless techniques that supplement light microscopy are used. (18, 19).

8. Samples

8.1 The minimum size of sample should amount to at least one core, preferably 6 in. (152 mm) in diameter and 1 ft (305 mm) long for each mixture or condition or category of concrete, except that in the case of pavement the full depth of pavement shall be sampled with a 4 or 6-in. (102 or 152-mm) core. Broken fragments of concrete are usually of doubtful use in petrographic examination, because the damage to the concrete cannot be clearly identified as a function of the sampling technique or representative of the real condition of the concrete. Cores smaller in diameter than 6 in. can be used if the aggregate is small enough; in deteriorated concrete, core recovery is much poorer with 2½-in. (54-mm) diameter core than with 6-in. diameter core. While it is desirable in examination and testing to have a core three times the maximum size of aggregate, this circumstance is a rare occurrence when concrete with aggregate larger than 2 in. is sampled, because of the cost of large bits and the problems of handling large cores.

8.2 Samples from Constructions—The most useful samples for petrographic examination of concrete from constructions are diamond-drilled cores with a diameter at least twice (and preferably three times) the maximum size of the coarse aggregate in the concrete. If 6-in. (152-mm) aggregate is used, a core at least 10 in. (250 mm) in diameter is desirable; usually a 6-in. diameter core is the largest provided.

8.2.1 The location and orientation of all cores, including cores or core lengths not sent to the laboratory, should be clearly shown; and each core should be properly labeled. For vertically drilled cores, the elevation or depth at top and bottom of each section should be shown, and core loss and fractures antedating the drilling should be marked. For cores taken horizontally or obliquely, the direction of the vertical plane and the tops and bottoms should be marked. A field log should be provided.

8.2.2 Broken pieces of concrete from extremely deteriorated structures or pieces removed while preparing for repair work are sometimes used for petrographic examination. The samples will be more useful if their original locations in the structure are clearly described or indicated in a sketch or photographs.

8.2.3 The information provided with the samples should include:

8.2.3.1 The location and original orientation of each specimen (see Practice C823),

8.2.3.2 The mixture proportions of the concrete or concretes,

8.2.3.3 Sources of concrete-making materials and results of tests of samples thereof,

8.2.3.4 Description of mixing, placing, consolidation, and curing methods,

8.2.3.5 Age of the structure, or in case of a structure that required several years to complete, dates of placement of the concrete sampled,

8.2.3.6 Conditions of operation and service exposure,

8.2.3.7 The reason for and objectives of the examination,

8.2.3.8 Symptoms believed to indicate distress or deterioration, and

8.2.3.9 Results of field tests such as measurements of pulse velocity (Test Method C215), rebound hammer numbers (Test Method C805) or probe readings (Test Method C803/C803M).

8.3 Samples from Test Specimens from Natural Exposures, Concrete Products, and Laboratory Specimens:

8.3.1 Information provided should include: materials used, mixture proportions, curing, age of concrete when placed in service or test, orientation in exposure, present age, condition surveys during exposure, characteristics of the natural or laboratory exposure, and method of manufacture of concrete products. Large concrete products may be sampled like constructions; smaller ones may be represented by one or more showing the range of condition from service or fabrication or both. 8.3.2 The exposure of laboratory specimens should be described with test results, age at test and available test results on the aggregates, hydraulic binders, and admixtures used. This information should accompany test specimens from natural exposures and concrete products or samples therefrom, if available.

9. Examination of Samples

9.1 *Choice of Procedures*—Specific techniques and procedures employed in examination of a sample depend on the purpose of the examination and the nature of the sample. Procedures to be used should be chosen after the questions that the examination is intended to answer have been clearly formulated. The procedures should be chosen to answer those questions as unequivocally and as economically as possible. The details that need to be resolved will be dictated by the objectives of the examination and will vary for different situations. Consequently, the selection and location of specimens from the samples submitted for examination should be guided by the objectives of the study. Test Method C457 should be referred to for those relevant subjects not described here.

9.2 Visual Examination and Outline of Additional Examination—A petrographic examination of concrete, mortar, or cement paste should begin with a review of all the available information about the specimen or specimens, followed by a visual examination of each sample. An outline of information that can be obtained is given in Table 1. That study should be followed by an examination using a stereomicroscope (see Table 2 and the section on Visual and Stereomicroscopic Examination). In some cases, further study is unnecessary, and a report can be prepared. In other cases, specimens are chosen during the visual and stereomicroscope examination for further processing and additional stereomicroscope study, more detailed examination using the petrographic or metallographic microscopes or by X-ray diffraction and other instrumental methods, and for other chemical or physical tests. Methods for specimen preparation are outlined in the Specimen Preparation Section. Tables 2-4 summarize characteristics of concrete conveniently observed with stereomicroscopic, petrographic, and metallographic microscopes. Examination using a stereomicroscope is outlined in the Visual and Stereomicroscopic Examination Section. Examination of fire-damaged concrete is outlined in Table 3; using a polarizing microscope in the Polarizing Microscope Examination Section and Table 4; and using a metallographic microscope in the Metallographic Microscope Examination Section. During each kind of study, the petrographer should note specific examinations to be made in detail, later, and may recognize the need to reexamine specimens. Observations possible using different kinds of microscopes are shown in Table 5; properties of some relevant compounds are listed in Table 6.

9.3 *Photographs*—Photographs and images should be maintained to illustrate features of the examined specimens, such as as-received conditions before they are altered, and important macro-and micro-features of prepared lapped sections, polished sections, fractured surfaces, thin sections, and immersion mounts. Photographs should have a scale or reference to scale.

10. Specimen Preparation

10.1 Preparation for Visual and Stereomicroscope Examination:

10.1.1 Diamond-drilled cores, formed or finished surfaces, freshly broken surfaces, or old crack surfaces should be examined in the condition received. It is sometimes helpful to have drilled surfaces and formed and finished surfaces wetted to increase contrast.

10.1.2 Diamond saw cuts should be oriented with relation to significant features of the concrete, either normal to the bedding directions in conventional concrete, or normal to a formed or finished surface, or to a crack or crack system, in order to reveal the structure and fabric of the concrete and the extent of alteration outward from the crack.

10.1.3 It is useful to prepare at least one sawed surface by grinding it with progressively finer abrasives (as described in Test Method C457) until a smooth matte finish is achieved and to select areas on the matching opposing surface for preparation of thin sections and specimens for optical, chemical, X-ray diffraction, or other examinations.

10.1.4 Specimens obtained by diamond drilling are not ordinarily damaged in the process; however, weak concrete damaged by chemical attack, an alkali–aggregate reaction, freezing and thawing, or several of these, will give poor core recovery with many fractures if it is drilled with a 2½-s-in. or 54-mm bit and barrel while it will give essentially complete recovery if drilled with a 6-in. (152-mm) diameter bit and barrel. This difference is particularly important in petrographic examinations made during condition surveys of old structures. Weakened concrete may also break during sawing. The removal and preparation of specimens for laboratory studies usually involves the application of force and sometimes the application of heat to the specimen.

10.1.5 The effects of force can be minimized during specimen preparation by using thicker slices and making only one cut parallel to the long axis of a core section. Fractured or fragile concrete can be supported by partially or completely encasing it in plaster, epoxy resin, or other reinforcing media before sawing.

10.1.6 Heat used while impregnating concrete with thermoplastic wax or resin will cause cracking if the concrete is heated while it is wet, and will alter the optical properties of some compounds, such as ettringite. Artifacts may therefore be produced and compound identification made difficult. These artifacts may be mistaken as original features. Care must therefore be used in evaluating a particular feature and indexing it as original in the specimen, or produced during the removal of the specimen from the structure or during laboratory processing.

10.1.7 When alkali–carbonate reactions are suspected and rims around crushed carbonate aggregate are seen, it is useful to etch a sawed or ground surface in 6 N or weaker hydrochloric acid to see if peripheral rims on coarse aggregate particles are more or less susceptible to etching than the interior of the particle. Since etching destroys the surface, this step should not be taken until all other examinations of the surface have been completed. Etching the ground surface for 30 s in 10 % hydrochloric acid is an appropriate procedure.

10.2 *Preparation of Immersion Mounts*—Immersion mount samples are prepared for examinations using the petrographic microscope. This type of examination provides versatility because materials can be immersed in liquids having different refractive indices. Detailed knowledge of the use of the capabilities of the petrographic microscope is required to properly examine immersion mounts.

10.2.1 Immersion mounts are useful for observing and identifying a variety of aggregate components, residual and relict portland cement particles, the calcium hydroxide component of cement hydration, components of blended cements, supplementary cementitious materials, components resulting from chemical alteration of cementitious components and of aggregates, secondary deposits from exposure of concrete to a variety of chemicals, and for confirming identifications by other methods.

10.2.2 Powders and fine chips for immersion mounts can be prepared by: (1) pulverization of samples from which specimens may be taken; (2) using a sharply pointed probe for removing specimens from small areas of aggregate and paste, material in aggregate sockets, voids, and cracks; and (3) scrapings from fracture and formed surfaces.

10.2.3 In immersion mounts, individual fragments are usually in random orientation so that the identification of principal refractive indices of a material can be determined in addition to data about other optical characteristics. Portions of powdered material, chips, or scraping are placed on a glass slide and immersed in an immersion liquid of known refractive index. A cover slip is used on top of the preparation. Based upon refractive indices and other optical properties, specific identifications can be made of unknown compounds.

10.2.4 Refractive index liquids available provide refractive index values to at least three decimal places (see 6.3.12). Liquids accurate to two decimal places can be used if the petrographer is knowledgeable about Becke line colors or other techniques.

10.3 Preparation of Thin Sections—The detailed description of thin-section preparation is beyond the scope of this practice. There are many laboratories that provide this service if in-house facilities are not available. The procedure includes slicing the concrete into 1/16-in. (2-mm) thick wafers if the concrete is strong and thicker slices if it is not. It may be necessary to impregnate the concrete with a resin before slicing to prevent disintegration. Diluted flexibilized epoxy resins or thermoplastic resins have been used successfully. The thin concrete slices are then mounted on glass slides with either flexibilized epoxy, Canada balsam, or Lakeside 70, and ground on laps using progressively finer abrasive until a thickness of 30 µm or less is obtained; thickness not greater than 20 µm is required for detailed examination of the paste in transmitted light. It is usually necessary to check the thickness of the section by the use of birefringent colors of common minerals in the aggregate, such as quartz or feldspar, during the final grinding stages. A cover glass is placed on the cleaned, prepared section and secured with Canada balsam or other media.

10.3.1 Semiautomatic thin-section making machines are available which prepare the original surface of the blank for

mounting, trim the excess thickness of the blank after mounting, and grind the section to 50 to 100 μ m, leaving little thickness to be removed by hand lapping.

10.4 *Preparation for Examination with the Metallographic Microscope:*

10.4.1 The preparation of specimens for examination with the metallographic microscope is described in Practice E3.

10.4.2 The procedures described here are intended as guides only. Methods should be used that are appropriate to the varieties of microscopical techniques to be employed, and to specimen condition and composition. It is impossible to provide instructions to suit every possible situation.

11. Visual and Stereomicroscope Examination

11.1 If there is more than one specimen, arrange them in logical order to represent: position in the structure and differences in materials, proportions, and exposure, or combinations of these. Photographs and sketches of significant features should be made before specimens are altered. Tables 1 and 2 list some features to be observed during visual and stereomicroscopic examination.

11.2 Concrete from Constructions (Core Log):

11.2.1 Fit fragmented cores together and determine if any pieces are missing. Measure cores to verify field data and prepare a diagramatic log of each core, if necessary. The log should be made to a scale to show relevant features. The log may be used to show fresh and old fractures, reacted particles, reaction products, changes in size or type of coarse and fine aggregates, distribution of coarse aggregate, honeycomb, segregation of components, cold joints or lift or course boundaries, location and direction of steel or other embedded items, changes in color of paste, and other significant features. Notes should be taken and suitably referenced in the log. If cores have been suitably packed so as to preserve the moisture content as drilled (which may or may not be the actual in-place moisture content), specimens should be carefully handled to preserve the moisture content and avoid breakage. Tests that may be made of specimens in the as-received moisture condition include compressive strength, static or dynamic modulus of elasticity, air content by high-pressure meter, permeability, and freezing and thawing.

11.2.2 During the visual examination, general comparison of cores representing different conditions, materials, and extent and nature of deterioration should be made and recorded. The specimens should be sorted into comparable groups based on condition or location of regions designated for more detailed examination. In some cases, during the visual examination or the stereomicroscope examination, one or more specimens from each group may be selected for more detailed studies. If a reduced number of specimens is to be selected for detailed examination, the selection should be made after careful visual and stereomicroscope examinations have been used to define one or more factors that characterize each group.

11.3 *Specimens from Natural Exposures*— These specimens should be laid out in logical order, either by materials, proportions, age, or combinations of these, and compared with respect to composition and condition. Significant features for

more detailed examination should be marked and noted. Table 3 shows features of fire-damaged concrete.

11.4 Concrete Products:

11.4.1 The samples may consist of complete units when they have relatively small dimensions (such as tile, block, or brick), or portions removed from units by coring or sawing. The samples should be organized and oriented in a manner appropriate to the objectives of the examination. So, for example, portions taken from a single product unit should be grouped together, and each sample should be described by visual observation and measurement of dimensions in relation to markings or labels. The following information should be recorded or clearly marked on the samples: location in the product unit (top, side, end, interior, etc.); vertical and horizontal directions as cast or molded; outer and inner ends; position in the product unit during curing period; position of the sample relative to highly stressed portions of the concrete adjacent to tendon anchorages; and location in the unit as put in place in construction, etc. Sketches or photographs of pertinent features should be recorded to show such conditions as cracking, staining, chemical deposits, presence of foreign matter, segregation, surface defects, and the like.

11.4.2 Procedures such as those set forth in 11.1 and 11.2 are applicable in the examination of concrete products. The investigation may be directed toward features resulting from the specific manufacturing operations involved, such as mixing, molding, demolding, curing, and any prestressing procedures. For example, lack of uniformity might originate in incomplete mixing, improper consolidation during molding, or incomplete or nonuniform curing. Surface defects and poor appearance may result from improper application of form-release agents, possibly giving rise to inhibition of hydration of the cement in a near-surface zone. Features like these can be detected and described by visual and microscopical examination of formed or molded surfaces, sawed and lapped surfaces, or fracture surfaces across the sample.

11.5 *Laboratory Specimens*—These should be laid out in logical order and compared with respect to composition and condition, and to features influenced or expected to be influenced by the test process.

11.6 Stereomicroscope Examination—The stereomicroscope examination reveals additional details at magnifications from $5 \times$ to $150 \times$ (see Tables 1 and 2). The stereomicroscope examination and visual examination are often carried on alternately. Examinations at low magnifications reveal characteristics of formed, finished, deteriorated, broken, sawed, or ground surfaces. Old cracks may be opened and their surfaces examined to detect reaction products and secondary alteration. Old cracks are frequently of different color than the mass of the concrete, and appear blurred by secondary deposits.

11.6.1 Freshly broken surfaces may follow structural weaknesses and reveal significant features that have not been masked by secondary alteration.

11.6.2 Sawed and ground surfaces are examined to detect fine cracks and trace networks of cracks that are not perceptible on drilled or sawed surfaces, to examine filling and partial filling in voids and cracks, and to detect rims on aggregate particles that may indicate chemical reactions between the cement and the aggregate. Rims on gravel or natural sand should be presumed to be a result of weathering in the deposit, unless samples of aggregates used are available and show that rims were not present before the aggregate was used in the concrete. Rims produced in the concrete on particles of sand and gravel are absent or relatively thin and faint at locations where the particle is in contact with an air void. Rims produced by weathering may mask rims produced by alkali-silica reaction. Rimmed crushed stone in concrete usually indicates alteration in the concrete, as alkali-silica reaction or alkali--carbonate reaction (10, 20, 21). Pale rims in mortar bordering coarse aggregate (5, 19) and pale areas in the mortar may be gel-soaked paste (4) or highly carbonated paste adjoining carbonate aggregate that has undergone an alkali-carbonate reaction.

11.6.3 Deposits in old cracks may include calcite or ettringite or calcium hydroxide, or combinations of these compounds, or more unusual crystalline substances, but sometimes include sand, silt, clay, and freshwater or saltwater organisms. Such organisms may provide evidence that a part of a structure that is not ordinarily submerged has been submerged.

11.6.4 Quantitative determination of constituents of concrete can be made by microscopical point-count or lineartraverse procedures in general accord with the requirements of Test Method C457. A total analysis may include the proportional amounts of coarse aggregate, fine aggregate, cementitious matrix, and air voids. The differentiation of coarse and fine aggregate is not accurate unless the two fractions are distinguishable lithologically, since the maximum dimension of the particles usually is not intersected by the prepared surface. Likewise, the proportion of individual rock types can be determined quantitatively by these methods, such as, the content of unsound or reactive constituents in the coarse or fine aggregate or both; proportions of lightweight and normal weight aggregate; and the abundance of granular contaminating substances.

12. Petrographic Microscope Examination

12.1 Characteristics of Good Concrete Thin Sections-Features that characterize good, thin sections of concrete or mortar are as follows: the mounted lower surface is free of abrasive and has been ground to a smooth matte finish ordinarily obtained by finishing the surface with optical alumina or equivalent; the lower surface of the blank is entire; air voids have complete peripheries; there is a sharp boundary between the void and surrounding mortar; deposits in voids are preserved; and aggregate that has been observed under the stereomicroscope to be entire when the blank was selected has remained entire and microfractures have not been produced in micro fsectioning. It is very difficult to avoid production of micro fsectioning when the aggregate is principally quartzite and quartz, if it is desired to reduce the section to a thickness of 30 µm so that the brightest birefringence color of quartz is first-order white. Some cracks will be formed and some loss of paste which is softer than quartz aggregate will occur.

12.1.1 The desirable thickness of the thin sections ranges from about 40 to 20 μm . Thinner sections may be required for

detailed examination of the cement paste matrix. It is sometimes necessary to give up normal thickness and use a thicker section to preserve fragile deposits in voids such as alkali--silica gel, ettringite, calcium hydroxide, calcite, aragonite, or thaumasite. When it is desired to preserve the contacts between mortar and coarse aggregate, it may be preferable to leave the section thicker than normal with the highest birefringence color of the quartz pale first-order yellow. In normal concrete, the material bordering the aggregate consists of amorphous cement gel, with calcium hydroxide crystals quite evenly distributed but with slight concentrations along the undersides of coarse aggregate and fine aggregate, if the section is cut parallel to the placement direction. In cases of alkali-silica reaction, there is usually a zone depleted in or free of calcium hydroxide surrounding reacted aggregate particles; sometimes gel is present surrounding the aggregate or soaking the paste so that it is completely dark with crossed polars and brown grading hazily to more normal paste in plane polarized light. It is fairly easy to recognize gel-soaked paste; it is possible with experience to recognize depleted calcium hydroxide around a reacted aggregate particle, so long as the fine aggregate or any crusher dust present does not contain much colorless mica. Thin flakes of muscovite can be confused with thin tablets of calcium hydroxide when both are viewed on edge; they can be distinguished if the higher index of the mica is observed.

12.1.2 It is sometimes preferable to lose part of the section or crack the quartz in order to distinguish among quartz (birefringence 0.009), calcium hydroxide (birefringence 0.027), and calcite (birefringence 0.172). When the three materials occur together, the quartz particles will be shaped like sand grains or rock fragments, while calcium hydroxide will be present either as tablets tangential to aggregate or as poikilitic crystals in the paste enclosing residual cement grains or areas of gel. The birefringence of calcium hydroxide is three times that of quartz; the birefringence of calcite is 6.4 times that of calcium hydroxide; and birefringence of aragonite is 5.7 times that of calcium hydroxide. While aragonite is fairly uncommon in concrete, calcite is common as a product of carbonation and as an ingredient of aggregate. At normal thickness of 30 µm, the highest birefringence of calcium hydroxide viewed parallel to the cleavage is bright first-order yellow with an occasional orange or first-order red area. Calcite in the same section has high-order white birefringence except in very minute grains in which it is very thin, approximately rhombic in shape, and the birefringence color is first-order white. The birefringence relations discussed in this paragraph are the basis that makes possible much of the interpretation of concrete thin sections.

12.2 Choice of Areas for Thin Sections of Concrete—Areas from which thin sections are to be prepared usually should be chosen after examining the sawed or sawed and ground surface with a stereomicroscope. Selection of the area may depend on the features to which the examination is directed, or the choice may be affected in the case of highly deteriorated concrete by the desire to choose a volume strong enough to endure sectioning even after impregnation. In that second case, an area of mortar with coarse aggregate at the corners or along the sides may be the successful choice. If it is desired to examine

the aggregate to compare it with aggregate of a known source to establish whether the two probably came from the same deposit or quarry, coarse aggregate should be chosen in sufficient number to cover the range of varieties present and their physical condition. If the concrete has been subjected to alkali–silica or alkali–carbonate reactions, areas selected for sectioning should include coarse aggregate with cracks inside the periphery but surrounding the center and cracks in the middle of the particle which narrow toward the border which may or may not contain gel in the case of alkali–silica reaction. Reaction-rimmed particles may be chosen for sectioning in the case of either kind of reaction, but it is ordinarily a futile effort; the rims distinct to the naked eye or the low power of the stereomicroscope may not be visible in thin section.

12.2.1 Features visible in the examination of thin sections of concrete are shown in Table 4.

13. Paste Features

13.1 Many physical and mineralogical properties of the paste are influenced, or are in part governed by, w/c and w/cm, extent of curing, fineness and composition of the portland cement and other cementitious materials, pozzolans, mineral and chemical admixtures, and fine material from aggregates (See Terminology C125). Among these properties, with respect to the evaluation of unaltered paste, are: (a) color, hardness density, and porosity (22-25); (b) texture of fracture surfaces (22 and 23); (c) size, abundance, color, and mineralogy of non-pozzolanic, and residual and relict pozzolanic and cementitious materials (22-24, 26); (d) size, abundance, and morphology of the calcium hydroxide component of cement hydration as may be affected by pozzolanic materials (22 and 23, 26); (e) degree of hydration of cementitious materials (22-28); (f) color intensity of dye-impregnated pastes (24,26); (g) nature of aggregate-paste bond; (h) rate of absorption of water droplets (24); (i) depth of carbonation (23); (j) magnitude of bleeding and segregation of concrete-making components (23, 27); and (k) paste micro hardness (25).

13.2 The *w/c* and *w/cm* and their uniform distribution throughout concrete may be affected by a number of influences that include: (a) the amount of original water, free water introduced by aggregates, and tempering and retempering water; (b) absorption of water by aggregates; (c) efficiency of mixing batch water and free water from aggregates; (d) bleeding and vibration after concrete placement; and (e) water lost due to evaporation and to absorption by the subbase.

13.3 Because of the variable nature of pastes, age of pastes, and exposure to a variety of external influences, there is no generally accepted standard procedure that employs microscopical methods for determining the w/c or w/cm of hardened concrete. A procedure for estimating w/c and w/cm (29) was critically evaluated in a SHRP study, but was not recommended by SHRP for inclusion in Practice C856.

14. Report

14.1 The report of the examination should include the following:

14.1.1 Location and orientation of the samples in the construction or products or type of specimen,

14.1.2 History of the samples insofar as is available,

14.1.3 Physical and chemical tests made on the samples, with their results,

14.1.4 Description of the samples and a report on mixture proportions, if available or if estimated, workmanship, construction practice, and original quality of the concrete in the constructions, insofar as such information is available, and

14.1.5 Interpretation, insofar as possible, of the nature of the materials and the chemical and physical events that have led to the success or distress of the concrete.

15. Keywords

15.1 aggregates; air voids; alkali-silica reaction; analysis; deterioration; examination; fire effects; hardened concrete; microscopy; paste; petrographic; secondary deposits

REFERENCES

- (1) Mather, K., "Petrographic Examination of Hardened Concrete in Significance of Tests and Properties of Concrete-Making Materials," *Symposium on Significance of Tests and Properties of Concrete and Concrete Making Materials,* ASTM 169 A, ASTM International, 1966, pp. 125–143.
- (2) Smith, Peter, "Investigation and Repair of Damage to Concrete Caused by Formwork and Falsework Fire," ACI Journal, JACIA, No. 11, Nov 1963; ACI Proceedings, PACIA, Vol 60, 1963, pp. 1535–1566.
- (3) Green, J. Keith, "Some Aids to the Assessment of Fire Damage," *Concrete*, COCTA, Vol 10, No. 1, January 1976, pp. 14–17.
- (4) Idorn, G. M., *Durability of Concrete Structures in Denmark*, Technical University of Denmark, Copenhagen, January 1967, p. 208.
- (5) Mielenz, R. C., "Petrography Applied to Portland Cement Concrete," *Reviews in Engineering Geology*, edited by T. Fluhr and R. F. Legget, Geological Society of America, GAEGA, Vol I, 1962, pp. 1–38.
- (6) Taylor, H. F. W., "Crystal Structures of Some Double Hydroxide Minerals," *Mineralogical Magazine*, MNLMB, Vol 39, No. 304, December 1973, pp. 377–389.

- (7) Idorn, G. M., "Concrete Deterioration of a Foundation," Acta Polytechnia (Copenhagen, Denmark), APOBA, No. 4, 1957, pp. 5–48.
- (8) Idorn, G. M., "Disintegration of Field Concrete," Danish National Institute of Building Research and Academy of Technical Science, Commission on Alkali Reactions in Concrete, *Progress Report N1*, DNBRA, 1956, 39 pp.
- (9) Hutton, C. O., "Two Unusual Occurrences of Paraluminite," New Zealand Journal of Science and Technology, NZTBA, Vol 26B, 1945, pp. 242–244.
- (10) McConnell, D., Mielenz, R. C., Holland, W. Y., and Greene, K. T., "Cement-Aggregate Reaction in Concrete," *Journal of the American Concrete Institute*, JACIA, *Proceedings*, Vol 44, October 1947, pp. 93–128.
- (11) Mather, B., "Cracking of Concrete in the Tuscaloosa Lock," *Highway Research Board Proceedings*, HIRPA, Vol 51, 1951, pp. 218–233.
- (12) Erlin, Bernard, and Stark, David C.," Identification and Occurrence of Thaumasite in Concrete," *Highway Research Record No. 113*, HRBRA, 1966, pp. 108–113.

- (13) Winchell, A. N., and Winchell, H., *The Microscopical Characters of Artificial Inorganic Solid Substances*, Academic Press, New York and London, 1964.
- (14) Lea, F. M., *The Chemistry of Cement and Concrete*, 3d ed., Edward Arnold Ltd., London, England, pp. XIV and 727.
- (15) Lerch, W., Ashton, F. W., and Bogue, R. H., "The Sulfoaluminates of Calcium," *National Bureau of Standards Journal of Research*, JRNBA, Vol 2, 1929, pp. 715–731.
- (16) Hansen, W. C., "Anhydrous Minerals and Organic Materials as Sources of Distress in Concrete," *Highway Research Record No. 43*, Highway Research Board, HRBRA, 1963, pp. 1–7.
- (17) Mielenz, R. C., "Reactions of Aggregates Involving Solubility, Oxidation, Sulfates, or Sulfides," *Highway Research Record No. 43*, Highway Research Board, HRBRA, 1963, pp. 8–18.
- (18) Erlin, Bernard, "Methods Used in Petrographic Studies of Concrete," Analytical Techniques for Hydraulic Cements and Concrete, ASTM STP 395, ASTM International, 1966, pp. 3–17.
- (19) Erlin, Bernard," Analytical Techniques, Observations of the Performance of Concrete in Service," *Highway Research Board Special Report 106*, Highway Research Board, HRBRA, Publication 309-01790-4, 1970.
- (20) Brown, L. S., "Some Observations on the Mechanics of Alkali-Aggregate Reaction," *ASTM Bulletin No. 205*, April 1955, p. 40.
- (21) *Symposium on Alkali-Carbonate Rock Reactions*, Highway Research Record No. 45, HRBRA, Washington, 1964.
- (22) Erlin, Bernie, "Other Viewpoints on Petrographic Reports," Concrete Construction Magazine, February 2000, pp. 21–27.
- (23) Erlin, Bernard, "Water-Cement Ratio," Concrete International, *American Concrete Institute*, March 2000, pp. 7–9.
- (24) Liu, J.J., and Kahn, M.S., "Comparison of Known and Determined Water-Cement Ratios Using Petrography," SP-191, "Water-Cement Ratio and Other Durability Parameters," *American Concrete Institute*, 2000, pp. 11–25.
- (25) Erlin, Bernard, Campbell, R.A., "Paste Micro-Hardness—Promising Technique for Estimating Water-Cement Ratio," SP-191, "Water-Cement Ratio and Other Durability Parameters," *American Concrete Institute*, 2000, pp. 43–55.

- (26) Jakobsen, V.H., Laugesen, P., Thaulow, N., "Determination of Water-Cement Ratio in Hardened Concrete by Optical Fluorescence Microscopy," SP-191, "Water-Cement Ratio and Other Durability Parameters," *American Concrete Institute*, 2000, pp. 27–36.
- (27) St. John, D.A., Poole, A.W., and Sims, I., Concrete Petrography, A Handbook of Investigative Techniques, Arnold, 1998, pp.141–150.
- (28) SHRP-C-339, "Concrete Microstructure: Recommended Revisions to Test Methods," Strategic Highway Research Program, National Research Council, Washington, DC 1993.
- (29) Nordtest Method, NT Build 361, 1991: Concrete, Hardened: Water-Cement Ratio.
- (30) Brownmiller, L. T., "The Microscopic Structure of Hydrated Portland Cement," *Journal of the American Concrete Institute*, JACIA, *Proceedings*, Vol 39, January 1943, pp. 193–210.
- (31) Natesaiyer, K., and Hover, K. C., "In Situ Identification of ASR Products in Concrete," *Cement and Concrete Research*, Vol 18, 1988, pp. 455–463.
- (32) Natesaiyer, K., and Hover, K. C., "Further Study of an Insitu Technique for the Identification of Alkali-Silica Reaction Products in Concrete," *Cement and Concrete Research*, Vol 19, 1989, pp. 770–778.
- (33) Natesaiyer, K., and Hover, K. C., "Some Field Studies of the New In situ Technique for the identification of ASR Products," *Proceedings* of the 8th International Conference on Alkali Aggregate Reaction, Kyoto, Japan, 1989, pp. 555–560.
- (34) Natesaiyer, K., Stark, D., and Hover, K. C., "Gel Fluorescence Reveals Reaction Product Traces," *Concrete International*, January 1991.
- (35) Pflug, H. D., and Crumpton, C. E., "Analysis of Sodium and Concrete by Fluorescence Photometry," ASTM Materials and Research Standards, July 1963.
- (36) Natesaiyer, K., "Some Applications of the Gel Fluorescence Test for Alkali-Aggregate Reaction in Concrete," *Cement and Concrete Deposits*, El Sevier Science Publishers Limited, England, 1993.
- (37) Strategic Highway Research Program (SHRP), "Handbook for the Identification of Alkali-Silica Reactivity in Highway Structures," SHRP-C/FR-91-101, National Research Council, 1991, p. 49.

SUMMARY OF CHANGES

Committee C09 has identified the location of selected changes to this standard since the last issue (C856 - 14) that may impact the use of this standard. (Approved Jan. 1, 2017.)

(1) Deleted Appendix X1.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/