



Standard Practice for Determining the Properties of Jacketing Materials for Thermal Insulation¹

This standard is issued under the fixed designation C921; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope

1.1 This practice covers jackets applied over thermal insulation on piping and equipment, including materials applied solely for physical protection, and materials applied as vapor retarders.

1.2 This practice provides material and physical requirements, or both, for jackets. Guidance in selecting the proper jacket for a given application can be found in Guide C1423.

1.3 This practice does not cover field applied mastics or barrier coatings and their attendant reinforcements, nor does it cover jackets for buried insulation systems.

1.4 The values stated in inch-pound units are to be regarded as standard. The values given in parentheses are mathematical conversions to SI units that are provided for information only and are not considered standard.

1.5 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- A240/A240M Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet, and Strip for Pressure Vessels and for General Applications
- A336/A336M Specification for Alloy Steel Forgings for Pressure and High-Temperature Parts
- A653/A653M Specification for Steel Sheet, Zinc-Coated

- (Galvanized) or Zinc-Iron Alloy-Coated (Galvannealed) by the Hot-Dip Process
- A792/A792M Specification for Steel Sheet, 55 % Aluminum-Zinc Alloy-Coated by the Hot-Dip Process
- B209 Specification for Aluminum and Aluminum-Alloy Sheet and Plate
- C168 Terminology Relating to Thermal Insulation
- C390 Practice for Sampling and Acceptance of Thermal Insulation Lots
- C921 Practice for Determining the Properties of Jacketing Materials for Thermal Insulation
- C1258 Test Method for Elevated Temperature and Humidity Resistance of Vapor Retarders for Insulation
- C1263 Test Method for Thermal Integrity of Flexible Water Vapor Retarders
- C1338 Test Method for Determining Fungi Resistance of Insulation Materials and Facings
- C1423 Guide for Selecting Jacketing Materials for Thermal Insulation
- D774/D774M Test Method for Bursting Strength of Paper (Withdrawn 2010)³
- D828 Test Method for Tensile Properties of Paper and Paperboard Using Constant-Rate-of-Elongation Apparatus (Withdrawn 2009)³
- D882 Test Method for Tensile Properties of Thin Plastic Sheeting
- D1204 Test Method for Linear Dimensional Changes of Nonrigid Thermoplastic Sheeting or Film at Elevated Temperature
- E84 Test Method for Surface Burning Characteristics of Building Materials
- E96/E96M Test Methods for Water Vapor Transmission of Materials

2.2 TAPPI Standards:

- T461 Flame Resistance of Treated Paper and Paperboard⁴

¹ This practice is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.33 on Insulation Finishes and Moisture.

Current edition approved Sept. 1, 2015. Published October 2015. Originally approved in 1979. Last previous edition approved in 2010 as C921–10. DOI: 10.1520/C0921-10R15.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ The last approved version of this historical standard is referenced on www.astm.org.

⁴ Available from Technical Association of the Pulp and Paper Industry (TAPPI), 15 Technology Parkway South, Suite 115, Peachtree Corners, GA 30092, <http://www.tappi.org>.

3. Terminology

3.1 *Definitions*—Definitions in Terminology **C168** apply to terms used in this practice, including the word jacket, which is defined as "a form of facing applied over insulation." In common use, the terms jacket and jacketing shall be considered interchangeable.

4. Classification

4.1 *Type I*—Semi-rigid, for physical abuse resistance, physical support, and finish.

4.1.1 Grade 1: Aluminum sheet metal,

4.1.2 Grade 2: Stainless steel sheet metal,

4.1.3 Grade 3: Coated steel sheet metal, and,

4.1.4 Grade 4: Plastic sheet.

4.2 *Type II*: Flexible for vapor retardance, or physical support or finish combination thereof.

4.2.1 Grade 1: Laminated multi-layer,

4.2.1.1 Class A: Below ambient application; extremely low permeance,

4.2.1.2 Class B: Below ambient application; very low permeance,

4.2.1.3 Class C: Below ambient application; low permeance, and

4.2.1.4 Class D: Above ambient application; no vapor retarder needed,

4.3 Grade 3: Fabric

4.3.1 No grades; support only, vapor retarder properties not applicable.

4.4 Grade 4: Plastic film

4.4.1 Class A: Below ambient application; extremely low permeance,

4.4.2 Class B: Below ambient application; very low permeance,

4.4.3 Class C: Below ambient application; low permeance, and

4.4.4 Class D: Above ambient application; no vapor retarder needed.

5. Significance and Use

5.1 Jackets provide one or more of three basic functions when applied over thermal insulation:

5.1.1 Physical protection, in the form of abuse resistance and added structural integrity or support for the insulating medium.

5.1.2 Resistance to moisture vapor intrusion into the insulating medium in those applications where ambient and operating temperatures create a vapor driving force toward the cold (insulated) surface.

5.1.3 Exposed finish for the insulation

5.2 Type I semi-rigid jackets, in the form of metallic or heavy gauge plastic sheet, are used over insulation on piping or equipment to provide high abuse resistance. In this case, the material is also referred to as a protective jacket.

5.3 The vapor retarding Type II flexible jacket (Grades 1 and 2, Classes A, B, and C) is used by itself in below ambient service applications not requiring high abuse resistance. In

those cases where high abuse resistance is required, it is applied to the insulation prior to installation of a protective jacket.

5.4 The non vapor-retarding Type II flexible jacket (Grades 1 and 2, class D) is used by itself in above ambient service applications not requiring high abuse resistance. It may also be used for support of the insulation prior to installation of a protective jacket in above ambient applications requiring high abuse resistance.

5.5 Since semi-rigid protective jackets do not perform a vapor retarder function, and flexible jackets do not provide high abuse resistance, the various materials categorized herein are commonly used in combination, but not interchangeably.

5.6 Vapor-retarding properties are not necessary for systems operating above ambient.

5.7 In applications where there is a need to reduce surface emittance, non-metallic jacket, or painted, or film covered metal jacket may be specified.

5.8 For direct outdoor exposure, certain Type I jackets may be used. UV resistance is an important consideration with the Grade 4 materials. Consult with the manufacturer for recommendations on suitability for these applications.

6. Materials and Manufacture

6.1 Jackets shall be composed of a single material or a lamination of several components. The material shall be in the form of rolls or sheets or performed to fit the surface to which they are to be applied. The materials may be applied in the field or may be a factory-applied composite with the insulation.

6.2 *Type I - Semi-rigid Protective:*

6.2.1 Semi-rigid jackets consist of metal jackets (Grades 1, 2, and 3) and heavy gauge plastic jackets (Grade 4).

6.2.2 Metal jackets are those whose primary material (usually the component of greatest thickness) is metal, such as aluminum alloy, stainless steel, or aluminum - zinc alloy coated steel sheet. Depending upon the metal, it may be available in a smooth mill finish, corrugated, embossed, painted or covered with a laminated, protective film. The inner surface (that side in contact with the insulation) is usually coated or covered with corrosion inhibiting film.

6.2.3 Aluminum Alloy jackets are commonly manufactured to Specification **B209**, Type 3003, 3004, 3104, 3105, 5005, 5052, or 1100. Aluminum temper ranges from half hard through full hard. Thicknesses generally available are 0.010 to 0.063 in. (0.25 to 1.60 mm) nominal.

6.2.4 Stainless steel jackets are manufactured to Specification **A240/A240M**, Type 301, 302, 304, or 316 stainless. Thicknesses generally available are from 0.010 to 0.032 in. (0.25 to 0.81 mm) nominal.

6.2.5 Coated steel jackets are manufactured to requirements in Specifications **A336/A336M**, **A653/A653M**, or **A792/A792M** as appropriate. Thickness generally available is 0.016 in. (0.41 mm) nominal. Other thicknesses shall be available as agreed upon between purchaser and seller.

6.2.6 Heavy gauge plastic Type I, Grade 4 jackets are manufactured in plastic films or sheet with materials such as

Polyvinylchloride (PVC) and Polyvinylidenechloride (PVdC) and are available in various thicknesses.

6.3 Type II - Flexible:

6.3.1 Type II, Grade 1 jackets are made of any of a number of different combinations of films, foils, cloths, papers and reinforcements.

6.3.2 Type II, Grade 3 jackets include, but are not limited to, cotton canvas (typically 4, 6, or 8 oz/sq. yd. (0.14, 0.20, or 0.27 kg/sq. m), woven glass fiber yarns, pre-sized glass cloth, and knit, woven, or non-woven synthetic fibers.

6.3.3 Type II, Grade 4 jackets are manufactured from any of a number of different plastic materials, ranging from soft and flexible to hard and rigid. These materials include, but are not limited to: polyvinylchloride, polyvinylfluoride, acrylic, and polyvinylidenechloride. Thicknesses vary with the type of material and must be appropriate to the intended application.

7. Material and Physical Requirements

7.1 Type I Semi-rigid Protective Jackets:

7.1.1 7.1.1 Material properties for semi-rigid jackets are shown in [Table 1](#).

7.2 Type II Flexible Jackets:

7.2.1 Physical property requirements that vary by Class or Grade are shown in [Table 2](#). Common requirements for Type II jackets are specified in this section.

7.2.2 All jackets shall demonstrate a maximum flame spread of 25 and smoke developed of 50 when tested on the service-exposed side for Surface Burning Characteristics (SBC), when tested in accordance with [10.4](#).

7.2.3 Jackets which contain paper or other absorbent materials shall not demonstrate an increase in char length of more than 20 % when tested for flame retardance permanence in accordance with [10.5](#).

7.2.4 All jackets shall not corrode, delaminate nor show permeance higher than the maximum for the class, when tested for elevated temperature and humidity resistance in accordance with [10.8](#).

7.2.5 All jackets shall not exhibit growth of fungus, or mold, when tested for fungi resistance in accordance with [10.7](#).

TABLE 2 Physical Properties for Type II Jackets

TYPE II JACKETS		GRADE 1 Laminated	GRADE 3 Fabric	GRADE 4 Plastic ^A
CLASS A Permeance	perms, max ng PA sm, max	0.01 0.58	...	0.01 0.58
CLASS B Permeance	perms, max ng PA sm, max	0.02 1.15	...	0.02 1.15
CLASS C Permeance	perms, max ng PA sm, max	0.05 2.90	...	0.05 2.90
CLASS D	no permeance requirement
Tensile Strength	lbs/in width, min. N/mm width, min.	30 5.3	30 5.3	7 1.2
Burst Strength, min	psi (kPa)	55 (380)	55 (380)	60 (411)
Dimensional Change	percent max	0.50	0.50	1.0

^A GRADE 2 was deleted in 2010 because the material was no longer produced and was replaced with GRADE 4.

7.2.6 All jackets shall not crack or delaminate when tested for thermal integrity at the maximum service exposure temperature of the jacket in accordance with [10.9](#).

8. Dimensions and Tolerances

8.1 Dimensions for roll or sheeted materials shall be as specified by the purchaser.

8.2 Except for metal jackets, tolerance for roll materials shall be $\pm \frac{1}{8}$ in. (± 3 mm) on width and +5,-0 % on length

8.3 Except for metal jackets, tolerance for roll materials shall be $\pm \frac{1}{8}$ in. (± 3 mm) on length and width.

TABLE 1 Physical Properties for Type I Jackets

TYPE I JACKETS	GRADE 1 Aluminum	GRADE 2 Stainless Steel	GRADE 3 Coated Steel	GRADE 4 Plastic
thickness in. (mm)	0.006–0.050 (0.15–1.27)	0.010–0.032 (0.025–0.81)	0.016 (0.41)	0.010–0.040 (0.25–1.00)
Outside finish				
option 1	smooth	smooth	smooth	
option 2	corrugated	corrugated	corrugated	matte
option 3	embossed	embossed	embossed	gloss
option 4	painted	painted	painted	colored
option 5	laminate	laminate	laminate	
Corrosion Inhibiting Coatings				
option 1	kraft/PE	kraft/PE	kraft/PE	n/a
option 2	ionomer	ionomer	ionomer	
option 3	coating	coating	coating	
Available Metal Alloys of Plastic Polymer Type	3003, 3004, 3105, 3104, 5005, 5052, 1100	301, 302, 304, 316	1010, 1015, 1020	PVC PVdC

8.4 Tolerances for metal jackets shall be as called out in Specifications **B209** or **A240/A240M**, as applicable to material.

9. Workmanship and Finish

9.1 There shall be no defects in materials or workmanship that will adversely affect the required performance of the jacket.

9.2 There shall be no defects that adversely affect the appearance of the jacket.

9.3 There shall be no defects that would affect the ability of the user to process material.

10. Test Methods

10.1 Permeance: Test in accordance with Test Methods **E96/E96M**, (desiccant method at 73°F (23°C) and 50 % RH)

10.2 Tensile Strength:

10.2.1 Test the tensile strength of plastic film jackets (Type II, Grade 2) in accordance with Test Method **D882**, with results reported in pounds per inch width of specimen width (Newtons per millimeter width).

10.2.2 Test the tensile strength of all other jackets in accordance with Test Method **D828**, with results reported in pounds per inch of specimen width (Newtons per millimeter width).

10.2.2.1 Tested specimens shall be 2 in. (51 mm) width with 1 in. (25 mm) between jaws.

10.3 *Burst Strength*—Test in accordance with Test Method **D774/D774M**.

10.4 *Surface Burning Characteristics*—Test in accordance with Test Method **E84**, **D828**.

10.5 *Flame Retardance Permanence*—Test in accordance with TAPPI T461.

10.6 *Dimensional Stability*—Test in accordance with Test Method **D1204**.

10.6.1 Expose the specimens to a temperature of 150 ± 4°F (66 ± 2°C) for 24 h.

10.7 *Fungi Resistance*—Test in accordance with Test Method **C1338**.

10.7.1 Test both sides of laminated products that use dissimilar materials, except metal foil need not be tested.

10.7.2 Test either side of plastic film materials.

10.7.3 Test three specimens of the selected sample and inspect for growth on any of the three.

10.8 *Elevated Temperature and Humidity Resistance*—Test in accordance with Test Method **C1258**. Low-Temperature Resistance.

10.9 *Thermal Integrity*—Test in accordance with Test Method **C1263**.

11. Sampling

11.1 Inspection and qualification shall be in accordance with Practice **C390**. Other provisions for sampling can be agreed upon between the purchaser, seller, and manufacturer.

12. Certification

12.1 When specified in the purchase order or contract, the purchaser shall be furnished certification that samples representing each lot have been either tested or inspected as directed in this practice and the requirements have been met. When specified in the purchase order or contract, a report of the test results shall be furnished.

13. Product Marking

13.1 The packaged jacket shall bear identification including the following information.

13.1.1 Manufacturer,

13.1.2 Product designation,

13.1.3 Roll, sheet, or unit dimensions, and

13.1.4 Lot number or date of manufacture.

13.2 If required by the user, the packaged material shall bear a marking of conformation to this practice, such as: Practice **C921**, Type II, Grade 1, Class A.

13.3 If required by the user, material which has been classified as to surface burning characteristics in accordance with Test Method **E84** by an independent testing laboratory agreed upon by both parties, shall bear the authorized label or marking of that institution.

14. Packaging

14.1 Unless otherwise specified, the material shall be supplied in the manufacturer's standard commercial package.

15. Keywords

15.1 below ambient; flexible; jacket; semi-rigid; thermal insulation

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/