

Standard Specification for Grout Fluidifier for Preplaced-Aggregate Concrete¹

This standard is issued under the fixed designation C937; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the U.S. Department of Defense.

1. Scope*

1.1 This specification covers fluidifier for grout used for preplaced-aggregate (PA) concrete.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 The following precautionary caveat pertains only to the test method portion, Section 8, of this standard: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- C33/C33M Specification for Concrete Aggregates
- C125 Terminology Relating to Concrete and Concrete Aggregates
- C150/C150M Specification for Portland Cement
- C219 Terminology Relating to Hydraulic Cement
- C618 Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete
- C637 Specification for Aggregates for Radiation-Shielding Concrete
- C938 Practice for Proportioning Grout Mixtures for Preplaced-Aggregate Concrete
- C939/C939M Test Method for Flow of Grout for Preplaced-Aggregate Concrete (Flow Cone Method)
- C940 Test Method for Expansion and Bleeding of Freshly Mixed Grouts for Preplaced-Aggregate Concrete in the Laboratory

C941 Test Method for Water Retentivity of Grout Mixtures for Preplaced-Aggregate Concrete in the Laboratory

C942 Test Method for Compressive Strength of Grouts for Preplaced-Aggregate Concrete in the Laboratory

C953 Test Method for Time of Setting of Grouts for Preplaced-Aggregate Concrete in the Laboratory

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this test method, refer to Terminologies C125 and C219.

4. Ordering Information

4.1 The purchaser shall specify the material desired as "grout fluidifier for preplaced-aggregate concrete." The material shall meet the requirements of this specification.

5. Materials

5.1 Grout ingredients shall conform to the following requirements:

5.1.1 Portland cement shall meet the requirements of Specification C150/C150M for the type to be used.

5.1.2 Pozzolan shall meet the requirements of Specification C618.

5.1.3 Fine aggregate shall meet the requirements of Specification C33/C33M except that grading shall conform to Specification C637, Table number 2, Grading 1 for Fine Aggregate.

6. Physical Requirements

6.1 The fluidifier, when tested in grout as specified herein, shall conform to the requirements of Table 1.

7. Sampling

7.1 The test sample of fluidifier shall have a mass of at least 225 g and shall be representative of the material supplied. If feasible, the test sample shall be composited from grab samples taken from not fewer than four packages selected at random.

8. Test Methods

8.1 *Summary of Method*—Physical properties of grout containing fluidifier are determined and compared with corresponding properties of grout made without fluidifier.

¹ This specification is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.41 on Hydraulic Cement Grouts.

Current edition approved Feb. 1, 2016. Published March 2016. Originally approved in 1980. Last previous edition approved in 2010 as C937–10. DOI: 10.1520/C0937-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

TABLE 1 F	Physical	Requirements	for	Grout	with	Fluidifier
-----------	----------	--------------	-----	-------	------	------------

Reduction in mixing water,							
(Test Method C939/C939M)	3						
(,							
Expansion Limits, %:							
Expansion, 3 h after mixing, (Test Method C940) with the fluidifier:							
0.80 or more Alkali Content of Cement, % expressed as Na ₂ O	7 to 14						
0.40 to 0.79 Alkali Content of Cement, % expressed as Na_2O	5 to 12						
0.39 or less Alkali Content of Cement, % expressed as Na_2O	3 to 9						
Bleeding, 3 h after mixing, (Test Method C940), max, % with the fluidifier	2						
Increase in water retentivity (Test Method C941), min, % of control	60						
Initial setting time, min, h (Test Method <mark>C953)</mark>	4						
Final setting time, max, h (Test Method C953)	24						
Compressive strength at 7 days and 28 days, (Test Method C942)							
min, % of control	90						

8.2 *Significance and Use*—The effects of adding fluidifier to a standard grout mixture are determined in order to evaluate its ability to reduce mixing water, prevent early stiffening, hold solid constituents in suspension, produce controlled expansion prior to initial setting, and maintain or increase compressive strength.

8.3 Procedure:

8.3.1 Have all grout materials including mixing water at $23.0 \pm 2.0^{\circ}$ C at the start of the test.

8.3.2 Maintain the laboratory and curing room at 23.0 \pm 2.0°C at all times during testing.

8.3.3 Grout Preparation:

8.3.3.1 Proportion two grout mixtures, one a control mixture without and one a test mixture with the grout fluidifier under consideration, each containing equal parts, by mass, of cementitious material and fine aggregate, with sufficient water to produce a grout efflux time by Test Method C939/C939M of 21 ± 2 s. The cementitious material shall consist of two parts portland cement to one part of pozzolan, by mass.

8.3.3.2 The test mixture shall contain grout fluidifier equal to 1% of the combined mass of portland cement plus pozzolan; unless otherwise recommended by the manufacturer. The control mixture shall contain no fluidifier.

8.3.3.3 The volume of each batch shall be approximately 0.03 m^3 .

8.3.3.4 Mix grout in a mixer of the type shown in Fig. 1 of Practice C938. Dampen the inside of the drum, start the mixer

and charge ingredients within a period of 2 min in the following order: water, fluidifier (if used), pozzolan, cement, and fine aggregate. Mix for 3 to $3^{1/4}$ min.

8.3.3.5 Determine time of efflux by Test Method C939/ C939M. If within acceptable range, proceed with tests to provide data required for the calculations.

8.4 *Calculations*—Calculate the following items:

8.4.1 Reduction in water requirement (R_w) :

$$R_{w} = \frac{\left(W_{c} - W_{t}\right) \times 100}{W_{c}} \tag{1}$$

where:

 R_{w} = reduction in water requirement, %,

 W_c = mass of water required in grout mixture without fluidifier, and

 W_t = mass of water required in grout mixture with fluidifier.

8.4.2 Increase in water retentivity (I_r) :

$$I_r = \frac{\left(R_t - R_c\right) \times 100}{R_c} \tag{2}$$

where:

 I_r = increase in water retentivity, %,

- R_c = time required to extract 60 mL of water from the control sample without fluidifier, s, and
- R_t = time required to extract 60 mL of water from the test sample with fluidifier.

8.5 Determine the expansion, 3 h after mixing, using Test Method C940.

8.6 Determine the bleeding, 3 h after mixing, using Test Method C940.

8.7 Determine the increase in water retentivity using Test Method C941.

8.8 Determine the initial and final time of setting using Test Method C953.

8.9 Determine the compressive strength at 7 days and 28 days using Test Method C942.

9. Report

9.1 *Report*—For each grout mixture, the following test data shall be reported:

9.1.1 Description and source of materials used,

9.1.2 Material proportions by mass,

9.1.3 Average time of grout efflux, s,

9.1.4 Expansion and bleeding, %,

9.1.5 Water retentivity, s,

9.1.6 Initial setting time, h,

9.1.7 Final setting time, h,

9.1.8 Compressive strength at 7 days, MPa, and

9.1.9 Compressive strength at 28 days, MPa.

9.1.10 The following computed values shall also be reported:

9.1.11 Reduction in water requirement, $R_w \%$,

9.1.12 Increase in water retentivity, I_r %, and

9.1.13 Compressive strength at 7 days, expressed as percentage of control specimens, %. 🕼 C937 – 16

10. Rejection

10.1 The purchaser has the right to reject material that fails to conform to the requirements of this specification. Rejection shall be reported to the producer or supplier in writing.

11. Packaging and Marking

11.1 Grout fluidifier shall be packaged in moisture-resistant containers and stored in a dry covered area to prevent deterioration.

11.2 Containers shall be marked to provide at least the following information:

11.2.1 A statement to the effect that the contained material meets the requirements of this specification.

11.2.2 Mass of the contained material.

11.2.3 Basic instructions for use of the material.

11.2.4 Manufacturer's lot number and date of manufacture.

12. Keywords

12.1 efflux time; fluidifier; grout; pre-placed aggregate; water demand; water retentivity

SUMMARY OF CHANGES

Committee C09 has identified the location of selected changes to this specification since the last issue, C937–10, that may impact the use of this specification. (Approved Feb. 1, 2016.)

(1) Removed inch-pound units statement from 1.2 and inchpound units throughout.

(2) Consolidated physical requirements into new Table 1.

(3) Added requirements to test material in accordance with the methods listed in Table 1.

(4) Revised 11.2.2 (formerly 10.2.2) to conform to Subcommittee C09.95 recommendation.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/