

Standard Test Method for Water Retentivity of Grout Mixtures for Preplaced-Aggregate Concrete in the Laboratory¹

This standard is issued under the fixed designation C941; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This test method covers the procedure for determining the water retentivity of freshly mixed hydraulic cement grout mixtures for preplaced-aggregate (PA) concrete.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

2.1 ASTM Standards:²

C125 Terminology Relating to Concrete and Concrete Aggregates

C219 Terminology Relating to Hydraulic Cement E832 Specification for Laboratory Filter Papers

3. Terminology

3.1 Definitions:

3.1.1 For definitions of terms used in this test method, refer to Terminologies C125 and C219.

4. Summary of Test Method

4.1 The time required for the extraction of a standard amount of water by vacuum from a grout specimen is measured.

5. Significance and Use

5.1 This test method measures the ability of a grout mixture to retain its mixing water.

5.2 It is used for qualifying grout fluidifiers to be used in the production of PA concrete.

5.3 It may be used to compare the effects of various admixtures or materials combinations on the water retentivity properties of any cement-water grout.

6. Apparatus

6.1 *Extraction Apparatus*, assembled as in Fig. 1, including the following:

6.1.1 *Funnel*, porcelain Büchner filtering, 111 mm inside diameter at the perforated plate and 500 mL in volume.

6.1.2 *Filter Paper*, Specification E832, Type 2, Class G, disk, 11-cm diameter filter paper.

6.1.3 *Graduated Cylinder*, 250 mL cut down to about 130 mL.

6.1.4 *Vacuum Gage* or manometer graduated in increments of 1 kPa to 100 kPa vacuum.

6.1.5 *Vacuum Pump* or other source of reduced pressure, capable of maintaining a minimum vacuum of 95 kPa on a system having a volume of not less than 1 L.

6.2 *Stop Watch*, having a least reading of not more than 0.2 s.

6.3 *Thermometer*, accurate to 0.5°C, for measuring ambient and grout temperatures.

7. Sampling

7.1 The test sample shall consist of at least 500 mL of freshly mixed grout representative of grout in the mixer. Bring the temperature of the laboratory sample of grout to 23.0 \pm 2.0°C and record the tempature.

7.2 Maintain the ambient temperature of the room in which the test is performed at $23.0 \pm 2^{\circ}$ C and record the temperature.

8. Procedure

8.1 Place a wetted filter paper on the perforated plate of the filtering funnel (see Fig. 1). Keep the top of the filtering funnel level. Apply and maintain a vacuum of at least 95 kPa in the system below the stopcock for the duration of the test. Introduce grout into the funnel until it is filled flush with the top. Open the stopcock between the filtering funnel and the graduated cylinder and at the same time start the stop watch.

¹This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.41 on Hydraulic Cement Grouts.

Current edition approved Feb. 1, 2016. Published April 2016. Originally approved in 1981. Last previous edition approved in 2010 as C941–10. DOI: 10.1520/C0941-16.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.





FIG. 1 Extraction Apparatus

Perform these operations not more than 1 min after taking the grout sample from the mixer.

8.2 When 60 mL of water have been removed from the specimen, stop the stop watch.

8.3 If using this method for acceptance testing of a grout fluidifier, take the test sample within 1 min after completion of 3 to $3\frac{1}{4}$ min mixing.

9. Report

9.1 Report the following information:

9.1.1 Identification of the grout specimen,

9.1.2 Measured time to extract 60 mL of water from the specimen, to the nearest 1 s,

9.1.3 Temperature of the grout sample at the beginning of the test, and

9.1.4 Ambient temperature during the test.

10. Precision and Bias

10.1 *Precision*—The single laboratory, three operators standard deviation has been found to be 11 s.

10.2 *Bias*—No statement on bias can be prepared because there are no standard reference materials.

11. Keywords

11.1 grout fluidifier; preplaced-aggregate concrete; water retentivity

SUMMARY OF CHANGES

Committee C09 has identified the location of selected changes to this specification since the last issue, C941–10, that may impact the use of this specification. (Approved Feb. 1, 2016)

(1) Revised units statement (1.2) and deleted inch-pound units	(3) Added 7.2.
throughout.	(4) Revised 8.1.
(2) Replaced the term "sample" with "specimen" in 4.1, 8.2,	(5) Removed second sentence of 10.1 .
9.1.1, and 9.1.2.	



ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/